2

DOE/PC/90044--5

DE92 010480

HIGH OCTANE ETHERS FROM SYNTHESIS GAS-DERIVED ALCOHOLS

Technical Progress Report for the Period
October-December 1991

Kamil Klier and Richard G. Herman
with
Marie Johansson and Owen C. Feeley

Zettlemoyer Center for Surface Studies
and Department of Chemistry
LEHIGH UNIVERSITY
Bethlehem, PA 18015

January 1992

PREPARED FOR THE

U. S. DEPARTMENT OF ENERGY
PITTSBURGH ENERGY TECHNOLOGY CENTER

Contract No. DE-AC22-90PC90044

MASTER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

FEB 06 1992

HIGH OCTANE ETHERS FROM SYNTHESIS GAS-DERIVED ALCOHOLS

Disclaimer

This report was prepared as an account of work sponsored by the United States Government. Neither the United States nor the United States DOE, nor any of their employees, nor any of their contractors, subcontractors, or their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product or process disclosed, or represents that its use would not infringe privately owned rights.

HIGH OCTANE ETHERS FROM SYNTHESIS GAS-DERIVED ALCOHOLS

OBJECTIVES OF THE RESEARCH

The objective of the proposed research is to synthesize high octane ethers, primarily methyl isobutyl ether (MIBE) and methyl tertiary butyl ether (MTBE), directly from $H_2/CO/CO_2$ coal-derived synthesis gas via alcohol mixtures that are rich in methanol and 2-methyl-1-propanol (isobutanol). The overall scheme involves gasification of coal, purification and shifting of the synthesis gas, higher alcohol synthesis, and direct synthesis of ethers.

The last stage of the synthesis involves direct coupling of synthesis gas-derived methanol and isobutanol that has been demonstrated by us to occur over superacid catalysts to yield methyl isobutyl ether (MIBE) at moderate pressures and a mixture of methanol and isobutene at low pressures. MIBE is an isomer of MTBE and a process is proposed whereby MTBE from the two alcohols is maximized and MIBE is minimized. This will be achieved by the proper choice of reaction conditions, i.e. intermediate pressures, and of inorganic acid catalysts that are stable at temperatures higher than 200°C, at which the carbonium ion reaction coupling of the two alcohols to MTBE is more effective than the oxonium ion or ester reaction coupling to MIBE.

Both organic and inorganic catalysts will be investigated, and the better catalysts of these classes will be subjected to long term performance studies. The long term performance studies of the combined process will extend to 1000 hr and detailed analytical data for all products will be provided. The project is divided into the following three tasks:

- Task 1. Synthesis of High Octane Ethers from Alcohol Mixtures Containing Predominantly Methanol and 2-Methyl-1-Propanol over Superacid Resins

Task 2. Inorganic Catalysts for the Synthesis of High Octane Ethers from Alcohols

Task 3. Long Term Performance and Reaction Engineering for Scale-Up of the Alcohols-to-Ethers Process

The expected result of the proposed research is a novel process for producing ethers, in particular MTBE, in which all five carbons of the unsymmetric C_1-O-C_4 ethers originate from coal-derived synthesis gas.

HIGH OCTANE ETHERS FROM SYNTHESIS GAS-DERIVED ALCOHOLS

SUMMARY OF TECHNICAL PROGRESS

The activity and selectivity properties of five inorganic solid acid catalysts, H-mordenite, montmorillonite, silica-alumina, sulfate-modified zirconia and γ -alumina, for the production of MTBE from methanol and isobutanol were evaluated. A standard test was utilized using 5.0 g of catalyst at 90°C and a total pressure of 1 atm. The flow rate of each alcohol was 1.72 mol/kg cat/hr, and the molar ratio of methanol to isobutanol was 1:1. The flow rate of nitrogen + helium was 16 mol/kg cat/hr. In general, these inorganic catalyst were less active than their organic counterparts at 90°C, and it was found necessary to study their activity and selectivity behavior at higher temperature, i.e. 90-175°C. H-Mordenite was able to selectively dehydrate methanol to form DME in the presence of isobutanol at temperatures above 90°C, whereas sulfate-modified zirconia selectively dehydrated isobutanol to form isobutene under the same conditions. It was found to be essential for the zirconia to be sulfated, since a test with unsulfated zirconia showed no activity. The general trend for DME yield was H-mordenite $\gg$ montmorillonite $\approx$ $\text{SiO}_2/\text{Al}_2\text{O}_3 \approx \text{ZrO}_2/\text{SO}_4^{2-} \gg \gamma\text{-Al}_2\text{O}_3$. Formation of isobutene followed the order $\text{ZrO}_2/\text{SO}_4^{2-} > \text{SiO}_2/\text{Al}_2\text{O}_3 > \text{montmorillonite} \gg \text{H-mordenite} \approx \gamma\text{-Al}_2\text{O}_3$.

Nafion-H MS, the only organic catalyst studied that is stable at the temperatures used for the inorganic catalysts, was tested at higher temperature for comparison with the inorganic catalysts. Major products at 90 and 125°C were MIBE and DME. At higher temperature, the catalyst was quite active toward the formation of oligomerization and isomerization products. A sample of potassium exchanged Nafion was found to be inactive for any reaction.

TECHNICAL PROGRESS

A. Standardized Test for Direct Coupling of Alcohols to Ethers

Introduction

A standard test for ether formation from methanol and isobutanol was introduced in the last quarterly report (1). A new series of tests has been conducted using inorganic catalysts. To allow for direct comparisons the same operating conditions that were used for the organic catalysts were also used to study these inorganic catalysts. In addition, their excellent thermal stabilities allowed the use of higher temperatures for reaction. The following catalysts have been evaluated:

H-Mordenite	(Norton Zeolon-900)
Montmorillonite K-10	(Aldrich)
Silica-Alumina	(Davison Grade 980)
Sulfate modified zirconia	(Prepared in house)
γ -alumina	(Fisher)

These catalysts were chosen for their strong acidity, ability to be used at high temperatures, and ease of regenerability. Mordenite, montmorillonite, silica-alumina, and γ -alumina have long histories of use in the petroleum industry, e.g. as fluidized catalytic cracking (FCC) and/or isomerization and reforming catalysts. Sulfate-modified zirconia has received recent attention as a possible isomerization or alkylation catalyst owing to its very strong acidity that has been characterized as a superacid (2, 3). The sulfating step has been claimed to stabilize the surface area and the tetragonal phase of zirconia, as well as forming strong Lewis and Brønsted acid sites (4). The surface chemistry and the nature of the active sites of $\text{ZrO}_2/\text{SO}_4^{2-}$ are believed to be as follows:

Although after calcination all of the inorganic catalysts possess both Lewis and Brønsted acidity, during the reactions of methanol and isobutanol the presence of the main product water will convert Lewis acid sites into Brønsted acid sites:

Experimental

As mentioned above, all but the sulfate-modified zirconia are commercially available. H-mordenite and silica-alumina were calcined at 400°C for 4 hr. γ -alumina was calcined at 450°C to ensure the presence of the γ -form of alumina. Montmorillonite was used as received with no further treatment.

Sulfate-modified zirconia ($\text{ZrO}_2/\text{SO}_4^{2-}$) was prepared according to the work of Hino and Atara (3). Zirconyl chloride octahydrate ($\text{ZrOCl}_2 \cdot 8\text{H}_2\text{O}$) was hydrolyzed with aqueous ammonia to precipitate zirconium hydroxide ($\text{Zr}(\text{OH})_4$). The zirconium hydroxide was washed with distilled water until free of chloride ions as determined by the silver nitrate test. This $\text{Zr}(\text{OH})_4$ was then dried overnight at 100°C. A 13 g dried portion of $\text{Zr}(\text{OH})_4$ was then placed on a folded filter paper and 200 ml of 1 N (0.5 M) sulfuric acid was poured over it. The sulfate modified zirconia was dried at 110°C and then calcined in air at 620°C

for 3 hr. This procedure is reported to give a superacidic catalyst ($H_0 < -16.04$) with a surface area of about $85 \text{ m}^2/\text{g}$. Zirconia (ZrO_2) was prepared in the same manner excluding the sulfating step, i.e. $\text{Zr}(\text{OH})_4$ was dried at 110°C then calcined at 620°C for 3 hr.

Nafion-H was exchanged to its potassium form, designated Nafion-K. To achieve the ion exchange 10 g of Nafion-H was immersed in 75 ml of 1 M potassium nitrate (KNO_3) and stirred for approximately 45 min. The solution was strongly acidic due to the exchange of H^+ for K^+ . A new portion of potassium nitrate was added after the previous was decanted and the catalyst was washed with distilled water. The procedure was repeated until full exchange was reached, as determined by testing the pH of the exchange solution. Four portions of KNO_3 were needed for total exchange of the Nafion-H. Amberlyst-15 was exchanged in the same manner, except ten portions of KNO_3 was required. The higher exchange capacity per weight, expressed in meq/g, of Amberlyst-15 vs. Nafion-H explains this requirement. Finally, the Nafion-K and K exchanged Amberlyst-15 were washed in distilled water and allowed to dry overnight at 90°C .

Operating conditions

The following standard test conditions were used to study the inorganic catalysts:

Temperature	90, 125, 150, 175°C
Pressure	1 atm
Methanol feed	$1.72 \text{ mol/kg catalyst/hr}$
Isobutanol feed	$1.72 \text{ mol/kg catalyst/hr}$
He+N_2 flow	$16.0 \text{ mol/kg catalyst/hr}$
Catalyst weight	5.0 g

The catalysts were diluted with 0.5 mm Pyrex beads to a total volume of 20 ml, which was centered in the reactor between two glasswool "plugs". The rest of the reactor volume was filled with 3 mm Pyrex beads. The reactor was brought to the reaction temperature in a flow of 80% He and 20% N_2 , then the alcohol mixture was delivered by pump to the reactor. Steady state conversions of methanol and

isobutanol were obtained within the first two hours of reaction.

Results

Catalytic Activity. The space time yields of products obtained under steady state conditions over the active inorganic catalysts are given in Table I. The entry "Butenes" includes iso-, 1-, and 2-butene with isobutene predominating (greater than 65% of the butene content).

TABLE I
Yields over Inorganic Catalysts
(mol/kg cat/hr)

	T _{Reaction}	DME	Butenes	MIBE	MTBE	C8 ether
H-Mordenite	90°C	0.060	-----	-----	-----	-----
	125°C	0.6599	-----	-----	-----	-----
	150°C	0.83	0.068	-----	-----	0.004
ZrO ₂ /SO ₄ ²⁻	90°C	-----	-----	0.003	-----	-----
	125°C	0.006	0.067	0.02	0.003	0.008
	150°C	0.027	0.696	0.068	0.009	0.017
	175°C	0.103	1.29	0.049	0.007	-----
Silica-Alumina	90°C	-----	-----	-----	-----	-----
	125°C	0.007	0.028	0.011	0.001	0.003
	150°C	0.021	0.225	0.032	0.005	0.014
	175°C	0.039	0.943	0.049	0.007	0.016
Montmorillonite	90°C	-----	-----	-----	-----	-----
	125°C	0.008	0.008	0.008	-----	0.004
	150°C	0.019	0.071	0.019	0.004	0.014
	175°C	0.034	0.378	0.029	0.014	0.031

The conversions of methanol and isobutanol, over the inorganic catalysts, are shown in Figure 1 and Figure 2, respectively, as a function of reaction temperature. The use of standard conditions at 90°C showed very low conversion of both methanol and isobutanol for all inorganic catalysts. Only H-mordenite showed significant activity at this temperature, reaching ≈10% conversion of methanol. Increasing the temperature to 125°C resulted in a large increase in methanol conversion over H-mordenite and only a minor change for the other catalysts. Further increase in temperature yielded ≈90% conversion of methanol

FIGURE 1

Conversion of methanol

H-Mord=H-Mordenite
Montmorill=montmorillonite

FIGURE 2

Conversion of i-Butanol

H-Mord=H-Mordenite
Montmorill=Montmorillonite

over H-mordenite, while the other catalysts still exhibited below 20% methanol conversion. At 150°C, the sulfate-modified zirconia showed 50% conversion of isobutanol, and this increased to 95% at 175°C. Silica-alumina and montmorillonite showed 63% and 30% conversion of isobutanol, respectively. γ -Alumina showed no significant conversion of isobutanol or methanol in the temperature range studied.

Product Selectivity. Sulfate-modified zirconia produced only methyl isobutyl ether at 90°C, but the conversion was very low (Figure 3). However, at higher temperature isobutanol was selectively dehydrated to isobutene in the presence of methanol. Non-sulfated zirconia was found to be totally inactive for the dehydration of either methanol or isobutanol over the temperature interval tested (90-175°C). H-Mordenite showed the opposite pattern by selectively dehydrating methanol to dimethylether (DME) at both 90 and 125°C (Figure 4). Only minor dehydration of isobutanol was seen at 150°C with nearly total conversion of methanol. Montmorillonite showed the highest relative selectivity to MTBE vs MIBE at 125°C (Figure 5), but at higher temperature butenes are the dominant product. Silica-alumina was also mostly selective to butenes (Figure 6). Reaction over γ -alumina resulted in only one product, DME, at 175°C, but the conversion was only a few percent (Figure 7).

Conclusions

The patterns that emerge are the following:

- (1) H-mordenite is a selective catalyst for dehydration of methanol to DME. Isobutanol is not converted to any ethers or dehydrated significantly to isobutene over H-mordenite under the conditions used. Evidently the pore size or shape of H-mordenite restricts reactions of isobutanol; even though the isobutanol molecule is small enough to enter the larger channel pores of mordenite, its

FIGURE 3

Selectivity of $\text{ZrO}_2/\text{H}_2\text{SO}_4$

Mol % Product

FIGURE 4
Selectivity of Mordenite
Mol % Product

FIGURE 5

Selectivity of Montmorillonite

Mol % Product

FIGURE 6

Selectivity of SiO₂-Al₂O₃

Mol % product

FIGURE 7
Selectivity of Alumina
Mol % Product

conversion is suppressed by one or all of the following three classic mechanisms of zeolite shape selectivity: (a) inaccessibility of acid centers that possibly reside primarily in the narrow side channels of the mordenite structure; this type of size exclusion in alcohol dehydration was first studied by Weisz et al. (5), and it should be noted that acid sites in mordenite are accessible to molecules as large as 1-methyl-2-ethylbenzene at higher temperatures (6) (b) retardation of isobutanol transport by preferential diffusion of methanol, e.g. diffusive selectivity as studied by Chen and Weisz (7) (c) size restrictions on the transition states involving isobutanol, isobutyl esters, and isobutyl oxonium ions. Csicsery first proposed the concept of restricted transition state selectivity in zeolites (6).

- (ii) Sulfate-modified zirconia is an efficient and highly selective catalyst for the dehydration of isobutanol to isobutene, with methanol dehydration to DME suppressed. The reasons for this selectivity pattern have not been established, but it is tentatively suggested that isobutanol is more strongly bonded than methanol to the sulfate groups on the zirconia surface so that methanol activation is suppressed. The relative bonding strength of isobutanol and methanol to the sulfate-modified zirconia would have to be more markedly different than that on Nafion H because DME and MIBE are co-products with isobutene over Nafion H but not over the sulfate-modified zirconia.
- (iii) The overall order of activities for the dehydration reactions over the inorganic acids tested is:

$$\text{ZrO}_2/\text{SO}_4^{2-} > \text{H-mordenite} > \text{SiO}_2/\text{Al}_2\text{O}_3 > \text{H-Montmorillonite} \gg \gamma\text{-Al}_2\text{O}_3.$$
- (iv) The inorganic catalysts are generally less active than the organic

polymeric catalysts at 90°C, except for the H-mordenite catalyst that is active and selective for methanol dehydration to DME. Higher temperatures are needed for significant alcohol dehydration with inorganic catalysts. In general, the organic polymeric catalysts are unstable at these higher temperatures.

The yields of DME observed for the inorganic catalysts followed the order H-mordenite $\gg$ montmorillonite $\approx$ $\text{SiO}_2/\text{Al}_2\text{O}_3 \approx \text{ZrO}_2/\text{SO}_4^{2-} \gg \gamma\text{-Al}_2\text{O}_3$. The relative order of yields of isobutene production followed the order $\text{ZrO}_2/\text{SO}_4^{2-} > \text{SiO}_2/\text{Al}_2\text{O}_3 > \text{montmorillonite} \gg \text{H-mordenite} \approx \gamma\text{-Al}_2\text{O}_3$. Probably, the most important finding of the inorganic catalyst testing is the remarkable selectivity properties of H-mordenite and $\text{ZrO}_2/\text{SO}_4^{2-}$. The ability of these catalysts to selectively dehydrate either methanol or isobutanol in a mixture containing both alcohols was unexpected. Even at near total conversion of one of the alcohols, the other alcohol remains essentially unconverted. The use of $\text{ZrO}_2/\text{SO}_4^{2-}$ may lead to a new process where methanol/isobutanol streams, the major products of higher alcohol synthesis over alkali/Cu/ZnO catalysts, can be selectively dehydrated to methanol/isobutene streams that are the current feedstocks for industrial MTBE production.

B. Extended Standard Test for Nafion-H MS

In the previous report (1), Nafion-H MS was tested under standard conditions (90°C, 1 atm) but not at higher temperatures. Conversion of both methanol and isobutanol was low (1.4%). For comparison to both organic resins and the inorganic catalysts, the experiment was repeated under standard conditions and was extended to higher temperature. Table II shows the activities of Nafion-H at 90, 125, 150, and 175°C.

Table II

Activities of Nafion-H MS for MeOH + i-BuOH Standard Test

Temperature (°C)	Methanol Conversion Percent	Isobutanol Conversion Percent
90	1.4	1.5
125	28.2	31.6
150	60.3	99.6
175	59.3	98.2

Conversion at 90°C corresponds well with previous results (1). Upon increasing the temperature to 125°C conversion was increased to ≈30% for both methanol and isobutanol with methyl isobutylether (MIBE) and DME as major products. A few minor peaks were not identified at this temperature. At higher temperatures (150 and 175°C), methanol conversion, predominantly to DME with MIBE becoming a very minor product, increased to ≈60%, whereas isobutanol was almost completely converted, predominantly to isobutene. It must be noted that at 150 and 175°C a large number of small unidentified peaks were seen. Upon unloading the catalyst from the reactor, the previously light yellow catalyst had changed color to black. It had a greasy "film" over it and smelled "oily". Apparently, due to its very strong acidity, Nafion-H at 150 °C and above is able to catalyze extensive isomerization and oligomerization.

In contrast to the results in Table II, the portion of Nafion-H MS that was exchanged with KNO₃, Nafion-K, showed no activity at all. This indicates that a catalyst possessing appreciable acidity is necessary for the reactions discussed above. This Nafion-K also retained its light yellow color even after being subjected to reaction conditions at 175°C, indicating the color change of Nafion-H was not due to thermal decomposition, but to hydrocarbonaceous deposits.

C. Catalyst Characterization using X-Ray Photoelectron Spectroscopy (XPS)

XPS measurement of Amberlyst-15, Nafion-H and sulfated zirconia have been conducted. XPS is a surface method reaching approximately 100 Å into the sample. It can be used to investigate the state of atomic species, as well as their relative concentration.

Experimental

Amberlyst-15 and potassium exchanged Amberlyst-15 were ground to a fine powder that was placed on a piece of silver foil mounted on a sample holder. Sulfated zirconia was used as prepared and placed on silver foil as described above. Neither Nafion-H nor potassium exchanged Nafion-H could be prepared using this technique. Instead, the resins were placed on a piece of aluminum foil covered with silver paint and pressed under high pressure for 15 min to give a smooth continuous surface to analyze.

Results

Amberlyst-15 is a poly(styrene-divinylbenzene) polymer that has been sulfonated with sulfuric acid. The only oxygen atoms present in this copolymer are in the sulfonyl group. XPS data showed that indeed the ratio of oxygen to sulfur was 3:1. The potassium exchanged Amberlyst-15 showed a ratio of sulfur to potassium of 1:1, which confirmed that the resin was 100% exchanged and no acid sites were present. Nafion-H has additional oxygen atoms in ether linkages to the fluorocarbon backbone, and the ratio of oxygen to sulfur increased to about 7:1. Potassium exchanged Nafion-H has no catalytic activity as mentioned earlier in this report. The lack of acid sites was confirmed by a ratio of sulfur to potassium of 1:1. It was also determined that the different oxygen atoms in Nafion-H can be distinguished from one another by a slight shift in binding energy. Sulfated zirconia has at least two different "types" of oxygen, which is demonstrated in Figure 8 as a shoulder on the main oxygen peak. The

FIGURE 8

XPS of oxygen in sulfated zirconia

Pass energy
150 eV

Slit width
1.1 mm

Energy step
0.05 eV

Det. height
70 %

Lens mode
TRANSMISSION

X-ray power
1.6 kW

Rec. time
00:12:56

Binding Energy [eV]

total number of oxygen atoms is about six times the number of sulfur atoms on the surface. The two maxima within the oxygen peak are about 2 eV apart; although this peak is very broad this follows the pattern described by Arata (3), where the shoulder refers to oxygen in the sulfate group and the peak at lower binding energy corresponds to oxygen on zirconia. Sulfur was reported to appear at 169.3 eV and that is approximately where the sulfur peak in this sample was observed (Figure 9). This binding energy for sulfur corresponds very well with the binding energy for sulfur in zirconium sulfate ($\text{Zr}(\text{SO}_4)_2$) obtained by Arata (8). Figure 10 show the spectrum of the zirconium $3d_{3/2}$ and $3d_{5/2}$ spinstates. The peaks are separated by approximately 2 eV which also follows the results Arata presented. These results confirm that the utilized preparation procedure indeed gave sulfated zirconia. The peaks in the spectra presented are not very well resolved due to differential charging of the sample. This phenomenon will always occur when XPS is performed on non-conducting materials, and charge compensation techniques need to be applied.

References

1. Klier, K., Herman, R. G., Johansson, M., Feeley, O. C., Bogar, S., Lawson, E., and Kieke, M., Quarterly Technical Progress Report DOE/PC/90044-4 (November 1991).
2. Hino, M.; Kobayashi, S.; Arata, K., *J. Am. Chem. Soc.*, 101 (1979) 6439.
3. Hino, M. and Atara, K., *J. Chem. Soc., Chem. Comm.*, (1980) 851.
4. Yamaguchi, T.; Tanabe, K.; Kung, Y.C., *Materials Chem. Phys.*, 16 (1986) 67.
5. Weisz, P.B.; Frilette, V.J.; Maatman, R.W.; and Mower, E.B., *J. Catal.*, 1, (1962) 307.
6. Csicsery, S.M., *J. Catal.*, 19, (1970) 394.
7. Chen, N.Y.; Mazuik, J.; Schwartz, A.B.; and Weisz, P.B., *Oil & Gas Journal*, (Nov. 18, 1968) 154.
8. Arata, K., in "Advances in Catalysis", Academic Press, Inc., San Diego, CA, 37 (1990) 165.

FIGURE 9

XPS of sulfur in sulfated zirconia

Pass energy
150 eV

Slit width
1.1 mm

Energy step
0.05 eV

Det. height
70 %

Lens mode
TRANSMISSION

X-ray power
1.6 kW

Rec. time
00:35:24

Binding Energy [eV]

FIGURE 10

XPS of zirconium in sulfated zirconia

END

**DATE
FILMED
5106192**