TECHNICAL REPORT

September 1, 1991 through November 30, 1991

Project Title:

INVESTIGATION OF A SULFUR REDUCTION TECHNIQUE
FOR MILD GASIFICATION CHAR

DE-FG22-91PC 91334

Principal Investigator:

Richard A. Knight, Institute of Gas Technology

Project Monitor:

Frank Honea, CRSC

ABSTRACT

The object of this program is to investigate the desulfurization of mild gasification char using hydrogen/methane mixtures in a laboratory-scale experimental study. Mild gasification is a coal conversion technique which produces a slate of solid, liquid, and gaseous co-products. Char is the major co-product, comprising about 60% of the yield from dry coal. Form coke for steelmaking and foundries presents the best potential high-value markets for chars produced from eastern bituminous coals. The value of form coke increases as sulfur content decreases; conventional metallurgical cokes generally contain about 1 wt% sulfur. Mild gasification char from high-sulfur Illinois coals must be upgraded to meet these criteria. One method that can accomplish this is desulfurization with reducing gases, which can be derived from the mild gasification co-product gases. Because form coke has a market value as high as \$200/ton, it can accommodate desulfurization costs and still be an economically attractive product. The desulfurization can be performed either on the granular char exiting the mild gasifier or on formed briquettes.

In the first year of the two-year program, char is being treated with mixtures of H_2 and CH_4 at temperatures of 1100° to 1550°F and pressures of 50 to 100 psig. The effects of temperature, pressure, residence time, gas velocity, and gas composition on sulfur removal and carbon gasification are being determined. The batch experiments are being performed in a nominal 2-inch-ID stainless-steel, batch, fluidized-bed reactor. The char to be desulfurized was produced by the IGT mild gasification process research unit (PRU) in a recently completed DOE/METC-sponsored technology development program. The parent coal was Illinois No. 6 from a preparation plant, and the char from the selected test contains 4.58 wt% sulfur.

In the second year, the study will be extended to include form coke briquettes made from mild gasification char. The data obtained from both years of the program will be used to design a desulfurization process to be integrated with the IGT mild gasification process.

In the first quarter, we have obtained and prepared a char for the desulfurization tests. Ultimate and proximate analyses were performed on this char, and its pore size distribution and surface area were determined. Also this quarter, the fluidized-bed reactor system was constructed and equipped with high pressure mass flow controllers and a high pressure sintered metal filter to remove fines from the effluent gas stream.

MASTER

This project is funded by the U. S. Department of Energy (METC) and by the Illinois Department of Energy and Natural Resources as part of their cost-shared program.

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

EXECUTIVE SUMMARY

The object of this program is to investigate the desulfurization of mild gasification char using hydrogen/methane mixtures in a laboratory-scale experimental study. Mild gasification is a coal conversion technique which produces a slate of solid, liquid, and gaseous co-products at conditions of low severity (1000° to 1300°F, <50 psig). A mild gasification process which uses a coaxial fluidized-bed/entrained-bed reactor system has been developed by IGT under U.S. DOE sponsorship (DOE Contract DE-AC21-87MC24266). Char is the major co-product, comprising about 60% to 70% of the yield from dry coal.

One major target use for mild gasification char is metallurgical form coke. Form coke for blast furnaces and foundries has a higher market value at low sulfur content. Conventional cokes generally contain about 1 wt% sulfur. Mild gasification chars from high-sulfur Illinois coals contain up to 3 wt% sulfur and must therefore be upgraded. One method that can accomplish this is desulfurization with reducing gases, which can be derived from the mild gasification co-product gases. The desulfurization can be performed either on the char particles exiting the mild gasifier or on formed briquettes made by a binderless technique, wherein hot (1100°F) char is blended with additional caking coal to provide an *in-situ* binder.

The sulfur content of char from mild gasification is largely dependent on the sulfur content of the parent coal. In the DOE-sponsored study, the parent coal, a conventionally washed Illinois coal, contained 3 to 5 wt% sulfur. The char sulfur content from a series of temperature-dependency tests ranged from 2.1 wt% to 2.8 wt%, which was 27% to 46% lower than that of the coal. It is estimated that desulfurization of the char by an additional 50% or more would be required to yield an attractive product for form coke production.

Research performed in the 1970's at IGT, U.S. Steel, Garrett Research, and elsewhere has shown that coal chars from various types of gasifiers can be effectively desulfurized by exposure to reducing gases at temperatures from 1100°F to 1500°F. Mixtures of hydrogen and methane are effective for this purpose. Although pure hydrogen is much more effective than pure methane, H₂/CH₄ mixtures are also more effective than pure methane, and the presence of methane inhibits carbon hydrogasification, thus allowing desulfurization to proceed with minimal carbon losses, compared to treatment with pure hydrogen. Also, the use of a process-derived gas mixture avoids the separation costs associated with the use of pure H₂. The product gas from mild gasification, on an inert-free basis, contains 20 to 28 vol% CH₄ and 28 to 50% H₂, depending primarily on temperature. Estimates show that the amount of H₂ gas produced in mild gasification is two to three times the amount required to stoichiometrically react with all of the sulfur in the char.

The ultimate goal of the project is to develop a method for desulfurization of mild gasification char, using process-derived gases. The objectives of the 24-month program are to conduct laboratory studies that assess the technical viability of the process concept, develop a preliminary process flow scheme, and make recommendations for integration of the desulfurization step into an ongoing mild gasification development program.

In the first year, granular char from the IGT mild gasification PRU is being treated with mixtures of H_2 and CH_4 at the following ranges of conditions:

- Temperatures of 1100° to 1550°F
- Pressures of 50 to 100 psig
- Residence times of 30 to 60 minutes
- Reducing gas H_2 content of 50 to 90 vol%

The batch experiments are being performed in a nominal 2-inch-ID stainless-steel, batch, fluidized-bed reactor. The char being desulfurized was produced by the IGT mild gasification process research unit (PRU) in a previous DOE/METC-sponsored technology development program. The parent coal was Illinois No. 6 coal from Peabody Coal Company's Randolph preparation plant, and the char contains 4.58 wt% sulfur. The effects of temperature, pressure, residence time, gas velocity, and gas composition on sulfur removal and carbon gasification are being determined.

In the second year, the study will be extended to include form coke briquettes made from the same mild gasification char. The briquettes will be made by a binderless technique, wherein hot (1100°F) char is blended with additional parent coal to provide an *in-situ* binder. A parametric study similar to that conducted in the first year will be performed on the "green" (uncalcined) briquettes, followed by calcination of the briquettes at 1800°F, which is required to cure the binder and develop optimal properties. In addition to the effects of process parameters on sulfur removal and carbon gasification, their effects on the strength, density, tumbler-test stability, and reactivity of the resultant form coke, which are important to their use in blast furnaces, will be investigated. The data obtained from both years of the program will be used to design a desulfurization process to be integrated with the IGT mild gasification process.

In the first quarter, we have obtained and prepared a char for the desulfurization tests. Ultimate and proximate analyses were performed on this char, and its pore size distribution and surface area were determined. Also this quarter, the fluidized-bed reactor system was constructed and equipped with high pressure mass flow controllers and a high pressure sintered metal filter to remove fines from the effluent gas stream.

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

OBJECTIVES

The ultimate goal of this project is to develop a method for desulfurization of mild gasification char, using process-derived gases. The overall objectives of the 24-month program are to conduct laboratory studies that assess the technical viability of the process concept, develop a preliminary process flow scheme, and make recommendations for integration of the desulfurization step into an ongoing mild gasification development program.

INTRODUCTION AND BACKGROUND

Mild gasification is an advanced coal carbonization process that emphasizes simple reactor and process design, low-severity processing conditions, and the use of advanced technical knowledge to bring a slate of value-added co-products (char, fuel gas, and oils/tars) to the marketplace in the next five years. The U.S. DOE has been supporting the development of this technology since 1987, and a project team consisting of Peabody Holding Company, Bechtel National, and IGT has completed a literature and market survey and technology development program including the design, construction and operation of a 100-lb/h PRU and the design of a 24-ton/day process development unit (PDU).^{1,2,3,4} The mild gasification reactor consists of a coaxial fluidized-bed/entrained-bed vessel which can process all types of coals. IGT has completed 47 mild gasification tests on four coals in the PRU, at temperatures ranging from 1034° to 1390°F.

-
- ¹ Knight, R.A., J. Gissy, M. Onischak, S.P. Babu, J.M. Wootten, and R.G. Duthie, "Development of An Advanced, Continuous Mild Gasification Process for the Production of Co-Products", Task 2 Topical Report to DOE/METC, Contract No. DE-AC21-87MC24266, (July 1990).
 - ² Knight, R.A., J. Gissy, M. Onischak, R.H. Carty, S.P. Babu, J.M. Wootten, and R.G. Duthie, "Development of An Advanced, Continuous Mild Gasification Process for the Production of Co-Products", Task 4 Topical Report to DOE/METC, Contract No. DE-AC21-87MC24266, (December 1990).
 - ³ Wootten, J.M., M. Nawaz, R.G. Duthie, R.A. Knight, M. Onischak, S.P. Babu, and W.G. Bair, "Development of An Advanced, Continuous Mild Gasification Process for the Production of Co-Products", Task 1 Topical Report to DOE/METC, Contract No. DE-AC21-87MC24266, (August 1988).
 - ⁴ Carty, R.H., M. Onischak, S.P. Babu, R.A. Knight, J.M. Wootten, and R.G. Duthie, "Development of An Advanced, Continuous Mild Gasification Process for the Production of Co-Products", Task 3 Topical Report to DOE/METC, Contract No. DE-AC21-87MC24266, (December 1990).

Figure 1 shows the variation of char sulfur content with mild gasification temperature from a series of PRU tests using Illinois No. 6 coal from Peabody's Randolph preparation plant. The parent coal, containing 3 to 5 wt% sulfur, is typical of a conventionally washed Illinois coal. As shown, the char sulfur content, ranging from 2.1 wt% to 2.8 wt%, is 27% to 46% lower than that of the coal. Expressed on a Btu basis, this represents a reduction of 20% to 38%.

For form coke made from mild gasification char, the guidelines on sulfur content are not strictly defined. In the blast furnace, coke acts as both a fuel and as a reductant for iron ore. Limestone is added to the furnace charge to bind the sulfur, and the amount of limestone added directly affects the economics of the process by limiting the steel output, consuming sensible heat, and adding material cost for the limestone. For these reasons, in this project, the target sulfur limit of 1.0 wt% for the form coke has been selected.

In the 1970's, research on coal and char desulfurization increased along with synfuels research in general. U.S. Steel Corporation, with ERDA support, developed the Clean Coke process, in which desulfurization of the char with recycled product gas played an important role.⁵ The recycle gas used for fluidization in the PDU was 71% CH₄, 13% C₂H₆, 10% CO, 2% H₂, and 4% higher hydrocarbons. At 1400°F, char was reduced in sulfur content from 1.7 wt% to 0.3 wt% in 180 min residence time, which is an 82% reduction. The H₂S concentration in the recycle gas was identified as a critical factor in achieving effective desulfurization, as shown by the finding that increasing the volumetric H₂S concentration in the recycle gas from 50 ppm to 500 ppm increased the char sulfur content from 0.21 wt% to 0.71 wt%. An associated study of char-sulfur chemistry⁶ found that, with an Illinois No. 6 hydro-gasification char, desulfurization with reducing gases occurred in two steps: an initial rapid-rate step associated with reduction of FeS₂ to FeS, and a slower secondary step where FeS is reduced to elemental iron. The study determined that, while H₂ is more effective than CH₄ for char desulfurization, mixtures of CH₄ and H₂ were also effective and, furthermore, the presence of methane inhibited carbon gasification at longer residence times while allowing desulfurization to continue.

The same study also found that, for a given char, the relationship between sulfur removal and carbon loss through gasification in the first 15-30 minutes follows a monotonic curve, regardless of the temperature, pressure, or gas atmosphere used. Figure 2 shows this relationship for an Illinois No. 6 char prepared at 1112°F. Based on this relationship, a 50% to 65% sulfur reduction, such as may be required for mild gasification char to meet the

⁵ Boodman, N.S., T. F. Johnson, and K.C. Krupinski, "Fluid-Bed Carbonization/Desulfurization of Illinois Coal by the Clean Coke Process: PDU Studies", ACS Div. of Fuel Chem. Prepr. 22:2, 28-44 (1977).

⁶ Kor, G.J.W., "Desulfurization and Sulfidation of Coal and Char", ACS Div. of Fuel Chem. Prepr. 22:2, 1-27 (1977)

Figure 1. SULFUR CONTENT OF MILD GASIFICATION CHAR AS A FUNCTION OF TEMPERATURE

selected form coke requirement of 1 wt% sulfur, could be achieved with an accompanying 10% to 13% carbon conversion.

In similar work, IGT studied the hydrodesulfurization of four bituminous coals at 1300° to 1500°F for 30 min in hydrogen.⁷ A reduction of 74% in the lb SO₂/MMBtu was achieved with Illinois No. 6 coal. This study emphasized the importance of maintaining a low H₂S concentration in the treatment gas, suggesting the use of a solid sulfur sorbent such as calcium oxide. The investigators also concluded that a mild pre-oxidation of the coal substantially increases subsequent sulfur removal by hydrodesulfurization. However, a more recent CRSC-funded study⁸ found that this interaction was dependent on the coal tested and the type of physical cleaning to which the coal had been subjected.

⁷ Fleming, D.K., R.D. Smith, and M.R.Y. Aquino, "Hydrodesulfurization of Coals", ACS Div. of Fuel Chem. Prepr. 22:2, 45-49 (1977)

⁸ Stephenson, M.D., A.D. Williams, M. Rostam-Abadi, and C.W. Kruse, "The Effect of Mild Oxidation on the Thermal Desulfurization and Hydrodesulfurization of two Illinois Bituminous Coals in a Fluidized-Bed Reactor", ACS Div. of Fuel Chem. Prepr. 33:4, 960-967 (1988)

Figure 2. GENERAL RELATIONSHIP BETWEEN INITIAL LOSS OF SULFUR AND CARBON FOR ILLINOIS NO. 6 CHAR PREPARED AT 1112°F

Research on char hydrodesulfurization was also done by Garrett Research and Development (later Occidental Petroleum). A 1976 paper⁹ discusses the effectiveness of acid-washing of char to remove Ca and Fe compounds which appear to contribute to the severity of H₂S inhibition. The hydrogen requirement with an acid-washed char was 12% of that required for an untreated char.

This study is evaluating the technical feasibility of desulfurizing mild gasification char and/or form coke briquettes with process-derived reducing gases. The unique aspects of this research are: the application of this technique to mild gasification char and/or briquettes made therefrom, and the integration of the technique with form coking. In the IGT fluidized-bed mild gasification process, bituminous coal is not pre-oxidized to prevent caking as has been done in other processes.^{5,7} The intrinsic caking tendency of the coal is instead overcome by a systematic control over the relationship of the

⁹ Robinson, L., "Hydrodesulphurization of Char", Fuel 55:3, 193-201 (1976)

incoming coal feed rate to the volumetric char inventory in the fluidized bed. The char thus differs in physical and chemical properties from both coal and from gasification or hydrogasification chars that have previously been studied. In form coke production, the hot (1100°F) char would be contacted with fresh coal which would supply an *in-situ* binder for briquetting. The resulting "green" briquettes would then be calcined in a shaft furnace at about 1800°F. The relative feasibility and impact on overall process efficiency of desulfurization before and after briquetting must be evaluated.

The product gas from mild gasification, on an inert-free basis, contains 20 to 28 vol% CH₄ and 28 to 50% H₂, where the H₂:CH₄ mole ratio increases monotonically from about 0.4 at 1100°F to 1.0 at 1300°F.² In addition to the presence of methane inhibiting the carbon gasification during desulfurization, the use of a process-derived gas mixture would be more economical than using pure hydrogen. If necessary, the hydrogen content of the desulfurizing gas can be adjusted via the shift reaction or partial steam reforming of the methane and other hydrocarbon gases. The effectiveness of varying mixtures of H₂ and CH₄ for desulfurization are being determined in the program.

The information thus obtained will be unique in its direct applicability to mild gasification, and thus will be of immediate value to further process development and the expanded utilization of high-sulfur Illinois coals.

EXPERIMENTAL PROCEDURES

Existing samples of mild gasification char from PRU tests conducted under a DOE/METC contract are being used instead of char made from IBCSP coals, because the former has been produced by the 100-lb/h PRU, and the cost of operating the PRU to make a char sample for this program would be prohibitive. We feel that a char produced in a laboratory unit would not necessarily be as truly representative of mild gasification char, and therefore the use of this material is justified. The coal used was an Illinois No. 6 fines (-1/4-inch) circuit from the Peabody Coal Company's Randolph preparation plant. Prior to feeding into the mild gasification reactor, the coal was blended with diluent char in a 1:1 weight ratio. Chars will be chosen for testing that contain a minimum of diluent coke breeze in the sample.

Task 1. Sample Preparation and Characterization

For the first-year experiments on granular char, samples will be crushed and screened to -80+100 mesh, divided by riffing into representative portions, and characterized in IGT laboratories according to the following protocol:

- proximate and ultimate analyses
 - heating value
 - pore volume and surface area
 - sieve analysis

Task 2. Equipment Preparation and Shakedown

The desulfurization experiments will be conducted in a nominal 2-inch batch reactor, which will be employed in a fluidized-bed mode for the first-year

granular char experiments and in a fixed-bed mode for the second-year briquette desulfurization experiments. The schematic diagram of the reactor system is shown in Figure 3. Existing furnaces, controls, instruments, and gas supply equipment will be used. A reactor vessel will be fabricated from Sch 80 316 stainless steel to safely operate up to 1800°F and 100 psig. The reactor system will also be modified to allow operation up to 100 psig by the addition of high-pressure mass flow controllers and a high-capacity sintered metal filter to retain fines, replacing the existing low-pressure cyclone.

In the first year, this task will cover the reactor fabrication, system cleanup, mechanical and electronic testing of components, and shakedown testing of the system.

Figure 3. SCHEMATIC OF EXPERIMENTAL DESULFURIZATION REACTOR

Task 3. Desulfurization

This Task is divided into two Subtasks as shown below. In the first year, the experimental work will be performed with granular char, and in the second year, with briquettes made from granular char and coal according to the procedure described in Task 1.

Subtask 3.1. Parametric Experiments

Char desulfurization experiments will be performed to determine the effects of temperature, pressure, residence time, and gas composition on the char sulfur content. Table 1 shows the specific values of these parameters to be tested. Not all of the combinations in the test matrix will be used. The combinations of parameters will be selected, based on the ongoing data interpretation, to maximize char desulfurization. A total of 24 experiments will be performed in each year of the program.

Table 1. EXPERIMENTAL PARAMETERS TO BE TESTED

Temperature, °F	1100, 1300, 1550
Pressure, psig	50, 100
Residence time, min	30, 60
Gas composition, vol% H ₂ ^a	50, 70, 90
Superficial gas velocity, ft/s ^b	0.1, 0.2

^a Balance CH₄

^b For first-year fluidized-bed experiments only

In a typical experiment, 50 to 100 grams of char or green briquettes or will be charged to the reactor, which will then be sealed. The reactor and associated tubing will be leak-tested and purged with inert gas. The reactor will then be heated to the desired desulfurization temperature while continuing the flow of inert gas. When the desired temperature is attained, the gas flow will be switched to the desired premixed gas (5%, 20%, or 50% H₂ in CH₄). Gas samples will be retrieved at five-minute intervals during the first 20 minutes, and thereafter at 15-minute intervals until the end of the desired residence time. Inert gas flow will then replace the reactive gas mixture, and the reactor will be rapidly cooled. When cooled to room temperature, the reactor will be opened to retrieve the desulfurized sample for analysis.

For first-year tests, the gas flow to the fluidized-bed reactor will be based on the required minimum fluidization velocity (u_{mf}). The parameters selected for gas velocity are slightly below and slightly above three times the u_{mf} for the largest (80-mesh) char particles. The required gas flow to attain the desired gas velocity will be calculated for each experiments based on the density and viscosity of the gas mixture used at the conditions of the experiment.

Subtask 3.2. Product Characterization and Evaluation

The desulfurized char or briquettes from each experiment will be evaluated by proximate and ultimate analyses. The amount of sulfur removal will be calculated based on the weight% of sulfur in char (from first-year experiments) or from coke (from second-year experiments). The heat content of the product chars will be calculated according to the following formula from the IGT Databook:¹⁰

$$Q_v \text{ (Btu/lb, dry basis)} = 146.58C + 568.78H + 29.4S - 6.58A - 51.53(O+N)$$

where C, H, S, A, and (O+N) are the respective weight % of carbon, hydrogen, total sulfur, ash and oxygen + nitrogen by difference.

Selected samples will also be analyzed for sulfur by type and measured calorific value, in order to study any effects of the experimental parameters on the distribution of inorganic or organic sulfur removed. It is estimated that about one of eight samples will be analyzed for sulfur by type and calorific value.

Gas samples from the desulfurization unit will be analyzed for H₂S content by the GC/FPD method.

Task 4. Data Analysis and Interpretation

The experimental data will be analyzed and interpreted to determine the effects of the selected parameters (temperature, pressure, residence time, gas velocity, and gas composition) on the following properties of the granular mild gasification char:

- Sulfur content, wt% of dry char
 - Percent carbon conversion, $100 \left[1 - \frac{m_r (\%C_r / 100)}{m_f (\%C_f / 100)} \right]$
- where m_f = feed char mass, m_r = residue mass, $\%C_f$ = feed char carbon content, and $\%C_r$ = residue carbon content.
- Higher heating value of char, Btu/lb (dry)

If the gas-phase H₂S concentration appears to be significantly affecting the desulfurization rates under some conditions, some modification of the test plan may be made in order to further study this effect. In this case, gas flow rates different from those dictated by the test plan parameters may be used.

¹⁰

Coal Conversion Systems Technical Data Book, U.S. DOE Document HCP/T2286-01, Section IA.30.5 (Feb 1978), pp. 1-2

RESULTS AND DISCUSSION

Task 1. Sample Preparation and Characterization

Several char product samples that were collected from mild gasification test conducted in the Process Research Unit (PRU) were investigated for use in this project. All of the chars were obtained from Illinois No. 6 coal. The main concern for the purpose of the desulfurization tests was to minimize the amount of diluent coke breeze in the sample. The best sample was coal agglomerates from PRU test MG-8 which was conducted with 100% coal feed, using coke breeze only in the starter bed. The fact that these chars were coal agglomerates minimized the amount of coke breeze in the material. The char was screened to -80+100 mesh. The results of the analyses on this material are given in Table 2.

Task 2. Equipment Preparation and Shakedown

The schematic diagram of the reactor system to be used in the desulfurization tests is shown in Figure 3. Existing furnaces, controls, instruments, and gas supply equipment is being used. This quarter, a reactor vessel was fabricated from Sch 80 316 stainless steel to safely operate up to 1800°F and 100 psig. Also this quarter, the reactor system was modified to operate to allow operation up to 100 psig by the addition of high-pressure mass flow controllers, a high-capacity sintered metal filter to retain fines, and a dome-loaded back pressure regulator. The shakedown of this unit will be conducted early in the next quarter.

Task 3. Desulfurization

No work was scheduled on this task for this quarter.

Task 4. Data Analysis and Interpretation

No work was scheduled on this task for this quarter.

Table 2. ANALYSIS OF MILD-GASIFICATION CHAR FROM PRU TEST MG-8

<u>Proximate Analysis</u>		<u>wt %</u>
Moisture		1.46
Volatile matter		11.64
Ash		34.81
Fixed Carbon		<u>52.09</u>
		100.00
<u>Ultimate Analysis</u>		
Carbon		54.63
Hydrogen		0.94
Sulfur		4.58
Nitrogen		1.11
Oxygen (by diff.)		3.41
Ash		<u>35.33</u>
		100.00
Bulk density, g/cc	0.739	
Surface area, m ² /g	17.68	

CONCLUSIONS AND RECOMMENDATIONS

The construction of the desulfurization reactor and modification of the gas metering and filtration system have been completed and shakedown will be conducted early in the next quarter. A representative mild-gasification char sample has been analyzed and is ready for testing. Conclusions and recommendations must await the results of the initial desulfurization tests which will be conducted next quarter.

This work was prepared with the support, in part, by grants made possible by the Illinois Department of Energy and Natural Resources through its Coal Development Board and Center for Research on Sulfur in Coal, and by the U.S. Department of Energy. However, any opinions, findings, conclusions, or recommendations expressed herein are those of the author(s) and do not necessarily reflect the views of IDENR, CRSC, and the DOE.

PROJECT MANAGEMENT REPORT
September 1 - November 30, 1991

Project Title: Investigation of a Sulfur Reduction Technique
for Mild Gasification Char

Principal Investigator: Mr. Richard Knight, Institute of Gas Technology

Project Monitor: Mr. Frank Honea, CRSC

COMMENTS

No change to the budget was implemented this quarter. However, due to delays in construction of the apparatus, the shakedown of the reactor has been delayed by one month. This should not affect the remainder of the test plan.

This project is funded by the U. S. Department of Energy (METC) and by the Illinois Department of Energy and Natural Resources as part of their cost-shared program.

END

**DATE
FILMED**

3 / 24 / 92