DOE/PC/90176--T49

ANNUAL TECHNICAL REPORT

September 1, 1990, through August 31, 1991

DOE/PC/90176--T49

DE92 004185

Project Title: **Dewatering Studies of Fine Clean Coal**

Principal Investigator: Dr. B. K. Parekh
Center for Applied Energy Research
University of Kentucky

Project Monitor: Dr. Dan Banerjee
Center for Research on Sulfur in Coal

ABSTRACT

Physical cleaning of ultra-fine coal using advanced froth flotation technique provides a low ash product; however, the amount of water associated with clean coal is high. Economic removal of water from the froth will be important for commercial applicability of the advanced flotation processes. The main objective of the present research program is to study and understand dewatering characteristics of ultra-fine clean coal and to develop process parameters to effectively reduce the moisture to less than 20 percent in the clean coal product. The research approach under investigation utilizes synergistic effect of metal ions and surfactant to lower the moisture of clean coal using the conventional vacuum dewatering technique.

During the first year of this two-year research project, studies were conducted on surface chemical characterization of ultra-fine clean coal in the presence of various types of metal ions and surfactants. The results of the study indicated that there is a direct correlation between the point-of-zero charge (PZC) of metal ion/fine coal system and lowering of moisture in the filter cake. Adsorption of either metal ions or surfactants alone did not provide a significant reduction of moisture in the filter cake. However, a combination of the two provided a filter cake containing about 20 percent moisture. Morphology studies of the filter cake showed segregation of larger particles at the bottom of the filter cake.

Efforts are in progress to optimize and determine effective ways to add the metal ions and surfactants to the slurry and conduct semicontinuous studies on filtration and dewatering of the fine coal slurry using a laboratory vacuum drum filter.

MASTER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

(This project is funded by the Illinois Department of Energy and Natural Resources as part of its cost-shared program with the U. S. Department of Energy.)

EXECUTIVE SUMMARY

Recovery of fine clean coal from waste stream offers an attractive source of low-ash, low-pyritic sulfur clean coal. In fine state, most of the mineral matter is liberated and could be effectively removed by the newly developed advanced column flotation technology. These fine coal cleaning techniques will be particularly applicable to the Illinois high ash, high pyrite sulfur coals, where ultra-fine grinding of coal is necessary to liberate the mineral matter. However, if the recovered fine clean coal cannot be dewatered economically to a low (less than 20 percent) moisture level, then acceptance of these newly developed techniques by the coal industry is unlikely.

The objective of the present research program is to study dewatering characteristics of ultra fine clean coal obtained from the Kerr-McGee's Galatia plant, and to develop process criteria to obtain a dewatered clean coal containing less than 20 percent moisture. In this study, a novel concept of utilizing synergistic effect of metal ions and surfactant is being explored. This is the first annual report of the two-year, funded research program.

During the first year of the program, adsorption studies were conducted on fine coal using di-, tri- and tetra-valent metal ions, as well as anionic, nonionic and cationic surfactants. Results of the study indicate that there is a direct correlation between the lowering of moisture content of the fine coal filter cake and the point-of-zero charge (PZC) observed with coal and metal ions. PZC is the pH of the system where there is no charge on the particle which facilitates coagulation of fine particles.

Addition of anionic and cationic surfactant did not show any PZC, however, nonionic surfactant showed PZC at pH ~ 3.0 . No significant moisture reduction was observed with addition of surfactant solution alone. However, combination of metal ion and surfactant provided a significant reduction in moisture content of filter cake, providing about 20 percent moisture product. The study also found that, for effective moisture reduction of the fine coal filter cake, the optimum amount of metal ion and surfactant requirements are as follows: 50 ppm for di-valent Cu^{+2} ion, ~ 5 ppm for tri-valent Al^{+3} and about 2 ppm for tetra-valent Ti^{+4} ions, and 0.25 to about 1.5 kg/ton of nonionic or anionic or cationic surfactant are needed. Morphology study of the filter cake showed segregation of larger size particles at the bottom of the filter cake.

During the next year of the program, studies will be conducted to determine the order of addition of reagents and a detailed morphology study of the filter cake will also be conducted. In the later part of the program, continuous dewatering tests on the fine size clean coal will be conducted using a bench scale vacuum drum filter device. In this continuous dewatering test, the optimum process parameters developed in the first year of the program will be utilized.

OBJECTIVES

The main objective of the present research program is to study and understand dewatering characteristics of ultra-fine clean coal obtained using the advanced column flotation technique from the Kerr-McGee's Galatia preparation plant fine coal waste stream. It is also the objective of the research program to utilize the basic study results, i.e., surface chemical, particle shape, particle size distribution, etc., in developing a cost-effective dewatering method. The ultimate objective is to develop process criteria to obtain a dewatered clean coal product containing less than 20 percent moisture, using the conventional vacuum dewatering equipment.

The above-stated objectives will be achieved using five (5) different tasks. Task 1 involving acquisition and characterization of the fine clean product obtained from the 'Ken-Flote' column and Task 2 on investigation of surface chemical properties of the coal before and after flotation, with and without the presence of various surfactants and metal ions have been completed. Task 3 on laboratory dewatering studies of the clean coal product utilizing information generated in Task 2 is in progress. Task 4 involving utilization of the novel AC Electro-Coagulation technique, and Task 5 on continuous dewatering tests using a laboratory vacuum drum filter utilizing the optimum dewatering conditions identified in Tasks 2, 3, and 4 will be conducted in the later part of the program.

INTRODUCTION AND BACKGROUND

Most of the coal presently used by the utility industry is cleaned at preparation plants employing wet processes. Water, while being the mainstay of coal washing, is also one of the least desirable components in the final product. The problem becomes severe as the coal particle size decreases. Most of the advanced physical and chemical coal cleaning processes utilize ultra-fine size coal. The clean coal product so obtained requires extensive dewatering before it can be used. Currently available dewatering techniques are inefficient for dewatering of ultra-fine (minus 325 mesh) coal. The coal industry in the U.S. has expressed serious concern about utilizing a novel advanced cleaning process, if an efficient and economical dewatering process is not available. Thus, the present research program presents a novel approach for the urgent problem which needs to be solved in a short period of time.

Although the term "dewatering" refers to removal of water, researchers have used different terms and descriptions to define water associated with particles. Brown et al⁽¹⁾ classified five types of water associated with coal, including interior adsorption, surface adsorption, capillary, interparticle and adhesion water. The last three types of water are termed as "free" water and are potentially removable by mechanical techniques. However, the first two types of water, known as "inherent" moisture, can only be removed by energy-intensive techniques such as thermal drying.

A variety of techniques are currently used in contemporary practice for dewatering coal. The type and efficiency of various dewatering equipment varies as a function of particle size. The degree of difficulty associated with mechanical dewatering increases as the surface area of the particles increases. Particles finer than 0.5 mm (28 mesh) present the greatest dewatering difficulty.

There has been a rapid increase in research and technology involving developments to improve fine-coal dewatering. Parekh et al⁽²⁾ have published a review on fine coal and refuse dewatering, which also included new dewatering technologies being developed in dewatering of fine coal. Methods for improving filtration of fine coal can be divided into two groups: those involving equipment modification and those involving process modifications.

In equipment modification, high pressure filters⁽³⁾, high 'g' centrifuges⁽⁴⁾, membrane pressure filters⁽⁵⁾ and electro-acoustic dewatering⁽⁶⁾ processes have shown remarkable success. However, all these processes are either too high in capital and operating costs or are in the early stages of testing.

In process modification, most of the research focussed on viscosity reduction, flocculation and surfactant addition. Addition of heat through direct heating of slurry or passing steam lowers the moisture to some extent. The flocculation process involves addition of polyelectrolyte flocculent, resulting in formation of flocs, changing the apparent particle size. Even though it provides increased filtration rate; however, due to different pore structure, higher final moisture contents can result. Addition of surfactants will produce either a reduction in the surface tension of the water or will adsorb onto the solid surface to make the particles more hydrophobic, and should result in a lower cake moisture.

Most of the dewatering research using surfactant and/or flocculants has been conducted using larger (>100 micron) size coal particles. There is little or no evidence of any research conducted on ultra-fine (<44 micron) coal particles. The present research project utilizes a novel concept of applying a synergistic effect of metal ions, surfactants and pH of the suspension in a single stage treatment to dewater and filter the ultra-fine clean coal to a low (<20 percent) moisture using the conventional vacuum dewatering technique.

This annual report summarizes the experimental results, conclusions and recommendations for the period September 1, 1990, through August 31, 1991.

EXPERIMENTAL PROCEDURES

Fine size clean coal product for the study was obtained from the Kerr-McGee's Galatia's fine coal waste stream using the "Ken-Flote" column. The fine clean coal was characterized for particle size distribution using the Granulometer, Model 715 (Marco Scientific), which utilizes the laser beam scattering principle similar to Microtrac equipment. The ash content was analyzed using the standard ASTM procedure.

For dewatering studies, the clean coal froth was thoroughly mixed with a stirrer in a 5-gallon bucket. For each dewatering test, a known quantity of the slurry was first conditioned with a reagent using a magnetic stirrer. The conditioned slurry was subjected to filtration using a Whatman No. 1 filter paper utilizing a bench scale dewatering equipment setup, as shown in Figure 1. The rate of filtration was monitored with time; and after about three minutes of filtration, the wet cake was weighed and dried at 100 °F and weighed again to determine the amount of moisture present in the cake.

The adsorption studies of metal ions and surfactants onto the coal was studied using the Zeta Meter, Model 3.0. For the study, a small amount of colloidal-size coal particles produced in a pestle and mortar was conditioned in a pH-adjusted, known strength, metal ion or surfactant solution. In the Zeta Meter, a constant voltage was applied in a cell containing the coal-metal ion or surfactant solution. The zeta potential was measured from the speed of migration of particles, and the sign of the particle charge is determined from the direction of the moving particle.

For the morphology study of the filter cake, an improved technique which provided a means to study in-situ morphology of the filter cake was developed. In this technique, as soon as the filter cake was formed, a mixture of acetone, Buhler Epoxide Resin, No. 20-8130-032, and Buhler Epoxy Hardener (Ratio 7:1:1) was added to penetrate through the cake. The acetone/resin mixture took about 10 minutes to saturate the cake. It was then dried overnight in an oven at 100 °F. The hardened cake was sliced in the middle for the study of the morphology of the filter cake using an image analysis system.

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

Figure 1. Bench Scale Dewatering Equipment Setup

RESULTS AND DISCUSSIONS

The particle size and ash distribution of the Kerr-McGee's Galatia plant flotation feed is given in Table 1.

Table 1. Particle Size and Ash Distribution of Flotation Feed from the Kerr-McGee Galatia Plant

<u>Size (mesh)</u>	<u>Weight Percent</u>	<u>Percent Ash</u>	<u>Percent Ash Distribution</u>
+200	15.2	7.0	2.5
200 x 325	9.4	13.1	2.9
325 x 500	8.4	17.5	3.5
-500	<u>67.0</u>	<u>56.6</u>	<u>91.1</u>
	100.0	41.72	100.0

The ash content of the feed was about 41.7 percent. Note that about 70 weight percent of the particles were in minus 500 mesh size, which also contained 90 percent of the total ash. The 'Ken-Flote' column flotation product obtained from this feed contained about 8 percent ash, and the average particle size (50th percentile) was 21 microns (Figure 2).

The electrophoretic mobility (EPM) of the coal before and after the column flotation is shown in Figure 3. Before flotation the coal shows point-of-zero charge (PZC) at pH ~ 4.7 . However, after flotation the coal surface becomes negatively charged at all pH. This is due to the negative charge carried by the oil droplets, which are adsorbed onto the coal surface.

Dewatering Studies

Baseline dewatering data of the column product, without utilizing any reagents, are shown in Figure 4. Note that at 3 minutes filtration time moisture in the filter cake was about 35 percent. Increasing filtration time to seven minutes provided only marginal improvements.

The thickness of the filter cake formed during filtration plays an important role in controlling the moisture contents of the cake. Figure 5 shows the effect of cake thickness versus filter cake moisture. Note that in up to 0.50 cm thickness the moisture in the filter cake was about 30 percent; but at higher thickness, the moisture rose rapidly to a high

Figure 2. Particle Size Analysis of the Column Flotation Product

Figure 3. Electrophoretic Mobility of Coal and Oil Droplets

Figure 4. Effect of Filtration Time on Final Cake Moisture of the Clean Coal Froth

Figure 5. Effect of Cake Thickness on Filter Cake Moisture

value. Based on these data, all the tests reported hereafter were conducted using the 0.50 cm thickness cake.

Addition of fuel oil is known to decrease moisture of the filter cake. In the present study, addition of about 2.5 pound/ton of fuel oil lowered the filter cake moisture from 34.5 percent to 30.5 percent. However, increasing the fuel oil dosages did not lower moisture in the filter cake.

Figure 6 shows the electrophoretic mobility of the clean coal and moisture content of the filter cake with respect to pH. The moisture content of the filter cake ranges from 32 to 36 percent. This type of behavior could be due to the absence of PZC for the system.

Metal Ions Effect on Dewatering

The electrophoretic mobility and filter cake moisture data with respect to pH in presence of 1×10^{-4} M/L (46 ppm) copper (Cu^{+2}) ions are shown in Figure 7. In presence of Cu^{+2} ions, coal reverses charge as pH is increased, showing PZC at pH 4.8 and 6.3. Note that filter cake moisture lowers significantly in the region of PZC. Between the two PZC, about 25 percent more moisture reduction was obtained.

The electrophoretic mobility and filter cake moisture data with respect to pH for 1×10^{-4} M/L (66 ppm) aluminum (Al^{+3}) and 1×10^{-4} M/L (80 ppm) titanium (Ti^{+4}) ions are shown in Figures 8 and 9, respectively. Note that, for Al^{+3} ions, lower moisture in the filter cake was obtained, around pH 7.0, which is the PZC of the system. Reduction in moisture content at pH ~ 3.0 and 10.0 is due to compression of the double layer. For titanium ions, lower moisture was obtained at pH ~ 5.0 , which is the PZC of the system.

The adsorption isotherm and electrophoretic mobility of copper (Cu^{+2}), aluminum (Al^{+3}) and titanium (Ti^{+4}) ions onto the coal are shown in Figure 10. The monolayer coverage of the Cu^{+2} and Al^{+3} ions, as shown by the plateau region on the adsorption isotherm, is at ~ 50 mg/liter and ~ 5 mg/liter, respectively. For Ti^{+4} ions, the plateau region was not clear, which may be due to a very small amount of metal ions required to show a monolayer coverage. Note that the charge reversal of the coal particle surface in the presence of Cu^{+2} and Al^{+3} takes place at the monolayer coverage region, which also corresponds to the minimum moisture content in the filter cake.

Effect of Surfactants on Dewatering

A series of dewatering tests were conducted using anionic (sodium 2-ethylhexyl sulfate), non-ionic (octyl phenoxy polyethoxy ethanol) and cationic (1-cetyl pyridinium chloride) surfactants. Table 2 lists basic information on the three surfactants investigated.

The electrophoretic mobility and filtration data for the anionic surfactant are shown in Figure 11. The adsorption of anionic surfactant (0.1 kg/ton) did not indicate any PZC of the system, and as expected, the filtration data shows no noticeable reduction in moisture content of the filter cake.

Figure 6. Electrophoretic Mobility and Filter Cake Moisture of the Clean Coal with respect to pH

Figure 7. Electrophoretic Mobility and Filter Cake Moisture of the Clean Coal in Presence of 1×10^{-4} M/L Copper Ions

Figure 8. Electrophoretic Mobility and Filter Cake Moisture of the Clean Coal in Presence of 1×10^{-4} M/L Aluminum Ions

Figure 9. Electrophoretic Mobility and Filter Cake Moisture of the Clean Coal in Presence of 1×10^{-4} M/L Titanium Ions

Table 2. List of Surfactants Investigated

	Surfactant		
	Sodium 2-Ethylhexyl Sulfate	Octyl Phenoxy Polyethoxy Ethanol	1-Hexadecyl Pyridinium Chloride
Type	Anionic	Non-ionic	Cationic
Abbreviation	S2ES	OPPE	CPC
Commercial Name	NAS 08	TRITON X-114	Cetyl Pyridinium Chloride
Active Ingredient, weight %	40%	100%	100%
Formula	$C_4H_9(C_2H_5)CH_2-SO_4Na$	$C_8H_{17}-C_6H_4-(OCH_2CH_2)_{7-8}OH$	$C_{16}H_{33}C_5H_5NCl$
Molecular Weight	232	536	340
Manufacturer	Niacet Corporation Niagara Falls, NY	Rohm and Haas Philadelphia, PA	Sigma Chemical St. Louis, MO

Figure 10. Adsorption Isotherms and Electrophoretic Mobilities of Copper, Aluminum and Titanium Ions on Fine Clean Coal

Figure 11. Electrophoretic Mobility and Filtration Data of the Fine Clean Coal in Presence of the Anionic (Sodium 2-Ethylhexyl Sulfate) Surfactant (Amount of Surfactant = 0.1 Kg/ton)

The electrophoretic mobility and filtration data in presence of 0.1 kg/ton nonionic surfactant are shown in Figure 12. Adsorption of this surfactant provided a PZC at pH ~ 3.0 . The filtration data shows about 4 percent moisture reduction at pH ~ 3.0 , which is close to the PZC.

The electrophoretic and filtration data in presence of 0.1 kg/ton cationic surfactant are shown in Figure 13. Note that, in presence of this surfactant, as expected, the coal surface became positively charged at all pH values and no PZC was present. The filtration data also showed no significant improvement in moisture reduction.

Combined Effect of Metal Ions and Surfactants

The effect of combining the metal ion and surfactant solution on filtration characteristics of fine coal was studied using a constant amount (1.5 kg/ton) of the cationic surfactant and various concentrations of Cu^{+2} , Al^{+3} and Ti^{+4} ions. Figure 14 shows the effect of varying dosages of the three metal ions on moisture content of the filter cake at pH of ~ 7.5 . Note that a minimum filter cake moisture is observed at 50 mg/liter of Cu^{+2} , 5 mg/liter of Al^{+3} and <2 mg/liter of Ti^{+4} metal ions. Under all these conditions, moisture in the filter cake averaged about 23 percent. One interesting observation to be made is that all these metal ion concentrations correspond to the monolayer coverage on coal particles.

To determine the optimum amount of surfactant needed in combination with metal ions to provide a low moisture filter cake, studies were conducted on varying amounts of surfactant, while keeping metal ions constant, e.g., copper (0.23 kg/ton), aluminum (0.15 kg/ton) and titanium (0.0067 kg/ton). These concentrations correspond to the lowest moisture content observed in the filter cake, as discussed earlier.

Figure 15 shows the effect of the anionic surfactant concentration with various metal ions on cake moisture contents. With copper ions, lowest moisture of 22 percent was obtained with a surfactant dosage of about 0.5 kg/ton. However, with aluminum and titanium, there was no noticeable improvement in filter cake moisture reduction.

For the nonionic surfactant, (octyl phenoxy polyethoxy ethanol) (Figure 16), the lowest moisture of 21 percent is obtained with copper ions; however, the amount of surfactant required is about 1.5 kg/ton. In this case, aluminum metal ions also provided 21 percent filter cake moisture using about 0.25 kg/ton of the surfactant. No noticeable improvement was observed with titanium ions.

With the cationic surfactant, (cetyl pyridinium chloride) (Figure 17), filter cake moisture obtained using Cu^{+2} and Al^{+3} reduced to about 22 percent using a surfactant dosage of 0.25 kg/ton. Again, in the case of titanium, no improvement in moisture reduction was observed. Results obtained with titanium metal ions are inconclusive. This could be due to either partial solubility of TiCl_4 salt used for the study, or the amount of titanium metal ions required for moisture reduction is very small, and in the present studies, an excess of titanium ions may have been used.

Figure 12. Electrophoretic Mobility and Filtration Data of the Fine Clean Coal in Presence of the Non-ionic (Octyl Phenoxy Polyethoxy Ethanol) Surfactant (Amount of Surfactant = 0.1 Kg/ton)

Figure 13. Electrophoretic Mobility and Filtration Data of the Fine Clean Coal In Presence of the Cationic (Cetyl Pyridinium Chloride) Surfactant (Amount of Surfactant = 0.1 Kg/ton)

Figure 14. Combined Effect of Cationic Surfactant (CPC) with Different Metal Ions (Copper, Aluminum and Titanium) on Filter Cake Moisture (Amount of Surfactant 1.5 Kg/ton)

Figure 15. Combined Effect of Anionic Surfactant with Different Metal Ions (Copper, Aluminum and Titanium) on Filter Cake Moisture

Figure 16. Combined Effect of Non-Ionic Surfactant with Different Metal Ions (Copper, Aluminum and Titanium) on Filter Cake Moisture

Figure 17. Combined Effect of Cationic Surfactant with Different Metal Ions (Copper, Aluminum and Titanium) on Filter Cake Moisture

Morphology Studies of Filter Cake

A filter cake obtained without the addition of metal ion or surfactant was divided into three parts using a specially designed cake slicer. The average particle size (D_{50}) of the top, middle and bottom layers of the cake was $22.3 \mu\text{m}$, $34.4 \mu\text{m}$ and $37.0 \mu\text{m}$, respectively. The moisture content of the cake layers did not vary significantly. These data, however, suggested that, during filtration, segregation of large particles takes place at the bottom of the cake.

The image analysis of the filter cake pellet obtained by adding acetone-diluted resin is shown in Figure 18. From these figures, the void fraction of the top, middle and bottom layers of the cake were calculated. The percent voids were found to be 42.8, 40.3 and 37.8 percent for top, middle and bottom layers, respectively. These data indicate the void area between the particles decreases from top to bottom. The void number also indicates a measure of moisture that becomes trapped between the particles.

CONCLUSIONS

Based on the above-mentioned results, the following conclusions are made.

- Column flotation product obtained from the Kerr-McGee's Galatia plant had an average particle size of 21 microns. Dewatering of this product on a Whatman No. 1 filter paper provided a filter cake containing about 35 percent moisture.
- Addition of 2.5 lb/ton (1.1 kg/ton) of fuel oil lowered moisture content to about 30 percent. Increasing the amount of fuel oil did not lower the moisture content of the filter cake.
- A direct correlation exists between the PZC obtained with a metal ion/coal system and moisture reduction in the filter cake.
- Monolayer coverage of Cu^{+2} and Al^{+3} on the coal occurred at $\sim 50 \text{ mg/liter}$ and $\sim 5 \text{ mg/liter}$, respectively. A monolayer coverage of the metal ions onto the coal corresponds to the point where lowest moisture was observed in the filter cake.

Gray - Vitrinite

White - Inertinite

Black - Voids

Figure 18. Photomicrograph of Filter Cake

- Adsorption of anionic and cationic surfactant do not show any PZC, however, one PZC at pH ~ 3.0 was observed with the non-ionic surfactant. Adsorption of these surfactants onto clean coal did not significantly lower moisture content in the filter cake.
- The combination of metal ion and surfactant provide a significant reduction in moisture content of the filter cake.
- The optimum amount of metal ion and surfactant concentration combination found to provide a low (~22 percent) moisture filter cake are listed as follows.

<u>Metal Ion</u>	<u>Surfactant</u>
Cu ⁺² (50 mg/liter)	1. Cetyl pyridinium chloride (CPC) (0.25 kg/ton)
	2. Sodium 2 - ethylhexyl sulfate (S2ES)(0.5 kg/ton)
	3. Octyl phenoxy polyethoxy ethanol (OPPE) (1.5 kg/ton)
Al ⁺³ (5 mg/liter)	1. CPC (0.25 kg/ton)
	2. S2ES (1.0 kg/ton)
	3. OPPE (0.25 kg/ton)
Ti ⁺⁴ (~2 mg/liter)	1. CPC (1.5 kg/ton)
	2. S2ES (0.5 kg/ton)

- Image analysis of the filter cake obtained without addition of any reagent showed void fraction, decreasing from 42.8 percent (top layer) to 37.8 percent (bottom layer).

FUTURE WORK

In the next year of the research program, additional studies will be conducted to identify the order of addition of metal ion and surfactant. Dewatering studies will then be conducted with the novel AC-electrocoagulator, which will provide in-line metal ions to induce coagulation.

Later on it is planned to conduct a semicontinuous dewatering test using a laboratory vacuum drum filter utilizing the optimum amount of reagents found to be effective in dewatering of ultra-fine size clean coal.

It is also planned to conduct detailed morphology studies of the filter cakes obtained under various operating conditions using the image analyzer system.

REFERENCES

- (1) Brown, N.K. et al, "Preliminary Engineering and Economic Evaluation of Coal Preparation Concepts," EPRI RP1030-2.
- (2) Parekh, B.K. and A. E. Bland, 1989, "Fine Coal and Refuse Dewatering _ Present State and Future Considerations," Flocculation and Dewatering, Processing Engineering Foundation Conference, Scheiner and Moudgil (Eds.), pp. 383-398.
- (3) Dosoudil, M., 1987, "Continuous Pressure Filtration in the Coal Industry," Coal Preparation, 87., Lexington, Kentucky.
- (4) Smith, L.B., and R.A. Wolfe, 1990, "High Gravity Centrifuge for Fine Coal Dewatering," Sixth Annual Coal Preparation, Utilization and Environmental Control Contractors' Conference. Department of Energy, Pittsburgh, Pennsylvania, pp. 259-265.
- (5) Vickers, F., 1982, "The Treatment of Fine Coal," Colliery Guardian.
- (6) Muralidhara, H.S., N. Senapati, and R.B. Beard, 1986, "A Novel Electro-acoustic Separation Process for Fine Particles Suspension," Advances in Solid-Liquid Separation, Battelle Press, Columbus, Ohio.

PROJECT MANAGEMENT REPORT

June 1, 1991 through August 31, 1991

Project Title: Dewatering Studies of Fine Clean Coal

Principal Investigator: Dr. B. K. Parekh
Center for Applied Energy Research
University of Kentucky

Project Monitor: Dr. Dan Banerjee
Center for Research on Sulfur in Coal

Comments

First-year efforts in the program were on schedule. At present, we do not anticipate any delay in the other tasks proposed for the continuation of the program.

(This project is funded by the Illinois Department of Energy and Natural Resources as part of its cost-shared program with the U. S. Department of Energy.)

SCHEDULE OF PROJECT MILESTONES

Hypothetical Milestones:

- A. Acquisition and Characterization of Samples (Task 1)
- B. Surface Chemical Studies (Task 2)
- C. Dewatering Studies (Task 3)
- D. AC Electro-Coagulation Studies (Task 4)
- E. Continuous Dewatering Tests (Task 5)
- F. Technical Report prepared and submitted
- G. Project Management reports prepared and submitted

Comments:

This is a 24-month research project. Task 3 and 4 will be completed next year. Task 5 will be initiated and completed next year.

YEAR 1: SEPTEMBER 1, 1990 TO AUGUST 31, 1991

EXPENDITURES - EXHIBIT B

Projected and Estimated Actual Expenditures by Quarter

Quarter*	Types of Cost	Direct Labor	Materials and Supplies	Travel	Major Equipment	Other Direct Costs	Indirect Costs	Total
Sept. 1, 1990 to Nov. 30, 1990	Projected	\$15,896	\$1,250	\$ 500	\$0	\$1,250	\$ 4,520	\$23,416
	Estimated Actual	\$13,542	\$ 347	\$ 20	\$0	542	3,468	\$17,919
Sept. 1, 1990 to Feb. 28, 1991	Projected	31,792	2,500	0	0	2,500	9,041	45,833
	Estimated Actual	30,970	2,668	600		1,200	8,505	43,943
Sept. 1, 1990 to May 31, 1991	Projected	47,688	3,750	2,940 *	0	1,750 *	13,562	69,690
	Estimated Actual	47,900	4,309	2,282	0	1,800	13,622	69,913
Sept. 1, 1990 to Aug. 31, 1991	Projected	63,584	5,000	3,760	0	3,000	18,083	93,427
	Estimated Actual	63,584	5,000	3,760	0	3,000	18,083	93,427

* Cumulative by quarter

*Money transferred from Other Direct Costs category to Travel category as per CRSC authorization.

COSTS BY QUARTER - EXHIBIT C

Dewatering Studies of Fine Clean Coal

Months and Quarters

O = Projected Expenditures -----

Δ = Actual Expenditures _____

Total CRSC Award \$ 93,427 Year 1

END

**DATE
FILMED**

2 / 03 / 92