437
10/9/79

NO STOCK

DOE/JPL/955164-1

DEVELOPMENT OF ECONOMICAL IMPROVED THICK FILM SOLAR CELL CONTACT

Quarterly Report No. 1

By
Bernd Ross
David Mentley

January 1979

Work Performed Under Contract No. NAS-7-100-955164

Bernd Ross Associates
San Diego, California

MASTER

U.S. Department of Energy

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

Solar Energy

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency Thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

DISCLAIMER

Portions of this document may be illegible in electronic image products. Images are produced from the best available original document.

NOTICE

This report was prepared as an account of work sponsored by the United States Government. Neither the United States nor the United States Department of Energy, nor any of their employees, nor any of their contractors, subcontractors, or their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness or usefulness of any information, apparatus, product or process disclosed, or represents that its use would not infringe privately owned rights.

This report has been reproduced directly from the best available copy.

Available from the National Technical Information Service, U. S. Department of Commerce, Springfield, Virginia 22161.

Price: Paper Copy \$4.50
Microfiche \$3.00

DRD Line No. SE-5

DISCLAIMER

This book was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise, does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

DEVELOPMENT OF ECONOMICAL
IMPROVED THICK FILM SOLAR
CELL CONTACT

BERND ROSS and DAVID MENTLEY

BERND ROSS ASSOCIATES
2154 Blackmore Ct.
San Diego, CA 92109

QUARTERLY REPORT NO. 1

January 1979

MASTER

Contractual Acknowledgement

The JPL Low-Cost Silicon Solar Array Project is sponsored by the U.S. Department of Energy and forms part of the Solar Photovoltaic Conversion Program to initiate a major effort toward the development of low-cost solar arrays. This work was performed for the Jet Propulsion Laboratory, California Institute of Technology by agreement between NASA and DOE.

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

TABLE OF CONTENTS

<u>Section</u>	<u>Titles</u>	<u>Page</u>
	Table of Contents-	ii
	List of Figures	iii
1.0	Summary	1
2.0	Introduction	2
3.0	Metal Systems Considerations	3
4.0	Metal Ink Binder	6
5.0	Considerations On Silicon Dioxide Removal	9
6.0	Silicon Dioxide Removal Experiments	10
7.0	Ammonium Fluoride	11
8.0	Ammonium Bifluoride	13
9.0	Teflon ^R	13
10.0	Silver Fluoride	17
11.0	Silver Paste Experiments	23
12.0	Further Experiments	24
13.0	Electrical Characteristics	33
14.0	Conclusions and Problems	35
15.0	Plans and Recommendations	36
	References	37
16.0	Progress on Program Plan	38

LIST OF FIGURES

<u>Figure</u>		<u>Page</u>
1	Solid solubility of silver in lead	5
2	Solid solubility of copper in zinc	5
3	Solid solubility of silver in tin	5
4	TGA/DTA traces of binder V5005	7
5	TGA/DTA traces of silver fluoride (AgF)	8
6	TGA/DTA traces of ammonium fluoride (NH_4F)	12
7	SEM photomicrograph of ammonium fluoride etching action on 3000 Å thick SiO_2 layer on silicon substrate at 600°C. Cambridge at 1700X	13
8	TGA/DTA traces of ammonium bifluoride (NH_4HF_2)	14
9	TGA/DTA traces of Teflon ^R (DLX 6000)	15
10	SEM photomicrograph of Teflon ^R etching action on 3000 Å thick SiO_2 layer on silicon substrate at 600°C. Cambridge at 1600X at 1600°C	16
11	SEM photomicrograph of silver fluoride (AgF) etching and wetting action on oxidized silicon (SiO_2 3000Å thick) at 500°C. Cambridge at 4000X	19
12	SEM photomicrograph of different region of same sample as Fig. 11 in backscatter mode on Cambridge at 1500 X	19
13	SEM photomicrograph of same sample as Fig. 12 taken in backscatter mode on Cambridge at 3700X	20
14	SEM photomicrograph of same region as Fig. 13 showing X-ray fluorescence silver map. Cambridge at 3700X. 2.98 KeV La . Integration time 1000 sec.	20
15	Vapor pressure curve of vapor above a) liquid silver fluoride and b) solid silver fluoride	22
16	SEM photomicrograph of screen-printed S012 silver-silver fluoride (10 wt%) ink. Cambridge at 17X.	26
17	SEM photomicrograph of same region as Fig. 16 at magnification of 412X.	26

<u>Figure</u>		<u>Page</u>
18	SEM photomicrograph of same region as Fig. 17 at magnification of 1700X	27
19	SEM photomicrograph of same region as Fig. 18 at magnification of 4200X	27
20	SEM photomicrograph of solar cell metallization with conventional fritted silver ink. Cambridge at 8000X.	28
21	SEM photomicrographs of firing progression of all metal silver paste S018. Cambridge at 3000X. a) 500°C b) 550°C c) 600°C d) 650°C e) 700°C f) 750°C	30
22	SEM photomicrograph of room temperature cleaved silicon substrate with all metal silver ink prints of S012 (10 wt% AgF) fired at 750°C a) magnification 1150X b) magnification 5700X c) magnification 11500X	32

During the first quarter of this investigation, materials were surveyed to provide candidates for an all metal electrode paste system. These consisted of a major constituent metal powder, a low melting metal powder suitable for a liquid phase sintering medium, and a powder material suitable as an etchant for silicon dioxide at sintering temperatures. By means of thermal gravimetric analysis a suitable binder was identified for low temperature fired inks.

The all metal ink concept was first demonstrated with the silver system to avoid the problems of limited process windows encountered with base metal systems.

A number of solid materials capable of selectively etching silicon dioxide at modest temperatures were identified. One of these, silver fluoride, has yielded very good results, wetting the silicon surface after removing a thick (3000Å) silica layer. Silver pastes containing the above materials have been prepared. A paste with silver fluoride was screened onto N-type silicon with 5Ωcm resistivity. The resulting contact pads had excellent adhesion but were not electrically ohmic. Metallurgically, these contacts have equal or better grain structure as commercial inks fired at the same temperatures. Another metal ink paste, incorporating boric acid, gave substantially lower resistances, however would not pass a 1-hour boiling DI water immersion without losing scratch resistance.

2.0 INTRODUCTION

The potential for economy and efficiency has been demonstrated for the thick film metallization process using screen printing for solar cell electrodes. However, process reliability and materials economy remain deficient. It is believed that these deficiencies can be removed by the use of ink formulations designed specifically for silicon solar cells, departing from ceramic technology tradition and utilizing all metal systems.

The objectives of this investigation are as follows:

1. Eliminate the glass frit which has been the conventional liquid phase sintering medium and adhesive for metallization inks.
2. Provide an appropriate metal which can serve as the liquid phase sintering medium.
3. Find a chemical constituent which effectively removes the native oxide from the silicon during the firing step, which can be made part of the ink, and which either becomes fugitive or remains an inert part of the matured metallization.
4. Maintain cognizance of the cost objectives of the LSA Project in selecting materials and processes.

3.0 METAL SYSTEMS CONSIDERATIONS

A large number of phase diagrams of binary metal systems were examined. Several systems were selected as potential candidates based upon conductivity, compatibility with silicon, process, solderability and cost. Process factors included mutual solubilities, temperature requirements and toxicity. Solubility curves were plotted from the phase diagrams for several systems. Metal system candidates included copper/tin, copper/zinc, nickel/zinc, cerium/copper, cerium/nickel, silver/tin, silver/lead, silver/antimony and silver/bismuth.

It is expected that the requirements for good liquid phase sintering are: good wetting of the major constituent powder grains (copper, nickel, or silver) by the frit metal liquid, reasonable solubility of the major constituent in the liquid metal, and generally compatible phase diagrams without intermetallics. Some solid solubility curves are plotted in Figures 1, 2, and 3. While silver in lead and copper in zinc appear well-behaved with increasing solubilities with temperature, the four experimental points given for silver in tin are puzzling and appear to indicate a retrograde solubility.

Initial experiments with base metal powders (copper-zinc and copper-tin) carried out in neutral atmospheres or forming gas showed both lacking adhesion and no sintering. This was attributed to oxide problems on silicon surfaces as well as on powder grains preventing wetting, along with excessive copper grain size. It was therefore decided to investigate SiO_2 removal, and to utilize

a major constituent powder with readily available optimal size ranges and generally well-known and well-behaved properties as a test vehicle for the all metal ink system. Since silver met these objectives, it was considered the best choice.

(Data taken from Ref. 1, p.38)

(Ibid, p. 651)

(Ibid, p.52)

4.0 Metal Ink Binder

The binder in the normal metal pastes is ethyl cellulose which has a very low volatility, with sublimation being complete only at temperatures as high as 800°C. Fortunately, a proprietary acrylic based binder was available from the subcontractor which depolymerizes at temperatures as low as 225°C. This can be seen from the combined TGA/DTA traces in Figure 4. This shows the weight loss (or gain) on the trace labeled TGA (thermal gravimetric analysis.) The differential thermal analysis indicates exothermic (+) and endothermic (-) reactions. These curves provide valuable information about the chemical and physical reactions taking place as the temperature is swept from room temperature to the desired upper limit. A check was made with this instrument on the decomposition temperature of silver fluoride. Figure 5 shows the TGA/DTA trace. A temperature of 470°C was found for decomposition. The dip of the DTA line below the average trace at 435°C indicates melting in agreement with the literature.²

PART NO. 990092

RUN NO. _____ DATE <u>10-6-78</u>	T-AXIS	DTA-DSC	TGA	TMA
OPERATOR <u>DM</u>	SCALE, mv/in. <u>0.8</u>	SCALE, °C/in. <u>4.0</u>	SCALE, mg/in. <u>5.0</u>	SCALE, mils/in. _____
SAMPLE <u>V5005 (BINDER)</u>	PROG. RATE, °C/min <u>25</u>	(mcal/sec)/in. _____	SUPPRESSION, mg _____	MODE _____
ATM <u>AIR</u>	HEAT <u>COOL</u> ISO _____	WEIGHT, mg _____	WEIGHT, mg <u>30.0</u>	SAMPLE SIZE _____
FLOW RATE <u>3 CU FT/HR</u>	SHIFT, in. <u>0</u>	REFERENCE _____	TIME CONST., sec _____	LOAD, g _____
			dY, (mg/min)/in. _____	dY, (10X), (mils/min)/in. _____

PART NO. 990092

RUN NO. _____ DATE _____	T-AXIS	DTA-DSC	TGA	TMA
OPERATOR <u>DM</u>	SCALE, mv/in. <u>0.8</u>	SCALE, °C/in. <u>4.0</u>	SCALE, mg/in. <u>5.0</u>	SCALE, mils/in. _____
SAMPLE: <u>SILVER FLUORIDE</u>	PROG. RATE, °C/min <u>15</u>	(mcal/sec)/in _____	SUPPRESSION, mg _____	MODE _____
<u>AgF</u>	HEAT _____ COOL _____ ISO _____	WEIGHT, mg _____	WEIGHT, mg <u>30.0</u>	SAMPLE SIZE _____
ATM <u>AIR</u> @ _____	SHIFT, in <u>0</u>	REFERENCE _____	TIME CONST., sec _____	LOAD, g _____
FLOW RATE <u>3 CFH/hr</u>			dY, (mg/min)/in _____	dY, (10X), (mils/min)/in _____

5.0 Considerations on Silicon Dioxide Removal

Silicon dioxide is easily removed with HF in an aqueous solution or by dry, hot fluorine, according to:

Since the use of HF is not convenient, we looked for fluorine-containing compounds which had low decomposition or melting temperatures and could be incorporated in the metal paste. The most attractive material appeared to be silver fluoride (AgF) which according to the literature, decomposes at 435°C. Others ordered included zinc fluoride (ZnF₂), aluminum fluoride (AlF₃), ammonium fluoride (NH₄F) and ammonium bifluoride (NH₄HF₂). The metal fluoride salts are expected to decompose with the fluorine becoming fugitive in the nascent state (F), causing it to be highly reactive. The cation is left behind reduced to the metallic form and is expected to combine with the other metallic ink constituents. This reaction would go in accordance with

In the ammonium salt decomposition the products are gaseous, ammonia, fluorine and in the case of NH₄HF₂, anhydrous hydrofluoric acid.

Since the metallic hydrides, titanium hydride and zirconium hydride, act in a very similar manner, releasing highly reactive

nascent hydrogen and leaving the metal behind, these hydrides were tried as well.

6.0 Silicon Dioxide Removal Experiments

Polished silicon wafers of N type material and a resistivity of $5\Omega\text{cm}$ were oxidized in air at a temperature of 1100°C for 30 minutes. The resulting silica layers gave uniform interference colors of reddish-purple and were estimated to be $2500\text{\AA}$ ($0.25\mu\text{m}$) thick. Subsequent SEM photographs showed the thickness to be closer to $3000\text{\AA}$ ($0.3\mu\text{m}$). The rationale for growing such a thick layer of SiO_2 was the ease with which the efficacy of an etchant material could be judged in this system. While the thickness of the native oxide is probably only a few atomic layers ($10 - 20\text{\AA}$), it is quite difficult to determine the existence of such layers by unsophisticated means.

A small quantity of pure fluorine containing material was placed in the center of the oxidized wafer. The wafer was put on a Kulicke-Soffa bonder heater stage and observed with a binocular microscope. The heater stage was set to a pre-determined temperature. This temperature was usually about 100°C above the estimated decomposition temperature. The estimate was based upon our TGA/DTA measurements and values obtained from the literature.

7.0 Ammonium fluoride

Figure 6 shows the TGA/DTA traces for ammonium fluoride (NH_4F). The TGA trace illustrates that weight loss occurs almost immediately, with the slope becoming quite steep at 150°C . While there are several inflection points, further emphasized by the structure apparent on the DTA trace, the weightloss is 71% complete at 250°C and 100% at 450°C . The structure exhibited in the DTA of Figure 6 is not understood. According to Berzelius³, NH_4F melts prior to decomposition, a phenomenon not noted by other references. The same reference points out that dissociation of ammonium fluoride proceeds according to $\text{NH}_4\text{F} \rightarrow \text{NH}_3 + \text{HF}$. Similarly, the reference asserts that NH_4F will dissociate into NH_4HF_2 and $\text{NH}_3^\dagger$ in the presence of water.

Figure 7 shows an electron micrograph taken on a Cambridge SEM 1700X magnification, showing the boundary between the virgin layer and the portion covered with ammonium fluoride. A light microscope examination showed a dark residue, whose nature remains unknown.

PART NO. 990092

RUN NO. _____ DATE <u>11-8-78</u>	T-AXIS	DTA-DSC	TGA	TMA
OPERATOR <u>DM</u>	SCALE, mv/in. <u>0.8</u>	SCALE, °C/in. <u>4.0</u>	SCALE, mg/in. <u>~12</u>	SCALE, mils/in. _____
SAMPLE <u>AMMONIUM FLUORIDE</u> <u>NH₄F</u>	PROG. RATE, °C/min. <u>2.5</u>	(mcal/sec)/in. _____	SUPPRESSION, mg _____	MODE _____
ATM <u>AIR</u> @ _____	HEAT COOL ISO _____	WEIGHT, mg _____	WEIGHT, mg <u>8.5</u>	SAMPLE SIZE _____
FLOW RATE <u>3 CU FT / HR</u>	SHIFT, in. <u>0</u>	REFERENCE _____	TIME CONST. sec _____	LOAD, g _____
			dY, (mg/min) / in _____	dY, (10X), (mils/min) / in _____

Figure 7. SiO_2 3000Å thick on silicon, left half of photomicrograph. Right portion etched by ammonium fluoride NH_4F at 600°C . Taken on Cambridge SEM at 1700X.

8.0 Ammonium bifluoride (NH_4HF_2)

Figure 8 shows the TGA/DTA traces of ammonium bifluoride to be very similar to those of ammonium fluoride. The action upon silicon dioxide was also similar, and therefore no electron micrograph is shown.

9.0 Teflon^R

Figure 9 shows the TGA/DTA trace for Teflon^R. The continuous rise in the TGA trace is possibly due to the aerodynamics of a different crucible, experiencing lift in the chimney of the apparatus, which would be interpreted as weight loss. Melting occurs at 320°C (DTA) and decomposition is apparent from the

PART NO. 990092

PART NO. 990092

weightloss beginning at 500°C and being complete at 630°C.

Figure 10 is an SEM photo of the interface of the attacked versus the non-attacked portions of the oxidized wafer. Optical microscopy again revealed a considerable amount of residue. There is an indication on the SEM that the silicon surface may have been attacked as shown in the apparent cratering on the left side of the photo.

Figure 10. SiO_2 3000 Å thick on silicon, right half of photo. Left half etched by decomposed Teflon^R at 600°C. Taken on Cambridge SEM at 1600X.

10.0 Silver fluoride AgF

Only a small quantity of silver fluoride was obtained due to its rather high price (over \$6/g). It was later established that this high price is not warranted by material and labor costs.⁴ An attempt to obtain electronmicrography of a silver fluoride grain proved to be impossible as the 10 KeV (100 μ A cathode current) electron beam decomposed the specimen grain in considerably less than a minute at 1000X magnification.

Figure 11 shows an SEM photo of a typical silver grain resulting from AgF dissociation at 500⁰C on an oxidized silicon wafer. Magnification is 4000X. It can be seen that a moat has been carved out of the silica around the original silver fluoride grain. The resulting silver blob has thinned down markedly near its periphery, making a low contact angle with the silicon, a condition expected when good wetting is demonstrated.⁵ The continuous metal surface is probably due to the catalytic action of the very fine particles generated by the decomposition of the silver fluoride, as well as the catalytic action of the freshly exposed silicon crystal surface. To verify the nature of the deposited material, a series of photomicrographs was taken at increasing magnification. The backscatter mode of the Cambridge SEM was employed, providing a higher yield of electrons from the surface of materials with a high atomic number relative to the darker background (Ag Z=47 : Si Z=14). Figure 12 shows a different portion of the same sample from which Figure 11 was taken, at 1600X magnification. Figure 13 shows a portion of Figure 12 at 3700X magnification, again employing the backscatter

mode. Figure 14 shows the same region as Figure 13, but as a silver elemental map using the L_{α} (2.98 KeV) line X-ray fluorescence. The open areas on the solid silver portions are due to the finite integration time utilized. The sparse number of dots, where no silver is expected, is from noise and possibly some contamination.

Figure 11. AgF on SiO_2 (3000 Å thick) at 500°C. Vicinity of reduced silver shows etching action on SiO_2 . Good wetting is indicated by low angle of periphery profile. Cambridge SEM at 4000X.

Figure 12. Different portion of same sample as above. Taken in back-scatter mode at 1500X. Cambridge SEM.

Figure 13. Same sample as Figures 12 and 11 (AgF) taken in backscatter mode on Cambridge SEM at 3700X.

Figure 14. Same sample as Figure 13 showing silver map of region above. Cambridge SEM 3700X 2.98KeV $L\alpha$. Integration time 1000 sec.

Figure 15 shows the pressure in atmospheres over silver fluoride at various temperatures. The curves were plotted from the two equations⁴ shown on the figure.

In addition to the above, the following were tried, all at a temperature of 600°C.

Aluminum fluoride AlF_3

Zirconium hydride ZrH_2

Titanium hydride TiH_2

There was no evidence of oxide removal discernible in the above materials.

Zinc fluoride ZnF_2

The zinc fluoride was evidently effective in removing the silicon oxide, however, it left behind a large amount of dark residue, probably ZnO . Since the other materials showed more promise, it was decided to abandon the above.

Fig.15

VAPOR PRESSURE OVER SILVER FLUORIDE

PRESSURE
(Atm)

Fig.15 Vapor pressure over a) liquid silver fluoride (AgF) and
b) solid silver fluoride (AgF)

(a) above liquid AgF $\ln P_{\text{atm}} = -0.937 \cdot 10^4 / T_0 K + 4.78$
for $854^\circ < T < 1024^\circ K$
(experimental, from reference 6)

(b) above solid AgF $\ln P_{\text{atm}} = -1.023 \cdot 10^4 / T_0 K + 10.07$
for $T \leq 708^\circ K$
(calculated, from reference 6)

11.0 Silver Paste Experiments

Approximately twelve different experimental pastes were fabricated. The initial paste, consisting of 5 wt%^{*} AgF and 95 wt%^{*} silver powder of particle size $\sim 0.1\mu\text{m}$ gave good results, but had poor initial rheological properties and continued to deteriorate. This was most likely a function of the extremely small particle size which provides a large area of grain surface, which in turn reduces the lubricating action of the resin binder causing the viscosity to increase.

Subsequently, a coarser silver consisting of powder and flakes was used and a masterpaste was compounded. The masterpaste contains the normal ingredients of metal powder and binder and allows the rapid preparation of a series of pastes to which only the silicon oxide scavenger is added.

Inks containing ammonium fluoride, bifluoride and Teflon^R had inadequate adhesion at all temperatures tried (600°C to 750°C.) The criterion was our ability to scrape the electrode off with a single-edged razor blade. In another test, 0.1" squares were soldered with 63-37 tin lead solder. Leach resistance was good and all samples were quickly wetted with solder. However, the Teflon^R additive electrodes could be pried off the wafer after soldering, in contrast to the silver fluoride electrodes. Coverage of the silver fluoride compounded electrodes looked good.

Figures 16, 17, 18, and 19 show a sequence of SEM photos of S012 ink paste prepared with 10 wt% added AgF fired at 750°C for five

* Here and throughout report, % refers to wt% of ink solids, only.

minutes. Figure 16 was done at the low magnification of 17X. Figure 17: 420X magnification, Figure 18: 1700X magnification, Figure 19: 4200X magnification. The ridges on the print in the Figures 16 and 17 are due to the paste rheology. It should be noted that the addition of Teflon^R powder had a beneficial effect upon the ink rheology. Figures 18 and 19 show that there is a considerable sintering action in this all metal ink even though no liquid phase sintering medium was used. This may be due to the finely divided silver particles from the AgF dissociation.

On the other hand there is considerably less visible wetting action in these photos. It is plausible that wetting occurs under the grains and the tenacious adhesion tends to support this view.

It is interesting to compare the sintering action obtained in this experiment with that on a production solar cell (Figure 20) employing a commercial lead oxide based glass frit ink. The magnification of the glass frit sample is almost twice that of the all metal system (8000X: 4200X) and the grain development and interlocking are excellent. The firing temperatures of the two inks are comparable. (All metal ink: 750°C, commercial fritted ink 700°C).

12.0 FURTHER EXPERIMENTS

In order to eliminate the Schottky type barrier referred to in.

the next section under electrical measurements, a paste (S018) was prepared containing 3 wt% boric acid (H_3BO_3) in addition to 5 wt% silver fluoride (AgF) and screened onto p-type wafers of 1 to 3 Ωcm solar cell material. The resistance measurement indicated the barrier to be attenuated (refer to electrical measurements). Subsequently, a wafer with the boron containing ink along with an identical screened contact except for the boron addition (S009) was boiled in de-ionized water for one hour. Both wafers were then subjected to an adherence test involving an Exacto knife. The contact with the H_3BO_3 addition could be scraped off with little difficulty whereas the "undoped" contact survived the test.

Figure 16. Print with SO12 (10% AgF). Pads are 0.100" X 0.100" spaced 0.050", on polished silicon. Fired at 750°C temperature peak for 5 min. Cambridge SEM at 17X.

Figure 17. Same as Figure 16 magnification 412X. Ridges are reproduction of screen mesh.

Figure 18. Same as Figures 11 and 12 except magnification 1700X. Note contiguous grain showing dense sintering.

Figure 19. As above except magnification 4200X. Well-knit structure.

Figure 20. Solar cell metallization with conventional fritted silver ink done with Cambridge SEM at 8000X magnification.

A number of temperature runs were made on S018 (5 wt% AgF, 3 wt% H_3BO_3) to observe sintering action and attendant grain growth as a function of temperature. The belt speed was held constant throughout the experiment and previously printed wafers were fired at 50°C intervals from 500°C to 750°C. All specimens were analyzed with an SEM at 3000X magnification. Unfortunately, a malfunction in the SEM produced images of poor quality, but the salient features of the effect of temperature increase on the grain size and fit are strikingly shown in Figure 21 a,b,c,d,e, and f. It is shown that there is an apparent reversal at 750°C in the trend in going from Figure 21a at 700°C to Figure 21f at 750°C. Since it is unlikely that the samples were interchanged, it is assumed that the grain size was in saturation, and the anomaly is due to local variations in screening parameters--possibly a site near the edge of a pad.

While this may be another example of a matured, all metal, sintered contact, it is possible that the boric acid doping agent serves the dual function of doping agent and non-metal liquid sintering medium. This comes about due to the large ratio in densities of silver/boric acid which increase the atomic percentage to 22 at%.

(a)

(b)

(c)

(d)

(e)

(f)

Figure 21. a) Paste S018 (with 5 wt% AgF and 3 wt% H_3BO_3) on silicon substrate, magnification 3000X, belt speed 12 cm/min, fired at 500°C b) same as (a) except fired at 550°C c) same as (a) except fired at 600°C d) same as (a) except fired at 650°C e) same as (a) except fired at 700°C f) same as (a) except fired at 750°C.

In order to determine whether the silicon surface is attacked by the hot fluorine gas during the silver fluoride decomposition, we cleaved several printed, fired silicon strips. The paste, S012, was chosen to contain 10 wt% of silver fluoride and was fired at 750°C to exaggerate the effect. Wafers were scribed and broken along the (110) plane both in room temperature air and under liquid nitrogen, to forestall smearing of the silver-silicon interface. The room temperature cleave gave a cleaner profile, with the results shown in Figure 22 a,b,c. (A) shows the edge of the print (toward the right side of the photo) at 1150X magnification. Due to the lacy nature of sintered paste contacts there are several areas at the edge where the silicon is not covered with silver. This results in highlighting or haloing the edge which is, in fact, a diffraction effect, but cannot be ascribed to a penetration since the silver fluoride is specifically absent from those areas.

The rectangle in Figure 22a shows the portion enlarged in Figure 22b and 5700X. An empty spot exists at the lower left extreme of the photo. Similarly, a rectangle shows the field of view seen in Figure 22c at 11,500X. Since the smallest distances that can be clearly resolved in this photo are less than 0.1 μ m, there do not appear to be any macroscopic penetrations into the silicon surface in the vicinity of the pad. Ten such areas were examined with similar results.

(a)

(b)

(c)

Figure 22. a) Profile of room temperature cleaved silicon printed with silver paste S 012 containing 10 wt% AgF fired at 750°C, belts speed 12 cm/min at 1150X magnification. Rectangle indicates area covered by b) 5700X magnification. Rectangle indicates area covered by c) 11,500X magnification.

13.0 Electrical Characteristics

None of the silver electrodes resulting from the various pastes applied to N-type silicon gave linear or ohmic current-voltage behavior. Low voltage resistance between pads 0.1" square with a separation of 0.050" gave in the tens of megohms. Wafer thickness and resistivity were 0.020" and 5 Ω cm. Similar results were seen for P-type material with wafer resistivity 1-3 Ω cm.

Curve traces of pairs of electrodes resulted in very horizontal regions near the origins, symmetrically disposed and steepening to read 0.5 mA at 4 volts. While the contacts were not ohmic, they did not represent good Schottky barriers, but were rather somewhere between. This was found during several attempts to obtain a definitive barrier height. During one such attempt, we tried to measure the capacitance versus bias voltage on a small signal 1 MHz capacitance bridge. The results, when plotted as $1/C_V^2$ (where C_V is the capacitance in picofarads) against the applied bias voltage (V) did not yield the expected straight line whose slope specifies the carrier concentration and whose intercept provides the Schottky diode internal voltage. A further try was performed by Rockwell International Science Center, Thousand Oaks, California through the kindness of Dr. Marshall Cohen, with similar results, presumably for the same reasons. Small square pads $(.05\text{cm})^2$ measured in this fashion gave approximately 120 pF capacitance or 0.05 $\mu\text{F}/\text{cm}^2$.

To reduce the leaky Schottky barrier, the paste (S018) discussed in the previous section (3. Further Experiments) was prepared

with a boron addition. The results of the measurements were variable, yielding a reduction in resistance for some electrodes of three orders of magnitude and for others of only one.

14.0 Conclusions and Problems

Good metallurgical contacts have been produced on silicon substrates utilizing all metal ink pastes including 5 wt% (solids) silver fluoride. The basic concept of all metal or glass fritless inks has been demonstrated in the silver system. This can be done at temperatures of 700° to 750°C, without the use of a low melting metal component providing a liquid sintering medium, due to the fine grain metallic silver furnished by decomposing silver fluoride. The silver fluoride wetting action on the freshly etched silicon surface gives contacts with excellent adhesion.

Three solid materials capable of removing SiO_2 from silicon at moderate temperatures have been found. While both Teflon^R and ammonium fluoride-bifluoride effectively remove silica, poor adhesions results when they are used in silver pastes. We believe this to be due to the activation temperatures being too far from the ink sintering temperatures. This causes the silicon to re-oxidize before the silver has a chance to wet it. Electrically, silver deposited from silver fluoride appears to create a leaky Schottky barrier, resulting in non-ohmic contacts.

Considerable difficulties were experienced due to shipping delays by suppliers of silver fluoride, or because of receipt of inferior product, usually caused by inadequate packaging. This caused the silver fluoride to be wet upon arrival and rendered it unusable. The supplier believes he has corrected this problem.

15.0 Plans and Recommendations

During the next quarter the following efforts will be made:

1. Experiments with all metal pastes including low melting point metal components to achieve firing temperatures in the 550°C to 650°C range.
2. Experiments with all metal pastes with ingredients designed to produce good ohmic contacts to N and P-type silicon substrates of modest resistivity.
3. Solar cells will be screened with all metal pastes judged to be the best produced to date, to determine the extent of problems yet remaining.
4. Generation of cost data.
5. Continued efforts with manufacturers and vendors of silver fluoride.

REFERENCES

1. "Constitution of Binary Alloys", M. Hansen and K. Anderko, 2nd edition, page 40, McGraw-Hill, New York, NY, (1958).
2. Handbook of Chemistry and Physics, 56th edition, CRC Press, Cleveland, OH, (1975-1976), Page B-138 S147.
3. Gmelin's Handbuch der Anorganischen Chemie 8. Aufl. Teil B3, page 146 (1973).
4. H.C. Urey, The Merck Index, page 948, 8th edition, P.G. Stecher, Ed. Merck & Co. (1968).
5. I.A. Aksay, C.E. Hoge, J.A. Pask, J. Phys. Chem. 78, page 1178, (1974)
6. K.F. Zmbov and J.L. Margrave, J. Phys. Chem. 71, page 446, (1967)

16.0 Progress on Program Plan