JAN 03 1992

DOE/PC/91334--T14

DE92 007878

QUARTERLY REPORT

September 1, 1991 through November 30, 1991

Project Title: **CLEAN, PREMIUM-QUALITY CHARS: DEMINERALIZED
AND CARBON ENRICHED**

DE-FG22-91PC 91334

Principal Investigator: Gerard V. Smith
Molecular Science Program
Southern Illinois University
Carbondale, IL 62901
(618) 453-7319

Other Investigators: Vivak M. Malhotra
Department of Physics
Southern Illinois University
Carbondale, IL 62901

Tomasz Wiltowski
Molecular Science Program
Southern Illinois University
Carbondale, IL 62901

Project Monitor: Frank Honea

ABSTRACT

The interaction of methane, hydrogen, helium, oxygen, and methane/oxygen with IBC-102 coal sample has been investigated in a thermogravimetric reactor at 20°C-650°C. The results show that above 370°C the reacting gases (except helium) dissolve in the softened coal and/or react with the mineral matter present in the coal. At a higher temperatures, the weight difference under reacting gases and helium start to decrease indicating that gasification process predominates. Comparison of relative reactivities using derivative TGA profiles (DTG) show that the rate of weight changes start to increase at approximately 370°C and reached maximum at 470°C. Differential Scanning Calorimetry (DSC) experiments show that for both IBC-102 coal alone and mixed with smectite, there are four thermal effects attributed to different processes occurring during coal gasification. ISDR-FTIR measurements suggest that the carboxylic groups may play an important role in the cross-linking process of coal, thus, the yield of chars.

MASTER

This project is funded by the U. S. Department of Energy (METC) and by the Illinois Department of Energy and Natural Resources as part of their cost-shared program.

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

EXECUTIVE SUMMARY

The goal of this project is to develop a process that can produce a clean, desulfurized, premium-quality char from Illinois basin coal. This goal is achieved by utilizing the effective capabilities of smectites in combination with methane to manipulate char yields. The general objectives are to determine the optimum particle size of the coal in this process, to find the type of smectite and the method of its dispersion on the coal surface, to find the best conditions of sulfur removing from the char under the combination of methane/oxygen or helium/oxygen, and, finally, to identify the conditions for smectites rejection from char by the gravitational separation technique.

The experiments were performed with IBC-102 coal using three different techniques: thermogravimetric analysis (TGA) including differential thermogravimetric (DTG), differential scanning calorimetry (DSC), and in-situ diffuse reflectance-FTIR (ISDR-FTIR).

The TGA results showed that all reacting gases (methane, hydrogen, methane/oxygen, and oxygen) dissolved in the softened coal and/or reacted with the mineral matter of the coal, resulting in slower than helium devolatilization between approximately 370° and 460°C for methane and hydrogen, and 520°C for methane/oxygen and oxygen alone. Above these temperatures, the weight differences under these gases and helium started to decrease.

The DSC were performed with IBC-102 coal alone and mixed with smectite. The thermographs for both samples showed four thermal effects attributed to four different processes during coal heating such as dehydration of coal and smectite (if present), cross linkage, and mild gasification. Smectite addition showed substantial effects on the cross-linkage temperature but did not change the maxima at mild gasification temperatures.

ISDR-FTIR spectra of IBC-102 were taken at five different temperatures: 20°C (293 K), 250°C (523 K), 301°C (574 K), 401°C (674 K), and 477°C (750 K). The results of these measurements strongly suggest the carboxylic groups present on the coal surface may play an important role in the cross-linking process, thus, on the yield of char.

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

OBJECTIVES

The goal of this project is to develop a bench-scale procedure to produce clean, desulfurized, premium-quality chars from the Illinois basin coals. This goal is achieved by utilizing the effective capability of smectites in combination with methane to manipulate the char yields. The major objectives are:

- to determine the optimum water-ground particle size for the maximum reduction of pyrite and minerals by the selective-bitumen agglomeration process
- to evaluate the type of smectite and its interlamellar cation which enhances the premium-quality char yields
- to find the mode of dispersion of smectites in clean coal which retards the agglomeration of char during mild gasification
- to probe the conditions that maximize the desulfurized clean-char yields under a combination of methane+oxygen or helium+oxygen
- to characterize and accomplish a material balance of chars, liquids, and gases produced during mild gasification
- to identify the conditions which reject dehydrated smectites from char by the gravitational separation technique
- to determine the optimum seeding of chars with polymerized maltene for flammability and transportation

INTRODUCTIONS AND BACKGROUND

The carbonization process of coal is a well-established technology^{1,2}, next only to the combustion utilization of coal, though its economic viability has considerably eroded due to the competition from other relatively cheap energy sources. Therefore, recent emphasis in the development of the carbonization process has been to recover liquids and gases from the coal, under mild gasification and gasification conditions, which can act as chemical feed-stock¹⁻¹⁶. Far less effort¹⁷⁻²¹ has been devoted in developing technology for producing enhanced yields of char or premium-quality char from coals. If the mild coal gasification process is to be commercially successful, then the production and utilization of clean, premium-quality chars are mandatory.

The high sulfur content, both inorganic and organic sulfur, of the Illinois bituminous coals in general and the high mineral content of some Illinois coals present significant hurdles for their effective, economical, and environmentally-acceptable utilization. This is especially true for the mild gasification of Illinois coals since it results in by-products, both liquids and solid, which have an environmentally unacceptable sulfur content. Additionally, the high ash content (for example, 10.4% in IBC-101 coal or 38.3% in IBC-104 coal) of Illinois coals may actually dilute the coal to such an extent that the coking properties of the coal are markedly diminished¹. Also, chars rich in minerals foul the catalytic promoters via catalytic-material-mineral reactions in the gasification process²². Therefore, it is imperative that prior to subjecting the Illinois coals to the mild gasification process to produce chars and liquids, the coal must be physically cleaned to reduce considerably the mineral and pyrite content.

The removal of pyrite and other minerals from Illinois bituminous coals have proven to be a vexing problem to coal preparation engineers. Most advanced, mechanical coal cleaning processes take advantage of the differences in the surface properties of minerals and organic coal in removing pyrite and other minerals. These processes (e.g., aggregate flotation, aglo-float process, static tube flotation, selective-froth flotation, microbubble flotation, air-sparked hydrocyclone, ultrasonically enhanced flotation, reverse coal-pyrite flotation, and the Otisca process) add surfactants, frothers, and surface-active polymers to separate minerals from coals^{23,24}. Unfortunately, the mechanical-coal cleaning processes have had only limited success²⁴ in rejecting pyrite from bituminous coal. In the aforementioned coal-cleaning processes, external additives are supplied to coal feed to selectively enhance the floatability of organic coal relative to minerals, and this results in the adsorption of additives on the surface of cleaned coal particles. The adsorption of additives will have serious repercussion during mild gasification.

The thermal decomposition of coal is a complex sequence of events, which can be described in terms of several physicochemical changes, e.g., it has been suggested¹³ that weak tar formation appears at about 350°C from volatilization of low molecular weight coal constituents, and this event is followed by major tar yields at 400°-450°C. It is also known¹, that certain coals become soft and flow when heated to 400°-600°C, where thermal depolymerization occurs with the release of liquids and gases. If surfactants and/or polymer additives are present on the surface of clean coal, then during the mild gasification process these additives will act as effective sites where cross-linking will agglomerate the coal particles and incorporate deleterious additives into the char, which may further retard the effective utilization of the chars. Consequently, the coal cleaning process employed to produce clean coal feedstock for mild gasification of coal must not include additives which can retard the mass transport.

In order to remove pyrite and other minerals from coal it was found²⁵ that prior to cleaning process, coal has to be ground with water. This wet grinding resulted in the formation of hydrated-sulfate species on pyrite, irrespective of their location. Additionally, it was observed that grinding the coal under water inhibited the coal's oxidation. This fact should further attenuate the cross-linking of coal under mild gasification¹³.

The chars produced from the clean coal can be upgraded by treatment with methane, which desulfurizes the char and deposits carbon on the coal surface. Desulfurization occurs chiefly from the interaction of methane with pyrite³⁶:

However, considering the fairly ready transfer of sulfur between the inorganic (mineral) and organic phases³⁷, desulfurization of the organic phases probably also occurs. In view of our previous study we strongly believe that when clean coal obtained from the selective bitumen agglomeration process, is subjected to mild gasification under the mixture of CH₄ with 2%O₂, a further reduction of the sulfur in char will occur. The combination of methane and oxygen gas will not only reduce the sulfur content of the remaining pyrite but also will eliminate organically bound sulfur.

Deposition of carbon from methane decomposition on chars may occur in an amorphous form with the extremely high surface area and in a filament form with high mechanical strength. These filaments grow from small crystallites of metals,^{38,39} which can be produced in the char.

Carbon may be deposited from methane by the action of high temperatures and/or metal catalysts⁴⁰ as well as carbon.^{41,42} High temperature deposition of carbon leads to either amorphous (soot-like)^{41,42} or graphitic carbon⁴⁰ depending on the presence and kind of sur-

face available. These carbons, especially the amorphous carbons, have very high surface areas. On the other hand, filamentous carbons have moderate surface areas but high mechanical strength. A modification of carbon filaments, "cauliflower-like" graphitic structures³⁹, exhibit moderately high surface areas.

Graphitic filaments of carbon and "cauliflower" graphitic structures are formed from essentially the same process, that is, by the decomposition of methane on Fe, Co, or Ni surfaces. On small crystallites, which are called "growth" crystals, catalytic decomposition of methane to carbon and hydrogen occurs at one of the crystal faces. The carbon so formed then diffuses through the crystallite and re-emerges at the opposite surface to form a hollow graphitic filament with a diameter approximately the size of the metal crystallite.³⁸ On larger crystallites "cauliflower-like" eruptions of graphitic carbon occur.³⁹ The fibers possess high mechanical strength⁴³ which they can impart to the char, and the "cauliflower" structures have fairly high surface areas. In this way methane treatment can upgrade char by desulfurizing it, by producing Fe⁰ "growth" crystallites, and by growing carbon filaments and/or graphitic "cauliflower" structures.

To determine the feasibility of decomposing methane on char a preliminary experiment was performed in the following way. In the microbalance reactor 61.945 mg of coal No. 106 were devolatilized to constant weight (47.652 mg) under flowing helium at 600° C then the gas was switched to methane. Upon first contact with methane the char decreased in weight to 47.559 mg in 22 minutes and then increased to 49.250 mg in 19 hrs. We assume that the weight decrease upon initial contact with methane was due to reduction of residual iron pyrite; however, that has not been established. We know from ongoing research that methane reacts with coal char to produce chemicals, so the weight decrease could be a chemical reaction(s) between the char and methane to produce vaporizable organic molecules. Nevertheless, the subsequent weight increase can only be due to carbon deposition on the char.

With this knowledge in hand we tested desulfurization ability and BTU increase by preparing two more samples from coal No. 106 in the plug flow reactor. One sample was treated with helium for 16 hrs at 500° C and the second sample was treated with methane for 19 hrs at 500° C. These samples were analyzed by Cephus Industries, Inc. of Marion, Illinois with the results shown in Table 1.

Table 1
BTU and S Contents of Chars from IBCSP Coal No. 106
Treated with Helium and Methane at 500° C

	after He	after CH ₄
BTU	11738	14503
%S	3.49	1.39

BTU content is 23.5% larger for the methane-treated than the helium-treated sample. Moreover, since the original coal had a reported value of 13226, the methane-treated sample has a 9.7% larger BTU value than the original coal. And sulfur content is substantially smaller also. The original sulfur content of the coal was 3.77% (0.01% sulfatic, 1.86% pyritic, and 1.90% organic). Helium treatment reduces it by 7.4% while methane treatment reduces it by 63.1%. This latter substantial reduction in sulfur is large enough to account for all of the pyritic sulfur and 26.8% of the organic sulfur.

Since the formation of free radicals by the rupture of coal bonds during mild gasification is believed to be an important step in the production of liquids and chars, we have recently attempted to enhance the yields of chars from IBCSP-104 coal using free radical promoters. It is well known that pyrite⁴⁴⁻⁴⁶ plays a critical role in generating free radicals in coal at about 500°C. Though pyrite act as a catalyst in promoting free radicals in coal, and thus may help in better polymerizing the coal, it unfortunately adds sulfur into the char. Also, pyrite does not retard agglomeration of the char during mild gasification. Therefore, any free radical promoter added to the clean coal should not only affect the free radical concentration but should also inhibit the agglomeration of the char.

It is well known that clay minerals display a number of catalytic activities including polymerization, desulfurization, cracking, and hydrogenation⁴⁷. Yet the role in mild gasification has been ignored. Granted that mineral matter in coal contains a significant amount of kaolinite and illinite clays, however, it is the naturally occurring smectites which display enhance catalytic activities due to their very large surface area and uncompensated edge structures. The EPR measurements⁴⁵ performed under vacuum showed that montmorillonite is effective promoters of free radicals in coal at about 500°C. Our recent, preliminary mild gasification experiments on IBC-104 coal with various cation exchange smectites revealed that all smectites, when appropriately dispersed in coal retarded the agglomeration of the char at 500°C under CH₄/O₂ mixture, and depending upon the exchanged cation of the smectite or type of smectite, the yields of liquids and chars were selectively enhanced.

EXPERIMENTAL PROCEDURE

Materials

Coal sample IBC-102 was obtained from the Illinois Coal Basin Coal Sample Program (IBCSP). It contains 39.8% of volatile matter, 6.9% of ash, 14.2% of moisture, and 3.29% of sulfur. Before the experiments, the coal sample was first ground in a planetary ball-mill to reduce its particle size to < 75 µm. Then, this < 75 µm particle-sized coal was further ground under water in a micro-rapid Brinkman mill to reduce its particle size to < 37 µm. The water-ground coal was dried at 24°C under flowing nitrogen and then sieved to recover the < 37 µm particle-sized coal.

In order to examine the catalytic effect, if any, of smectite minerals on the cross-linkage process of coal, the following procedure was adopted to prepare the coal-smectite mixture: (i) The < 37 µm particle-sized coal and Ca-montmorillonite (Cheto, Arizona) were accurately weighed in order to produce a mixture which had a coal-to-montmorillonite ration of 2:1 (by weight). The methanol was added to the coal-montmorillonite mixture, and the mixture was vigorously stirred in an attempt to produce a homogeneous distribution of coal and smectite within the mixture. After about one hour of agitation, the methanol was removed from the sample by subjecting it to a vacuum.

The methane (UHP grade), helium, hydrogen, and oxygen were obtained from MG Industries, Scientific Gas Division. The mixture of 2% of oxygen in methane or in helium was prepared by mixing the proper amounts of the gases. The gases were dried over an activated molecular sieve trap. Methane, helium, and hydrogen were further purified by flowing them through a Mn/SiO₂ trap in order to remove oxygen.

Apparatus

Temperature programmed reactions of coal under different environments were performed using a Cahn 113 microbalance reactor. It consists of a quartz-tube reactor with an inner

diameter of 22 mm heated in a split-shell furnace, a quartz bucket for the coal sample, and auxiliary equipment for introduction and metering of gas flow. Flow of gases (28 mL/min) was maintained by micrometer valves and monitored by Sierra Top Trak model 821S2 mass flowmeters. An auxiliary helium feed (10 mL/min) system was used for purging the "vacuum" bottle containing the motor assembly of the microbalance. The temperature control system utilizes a Micricon 823 computer connected to a thermocouple suspended just below the sample pan. The weight change signal is digitized by the IBM compatible computer using a locally developed data acquisition program/display and stored for further evaluation. Normally, the coal samples were pretreated for 12 hrs at room temperature under flowing reaction gas to obtain a constant weight. Each experiment was performed at 20°C-650°C with a ramp of 10 deg/min.

Before the kinetic results were calculated, the data were normalized. The normalization procedure accounts for the effect of temperature on the volume flow of the gases as well as recalculation of the results to the same initial weight for each sample. This was done in the following way. Several blank tests were performed with crushed glass loaded in the microbalance under flowing helium at elevated temperatures. The weight "loss" of this sample (which is due only to changes of the volume flow of the gas) was subtracted from each experiment. Therefore, the weight losses of coal samples are due only to the removal of the volatile materials because weight changes due to temperature and gas density changes are removed.

Calorimetric data under pyrolytic conditions were recorded on a Perkin-Elmer DSC7 system, interfaced with a Perkin-Elmer 7700 computer. The DSC was calibrated for temperature and enthalpy, applying the procedure reported in the literature⁴⁹⁻⁵¹. The temperature calibration was performed by the two-point method, using the melting transitions of indium (430 K or 157°C) and zinc (693 K or 420°C). The accuracy in temperature between 300 K and 693 K, based on our calibration procedure, was estimated to be ± 1 K. The enthalpy calibration was performed using indium heat of fusion as the standard. After the enthalpy calibration, the DSC data on zinc metal were re-recorded, and the observed enthalpy of the melting transition of zinc was consistent with the values reported in the literature. The conditions under which the instrument calibration was performed exactly matched the experimental conditions, namely the scan rate of 10 K/min., helium purge at 0.207 MPa pressure. Also, during both calibration and pyrolysis runs, the dry box assembly over the sample head was flushed with nitrogen gas to maintain thermodynamic equilibrium. Aluminum sample pans, in an unsealed mode, were generally used to probe the pyrolytic behavior of coal. This was achieved by pushing down the top sample pan cover gently onto the bottom pan containing the coal. Typically 30 mg of sample were used for our DSC measurements.

For In-situ Diffuse Reflectance-FTIR (ISDR-FTIR) measurements, $< 37 \mu\text{m}$ particle-sized coal sample was placed in a vacuum chamber mounted in a diffuse reflectance center-focused accessory in the optical compartment of the Nicolet 740 FTIR spectrometer. The spectrometer was linked to a Nicolet 620 computer and was fitted with a high sensitivity MTC detector. The vacuum chamber had potassium bromide optical flats and was connected via a flexible, stainless steel tube to a vacuum pumping station. Two hundred scans at a resolution of 4 wavenumber were collected at each desired temperature. The heater assembly, mounted underneath the sample cup containing the coal, was used to alter and control the sample temperature to ± 2 K. At present our ISDR-FTIR system is capable of operating at $27^\circ\text{C}(300 \text{ K}) < T < 500^\circ\text{C}(773 \text{ K})$.

RESULTS AND DISCUSSION

Non-isothermal reactivities

As was mentioned in the experimental part of this report, the coal samples were heated in the reacting environment at a rate of 10 deg/min up to 650°C. The weight losses were continuously recorded and, at the end of each experiment, were calculated, normalized, and plotted. The curves of the percentages of weight loss versus temperature for IBC 102 coal reacted with the different gases are shown in Figures 1-5. Figure 6 shows the plots of the rate of weight loss for the coal sample treated with different gases. The characteristic of the rate of the weight loss curves may be interpreted as follows: 1) At low temperature there is an initial weight loss as moisture is being removed. 2) As the temperature is raised, the weight of the coal decreases, however the rate of the weight loss for each gas is constant till 250°C is reached. 3) As the temperature continues to increase, the weight continues to decrease until the maximum of the weight loss rate is observed. After that, the rate of the weight loss decreases, possibly due to the fact that the reacting gas has fully permeated the entire coal bed. Thus, with increased conversion and pore enlargement the weight loss rate may shift between the intrinsic-reactivity-limited to the mass-transport-limited region. Another suggestion to account for this observation is that at low temperature, the release of volatile matter is slow. However, at elevated temperatures, volatile-matter release is rapid reaching the maximum rate at a certain temperature. Simultaneously, this rapid devolatilization process causes blocking of the entrance of the reacting gases into the pore system of the coal. Also, it is interesting to note that regardless of the reacting gas, the maximum rate of weight loss is observed at 460°C. Additionally, the higher maximum reaction rates were observed for hydrogen, methane, and methane with oxygen. By contrast, the lower maximum reaction rate was observed for oxygen. It may be suggested that coal agglomerates under flowing oxygen more than under other gases. This agglomeration prevents diffusion of the reacting gas into the structure, and thus causes lower reactivity.

Comparison of non-isothermal reactivities (Temperature Programmed Pyrolysis)

In order to compare the reactivity of coal samples under different environments, the results from each experiment were normalized for the same initial weight. The weight change under helium was subtracted from the weight changes under CH_4 , H_2 , O_2 , and CH_4/O_2 . The resulting plots are shown in Figure 7. No difference in devolatilization by hydrogen, methane/oxygen, oxygen, and helium is observed until approximately 370°C. However, methane devolatilizes slightly faster than He until the same temperature is reached. As the temperature increases, devolatilization rates decrease relative to the He devolatilization rate. This decrease in rates continues up to approximately 460°C for methane and hydrogen and 520°C for methane/oxygen and oxygen alone. Above these temperatures, the weight differences under these gases and helium start to decrease.

The presence of these four gases has a similar effect on coal during heating which is not exhibited by He. It was hypothesized in our previous report⁴⁸, that this effect may be related to the fact that these gases are converting some of the mineral matter into catalysts through a chemical reaction which causes the observed increase in weight. Once these catalysts are formed, they enhance devolatilization processes. This explanation can be supported by our previously presented results⁴⁸, where similar experiments were performed with IBC-104 coal samples. When comparing these results, it may be seen that the effect of H_2 , CH_4 , and CH_4/O_2 was greater for that coal than for presently used IBC-102 coal. One of the differences between these two coals is the mineral matter concentration, IBC-104 contains 38.4% ash, whereas IBC-102 contains only 6.9%. Thus, the amount of the active catalyst formed

during the devolatilization should be larger in the case of IBC-104 coal. The weight loss above these critical temperatures (460°C and 520°C), when the maximum in the difference between helium and other gases was reached, is related to the amount of the catalyst present in the coal. In the previous paragraph we stated that after reaching the maximum rate of the weight loss, the mechanism of the reaction may switch between intrinsic region and mass-transport region. In the intrinsic region, there are several factors controlling the rate. One of these is the catalytic effect of minerals, others are the surface area and active site density. Thus, for the IBC-104 coal (which contains more minerals than IBC-102 coal) the differences between the experiments with methane, hydrogen, or methane/oxygen and helium should be greater, according to the reasons explained above.

Differential Scanning Calorimetry (DSC) measurements

Figure 8 presents the observed DSC thermograph, obtained under helium purge, at 313 K < T < 863 K of < 37 micron particle-sized IBC-102 coal. Four thermal events can be recognized from Fig. 8. The first thermal event, manifested as a very broad peak centered around T < 361 K, can be associated with water loss from the coal. The broad peak at 361 K is asymmetric, starting at 321 K and ending at 413 K, and signifies the desorption of water from coal via a complex combination of desorption mechanisms^{50,52}. The significance of the weak exothermic event located at 540 K is not evident to us at present. However, it is worthwhile to point out that the exothermic event at 540 K for the IBC-102 coal is not an experimental/instrumental odd effect since persists when the measurement is repeated.

A third thermal event, in the form of a broad peak around 627 K, can clearly be seen from Fig. 8. Lucht et al.⁵³, from their DSC data on fresh coals, argued that the thermal process at 630 K suggests the existence of a glass-to-rubber transition for coal. However, their reported DSC thermograph is not consistent with a typical glass-to-rubber transition behavior. It is well known that when glass transforms to rubber, molecular chain mobility increases. This implies that the molecular chains are more free to vibrate and, therefore, will absorb more heat. Consequently, in a DSC experiment, increased heat will be supplied to maintain the constant heating rate. This will result in a displacement in the DSC curve opposite to that reported by Lucht⁵³. In view of the above, we discount that the thermal event observed at 627 K for IBC-102 coal can be associated with a typical glass-to-rubber transition. If it is argued that the thermal event at 627 K is not a glass-to-rubber transition, then it is possible to suggest that the exothermic event at 627 K may be cross-linking reactions in coal. However, additional DSC and spectroscopic measurements will be required to confirm or discount the aforementioned speculation.

The major thermal event for IBC-102 coal is observed around 720 K. Two strong, superimposed exothermic peaks are observed at 714 K and 726 K as depicted in Fig. 8. Based on published work, these peaks can be assigned to the major mild gasification reactions^{53,54}. It is generally believed that the carbonization process starts at approximately 623 K, initially with the release of carbon dioxide and hydrogen. As temperature is increased beyond 623 K, methane and other lower aliphatics are evolved along with hydrogen and carbon monoxide. The rupture of hydrogen bonded cross-links and the breaking of aliphatic and hydroaromatic bonds provide sufficient energy for the competing endothermic devolatilization of condensable liquids and tars. The above-mentioned process effectively produces an exothermic curve at about 720 K in the DSC thermograph.

Figure 9 presents the DSC thermograph obtained at the same conditions as above, for the coal mixed with montmorillonite. Again, we observed four thermal events along with an additional exothermic effect, which is attributed to dehydration of smectite. The effect of smectite on the enthalpy of mild gasification appears to be small. Since in the case of the coal alone the exothermic curve for this process was at 720 K, here with smectite, this maximum ap-

pears about 724 K. However, the effect of smectite on the cross-linkage process is substantial. When the coal sample was mixed with this monmorillonite, the cross-linkage temperature is observed to increase by 13°C.

In-situ Diffuse Reflectance-FTIR (ISDR-FTIR) measurements

Figure 10 depicts the effect of temperature, at a few selected temperatures, on the ISDR-FTIR spectra of IBC-102 coal under vacuum condition. The significance of the vacuum in our ISDR-FTIR measurements is that as the gases or other products/by-products are produced due to the mild gasification process they are swept out of the reactor. On raising the temperature of the sample to 408 K, absorbance loss occurs in the water stretching and bending regions, i.e., at 3623, 3400, and 1630 cm^{-1} . This observation is consistent with the DSC results. At 408 K < T < 623 K, no major changes in the ISDR-FTIR spectra result, as seen from the difference spectrum depicted in Fig. 11. However, it is worthwhile to point out that a very weak absorbance loss is produced and appears as broad bands which center around 3330 and 1653 cm^{-1} . This observation can be assigned to the loss of strongly hydrogen bonded water in coal. As the temperature of the sample is raised to 674 K, changes begin to manifest at 1658 and 1509 cm^{-1} regions. However, the loss in intensity of 1658 and 1509 cm^{-1} bands at 674 K is not significant enough for us to make definite conclusions at present. At 750 K major changes appear in the ISDR-FTIR spectrum of IBC-102 coal. These changes can be best visualized by generating a difference spectrum, i.e., ISDR-FTIR (750 K) - ISDR-FTIR (523 K). The difference spectrum is reproduced in Fig. 12. As can be seen from this figure, weak absorbance loss occurs at 3529, 2922, 2860, 1668, 1597, 1444, 1379, 1240 and 1147 cm^{-1} , and absorbance gain appears at 1832 and 1770 cm^{-1} . The absorbance loss at 2922, 2860, 1441, and 1379 cm^{-1} suggests that $-\text{CH}_2-$ groups are lost from the coal by subjecting it to thermal treatment at 750 K. The vibration at 1668 cm^{-1} , which is a C=O stretch oscillator, can be assigned to unsaturated ketones or esters. The bands at 1240 and 1147 cm^{-1} originate from the C-O stretch and signify the loss of ether and ketone groups from the coal on subjecting it to heat treatment. However, what is surprising is the appearance of absorbance gain at around 1832 and 1770 cm^{-1} . These vibrations can be assigned to anhydrides. This observation suggests that carboxylic acid groups may play an important role in the cross-linking process of coal, thus, the yield of chars. Additional ISDR-FTIR measurements are in progress, especially under various gaseous environments, to map out strategies to enhance the char yields.

CONCLUSIONS AND RECOMMENDATIONS

1. A new technique was developed in which the weight losses were compared under different environments. This method has the advantage that under the same experimental conditions, the direct differences between the runs are obtained.
2. More experiments need to be performed in order to correlate the temperature ramp, initial weight of the coal sample, and flow rate of the reacting gas, with the weight loss rate. This will determine the optimum conditions for enhanced quality char formation.
3. In order to compare the thermal effects of the coal interaction with methane, hydrogen, oxygen, and methane/oxygen, the additional experiments with these gases will be performed using differential scanning calorimetry.
4. ISDR-FTIR results suggest that carboxylic groups may play an important role in the cross-linking process of coal. It is of interest to check if this key role of acid carboxylic groups occurs also under methane and other gases environments.

REFERENCES

1. Speight, J.G., 1983, The Chemistry and Technology of Coal, Marcell Dekker, Inc., New York.
2. Berkowitz, N., 1985, The Chemistry of Coal, Elsevier, New York
3. Cypres R., S. Furfari, 1982, Fuel, **61**, 721
4. Steiberg, M.M., M.S. Sundaram, 1986, Energy Res. Abstr., Abstr. # 15465
5. Steinberg, M., 1986, Int. J. Hydrogen Energy, **11**, 715
6. Hefta, R.S., H.H. Schobert, W.R. Kube, 1986, Fuel, **65**, 1196
7. Khan, M.H., F.Y. Hshieh, L. Headley, 1989, ACS Preprint Fuel Div., **34(4)**, 1167
8. Khan M.R., 1989, Fuel, **68**, 1522
9. Smith, G.V., T. Wiltowski, 1990, "Chemicals from Coal and Methane", CRSC Final Report.
10. Snape, C.E., 1991, Fuel, **70**, 285
11. Pugmire, R.J., M.S. Solum, D.M. Grant, S. Critchfield, 1991, Fuel, **70**, 414
12. Ibarra, J.V., R. Moliner, M.P. Gavilan, 1991, Fuel, **70**, 408
13. Hodek W., J. Kirschstein, K.H. Van Heek, 1991, Fuel, **70**, 424
14. Khan, M.R., 1987, Fuel Science and Technology International, **5**, 185
15. Chu, C.I., C.J. Im, B.L. Gillespie, 1989, DOE Report, DE-AC-218MC23289
16. Smith, G.V., T. Wiltowski, J.B. Phillips, 1989, Energy & Fuels, **3**, 541
17. Khan, M.R., F.Y. Hshieh, 1989, ACS Preprints Fuel Div., **34(4)**, 1245
18. Daw, C.S., 1989, ACS Preprints Fuel Div., **34(4)**, 1256
19. Rostam-Abadi, M., J.A. DeBarr, W.T. Chen, D.P. McCollor, S.A. Benson, 1989, ACS Preprints Fuel Div., **34(4)**, 1264
20. Wells, W.F., L.D. Smoot, 1991, Fuel, **70**, 454
21. Derbyshire, F., 1991, Fuel, **70**, 276
22. Kuhn, L., H. Plogmann, 1990, Fuel, **62**, 205
23. "Research Program for Illinois Basin Coals", CRSC, Champaign, Illinois (1984)
24. Gala, H., 1987, "Surface Science of Coal Preparation", DOE Report #DE-AC22-84PC72571, and references cited therein

25. Malhotra, V.M., M. Saporoshenko, A.C. Kent, 1990, "Modification of Pyrite Surfaces and Preparation of Cleaned Ultrafine Coal", CRSC Final Report
26. Malhotra, V.M., W.R.M. Graham, 1983, Bull. Amer. Phys. Soc., **28**, 202
27. Malhotra, V.M., W.R.M. Graham, 1983, Fuel, **62**, 1255
28. Malhotra, V.M., W.R.M. Graham, 1984, ACS Preprint Div. Petroleum Chem., **29(1)**, 261
29. Malhotra, V.M., H.A. Buckmaster, 1984, ACS Preprint Div. Petroleum Chem., **29(4)**, 1232
30. Malhotra, V.M., H.A. Buckmaster, 1985, Fuel, **64**, 335
31. Malhotra, V.M., H.A. Buckmaster, 1985, Applied Clay Science, **1**, 225
32. Mu, R., V.M. Malhotra, Y.P. Chugh, 1987, "Effects of Heavy Crude Oil Treatment on the Surface Wetting Properties of Coal", in Processing and Utilization of High Sulfur Coal, Elsevier, New York, pp 94-106
33. Malhotra, V.M., R.D. Moore, 1985, "Thermal Shock of Heavy Oil Formations: FTIR Study", 27th Rocky Mountain Conference for Applied Spectroscopy, Denver, Colorado
34. Malhotra, V.M., Y. Dang, R.Mu, W.A. Helmer, A. Kent, F. Oksus, 1989, "Heavy Oil Fractions Assisted Deewatering and Agglomeration of Ultrafine Bituminous Coal: FTIR, DRIFT, and Photoacoustic-FTIR Measurements", 31st Rocky Mountain Conference for Applied Spectroscopy, Denver, Colorado, #245
35. Malhotra, V.M., R.N. Zitter, 1989, "Coal-Water Interactions and Preparations of Dewatered Ultrafine Clean Coal", DOE Report #DE-FC22-88PC88861
36. Wiltowski, T., R. Walker, D. Ellison, G.V. Smith, (in preparation)
37. Dunkerton, L.V., S. Mitra, J.B. Phillips, G.V. Smith, C.C. Hinckley, and Teresa Wiltowska, 1988, FUEL, **67**, 967-972
38. Yang, R.T. and F.P. Chen, 1989, J. Catal. **115**, 52-64
39. Sacco, A. Jr., F.W.A.H. Geurts, G.A. Jablonski, S. Lee, and R.A. Gately, 1989, J. Catal. **119**, 322-341
40. Baird, T., J.R. Fryer, B. Grant, 1974, Carbon, **12**, 591-602
41. Lieberman, M.L. and Noles, G.T., 1974, Carbon, **12**, 689-693
42. Palmer, H.B., J. Lahaye, and K.C. Hou, 1968, J. Phys. Chem., **72**, 348-353
43. Rostrup-Nielsen, J.R., 1984, Catalysis, Science and Technology, **5**, 1-117
44. Seehra, M.S., G. Ghosz, S.E. Mullins, 1986, Fuel, **65**, 1315

45. Ali, M.S., W.R.M. Graham, 1987, ACS Preprints Fuel Div., 32(3), 217
46. Montano, P.A., G. Granoff, 1980, Fuel, 59, 214
47. Ruppert, J.P., W.T. Granquist, T.J. Pinnavalia, 1987, "Catalytic Properties of Clay Minerals" in Chemistry of Clays and Clay Minerals, ed.: A.C.D. Newman, Longman Scientific & Technical, Essex, England
48. Smith G.V., T. Wiltowski, T. Wiltowska, E. Myszka, M. Gasior, G. Voss, R. Song, 1991, The Methoxycoal Process, CRSC Final Report,
49. Mu, R., V.M. Malhotra, 1991, Phys. Rev., B44, 4296
50. Mu, R., V.M. Malhotra, 1991, Fuel, 70, 1233
51. Jasty, S., V.M. Malhotra, 1992, Phys. Rev., B45, to appear
52. Dang, Y., V.M. Malhotra, 1991, Fuel, submitted
53. Lucht, L.M., J.M. Larson, N.A. Peppas, 1987, Energy & Fuel, 1, 56
54. Yurum, Y., A.K. Karabakan, N. Altuntas, 1991, Energy & Fuel, 5, 701

IBC-102, He; 20-650C; 10 deg/min

Figure 1. Plot of the % of remaining weight versus temperature for IBC-102 coal sample treated with He

IBC-102; CH₄; 20-650C; 10 deg/min

Figure 2. Plot of the percent of remaining weight versus temperature for IBC-102 coal sample treated with methane

IBC-102, hydrogen, 20-650C; 10 deg/min

Figure 3. Plot of the percent of remaining weight versus temperature for IBC-102 coal sample treated with hydrogen

IBC-102; CH₄/O₂; 20-650; 10 deg/min

Figure 4. Plot of the percent of remaining weight versus temperature for IBC-102 coal sample treated with the mixture of methane and 2% of oxygen

IBC-102, He/O₂; 20-650C; 10 deg/min

Figure 5. Plot of the percent of remaining weight versus temperature for IBC-102 coal sample treated with the mixture of helium and 2% of oxygen

IBC-102; DTGA; 20-650C; 10 deg/min

Figure 6. Comparison of DTG curves for the IBC-102 coal treated with different gases

IBC 102(M), 20-650C, 10C/min

Figure 7. Plot of weight difference from collecting data of weight losses of IBC-102 coal under different atmospheres

DSC THERMOGRAPH : MILD GASIFICATION

Figure 8. Thermogram of IBC-102 coal sample under helium

DSC THERMOGRAPH : MILD GASIFICATION

Figure 9. Thermogram of IBC-102 coal mixed with smectite (2:1)

IN-SITU DR-FTIR MEASUREMENTS

Figure 10. ISDR-FTIR spectra of IBC-102 coal sample at different temperatures

IN-SITU DR-FTIR MEASUREMENTS

Figure 11. ISDR-FTIR difference spectra of IBC-102 coal sample

IN-SITU DR-FTIR MEASUREMENTS

Figure 12. ISDR-FTIR difference spectra of IBC-102 coal sample

PROJECT MANAGEMENT REPORT

September 1, 1991 through November 30, 1991

Project Title: **CLEAN, PREMIUM-QUALITY CHARS: DEMINERALIZED AND
CARBON ENRICHED**

Principal Investigator: Gerard V. Smith
Molecular Science Program
Southern Illinois University
Carbondale, IL 62901
(618) 453-7319

Other Investigators: Vivak M. Malhotra
Department of Physics
Southern Illinois University
Carbondale, IL 62901

Tomasz Wiltowski
Molecular Science Program
Southern Illinois University
Carbondale, IL 62901

Project Monitor: Frank Honea, CRSC

This project is funded by the U. S. Department of Energy (METC) and by the Illinois Department of Energy and Natural Resources as part of their cost-shared program.

**DATE
FILMED**

3 / 24 / 92