**A NOVEL APPROACH TO HIGHLY DISPERSING CATALYTIC
MATERIALS IN COAL FOR GASIFICATION**

Ninth Quarterly Report
for the Period
October 1, 1991 - December 31, 1991

Godfried M.K. Abotsi and Kofi B. Bota
Principal Investigators

Research Center for Science and Technology
Clark Atlanta University
Atlanta, GA 30314

PREPARED FOR
UNITED STATES DEPARTMENT OF ENERGY
UNDER CONTRACT NO. DE-FG22-89PC89760

MASTER

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

FEB 10 1982

DISTRIBUTION

Dr. Jagdish L. Malhotra
U.S. Department of Energy
Morgantown Energy Technology Center
P. O. Box 880
Morgantown, WV 26505

Marilyn Keane
PM-40, MS922-206
U.S. Department of Energy
Pittsburgh Energy Technology Center
P. O. Box 10940
Pittsburgh, PA 15236

Cynthia Y. Mitchell
Contract Specialist
AD-22, 921-165
U.S. Department of Energy
Pittsburgh Energy Technology Center
P. O. Box 10940
Pittsburgh, PA 15236

Kay Downey
Office of Technology Transfer
U.S. Department of Energy
Pittsburgh Energy Technology Center
P. O. Box 10940
Pittsburgh, PA 15236

ABSTRACT

This project seeks to develop a technique, based on coal surface properties, for highly dispersing catalysts in coal for gasification and to investigate the potential of using potassium carbonate and calcium acetate mixtures as catalysts for coal gasification. The lower cost and higher catalytic activity of the latter compound will produce economic benefits by reducing the amount of K_2CO_3 required for high coal char reactivities.

As was shown in previous reports, coal loading with potassium or calcium at different pHs produced CO_2 gasification activities which increased in the order $pH\ 6 > pH\ 10 \gg pH\ 1$. The current report shows that a similar trend was obtained when calcium and potassium were simultaneously loaded and char reaction times were less than about 75 min. Beyond this time, the coal impregnated with catalyst at pH 1 became more reactive, reaching 100% conversion after 1.5h. X-ray diffraction analysis suggests that the catalysts are well dispersed around pH 1 and 6 whereas reduced dispersion was obtained at pH 10. The reactivities are independent of the surface areas of the coals.

INTRODUCTION

Catalyzed coal gasification requires the adsorption of the catalyst precursor onto the coal surface as the first step in a series of consecutive reactions. Previous studies (1) have shown that char reactivities are dependent on the catalyst precursor and the method applied to load the coal with the catalyst. This report is part of ongoing research aimed at understanding the roles of coal surface charge and the pHs of catalyst impregnating solutions on the adsorption and activities of calcium acetate and potassium carbonate. As reported previously (2,3), the reactivities of chars derived from a lignite, subbituminous, and bituminous coals are strongly dependent upon the coal surface charge and the pHs at which calcium or potassium was adsorbed onto the coal. The current report discusses the reactivities of the demineralized bituminous coal in carbon dioxide, catalyzed by a combination of calcium and potassium. Catalyst dispersion was evaluated using X-ray diffraction while surface areas were measured by the N₂ BET technique.

EXPERIMENTAL

The effect calcium and potassium on char reactivity was studied by simultaneously adsorbing both metals onto the demineralized bituminous coal (Illinois No. 6) at equilibrium pHs of about pH1, 5 and 9. Details of the metal adsorption and the gasification reactions in CO₂ have been provided previously (2,3).

RESULTS AND DISCUSSION

As reported previously (2,3), calcium and potassium adsorption onto the raw or demineralized coals was minimal in strongly acidic solutions, but greatly enhanced in basic media. Intermediate metal loading was obtained in near neutral solutions ($\approx$ pH 6). The variations in metal uptake has been attributed to differences in the negative surface charge densities of the coals.

The reactivities of the demineralized bituminous coal containing calcium and potassium are shown in Figure 1. It is observed that the unloaded acid-leached coal (DEM bituminous) is substantially less reactive than the calcium and potassium exchanged coals. For reaction times less than about 75 min, char reactivities followed the order pH 4.9 > pH 8.6 > pH 0.9. It is also observed that within this time on stream, the reactivity of the char loaded with the catalyst at $\approx$ pH 1 increases linearly with time, in contrast to the chars loaded with catalyst at the other pHs. After $\approx$ 75 min, the reactivity of the pH 0.9 char becomes more pronounced and 100% char gasification occurs after 100 min of reaction. These gasification rates are similar to those reported earlier for calcium (2) and for the potassium-loaded lignite, PSOC 1482 (3).

To ascertain the effect of catalyst dispersion on the reaction rates, the demineralized lignite loaded with calcium at pH 1, pH 6 or pH 10 was examined with X-ray diffraction using $\text{CuK}\alpha$ radiation. The metal content of the coals have been provided in an earlier report (2). It can be seen from Figure 2 that calcium loading at pH 1 or pH 6 did not produce any diffraction peaks above the background of the coal. This phenomenon has been attributed to very fine and highly dispersed catalyst particles.

However, calcium loading at pH 10 produced diffraction peaks characteristic of CaO (4) and indicates reduced catalyst dispersion. It is suggested a similar catalyst dispersion trend occurs when the coal is simultaneously loaded with calcium and potassium.

Figure 3 shows that there is little variation in the N₂ BET surface areas of the raw or demineralized bituminous (Illinois No. 6) coal with calcium or potassium loading pH. We believe the differences in the surface areas which ranged from about 0.6 to 7.0 m²g⁻¹ are not significant enough to affect the char reactivity rates and we therefore conclude that the observed reactivities are predominantly determined by the degree of catalyst dispersion.

REFERENCES

1. Wood, B.J. and Sancier, K.M., 1984, Catal. Rev.-Sci. Eng., 26(2), 233-279.
2. Abotsi, G. M. K. and Bota, K. B., 1990. "A Novel Approach to Highly Dispersing Catalytic Materials in Coal for Gasification," Seventh Quarterly Report prepared for the Department of Energy under contract no. DE-FG22-89PC89760.
3. Abotsi, G. M. K. and Bota, K. B., 1990. "A Novel Approach to Highly Dispersing Catalytic Materials in Coal for Gasification," Eighth Quarterly Report prepared for the Department of Energy under contract no. DE-FG22-89PC89760.
4. Radovic, L. R., Walker, P. L., Jr. and Jenkins, R. G., 1983, Fuel 62, 209-212.

Figure 1. Char reactivities in CO_2 of the demineralized bituminous coal (PSOC 1493) and its samples containing calcium and potassium introduced at pH 0.9, 4.9 and 8.6.

Figure 2. X-ray diffraction patterns for the demineralized North Dakota lignite (PSOC 1482) exchanged with calcium at pH 1, 6 or 10.

Figure 3. N₂ BET surface areas of the raw and the acid-leached bituminous coals loaded with calcium at pH 1, 6 or 10.

**DATE
FILMED**

5/01/92