TECHNICAL REPORT
September 1-November 30, 1991

Project Title: Development of Novel Copper-Based Sorbents
for Hot-Gas Cleanup DE-FG22-91PC91334

Principal Investigator: Javad Abbasian, Institute of Gas Technology

Co-Principal Investigator: Maria Flytzani-Stephanopoulos, Massachusetts
Institute of Technology

Other Investigator: Andy H. Hill, Institute of Gas Technology

Project Monitor: Franklin I. Honea, CRSC

ABSTRACT

The objective of this investigation is to evaluate several novel copper-based binary oxides for their suitability as regenerable sorbents for hot gas cleanup application in the temperature range of 650° to 850°C (1200°-1550°F).

To achieve this objective, several novel copper-based binary oxide sorbents will be prepared. Experimental tests will be conducted at ambient pressure to determine the stability, sulfidation capacity, regenerability, and sulfidation kinetics of the novel sorbents. Tests will also be conducted at high pressure for the determination of the sulfidation reactivity, regenerability, and durability of the sorbents. The attrition characteristics of the sorbents will also be determined.

A new copper oxide-based sorbent, designated S_x , was synthesized by the amorphous citrate technique, and tested in reductive sulfidation in the packed-bed microreactor at $P = 1$ atm. The H_2S removal efficiency of this sorbent was 99.9% in three cycles of sulfidation at 650°C with intermittent regeneration at 750°C. The performance of the new sorbent was a little better than the best sorbent tried to date in sulfidation, namely Cu-2Cr-O tested during the last quarter. After the 3 cycles, the surface area of this sorbent was 3 m²/g. Thus, sorbent S_x has now been included in the list that will undergo further detailed evaluation at 850°C (1123 K) along with sorbent Cu-2Cr-O.

New sulfidation tests were conducted at 850°C with the Cu-Mn-O sorbent, a high-sulfur capacity material, as reported last quarter. The sulfur capacity of this sorbent remains high at 850°C, however, its H_2S -removal efficiency is only ca 90% prior to breakthrough.

X-ray diffraction analysis of the fresh sorbents began this quarter. A single crystalline phase, $Cu_{1.4}Mn_{1.6}O_4$, dominates the diffractogram. The 3Cu-Mg-O and Cu-2Cr-O sorbents will be analyzed next by XRD.

MASTER

This project is funded by the U. S. Department of Energy (METC) and by the Illinois Department of Energy and Natural Resources as part of their cost-shared program.

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

EXECUTIVE SUMMARY

The objective of this investigation is to evaluate several novel copper-based binary oxides for their suitability as regenerable sorbents for hot gas cleanup application in the temperature range of 650° to 850°C (1200°-1550°F). Such High temperatures will be required for the new generation of gas turbines in Integrated Gasification Combined Cycle (IGCC) Systems.

Coal gas desulfurization to sufficiently low levels at temperatures of 600° to 800°C (1100° to 1400°F) is now recognized as crucial to the efficient and economic coal utilization in coal gasification-combined cycle (IGCC) power generation (using gas turbines) and gasifier/fuel cell power plants. The implementation of hot coal gas desulfurization heavily relies on the development of regenerable sorbent materials which have high sulfur capacity and can efficiently remove H_2S (from several thousand ppm levels down to a few ppmv) over many cycles of sulfidation/regeneration. Structural stability and good mechanical strength are additional desired features of sorbents. Not surprisingly, only a few metal oxides can meet these stringent requirements.

This research program will focus on the evaluation of regenerable and novel copper-based sorbents for hot gas cleanup. The results of this project will be used to determine the most promising sorbent for further development. The sorbents to be developed in this program will have the potential of reducing the sulfur content of the fuel gas at elevated temperatures (above 1200°F) to very low levels (a few ppm), resulting in significant increase in the efficiency of the IGCC or gasifier/fuel cell power plants.

A new copper oxide-based sorbent, designated S_x , was synthesized by the amorphous citrate technique, and tested in reductive sulfidation in the packed-bed microreactor at $P = 1$ atm. The H_2S removal efficiency of this sorbent was 99.9% in three cycles of sulfidation at 650°C with intermittent regeneration at 750°C. The performance of the new sorbent was a little better than the best sorbent tried to date in sulfidation, namely Cu-2Cr-O tested during the last quarter. After the 3 cycles, the surface area of this sorbent was 3 m²/g. Thus, sorbent S_x has now been included in the list that will undergo further detailed evaluation at 850°C (1123 K) along with sorbent Cu-2Cr-O.

New sulfidation tests were conducted at 850°C with the Cu-Mn-O sorbent, a high-sulfur capacity material, as reported last quarter. The sulfur capacity of this sorbent remains high at 850°C, however, its H_2S -removal efficiency is only ca 90% prior to breakthrough.

X-ray diffraction analysis of the fresh sorbents began this quarter. A single crystalline phase, $Cu_{1.4}Mn_{1.6}O_4$, dominates the diffractogram. The 3Cu-Mg-O and Cu-2Cr-O sorbents will be analyzed next by XRD.

OBJECTIVE

The overall objective of this program is to evaluate several novel copper-based sorbents for their suitability for hot gas cleanup application in the temperature range of 1200° to 1550°F.

The program goals are specifically directed toward the Gas Cleanup, Research Priority 6.1A: Removal of Sulfur-Containing Gases From the Hot Overhead Effluent Obtained by Gasification of High-Sulfur Illinois Coal. The program is targeted toward the determination of structural stability, sulfidation reactivity, regenerability, durability, and attrition resistance characteristics of the novel copper-based sorbents.

The specific objectives of this program are to:

1. Prepare and characterize specific compounds of copper oxide with each of the oxides of Mg, Ti, Al, Cr, Si, Fe, and Mn;
2. Determine the reduction stability of the binary oxides in H_2 - N_2 and H_2 - H_2O - N_2 gas mixtures to be carried out at temperatures of 650° to 1000°C (1000°-1800°F);
3. Carry out sulfidation screening tests with the stable CuO-phases identified in (2) using H_2 - H_2S - N_2 and H_2 - H_2S - H_2O - N_2 gas mixtures and temperatures of 650° to 850°C (1200° to 1550°F).
4. Determine the sulfidation rate constants and measure overall rates of sulfidation reactions with the most promising sorbents.
5. Carry out up to fifteen sulfidation-regeneration cycles with selected sorbent compositions and determine sorbent regenerability and structural stability in cyclic operation using H_2 - H_2S - H_2O - N_2 mixtures as well as simulated coal gasifier exit gas containing COS, HCl, and other constituents.
6. Carry out attrition tests with the promising sorbents to determine their suitability for moving-bed or fluidized-bed application.

INTRODUCTION AND BACKGROUND

The main goal of the CRSC sponsored research on sulfur in coal is to increase the utilization of high-sulfur Illinois coals using a method that is both economical and environmentally acceptable. The market share of high-sulfur coal has suffered losses because of the trend towards more stringent government-imposed limitation on sulfur emission. Thus, there is a real need to develop technologies for reducing sulfur emissions while minimizing solid wastes for disposal.

Integrated Gasification Combined-Cycle (IGCC) Power Plants and Fuel Cell Power Generation Technologies are among the leading contenders for coal conversion. Development of technology for coal gas desulfurization to sufficiently low

levels at temperatures of 650° to 850°C (1200° to 1550°F) is now recognized as crucial to the efficient and economic coal utilization in emerging technologies such as Coal Gasification-Combined Cycle Power generation (using gas turbines) and gasifier/fuel cell power plants. The implementation of hot gas desulfurization technology heavily relies on the development of regenerable sorbent materials which have high sulfur capacity and can efficiently remove H_2S (from several thousand ppm levels down to a few ppmv) over many cycles of sulfidation/regeneration. COS, CS_2 , and other organic sulfur compounds, present in gasifier fuel gas streams, also need to be removed regeneratively and efficiently by the sorbents. Structural stability and good mechanical strength are additional desired features of the sorbents.

In recent years it has been shown that certain mixed oxides have superior properties compared to single oxides for hot gas cleanup. A compound of zinc and iron oxides, zinc ferrite ($ZnFe_2O_4$), developed by DOE/METC has reached the pilot-stage of testing for desulfurization of low-Btu gases. The H_2S removal efficiency of $ZnFe_2O_4$ is similar to ZnO because zinc ferrite is converted into a mixture of ZnO and Fe_3O_4 when exposed to the reducing gas. Similarly, the rate of zinc loss (via ZnO reduction) is the same in both $ZnFe_2O_4$ and ZnO. Therefore, the application of zinc ferrite is limited to temperatures below 600°C (1100°F).

Titanium dioxide was examined as a potentially better alternative to iron oxide additives in terms of the higher stability of the titanates over the ferrite compounds of zinc, and their not too different sulfidation equilibria. With zinc titanates, the sulfidation temperature was shown to extend to 700°C (1300°F), and sintering of ZnO was greatly reduced. Because zinc titanate also showed better attrition resistance than zinc ferrite in preliminary pilot tests at General Electric and better regenerability and mechanical stability in the highly reducing Texaco gasifier-exit gas composition, further development of the zinc titanates is underway.

However, at sulfidation temperatures above ~750°C (1400°F), zinc titanates will also suffer zinc losses. Such high temperatures will be required for the new generation gas turbines (with inlet temperatures exceeding 1400°F). If gas cleanup can be performed at matching conditions, then higher power plant cycle efficiency gains will be realized. For these applications the metal oxide sorbents should have low vapor pressures in all their oxidation states (including the metallic state).

Copper oxide-based sorbents have been examined to a lesser extent than zinc oxide sorbents for high-temperature gas desulfurization. Mixed oxides of copper, iron and aluminum in bulk (unsupported) form were developed earlier and were found suitable for desulfurization of gases from fluidized-bed gasifiers at temperatures up to 800°C (1472°F). Presently, work with another type of copper compound, copper manganates, is being carried out by ElectroChem. Instability problems in the presence of water vapor have been reported for the $CuMn_2O_4$ phase, which has high sulfur capacity at high temperature. Other copper-based mixed oxide sorbents have not been tested for their suitability for hot gas cleanup. Systematic evaluation of novel copper-

based sorbents is very important because of their potential for hot gas cleanup application at higher temperatures.

This research program has focused on the evaluation of regenerable and novel copper-based sorbents for hot gas cleanup. The results of this project will be used to determine the most promising sorbent for further development. The sorbents to be developed in this program will have the potential of reducing the sulfur content of the fuel gas at elevated temperatures (above 1200°F) to very low levels (a few ppm), resulting in significant increase in the efficiency of the IGCC or gasifier/fuel cell power plants.

EXPERIMENTAL PROCEDURE

Sulfidation-Regeneration Tests

The sulfidation regeneration tests were carried out in the quartz micro-reactor unit at ambient pressure in the temperature range of 650° to 850°C (1200°-1550°F). These tests were conducted using two sorbents, namely, copper-manganese oxide sorbent and a new sorbent designed at Cu-X-O. Sulfidation of sorbents was carried out in 10% H₂S-20% H₂O-69.5% N₂ gas mixture at a sulfidation temperature of 650°C (1200°F) or 850°C (1560°F) with a space velocity of 2000 h⁻¹. Regeneration was conducted with a 6% O₂-94% N₂ gas mixture at 750°C (1380°F) with a space velocity of 2000 h⁻¹. Sorbents used in these tests were granular form -20 + 35 mesh (400-800 μm size) particles.

RESULTS AND DISCUSSIONS

Sulfidation tests were conducted with copper manganese (Cu-Mn-O) sorbent at 850°C (1123°K). The results are shown in Figure 1. The sulfur capacity of this sorbent remains high at 850°C (similar to the sulfur capacity at 650°C reported last quarter), however its H₂S-removal efficiency is only 90% prior to breakthrough. Two cycles are shown in Figure 1. A third sulfidation, interrupted at $t/t^* = 1$, also had pre-breakthrough H₂S levels of 50-70 ppm. The results of these tests also suggests that manganese oxide participates in the sulfidation. The values of sorbent conversion presented as t/t^* is based on formation of only Cu₂S in the product.

During this quarter, a new copper oxide-based sorbent, designated S_x was synthesized by the amorphous citrate technique, and tested in reductive sulfidation in the packed-bed microreactor at P = 1 atm. The H₂S removal efficiency of this sorbent was 99.9% in three cycles of sulfidation at 650°C with intermittent regeneration at 750°C (Figure 2). The sulfidation gas composition was the same as in all prior sulfidation screening experiments, namely, in mol %: 10 H₂ - 0.5 H₂S - 20 H₂O - bal N₂. Regeneration was carried out with 6% O₂ - 94% N₂. The space velocity was 2000 h⁻¹ (STP) for both sulfidation and regeneration. The performance of the new sorbent S_x was a little better than the best sorbent tried to date in sulfidation, namely Cu-2Cr-O (see last quarterly report). After the 3 cycles shown in Figure 2, the surface area of this sorbent was 3 m²/g. Thus, sorbent S_x has now been included in the list that will undergo further detailed evaluation at 850°C (1123 K) along with sorbent Cu-2Cr-O.

X-ray diffraction analysis of the fresh sorbents began this quarter. Figure 3 shows the XRD of Cu-Mn-O, prepared by the citric acid method with calcination at 850°C. A single crystalline phase, $\text{Cu}_{1.4}\text{Mn}_{1.6}\text{O}_4$, dominates the diffractogram. The 3Cu-Mg-O and Cu-2Cr-O sorbents will be analyzed next by XRD. Preliminary runs indicate two separate phases for 3Cu-Mg-O and a single phase for Cu-2Cr-O.

New batches of the sorbent Cu-2Cr-O were prepared by the amorphous citrate technique, calcined at 550°C (3 h), crushed and sieved in granular form (-20+35 mesh) for bench-scale testing.

CONCLUSIONS AND RECOMMENDATIONS

Based on the results of the experiments conducted to date, the novel copper-based sorbents are ranked as follows:

- (i) Reduction Stability: Cu-Cr-O
- (ii) H_2S Removal Efficiency: Cu-X-O
Cu-2Cr-O
- (iii) Sulfur Capacity: Cu-Mn-O
- (iv) Still Uncertain: 3Cu-Mg-O (high stability phase Cu_3MgO_4 has not been prepared)
- (v) Dropped from the list: Cu-Si-O (based on literature information: Env. Sci. ETchnol. 23(2), 218 (1989). Cu-Al-O; Cu-Fe-O (Flytzani-Staphanopoulos et al., Final Reports to DOE, 1985; 1987)

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

Figure 1. CYCLIC SULFIDATION OF Cu-Mn-O AT 850°C (1123 K)

$T = 923 \text{ K}$

Figure 2. CYCLIC SULFIDATION OF Cu-X-O SORBENT AT 650°C (923 K)

Z20353 11/15/91 S- 0.040 T- 5.000 CU-MN
PDF (1) -35, 1030

Figure 3. RESULT OF X-RAY DIFFRACTION (XRD) ANALYSIS OF FRESH Cu-Mn-O SORBENT

REFERENCES CITED

1. Marcilly, C., P. Corty, and B. Delmon, "Preparation of Highly Dispersed Mixed Oxides and Oxide Solid Solutions by Pyrolysis of Amorphous Organic Precursors," J. Am. Ceram. Soc. **53**(1), 56-57 (1970).
2. Barin, I. and O. Knacke, "Thermochemical Properties of Inorganic Substances," Springer Verlag, Berlin and New York, 1973.
3. Barin, I., O. Knacke and O. Kubaschewski, "Thermochemical Properties of Inorganic Substances," Supplement, Springer Verlag, Berlin and New York, 1977.
4. Jacob, K. T., G. M. Kale, G. N. K. Iyengar, "Oxygen potentials, Gibbs energies and phase relations in the Cu-Cr-O system," J. Mat. Sci. **21** 2753-2758 (1986).
5. Jacob, K. T. and C. B. Alcock, "Thermodynamics of CuAlO_2 and CuAl_2O_4 and Phase Equilibria in the System Cu_2O - CuO - Al_2O_3 ," J. Am. Cer. Soc. **58**(5-6), 192-195 (1975).
6. Pejryd, L. and E. Rosen, "Determination of the Stability of Cu_3TiO_4 by Solid-State Emf Measurements," High Temp.-High Press. **14**, 599-606 (1982).
7. Godalla, A. M. M. and J. White, Trans-Brit Ceram. Soc. **65** 157-164 (1966).
8. Onderka, B. and K. Fitzner, "Stability of the Guggenite Phase in the CuO - MgO System," Archives of Metallurgy **33**(1), 135-143 (1988).
9. Flytzani-Stephanopoulos, M. G. R. Cavallas, K. Jothimurugesan, S. Lew, P. K. Sharma, M. J. Bagajewicz and V. Patrick, "Detailed Studies of Novel Regenerable Sorbents for High-Temperature Coal-Gas Desulfurization," Final Report DE-FC21-85MC221930, October 1987.

This work was prepared with the support, in part by grants made possible by the Illinois Department of Energy and Natural Resources through its Coal Development Board and Center for Research on Sulfur in Coal, and by the U.S. Department of Energy. However, any opinions, findings, conclusions, or recommendations expressed herein are those of the authors and do not necessarily reflect the views of IDENR, CRSC and DOE.

END

DATE
FILMED

4 102 192

I