WSRC-TR--91-403

DE92 009534

MAR 1 6 1992

ENVIRONMENTAL TEST PROGRAM FOR SUPERCONDUCTING MATERIALS AND DEVICES: PRELIMINARY RESULTS OF TESTING PROGRAM AT SAVANNAH RIVER SITE (U)

by

H. W. Randolph, et al

Westinghouse Savannah River Company
Savannah River Site
Aiken, South Carolina 29808

DISCLAIMER

This is a Technical Report

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

This paper was prepared in connection with work done under Contract No. DE-AC09-89SR18035 with the U.S. Department of Energy. By acceptance of this paper, the publisher and/or recipient acknowledges the U.S. Government's right to retain a nonexclusive, royalty-free license in and to any copyright covering this paper, along with the right to reproduce and to authorize others to reproduce all or part of the copyrighted paper.

MASTER

Interim Report

**ENVIRONMENTAL TEST PROGRAM FOR SUPERCONDUCTING
MATERIALS AND DEVICES**

Preliminary Results of Testing Program at SRS

to

**Dr. Gene Haertling
Ceramic Engineering
Clemson University
Clemson, SC 29634**

Investigators:

Henry Randolph	- Westinghouse Savannah River Co.
Darren Verebelyi	- Westinghouse Savannah River Co.
	- Clemson University

Contract No. NAG-1-1127

May 30, 1991

Introduction

The properties of $\text{YBa}_2\text{Cu}_3\text{O}_{7-x}$ superconducting tapes designed and fabricated into SAFIRE-type, encapsulated, grounding links by the Ceramic Engineering Department at Clemson University are under investigation (NASA Contract No. NAG-1-1127). Testing at the Savannah River Site will include gamma irradiation, vibration, and long-term evaluation. The gamma irradiation portion of testing has been completed. The long-term testing began in January and will continue. The vibration test has yet to be started.

Radiation Test

Eight samples were irradiated in a high level gamma well. These samples were received from Clemson with known resistance vs. temperature curves. Before irradiation the samples were videotaped with the full screen of a monitor equaling the width of the sample. The samples were then immersed in liquid nitrogen and exposed to ^{137}Cs for 126 total hours over a 10 day period. The main energy peak of the ^{137}Cs spectrum is at 661.66 keV. The calibrated exposure rate was 96.940 R/hr as shown in Table 1. The equivalent gamma radiation dose in water is equal to 11,000 rad. The cross section for gamma absorption in 123 material is greater than water so this dose would be a lower limit.

After irradiation these samples were videotaped again in the same manner as before exposure. The only physical change resulting from the treatment was minor epoxy liftoff from the 123 material. This has also been observed at Clemson on some samples during long periods of liquid nitrogen immersion. The samples were returned to Clemson for comparison resistance vs. temperature curves.

Long-Term Test

The long-term test is monitoring for decomposition by-products and changes in resistance while maintaining low temperature(77K) and high vacuum(10^{-7} torr). The equipment to perform measurements includes a cryostat and a vacuum system consisting of stainless steel piping configured to accommodate two, 20-pin, electronic signal feedthroughs, an ion pump, and a mass spectrometer head. The cryostat is immersed in liquid nitrogen from a 50 liter dewar. Liquid nitrogen is replenished to the 50 liter dewar by an interchangeable 160 liter dewar.

Continuous data acquisition by computer control compiles measurements of current, voltage, temperature, pressure, and partial pressure. Data are taken on 15 minute intervals and written into two text files along with a date and time stamp. Measurements are taken by a Hewlett Packard 3457A Multimeter, Hewlett Packard Scanner, and Dycor Quadrupole Mass Spectrometer. The multimeter was certified and is NIST traceable.

Voltage and current measurements are written to disk and resistance is calculated from Ohm's law. Temperature is calculated from the resistance measurement of a calibrated ceramic RTD. Pressure is calculated from a voltage measurement on the ion pump controller. Partial pressures of 12 masses are normalized to the ion pump pressure in torr.

A current of 10ma was applied to all eight samples for the first week, then the current was removed from four samples for the balance of the test. Samples were arranged in two groups of four as given in Table 2. The one inch diameter cryostat holds the samples as shown in Figure 1. This orientation allows the temperature measurement to be an upper limit. The continuous current samples are at a lower temperature due to their position at the bottom of the cryostat. The thermal transfer of the tube produces a temperature

gradient of approximately 7K from the bottom of the cryostat to the ceramic RTD.

Results

The long term test portion of the program has been in progress for more than 3000 hours. Data were collected each minute during the initial cooling of the samples on 15 Jan 91. Data from sample number 212 were omitted due to its failure to go superconducting after its initial testing on 21 Dec 90. These data were plotted as resistance vs. temperature for each sample and are given in Figures 2,3, and 4. The pressure during the superconducting transition changed for an unexplained reason, with an increase in pressure from $1\text{E-}5$ to $5\text{E-}2$ torr. The transition temperature is defined as the point in which the resistance is 10 milliohms. The seven samples all exhibited transitions at approximately 79K. This transition temperature is 9K below a similar curve, shown in Figure 5, which was taken at Clemson. Curves from similar samples tested at SRS in the past have shown transitions at about 89K. A typical example is given in Figure 6.

Resistance data for the three constant current samples are graphed in Figures 7-15. The three samples produced data that were very consistent. The only anomaly was during the first 700 hours of sample number 204. Shortly after the initial cooling of sample number 204, a negative potential of approximately 5 microvolts was recorded. This effect disappeared 700 hours later during a section of data loss. Raw data are missing for various reasons and the corresponding times are recorded in Table 3. The current supply was interrupted only once. This 24 hour period on 27 Feb 91 was due to a power outage.

Degradation evaluation of 123 material is of prime importance in the long-term portion of testing. Analysis of degradation of the samples was done by using six data sets each 10 hours in length. These sets are chosen at stable sections of the data at

approximately 84K. Figure 16 shows the average resistance divided by the average temperature for the six ranges. The resistance range of 200-400 microhms is comparable to the lead and contact resistance expected. The fact that these values do not increase is an indication that there is no degradation of the 123 material's superconducting properties.

Data for pressure and temperature of the system are also graphed in Figures 17, 18, & 19. Pressure is presently less than $8\text{E-}8$ torr. This is down from a typical $3\text{E-}7$ torr in February. Partial pressure data plotted for particular masses of interest are given in Figure 20. The decrease in pressure over time is normal and is due to the continuous pumping of surface sorbed gases. The ratios change as material is removed from surfaces at different rates.

Continuing work

Data will continue to be obtained and is expected to show a continuing decrease in water content of the vacuum system and a slow decline in hydrogen pressure. Full scans of all masses will be taken periodically and compared to data with the isolation valve closed so an assessment of any by-products from decomposition can be analyzed. The vibration test will be performed when equipment becomes available.

TABLE 1

GAMMA WELL CALIBRATION

SRL EXPERIMENT -- March 1991

Calibrated by: W. H. Wilkie
Date: 3/05/91

Reviewed by: _____
Date: _____

Temperature (Celsius): 21.5
Pressure (mm Mercury): 750.6
T/P Correction factor: 1.0108

Keithley Capintec Capintec Thermometer Barometer
Model 35617 PM-30 PM-500 -1 to 51 C B&H dig.

Serial Numbers: 36996 C1130.7065 C1152.7095
M&TE Number: 34002-4493 34002-1923 34002-4459
SRS Gauge DPN#: HP-507 HP-1024 SL-3708
Certification Date: 2/15/91 12/07/90 12/08/90 5/10/90 4/30/90
Expiration Date: 2/15/92 12/07/91 12/08/91 5/10/91 1/91
Calibration Factor (R/C): 1.15e8 6.167e6
Six-month Decay Factor: .9886

SHIELD OPEN -- 2.75 INCHES ABOVE LUCITE TROLLEY

Well Setting (ft)

Exposure Rate (mR/h)

***** PM-30 Uncorrected *****

Well Setting (ft)	START		STOP		Ion ch. current (pA)	PM-30 Corrected (mR/h)	
	n	coulombs (nC)	n	coulombs (nC)			
.35	3	5.0260	27	61.2700	234.35	96950	Inside dewer
.35	3	5.0470	27	61.2800	234.30	96931	Inside dewer
.35	3	5.2420	12	27.2200	244.20	101025	Outside

TABLE 2

	<u>SAMPLE</u>	<u>TYPE*</u>	<u>CURRENT</u>
GROUP 1:	203	TAB	YES
	204	TAB	YES
	212	PIN	YES
	213	PIN	YES
GROUP 2:	232	TAB	NO
	209	TAB	NO
	214	PIN	NO
	217	PIN	NO

* TAB = Silver foil tab
 PIN = Gold plated pin

TABLE 3**MISSING DATA SEGMENTS**

<u>DATE</u>	<u>START</u>	<u>STOP</u>	<u>HOUR</u>
15 Feb	8:55		737
19 Feb		9:10	834
27 Feb	18:52		1036
28 Feb		19:07	1055
8 Mar	19:06		1259
11 Mar		16:14	1328
	:		
12 Apr	7:36		2089
13 Apr		7:12	2112
25 Apr	12:45		2406
1 May		0:45	2539

FIGURE 1 SCHEMATIC ORIENTATION OF SAMPLES IN CRYOSTAT

FIGURE 2 INITIAL RESISTANCE VS. TEMPERATURE (T_c) CURVE FOR SUPERCONDUCTING GROUNDING LINKS

FIGURE 3 INITIAL RESISTANCE VS. TEMPERATURE (T_c) CURVE FOR SUPERCONDUCTING GROUNDING LINKS

FIGURE 4 INITIAL RESISTANCE VS. TEMPERATURE (T_c) CURVE FOR SUPERCONDUCTING GROUNDING LINKS

FIGURE 5 TYPICAL TRANSITION CURVE OF A SUPERCONDUCTING GROUNDING
 LINK TAKEN AT CLEMSON ($T_c = 88K$)

FIGURE 6 TYPICAL TRANSITION CURVE OF A SUPERCONDUCTING GROUNDING
LINK TAKEN AT SRS ($T_c = 89K$)

FIGURE 7 RESISTANCE VS. HOURS FOR SAMPLE 203
0-1000 HOURS

FIGURE 8 RESISTANCE VS. HOURS FOR SAMPLE 203
1000-2000 HOURS

FIGURE 9 RESISTANCE VS. HOURS FOR SAMPLE 203
2000-3000 HOURS

FIGURE 10 RESISTANCE VS. HOURS FOR SAMPLE 204
0-1000 HOURS

FIGURE 11 RESISTANCE VS. HOURS FOR SAMPLE 204
1000-2000 HOURS

FIGURE 12 RESISTANCE VS. HOURS FOR SAMPLE 204
2000-3000 HOURS

FIGURE 13 RESISTANCE VS. HOURS FOR SAMPLE 213
0-1000 HOURS

FIGURE 14 RESISTANCE VS. HOURS FOR SAMPLE 213
1000-2000 HOURS

FIGURE 15 RESISTANCE VS. HOURS FOR SAMPLE 213
2000-3000 HOURS

FIGURE 16 123 MATERIAL DEGRADATION CHECK OF SAMPLES 203, 204, AND 213.

FIGURE 17 TEMPERATURE AND SYSTEM PRESSURE VS. HOURS
0-1000 HOURS

FIGURE 18 TEMPERATURE AND SYSTEM PRESSURE VS. HOURS
1000-2000 HOURS

FIGURE 19 TEMPERATURE AND SYSTEM PRESSURE VS. HOURS
2000-3000 HOURS

FIGURE 20 THE PARTIAL PRESSURES OF VARIOUS GASES PRESENT IN THE VACUUM SYSTEM AND THEIR CHANGE WITH TIME

END

**DATE
FILMED**

4 / 17 / 92