PYRITE SURFACE CHARACTERIZATION AND
CONTROL FOR ADVANCED FINE COAL
DESULFURIZATION TECHNOLOGIES

DOE/PC/90295--T5

DE92 007850

DOE Grant No: DE-FG22-90PC90295

Third Quarterly Technical Progress Report
(March 1, 1991--May 30, 1991)

by

Xiang-Huai Wang (Principal Investigator)

J. W. Leonard, B.K. Parekh (Co-PIs).

A.M Raichur and Chengliang Jiang (Graduate Students)

Department of Mining Engineering and
Center for Applied Energy Research,
University of Kentucky,
Lexington, Kentucky 40506

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

MASTER

TABLE OF CONTENTS

Summary	 1
Introduction	 3
Description of Experimental Approaches	... 3
A. Electrochemical Techniques	 4
B. Contact Angle Measurements	 5
C. Film Flotation Tests	 6
Results and Discussion	... 6
I. Surface Hydrophobicity Characterization	 6
I.A Contact Angle Measurements	7
I.B Film Flotation Tests	 8
II. Electrochemical Studies	 9
Future Work	10
References	12
List of Figures	13

SUMMARY

This report is concerned with progress made during the third quarterly period, i.e., from March 1, 1991 to May 31, 1991, for the project entitled "Pyrite surface characterization and control for advanced fine coal desulfurization technologies", DE-FG22-90PC90295.

The objective of this project is to conduct extensive studies on the surface reactivity of pyrite by using electrochemical, surface analysis, potentiometric and calorimetric titration, and surface hydrophobicity characterization techniques and to correlate the alteration of the coal-pyrite surface with the efficiency of pyrite rejection in coal flotation. The products as well as their structure, the mechanisms and the kinetics of the oxidation of coal-pyrite surfaces and their interaction with various chemical reagents will be systematically studied and compared with that of mineral-pyrite and synthetic pyrite to determine the correlation between the surface reactivity of pyrite and the bulk chemical properties of pyrite and impurities. The surface chemical studies and the studies of floatability of coal-pyrite and the effect of various parameters such as grinding media and environment, aging under different atmospheres, etc. on thereof will lead to identifying the causes and possible solutions of the pyrite rejection problems in coal cleaning.

The surface hydrophobicity of coal-pyrites and ore-pyrites has been characterized by film flotation tests and contact angle measurements. The film flotation results indicate that pyrite samples from different sources have quite similar surface hydrophobicity which is close to that of the coal (Upper Freeport) when prepared by dry grinding. The average critical surface tension of wetting (γ_c) determined by film flotation tests is 35 to 45 dyne/cm. Surface cleaning by ultrasonication and washing with EDTA leads to lower critical surface tension of wetting (γ_c), indicating that the hydrophilic surface layers are selectively removed. Wet grinding affects adversely the surface hydrophobicity of the pyrites. Contact angle measurements with the Illinois No.6 coal-pyrite demonstrate that

slightly to moderately oxidized surfaces have greater hydrophobicity than freshly wet ground surfaces.

The electrochemical behavior of pyrite electrodes in highly alkaline solutions (pH=10-12) has been studied. Except for the coal-pyrite received from Pittsburgh No.8 and Kentucky No.9 coal mines, a rotation-dependent oxidation peak (I) is observed for all the other pyrite electrodes at a potential of about 300 mV vs SCE. This oxidation peak is characterized by the following features:

- (1) the peak potential is nearly independent of the solution pH in the pH range of 10-12.
- (2) the peak current increases with increasing solution pH.
- (3) the peak becomes a plateau when the electrode is rotated, and the limiting current is a linear function of the square root of rotation speed.

The following reaction is suggested to be responsible for this oxidation peak and control the initial oxidation process of the pyrite surface:

This reaction is controlled by the mass-transportation. At higher potential, pyrite surface is oxidized to form ferric hydroxide, elemental sulfur and sulfoxy anions.

No well-defined oxidation or reduction peaks have been observed for the two coal-pyrite electrodes from Kentucky No.9 coal and Pittsburgh No.8 coal seams.

INTRODUCTION

In many U.S. coal deposits, pyritic sulfur is predominant and its removal from the coal could meet acid rain control legislation standards. The first requirement for the removal of intimately locked fine pyritic sulfur from coals is to grind the coal to an ultrafine size to liberate pyrite particles. Such ultrafine pyrite particles cannot be separated from coal by conventional physical washing methods. Therefore, advanced coal cleaning technologies need to be developed. Froth flotation, agglomeration and flocculation have shown the potential for removing pyritic sulfur from coal. These techniques are based on differences in the surface properties, particularly the hydrophobicity, of coal and coal-pyrite. However, rejection of pyrite from coal by these surface-based techniques has been a very elusive problem. It has been observed that the rejection of pyrite varies greatly from one coal seam to another or even from the day to day operation within the same coal seam. The causes of such problems are complex and have not been well characterized. The aim of this project is to conduct comparative studies on the surface properties of coal-pyrite from different coal deposits, mineral pyrite and synthetic pure pyrite. Such systematic studies will elucidate the correlation of pyrite surface properties/reactivity with bulk chemical composition, structure, impurities and superficial alteration.

DESCRIPTION OF EXPERIMENTAL APPROACHES

In addition to the superficial chemical alteration of pyrite, such as surface oxidation and adsorption of various chemicals on pyrite surfaces, bulk chemical composition variation may also greatly change surface properties and reactivity of pyrite. Stoichiometrically, pyrite has the chemical composition of iron disulfide, FeS_2 . However, natural iron disulfides show a composition deviation from FeS_2 , with the ratio of S/Fe varying from 1.9 to 2.1. They may also contain a great amount of impurities as crystalline inclusions. This is particularly true for coal pyrites which usually contain carbon and

organic materials. Natural iron disulfides occur in two crystalline modifications: pyrite and marcasite. Pyrite has a cubic structure, while marcasite has an orthorhombic structure. Their chemical reactivity, particularly to oxygen, is considerably different. Furthermore, the geological conditions for the formation of pyrite from different sources, especially in coal, are different. Finally, pyrite may exist in p-type or n-type semiconducting form. In this project, these bulk chemical parameters will be characterized in detail and their contribution to the surface properties of pyrite will be systematically studied.

Experimental Methods

A. Electrochemical Techniques

Electrochemical techniques have been widely used to study the nature, mechanisms and kinetics of redox reactions at sulfide surfaces. The following electrochemical techniques have been or will be used in the present research: cyclic voltammetry, steady state polarization, chronopotentiometry (or galvanostatic polarization), and AC impedance/capacitance spectroscopy. The principles and usefulness of these techniques have been described in electrochemistry textbooks (e.g, Bard & Faulkner, 1980). A standard three-electrode system is used in this research.

Electrochemical Set-UP: A pyrite electrode is the working electrode. The counter electrode is a platinum electrode. The potentials were measured against a saturated calomel electrode (SCE) which potential is related to the standard hydrogen scale by the following relationship:

$$E_{SCE} \equiv E_h - 245 \text{ (mV)}$$

The electrochemical system used in the present study consists of a EG&G Princeton Applied Research (PAR) Model 273 potentiostat/galvanostat, a Salatron Model 1255 HF frequency response analyzer (FRA) and a PAR model 660 rotating-disc electrode apparatus. The system, including data acquisition, is operated by a 386 IBM computer. All other measurements were performed with a user-modified Headstart Creative Software.

The rotating-disc electrode (RDE) technique enable one to study the effect of rotating the electrode on the reaction processes occurring at the electrode surface, and thereby to distinguish the solution species involved reactions from solid species reactions. The EG&G Princeton Applied Research manufactured RDE system has several drawbacks. Therefore, the RDE has been modified so that only the lower portion of the shaft rotates, while the upper part remains stationary. This enables the upper portion to keep tight contact with the cell lip. The cell will thus be sealed from the ambient, which prevent any oxygen/air entrance into the electrochemical cell. The atmosphere in the cell can be well controlled.

Pyrite Electrodes: The respective pyrite samples were cut to a cubic shape and attached to brass rods using conducting carbon glue. The electrodes were moulded in epoxy resin and one face was initially ground using SiC polishing papers 400 and 600 grit to expose to the electrolyte. Before each measurement, the electrode was polished using 0.05 μm Alumina in air with distilled, deionized and deoxygenated (DDD) water and rinsed with DDD water. The measured geometric surface areas were used for calculating the current density.

B. Contact Angle Measurements

The hydrophobicity characterization of pyrite surfaces have been conducted by measuring the contact angles with a Ramer-Hart contact angle goniometer. An enviromental chamber for the contact angle goniometer has been set up. Using this chamber, the atmosphere and humidity for the contact angle measurement using the sessile drop method can be controlled. Contact angle measurements can be carried out in nitrogen, oxygen, carbon dioxide or the atmosphere simply by connecting the environmental chamber to the gas plugs. The relative humidity is controlled by passing the gas through a bottle which is filled with distilled water.

C. Film Flotation

The surface hydrophobicity of solid powders has been studied using film flotation tests. This technique was developed by Fuerstenau and co-workers [1987] and Diao [1990] for the surface characterization of coal powders. Their studies showed that it is a good technique for characterizing the surface hydrophobicity of fine particles. In the film flotation tests, aquatic methanol solutions (i.e., mixtures of water with methanol at different volume ratio) possessing a wide range of surface tensions (from 20 to 72 dyne/cm) are used. 100 milligrams of particles of size 100x150 mesh are carefully (in single layer of particles) spread over the surface of aquatic methanol solution. Depending on the surface hydrophobicity of the particles, portions of the particles will stay at the surface (hydrophobic), while others are immersed in the solution (hydrophilic). The floated particles are then collected by vacuum sucking through a small glass tube, dried and weighed. The percentage of the floated can be calculated and is plotted against the surface tension of the solution.

RESULTS AND DISCUSSION

A large number of experiments have been performed on the surface characterization of the pyrite samples collected from different coal seams. Comparative measurements were also made with mineral and synthetic pyrite samples. Although the results are interesting, so far it has not been possible to understand most of the results. Therefore, only a few examples will be given here.

I. Surface Hydrophobicity Characterization:

Contact Angle Measurements: Figure 1 shows the contact angle variation with time for an Illinois No.6 coal-pyrite. In this study, the sample was first polished then put in 100 ml solution which was saturated with one of the gases (nitrogen, oxygen or carbon

dioxide). Note that in case of carbon dioxide, it was found that the pH of the solution dropped to about 4 after bubbling CO₂ gas for ten minutes. NaOH solution was added to the solution to keep the solution pH at the neutral range (6.5-7.5). At a specified time, the pallet was taken out from the solution, rinsed with distilled water and put in the measuring chamber which was connected to nitrogen. After about one minute (to let the surface dry), three water droplets of 2 μ l was put on the different surface sites, and the contact angle of each droplet on the surface was read immediately. The values in Fig.1 are generally the average values of 3 separate tests (i.e., 9 readings).

It is interesting to see that the contact angle of the pyrite sample changes with the time that it has been immersed in the solution. Under oxygen saturated solutions, the contact angle first increases, reaches a maximum value of close to 80 degree, and then decreases upon prolonged reaction. Under nitrogen, the contact angle also increases with time but much more slowly than under oxygen. These studies indicates that slight to moderately oxidized pyrite surfaces are more hydrophobic than the freshly cleaned surface. Interestingly, under carbon dioxide, the contact angle decreases with time that the surface is exposed.

Our comparative studies (see previous quarterly reports of this project) with other pyrite samples (marcasite from Indian and cubic Spanish ore pyrite) show that the contact angles of "clean" surfaces (measured on freshly polished surfaces within 10 seconds) indicates that the Il.#6 coal pyrite displays much higher contact angles than the cubic ore pyrite from Span. However, both the coal pyrite and ore pyrite show a similar variation of contact angle with pH. The contact angles of the marcasite are more or less constant in the pH range studied and are higher than that of Il.#6 coal pyrite and cubic ore pyrite. It should be noted that the contact angles shown in Fig.1 are not equilibrium values. It was noted that the contact angles for the pyrite sample studied decrease with increasing contact time. The reasons for the depletion of the water droplet are complex and not understood at this time.

Film Flotation: The results of film flotation tests are presented in Fig.2 for the four pyrite samples (coal pyrite samples from Ky No.9, Il. No.6 and Pa. No.8 and ore-pyrite from Peru) prepared by dry grinding using a mortar and pestle. The results show that the surface hydrophobicity of the three coal-pyrites are quite similar and have an average γ_c (i.e., at 50% floated) 40-48 dyne/cm. However, the ore-pyrite from Peru is more hydrophobic than the coal-pyrite samples and exhibits a γ_c of about 34 dyne/cm. This is not in agreement with the results reported previously (see the 2nd quarterly report). The discrepancy may be attributed to two reasons. First, the samples of the ore-pyrite used in the tests were different. Secondly, the preparation procedures of samples were not the same. These problems are under investigation.

Figure 3 compares the film flotation results of the coal, coal-pyrite and ore-pyrite after ultrasonication. The procedures for the ultrasonic treatment are as follows: 10 grams of the prepared samples were suspended in a 100 ml distilled water. The suspension was ultrasonically treated for one minute, then centrifuged and the pyrite particles separated. These procedures were repeated until the pH of the supernate solution was about 7. It can be seen from Fig.3 that after ultrasonication, the coal-pyrite samples become almost identical with a γ_c value of about 37 dyne/cm which is quite close to that of coal (from Upper Freeport) and the ore-pyrite (from Peru). The ultrasonication has only slight effect on the γ_c of the coal and the ore-pyrite.

The effects of the different chemical and mechanical "cleaning" treatment of the samples on the film flotation behavior are shown in figures 4-7. EDTA-a strong iron-complexing agents, has similar effect to the ultrasonication treatment, that is, it cleans the surface by removing the surface iron hydroxide. The results are in good agreement with that of Wang and Forssberg [1990] and Chander et al [1991]. However, wet grinding renders all the pyrite samples more hydrophilic, while it has little effect on the coal sample studied.

II. Electrochemical Studies

The initial oxidation processes of pyrite surfaces are of great importance in controlling the inherent surface hydrophobicity of pyrites. In the second quarterly report, the electrochemical behavior of pyrite from coal and ore sources and synthetic pure pyrite in acidic solutions ($\text{pH}=1-4$) has been compared. It was found that there was no significant difference in the open-circuit potential and cyclic voltammetry of the different pyrite electrodes studied.

During this reporting period, the surface oxidation of pyrite in alkaline solutions ($\text{pH}=10-12$) have been studied. Eight different pyrite electrodes (see Table 1) were prepared and studied. Based on the similarity of the electrochemical behavior of the electrodes, they can be separated into two classes: class A and B. PAPY and KYPY belong to class B, while the rest all belong to class A. Typical cyclic voltammograms for the class A electrode are shown in Fig.8. At a stationary electrode, when the potential sweep is initiated in the positive-going direction from the mixed-potential (ca., -100 to -150 mV, at $\text{pH}=10$), an significant oxidation peak (peak I) is observed at potential around 300 mV vs SCE. Another prominent oxidation peak (II) appears when the potential is above 500 mV vs SCE. Interestingly, when the electrode is rotated, peak I becomes a plateau, while

Table 1 Pyrite electrodes used in the electrochemical studies

Abbreviation	Source	Semiconducting Properties
PAPY	Coal-pyrite from Pittsburgh No.8 Coal	n-type
KYPY	Coal-Pyrite from Kentucky No. 9 Coal	n-type
SPPY	Ore Pyrite from Spain	p-type
PUPY	Ore-Pyrite from Peru	p-type
SWPY	Ore-Pyrite from Boliden, Sweden	p-type
CNPY	Coal Pyrite from Sichuan Coal Seam, China	p-type
ICPY	Coal-pyrite from Illinois No.6 coal (Lilly)	n-type
Marc	Marcasite from Indiana	p-type

peak II shows no significant change. At lower potentials, good-shaped reduction peak, III, is observed at potentials of -800 mV (peak III) on the negative-going sweep and oxidation peak, IV, at -300 mV on the second positive going direct. The currents of two peaks are not significant on the stationary electrode. In general, the results are in good agreement with published studies (Ahlberg, Forssberg and Wang, 1990).

The rotation dependence of peak I is of great interest and has thus been extensively studied. Figure 9 shows the variation of the limiting current of I with rotation speed. It can be seen that the limiting current of I increases with increasing rotation speed. Furthermore, by plotting the limiting current against the square root of rotation speed, two perfectly parallel straight lines are obtained, as shown in Fig.10, with the back scan current passing through the origin. These results indicates that the peak (I) must be oxidation of a soluble species at the pyrite surfaces. The back sweep current is the true current resulting from this oxidation reaction, while the difference in current between the forward and back scan is the oxidation of pyrite surface under these potentials. Figure 11 shows the dependence of peak I on the solution pH. It can be seen that the peak increases significantly with increasing pH from 10 to 12.

Further studies demonstrate that this phenomenon can be observed on all pyrite electrodes except for PAPY and KYPY (i.e., class A), indicating that it is independent of the sources, crystal structure and semiconducting properties, see Fig.12 for ICPY, for example. From these studies, it is suggested that the initial oxidation of the pyrite surface is controlled by the following reaction (peak I):

Peak II is the oxidation of the pyrite surface. Our present experimental data, however, are not sufficient to conclude the exact reaction stoichiometry. More extensive studies, particularly surface spectroscopic studies, are needed. Thermodynamic calculations of the pyrite system are helpful, but not decisive. The Eh-pH stability

diagrams of the Fe-S-H₂O system are shown in Fig. 13 and Fig. 14. Thermodynamically, pyrite will be oxidized to ferric hydroxide and sulfate (Fig.13). However, the kinetics strains and the very large overpotential needed for elemental sulfur oxidation into sulfate may restrict the oxidation of the pyrite to some metastable species, for example, to sulfite and thiosulfate, as shown in Fig.14. Thus, the overall reaction of pyrite oxidation can be expressed by the following reaction is very complex. It probably consists of a number of parallel reactions including the formation of elemental sulfur, thiosulfate and sulfate. The relative proportion will depend on the electrode potential and hydrodynamic conditions.

The electrochemical behavior of the class B pyrite electrodes are significantly different. Figure 15 shows the typical cyclic voltammograms of the KYPY electrode. The PAPY electrode follows exactly the same electrochemical behavior. It can be seen from Fig.15 that there is no well-defined oxidation or reduction peaks. Similar results were reported by other investigator [Wordsworth et al, 1991].

FUTURE WORK

So far, electrochemical studies have been conducted in extreme pH solutions, i.e., either highly acidic or highly alkaline. Next, the electrochemical behavior of the different pyrite electrodes in solutions of pHs from a weakly acidic to a weakly alkaline (4-10) range will be systematically investigated. ESCA, AES and SEM techniques will be used to directly identify the surface chemicals.

The surface hydrophobicity of the different pyrite samples will be further quantitatively characterized using a new method developed very recently by the PI of this project. It is anticipated to use the microcalorimetric method to measure the heat of wetting to study the surface hydrophobicity of the synthetic pyrite samples.

REFERENCES

- Bard, A. and Faulkner, L.R., (1980), *Electrochemical Methods: Fundamentals and Applications*. John Wiley & Sons, 705pp.
- Chander, S., (1991), Oral presentation at 1991 SME annual meeting, Denver, Co.
- Chander, S. and Aplan, F.F., (1990), *Surface and Electrochemical Studies in Coal Cleaning*, Final Report, DE-FG22-85PC80523. 97pp.
- Diao, J.L., (1990), *Coal Surface Characterization by Film Flotation*, Ph.D. Thesis, University of California, Berkeley, Ca.
- Ahlberg, E., Forssberg, E. and Wang, X.H., (1990), Surface oxidation of pyrite in alkaline solution, *Journal of Applied Electrochemistry*, Vol.20, pp1033-1039.
- Wang, X.H., (1989), *The chemistry of Flotation, Activation and Depression of Iron-Containing Sulfide Minerals*. Ph.D. Thesis, Lulea University, Sweden. 514pp.
- Wang, X.H. and Forssberg, (1990) EDTA Induced flotation of sulfide minerals. *Journal of Colloid and Interface Science*, Vol.140, pp217-226.
- Wang, X.H., Parekh, B.K. and Leonard, J.W., (1990), Pyrite surface characterization and control for advanced coal desulfurization technologies. First Quarterly Technical report, DE-PS22-90PC90295.

Fig.1 Contact angle of a water droplet on an Illinois coal-pyrite as a function of the time of the surface immersed into the solutions saturated with nitrogen, oxygen or carbon dioxide.

Fig.2 Flotation percentage as a function of surface tension of aquatic methonal solution for pyrite from different sources.

Fig.3 Flotation percentage as a function of surface tension of aquatic methanol solution for pyrite from different sources after cleaning by ultrasonication.

Fig.4 Flotation percentage of ore-pyrite from Peru as a function of surface tension of aquatic methonal solution after different chemical and mechanical treatment.

Fig.5 Flotation percentage of Kentucky No.9 Coal-Pyrite as a function of surface tension of aquatic methanol solution after different chemical and mechanical treatment.

Fig.6 Flotation percentage of Illinois Coal-Pyrite as a function of surface tension of aquatic methonal solution after different chemical and mechanical treatment.

Fig.7 Flotation percentage of Pittsburgh No.8 Coal-Pyrite as a function of surface tension of aquatic methonal solution after different chemical and mechanical treatment.

Fig. 8 Cyclic voltammograms of ore-pyrite (from Span) at pH=10.
Initial sweep started from OCP in positive direction.
A--stationary; B--rotation speed: 500 RPM.

Fig.9 Linear sweep voltammograms of ore-pyrite (from Peru) at different rotation speed. Solution pH=10. Sweep rate: 20 mV/s. Sweeps initiated in from the open-circuit potential.

Fig.10 Limiting current of peak I as function of the square root of rotation speed for ore-pyrite (from Peru) at pH=10. Both the Forward scan and back scan are plotted. Sweep rate: 20 mV/s.

Fig.11 Cyclic voltammograms of stationary ore-pyrite electrode (from Peru) in solutions of different pH from 10 to 12.

Fig.12 Linear sweep voltammograms of the Illinois No.6 coal-pyrite electrode at different rotation speeds at pH=10.0. Only the forward sweeps are shown. Sweep rate: 20 mV/s.

Fig.13 Eh-pH stability diagram for the iron-sulfur-water system at total concentrations of $[\text{Fe}] = [\text{S}] = 1.0 \cdot 10^{-3} \text{ M}$.

Fig.14 Eh-pH stability diagram for the iron-sulfur-water system at total concentrations $[\text{Fe}] = [\text{S}] = 1.0 \cdot 10^{-3} \text{ M}$, metastable sulfite is considered as the "final" oxidation product, i.e., species with oxidation state higher than S(IV) are excluded.

Fig.15 Cyclic voltammograms of Kentucky No.9 coal-pyrite electrode at pH=10.0. Initial sweep started in negative-direction from the open-circuit potential. Sweep rate: 20 mV/s.

END

DATE
FILMED

4 102 192

I