DOE/ER/54107--2

DE92 005525

DEVELOPMENT OF A CHEMICAL KINETIC
MEASUREMENT APPARATUS AND
THE DETERMINATION OF THE REACTION
RATE CONSTANTS FOR
LITHIUM-LEAD/WATER INTERACTIONS

Progress Report

October 1990 - September 1991

Dr. Paul Orleans Biney
Mechanical Engineering Department
Prairie View A&M University
Prairie View, Texas 77446

November 1991

PREPARED FOR THE U.S. DEPARTMENT OF ENERGY UNDER GRANT NUMBER
DE-FG05-90ER54107

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

MASTER

zhy
DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

Technical Progress Report For the Period
October 1, 1990 - September 20, 1991

On the Development of a Chemical
Kinetic Measurement Apparatus and
the Determination of the Reaction Rate Constants
For
Lithium-Lead/Steam Interaction

Prepared by:

Dr. Paul Orleans Biney
Department of Mechanical Engineering
P.O. Box 397
Prairie View A&M University
Prairie View, Tx. 77446
Telephone: 409-857-4023
Fax: 409-857-2222

Submitted to the

OFFICE OF FUSION ENERGY
DEPARTMENT OF ENERGY

Through the

Prairie View A&M Research Foundation
P.O. Box 3578
College Station, Texas 77843
October 15, 1991

Funded Project Period
09/21/90 - 9/20/91

PRINCIPAL INVESTIGATOR

Paul Orleans Biney, Ph.D.
Assoc. Professor
Mechanical Engineering Dept.

TABLE OF CONTENTS

	Page
ABSTRACT	
I. INTRODUCTION	1
A. Objectives of Research	1
B. Project Schedule	1
C. Assignment of Graduate and Undergraduate Research Assistants	2
II. PRELIMINARY DESIGN OF EXPERIMENTAL SYSTEM.....	5
A. Experimental Test Matrix.....	5
B. Preliminary System Design	8
C. Detailed System Design	8
(i) Lower reaction Vessel	10
(ii) Furnace	10
(iii) Upper Vessel.....	13
(iv) Mid-Section Butterfly Valve.....	13
(v) Design of Convection Coil.....	16
D. Sub Assembly and Operation of System	17
E. Data Acquisition and Control System	21
III. DATA REDUCTION AND ANALYSIS	25
A. Preliminary Determination of Hydrogen Concentration and Pressure in the Gas Region of the Upper Chamber	25
B. Determination of Mass of Hydrogen Generated	29
(i) Mass of Argon and Hydrogen	29
(ii) Gas Leakage Correction	31
IV. MASS TRANSFER MODEL FOR LITHIUM	33
A. Basic Assumptions	33
B. Model Equations	34

V. PROBLEMS ENCOUNTERED AND FUTURE DIRECTIONS OF RESEARCH	39
A. Problems Encountered in the First Year	39
B. Future Directions of Research	39
VI. CONCLUSIONS	43
REFERENCES	44
NOMENCLATURE	45

LIST OF FIGURES

		Page
Figure 1	First Year Project Schedule.....	3
Figure 2	Preliminary Design of Experimental System	9
Figure 3	Lower Reaction Vessel	11
Figure 4	Furnace	12
Figure 5	Upper Vessel	14
Figure 6	Butterfly Valve	15
Figure 7	Partial Assembly of Experimental System ..	19
Figure 8	Data Acquisition and Control System	22
Figure 9	Mass Transfer Coordinate System	35
Figure 10	Original First Year Schedule	41
Figure 11	Second Year Project Schedule	42

LIST OF TABLES

	Page
Table 1 Experminetal Test Matrix for Lithium-Lead/ Water Reaction	6
Table 2 Steam Reaction	7
Table 3 Design Specifications for Cooling Coil	18
Table 4 Specifications for Analog Input/Output	23
Table 5 Specifications for Digital Input/Output	24
Table 6 Pressure and Mole Fractions of Hydrogen generated for $\text{Li}_{17}\text{Pb}_{83}$ /Water Reaction, $T_w =$ 80°C, 5% Reaction	27
Table 7 Pressures and Mole Fractions of Hydrogen generated for $\text{Li}_{17}\text{Pb}_{83}$ /Water Reaction, $T_w =$ 100°C, 10% Reaction	28

ABSTRACT

An experimental set-up for accurate measurement of hydrogen generation rate in Lithium-Lead ($\text{Li}_{17}\text{Pb}_{83}$) Steam or water interactions is being designed. The most important features of the design include a pneumatic actuated quick opening and closing butterfly valve used to control the reaction time and the placement of all measuring devices below a water line to minimize leakage of the hydrogen collected. A PC based data acquisition and control system provides remote process sequencing, acquisition and control of all major components of the set-up.

I. INTRODUCTION

This technical progress report covers work done on this project for the period October 1, 1990 through September 30, 1991. Graduate and Undergraduate Research Assistants were assigned to the project in October of 1990, after which some time was spent to bring the students up to date on some important theoretical and design aspects needed to achieve project objectives.

The greatest challenge in the design is ensuring a system with minimum leakage rate in order to obtain accurate accounting of reaction product gases. This greatly affects the placement of thermocouples, transducers and other instruments needed in the design.

A. Objectives of Research

The objectives of the research are:

- (i) The design and construction of an experimental set up that can be used to obtain accurate measurements of hydrogen generation rate during the initial and subsequent stages of liquid metal/water or steam reactions.
- (ii) The use of data collected in conjunction with an improved liquid metal transport reaction model developed to determine the empirical chemical kinetics reaction rate constants.
- (iii) To involve minority graduate and undergraduate students in this research.

B. Project Schedule

To enable the objectives listed above to be met, the overall project was divided into 10 main steps, namely

1. The search for qualified graduate and undergraduate students for the research and their subsequent introduction to the project.
2. Preliminary design of experimental system and determination of experimental test matrix.
3. Identification of manufactures/vendors and price list for all major components in preliminary design.
4. Modification of preliminary design. The final design of the experimental system.
5. Production of Working Drawings.
6. Procurement of components and modification of Liquid Metal Transport Reaction Model for experimental analysis.
7. Construction of experimental system.
8. Testing & correction of experimental system.
9. Data Collection on Hydrogen generation rate:
 - (a) Liquid Lithium-lead/water reaction
 - (b) Liquid Lithium-lead/Steam reaction
10. Analysis of Data using the modified liquid metal Transport Reaction Model to obtain the empirical reaction rate constants.
11. Preparation of final Research Report.

Figure 1 shows the project schedule for the first year of the project. The details of the work done at the various phases of the project are described in this report.

C. Graduate and Undergraduate Research Assistants.

The first phase of the project involved obtaining qualified graduate and undergraduate students to work on the project. In this regard, James Akpan, an MS graduate student in the Mechanical Engineering Department was appointed a graduate Research Assistant and is working on this research for his MS

Figure 1 Revised First Year Schedule

Thesis. In addition, Robert Tetteh, who has been voted as the most outstanding undergraduate Mechanical Engineering Junior student, expressed great interest in the research work and was hired as an Undergraduate Assistant in the project. While James will primarily be in charge of the overall research, his concentration will be in the more technical aspects of data acquisition, analyses and chemical kinetics of the work. Robert will be involved in the design of the system, procurement of components and assembly of the system. James and Robert have spent a considerable portion of the first phase of the project in literature research into data acquisition, liquid metal/water/steam reactions, chemical reaction kinetics and fusion safety in general. In addition, Mr. Ali Ekhlassi was assigned to work on the project as a Technician for the period September 1, 1991 to December 31, 1991. Mr. Ali Ekhlassi will be responsible for fabrication assembly, and testing of the experimental apparatus. Mr. Ekhlassi is an experienced Technician whose services will be extremely beneficial at this stage of the project.

II. PRELIMINARY DESIGN OF EXPERIMENTAL SYSTEM

A. Experimental Test Matrix

To enable us determine the operating condition of the system to be designed, a detailed experimental matrix was developed. The primary variable to be controlled during the experiment are:

1. Initial Liquid Metal Temperature T_{LM}
2. (a) Initial Water Temperature T_w or
(b) Initial Vapor temperature T_v
3. Initial System Pressure P_i
4. Total reaction time t_R and
5. Initial Mass of liquid Metal M_{LM}

To ensure that the surface area for reaction is constant throughout an experiment, the area will be the maximum that prevents Taylor instability. The Secondary variables to be measured include:

1. Reaction product gas temperature T_g .
2. Reaction product gas pressure P_g .
3. Hydrogen Concentration in reaction product gas C_{H_2} .
4. Liquid Metal Temperature T_{LM} .
5. Lower gas chamber volume V_d .
6. Low gas chamber pressure P_d .
7. Lower gas chamber temperature T_d .
8. Initial Upper Gas Chamber Volume V_u .

Table 1 Experimental Test Matrix for
Lithium Lead/Water Reaction

Liquid Metal Temperature °C	Initial Water Temperature °C	Reaction Time s	Liquid Metal Mass gm
350	90	0.5, 1.0, 2.0, 200	60
350	90	0.5, 1.0, 2.0, 200	30
350	80	0.5, 1.0, 2.0, 200	30
350	70	0.5, 1.0, 2.0, 200	60
400	60	0.5, 1.0, 2.0, 20, 200	50
400	60	0.5, 1.0, 2.0, 20, 200	50
400	90	0.5, 1.0, 2.0, 20, 200	40
400	90	0.5, 1.0, 2.0, 20, 200	70
400	70	0.5, 1.0, 2.0, 20, 200	50
400	80	0.5, 1.0, 2.0, 20, 200	20
400	90	0.5, 1.0, 2.0, 20, 200	20
400	60	0.5, 1.0, 2.0, 20, 200	30
400	60	0.5, 1.0, 2.0, 20, 200	30
500	90	0.5, 1.0, 2.0, 15, 200	60
500	90	0.5, 1.0, 2.0, 15, 200	30
500	70	0.5, 1.0, 2.0, 15, 200	30
600	90	0.5, 1.0, 2.0, 15, 200	50
600	90	0.5, 1.0, 2.0, 15, 200	50
600	70	0.5, 1.0, 2.0, 15, 200	20
650	90	0.5, 1.0, 10, 200	50
650	80	0.5, 1.0, 10, 200	50
650	70	0.5, 1.0, 10, 200	50

Table 2 Experimental Test Matrix
Lithium-Lead/Steam Reaction

Liquid Metal Temperature °C	Initial Steam Temperature °C	Reaction Time s	Liquid Metal Mass gn
350	100	50,200	50
350	200	50,200	50
400	100	50,200	60
400	150	25,50,200	60
400	150	50,200	30
400	250	25,50,200	50
400	250	25,50,200	30
500	150	25,50,200	50
500	200	25,50,200	50
600	100	25,50,200	50
600	200	25,50,200	50
650	150	25,50,200	50
650	200	25,50,200	50

The complete preliminary proposed experimental matrix is shown in Table 1. Table 2 shows the test matrix if we decide to perform the steam test.

B. Preliminary System Design

Figure 2 shows the preliminary design that was initially considered. In this design, significant changes have been made in the upper chamber and mid-section area of the apparatus. The attachment of the pressure transducers, thermocouples, and the convection coil have been located below the water level to minimize leakage of the hydrogen gas produced. The transducer and thermocouple wells are being modified by replacing them with a design that allows direct contact of the thermocouples with the gas and water regions. The convection coil is passed through a flanged part at the base of the upper chamber and below the water level. The principle behind these changes are that liquid leakages are far easier to control than hydrogen gas leakage. Thus we want to ensure that there are no flanged or screwed joints in the region where the gas collects after the reaction.

C. Detailed System Design

Several changes have been made in the preliminary design shown in figure 2, the most important of which is the cooling method for the butterfly valve section. As a result of the high temperatures encountered by the lower reaction chamber and subsequently conducted to the butterfly valve, it is extremely important that the section close to the valve seat be effectively

Figure 2 Preliminary Design of Experimental System

cooled to maintain proper, functioning of the valve.

(i) Lower Reaction Vessel

Figure 3 shows the details of the lower reaction vessel which will contain the liquid lithium lead. The flange at the top is an integral part of this section. The flange has an internal cooling channel just beneath the butterfly valve seat. Chilled water from a bath will be circulated through this channel to maintain satisfactory temperatures at the valve section. This section is constructed of HT-9 steel. This type of steel was selected because, extensive work conducted by Chen and Qian [1] on the corrosion of various types of steel by liquid lithium indicated that whereas 316 and other steels are highly corroded by liquid lithium at elevated temperatures, HT-9 steel has extremely high resistance to lithium corrosion. At the lower section, a 4 inch long NANMAC eroding tip fast response thermocouple is permanently inserted - The tip of this thermocouple makes contact with the liquid metal and thus directly measures the liquid metal temperature. All basic dimensions of the lower reaction chamber are provided in Figure 3.

(ii) The Furnace

Figure 4 shows the details of the design of the furnace into which the lower section described in figure 3, containing the lithium-lead is inserted, and heated to required liquid metal temperature. Parts A and B constitute a Watlow semi cylindrical high watt density ceramic fiber heater (750 Watts). Two such

Figure 4 Furnace

heaters are used in the furnace providing a total heating power of 1500 watts. Parts C and D are cylindrical ceramic fiber insulation modules used to insulate the lower section of the furnace. Part E is made of ceramic fiber blanket insulation. The outer shell of the furnace is made of stainless steel sheet metal.

(iii) Upper Vessel

The upper vessel, constructed with 316 stainless steel is shown in Figure 5. Initially, space V contains saturated water vapor, whose temperature is measured using an adjustable probe NANMAC right angle thermocouple C, which also eventually measures the upper gas temperature once reaction is initiated. A second NANMAC thermocouple B measures the temperature of the water in the upper chamber. A pressure transducer A, measures the system pressure in the upper chamber. A convection coil D, connected to a constant temperature bath is used to control the initial temperature of the water. The upper chamber is bolted to the butterfly valve through a flange F.

(iv) Mid-Section Pneumatic Controlled Butterfly Valve

A pneumatic controlled 2-1/2 inch size 316 stainless steel butterfly valve shown in Figure 6 separates the lower reaction chamber from the upper collection chamber. The valve is an ANSI class 300 high temperature valve. The valve was chosen due to its negligible leakage characteristic, sealing capacity and cycle time (250 ms). The upper and lower sections of the apparatus are connected to the butterfly valve through a flange with a series

Figure 5 Upper Vessel

All Dimensions are in Inches

A = 4 1/8
B = 6
C = 4 1/16
D = 4

E = 1 7/8
F = 1 1/4
G = 3/8
H = 9/16
Q = 2 3/8

Figure 6 Butterfly Valve

of o-rings used to minimize leakage. The flange connection also facilitates easy disconnection of the lower portion of the apparatus for the purpose of loading and unloading the liquid-metal into and out of the vessel in a glove box. To ensure that the butterfly valve and its actuator are operated within their specified temperature range, the valve section is water-cooled internally as described earlier.

(v) Design of Convection Coil

The experimental determination of the rate of hydrogen production during Lithium-Lead/Water reaction involves two distinct stages, the heating stage and the reaction stage. During the heating stage, the lower portion of the apparatus is electrically heated to melt the lithium-lead and to bring it to the required initial temperature T_{LM} . The reaction stage begins when the butterfly valve is opened and water from the upper chamber makes contact with the liquid metal in the lower section. This stage ends when the butterfly valve is closed at the end of a pre-determined reaction time, t_R . During the heating stage, it is important to ensure that both the butterfly valve and the electrical resistance heating elements are maintained within their stated operating temperature range. It is also important to ensure that right size heaters and adequate insulation is provided to obtain a reasonable heating time (30-45 minutes). These require that a heat transfer analysis be done at the early design stages of the system to ensure that the system under design will satisfy the required constraints. A two-dimensional finite element analysis

has been used to analyze the heat transfer characteristics of the lower portion of the apparatus during the heating stage.

During the heating stage of the experiment, heat is transferred from the lower chamber to the upper chamber, and subsequently by convection to the water in that chamber. This heat has to be removed to maintain a constant water temperature in the upper chamber. The description below gives summary of analysis performed to ensure that the convection coil selected has adequate heat transfer area to remove this heat.

Finite element analysis described earlier indicated a total of 375 Watts of heat will have to be removed. Based on this a number of constant temperature baths were reviewed to provide the cooling capacity and flow. Also the pump characteristics of the baths were noted.

From the experimental test matrix given earlier in Table 1, the temperature of the pool of water outside the coil ranges from 60°C to 90°C. The above information, together with an assumed bulk inlet temperature of 5°C at the inlet of the coil were used to estimate the heat transfer area, the length of tube required, the head loss in the cooling coil circuit and the flow rate for the given system characteristics. The results of the coil design calculator are summarized in Table 3.

D. Sub Assembly and Operation of System

Figure 7 shows a partial assembly of the furnace, the lower reaction chamber, the mid-section pneumatic controlled butterfly valve, the cooling coil and the upper collection chamber. The furnace sections B,C and D; the lower section R; and the upper

Table 3 Design Specifications for Cooling Coil

Tube Material	316 Stainless Steel
Tube Inside Diameter	3/16 inch
Tube Outside Diameter	1/4 inch
Minimum tube Length required	28 inches
Design tube length	40 inches
Mean Coil diameter	1 3/8 inches
Bulk Fluid Inlet Temp	5°C
Flow Rate through Tube	5 liters/min

Figure 7 Partial Assembly of Experimental System

sections A,E,G,F and Q have been previously described.

During the heating stage of the process, the furnace is on and the sample of lithium lead O in lower reaction chamber R is heated to a predetermined temperature. The butterfly valve is closed and argon flows through solenoid valves K and L past the lower chamber and exits through solenoid valve M. Solenoid valve J is also opened and the system pressure in the lower chamber monitored by pressure transducer H and temperature by thermocouple S.

A 30 seconds count down time is planned prior to the opening of the butterfly valve. At the beginning of this count down period, valves M and K are closed to stop the argon flow at which time pressure transducer H and thermocouples monitor the pressure and temperature of the closed lower argon space in the lower chamber. Data obtained during this countdown phase will be used to determine the mass of argon in the lower chamber. At the end of the countdown period, valve L is closed, the butterfly valve N is opened and reaction between the lithium-lead and water is initiated and made to continue for a pre-determined period of time after which the butterfly valve is closed, Valve M opened and any hydrogen produced after that time is made to flow into a collection tank not shown in the figure. During the reaction period, the hydrogen produced collects above the water in the upper chamber, where the temperature and pressure are measured by F and E respectively. The timing, sequencing and control of all the solenoid valves and the pneumatic controlled butterfly valve are done through Keithly Measurement and Control System Model 575-2.

E. Data Acquisition and Control System

At the heart of the data acquisition and control system is a Keithley Model 575-2 Measurement and Control unit shown in Figure 8.

A summary of the analog input/output and digital input/output features of the unit are given in Tables 4 and 5 respectively. Sixteen of the 32 digital input/output channels will be dedicated for power control of on/off devices including all solenoid valves and the butterfly valve through the use of a power control modules and relay board.

A 16 channel thermocouple module capable of handling J,K,S,T, B,E and R single or mixed thermocouples and having an isothermal block is used for all temperature measurements.

Figure 8 Data Acquisition and Control System

Table 4 Analog Input/Output Features of Data Acquisition and Control System

Feature	Description/Range
SPEED	50,000 READINGS/S
RESOLUTION	16 BITS
FULL SCALE RANGES	+100mV, +200mV, +500mV +1V, +2V, +5V, +10V
CHANNELS	8 DIFFERENTIAL 16 SINGLE ENDED PLUS 8 ADDITIONAL SINGLE ENDED
ANALOG OUTPUT	
CHANNELS	2, SINGLE ENDED
OUTPUT RANGES	+10V, +5V, +2V, +1V
RESOLUTION	13 BITS

Table 5 Digital Input/Output and Power Control Features of Data Acquisition and Control System

Feature	Description/Range
CHANNELS	32 NON-ISOLATED, PROGRAMMABLE FOR INPUT OR OUTPUT IN GROUPS OF 8 CHANNELS. 16 CHANNELS CAN DRIVE POWER CONTROL RACK FOR ON/OFF CONTROL OF POWER DEVICES.
TRIGGER FUNCTION CHANNELS	1, DIFFERENTIAL INPUT
TRIGGER SOURCE	EXTERNAL INPUT, ANY INPUT CHANNEL, OR SOFTWARE STORBE.
RANGES	0 TO -10V, 0 TO -1V, 0 TO 10V 0 TO -10 V
RESOLUTION	8 BIT
INPUT COUPLING	AC OR DC

III. DATA REDUCTION AND ANALYSIS

A. Preliminary Determination of Hydrogen Gas Concentration and Pressure in the Gas Region of the Upper Chamber

In order to provide estimates of gas pressures and concentration of hydrogen gas in the gas region, a preliminary analysis was made to obtain the range of hydrogen gas concentration and partial pressures that may be encountered in the course of the experiment.

The analysis was based on the following:

1. The mass of liquid metal initially in reaction vessel is known.
2. The percent of metal reacted was varied from 1% to 20% (a typical range for such non-mixing reactions)
3. The upper chamber gas region volume was varied by varying the water level in the upper chamber (of diameter 5 cm) to produce gas volume heights of from 1 cm to 20 cm
4. Saturated liquid is assumed to be in the upper chamber, and the liquid temperature was varied from 60 to 100°C.

The above information are used in conjunction with the chemical reaction equation for lithium-lead ($\text{Li}_{17}\text{Pb}_{83}$)/water reaction to determine the partial pressure and mole fraction of hydrogen generated during the reaction. Tables 2 and 3 give sample calculation results for ($\text{Li}_{17}\text{Pb}_{83}$)/water reaction. In the tables, the first column gives the height of the gas accumulation section of the upper chamber, the second column gives the partial pressure of hydrogen in the gas column and the last column gives the mole fraction of hydrogen gas in the gas column. The percentage reaction assumed and the initial saturated liquid

temperature are also indicated on the Table. Similar tables have been developed for other ranges of initial water temperatures and percent reaction. From the table, it is evident that in addition to the original purpose of the water in serving as a reactant and condensing medium for any water vapor generated as a result of the reaction, the variation of its column height will directly change the gas volume above it and hence can be used as a means of controlling the total pressure generated by hydrogen production and accumulation in the gas region. In doing so, we can also have control over the partial pressure of the hydrogen and therefore its concentration.

Table 6 Pressure and Mole Fractions of Hydrogen Generated for $\text{Li}_{17}\text{Pb}_{83}$ /Water Reaction, $T_w = 80^\circ\text{C}$, 5% Reaction

Gas accumulation height (cm)	H2 Partial Pressure (MPa)	H2 Mole Fraction
2	0.079	0.049
3	0.053	0.048
4	0.040	0.047
5	0.032	0.047
6	0.026	0.046
7	0.023	0.045
8	0.019	0.045
9	0.018	0.044
10	0.016	0.044
11	0.015	0.043
12	0.013	0.042
13	0.012	0.042
14	0.012	0.041
15	0.011	0.041
16	0.010	0.040
17	0.010	0.040
18	0.009	0.040
19	0.009	0.039
20	0.008	0.039

$\text{Li}_{17}\text{Pb}_{83}/\text{H}_2\text{O}$ reaction

Water temperature = 80°C

Mass of $\text{Li}_{17}\text{Pb}_{83}$ = 43 g

% Metal Reacted = 5

Initial System Pressure = P_{sat} at 80°C

Table 7 Pressures and Mole Fractions of Hydrogen Generated for $\text{Li}_{17}\text{Pb}_{83}$ /Water Reaction, $T_w = 100^\circ\text{C}$, 10% Reaction

Gas accumulation height (cm)	H2 Partial pressure (MPa)	H2 mole fraction
2	0.166	0.094
3	0.111	0.092
4	0.083	0.089
5	0.066	0.087
6	0.055	0.085
7	0.047	0.083
8	0.041	0.080
9	0.037	0.079
10	0.033	0.077
11	0.030	0.075
12	0.028	0.074
13	0.024	0.071
14	0.022	0.071
15	0.022	0.069
16	0.021	0.068
17	0.019	0.066
18	0.018	0.064
19	0.017	0.063
20	0.017	0.063

$\text{Li}_{17}\text{Pb}_{83}/\text{H}_2\text{O}$ reaction

Water temperature = 100°C

Mass of $\text{Li}_{17}\text{Pb}_{83}$ = 43 g

% Metal Reacted = 10

Initial System Pressure = P_{sat} at 100°C

B. Determination of Mass of Hydrogen Generated

The data collected from the experiment, the physical inside dimensions of system, the leakage characteristics of the system and information on the solubility of Argon and hydrogen in water are used to determine the amount of hydrogen generated during the reaction. This is done by accounting for all calculable components of pressure in the system.

(i) Mass of Argon and Hydrogen

The mass of argon in the system just before the reaction can be calculated from the equation

$$N_{Ar} = \frac{(P_{sys} - P_{H_2O})}{R T_{gas}} V_{ugc} + \frac{P_{Lc} V_{Lc}}{R T_{Lc}} + N_{Ar_{sol}} (T_w, P) \quad (1)$$

where

P_{sys}	=	Total system pressure in the upper gas region
P_{H_2O}	=	Vapor pressure of water at upper gas temp, T_{gas}
R	=	Universal gas constant
P_{LC}	=	Argon pressure in the lower chamber just before the reaction
T_{LC}	=	Temperature of argon in the lower chamber just before the reaction
V_{LC}	=	Volume of argon in the lower chamber (equals free volume in lower chamber)
V_{ugc}	=	Volume of the upper gas chamber
$N_{Ar_{sol}} (T_w, P_{sys})$	=	Amount of argon in the solution in the upper chamber at the given system pressure and upper water temperature

The amount of Argon in solution is calculated using information on the solubility of argon in water at 25°C and 1 atm, and the fact that the solubility reduces to zero at $T_{sat} = 100^\circ\text{C}$ and 1 atm. Thus by interpolation, the solubility of argon, X_{Ar} , is given by

$$X_{Ar} (T_w, P_{sys}) = X_{Ar} (25^\circ\text{C}, 1 \text{ atm}) \frac{(T_{sat} - T_w)}{T_{sat} - 25} \frac{P_{sys}}{1 \text{ atm}}$$

with T_w being the water temperature

The amount of argon in solution is then calculated using

$$N_{Ar\text{sol}} = X_{Ar} (T, P_{sys}) N_{H2O} \quad (2)$$

where N_{H2O} is the amount of water in the upper chamber

From the above information, the partial pressure of hydrogen is given by

$$P_{H2} = P_{sys} - P_{vap} - P_{Ar} - N_{H2\text{sol}} R T_{gas} / V_{gas} \quad (3)$$

Where $N_{H2\text{sol}}$ is the amount of hydrogen generated that goes into Solution and is determined in a similar manner as the determination of amount of Argon in Solution.

$$N_{H2\text{sol}} = X_{H2} (T_w, P_{sys}) N_{H2O} \quad (4)$$

where

$$X_{H_2} (T, P_{sys}) = X_{H_2} (25^\circ C, 1 \text{ atm}) \frac{(T_{sat} - T)}{T_{sat} - 25} \frac{P_{sys}}{1 \text{ atm}} \quad (5)$$

(ii) Gas Leakage Corrections

It may be necessary to correct the amounts of hydrogen accounted for in the upper chamber and in solution for leakage in order to accurately ascertain the amount of hydrogen produced from the reaction depending on leakage test results of the system. The total amount of hydrogen leakage from $t = 0$ to time t is given by

$$N_{H_2 \text{ leak}} (t) = N_{H_2} (t - \Delta t) - \frac{\frac{dp}{dt} \Delta t V_{gas}}{R T_{gas}} \frac{P_{H_2}}{P_{Ar} + P_{H_2} + P_{vap}} \quad (6)$$

Thus the amount of hydrogen generated by the reaction up to time t is given by

$$N_{H_2} (t) = \frac{P_{H_2} (t) V_{gas}}{R T_{gas}} + N_{H_2 \text{ sol}} (t) + N_{H_2 \text{ leak}} (t) \quad (7)$$

Similarly, the amount of Argon in the upper gas chamber at time t is given by

$$N_{Ar} (t) = N_{Ar} (t - \Delta t) - \frac{\frac{dp}{dt} \Delta t V_{gas}}{R T_{gas}} * \frac{P_{Ar}}{P_{Ar} + P_{H_2} + P_{vap}} \quad (8)$$

A leakage test on the system will be used to determine $P_{yy}(t)$ from which dP/dt can be evaluated.

IV. MASS TRANSFER MODEL FOR LITHIUM-LEAD/WATER REACTION

A liquid metal transport reaction model developed by Herzog [2] is being improved and will be used to estimate the empirical chemical reaction rate and diffusion parameters for the lithium-lead/water chemical reaction. This model is based on the premise that the rate of reaction during lithium-lead/water interactions is primarily controlled by the rate of diffusion of lithium atoms to and products away from the liquid metal surface right from the beginning of the reaction. One of the most difficult aspects of using the model is the requirement of determining the initial hydrogen generation rate. The experimental data during the first few seconds obtained by both Herzog and Lomperski were not reliable enough to enable accurate prediction of the initial hydrogen generation rate, even though the integrated hydrogen generated could be reliably determined from the experimental results. Data from the present research will provide reliable data for determining the initial hydrogen generation rate for use in the liquid metal transport model. This model proposed by Herzog [2], is discussed in detail by Herzog and Biney et al [3].

A. Basic Assumptions

The liquid metal transport reaction model is based on the following assumptions: (1) the reaction occurs only at the surface, (2) the system is assumed to be one dimensional since the driving force of diffusion will result in an axial variation of molar concentration of reactants and products, (3) the concentration of lead is assumed to be approximately constant throughout the interaction since there

are about 5 atoms of lead to 1 atom of lithium in the alloy and lead is chemically inert during the interaction, (4) the liquid metal is incompressible, (5) the gases produced during the reaction are ideal, (6) there is no convective motion in either the gas or liquid metal pool and (7) there is no bulk mixing within the liquid metal pool. Since in the tests, the diameter of the liquid metal surface was stable relative to a Taylor unstable wavelength and thus the reaction surface area remains approximately constant. Figure 9 shows the reference coordinate system used for the model. In the figure, the interaction surface is shown located a distances from the bottom of the liquid metal pool. Hypothetical concentrations of the products and reactants are also indicated on the figure. A vapor film of thickness δ is shown above the interaction surface and a pool of subcooled water above the vapor film.

B. Model Equations

The basic equations are reviewed here. A complete description can be found in References 2 and 3. For this multi-component system the continuity equation is given by:

$$\partial C_i / \partial t = - \partial / \partial z (C_i V + J_i) \quad (1)$$

which when applied to the reactant and product results in the following two equations:

$$\partial C_{Li} / \partial t = D_{lm} \partial^2 C_{Li} / \partial z^2 - C_{Li} \partial V / \partial z - V \partial C_{Li} / \partial z \quad (2)$$

Figure 9 Mass Transfer Coordinate System

$$\partial C_{pd}/\partial t = D_{lm} (\partial^2 C_{pd}/\partial z^2) - C_{pd} (\partial V/\partial z) - V (\partial C_{pd}/\partial z) \quad (3)$$

The boundary conditions for the continuity equations are: At $z = 0$, $\partial C_{Li}/\partial z = 0$; at $z = s$, $C_{Li} = 0$; and the initial condition is $C_{Li}(z, 0) = C_{Li, max}$.

Under assumptions 3 and 4, the equation of energy for the liquid metal pool is given

$$\rho (DH/Dt) = - \partial/\partial z (K_{lm} \partial T/\partial z + M_i H_i J_i) - DP/Dt \quad (4)$$

Substituting the relation $H = U + PV$ and simplifying we obtain the equation:

$$\begin{aligned} \rho C_p (\partial T/\partial t + V \partial T/\partial z) = & k_{lm} \partial^2 T/\partial z^2 - (J_{Li} M_{Li} C_{pLi} + J_{pd} M_{pd} C_{ppd}) \partial T/\partial z \\ & + M_{Li} H_{Li} \partial J_{Li}/\partial z + M_{pd} H_{pd} \partial J_{pd}/\partial z \end{aligned} \quad (5)$$

Where $J_i = -D_{lm} \partial C_i/\partial z$ and the condensed phase liquid metal diffusivity D_{lm} is assumed to be of the Arrhenius form:

$$D_{lm} = D_0 \exp [-\Delta E_d/(RT)] \quad (6)$$

The boundary conditions for the energy equation are: $T(0, t) = T_c(t)$, a known temperature at the base of the metal pool; at $z = s$, $q_{cond} + q_{gen} = q_{conv}$, where q_{cond} is the heat transfer by conduction from the base to the surface, q_{gen} is the heat generated at the surface as a result of the exothermic chemical reaction and q_{conv} is the heat transfer by convection from the reaction surface to the vapor film given by lamnar film boiling. Each flux is given by

$$q_{\text{cond}} = - k_{\text{km}} \partial T / \partial z \quad (7)$$

$$q_{\text{gen}} = R_{\text{Li}} (n_{\text{pd}} h_{\text{pd}} - n_{\text{react}} h_{\text{react}}) \quad (8)$$

$$q_{\text{conv}} = h_{\text{fb}} (T(s, t) - T_{\text{sat}}) \quad (9)$$

The stable film boiling heat transfer coefficient h_{fb} is obtained from the laminar film boiling model on a flat horizontal surface [4]. The two continuity equations and the one energy equation constitute three equations with five unknowns:

$T(z, t), C_{\text{Li}}(z, t), C_{\text{pd}}(z, t), D_0$ and ΔE_d . Assumptions 2 and 3 imply that the molar flow rates of lithium and product (LiOH) are equal but opposite in direction. Thus the sum of the molar concentrations will be a constant equal to the initial lithium concentration in the alloy $C_{\text{Li max}}$. Thus equation 3 can be replaced with

$$C_{\text{pd}}(z, t) + C_{\text{Li}}(z, t) = C_{\text{Li max}} \quad (10)$$

The initial rate of hydrogen generation S , is calculated using experimental data

$$dN_{\text{Ar}}/dt = S \quad (11)$$

Finally the model is made to match the experimental results; i.e., the final amount of hydrogen generated 200 s into the reaction. These last two conditions bring the set of equations to five with five unknowns.

The experimental results will be used to determine the moles of hydrogen produced at the end of 200 s. The initial rate of

hydrogen generation will be determined from the experimental data. These two pieces of experimentally derived information will be supplied to the liquid metal transport reaction model and the reaction rate constants B and E in the parabolic rate equation

$$\partial/\partial t [m/A]^2 = B_1 \exp [- \Delta E/(RT)] \quad (12)$$

as well as the constants in the Arrhenius equation D_0 and ΔE_d determined. One should note that mechanistically these constants B and ΔE are directly related to D_0 and ΔE_d in the liquid metal diffusivity, Equation (6).

V. PROBLEMS ENCOUNTERED AND FUTURE DIRECTIONS OF RESEARCH

A. Problems Encountered In the first Year

Two major problems were encountered during the first six months of the project, all being the result of the project contract date occurring almost a month after beginning of the semester. The principal investigator was unable to obtain release time to actively work on the project in the Fall Semester of 1990 (August 28 - December 31, 1990) because of the late contract date. A college technician could not be assigned to work on the project in the Fall Semester of 1990 as a result of the late contract date. We could also not get the college technician to work on the project in the Spring Semester of 1991 (January - May 1991) due to heavy work load already being assigned by the college.

B. Future Direction of Research

Figure 10 shows the original first year schedule proposed at the beginning of the research. Figure 1 gives the true reflection of activities that occurred in the first year of the project. The major reasons for falling behind schedule as evidenced by the two figures are those discussed above. In addition, considerable time was spent in addressing the problem of designing a system with the least leakage possibilities. Several conceptual designs were made before arriving at the current optimum condition. Figure 11 shows the project schedule for the second year that reflects the current stage of the project.

We anticipate completing the second year project schedule on time. The overall project objectives have not changed. After the

construction and testing phases in the first quarter of the second year, the rest of the period will be mainly devoted to data collection, analyses of experimental data and determination of chemical reaction rate constants for the lithium-lead/water reaction. The final project report will also be prepared at this time and the graduate student will complete his MS Thesis.

Figure 10 Original First Year Project Schedule

Figure 11 Revised Second Year Project Schedule

VI. CONCLUSIONS

The first one year of the research has been very productive.

One graduate and one undergraduate research assistants have been working on the research. The students have been brought up to date on the theoretical and design aspects of the research. Regular brainstorming sessions, organized by the research team, have lead to several improvements in the original design, the major of which is the decision to let measuring devices penetrate the test section below the water-level and to eliminate any screw or flanged joint in the upper portion above the water level to minimize leakage of hydrogen from the apparatus.

All major equipment have been ordered and majority received. A finite element model of the lower section was developed and used in analyzing the heating stage, enabling us to select furnace components and modify design to protect the pneumatic controlled butterfly valve by the use of internal cooling. An experimental test matrix has been developed . A detailed Project Schedule has been developed to reflect the stage at this time. The second year schedule is being followed. Funding the second year has been received and this will facilitate successful completion of the project objectives.

REFERENCES

- [1] Chen, Jiming; Qian, Jiapu; "The Corrosion Behavior of Fe-Ni - Cr Alloys in Liquid Lithium", Proceedings of 9th Topical Meeting on the Technology of Fusion Energy, 1990.
- [2] Herzog, J.P., "Lithium-Lead/Water Interactions: Experiments and Analysis", Ph.D. Dissertation, Fusion Technology Institute, Nuclear Engineering and Engineering Physics Department, University of Wisconsin - Madison.
- [3] Biney , P.O., Corradini, M.L. Lomperski, S. and Krueger, J., "A Mass Transport Model for Hydrogen Generation During Lithium-Lead/Water Interactions". Presented at the 13th Symposium of Fusion Energy, Knoxville, TN October 1989.
- [4] Collier, J., Convective Boiling and Condensation, McGraw-Hill 1972 pp 124-133.

NOMENCLATURE

A	Surface area
B_1	Arrhenius rate constant
C	Molar Concentration
D_0	Diffusion Coefficient proportionality constant
D_{lm}	Diffusion Coefficient of liquid metal
E	Activation energy
H	Enthalpy
h	Molar enthalpy also as heat transfer coefficient
J	Molar flux
k	Thermal conductivity
M	Molecular weight
P	Pressure
g	Heat flux
R	Universal gas constant
S	Experimentally determined initial reaction rate
T	Absolute temperature
t	time
V	Velocity
Z	Principal coordinate direction
ρ	density

Subscript

pd	products
lm	liquid metal
cond	conduction
gen	generated
conv	convective
sat	saturated
Ar	Argon
fb	film boiling

END

DATE
FILMED
2/20/92

I