TECHNICAL REPORT

DE92 007889

September 1, 1991 through November 30, 1991

Project Title: Evaluation and Utilization of Illinois FBC
Residues for Construction Materials
DE-FG22-91PC91334

Principal Investigator: Nader Ghafoori
Department of Civil Engineering & Mechanics
Southern Illinois University-Carbondale

Other Investigator: Sedat Sami
Department of Civil Engineering & Mechanics
Southern Illinois University-Carbondale

Project Monitor: Dr. Dan Banerjee, CRSC

ABSTRACT

The overall objective of this program is to investigate the extent to which fluidized bed combustion (FBC) by-products can be properly utilized as the viable construction materials. This investigation focuses primarily on the properties of residues derived from fluidized combustion burning of Illinois high-sulfur coal. The research plan calls for evaluation of physico-chemical and engineering characteristics of the FBC-based cement and non-cement mixes. The results of this study will be used to compare the physical and mechanical properties of the FBC-based mixtures with those of conventional mixes. The suitability of using FBC residues as a filler or binder aggregate for construction applications such as structural concrete members, precast building products, and as base or surface course for gravity dams and pavements in the form of conventional and roller compacted materials will then be evaluated.

During this reporting period, the literature survey, preparation of raw materials, and chemical analyses were completed. Some of the physical properties and preconditioning studies were determined and efforts are in progress to complete these tasks.

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

MASTER

This project is funded by the U. S. Department of Energy (METC) and by the Illinois Department of Energy and Natural Resources as part of their cost-shared program.

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

EXECUTIVE SUMMARY

By-product residues of six FBC-based co-generation plants, operating in State of Illinois, were considered. Based on uniformity in operating parameters of plant and homogeneity of the resultant by-products, Archer Daniel Midland Corp. (ADM) in Decatur was selected for this project. Type "F" fly ash, for production of non-cement roller compacted FBC mixes, is supplied by Tennessee Valley Authority (TVA). Portland cement, five different types, is supplied by Holnam Inc., Dundee, Michigan. Natural Aggregates, for production of control samples, are obtained from southern Illinois quarries.

Chemical analyses of "ADM" fly ash and spent bed, and "TVA" fly ash are reported in Table 1. As expected, large amount of unhydrated calcium oxide and sulfur trioxide are found in "ADM" by-product residues. Both of these compounds are responsible for high heat of hydration and its subsequent molar volume expansion. Preconditioning studies in reducing the heat incursions and thermal cracking are on-going. Size distribution and physical properties of "ADM" spent bed are reported in Figure 1 and Table 3, respectively.

Table 2 presents chemical and physical data for five different types of Portland cement having "C3A" of 3, 5, 7, 9.9, and 13 percent. Physical properties of natural fine and coarse aggregates are reported in Tables 4 and 5, respectively.

During the next reporting period work on all tasks will be initiated and/or continued.

Table 1: Chemical Test Data of By-Product Residues

Chemical Composition	"ADM" Fly Ash	"ADM" Spent Bed	"TVA" Fly Ash	Fly Ash Specifications (ASTM C618)
Silicon Oxide (SiO_2)	22.1	9.70	49.90	-----
Aluminum Oxide (Al_2O_3)	6.80	3.69	21.50	-----
Iron Oxide (Fe_2O_3)	6.67	2.16	16.60	-----
Total ($\text{SiO}_2 + \text{Al}_2\text{O}_3 + \text{Fe}_2\text{O}_3$)	35.57	15.55	88.00	50.0 Minimum, ----> Class C 70.0 Minimum, ----> Class F
Sulfur Trioxide (SO_3)	15.67	24.42	1.56	5.0 Maximum
Calcium Oxide (CaO)	38.7*	53.10*	3.34	Less than 10%, ----> Class F More than 10%, ----> Class C
Magnesium Oxide (MgO)	1.29	0.88	0.99	-----
Loss of Ignition	5.46	0.80	2.46	6.0 Maximum
Free Moisture	0.11	0.0	0.30	3.0 Maximum
Water of Hydration	0.71	2.65	0.0	-----
Na_2O	0.50	0.16	.60	-----
Available Alkalies as Na_2O	N/A	N/A	0.18	1.5 Maximum
K_2O	1.12	.39	2.62	-----
Others ($\text{TiD}_2 + \text{P}_2\text{O}_5 + \text{SrO} + \text{BaO}$)	0.83	2.04	0.0	-----
PH	12.2	12.0	N/A	-----

*Mostly unhydrated lime

Table 2: Chemical and Physical Test Data of Portland Cement

Chemical Composition	#1	#2	#3	#4	#5
Silicon Dioxide (SiO_2)	22.5	21.4	21.3	20.86	20.9
Aluminum Oxide (Al_2O_3)	3.9	4.7	5.0	5.54	6.1
Ferric Oxide (Fe_2O_3)	4.3	4.4	3.6	2.84	2.0
Calcium Oxide (CaO)	64.4	63.3	65.2	61.74	64.9
Magnesium Oxide (MgO)	2.0	1.2	1.2	3.79	1.2
Sulfur Trioxide (SO_3)	2.0	2.6	2.4	3.07	2.7
Loss of Ignition	1.0	1.3	1.4	1.52	1.5
Insoluble Residues	0.15	0.1	0.20	0.11	0.4
Tricalcium Silicate (C_3S)	53	50	58	42.7	54
Dicalcium Silicate (C_2S)	24	24	17	27.6	19
Tricalcium Aluminate (C_3A)	3	5.0	7	9.9	13
Tetracalcium Alumino-ferrite (C_4AF)	13	13	11	8.7	6
Na_2O Equivalent	0.43	0.44	0.11	0.87	N/A
Physical Tests					
Soundness	-0.03	-0.01	-0.002	0.34	0.19
Specific Surface Blain (M^2/Kg) Wagner (M^2/Kg)	341.9 215.2	400.00 N/A	384.5 N/A	375 N/A	369.1 167.6
Time of Setting Vicat, initial Vicat, final	N/A N/A	1 hr. 40 mins. 3 hrs. 30 mins.	N/A N/A	1 hr. 55 mins. 3 hrs. 50 mins.	2 hrs. 0.0 mins. 4 hrs. 10.0 mins.
Comp. Strength 3-day (Pai) 7-day (Pai)	3330 4090	3070 4170	3200 4150	3030 4105	3350 4850

Table 3: Physical Properties of FBC Spent Bed

Fineness Modulus	Specific Gravity - OD	Specific Gravity- SSD	Absorption (%)
2.80	2.15	2.36	9.65

Table 4: Physical Properties of Natural Fine Aggregate (River Sand)

Fineness Modulus	Specific Gravity - OD	Specific Gravity - SSD	Absorption (%)	Organic Impurities	Clay Lump & Friable Particles (%)
2.80	2.65	2.66	0.5	None	1.75

Table 5: Physical Properties of Natural Coarse Aggregate (Limestone)

Max. Size (Max. Nominal Size)	Specific Gravity - OD	Specific Gravity - SSD	Absorption (%)	Rodded Unit Weight - OD (lb/ft ³)	Rodded Unit Weight - SSD (lb/ft. ³)	Void Ratio
1 (3/4)	2.64	2.67	0.75	93.5	94.2	43.75

Figure 1: Sieve Analysis of Spent Bed and Natural Sand

▲ RIVER SAND ✕ ADM BOTTOM ASH * ASTM UPPER BOUND ✕ ASTM LOWER BOUND

END

DATE
FILMED

4 / 01 / 92

I