DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

The Role of Grain Boundaries on the Strength, Ductility and Toughness of $L1_2$ Intermetallic Compounds

DOE/ER/45260--T1

DE92 007464

*A progress report on year - 2
prepared for*

U.S. Department of Energy
Office of Basic Energy Sciences
Grant no. DE-FG02-86ER45260

by the
Thayer School of Engineering
Dartmouth College
Hanover, New Hampshire 03755

March 11, 1988

Erland M. Schulson
Principal Investigator and
Professor of Engineering

MASTER

Further to progress report no. 1, dated March 16, 1987, this report summarizes progress during year 2 (March 17, 1987 - March 11, 1988) on the effects of grain size on the structure and mechanical properties of Ni_3Al and Ni_3Si .

1. Grain Boundary Disorder and the Ductility of Ni_3Al

From previous work it was established that the addition of boron to stoichiometric Ni_3Al not only increases ductility, but also reduces the impediment imposed by grain boundaries to dislocation slip. The former effect is well known. The latter was deduced from the observation that the addition of boron reduces the contribution of grain boundaries to both strength (Schulson et al. 1985, 1986) and hardness (Weihs et al. 1987).

The two effects appear to be very closely coupled. If, in segregating to grain boundaries as it does (Liu et al. 1985), boron lessens the tendency for dislocations to pile up and thereby concentrate stress, then it should also lessen the tendency for crack nucleation. In other words, boron in some way appears to ease the accommodation of slip at grain boundaries. As a result, slip can be more easily transmitted from grain to grain, and so polycrystals can more easily exhibit extensive plasticity before fracturing.

The question, then, is the mechanism of accommodation. One possibility is that grain boundary dislocations become more mobile. Another is that dislocation sources within the boundary or its vicinity become more easily activated. Both mechanisms can dissipate strain at the head of a pile-up. But how does boron ease their operation? Maybe it doesn't. Maybe it's not boron per se that's important here, but a structural change brought about through the presence of boron. Given that boron forms nickel-rich borides, then perhaps in segregating to grain boundaries boron attracts excess nickel, thereby lowering the aluminum concentration and, more importantly, lowering the degree of long range atomic order within the boundary and its vicinity. Such a change would ease the motion of boundary dislocations by reducing the order barrier to motion, and it would ease the generation of dislocations by lessening the anti-phase boundary barrier to generation.

To test this hypothesis, the Ni:Al ratio was measured on grain boundaries of stoichiometric Ni_3Al with and without boron (0.35 at. %) using a high-brightness STEM (in collaboration with J.R. Michael at Bethlehem Steel Labs). Tables 1 and 2 show the results. In the presence of boron, the Ni:Al ratio is greater than 3:1. Given that the electron beam has width (about 1 nm as it enters the foil), then the actual ratio at the grain boundary is probably even greater than indicated from these results. The data imply, therefore, that in the presence of boron the boundaries are either partially or completely disordered.

NUMBER OF COUNTS

Grain Boundary Number	Matrix #1				Matrix #2		Grain Boundary		Calculated at. % at grain boundary	
	Ni	Al	Ni	Al	Ni	Al	Ni	Al	Ni	Al
1	44,767	5,528			45,604	4,547	78.7	21.3		
	34,321	4,326			35,444	3,348	79.8	20.2		
2	16,188	1,321			15,988	692	84.5	15.5		
	17,436	1,335			17,483	539	87.4	12.6		
3	31,769	4,055	35,887	3,986	34,721	3,179	79.0	21.0		
					40,101	3,892	78.0	22.0		

Table 1

Ni K_α and Al K_α x-ray counts from three grain boundaries and the adjacent matrix in stoichiometric Ni₃Al containing 0.35 at.% boron.

The calculated 'composition' of the grain boundary is also shown (see text for details).

NUMBER OF COUNTS

Grain Boundary Number	Matrix #1		Matrix #2		Grain Boundary		Calculated at. % at grain boundary	
	Ni	Al	Ni	Al	Ni	Al	Ni	Al
1	75,348	11,311	81,721	12,200	72,801	10,510	75.7	24.3
	124,565	17,375	135,999	18,959	99,275	13,365	75.7	24.3
2	174,419	19,646	184,641	20,068	176,127	19,428	75.0	25.0
	64,584	8,418	102,972	13,010	91,033	11,734	75.2	24.8
3	49,333	6,953	56,672	7,846	63,792	8,494	75.9	24.1

Table 2

Ni K α and Al K α x-ray counts from three grain boundaries and the adjacent matrix in stoichiometric Ni₃Al annealed for one hour at 1273K.

The calculated grain boundary 'compositions' are shown (see text for details).

A broader question thus arises. Could it be, as wondered by Baker and Schulson, that there are two requirements for extensive ductility of polycrystalline intermetallic compounds and ordered alloys: four or five independent slip systems, and at least some degree of disorder at the grain boundaries?

2. The Ductility of Quenched $\text{Ni}_3\text{Al} + \text{B}$

Further to the result reported in progress report no.1, another polycrystalline specimen of stoichiometric Ni_3Al containing 0.35 at. % boron was annealed in flowing argon at 1200°C and then quenched in water. This time, the specimen was sealed within an evacuated vycor capsule to avoid oxidation. Upon smashing the capsule the specimen broke. This result suggests that the heat treatment embrittled an otherwise somewhat ductile alloy ($> 10\%$ elongation expected at room temperature). Whether the effect reflects an annealing-induced desegregation followed by a quench-suppression of nickel enrichment, in line with current thinking about the ductility of $\text{Ni}_3\text{Al} + \text{B}$ (noted above), remains to be established.

3. The Strength of Ni_3Al Containing Titanium and Boron

In the light of current knowledge of boron strengthening of Ni_3Al (Baker et al. 1988) the results were analyzed of earlier measurements of the room-temperature tensile and compressive yield strength of the "glass brittle" alloy 24.7 at.% Al, 1.5 at.% Ti, 2.8at.% B, bal. Ni, which had been prepared by consolidating rapidly solidified powder.

When plotted in terms of $(\text{grain size})^{-1/2}$ both the tensile and the compressive strengths were found to be in rough accord with a Hall-Petch relationship, Figure 1. (This is not to mean that other functionalities are not appropriate, for they are, but only that the rather scattered data can be roughly described by the H.-P. equation.)

The tensile strength may be explained in terms of the propagation under load of pre-existing flaws, for the aggregates did contain grain boundary pores. If so, then the slope of Fig.1 (tensile) implies a fracture toughness of about $3.8 \text{ MPa}\cdot\text{m}^{1/2}$. A value this low is typical of ceramics and is in keeping with the extreme fragility of the alloy.

The H.-P. intercept (i.e., the lattice resistance) for the compressive strength, 1430 MPa, can be explained solely in terms of a linear combination of solid solution strengthening mechanisms. Given boron strengthening of 387 MPa/at.% (Baker et al. 1988), this component contributes 1084 MPa to the lattice resistance. Strengthening derived from Ti at 20 MPa/at.% contributes 30 MPa. And strengthening through the nonstoichiometric Ni:Al ratio of 2.87:1, based upon 100 MPa/at.%

Fig. 1: The tensile strength (●) and the compressive yield strength at 0.2% offset (○) of Ni₃Al + Ti + B at room temperature versus (grain size)^{-1/2}.

Al in excess of stoichiometry, is about 100 MPa. Thus, when added to the intrinsic lattice resistance of about 92 MPa for stoichiometric, unalloyed Ni_3Al , the result is $1084 + 30 + 100 + 92 = 1306$ MPa, vs. 1430 MPa.

4. The Lattice Strengthening of Ni_3Al with Boron Vs. Deviation from Stoichiometry

From the foregoing report, it can be seen that boron is an extraordinarily potent strengthener of Ni_3Al . The effect is not caused by a second phase. Rather, it is a solid solution effect and, as noted elsewhere (Baker et al. 1988), may reflect a slight tetragonality to the unit cell owing to the possible interstitial siting of boron in the octahedral sites at the mid-points of the edge of the unit cell. These sites are smaller than the body-centered octahedral site.

This explanation implies that if the difference in size between the two octahedral sites were reduced, then the tetragonality would be reduced and the degree to which boron raises the lattice resistance to slip would be reduced. One way to reduce the difference is to deviate from stoichiometry.

To test this hypothesis, the compressive yield strengths of alloys on either side of stoichiometry, with and without boron, were measured. The specific compositions were Ni 24 at. % Al and Ni 26 at. % Al with and without 0.35 at. % boron. To avoid the influence of significant grain boundary contributions to the strength, only coarsely grained ($d \gtrsim 100$ microns) aggregates were tested. The material was obtained from a commercial source (Homogeneous Metals) as powders, and then consolidated by canning in stainless steel jackets and extruding (area reduction ratio of 6:1) at 1100°C using the press at ORNL. Subsequently, cylindrical specimens were annealed at 1200°C to promote grain growth.

The results showed that boron is less effective in strengthening the off-stoichiometric alloys. The Ni-rich alloy is strengthened by about 140 MPa/at. % boron and the Al-rich alloy, by about 243 MPa/at. % boron. These results compare with 387 MPa/at. % for the stoichiometric alloy. Corresponding to the reduction is the absence of apparent broadening of high index lines on Debye-Scherrer X-ray patterns from the boron-containing alloys, suggesting reduced tetragonality. Such broadening is apparent on patterns from stoichiometric material with boron.

5. Microstructure of Extruded Ingots of Ni_3Al Containing Boron

In all previous work at Dartmouth, test material was prepared by extruding powder which had been produced from ingots. To explore an alternate and potentially simpler route, attempts were made to produce sound material by extruding the ingots directly. All failed.

Ingots of stoichiometric composition and containing 0.05, 0.09, 0.19, 0.37, 0.75 and 1.12 at.% boron were homogenized in air at 1200°C for 24 hours, canned in stainless steel, and then extruded at 1250°C. Segments of the first extrusion were re-extruded at 1093°C. (Extrusions were performed at NASA-Lewis).

The extruded product contained pores, some rather angular. Examination revealed that these defects were probably molten spots at the extrusion temperature owing to localized enrichment of boron and attendant reduction of the solidus temperature. During extrusion, the liquid changed shape and during subsequent cooling, solidified, leaving shrinkage cavities.

It is concluded, therefore, that owing to heterogeneous boron concentrations, even after "homogenizing", the direct extrusion of boron-containing ingots of Ni_3Al does not produce a sound product.

6. The Structure and Mechanical Properties of Ni_3Si With and Without Boron

Solidified and consolidated (extruded) powders of Ni_3Si (23.0 at.% Si) with and without boron (0.19 at.% B) are being investigated.

Light microscopy of the powders (in their as received state) revealed a segregated, dendritic structure whose scale is of the order of one micron. X-ray diffraction of the powders indicated tentatively that the predominant phase is Ni supersaturated with Si. Evidence of other phases such as β_2 and β_3 (monoclinic, distorted L1_2) and γ ($\text{Ni}_{31}\text{Si}_{12}$, complex hexagonal) was also observed, but the L1_2 - ordered Ni_3Si (β_1) appeared not to be present, indicating that the powders were in a highly non-equilibrium state.

Subsequent annealing of the powders resulted in the rapid formation of the β_1 phase by two possible mechanisms. One is by a peritectoid transformation ($\alpha + \gamma \rightarrow \beta_1$), at temperatures below $\approx 927^\circ\text{C}$, where α represents the Ni-Si solid solution; the other is by a eutectoid transformation ($\beta_2 \rightarrow \beta_1 + \gamma$).

Powders were consolidated by extrusion in stainless steel jackets at 1100°C, through a 6:1 reduction in area. X-ray analysis of the extruded material revealed some minor flaws along the spine of the rods. Longitudinal and transverse sections of the extruded rods revealed a segregated microstructure of 2-10 μm in size. β_1 is the predominant phase in the extruded rods; α , β_2 and γ are also observed, but in smaller amounts than in the as-received powders.

Subsequent annealing of the extruded rods at 700°C, 800°C and 927°C completed the transformation to a single phase (β_1). 800°C was the most effective temperature for completing

the transformation while retaining the most finely grained microstructure; 927°C is the most effective temperature for grain growth. Boron augments the scale of the microstructure in the extruded rods, yet impedes grain growth of the ordered β_1 phase during annealing.

The hardness of the extruded material at room temperature appears to exhibit Hall-Petch character, Fig. 2:

$$H = H_0 + k_H d^{-0.5}$$

Caution is appropriate, however, before interpreting the slopes of the curves. Few data points are available, and the range in grain size (≈ 15 to $100 \mu\text{m}$) is small. Moreover, the finest grained $\text{Ni}_3\text{Si} + \text{B}$ contained about 30% by volume of hard, remnant parent phases, thereby biasing the hardness to a level higher than it should be.

Tensile specimens have been made and will be tested shortly.

References to the above:

- Baker, I., Huang, B., and Schulson, E.M., 1988, *Acta Met.* (in press)
Liu, C.T., White, C.L., and Horton, J.A., 1985, *Acta Met.* 33, 213
Schulson, E.M., Weihs, T.P., Viens, D.V., and Baker, I., 1985, *Acta Met.* 33, 1587
Schulson, E.M., Weihs, T.P., Baker, I., Frost, H.J. and Horton, J.A., 1986, *Acta Met.* 34, 1395
Weihs, T.P., Zinoviev, V., Viens, D.V. and Schulson, E.M., 1987, *Acta Met.* 35, 1109

7. Papers Published or In Press

- (i) The Strength, Hardness and Ductility of Ni_3Al With and Without Boron
T.P. Weihs, V. Zinoviev, D.V. Viens and E.M. Schulson
Acta Met., 35 (1987) 1109-1118
- (ii) The Strength and Ductility of Intermetallic Compounds: Grain Size Effects
E.M. Schulson, I. Baker and H.J. Frost
Proc. M.R.S. Symp. 81 (1987) 195-205
- (iii) In-Situ Straining of Ni_3Al in a Transmission Electron Microscope
I. Baker, E.M. Schulson and J.A. Horton
Acta Met. 35 (1987) 1533-1541

- (iv) The Structure, Properties and Potential Applications of Intermetallic Compounds Produced from Powders
E.M. Schulson
Inter. J. of Powder Met. 23 (1987) 25-32
- (v) Discussion of "The Role of Boron in Ductilizing Ni₃Al"
E.M. Schulson, I. Baker and H.J. Frost
Met. Trans. A 18A (1987) 1995
- (vi) Effect of Boron on the Composition of Grain Boundaries in Ni₃Al
I. Baker, E.M. Schulson and J.R. Michael
Proc. Analytical El. Microscopy, (Hawaii) 1987, 218-220
- (vii) Strength of Ni₃Al Containing Titanium and Boron
S.R. Spear, G.W. Clothier, E.M. Schulson and I. Baker
Met. Trans. A. (in press)
- (viii) The Effect of Boron on the Chemistry of Grain Boundaries in Stoichiometric Ni₃Al
I. Baker, E.M. Schulson and J.R. Michael
Phil. Mag. (in press)
- (ix) The Microstructure of Ni₃Al Ingots Containing Boron
V. Zinoviev, E.M. Schulson and I. Baker
Metallography (in press)
- (x) The Microstructure of Extruded Ingots of Ni₃Al Containing Boron
V. Zinoviev, E.M. Schulson and I. Baker
Metallography (in press)
- (xi) The Effect of Boron on the Lattice Properties of Ni₃Al
I. Baker, B. Huang and E.M. Schulson
Acta Met. (in press)

MACROHARDNESS (RA)

Fig. 2: Hardness versus (grain size)^{-1/2} for Ni_3Si and $\text{Ni}_3\text{Si} + \text{B}$.

END

**DATE
FILMED**

3 / 10 / 92