2

DOE/1

1 1991

3

DOE/PC/88654--T3

DE92 004870

**COMBUSTION CHARACTERIZATION OF
BENEFICIATED COAL-BASED FUELS**

QUARTERLY REPORT NO. 4 FOR THE PERIOD FEBRUARY TO APRIL 1990

PREPARED BY
COMBUSTION ENGINEERING, INC.
1000 PROSPECT HILL ROAD
WINDSOR, CT 06095

PROJECT MANAGER
MICHAEL J. HARGROVE

PRINCIPAL INVESTIGATORS
O. K. CHOW AND N. Y. NSAKALA

JUNE 1990

PREPARED FOR
US DEPARTMENT OF ENERGY
PITTSBURGH ENERGY TECHNOLOGY CENTER
UNDER CONTRACT NO. DE-AC 22-89 PC 88654

MASTER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

2

DISCLAIMER

This report was prepared as an account of work sponsored by the United States Government. Neither the United States nor the United States Department of Energy, nor Combustion Engineering, Inc., nor any of their employees, subcontractors, suppliers, or vendors makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, mark, manufacturer, or otherwise, does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof.

ACKNOWLEDGEMENTS

The authors gratefully acknowledge the following contributors to this report: B. F. Griffith, K. W. Johnson, M. J. Kozlak, A. A. Levasseur, R. L. Patel, B. C. Teigen, and D. E. Thornock of Combustion Engineering, Inc.; J. M. Beér, A. F. Sarofim, and M. A. Toqan of the Massachusetts Institute of Technology; S. Johnson, J. Moore, and S. Srinivasachar of Physical Sciences, Inc. Technology Company; and D. W. Brekke, S. A. Benson, and J. P. Hurley of the University of North Dakota Energy and Environmental Research Center.

QUARTERLY REPORT

TABLE OF CONTENTS

INTRODUCTION	1
SUMMARY	2
TASK 1 - FUEL PREPARATION	3
TASK 2 - BENCH SCALE TESTS	4
TASK 3 - PILOT-SCALE TESTS	20
TASK 4 - SCALE-UP TESTS	43
TASK 5 - TECHNO-ECONOMIC EVALUATION	43
TASK 6 - TECHNICAL REPORTING	43
WORK PLANNED FOR NEXT QUARTER	44

INTRODUCTION

The Pittsburgh Energy Technology Center of the US Department of Energy has contracted with Combustion Engineering, Inc. (CE) to perform a three-year project on "Combustion Characterization of Beneficiated Coal-Based Fuels." The beneficiated coals are produced by other contractors under the DOE Coal Preparation Program. Several contractor-developed advanced coal cleaning processes are being run at the cleaning facility in Homer City, Pennsylvania, to produce 20-ton batches of fuels for shipment to CE's laboratory in Windsor, Connecticut. CE then processes the products into either a coal-water fuel (CWF) or a dry microfine pulverized coal (DMPC) form for combustion testing.

The objectives of this project include: 1) the development of an engineering data base which will provide detailed information on the properties of BCFs influencing combustion, ash deposition, ash erosion, particulate collection, and emissions; and 2) the application of this technical data base to predict the performance and economic impacts of firing the BCFs in various commercial boiler designs.

The technical approach used to develop the technical data includes: bench-scale fuel property, combustion, and ash deposition tests; pilot-scale combustion and ash effects test; and full-scale combustion tests. Subcontractors to CE to perform parts of the test work are the Massachusetts Institute of Technology (MIT), Physical Science, Inc. Technology Company (PSIT), and the University of North Dakota Energy and Environmental Research Center (UNDEERC).

Twenty fuels will be characterized during the three-year base program: three feed coals, fifteen BCFs, and two conventionally cleaned coals for full-scale tests. Approximately nine BCFs will be in dry microfine coal (DMPC) form, and six BCFs will be in coal-water fuel (CWF) form. Additional BCFs would be characterized during optional project supplements.

SUMMARY

During the first quarter of 1990, the following technical progress was made.

- Evaluated the ignitibility and reactivity characteristics of three microbubble flotation process beneficiated products, one spherical agglomeration product, and three feed coals including flammability indices, TGA, and BET surface areas.
- Completed pilot-scale burner tests firing Upper Freeport microbubble product in CWF form.
- Completed pilot-scale combustion and ash deposition tests of the Upper Freeport and Pittsburgh No. 8 microbubble products, as well as the Upper Freeport spherical agglomeration product.
- Continued analyses of as-fired fuels and resulting ash deposits.

TASK 1 - FUEL PREPARATION

Beneficiated coals (BCs) and feed coals are acquired from other DOE projects and shipped to CE. These fuels are then processed into either a dry, pulverized coal form by CE or a coal-water fuel (CWF) form using OXCE Fuel Company technology. The feed coals are fired as standard grind (70% minus 200 mesh) pulverized coal (PC), while the dry beneficiated fuels are generally dry, microfine pulverized coal (DMPC).

Nine twenty-ton batches of test fuel have been produced under the DOE-PETC Coal Preparation program since 1987. These fuels include:

1. Illinois No. 6 feed coal
2. Pittsburgh No. 8 feed coal
3. Upper Freeport feed coal
4. Illinois No. 6 microbubble flotation product
5. Pittsburgh No. 8 microbubble flotation product
6. Upper Freeport microbubble flotation product
7. Illinois No. 6 spherical agglomeration product
8. Pittsburgh No. 8 spherical agglomeration product
9. Upper Freeport spherical agglomeration product

The first four fuels were tested during the previous two quarters.

The Upper Freeport microbubble product was made into CWF at OXCE's facilities. Forty percent of the CWF was supplied to MIT for their pilot-scale combustion tests. The balance was fired in the CE FPTF in March. The Pittsburgh No. 8 microbubble product was dried and pulverized for firing in the FPTF.

The Illinois No. 6, Upper Freeport, and Pittsburgh No. 8 feed coals were made into beneficiated products using the spherical agglomeration process at the Homer City plant. The products were then shipped to CE for testing. The Upper Freeport spherical agglomerates were fired in the FPTF in April. The Illinois No. 6 and Pittsburgh No. 8 agglomerates are scheduled for firing in May and June, respectively.

TASK 2 - BENCH-SCALE TESTS

All test fuels are fully characterized using various standard and advanced analytical techniques. These tests evaluate the impacts of parent coal properties and beneficiation process on the resulting BCF's qualities.

A few selected fuels are tested in a laminar flow drop tube furnace to determine fly ash particle size and chemical composition. Results include mineral matter measurements and modeling of fly ash history.

A swirl-stabilized, entrained flow reactor is used to characterize the surface compositions and the states of ash particles formed during combustion. Deposition rates on a target are determined, and the size and compositions of the deposits from different fuels are compared.

Standard ASTM Analyses

The ASTM standard tests normally carried out on coals for analytical purposes are being used to characterize the present fuels. These include: proximate, ultimate and screen analyses, higher heating value, ash composition, and ash fusibility temperatures.

Mineralogical Characteristics of Test Fuels

Computer controlled scanning electron microscopy (CCSEM) has been used by a number of investigators to determine the size and composition of mineral grains in coals. The information can be used in a variety of ways to provide insight into the fundamental processes and reactions occurring during preparation and utilization of coal. In the present study, the data is used to determine the effects of cleaning on the size and composition of the mineral matter in the fuels. To determine the effectiveness of the microbubble cleaning process on individual specific gravity fractions, samples of each fuel were fractionated using float-sink techniques. A Certigrav was used to provide four fractions: 1.4 float, 1.4-2.5, 2.5-2.9, and 2.9 sink. The settling rate was enhanced through centrifugation at 3000 RPM. Ash content, composition, and fusion temperatures were determined for each fraction, whose yield was also determined.

Ignitibility Characteristics of Test Fuels

This test entails firing 0.2 gram of sized mesh fuel in an oxygen atmosphere through a preheated furnace. The temperature of the furnace is raised incrementally until a point is reached where the fuel ignites. This temperature, referred to as Flammability Index, compared to those of the fuels in the CE data bank indicates

the ignition temperature/flame turndown on a relative basis. The standard size for pulverized coal is 200x0 mesh. Due to the fact that the microbubble process produces, by design, micro-fine products, it was decided to also include 325x0 mesh fuel samples in this study. Results therefore, can depict the effects of fuel nature, beneficiation process and particle size on ignition characteristics.

Drop Tube Furnace Tests

Work on DTFS-1 combustion testing at CE of coal feed stocks and BCFs prepared therefrom continued during this quarter. The following seven fuels have been tested to varying degrees: (1) the Illinois No. 6 high volatile bituminous (hvCb) coal and two BCFs prepared from it in the microbubble flotation and spherical oil agglomeration processes; (2) the Upper Freeport medium volatile bituminous (mvb) coal and a BCF prepared from it in the microbubble flotation process; and (3) the Pittsburgh No. 8 high volatile A bituminous (hvAb) coal and a BCF prepared from it in the microbubble flotation process. Drop tube furnace tests were also run at PSIT to evaluate ash effects.

CE's two-step standard procedure for evaluating the reactivities of chars is carried out as follows: (1) a 200x400 mesh size fraction of the solid fuel under study is pyrolyzed in the Drop Tube Furnace System in a nitrogen atmosphere at 2650°F to drive off the volatile matter under appropriately rapid heating conditions, and the resulting char is size graded to 200x400 mesh; and (2) this 200x400 mesh char is subsequently subjected to TGA reactivity in air at 1290°F and BET surface area measurement in nitrogen at -321°F. This procedure is depicted graphically in Figures 1 and 2. For the same reason given above, a 325x0 mesh size fraction was also studied here to determine the effects of feed coal nature, beneficiation process and particle size on char reactivities.

RESULTS

Chemical Analyses of Test Fuels

The chemical analyses of the test fuels are given in Table 1. It is noteworthy that the microbubble flotation process (MFP) performed on Illinois No. 6, Pittsburgh No. 8, and Upper Freeport coals led to the following results: ash contents reduced by more than 50%; pyritic sulfur contents reduced by more than 80%; calorific values increased by more than 5%. The spherical oil agglomeration process (SOAP) also performed on Illinois No. 6 coal led to a BCF sample of similar quality to the one prepared in the microbubble process. These changes did, however, not materially improve the ash qualities of the BCF products, as is shown in the following section.

FIGURE 1 SCHEMATIC OF DROP TUBE FURNACE SYSTEM-1(DTFS-1)

CHAR PREPARATION

CHAR EVALUATION

FIGURE 2 TGA AND BET EVALUATION OF COAL CHARS

TABLE 1
TYPICAL FUEL ANALYSES FOR
FPTF COMBUSTION PERFORMANCE TESTS

	ILLINOIS NO. 6		UPPER FREEPORT		PITTSBURGH NO. 8	
<u>QUANTITY</u>	<u>PARENT</u>	<u>DMPC</u>	<u>PARENT</u>	<u>MCWF</u>	<u>PARENT</u>	<u>DMPC</u>
Proximate (wt%)						
Moisture	4.5	7.0	1.4	38.7	1.9	2.9
Volatile Matter	36.9	37.6	27.7	18.6	38.2	40.4
Fixed Carbon	50.0	51.5	60.3	39.3	50.5	53.5
Ash	8.6	3.9	10.6	3.4	9.4	3.2
HHV, Btu/lb	12100	12265	13420	8500	12775	13629
Ultimate (dry, wt%)						
Hydrogen	5.0	4.8	4.7	5.3	5.0	5.7
Carbon	69.3	75.5	76.9	79.6	71.4	77.5
Sulfur	3.0	2.7	1.8	1.4	4.5	3.3
Nitrogen	1.3	1.0	1.3	2.2	1.2	1.3
Oxygen	12.4	11.8	4.6	6.0	8.4	8.9
Ash	9.0	4.2	10.7	5.5	9.5	3.3
Forms of Sulfur (dry, wt%)						
Pyritic	0.53	0.09	0.49	0.05	1.34	0.03
Sulfate	0.35	0.41	0.55	0.56	0.44	0.60
Organic	2.12	2.20	0.76	0.79	2.72	2.67
Ash Fus. Temps (RED.ATM, °F)						
IDT	2000	2020	2010	1900	2130	1900
ST	2280	2180	2380	2000	2390	1980
HT	2420	2230	2450	2080	2440	2020
FT	2530	2280	2400	2120	2490	2119
Ash Composition						
SiO ₂	51.7	42.0	43.8	38.3	39.3	34.1
Al ₂ O ₃	20.7	19.3	24.2	24.7	20.2	22.3
Fe ₂ O ₃	16.9	21.2	18.8	17.0	31.4	27.7
CaO	2.2	3.7	3.1	3.1	3.0	4.6
MgO	0.9	1.4	0.9	1.2	0.8	1.3
Na ₂ O	0.5	2.3	0.9	7.0	0.5	2.2
K ₂ O	2.0	2.3	2.2	2.5	1.5	1.6
TiO ₂	0.8	2.2	0.2	1.8	1.0	1.8
P ₂ O ₅	0.0	0.1	0.2	0.2	0.1	0.2
SO ₃	2.1	3.4	3.9	2.8	2.1	3.2

Mineralogical Characteristics of Illinois No. 6 Coal and its Microbubble Product

In general, it was found that the small size of the coal and mineral matter in the MFP decreased the precision of the CCSEM data, thereby making interpretation more difficult than usual. The relative sizes of the particles in the parent and the MFP fuels are shown in figures 3A and 3B. The precision in the CCSEM data decreased because so few mineral grains larger than ten microns in diameter were present in the MFP. Counting statistical variations in the data played a much larger role than normal in interpreting the data. The CCSEM analyses show a significant reduction in silicate minerals. The size of most of the aluminosilicate particles in the coal are reduced during the cleaning process through comminution and deaggregation of clay platelets (due to slurring) to less than one μm in diameter, making them undetectable by CCSEM. In fact, the presence of the aluminosilicate particles in the submicron range can only be inferred from the insignificant decrease in the aluminum content of the fuel ashes caused by cleaning. Because the quartz grains in the coal are much harder than the clay grains, they are not similarly reduced in size. Therefore, quartz makes up a larger fraction of the mineral matter detectable by CCSEM in the MFP.

The yield, ash contents, normalized compositions, and reducing atmosphere fusibility temperatures of the specific gravity fractions of the Illinois No. 6 parent coal and its microbubble flotation product are shown in Tables 2 and 3. A comparison of the yield values for the two fuels shows that the cleaning process was efficient at removing the heavier (1.4 sink) portion of the parent coal. The ash compositions of the 1.4 float fractions of each fuel were fairly similar to the ash compositions of the bulk fuels. The steady reduction in aluminum content as density increases shows that the clays in both fuels are predominantly present as very fine or included particles and, therefore, do not concentrate in the specific gravity fraction (2.5-2.9) that covers the density of most clays (2.6). The higher calcium and sulfur contents of the 1.4-2.5 fractions for each fuel show that the gypsum of each fuel tends to separate from the carbonaceous portion of the coal during grinding and so is free to concentrate in the fraction that covers the specific gravity of gypsum (2.3). The much higher concentrations of calcium and sulfur in the MFP's 1.4-2.5 fraction as compared to the bulk MFP fuel indicates that gypsum is more highly liberated during the microbubble cleaning process than during normal grinding. The relatively high concentrations also show that the microbubble process does not remove a significant fraction of the liberated gypsum. The ash fusibility temperatures of these fuels also indicate higher slagging and fouling potentials for the MFP fuel than for its parent coal. Fuel size data are shown in Table 4.

Figure 3A SEM Photo of Illinois #6 Parent Coal (500X)

Figure 3B SEM Photo of Illinois #6 Microbubble Flotation Process Product (500X)

Table 2. Gravity Fractionation Data For Illinois #6 Coal

	Specific Gravity, g/cm ³			
	<1.4	1.4-2.5	2.5-2.9	>2.9
Yield, Wt.%	85.27	13.86	0.52	0.35
Ash, Wt.%	4.6	26.1	79.1	64.8
Composition, Wt.%				
SiO ₂	52.60	53.50	60.40	ND
Al ₂ O ₃	23.90	22.00	17.40	
Fe ₂ O ₃	13.90	12.50	14.80	
TiO ₂	1.90	0.60	0.30	
P ₂ O ₅	0.00	0.00	0.00	
CaO	2.10	3.90	2.70	
MgO	1.80	1.50	0.80	
Na ₂ O	0.00	0.50	0.00	
K ₂ O	3.00	2.60	1.50	
SO ₃	0.90	2.90	2.10	
Ash Fusion				
IDT, °F	2020	2020	2000	ND
ST, °F	2200	2100	2090	
HT, °F	2320	2162	2260	
FT, °F	2340	2250	2330	

ND - Not Determined

Table 3 Gravity Fractionation Data For Illinois #6 MFP Fuel

	Specific Gravity, g/cm ³			
	<1.4	1.4-2.5	2.5-2.9	>2.9
Yield, Wt.%	96.44	2.73	0.81	0.02
Ash, Wt.%	3.5	8.0	7.8	71.2
Composition, Wt.%				
SiO ₂	43.30	40.90	49.50	ND
Al ₂ O ₃	21.00	17.10	15.60	
Fe ₂ O ₃	20.90	12.20	21.50	
TiO ₂	2.70	1.20	1.20	
P ₂ O ₅	0.10	0.60	0.20	
CaO	3.20	10.20	4.00	
MgO	1.70	1.10	1.30	
Na ₂ O	2.30	1.20	1.40	
K ₂ O	2.80	1.80	1.10	
SO ₃	1.90	13.50	4.30	
Ash Fusion				
IDT, °F	1870	1980	ND	ND
ST, °F	1900	2050		
HT, °F	2010	2100		
FT, °F	2150	2180		

ND - Not Determined

TABLE 4
PARTICLE SIZE DISTRIBUTIONS OF FPTF BELT FEED SAMPLES

WEIGHT PERCENT GREATER THAN X						
SCREEN SIZE X (microns)	UPPER FREEPORT (Coal) (MFP)		PITTSBURGH NO. 8 (Coal) (MFP)		ILLINOIS NO. 6 (Coal) (MFP)	
1180	---	0.1	---	---	---	---
600	0.1	0.2	0.1	---	---	0.1
300	0.7	0.6	0.5	0.4	0.8	0.4
150	5.9	5.0	4.1	3.0	5.9	3.3
75	26.9	19.5	21.3	11.0	26.2	8.6
45	66.2	27.5	56.1	25.3	57.0	12.7
Rosin-Rammler Parameters						
R	0.96	0.97	0.99	0.99	0.96	0.99
n	1.05	0.55	1.12	0.72	0.93	0.49
x ¹ (lm)	72.90	24.76	65.82	26.80	57.24	11.18
x (lm)	71.62	41.64	63.23	33.14	59.17	22.95
=====						

n = dispersion factor
R = correlation coefficient of Rosin-Rammler plot
x¹ = fineness factor
x = mean weight particle size

Ignitibility Characteristics of Test Fuels

The Flammability Index (FI) was used as a measure of the ignitibility characteristic of each test fuel. Results are presented below:

<u>Fuel</u>	<u>Flammability Index, °F</u>	
	(200x0 mesh)	(325x0 mesh)
Upper Freeport Coal	1060	1060
Upper Freeport Microbubble Product	850	840
Illinois No. 6 Coal	950	950
Illinois No. 6 Microbubble Product	850	840
Illinois No. 6 Spherical Agglomeration Product	850	840
Pittsburgh No. 8 Coal	940	920

Comparatively, the FI results in the CE data bank show 800-950°F for lignites, 900-1050°F for subbituminous coals, 1050-1250°F for bituminous coals and 1450-1700+° for anthracites. As such, the present results indicate two important things: (1) the two particle size fractions used gave essentially the same FI values, implying that they can be used interchangeably, as far as this test is concerned; and (2) each of the feed coals and BCFs has good ignitibility characteristics and should not cause ignitibility/flame turndown problems under normal pulverized-fuel firing conditions.

Reactivities and Physical Characteristics of Test Fuel Chars

The TGA and BET test procedures entailed pyrolyzing 200x400-mesh and 325x0-mesh size fractions of feed stocks in the DTFS in a nitrogen atmosphere at 2650°F to drive off the volatile matter. The resulting chars, sized to 200x400 and 325x0 mesh, were subjected to TGA and BET measurements in air at 1290°F (700°C) and nitrogen at -321°F (-196°C), respectively. The TGA results from this study are presented along with those obtained previously on chars prepared from reference coals with which CE has field experience. The BET data are shown below.

<u>Fuel</u>	<u>BET Surface Area of Char, m²/g (daf)</u>	
	(200x400 mesh)	(325x0 mesh)
Upper Freeport Coal	23.6	28.8
Upper Freeport Microbubble Product	17.8	32.1
Illinois No. 6 Coal	33.1	32.5
Illinois No. 6 Microbubble Product	31.0	39.4
Illinois No. 6 Spherical Agglomeration Product	35.9	48.6
Pittsburgh No. 8 Coal	29.3	49.8
<u>Reference Coals</u>		
Wyoming Sub A Coal	64.0	--
W. Virginia mvb Coal	11.9	--
Pennsylvania Anthracite	2.6	--

The TGA burn-off curves (Figures 4 and 5) indicate that: (1) the microbubble coal cleaning process did not adversely affect the reactivities of the resulting chars; (2) the spherical agglomeration process also did not adversely affect the reactivity of the char; (3) the impact of particle size on reactivity is more pronounced for the least reactive coal char (i.e., the one prepared from the Upper Freeport coal); and (4) all the chars studied to date are considered to have good combustion reactivities (they are all significantly more reactive than a char prepared from a West Virginia medium volatile bituminous coal, which is successfully burned in a CE utility boiler). The BET specific pore surface areas are generally in support of the TGA burn-off curve results.

In as much as char burnout (rather than volatile matter release and burnout) constitutes the rate-determining step in the overall scheme of pulverized coal combustion, it appears, based on these preliminary results and CE's field experience, that the microbubble and spherical oil agglomeration cleaning processes did not adversely affect the burnout properties of the Upper Freeport and Illinois No. 6 feed coals. Future activities on combustion kinetic studies (Task 2.2) and on-going pilot-scale tests (Task 3) will enable CE to quantitatively evaluate the effects of various coal cleaning process on BCF burning characteristics. In fact, work carried out to date in CE's 4 million Btu/hr pilot-scale test facility indicates that both Illinois No. 6 coal and its microbubble flotation product burned equally well (to >99% efficiency), which agrees with the bench-scale results.

FIGURE 4 TGA BURN-OFF CURVES IN AIR AT 700°C FOR BCF AND REFERENCE COAL CHARs SIZED TO 200X400 MESH

FIGURE 5 TGA BURN-OFF CURVES IN AIR AT 700° C FOR BCF CHARS
SIZED TO 200X400 MESH AND 325X0 MESH

MIT drop-tube furnace combustion tests of the Upper Freeport coal and BCF continued. Initial results from burnout tests in the MIT laminar flow reactor are shown in Figure 6 for two size fractions. As expected, increases in furnace temperature or oxygen concentration result in higher levels of burnout (the ordinate represents the percent ash in the captured solid sample from the furnace; 70 percent ash is approximately 90 percent carbon burnout). It was also expected that the smaller size fraction (38-45 μ m) would have better burnout characteristics than the 75-90 micrometer fraction. However, the data in Figure 6 show the opposite trend. Both size fractions were fed at the same rate, and it is suspected that coal particle agglomeration during devolatilization contributed to the reduced burnout of the smaller size fraction. Previous work has shown that a reduced feed rate for smaller particles is desirable for eliminating the possibility of particle agglomeration.

To address this issue, the smaller size fraction was then fed at a volumetric rate five times lower than the larger fraction. Figure 7 shows the comparison of the progression of the carbon burnout of the 38-45 micrometer and 75-90 micrometer fractions at 1750°K and 10 percent oxygen. The results show that the burnout behavior of the two size fractions is very similar, which confirms that the 38-45 micrometer fraction was agglomerating in the devolatilization zone at the higher feed rate.

Combustion tests in the drop-tube furnace of the spherical oil agglomeration beneficiated Upper Freeport coal are underway. Because of the fine particle size of the fuel, the feeding system for the drop-tube furnace was modified to remove large agglomerates of coal particles. As expected, burnout times for the fine particles are shorter than for the larger particles in the raw fuel. Fly ash samples from the spherical agglomeration beneficiated coal have been collected and are awaiting CCSEM analysis.

Ash deposition tests were carried out for the Upper Freeport feed coal and SOAP in the PSIT drop tube furnace to determine differences in the deposition propensity. Uncooled mullite substrates were used as the deposition surface. Furnace gas temperature and the corresponding ash particle temperature at the substrate were varied and the deposition efficiency measured.

As shown in Figure 8, the deposition efficiency decreased with temperature for both the fuels. The higher deposition efficiency for the lower tube is because of a higher impaction velocity corresponding to a higher velocity at this location, i.e., a larger fraction of the smaller ash particles impact the lower tube. The higher deposition efficiency for the parent coal compared to the beneficiated coal is due to the larger sized ash particles formed from the combustion of this coal. Visual and photographic observations of the morphology of the deposit at the highest temperature indicated a molten slag for both the fuels. At the lower temperatures, also, no difference was observed in the level of sintering in the deposit between the two coals, although the amount of

FIGURE 6 Burnout of Raw Upper Freeport Coal

FIGURE 7 Burnout of Upper Freeport Coal
75-90 μm and 38-45 μm Fraction at 1750 K and 10% O_2

deposit for the beneficiated coal was smaller. Chemical analysis of the deposit will be obtained as the next step, and this should reveal if any differences in deposit composition exist. In summary, the difference in the deposition behavior of the two coals is mainly due to larger ash particle sizes generated from the combustion of the parent coal.

Figure 8. Deposition Efficiency for Ash from Combustion of Upper Freeport Coals

TASK 3 - PILOT SCALE TESTING

Combustion experiments are conducted with selected fuels in MIT's Combustion Research Facility (CRF) to characterize the effects of fuel type, beneficiation process, and firing mode upon flame stability, carbon conversion, and gaseous emissions. Combustion tests are also run in CE's Fireside Performance Test Facility (FPTF) with most of the base project fuels, to evaluate combustion performance, furnace wall slagging, convection pass fouling, fly ash erosion, electrostatic precipitator performance, and emissions.

3.1 Pilot-Scale Atomization, Combustion, and Emissions Tests at MIT

Combustion and atomization tests on the microbubble beneficiated Upper Freeport coal water fuel (CWF) were performed during this period. A total of five experimental flames were established using the coal water fuel. The excess air level was varied on flames one through three, with the oxygen concentration in the flue gas analyzed at 2.7, 3.8, and 1.9 volume percent, respectively. For these flames, the fuel temperature was held at room temperature. Cases four and five were established with 3.4 and 2.0 volume percent oxygen in the flue, with the fuel heated to 110°C.

Atomization tests were performed on the fuel in a cold spray test rig to explore the effects of atomizing air flow and fuel temperature on CWF droplet size. The results of the spray tests are reported in Figure 9. The low temperature fuel case is shown in the top panel and the higher temperature case in the lower panel. The droplet or particle sizes, as measured by the Malvern Particle Sizer, are shown versus the atomizing air to fuel mass ratio. The droplet or particle size data are reported as circles plotted at percentiles. The tests were performed by setting a constant fuel flow rate and varying the atomizing air flow. As expected, the data show that increasing the atomizing air flow will decrease the droplet size, up to a limit. Also, the effect of fuel temperature can be seen by the decrease in the larger sized droplets for the heated fuel case.

The carbon burnout profiles of the flames using the heated CWF as compared to the room temperature fuel are shown in Figure 10. This comparison is made in the top panel, while the lower panel compares the carbon monoxide levels in the early part of the flame (note the change in scale of the x-axis between the two panels). As can be seen from Figure 10, the early burnout behavior of both cases is similar, but the heated fuel flame was found to have higher levels of burnout in the middle part of the flame. By the furnace exit, the burnout of the two cases are the same, about 99.5 percent. The difference in the middle of the flame is thought to be caused by the larger droplets in the room temperature fuel case.

FIGURE 9

FIGURE 10

A comparison of the char particle size distributions in the flame for the effect of fuel temperature is shown in Figure 11. The coal particle size in the CWF and the fuel spray droplet size (from the spray rig test) are also shown. The char sampled very early in each flame is larger than the fuel droplets found in the spray testing. It is thought that the heating of the droplets by the radiation in the flame interferes with the breakup of the fuel spray. The char size sampled in the early part of the heated fuel flame shows that the higher fuel temperature results in smaller char sizes.

At 1.8 meters axial distance, the char sizes from the two flames are identical. However, by looking at Figure 10, it can be seen that the mass fraction for the room temperature fuel case is 25 percent compared to 15 percent for the higher fuel temperature flame. The conclusion is that the flame temperature and residence time for both cases can cause the smaller droplets to burn out quickly, but the larger droplets (and the larger fraction of the large droplets) in the room temperature fuel case take longer residence times to burn out. The last points on the right of Figure 11 represent the char left at 99.5 percent carbon burnout. The larger sizes in the room temperature fuel flame show the resulting effect of the poorer atomization.

The effects of excess air on carbon burnout for the comparison of fuel temperature are shown in Figure 12. The data is the opposite of what was expected; the burnout is better for lower excess air levels for both fuel temperatures. This effect is suspected to be a result of changes in the near-field aerodynamics by the increases in the momentum of the additional air.

In preparation for the upcoming test of pulverized Upper Freeport feed coal, the pulverized coal feeding system at MIT was overhauled to insure safe and consistent operation on pulverized coal. Level indicators were added to the feeding system and vibrators were added to the storage hopper. Preliminary tests on the warm-up fuel indicate that the operation of the feeding system with pulverized coal will be stable.

3.2 Combustion Performance Tests - CE

The combustion and ash performance of seven test fuels have been evaluated in CE's Fireside Performance Test Facility (FPTF) shown in Figure 13. These fuels included Upper Freeport spherical agglomerate product (SOAP), Illinois No. 6, Upper Freeport, and Pittsburgh No. 8 microbubble flotation products (MFPs), and their respective parent coals. Most of the test data from the three MFPs have been reduced and are discussed in this report.

FIGURE 11

FIGURE 12

FIGURE 13 FIRESIDE PERFORMANCE TEST FURNACE

Due to the high moisture contents of the as-received MFPs, they were initially air dried to facilitate handling. The Illinois No. 6 and Pittsburgh No. 8 MFPs were then further dried into a dry microfine pulverized coal form using a CE size 271 bowl mill, and the Upper Freeport MFP was formulated into a microfine coal-water fuel. The parent coals were prepared as standard grind pulverized coals (70% through 200 mesh). The chemical analyses of the as-fired test fuels are shown in Table 5.

The combustion and ash performance of each test fuel were evaluated at firing rates between 3.5×10^6 and 4.0×10^6 Btu/hr under operating conditions simulating those of commercial boilers (Table 6). Each test was conducted with approximately 20% excess air. Preheated combustion air was used to offset relatively high furnace heat absorption and provide flame temperature control (approximately 2800°F to 3000°F). The Upper Freeport MFP MCWF was preheated to 240°F fuel temperature for improved atomization during testing. Furnace residence time varied from 1.01 to 1.23 seconds. The FPTF furnace gas temperature profiles during these tests are illustrated in Figure 14. The furnace slagging, convection pass fouling, fly ash erosion and fly ash collectibility characteristics of each fuel were determined during these test runs. Ash samples were collected after each test and sent to UNDEERC for analyses.

Furnace Slagging Characteristics

Test results for the three MFPs indicate that from a heat transfer standpoint, firing the MFPs resulted in higher waterwall heat absorption than the parent coals. However, from a deposit cleanability standpoint, no improvement was observed with the MFPs.

The waterwall heat flux data from test runs at 4×10^6 Btu/hr firing rate and similar gas temperatures for the MFPs and parent coals are depicted by the plots shown in Figure 15. During the initial two to four hours, waterwall heat flux values decreased with time for each fuel, due to deposit accumulation on the waterwall surface. After this period, waterwall heat flux with the parent coals continued to drop, whereas, with the MFPs, it remained relatively high and constant, indicating the deposit thickness approached steady state and had minimal impact on waterwall heat transfer. The difference in heat flux reduction between the MFP and parent coal was coal type dependent. It was largest between the Pittsburgh No. 8 fuels, followed by the Upper Freeport, and the Illinois showed the least difference.

The heat flux results are in general agreement with the waterwall deposits observed during testing. Deposits generated from the MFPs were much thinner than those from the parent coals. The Upper Freeport MFP had a physical state similar to its parent coal deposits, but the Illinois No. 6 and Pittsburgh No. 8 MFP deposits

TABLE 5
TYPICAL FUEL ANALYSES FOR
FPTF COMBUSTION PERFORMANCE TESTS

	ILLINOIS NO. 6		UPPER FREEPORT		PITTSBURGH NO. 8	
<u>QUANTITY</u>	<u>PARENT</u>	<u>MFP DMPC</u>	<u>PARENT</u>	<u>MFP MCWF</u>	<u>PARENT</u>	<u>MFP DMPC</u>
Proximate (wt%)						
Moisture	4.5	7.0	1.4	38.7	1.9	2.9
Volatile Matter	36.9	37.6	27.7	18.6	38.2	40.4
Fixed Carbon	50.0	51.5	60.3	39.3	50.5	53.5
Ash	8.6	3.9	10.6	3.4	9.4	3.2
HHV, Btu/lb	12100	12265	13420	8500	12775	13629
Ultimate (dry, wt%)						
Hydrogen	5.0	4.8	4.7	5.3	5.0	5.7
Carbon	69.3	75.5	76.9	79.6	71.4	77.5
Sulfur	3.0	2.7	1.8	1.4	4.5	3.3
Nitrogen	1.3	1.0	1.3	2.2	1.2	1.3
Oxygen	12.4	11.8	4.6	6.0	8.4	8.9
Ash	9.0	4.2	10.7	5.5	9.5	3.3
Forms of Sulfur (dry, wt%)						
Pyritic	0.53	0.09	0.49	0.05	1.34	0.03
Sulfate	0.35	0.41	0.55	0.56	0.44	0.60
Organic	2.12	2.20	0.76	0.79	2.72	2.67
Ash Fus. Temps (RED.ATM, °F)						
IDT	2000	2020	2010	1900	2130	1900
ST	2280	2180	2380	2000	2390	1980
HT	2420	2230	2450	2080	2440	2020
FT	2530	2280	2400	2120	2490	2119
Ash Composition						
SiO ₂	51.7	42.0	43.8	38.3	39.3	34.1
Al ₂ O ₃	20.7	19.3	24.2	24.7	20.2	22.3
Fe ₂ O ₃	16.9	21.2	18.8	17.0	31.4	27.7
CaO	2.2	3.7	3.1	3.1	3.0	4.6
MgO	0.9	1.4	0.9	1.2	0.8	1.3
Na ₂ O	0.5	2.3	0.9	7.0	0.5	2.2
K ₂ O	2.0	2.3	2.2	2.5	1.5	1.6
TiO ₂	0.8	2.2	0.2	1.8	1.0	1.8
P ₂ O ₅	0.0	0.1	0.2	0.2	0.1	0.2
SO ₃	2.1	3.4	3.9	2.8	2.1	3.2

TABLE 6

**COMBUSTION PERFORMANCE TEST MATRIX
20% EXCESS AIR**

FUEL TYPE	FIRING MODE	FIRING RATE (10 ⁶ Btu/h)	AVG. FLAME TEMPERATURE (°F)	FURN. OUTLET TEMPERATURE (°F)	TEST DURATION (h)

Illinois #6					
Parent	PC	3.75	2740	2250	12
		4.00	2870	2320	24
		4.00	2980	2350	24
MFP	DMPC	4.00	3030	2450	24
		4.00	2960	2340	24

Upper Freeport					
Parent	PC	3.75	2910	2290	12
		4.00	2990	2340	24
MFP	MCWF	4.00	2970	2270	20

Pittsburgh #8					
Parent	PC	3.75	2920	2290	12
		4.00	2990	2360	12
		3.50	2860	2230	12
MFP	DMPC	3.75	2960	2260	24
		4.00	2980	2360	24

FIGURE 14 FPTF Temperature - Residence Time Profiles During MFP and Parent Coal Testing

FIGURE 15 Comparison of Waterwall Heat Transfer Characteristics Between MFPs and Parent Coals at 4×10^6 Btu/h

consisted of a very thin fused scale compared to the molten deposits generated from their respective parent coals. A summary of the waterwall deposit physical characteristics are shown in Table 7.

Soot blowing was conducted at the end of each test run to assess waterwall deposit cleanability. Sufficient time was allowed when possible for the waterwall deposits to approach long-term characteristics, thereby more closely simulating field deposits generated during continuous operation of a commercial boiler. Results showed that although deposits generated from the MFPs were thinner than the parent coal deposits, cleanability did not improve. The critical furnace temperatures where deposits were still cleanable by wall blowers remained in the same temperature range for each MFP and parent coal type.

Convection Pass Fouling Characteristics

The fouling characteristics of the six test fuels are summarized in Table 8. In general, convection tube deposits generated from the MFPs were more sintered and had higher deposit-to-tube bonding strengths than those from the parent coals. Convection tube deposit buildup rates were reduced with the Illinois No. 6 and Pittsburgh No. 8 MFPs, but were similar with the Upper Freeport MFP, compared to their respective parent coals.

The deposit-to-tube bonding strength was measured using a digital penetrometer. This device provides a quantitative measurement which can be related to the ease of deposit removal by soot blowing. Standard values were established by CE based upon calibration between field measurements and observed commercial soot blower effectiveness. Typically, deposits having bonding strengths of up to 15 are considered cleanable. At similar gas temperatures, firing the Illinois No. 6 MFP produced deposits with higher bonding strengths than those from the parent coal (10 to 13 versus 5 to 9), but remained at moderate levels for cleanable deposits. For both the Upper Freeport and Pittsburgh No. 8 MFPs, deposit bonding strengths increased from a low level to the maximum level acceptable for cleanable deposits (from 1 to 4 and 5 to 7 for the parent coals to 15 and 16 for the MFPs, Upper Freeport and Pittsburgh No. 8 fuels, respectively). Comparisons of convection deposit-to-tube bonding strength between MFPs and parent coals are illustrated in Figure 16.

The convection tube deposit build-up rate for each test fuel was reflected by the sootblowing requirements. At similar conditions, firing the Illinois No. 6 and Pittsburgh No. 8 MFPs significantly reduced the sootblowing requirements (from 4 hours to 8 hours and 8 hours to 12 hours, respectively). However, for the Upper Freeport MFP, soot blowing requirements remained similar to its parent coal (2 to 3 hours).

TABLE 7

WATERWALL DEPOSIT
PHYSICAL CHARACTERISTICS

FUEL TYPE	FIRING MODE	FIRING RATE (10 ⁶ Btu/h)	AVG FLAME TEMP (°F)	DEPOSIT PHYSICAL STATE	DEPOSIT THICKNESS (mil)	DEPOSIT CLEANABILITY
Illinois #6						
Parent	PC	3.75	2740	sintered		good
		4.00	2870	sintered		good
		4.00	2980	molten	109	poor
MFP	DMPC	4.00	3030	fused		poor
		4.00	2960	scale	19	poor
Upper Freeport						
Parent	PC	3.75	2910	molten		good
		4.00	2990	molten	320	poor
MFP	MCWF	4.00	2970	molten	234	poor
Pittsburgh #8						
Parent	PC	3.75	2920	molten		good
		4.00	2990	molten	125	poor
		3.50	2860	molten		good
MFP	DMPC	3.75	2960	fused		poor
		4.00	2980	scale	21	poor

TABLE 8

CONVECTION TUBE FOULING
CHARACTERISTICS

FUEL TYPE	FIRING MODE	FIRING RATE (10 ⁶ Btu/h)	GAS TEMP ENTERING (°F)	DEPOSIT PHYSICAL STATE	AVERAGE DEPOSIT BONDING STRENGTH	SOOTBLOWING FREQUENCY (h)
Illinois #6						
Parent	PC	3.75	2250	sintered	5	6
		4.00	2320	sintered	7	4
		4.00	2350	sintered	9	4
MFP	DMPC	4.00	2440	sintered	13	8
		4.00	2340	sintered	10	8
Upper Freeport						
Parent	PC	3.75	2290	sintered	<1	6
		4.00	2340	sintered	4	2
MFP	MCWF	4.00	2320	sintered/molten	15	3
Pittsburgh #8						
Parent	PC	3.75	2290	sintered	5	8
		4.00	2360	sintered	7	8
		3.50	2230	sintered	5	8
MFP	DMPC	3.75	2260	sintered	15	12
		4.00	2360	sintered	16	12

FIGURE 16 Comparison of Convection Deposit-to-Tube Bonding Strength Between MFPS and Parent Coals

An unusual characteristic was also observed during the Illinois No. 6 MFP testing. This phenomenon was not observed with the parent coals and other MFPs, nor with other conventional pulverized coals test-fired in the FPTF. Fine powdery deposits were developed at gas temperatures below approximately 1500°F with the Illinois No. 6 MFP. These powdery deposits adhered to the duct walls and low temperature surfaces downstream of the FPTF superheater section. These observations indicate that this fuel could present fouling problems in the economizer and airheater sections of steam generators.

The ash performance characteristics of the MFPs can be generally explained by the ASTM as-fired fuel analyses shown in Table 5. The ash fusibility temperatures of each of the MFPs were lower than those of the corresponding parent coals. The lower temperatures appears to be caused by the changes in the ash constituents of each fuel. Ash composition showed reduction in silicate, which was probably preferentially removed during the microbubble flotation process, thereby causing a relative enrichment in the basic constituents of each fuel. Lower ash fusibility temperatures tend to form more fluid deposits on the furnace walls.

Ash deposits build-up rates should be generally reduced with the MFPs due to their lower ash contents. However, this benefit was partially offset by the enrichment of sodium in each MFP. Convection tube deposits from the MFPs were more sintered with higher deposit-to-tube bonding strengths than the parent coal deposits. The increase in sodium appeared to be related to the microbubble flotation process, and with the Upper Freeport MFP, a commercially established process which included a sodium-based additive used to formulate a heatable microfine coal-water fuel. Active alkalis such as sodium are very instrumental in ash fouling behavior due to their propensity to form very low melting temperature compounds and to act as a bonding medium cementing deposits together.

The reasons for the adhering tendency of the Illinois No. 6 MFP fly ash are not clear. On-going fuel analyses being conducted by UNDEERC indicated that sulfation of liberated calcium oxide particles from this fuel may be the cause of this phenomenon. Additional results from analyses on deposit samples and other MFPs, as they become available, may help to explain the fouling behavior of this fuel.

Fly Ash Erosion

The fly ash erosion test results indicate that firing the MFPs produced significantly less erosion than the parent coals. These results were anticipated due to the reduction in ash loadings from the beneficiation process and the generally smaller fly ash particles generated from the MFPs. A summary of the erosion data is shown in Table 9. To provide a basis for comparison, the experimental erosion rates were normalized to 60 ft/s using a

TABLE 9

FLY ASH EROSION
CHARACTERISTICS

PARAMETER	ILLINOIS NO. 6		UPPER FREEPORT		PITTSBURGH NO. 8	
	<u>Parent</u>	<u>MFP</u>	<u>Parent</u>	<u>MFP</u>	<u>Parent</u>	<u>MFP</u>
Ash Loading lb/h	16.2	7.7	18.3	9.0	16.7	5.4
Fly Ash Size MMD, microns	7.5	3.2	---	---	---	---
Gas Velocity ft/sec	264	273	255	252	233	237
Raw Rear Microns	8.0	5.5	24.7	1.9	26.2	2.0
Normalized Wear ¹ mil/10,000h	2.4	0.4	3.0	0.5	3.8	0.2
Quartz Content in Fly Ash, %	17.8	5.0	---	---	---	---

¹Normalized to 60 ft/s and 10,000 h

velocity correlation. Generally, erosion is expected to increase exponentially with velocity and linearly with ash loading.

The impact of the microbubble flotation process on erosion characteristics is illustrated in Figure 17. Reduction in ash loading by 52%, 51%, and 68% resulted in approximately 83%, 83% and 95% decreases in erosion rate for the Illinois No. 6, Upper Freeport, and Pittsburgh No. 8 coals, respectively.

The improvement in erosion rates beyond those projected for the reduction in ash loadings is attributed to the relative erosiveness of the ash. CCSEM analyses of the fly ash samples conducted by UNDEERC (Table 10) showed a significant reduction in quartz concentration for the Illinois No. 6 MFP compared to that of the parent coal fly ash (5.1% versus 17.8%). These results may explain the differences in erosion behavior between the MFPs and their parent coals. Quartz is generally considered to be one of the most erosive constituents of fly ashes that can significantly contribute to overall erosion characteristics.

Fly Ash Collectability

Fly ash collectability of the test fuels was evaluated in a pilot-scale ESP. Results are summarized in Table 11. Comparison between the MFPs and parent coals showed some marked differences. In general, fly ash collectability was affected by fuel type and firing mode.

As illustrated in Figure 18, firing the Illinois No. 6 and Pittsburgh No. 8 MFPs as dry microfine pulverized coal significantly reduced the ESP collection efficiency from that of their parent coals. The lower collectability of these two MFP fly ashes apparently was caused by electrical resistivities higher than those of their respective parent coal. During the Upper Freeport MFP testing, these effects seemed to be more than offset by the higher moisture concentration in flue gas because of the microfine coal-water fuel firing mode. The ESP collection efficiency was higher with the Upper Freeport MFP microfine coal-water fuel than with its parent coal.

Additional evaluation of fly ash particle size distributions and chemical compositions, as well as bench-scale resistivity measurements are on-going to help better understand the differences between the BCFs and parent coals.

FIGURE 17 Comparison of Fly Ash Erosion Between MFPs and Parent Coals

TABLE 10

CCSEM DATA FOR THE ILLINOIS NO. 6 MFP AND PARENT COAL FLY ASHES
PARENT COAL FLY ASH

Diameter (lm)	1.0-2.2	2.2-4.6	4.6-10	10-22	22-48	>48	Total Wt%
Quartz	2.2	4.3	3.5	5.9	1.3	0.6	17.8
Iron Oxide	0.0	0.2	1.1	1.5	0.6	0.0	3.4
Aluminosilicate	0.3	2.1	4.4	13.4	3.5	0.0	23.7
CA-aluminosilicate	0.2	0.3	0.5	1.1	1.1	0.0	3.0
Fe-aluminosilicate	3.1	6.2	3.0	6.5	3.1	0.0	22.0
K- aluminosilicate	0.2	0.9	3.6	9.1	4.1	0.0	17.8
Gypsum	0.0	0.0	0.0	0.0	0.0	0.0	0.0
Ca-Silicate	0.2	0.5	0.5	0.6	0.4	0.0	2.2
Aluminosil/Gypsum	0.0	0.0	0.0	0.0	0.0	0.0	0.0
Ca-Aluminate	0.0	0.0	0.0	0.0	0.1	0.0	0.1
Calcite	0.0	0.1	0.5	0.1	0.2	0.0	0.8
Pyrrhotite	0.0	0.0	0.3	0.0	0.0	0.0	0.3
Ca-Rich	0.0	0.0	0.2	0.0	0.0	0.0	0.2
Si-Rich	0.1	0.1	0.2	1.6	0.9	0.0	2.8
Unknown	0.4	0.6	1.2	2.3	1.2	0.0	5.6
TOTAL	6.5	15.2	19.0	42.3	16.5	0.6	100.0

MFP FLY ASH

Diameter (lm)	1.0-2.2	2.2-4.6	4.6-10	10-22	22-48	>48	Total Wt%
Quartz	0.2	1.3	1.3	1.3	1.0	0.0	5.0
Iron Oxide	0.0	0.0	0.3	3.1	4.1	0.0	7.5
Aluminosilicate	0.0	0.8	1.9	2.4	0.0	0.0	5.1
CA-aluminosilicate	0.1	0.4	0.4	0.9	0.5	0.0	2.4
Fe-aluminosilicate	6.7	24.1	6.3	8.4	3.6	7.8	56.8
K- aluminosilicate	0.0	0.5	0.2	1.0	0.4	3.9	6.1
Gypsum	0.0	0.0	0.0	0.7	0.9	0.0	1.6
Ca-Silicate	0.0	0.1	0.0	0.0	0.0	0.0	0.1
Aluminosil/Gypsum	0.0	0.1	0.0	0.6	0.3	0.0	0.9
Ca-Aluminate	0.0	0.0	0.0	0.0	0.0	0.0	0.0
Calcite	0.0	0.0	0.0	0.4	0.2	0.0	0.6
Pyrrhotite	0.0	0.0	0.0	0.0	0.0	0.0	0.0
Ca-Rich	0.0	0.0	0.0	0.0	0.0	0.0	0.0
Si-Rich	0.1	0.2	0.0	0.4	0.0	0.0	0.7
Unknown	0.6	1.9	0.9	5.7	2.2	2.0	13.2
TOTAL	7.7	29.3	11.3	24.8	13.3	13.7	100.0

TABLE 11

**PILOT-SCALE ELECTROSTATIC
PRECIPITATOR PERFORMANCE**

<u>PARAMETER</u>	<u>ILLINOIS NO. 6</u>		<u>UPPER FREEPORT</u>		<u>PITTSBURGH NO.8</u>	
	<u>Parent</u>	<u>MFP</u>	<u>Parent</u>	<u>MFP</u>	<u>Parent</u>	<u>MFP</u>
Flue Gas Flow Rate SCFM, dry	1,414	1,528	1,440	1,442	1,607	1,439
Flue Gas Moisture, %	4.0	5.8	4.1	7.0	4.3	4.1
SO ₃ Concentration, ppm	3.5	4.3	3.0	3.4	3.0	4.8
Fly Ash Size, MMD Microns	7.5	3.2	---	---	---	---
Fly Ash Resistivity 10 ¹³ ohm-cm	0.2	2.7	---	---	1.7	4.3
ESP Collection Efficiency, %	91	23	55	72	95	53
Migration Vel. cm/s	8.3	1.0	1.9	4.1	12.0	2.6
Specific Collection Area, ft ² /1000 acfm	147	129	139	149	123	141

FIGURE 18 Pilot-Scale Electrostatic Precipitator Collection Efficiencies

TASK 4 - SCALE-UP TESTS

The purpose of the scale-up tests is to verify that the results obtained from tests done at bench and pilot scales in Tasks 2 and 3 can be used to provide reasonable estimates of the performance effects when firing BCFs in commercial-scale boilers. Two beneficiated fuels will be fired in either a small utility boiler or full-scale test furnace.

The only activities in this task were discussions on fuel procurement, alternative test facility selection, and scheduling. Recommendations were submitted to the DOE.

TASK 5 - TECHNICAL-ECONOMIC EVALUATIONS

The results of bench-scale, pilot-scale, and scale-up tests (Tasks 2, 3, and 4) are used to predict the performance of three commercial boilers. The boilers include: a 560 MW coal-designed, utility unit; a 600 MW oil-designed utility unit; and an 80,000 lb/hr oil-designed, shop-assembled, industrial unit. Eight of the base project BCFs are used in models of each unit to calculate performance.

The writing of a report describing the commercial boilers which will be evaluated continued.

TASK 6 - TECHNICAL REPORTING

In addition to issuing the quarterly technical report, two technical papers were presented at the Fifteenth International Conference on Coal and Slurry Technologies, April 23 to 26, 1990, in Clearwater, Florida.

1. "Physical, Chemical, and Reactivity Characteristics of Beneficiated Coal-Based Fuels," by N. Y. Nsakala, R. L. Patel, J. P. Hurley, S. A. Benson, and M. J. Hargrove.
2. "Performance Characteristics of Beneficiated Coal-Based Fuels," by O. K. Chow, M. J. Hargrove, and D. E. Thornock.

WORK PLANNED FOR NEXT QUARTER

- ° Prepare the Illinois No. 6 and Pittsburgh No. 8 spherical agglomeration products for testing as dry pulverized fuel.
- ° Continue standard bench-scale tests.
- ° Continue drop tube furnace tests at CE and MIT.
- ° Test Upper Freeport feed coal in MIT's CRF.
- ° Test Illinois No. 6 and Pittsburgh No. 8 SOAP's in CE's FPTF.
- ° Complete report describing the Task 5 boilers.

END

**DATE
FILMED**

2 / 11 / 92