LA-11058-MS

UC-34

Issued: August 1987

LA--11058-MS

DE87 012694

Sesame Equation of State Number 7411, Al_2O_3

J. F. Barnes
S. P. Lyon

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

MASTER

Los Alamos Los Alamos National Laboratory
Los Alamos, New Mexico 87545

Reproduction of this report is unlimited.

SESAME EQUATION OF STATE NUMBER 7411, Al_2O_3

J. F. Barnes
and
S. P. Lyon

ABSTRACT

A new global equation of state for Al_2O_3 ("alumina") has been constructed and placed on the SESAME Library as material number 7411.

The compound Al_2O_3 , "alumina", occurs abundantly in nature as the mineral corundum. A SESAME equation of state (EOS), material number 7410, was created for alumina in 1972. However, some of the physics models used in producing global EOSs for the data library have changed considerably since that time; in particular, J. D. Johnson's improved treatment¹ (CHART JD Model) of the ion thermal (nuclear) contribution to pressure and energy has been incorporated into the GRIZZLY² code and is used as the preferred model. Because of the importance of corundum to mixture EOSs for various soils, we considered it advisable to produce a revised global EOS for the material, and it has been placed on the library as EOS number 7411. Although it turned out that there is no apparent large difference between 7410 and 7411, we do recommend usage of the newer EOS.

Alumina exhibits a very high shear strength which has a considerable effect on the experimentally obtained shock Hugoniot. The data are

thoroughly discussed by Graham and Brooks³. The shear offset must be corrected for in constructing an equilibrium equation of state; here we accomplish this by simply representing the U_s-U_p shock data as given in Marsh⁴ by a single straight line through the high pressure data with an intercept at the experimentally obtained bulk sound speed. We used the fit $U_s = 7.93 + 1.298 U_p$ km/s. Shock data were matched to the Thomas-Fermi Dirac calculations at a compression of 1.35.

We used the GRIZZLY code and treated the compound as an average atom with atomic number $\bar{Z} = 10.0$ and atomic weight $\bar{A} = 20.392$. Density at room temperature was taken as 3.97 g/cm^3 . GRIZZLY constructed the cold curve using the default formulation of the Grüneisen parameter

$$\gamma(\eta) = \gamma_0 \left(\frac{1}{\eta}\right) + \frac{2}{3} \left[1 - \left(\frac{1}{\eta}\right)\right]^2$$

with $\gamma_0 = 1.595$, which is both the thermodynamic value and the 2S+1 value from the shock data. The Debye, or characteristic, temperature was calculated to be 1034 K from longitudinal and transverse sound speeds.

The cohesive energy, or energy required to separate Al_2O_3 into 5 separate atoms at 0 K, was calculated as 725 kcal/mole, or 145 kcal/mole for the average atom. The form of the cold curve in expansion was then adjusted with the Lennard-Jones (L-J) parameter in an attempt to produce a critical temperature close to our very rough estimate of 1 eV, a figure based on the known boiling point of Al_2O_3 . It proved not to be possible to lower the calculated T_c beneath about 14,600 K without severely disturbing the calculated isotherms. The corresponding value of the L-J parameter is 0.5.

The following graphs were made for EOS 7411 using the SES2D graphics code. Figures 1 and 2 are the pressure and energy isotherms plotted over the entire temperature range of the tables. Figure 3 shows shock speed versus particle speed along the principal Hugoniot, as used in the model.

REFERENCES

1. J. D. Johnson, private communication.
2. J. Abdallah, Jr., "User's Manual for GRIZZLY," Los Alamos National Laboratory report LA-10244-M (September, 1984).
3. R. A. Graham and W. P. Brooks, J. Phys. Chem. Solids 32, 2311 (1971).
4. S. P. Marsh, editor, LASL Shock Hugoniot Data, U.C. Press (1980).

7411-IST
 TEMP (K)
 A-0.00+00
 B-2.98+02
 C-1.16+03
 D-5.80+03
 E-1.16+04
 F-2.32+04
 G-3.48+04
 H-5.80+04
 I-1.16+05
 J-2.32+05
 K-3.48+05
 L-5.80+05

M-1.16+06
 N-2.90+06
 O-6.96+06
 P-1.74+07
 Q-6.96+07
 R-2.32+08
 S-1.16+09

changes ?

THURSDAY 14 MAY 87

T4 CRAY SES2D 1R

Figure 1. Selected pressure isotherms for EOS 7411

THURSDAY 14 MAY 87

changes ?

7411-15T
T4 CRAY SE52D 1R
A-0.00+00
B-2.98+02
C-1.16+03
D-5.80+03
E-1.16+04
F-2.32+04
G-3.48+04
H-5.80+04
I-1.16+05
J-2.32+05
K-3.48+05
L-5.80+05

M-1.16+06
N-2.98+06
O-5.96+06
P-1.74+07
Q-6.96+07
R-2.32+08
S-1.16+09

T4 CRAY SE52D 1R

Figure 2. Selected energy isotherms for EOS 7411

7411-HU1
E0 MJ/KG
0.00+00

changes ?

THURSDAY 14 MAY 87

T4 CRAY SES2D 1R

Figure 3. Shock velocity versus particle velocity along the principal Hugoniot for EOS 7411