DOE/MC/24164--3012

DE91 002092

**Characterization and Development of
a New Ceramic Electrolyte for
Fuel Cell Applications**

DEC 24 1991

Final Report

June 1991

Work Performed Under Contract No.: DE-AC21-87MC24164

For
U.S. Department of Energy
Office of Fossil Energy
Morgantown Energy Technology Center
Morgantown, West Virginia

By
Solid-State Fuel Cells, Inc.
Columbia, Maryland

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise, does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

This report has been reproduced directly from the best available copy.

Available to DOE and DOE contractors from the Office of Scientific and Technical Information, P.O. Box 62, Oak Ridge, TN 37831; prices available from (615)576-8401, FTS 626-8401.

Available to the public from the National Technical Information Service, U.S. Department of Commerce, 5285 Port Royal Rd., Springfield, VA 22161.

**Characterization and Development of
a New Ceramic Electrolyte for
Fuel Cell Applications**

Final Report

Work Performed Under Contract No.: DE-AC21-87MC24164

**For
U.S. Department of Energy
Office of Fossil Energy
Morgantown Energy Technology Center
P.O. Box 880
Morgantown, West Virginia 26507-0880**

**By
Solid-State Fuel Cells, Inc.
P.O. Box 40
Columbia, Maryland 21045**

June 1991

MASTER

EXECUTIVE SUMMARY

This report provides an account of work performed by Solid-State Fuel Cells, Inc. under DOE/METC Contract No. DE-AC21-87MC24164 and EPRI Contract No. RP270-4. The work consisted of research directed toward characterization and development of new solid electrolyte materials that are potentially superior to other solid electrolyte materials currently under development (such as zirconia-based materials). The program is devoted to development of new ceramic electrolytes for fuel cell applications. The work described herein comprises the first part of an overall (three phase) program contemplated for the pursuit of fuel cell applications using these materials.

The initial effort under this study dealt with the preparation and sintering of suitable samples from selected binary and ternary metal oxide systems. These samples were subsequently utilized in ionic conductivity and thermogravimetric testing. Also, disk-type samples were later employed in electrode deposition studies and in cell coupon preparation and characterization testing.

The ionic conductivity results served to support the earlier observation of very attractive ionic conductivity properties for some of these systems, even at relatively low temperatures. Ionic conductivities were determined as a function of temperature for 16 sample types. One of the binary systems was identified as being particularly attractive over a certain range of compositions. A cross-doped (ternary) system also showed very encouraging results, but subsequent attention was focused on the binary system because of indications of more favorable stability characteristics.

The coefficient of thermal expansion was also determined for a selected binary composition. The thermal expansion characteristics of this material were found to be reasonably compatible with those of various suitable sealing and structural materials between room temperature and 850°C (which is expected to be the approximate upper limit for fuel cell operation, thereby taking advantage of the attractive "low-temperature" ionic conductivity of these materials along with the greater voltage driving forces and superior start-up characteristics associated with lower temperatures).

Thermogravimetric studies were carried out in an oven under a hydrogen atmosphere; humidification levels ranged from zero to about 27 percent H₂O. Significant weight losses were observed throughout this range, with the binary system cited in the ionic conductivity studies faring best among all the materials tested. Analysis has shown that the tendency of these materials toward reductive weight loss (as relevant to a fuel cell anode environment) can be counteracted in an operating fuel cell. The counterbalancing factor could be either a high H₂O/H₂ ratio (obtained perhaps by employing anode gas recycle) or the fuel cell current density itself. Oxygen ion migration from cathode to anode in an operating fuel cell will tend to counteract the reductive loss of oxygen atoms from the metal oxide lattice. Based on the thermogravimetric results for a selected composition from the preferred binary system, it is estimated that the minimum current density required to prevent

reductive loss of oxygen atoms at the anode would be only 4-55 mA/cm² over the temperature range 600-850°C. (This is small relative to current densities anticipated in fuel cells utilizing these new electrolyte materials.)

Electrode technology developed for these electrolyte materials has focused on deposition of electrode layers onto the faces of electrolyte disks. The preferred electrode source at present is a suspension of finely ground platinum metal in an organic medium. The development work has led to the attainment of electrode layers having mechanical and chemical stability at operating temperature, good adhesion, and substantial current-carrying capability (1-2 A/cm²) with no degradation over tens of hours. Much progress has been made in narrowing the experimental variables, but further optimization is required, especially with regard to platinum loading and porosity. The electrolyte sample preparation methodology successfully produced attractive ionic conductivity results. Rate-controlled sintering studies have shown that ionic conductivity and other properties (primarily mechanical) can be upgraded through optimization of preparation and sintering methodologies.

Coupon-type cell structures and associated test fixtures were designed based in part on the work of other researchers in solid electrolytes. Cell testing was accomplished in spite of difficulties with the cell fixture and very respectable power densities were obtained at relatively low temperatures.

TABLE OF CONTENTS

	<u>Page</u>
1.0 INTRODUCTION	1-1
2.0 BACKGROUND	2-1
2.1 PROGRAM ORIGIN	2-1
2.2 TECHNICAL DISCUSSION	2-2
2.2.1 Materials and Electrode Characterization	2-3
2.2.2 Cell and Stack Technology	2-5
2.2.3 System Design, Analysis and Engineering	2-6
3.0 TASK WORK DESCRIPTION	3-1
3.1 TASK I-1: ELECTROLYTE MATERIALS DEVELOPMENT	3-1
3.1.1 Sample Preparation Methods	3-1
3.1.2 Ionic Conductivity Studies	3-2
3.1.3 Thermal Expansion Characteristics	3-7
3.2 TASK I.2: TESTING OF ELECTROLYTE STABILITY UNDER A REDUCING ENVIRONMENT	3-7
3.2.1 Thermodynamic Equilibrium Considerations	3-10
3.2.2 Thermogravimetric Testing	3-18
3.2.3 Analysis of Electrolyte Stability Under Fuel Cell Operating Conditions	3-22
3.3 TASK I.3: DEVELOPMENT OF CELL ELECTRODES	3-26
3.4 TASK I.4: TEST FIXTURES DESIGN AND FACILITY ERECTION	3-28
3.4.1 Preliminary Design Concepts	3-28
3.4.2 Alternative Design Concepts	3-30
3.4.3 Facility Erection	3-37
3.5 TASK I.5: PRELIMINARY COUPON CELL TESTS	3-37
3.5.1 Tape Casting	3-37
3.5.2 Coupon Fabrication	3-38
3.5.3 Cell Assembly	3-42
4.0 CONCLUSIONS	4-1

TABLE OF CONTENTS
(CONT'D)

	<u>Page</u>
APPENDIX A	A-1
APPENDIX B	B-1
APPENDIX C	C-1
APPENDIX D	D-1
APPENDIX E	E-1

The Appendices of this report contain information that is proprietary to Solid-State Fuel Cells, Inc.; therefore, the Appendices are not included in this report.

LIST OF FIGURES

	<u>Page</u>
FIGURE 1 IONIC CONDUCTIVITY MEASUREMENTS OS-3 TYPE SYSTEMS	3-5
FIGURE 2 IONIC CONDUCTIVITY MEASUREMENTS OS-2/OS-3 TYPE SYSTEMS	3-5
FIGURE 3 	3-8
FIGURE 4 RESULTS OF EQUIVALENT REDUCTIVE CURRENT DENSITY ESTIMATES FOR OS-3 (3-F)	3-24
FIGURE 5 FUEL CELL COUPON	3-29
FIGURE 6 CELL ASSEMBLY	3-31
FIGURE 7 REINFORCED CELL COUPON STRUCTURE	3-32
FIGURE 8 SOLID-STATE FUEL CELL DESIGN	3-34
FIGURE 9 DOUBLE POROSITY CELL OF GORIN AND RECHT	3-35
FIGURE 10 SOLID ELECTROLYTE CELL	3-36
FIGURE 11 SCANNING ELECTRON MICROGRAPH OF THE SURFACE OF AN UNFIRED TAPE	3-39
FIGURE 12 UNFIRED ELECTRODED TAPE	3-40
FIGURE 13 CROSS-SECTIONAL VIEW OF THE LAMINATING DIE: A) 1-IN. DIA., B) SILICONE-COATED POLYESTER, C) ELECTRODED GREEN TAPE, D) 2 RINGS, E) 5/8-IN. DIA., F) HOLLOW CYLINDER, 1-IN. DIA.	3-41
FIGURE 14 SCANNING ELECTRON MICROGRAPH OF THE PLATINUM ELECTRODE SURFACE	3-43
FIGURE 15 SCANNING ELECTRON MICROGRAPH OF THE TOP SURFACE OF THE SOLID ELECTROLYTE	3-44
FIGURE 16 SCANNING ELECTRON MICROGRAPH OF THE SOLID ELECTROLYTE FRACTURE SURFACE	3-45
FIGURE 17 COUPON ARRANGEMENT IN CELL HOLDER	3-48
FIGURE 18 GAS MANIFOLD SYSTEM	3-50

LIST OF FIGURES **(CONT'D)**

	<u>Page</u>
FIGURE 19 ELECTRONIC DATA COLLECTION SYSTEM	3-51
FIGURE 20 POWER DENSITY AS A FUNCTION OF CURRENT DENSITY FOR VARIOUS TEMPERATURES	3-53
FIGURE 21 POWER DENSITY AS A FUNCTION OF CURRENT DENSITY FOR VARIOUS TEMPERATURES (Detail At Origin)	3-55
FIGURE 22 VOLTAGE AS A FUNCTION OF CURRENT DENSITY FOR VARIOUS TEMPERATURES	3-56
FIGURE 23 POWER DENSITY VS. TIME	3-58
FIGURE 24 VOLTAGE VS. TIME	3-59
FIGURE A-1 ILLUSTRATION OF THE SOLID-STATE FUEL CELLS, INC. PROPRIETARY CELL DESIGN CONCEPT	A-2
FIGURE A-2 GROOVE PATTERNS	A-5
FIGURE A-3A MICROSCOPIC SURFACE - FINE CRYSTALLINE STRUCTURE FORMATION	A-8
FIGURE A-3B GROOVE PATTERNS	A-8
FIGURE B-1 SCHEMATIC OF POWER PLANT FOR ELECTRIC UTILITY APPLICATION	B-3
FIGURE C-1 LOG CONDUCTIVITY VS COMPOSITION $Nb_2O_5-Bi_2O_3$	C-2
FIGURE C-2 THERMAL EXPANSION CHARACTERISTICS OF VARIOUS MATERIALS	C-4
FIGURE C-3 POWDERS USED IN THE SINTERING STUDY (A: 9%, B: 15%, C: 21% Nb_2O_5)	C-6
FIGURE C-4 TYPICAL SINTERING SCHEDULE FOR BNO PELLET	C-8
FIGURE C-5 POLISHED AND ETCHED, BNO DISK (OPTICAL MICROGRAPH 400X, SAMPLE SINTERED AT 925°C FOR 10 HOURS)	C-13
FIGURE C-6 ETCHED AND UNETCHED FRACTURE SURFACES OF BNO DISK SINTERED AT 925°C FOR 2 HOURS (A: ETCHED SURFACE, B: UNETCHED SURFACE)	C-15

LIST OF FIGURES

(CONT'D)

	<u>Page</u>
FIGURE C-7 DENSIFICATION OF BNO AS A FUNCTION OF SOAK TIME AT VARIOUS TEMPERATURES	C-17
FIGURE C-8 DENSIFICATION OF BNO AS A FUNCTION OF TEMPERATURE AT FIXED SOAK TIMES	C-18
FIGURE C-9 BNO SAMPLE SINTERED AT 925°C FOR 10 HOURS (THIS WAS THE HIGHEST DENSITY ACHIEVED)	C-20
FIGURE C-10 MICROSTRUCTURE DEVELOPMENT DURING SINTERING OF BNO (SINTERING TIME: 1 HOUR. SINTERING TEMPERATURES: A-UNSINTERED; B-700; C-800; D-850; E-900; AND F-925°C)	C-21
FIGURE C-11 SINTER NECK DEVELOPMENT IN BNO SINTERED AT 700°C FOR 10 HOURS	C-23
FIGURE C-12 DIFFERENTIAL THERMAL ANALYSIS (HEATING ONLY) ON PRE-SINTERED BNO POWDER CONTAINING 0.4 WT% PVA BINDER	C-30
FIGURE C-13 FRACTIONAL DENSITY AND DENSIFICATION RATE VERSUS TEMPERATURE FOR SAMPLE BNO.1 SHOWING INCIPIENT MELTING	C-37
FIGURE C-14 FRACTIONAL DENSITY VERSUS ELAPSED TIME FOR THE THE HEATING RATES USED IN THE RATE-CONTROLLED SINTERING DATABASE	C-39
FIGURE C-15 COMPOSITE CURVE SHOWING THE RESPONSE OF FRACTIONAL DENSITY TO SINTERING TEMPERATURE	C-40
FIGURE C-16 DATABASE SHOWING THE VARIATION OF DENSIFICATION RATE WITH FRACTIONAL DENSITY	C-42
FIGURE C-17 DENSIFICATION RATE (EXPANDED SCALE) VERSUS FRACTIONAL DENSITY FOR SAMPLE BNO.3	C-43
FIGURE C-18 DENSIFICATION RATE VERSUS SINTERING TEMPERATURE FOR SAMPLE BNO.3	C-44
FIGURE C-19 DENSIFICATION RATE VERSUS SINTERING TEMPERATURE FOR SAMPLE BNO. 2	C-45

LIST OF FIGURES

(CONT'D)

		<u>Page</u>
FIGURE C-20	SAMPLE BNO.1 HEATED AT 5°C/MIN TO 1000°C. (PARTIAL MELTING OCCURRED. PORES: PREDOMINANTLY TYPE 1 AND 2; MINOR AMOUNT OF TYPE 4; NO TYPE 3. SEM: 600X; FRACTURE SURFACE.)	C-49
FIGURE C-21	SAMPLE BNO.4 HEATED AT 10°C/MIN TO 935°C. (NO MELTING. PORES: PREDOMINANTLY TYPE 3; NO TYPE 1 AND 2. SEM: 600X; FRACTURE SURFACE.)	C-50
FIGURE C-22	SAMPLE BNO.2 HEATED AT 2.5°C/MIN TO 935°C. (NO MELTING. PORES: PREDOMINANTLY TYPE 3 AND 4; NO TYPE 1 OR 2. SEM: 600X; FRACTURE SURFACE.)	C-52
FIGURE C-23	SAMPLE BNO.3 HEATED AT 1.25°C/MIN TO 935°C. (NO MELTING. PORES: PREDOMINANTLY TYPE 3, BUT LESS ANGULAR; NO TYPE 1 AND 2. SEM: 600X; FRACTURE SURFACE.)	C-53
FIGURE C-24	SAMPLE BNO.4 HEATED AT 10°C/MIN TO 935°C. (NO MELTING. PORES: PREDOMINANTLY TYPE 5. SEM: 3000X; POLISHED AND ETCHED SURFACE.)	C-55
FIGURE C-25	GRID USED FOR ESTIMATING POROSITY BY POINT-COUNTING	C-57
FIGURE C-26	SAMPLE BNO.4 HEATED AT 10°C/MIN TO 935°C. (SAMPLE POLISHED AND ETCHED TO REVEAL GRAIN SHAPE AND SIZE. NOTE 50μm MARKER. SEM: 600X POLISHED AND ETCHED SURFACE.)	C-59
FIGURE C-27	SAMPLE BNO.1 HEATED AT 5°C/MIN TO 1000°C. (PARTIAL MELTING OCCURRED. SAMPLE POLISHED AND ETCHED TO REVEAL GRAIN SHAPE AND SIZE. NOTE 50μm MARKER. SEM: 600X; POLISHED AND ETCHED SURFACE.)	C-60
FIGURE C-28	SAMPLE BNO.2 HEATED AT 25°C/MIN TO 935°C. (SAMPLE POLISHED AND ETCHED TO REVEAL GRAIN SHAPE AND SIZE. NOTE 50μm MARKER. SEM: 600X; POLISHED AND ETCHED SURFACE.)	C-61
FIGURE C-29	SAMPLE BNO.3 HEATED AT 1.25°C/MIN TO 935°C. (SAMPLE POLISHED AND ETCHED TO REVEAL GRAIN SHAPE AND SIZE. NOTE 50μm MARKER. SEM: 600X; POLISHED AND ETCHED SURFACE.)	C-62

LIST OF FIGURES
(CONT'D)

	<u>Page</u>
FIGURE D-1 WEIGHT LOSS IN H_2/H_2O	D-2
FIGURE D-2 ANALYSIS OF BINARY COMPOSITION	D-4
FIGURE E-1 	E-6
FIGURE E-2 RESISTANCE CHARACTERISTICS OF PLATINUM INKS AND RESINATES	E-9
FIGURE E-3 EFFECT OF CURRENT DENSITY ON CONDUCTIVITY OF ELECTRODED OS-3 DISK	E-11

LIST OF TABLES

	<u>Page</u>
TABLE I IONIC CONDUCTIVITY PARAMETERS	3-4
TABLE II COMPARATIVE IONIC CONDUCTIVITIES AT 500°C.	3-9
TABLE II FREE ENERGIES OF FORMATION	3-11
TABLE IV EQUILIBRIUM CONSTANTS AS FUNCTION OF TEMPERATURE	3-12
TABLE V CASE 1	3-14
TABLE VI CASE 2	3-15
TABLE C-I DENSITY, PERCENT THEORETICAL DENSITY, AND LINEAR SHRINKAGE OF 15 PERCENT Nb ₂ O ₅ PELLETS	C-12
TABLE C-II AVERAGE GRAIN SIZE OF SINTERED 15 PERCENT Nb ₂ O ₅ PELLETS	C-16
TABLE C-III COMPARISON OF DIFFERENT POWDERS SINTERED AT 900°C FOR TWO HOURS	C-25
TABLE C-IV GEOMETRICAL AND FRACTIONAL DENSITY OF GREEN PELLETS OF Bi ₂ O ₃ - 15 Mol% Nb ₂ O ₅ CONTAINING 0.4 WT% PVA BINDER	C-33
TABLE C-V DILATOMETER HEATING RATES USED FOR DATABASE GENERATION	C-34
TABLE C-VI MEASUREMENTS ON SINTERED PELLETS OF Bi ₂ O ₃ - 15 Mol% Nb ₂ O ₅	C-35
TABLE C-VII ESTIMATED POROSITY OF SINTERED SAMPLES BY POINT COUNTING COMPARED WITH THE FRACTIONAL DENSITY BY ARCHIMEDES TECHNIQUE	C-58
TABLE D-1 FITTING PARAMETERS TO THE 1st ORDER RATE EQUATION (EQ. [D-1]) DESCRIBING WEIGHT LOSS IN A HYDROGEN ATMOSPHERE - Bi ₂ O ₃ :Nb ₂ O ₅	D-3
TABLE D-2 FITTING PARAMETERS TO THE 1st ORDER RATE EQUATION (EQ. [D-1]) DESCRIBING WEIGHT LOSS IN A HYDROGEN ATMOSPHERE - Bi ₂ O ₃ :Nb ₂ O ₅ :Y ₂ O ₃	D-6

SECTION 1.0

INTRODUCTION

This report provides an account of work performed by Solid-State Fuel Cells, Inc., under DOE/METC Contract No. DE-AC21-87MC24164 and EPRI Contract No. RP2706-4. This work consisted of research directed toward characterization and development of new solid electrolyte materials that are potentially superior to other solid electrolyte materials currently under development (such as yttria-stabilized zirconia). The solid electrolyte technology described herein is based on new ceramic materials generally described as Bismuth Oxide doped with Niobium or Yttrium oxides that were exclusively* licensed to Solid-State Fuel Cells, Inc. by CeramPhysics, Inc. The technology is also based on further material, cell, and stack technology concepts and manufacturing methods that were earlier reduced to practice by Solid-State Fuel Cells, Inc., and which are therefore proprietary to the Company.

The scope of applications of the subject electrolyte technology includes three energy-related end-uses. The first end-use is in solid-electrolyte fuel cell applications, the second end-use is in oxygen sensing, and the third end-use is in oxygen enrichment and/or production.

In the fuel cell end-use application, the oxygen-ion conducting electrolyte is provided with two porous electrodes and is employed to provide direct current electricity by reacting gaseous fuels and oxygen (air) electrochemically. In oxygen sensing, a similar electrolyte/electrodes arrangement is employed to detect a difference in partial pressure of oxygen in gaseous streams that are introduced to each electrode. This can be employed to detect excess air operation in combustion and heat-engine systems as a means of optimizing system performance and efficiency.

*Letters Patent No. 4,462,891, July 31, 1984
U.S. Patent App. No. 628,381, filed July 12, 1984 (Docket LAE 010P2)

When the electrolyte is employed for oxygen production, D.C. current is supplied to the electrolyte which is maintained at elevated temperatures to induce oxygen-ion migration through the electrolyte, thus providing an electrically driven oxygen pump that can, for example, separate oxygen from air. The separated oxygen can be employed in a wide spectrum of energy-related applications such as oxygen-blown gasification, oxygen-enriched combustion, and oxygen-blown autothermal steam reforming of hydrocarbon fuels for the production of hydrogen.

The primary advantage provided by the new solid-electrolyte technology is the high ionic conductivity (up to 50 times that of yttria-stabilized zirconia) of the materials. This, along with other characteristics of the proposed materials (such as high thermal shock resistance and lower temperature of operation) is expected to result in significant technical and economic benefits in all three end-use applications.

The program is devoted to the characterization and further development of Bismuth-Niobium (OS-3), Bismuth-Yttrium (OS-2), Bismuth-Erbium (OS-4), and finally, the Bismuth-Yttrium-Niobium ternary system for fuel cell applications. In particular, the initial focus of the research has been to investigate the thermodynamic stability of these materials regarding resistance to reduction when exposed to reducing atmospheres typical of the fuel cell operating environment. This application is considered to be the most demanding on the material stability when compared to both the oxygen sensor and the oxygen pump applications.

The work described herein is the first part of an overall program that is contemplated for the pursuit of fuel cell applications for these electrolytes. The overall program is structured in three phases of research and development, and the subject of this report is work comprising the first part of Phase I (Phase I-A). The primary thrust of each phase of the program is as follows:

- Phase I: Materials Research, Conceptual Design and System Engineering Evaluation.

- Phase II: Cell and Stack Technology Development and Testing and Preliminary Plant Design.
- Phase III: Plant Design, Stack Technology and Pilot System Verification (75 kW).

In this report a presentation of the overall program background is provided in Section 2.0. This includes a technical discussion of the technology in the context of the current state of the art. The task work description for the applicable portion of Phase I (Phase I-A, Tasks I.1 through I.5) is presented in Section 3.0. Specifically, Phase I-A comprises the following elements:

- Electrolyte Materials Development - Task I.1,
- Testing of Electrolyte Stability Under a Reducing Environment - Task I.2,
- Development of Cell Electrodes - Task I.3,
- Test Fixtures Design and Facility Erection - Task I.4, and
- Preliminary Coupon Cell Tests - Task I.5.

Task I.1, I.3, and I.4 have been performed under DOE/METC sponsorship, while Tasks I.2 and I.5 have been performed under EPRI sponsorship.

SECTION 2.0

BACKGROUND

2.1 PROGRAM ORIGIN

The solid-electrolyte technology investigated herein is based on a set of ceramic, oxygen-ion conducting electrolytes that were initially developed by CeramPhysics for oxygen-sensor applications. A modest project was sponsored by the DOE/Energy Related Inventions Program (Contract No. DE-FG01-82CE-15089) to investigate the feasibility of these materials in oxygen-sensor applications. Upon later review of the disclosure materials and the oxygen sensor program results, it became evident that the materials may have a significant potential for fuel cell applications. It was recognized, however, that more material research and novel cell and stack technology development, including manufacturing methods, would be required to realize the potential of such materials. This resulted in the formulation of a number of novel technical concepts and an agreement as follows:

- Cross doping of the basic materials may be desirable to enhance the material stability for fuel cell applications and should be investigated.
- Novel concepts for cell and stack design, including methods of manufacturing, were formulated. These fuel cell and stack technology concepts are aimed at taking the maximum possible advantage of the superior ionic conductivity of the materials in the fuel cell applications of the materials.
- New system configuration concepts that are aimed at improved system efficiency and power density.
- A cooperative venture was formed through a jointly owned corporation for the dedicated pursuit of commercial fuel cell applications of the ceramic electrolytes and improvements thereof.

2.2 TECHNICAL DISCUSSION

The proposed electrolyte materials (named by CP: OS-2, OS-3, and OS-4) possess a number of attractive properties. The most significant property is the high ionic conductivity of the materials and the range of temperatures in which these materials become conducting to oxygen ions. The significance of this is the ability to operate the electrolyte at low temperatures in relation to those required by state-of-the-art solid electrolyte materials (yttria-stabilized zirconia), while matching or exceeding the performance of these materials. This also has implications for materials employed for electrodes, cell life, and overall system performance. Tests that were conducted in-house on the electrolytes' ionic conductivity, which were later confirmed by independent tests at Argonne National Laboratory on one of the materials (OS-3), verified that the materials (at a given temperature) possess 30 to 50 times the ionic conductivity of yttria-stabilized zirconia. This allows superior trade-offs between current density and operating cell voltage. Operation at higher voltage could be employed to improve the stack conversion efficiency; however, the resultant reduction in current density may be undesirable due to the corresponding reduction in output power density, the latter being of significance to plant size, weight and capital cost per kW of output capacity. Clearly, the higher the power density, the smaller the plant size for a given output capacity, and, in general, the lighter the stack weight, the lower the capital cost per kW of capacity.

The free energies and hence the associated Nernst-Einstein potentials of the overall reactions are enhanced at lower temperatures. This is expected to improve the ideal efficiency. Through the appropriate cell/stack design, the actual cell voltage and, hence, efficiency could be maintained high by reducing losses. However, with the reduced temperatures the desired cathode activity might require the use of a thin-layer electrode with catalytic capability.

The second most significant property of the new electrolyte materials relates to manufacturability. The proposed electrolyte materials have low sintering temperatures (approximately 1000°C). In addition, these materials have excellent sintering characteristics which yield dense structures when

employing standard ceramic manufacturing techniques. The combined effect of superior low-temperature conductivity and manufacturability of the proposed electrolytes provides an opportunity for new cell and stack design concepts with significant stack and system performance implications.

The proposed materials also have high thermal shock resistance. Thermal cycling tests at the CeramPhysics laboratory have shown this to be greater than that for yttria-stabilized zirconia. This is primarily due to their higher thermal conductivity in relationship to their thermal coefficient of expansion. A lower stack operating temperature, coupled with higher thermal shock resistance, could be employed in the design of stacks with improved start-up rate and load following capability. As discussed in Section 3.0, the thermal coefficient of expansion of these materials is similar to that of several materials that could be employed to seal the stack at the expected range of operating temperatures.

The technology development needs associated with the new alternative solid-oxide fuel cell technology are as follows:

2.2.1 MATERIALS AND ELECTRODE CHARACTERIZATION

Tests conducted at Argonne National Laboratory on the OS-3 material confirmed the high ionic conductivity; however, tests conducted on the material in a highly reducing environment (on both sides of the electrolyte) indicated that the material was not suitable under the test operating conditions (oxygen partial pressures lower than 10^{-22} atm. and temperatures above 600°C). Under these conditions the material appeared to have been reduced to the parent metal.

Additional tests were also conducted on the OS-3 material at 600°C by CP with an air and a hydrogen electrode. These tests indicated that after exposure of the cell to the reducing fuel environment the open-circuit cell voltage became low. This suggested an increase in the electronic conductivity of the electrolyte which in turn suggested that the electrolyte may have been reduced. However, it should be noted that these tests were carried out with

very low current flow because of the inferior electrodes and thick electrolyte layers employed.

The tests conducted at Argonne and at CP are believed to have exposed the electrolyte to operating conditions that are more stringent than what would be occurring in an actual fuel cell stack using OS-3 materials as an electrolyte. In the Argonne test, the highly reducing atmosphere was introduced to both sides of the electrolyte. No oxygen ions were migrating through the electrolyte from an air-side electrode to the fuel-side electrode. Therefore, the effective partial pressure of oxygen at the anode/electrolyte interface was significantly lower than what would be expected under normal fuel cell operating conditions at an anode.

In the case of tests conducted at CP, an air electrode was employed; however, the electrolyte was very thick (on the order of 0.100 inches) and the ink electrodes (electrodes formed by the deposition of a metal from an ink-type dispersion) were very thin. The combined high resistance in the electrolyte and the very high in-plane IR-losses in the electrodes reduced the current density in the cell to extremely low levels (on the order of 2.5 mA/cm^2). Thus, the rate of oxygen ion migration through the electrolyte was insignificant, and hence the rate of emergence of oxygen at the anode side of the electrolyte was also very low. Therefore, conditions which existed at the anode side of the electrolyte in the CP test were similar to those found on both sides in the Argonne tests. If the ionic flow of oxygen had been at a typical operating current density, the oxygen ions migrating to the anode side of the electrolyte would have formed water at a higher rate and would have increased the effective oxygen partial pressure to more realistic levels in the electrolyte. It should be noted that typical anode streams would contain about 11 percent H_2O by volume to simulate reformat gas derived from 1.5 moles of H_2O per mole of CH_4 . This alone would yield an effective oxygen partial pressure on the order of 10^{-8} to 10^{-10} atm at the anode side of the electrolyte. This, of course, does not even take into account the additional H_2O that is formed as the H_2 in the reformat gas reacts at the anode.

The work described in Section 3.0 serves to put in perspective many of the questions left unanswered after the prior studies. That is, the issue of thermogravimetric stability has been examined as a function of operating temperature, cell current density, and anode stream composition. Experimental studies have been carried out for various compositions of the promising new materials. In addition, cross-doped combinations of these materials have also been examined.

Another important aspect of this element of the program is the investigation of the electrode materials and methods of application to the electrolyte. This part of the research and development effort is directly related to the following program element, which deals with cell and stack design and the methods of manufacturing. The electrode material and methods of application are strongly affected by the design concepts for the cell and, to a lesser extent, stack requirements. In the subject technology the cell electrodes will not be required to carry the current for long distances (relatively speaking); therefore, the initial focus of the electrode research and development has been on thin electrodes that are sufficiently porous and that can harvest the high ionic conductivity of the electrolyte with minimum electronic and diffusion-related losses. Thermal expansion compatibility is also a major requirement for such electrodes within the context of the intended cell and stack design and the expected stack operating temperatures.

2.2.2 CELL AND STACK TECHNOLOGY

New and novel cell and stack design concepts were investigated in order that the full potential of the electrolyte materials evaluated in this program be realized. One of the most important considerations is the fact that cell design improvements are needed in order to reduce IR-losses and thereby take advantage of the high ionic conductivity of these new electrolytes. Another consideration stems from the fact that these electrolytes could be employed at lower temperatures; and selections of electrode, interconnection, and sealing materials were made accordingly. As a result of such considerations, novel cell design and manufacturing methods (suited for the superior characteristics of the new electrolyte materials) have been examined as part of this program. These include "planar" configurations with internal manifolding for the

reactants. The details are discussed along with the corresponding manufacturing methodology concepts in Appendix A.

2.2.3 SYSTEM DESIGN, ANALYSIS AND ENGINEERING

It is essential that the materials research as well as the cell/stack technology development activities be driven by the configuration and performance requirements of the complete power plant system. While a detailed power plant system design is neither warranted nor urgent within Phase I-A, it is prudent to define the target power plant system to the level necessary to mission-orient the research and development program. In addition, the significance of the research results can be assessed through consideration of their impact on the overall system, thereby allowing ongoing optimization of the system in light of what is achievable in the laboratory.

The target power plant system is projected to have the following characteristics:

- Capacity: 10 - 50 MWe
- Fuel Capability: Natural Gas, Naphtha, Coal Slurry, Heavy Oils (#2 and #4)
- Heat Rate: 8,300 - 6,800 Btu/kWh (fuel dependent)
- Fuel Processor: Two-stage
- Fuel Cell Stack: 600 - 800°C

A discussion of system design concepts is presented in Appendix B.

SECTION 3.0

TASK WORK DESCRIPTION

This section provides an accounting of the work performed in the Phase I-A program, comprising Tasks I.1 through I.5. The descriptive information is broken down by task.

3.1 TASK I.1: ELECTROLYTE MATERIALS DEVELOPMENT

The ceramic materials that are the subject of this research program are designated OS-2, OS-3, and OS-4. These materials are clearly distinguishable from each other on the basis of chemical constitution. This program has not been restricted to these three materials, however. Other materials have been prepared which can be considered modifications of the original materials; in all cases these modifications are compositional in nature, but the basic chemical constituencies remain the same. In addition, materials have been prepared which are cross-dopings among the basic OS-2, OS-3, and OS-4 types.

The early work of this program concentrated on testing that served to narrow the field of candidate materials. As a result of this work (see Section 3.2.2.1, below), all systems containing the OS-4 type materials were eliminated from further consideration; this was based on the following reasons: (i) the thermodynamic stability of these materials in reducing atmospheres was found to be relatively poor compared to that of systems containing the OS-2 and OS-3 type materials, and (ii) the OS-4 type material is substantially more expensive than the OS-2 and OS-3 type materials.

3.1.1 SAMPLE PREPARATION METHODS

Chemically pure starting powders of the various constituents were combined in the appropriate ratios and mixed by ball-milling with alcohol. Following drying and calcining steps the powders were cold-pressed into disks suitable for ionic conductivity measurements and sintered on predetermined schedules. All samples were x-rayed to verify proper phase formation. These ceramics appear to sinter via a liquid-phase-sintering mechanism, and they

have a very dense appearance. However, an optimized sintering schedule has not yet been determined. The methodology is described in detail in Section III of Appendix C.

The encouraging ionic conductivity results obtained with these materials along with the associated uncertainty regarding the effectiveness of the sintering cycles employed point toward a need for more comprehensive fabrication process development activities. Specifically, automated sintering-rate studies are needed to allow maximized density of the sintered material as well as optimized microstructure. This is expected to have positive effects on material strength ionic conductivity, and (potentially) thermogravimetric stability. Also, the achievement of optimum properties through rate-controlled sintering should yield a high degree of repeatability in the fabrication of electrolyte materials. Substantial progress has been made in the study of such rate-controlled sintering processes as applied to the subject electrolyte materials; this work is described in Section IV of Appendix C.

3.1.2 IONIC CONDUCTIVITY STUDIES

3.1.2.1 EXPERIMENTAL PROCEDURES AND RESULTS

Samples were formed into disks for ionic conductivity studies by the methodology discussed in Section 3.1, above; the final sample size was 1.27 cm in diameter and 0.1 cm in thickness. Platinum electrodes were applied at both surfaces. Measurements were made in air by the two-lead method.

Ionic conductivity data were successfully obtained over the temperature range 200° - 400°C. Above 400°C, however, it was found that resistance in the leads had a significant effect on the measurements. Consequently, the 200° - 400°C data were curve-fitted to the ionic-conductivity relation

$$\sigma = (\sigma_0/T) \exp (- Q/kT) \quad (1)$$

where σ is the ionic conductivity, σ_0 is the ionic conductivity coefficient, and Q is the activation energy and k is Boltzmann's constant. The

determination of the constants σ_0 and Q in this expression allowed extrapolation of the data to temperatures above 400°C.

A total of 16 samples have been evaluated for ionic conductivity in accord with the methods described above. These samples consisted of eight variations of the OS-3 type and eight that represent combinations of the OS-2 and OS-3 types.

The constants σ_0 and Q in Equation (1) were determined from the data for each of the 16 samples. The results are shown in Table I, where the various OS-3 type samples are designated 3-A through 3-H and the OS-2/OS-3 type samples are designated 2/3-A through 2/3-H. These designations are identified in Section I of Appendix C.

The experimental results for the OS-3 type samples are shown in Figure 1, where $\ln(\sigma T)$ is plotted vs. $1/T$ according to Equation (1). Significantly, the ionic conductivity is maximized for the OS-3 type samples at a composition which deviates from OS-3 per se. (Note that in Figure 1 the curves for 3-A, 3-B, and 3-E are omitted for clarity.)

These results are shown in Figure C-1 (Appendix C) in terms of ionic conductivity versus composition (at 500°C). Previous data from the literature are also shown in Figure C-1 for comparison.

The results for the OS-2/OS-3 type samples are shown in Figure 2; the corresponding data for OS-3 (3-F) are shown as a dashed line in this figure for comparative purposes. It is seen that the 2/3-B and 2/3-G compositions have higher ionic conductivities than OS-3 (although not as high as the 3-C variation).

3.1.2.2 DISCUSSION AND CONCLUSIONS

A large amount of materials formulation and measurement work is comprised in the section presented above. The reported data are specific to the electrolyte fabrication methods and measurement techniques employed. It is

TABLE I:
IONIC CONDUCTIVITY PARAMETERS

<u>SAMPLE DESIGNATION</u>	<u>σ_0 ($K \Omega^{-1} cm^{-1}$)</u>	<u>Q (eV)</u>
3-A	2.85×10^6	1.03
3-B	9.04×10^6	0.977
3-C	3.92×10^7	0.998
3-D	2.66×10^7	1.02
3-E	4.19×10^6	0.929
3-F (OS-3)	9.47×10^6	0.949
3-G	1.42×10^6	0.949
3-H	4.55×10^5	0.969
2/3-A	(did not survive platinization)	
2/3-B	3.58×10^7	1.02
2/3-C	1.76×10^7	1.01
2/3-D	3.72×10^6	0.959
2/3-E	1.07×10^8	1.09
2/3-F	1.46×10^6	0.901
2/3-G	7.12×10^7	1.07
2/3-H	9.50×10^6	0.997

**FIGURE 1: IONIC CONDUCTIVITY MEASUREMENTS
OS-3 TYPE SYSTEMS**

**FIGURE 2: IONIC CONDUCTIVITY MEASUREMENTS
OS-2/OS-3 TYPE SYSTEMS**

expected that improved ceramic fabrication methods and improved measurement techniques (i.e., four-lead ionic conductivity measurements over a broader range of temperatures) might result in enhanced conductivity values, but the ordering of the data among the samples of varying composition will not change. It should be noted that the activation energies for all the compositions in Table I are closely grouped ($Q = 0.994 \pm 0.050$ eV). This result not only clearly indicates ionic conduction (i.e., negligible electronic conduction) but also supports the validity of the methodology.

The central result of this study is that the ionic conductivity of the original OS-3 composition (3-F) is exceeded by the conductivities of three new compositions: (3-C, 2/3-B, and 2/3-G). These results are specifically illustrated in Figure 3 and quantified at 500°C in Table II.

3.1.3 THERMAL EXPANSION CHARACTERISTICS

The thermal expansion characteristics of OS-3 have been studied and compared with those of various structural materials. This work is presented in Section II of Appendix C.

3.2 TASK I.2: TESTING OF ELECTROLYTE STABILITY UNDER A REDUCING ENVIRONMENT

In order to investigate the thermodynamic stability of the electrolyte materials, two sets of tests were provided for in this program. The first is thermogravimetric tests which are the subject of this task. The second is cell tests with small fuel and air electrodes (cell coupons) and associated migration of oxygen ions in a flux from the cathode to the anode under typical fuel cell operating conditions (see Section 3.5, below).

This task is broken down into three activities: (i) examination of thermodynamic equilibrium in relation to potential instability of these electrolyte materials in reducing environments, including determination of key factors affecting such a phenomenon; (ii) experimental thermogravimetric weight-loss tests on sample electrolyte disks maintained at various temperatures in an oven; and (iii) development of analytical models that are

FIGURE 3

TABLE II:
COMPARATIVE IONIC CONDUCTIVITIES AT 500°C

<u>COMPOSITION</u>	<u>σ (Ω^{-1} cm^{-1})</u>
3-F (OS-03)	4.57×10^{-3}
3-C	15.7×10^{-3}
2/3-G	10.0×10^{-3}
2/3-B	10.5×10^{-3}

structured to utilize thermogravimetric data and provide predictions of electrolyte stability under various fuel cell operating conditions.

3.2.1 THERMODYNAMIC EQUILIBRIUM CONSIDERATIONS

In this analysis, four species are considered for the anode gas stream, namely: CO, CO₂, H₂, and H₂O. The basis for the analysis is thermodynamic data on free energy change, provided in the JANAF tables of the third edition, Volume 14, 1985, Supplement No. 1 (ISBN 0-88318-473-7). The free energies of formation of CO, CO₂ and H₂O are given in Table III. (The free energies of formation of C, H₂, and O₂ are defined as zero.) The reactions considered in the analysis are:

Reaction (4) simply comprises Reaction (2) minus Reaction (3), and it represents water gas shift reaction.

Based on the data of Table III, the equilibrium constants (equal to $-\Delta G/RT$) for all three reactions were calculated and are shown in Table IV. As can be gleaned from Table IV, the shift reaction is the one that will have the most influence on changes in the original species concentrations, with the other two having effects lower by several orders of magnitude.

Thus, shift reaction equilibrium was used to determine the partial pressures of the four anode gas species, but the equivalent oxygen partial pressures were calculated from the equilibrium of Reaction (2) or Reaction (3).

This procedure was entered in a Lotus 1-2-3 spreadsheet and used to investigate the behavior of equilibrium partial pressures in the anode gas stream as a function of nominal cell temperature and initial gas composition. Two cases are presented herein to delineate the results as follows: Case 1 approximates a coal gasifier stream, and Case 2 approximates an output of a

TABLE III:
FREE ENERGIES OF FORMATION

DEG.K.	DEG.C.	DEG.R.	DEG.F.	CO DELTA G _f (KJ/MOL)	CO ₂ DELTA G _f (KJ/MOL)	H ₂ O DELTA G _f (KJ/MOL)
(ROUNDED TO THE NEAREST DEGREE)						
500	227	868	440	-155.414	-394.939	-219.069
600	327	1048	620	-164.486	-395.182	-214.018
700	427	1228	800	-173.518	-395.398	-208.819
800	527	1408	980	-182.497	-395.586	-203.501
900	627	1588	1160	-191.416	-395.748	-198.086
1000	727	1768	1340	-200.275	-395.886	-192.593
1100	827	1948	1520	-209.075	-396.001	-187.035
1200	927	2128	1700	-217.819	-396.098	-181.428
1300	1027	2308	1880	-226.509	-396.177	-175.775
1400	1127	2488	2060	-235.149	-396.240	-170.090
1500	1227	2668	2240	-243.740	-396.288	-164.375
1600	1327	2848	2420	-252.284	-396.323	-158.639
1700	1427	3028	2600	-260.784	-369.344	-152.883
1800	1527	3208	2780	-269.242	-396.353	-147.111
1900	1627	3388	2960	-277.658	-396.349	
2000	1727	3568	3140	-286.034	-396.333	
2100	1827	3748	3320	-294.372	-396.304	
2200	1927	3928	3500	-302.672	-396.262	
2300	2027	4108	3680	-310.936	-396.209	
2400	2127	4288	3860	-319.164	-396.142	
2500	2227	4468	4040	-327.356	-396.062	

Data From JANAF, Third Edition, Volume 15, 1985, Supplement No. 1
(ISBN 0-88318-473-7)

Pressure = 1 Bar

TABLE IV:
EQUILIBRIUM CONSTANTS AS FUNCTION OF TEMPERATURE

DEG.K.	DEG.C.	DEG.R.	DEG.F.	CO+½O ₂ = CO ₂ (JANAF) K2	H ₂ +½O ₂ = H ₂ O (JANAF) K3	CO+H ₂ O = CO ₂ +H ₂ (JANAF) K4
<u>(ROUNDED TO THE NEAREST DEGREE)</u>						
500	227	868	440	1.0536E+25	7.6855E+22	1.371E+02
600	327	1048	620	1.2123E+20	4.2822E+18	2.831E+01
700	427	1228	800	3.6030E+16	3.8199E+15	9.432E+00
800	527	1408	980	8.1865E+13	1.9367E+13	4.227E+00
900	627	1588	1160	7.2260E+11	3.1366E+11	2.304E+00
1000	727	1768	1340	1.6502E+10	1.1479E+10	1.438E+00
1100	827	1948	1520	7.5206E+08	7.6108E+08	9.882E-01
1200	927	2128	1700	5.7568E+07	7.8931E+07	7.293E-01
1300	1027	2308	1880	6.5653E+06	1.1551E+07	5.684E-01
1400	1127	2488	2060	1.0240E+06	2.2185E+06	4.616E-01

steam reformer and shift reactor train. The results of these cases are shown in Tables V and VI, respectively.

In both cases it is noted that the equilibrium oxygen partial pressures calculated from the equilibrium constants of Reactions (2) and (3) are the same, as expected. In Case 1 the equilibrium oxygen partial pressure ranges from approximately 10^{-25} to 10^{-20} atm. in the temperature range of 600°C to 800°C. This temperature range is of particular interest since it represents the expected range of operation for the SSFC electrolytes. For Case 2 the range is from approximately 10^{-24} to 10^{-19} atm. for the same temperature interval.

The next consideration involves the thermodynamic stability of the electrolyte in association with the anode gas stream composition. The mechanism for reduction of the electrolyte ceramic at the anode may be expressed as

(i.e., reduction of a metal oxide to a metal via reaction with hydrogen). The corresponding equilibrium constant would be

$$K_{eq} = \frac{(a_M)^x (a_{H_2O})^y}{(a_{M_xO_y}) (a_{H_2})^y} \quad (6)$$

$$\text{where } K_{eq} = -\Delta G/RT \quad (7)$$

It may be assumed that M and M_xO_y are sustained as separate phases (irrespective of relative amounts) and that the solubility of gases in them is small. Their activities can then be taken as unity; therefore, Equation (6)

TABLE V: CASE 1

INITIAL COMPOSITION

CO 22.000%
H₂O 11.000%
CO₂ 0.000%
H₂ 67.000%

DEG.K. (ROUNDED TO THE NEAREST DEGREE)	DEG.C.	DEG.R.	DEG.F.	CO	H ₂ O	CO ₂	H ₂	O ₂ FROM K2	O ₂ FROM K3
Equilibrium Values (%)									
500	227	868	440	11.515	0.515	10.485	77.485	7.470E-51	7.470E-51
600	327	1048	620	12.897	1.897	9.103	76.103	3.390E-41	3.390E-41
700	427	1228	800	14.815	3.815	7.185	74.185	1.812E-34	1.812E-34
800	527	1408	980	16.588	5.588	5.412	72.412	1.588E-29	1.588E-29
900	627	1588	1160	17.952	6.952	4.048	71.048	9.733E-26	9.733E-26
1000	727	1768	1340	18.924	7.924	3.076	70.076	9.704E-23	9.704E023
1100	827	1948	1520	19.600	8.600	2.400	69.400	2.651E-20	2.651E-20
1200	927	2128	1700	20.073	9.073	1.927	68.927	2.781E-18	2.781E-18
1300	1027	2308	1880	20.409	9.409	1.591	68.591	1.410E-16	1.410E-16
1400	1127	2488	2060	20.653	9.653	1.347	68.347	4.054E-15	4.054E-15

TABLE VI: CASE 2

INITIAL COMPOSITION

CO 0.000%
H₂O 11.000%
CO₂ 22.000%
H₂ 67.000%

DEG.K. (ROUNDED TO THE NEAREST DEGREE)	DEG.C.	DEG.R.	DEG.F.	CO	H ₂ O	CO ₂	H ₂	O ₂ FROM K2	O ₂ FROM K3
				<u>Equilibrium Values (%)</u>					
500	227	868	440	0.860	11.860	21.140	66.140	5.444E-48	5.444E-48
600	327	1048	620	3.048	14.048	18.952	63.952	2.631E-39	2.631E-39
700	427	1228	800	6.047	17.047	15.953	60.953	5.361E-33	5.361E-33
800	527	1408	980	8.965	19.965	13.035	58.035	3.155E-28	3.155E-28
900	627	1588	1160	11.407	22.407	10.593	55.593	1.651E-24	1.651E-24
1000	727	1768	1340	13.322	24.322	8.678	53.678	1.558E-21	1.558E-21
1100	827	1948	1520	14.785	25.785	7.215	52.215	4.210E-19	4.210E-19
1200	927	2128	1700	15.897	26.897	6.103	51.103	4.447E-17	4.447E-17
1300	1027	2308	1880	16.745	27.745	5.255	50.255	2.284E-15	2.284E-15
1400	1127	2488	2060	17.401	28.401	4.599	49.599	6.662E-14	6.662E-14

simplifies to

$$K_{eq} = \frac{(a_{H_2O})^y}{(a_{H_2})^y} = \left[\frac{(a_{H_2O})}{(a_{H_2})} \right]^y \quad (8)$$

If it is assumed that the gases are ideal (pressures that are not excessive), the activities can be replaced by partial pressures as follows:

$$K_{eq} = \left[\frac{(P_{H_2O})}{(P_{H_2})} \right]^y \quad (9)$$

The free energies of formation for the new ceramic materials that are the subject of this study are not known. Therefore, ΔG , and hence K_{eq} , for Reaction (5) cannot be determined. Nevertheless, the structure of Equation (9) allows certain information to be inferred relative to the equilibrium conditions for Reaction (5).

Equation (9) shows that the tendency for reduction to occur via Reaction (5) is determined solely by the P_{H_2O}/P_{H_2} ratio in relation to this ratio at equilibrium. Hence, if P_{H_2O}/P_{H_2} is greater than the equilibrium ratio (as stated in Equation [9]), the thermodynamic driving force for Reaction (5) will be to the left; i.e., no reduction will occur. Conversely, if P_{H_2O}/P_{H_2} is less than the equilibrium ratio, the thermodynamic driving force will be to the right; in this case, reduction of the metal oxide will tend to occur. (This, of course, says nothing about reaction rates, which could certainly be negligible, depending upon conditions.)

Additional judgments can be offered relative to Reaction (5) and Equation (9). With regard to the ceramic materials it is evident that for reasonably stable metal oxides (i.e., oxides of reasonably active metals) the general tendency for Reaction (5) will be to the left (favoring the oxide over the metal). It is likewise inferred that the free energy change for this reaction (at temperatures that are not excessive) is positive; consequently, $\ln K_{eq}$ is negative (see Equation [7]), which means that $K_{eq} < 1$. Accordingly,

it is expected that the (P_{H_2O}/P_{H_2}) is less than unity at equilibrium, or P_{H_2} must be greater than P_{H_2O} (by some unknown degree) in order for metal oxide reduction to be thermodynamically favored. (Typically, however, such tendencies for reactions to proceed to the left from a thermodynamic point of view are mitigated with increasing temperature.)

The above observations with regard to the criticality of the P_{H_2O}/P_{H_2} ratio have the utmost importance when viewed in the context of the fuel cell anode environment. There are three factors that determine the local P_{H_2O}/P_{H_2} ratio (or equivalent oxygen partial pressure via Reaction [3]) at the fuel cell anode: (i) the relative H_2O and H_2 concentrations in the anode feed gas; (ii) the degree of hydrogen utilization at anode (since H_2 molecules are destroyed and H_2O molecules are created as the anode reaction proceeds); and (iii) the relative concentrations of both CO and CO_2 in the anode feed gas, since the P_{H_2O}/P_{H_2} ratio will tend to be adjusted in accordance with water gas shift equilibrium (Reaction [4]). It is therefore seen that there are elements present in the fuel cell anode environment that tend to discourage metal oxide electrolyte reduction; such discouragement is aided by higher water content in the anode feed gas stream, higher hydrogen utilization rate at the anode, and higher CO_2/CO ratios in the anode feed gas stream. It is also clear that the local tendency toward reduction at the anode diminishes substantially as the anode reaction proceeds.

The upshot of this discussion is that the assessment of reductive stability of these new ceramic materials in dry hydrogen environments does not realistically translate into applicability in fuel cell anode environments. It should be noted that these considerations have been offered from a thermodynamic point of view alone thus far. These do not involve the issues of rates of reductive reaction and counteracting tendencies associated with oxygen ion migration from the cathode to the anode in an operating fuel cell environment, both of which are addressed in subsequent sections of this report.

3.2.2 THERMOGRAVIMETRIC TESTING

3.2.2.1 EXPERIMENTAL APPARATUS AND PROCEDURES

Experimental thermogravimetric tests were conducted on electrolyte disks in an oven maintained at various temperatures. The specially designed oven includes a test chamber that comprises a 14-inch long, 3-inch o.d., thin-walled stainless steel tube. At the back end the tube has been closed by welding a flat stainless steel plate to it, and this end is inserted into the oven. The front end of the tube exits the oven through a tight-fitting hole in two firebricks and terminates in a "Laddish"-type flange. The other half of this flange is attached to a stainless steel shelf which extends to the back of the chamber and on which the experiments are mounted. A Teflon O-ring between the two flange halves makes the entire chamber leak-tight.

Two valved $\frac{1}{4}$ -inch stainless steel tubes (one entering at the front, the other exiting at the rear) allow for complete control of the inner atmosphere. The inlet port is connected to a manifold system which allows the introduction of different gases into the chamber. For the experiments described below, the outlet port was vented to the atmosphere, and during the thermogravimetric measurements a constant gas flow was maintained through the oven. When the gas was nitrogen, it was vented directly into the atmosphere; when it was hydrogen, it was burned at the exit port.

All weight measurements were made on an equal-arm balance capable of resolving 0.1 mg. These could only be made at room temperature before and after treating the samples. It was necessary to transfer the samples to the scale pan with tweezers, which can introduce mechanical flaking. From experience, the measurement uncertainty from all sources was judged to be at worst ± 0.2 mg. Therefore, the only points reported are for mass changes of at least 1.0 mg. Since most of the samples measured had masses on the order of 200-400 mg, it was not possible to determine weight losses at low temperatures where the total weight losses were less than the measurement error.

Unless otherwise noted, temperatures were measured with a platinum thermometer placed in close proximity to the sample and which followed the DIN curve for platinum ($\alpha = .00385^{\circ}\text{C}^{-1}$). The oven temperature can be controlled to within $\pm 2^{\circ}\text{C}$ for long periods of time.

The hydrogen and nitrogen used for the thermogravimetric tests were purchased as high-purity gases with the minimum concentration of oxygen and water. Both were analyzed with an industrial zirconia oxygen analyzer (Thermox-Ametek) for oxygen partial pressure. The oxygen partial pressure at each experimental temperature point was determined using this equipment.

Initial tests were made on a sample of OS-3, starting at about 200°C and proceeding upwards in steps of 100°C to 700°C . At the highest temperature, a second (virgin) sample of OS-3 was tested. Both samples had initial masses of about 0.4 gm, and the resulting weight-loss data showed good agreement between the two samples. This is illustrated by the squares in Figure D-1 (Appendix D).

The procedure in these tests was to purge the test chamber with hydrogen at room temperature, heat to the test temperature as quickly as possible, and, after the test, cool as quickly as possible. The hydrogen flow was continuous and was burned as the gas left the oven. This procedure was used to avoid reaching the flash point of hydrogen with air in the test chamber, especially above 500°C . However, there was some concern regarding the possibility of introducing integrated weight losses below the measurement temperature.

After this initial survey, the test procedure was improved by setting up a more elaborate gas flow system. Valves were installed so that nitrogen, hydrogen, or a small air flow (from a fan) could be fed into the test chamber; and the following procedure was then used for all subsequent measurements: The oven was first brought to temperature and allowed to stabilize (over about one hour). The test chamber was then purged with nitrogen for about two minutes, and the hydrogen flow was started. The elapsed time was recorded until the above procedure was reversed for cool-down. In this method, all of the weight loss occurred while the sample was at the test temperature.

A series of tests was then run on one sample of OS-3 from 100°C to 850°C in steps of 50°C. At 800°C and 850°C a second (virgin) sample of OS-3 was added. These results are shown as circles in Figure D-1. There were no measurable weight losses for OS-3 below 600°C. (The initial sample weighed about 0.2 gm, and the second OS-3 sample weighed about 0.8 gm; here again, there appear to be minor differences in the results obtained for the two samples.)

The experience with OS-2 and OS-4 was quite different. During the initial series of tests, these two materials showed no weight loss at 200°C for two hours. However, at 300°C for two hours there was a significant enough oxygen loss that the samples turned to powder; and a second series of tests at more closely spaced temperature points confirmed this result. During the second series for both materials, the weight loss at 255°C after three hours was on the order of the uncertainty of the measurements; OS-4 showed no weight loss at 277°C, while OS-2 showed a 5 percent weight loss at this temperature after three hours. At 300°C after two hours, both samples again crumbled. At present, there are not enough reliable points to produce meaningful weight-loss versus temperature plots for these two materials.

Because of the relatively stable performance of OS-3 samples, even at elevated temperatures, and the relatively poor stability of the OS-2 and OS-4 compositions, it was decided that future work would be concentrated on the OS-3 type materials. However, systems involving cross-doping of the OS-3 and OS-2 type materials were also investigated in subsequent thermogravimetric testing.

Since the ionic conductivity measurement results (Section 3.1.2.1, above) indicated that the OS-3 type material designated 3-C had even higher ionic conductivity than OS-3 (3-F) itself, a series of samples covering the range in composition between 3-C and 3-F was prepared for thermogravimetric testing. These included the 3-D and 3-E compositions evaluated in Section 3.1.2.1, as well as two new compositions, designated 3-J and 3-K. The cross-doped samples prepared for this round of testing correspond to the 2/3-A, 2/3-B, 2/3-E, and 2/3-G compositions studied in Section 3.1.2.1.

The experimental thermogravimetric procedures were the same as those carried out in the tests most immediately prior to these, as described above. The data acquired include two sets for OS-3 (3-F), one from the present series, and one from the previous series, for comparison. The results are presented in Appendix D and discussed below.

3.2.2.2 DISCUSSION OF RESULTS

It has been found that the composition corresponding to 3-C is more stable than those closer to and including OS-3 (See Appendix D). Correspondingly, the 3-C composition was found to be the one having the highest ionic conductivity of all the materials examined in this study (see Section 3.1.2.1, above). There is, however, some initial evidence that the 3-C composition is not phase-stable over long periods of time at elevated temperatures. It might be necessary, therefore, to trade off ionic conductivity versus phase stability in the OS-3 type material. The material of choice might be one intermediate in composition between 3-C and 3-F (OS-3); this would reduce somewhat both the ionic conductivity and the thermogravimetric performance (from those of 3-C) but could provide the desired stability of the inorganic phase structure.

The thermogravimetric measurements on the OS-2/OS-3 type cross-doped materials were less encouraging than those of the OS-3 type materials (see Appendix D). The two cross-doped materials with the highest ionic conductivities (both superior to OS-3) were far less stable than OS-3. Samples of 2/3-B and 2/3-G had lost enough mass at 400°C that they crumbled into smaller pieces. High weight-loss results were obtained for 2/3-G, and only one measurable data point could be acquired for 2/3-B.

These results do not rule out cross-doped compositions since those with higher ionic conductivities might still be stable in an actual fuel cell anode environment. However, there are no perceived trends that would indicate any cross-doped compositions having both higher conductivity and greater stability than OS-3. Therefore, the material of choice at present would remain an OS-3 type material, probably intermediate in composition between 3-F (OS-3) and 3-C.

3.2.3 ANALYSIS OF ELECTROLYTE STABILITY UNDER FUEL CELL OPERATING CONDITIONS

The thermogravimetric results of Section 3.2.2 and Appendix D indicate the reductive weight loss characteristics of the candidate electrolyte materials over the temperature range of interest. In the following discussion, the thermogravimetric results are analyzed with respect to their applicability in an actual fuel cell anode environment.

There are two major considerations in translating these results into predictions of electrolyte stability in an operating fuel cell. First, the P_{H_2O}/P_{H_2} ratios employed in the thermogravimetric studies were in the range to be expected in typical fuel cell anode feed gas streams; however, this does not account for the relatively high P_{H_2O}/P_{H_2} ratios that tend to prevail as the fuel cell reaction proceeds at the anode. Therefore, the thermogravimetric results tend to exaggerate the overall reduction effects at the fuel cell anode. Nevertheless, it will be assumed in subsequent discussion that the P_{H_2O}/P_{H_2} ratios employed in the experimental studies of this program satisfactorily represent actual fuel cell anode conditions.

The second consideration to be dealt with involves the flux of oxygen ions migrating from the cathode to the anode in an operating fuel cell, and this issue is by far the more crucial one. This flux will tend to counteract the electrolyte reduction phenomenon since O^{2-} ions will migrate to vacancies created in the metal oxide lattice by reduction with hydrogen. These sites will thereby undergo reoxidation with discharge of electrons to the electronically conducting structure of the anode. The balance of the oxygen ions migrating from the cathode to the anode will likewise produce current by reacting with hydrogen at the anode in the conventional manner. Thus, the tendency for electrolyte reduction at the anode will be resisted provided that the flux of oxygen ions (i.e., current density) is great enough to offset the rate at which bound oxygen is removed from the metal oxide lattice by reduction with hydrogen.

It is apparent that a normal operating fuel cell can sustain a stable electrolyte structure at the anode; but, on the other hand, the open-circuit condition (where there is no flux of oxygen ions) should be avoided. Furthermore, there is a minimum current density below which the fuel cell should not be operated if reduction tendencies are to be avoided. It is therefore important to examine fuel cell operation in terms of minimum current densities to determine the practicality of such conditions.

The weight-loss rates determined in the thermogravimetric testing (Section 3.2.2 and Appendix D) can be translated into equivalent fluxes of bound oxygen ions removed from the electrolyte by reduction. This flux can correspondingly be expressed in terms of a current density as follows:

$$J_b = \frac{Fn}{M} \frac{dm/dt}{A} \quad (\text{amperes/cm}^2) \quad (10)$$

where F is Faraday's constant, M is the molecular weight of oxygen, n is the number of gram-equivalents per gram-mole, dm/dt is the weight-loss rate for the electrolyte sample, and A is the electrolyte cross-sectional area.

The weight-loss data for OS-3 (3-F) are utilized to plot the corresponding current density due to reduction over the temperature range 600°C to 850°C in Figure 4. It is seen that J_b varies from 4 to 55 mA/cm² over this range.

It was determined in the ionic conductivity studies of Section 3.1 that the OS-3 electrolyte material, along with several others, has attractive ionic conductivity characteristics over the temperature range of interest. As such, the OS-3 material is capable of supporting high current densities in an operating fuel cell. To illustrate this the performance of an OS-3 electrolyte operating in a fuel cell at 800°C will be considered. Taking the empirically determined parameters σ_0 and Q from Table I and using these in Equation (1), the ionic conductivity of OS-3 at 800°C is found to be

FIGURE 4: RESULTS OF EQUIVALENT REDUCTIVE CURRENT DENSITY ESTIMATES FOR OS-3 (3-F)

$$\sigma = \frac{9.47 \times 10^6}{1073} e^{-\left[\frac{0.949}{(8.59 \times 10^{-5}) (1073)} \right]}$$

$$= 0.298 \Omega^{-1} \text{cm}^{-1}$$

Such ionic conductivities can indeed support high current densities. This is illustrated below by considering the voltage driving force necessary to provide a high current density of 1 A/cm² through an OS-3 electrolyte with an assumed thickness of 1 mil (0.00254 cm) at 800°C.

$$V = iR = J_m AR = J_m A (1/\sigma) L/A = J_m L/\sigma \quad (11)$$

where V is the voltage driving force for ionic conduction across the electrolyte, i is the ionic current, R is the resistance across the electrolyte, J_m is the current density across the electrolyte resulting from mobile oxygen ions, and L is the electrolyte thickness. Using the value for σ determined above it is seen that the voltage loss (iR-loss) across the electrolyte is only about 8.5 mV at a current density of 1 A/cm² (a very small fraction of the operating cell voltage).

It is now clear that the current densities in an operating fuel cell will far exceed those necessary to sustain a stable electrolyte phase in the anode environment. It would be necessary, however, to maintain current densities greater than that which is equivalent to J_b (Equation [10], above) under all operating modes where hydrogen is fed to the anode. As seen in the case of OS-3, this would not constitute a burden to the fuel cell system since J_b is very small with respect to anticipated operating current densities; such minimum current densities are likely to be exceeded during standby operation, for instance, merely in delivering parasitic power requirements for the fuel cell system.

3.3 TASK I.3: DEVELOPMENT OF CELL ELECTRODES

The electrodes in solid electrolyte fuel cells serve two purposes: (1) they act as catalysts to promote the exchange of electrons between oxygen molecules and ions, and (2) they provide a conductive path for the electrical current produced by the fuel cell. To perform these tasks the electrodes should be good catalysts, be chemically stable, have good adhesion to the electrolyte, and have low resistance while being porous. Platinum has served as the material of choice, both because it meets the above requirements and because of the additional requirement of stability at high temperatures in traditional oxygen conducting fuel cells that operate at temperatures near 1000°C. Platinum is expensive, however, and the potential lower operating temperatures using the new electrolyte materials open up the possibility of using less expensive materials. Tests of different materials are described in Appendix E.

All of the experiments conducted were designed to test one or more of the properties of good electrodes as listed above. DC conductivity and Nernst voltage experiments were conducted as prima facie tests of catalytic activity since these tests can only be successful if there are catalyzed oxygen ions flowing through the material. Several of the other tests described in Appendix E are designed to test the electrical properties and the practical limits of these properties under various conditions (e.g., what is the maximum current density an electrode can support under specifically defined conditions?). A common parameter to both catalytic and electrical tests is the density and thickness of the electrode material. If the electrodes are too thick, performance can be degraded by diffusion impeding the flow of oxygen. On the other hand, the electrical properties of electrodes generally improve as they become thicker. A compromise exists between these two requirements, and defining this compromise is one of the main objectives of the electrode research.

Many of the tests conducted were not included as part of a large matrix of experiments with a wide range of parameter variations (e.g., dc conductivity versus firing temperature versus electrode thickness). Instead, the tests were carried out on an ad-hoc, trial-and-error basis in response to specific

and narrow objectives; for instance, the need to produce an electrode which gives the full Nernst voltage for the cell. In many of these cases the tests provided a working solution for the particular problem, but the solution may not be ideal and therefore may provide only a starting point for defining the limits for the parameter variations which need to be investigated. The work carried out serves to define these starting points as well as their fit into the larger framework of questions to be answered more fully in the future on how to make the best and least expensive electrodes.

Many of the tests were performed in the specially designed oven test chamber described in Section 3.2.2.1. Sealed alumina thermocouple protection rods enter the front flange through O-ring seals and also allow for silver electrical leads to enter the chamber. All the leads are shielded at the front and connect to couplings for total electrical isolation. A platinum thermometer inside the test chamber measures the temperature, and the inner shelf is slotted so that different supports and experiments can be attached easily.

The experiments described in Appendix E fall into two broad categories. The first group involved testing of various electrode materials including several "traditional" platinum inks, other metal inks and other forms of platinum. At present no material has proven superior to an application of finely ground platinum metal mixed in an organic medium. The limits of application density and firing temperature have also been explored in relation to mechanical properties and proper catalysis for oxygen reduction.

The second broad area involved a number of experiments designed to quantify the relation between electrode resistance and the density of the electrode material. These studies included an experiment which assessed resistance as a function of density for two different forms of platinum in an effort to reduce the cost of platinization by highly uniform coating methods. This experiment proved successful in that small amounts of platinum could form continuous electrodes at densities significantly lower than the densities required for traditional inks. On the other hand, utilization of these electrodes is limited to uses where cost is more important than total resistance.

Finally, the temperature dependence of the effective resistivity of platinum electrodes was measured.

3.4 TASK I.4: TEST FIXTURES DESIGN AND FACILITY ERECTION

The research effort of this program is directed toward the channeling of electrolyte materials progress into practical manifestations via fuel cell coupon testing. This task provides the designs and hardware necessary to accomplish such testing.

Cell coupon tests must be performed on a thin ceramic electrolyte, and the fabrication of such an electrolyte can easily amount to a major undertaking in its own right. Having a thin electrolyte is necessary for achieving respectable levels of current density under fuel cell operating conditions. This is important not only from a performance determination point of view, but also, as discussed in Section 3.2, with respect to the influence of the oxygen ion flux on electrolyte stability at the anode. The preliminary design concepts for fabricating and testing a coupon cell are presented below.

3.4.1 PRELIMINARY DESIGN CONCEPTS

The electrolyte ceramic material that is the focus of this program is tape-castable, as demonstrated in an earlier CeramPhysics program that was funded by DOE. Such tapes can be formed in the green state as thin as 1-2 mil, but individual tapes cannot be fired due to warpage. Ceramic capacitors are fabricated from tapes where 40 to 60 tapes are stacked and fired as a monolith, and structural integrity is achieved by applying some pressure to the stack of tapes during firing.

The concept for a fuel-cell coupon is to fire a single tape of the electrolyte in a manner that mimics the ceramic-capacitor process. This concept is shown schematically in Figure 5, and the intention is that the two foamed alumina blocks add structural integrity to the single electrolyte tape during firing. Moreover, the foamed alumina would allow easy access of both air and fuel-gas to the electroded ceramic electrolyte during testing.

FIGURE 5: FUEL CELL COUPON

The green tape would have electrodes silk-screened on both sides as shown in Figure 5; note the unelectroded margins in Figure 5 to avoid shorting. The green tape is flexible, and the edges of the tape would be bent over onto the foamed-alumina blocks as shown in Figure 5 to facilitate electrical contact as described below.

A drilled port is shown in the upper block in Figure 5, and an alumina tube is later inserted into this port. The port extends into the block only the distance needed to support the tube.

The block-tape-block combination would be fired as a unit, including the binder-burnout step. Note that the foamed alumina also allows easy escape of the organics during binder burnout. A small amount of sealant may prove necessary between the bent edges of the tape and the blocks during this firing to maintain the configuration.

Following this firing step, the bent and electroded edges of the fired tape would have silver tabs fired on as shown in Figure 6. Finally, in a one-step operation, the top block would be hermetically sealed and the alumina tubes sealed in place in the drilled ports, as shown in Figure 6. The final arrangement is shown in the lower drawing in Figure 6; fuel gas enters one alumina tube, spent gas exits the other tube for analysis, and power leads are attached to the silver tabs.

The hermetic seals shown in Figure 6 take advantage of the ceramic sealants developed by CeramPhysics for these materials, and two possibilities exist: (1) in the simplest case, the seals are simply a paint-on sealant; or (2) alumina plates are sealed to the upper block.

3.4.2 ALTERNATIVE DESIGN CONCEPTS

The preliminary design concepts described above evolved during the program, with regard to both coupon fabrication and fixture preparation. The techniques for processing the electrolyte powder (e.g., OS-3, supplied by CeramPhysics) into tapes are described in Section 3.5.1, below.

FIGURE 6: CELL ASSEMBLY

3.4.2.1 COUPON CONFIGURATION

A reinforced, multi-layer tape configuration has been designed so as to prevent the thin electrolyte coupon from cracking, or even collapsing due to thermal or mechanical stresses, in the test fixture. This design is illustrated in Figure 7, below.

FIGURE 7: REINFORCED CELL COUPON STRUCTURE

In this design ring-shaped pieces are cut from the green electrolyte tapes and laminated to form a 1 mm thick frame. A top layer of green tape with Pt electroding on both sides is laminated to the base, followed by co-firing and sintering. An alumina die is used so that the entire coupon can be supported during laminating and firing. The frame, which is formed from laminated material, provides structural support to the coupon cell. This allows the cell to have a thin electrolyte layer and, therefore, would support high current density at reasonable cell operating voltage. This in turn permits testing of the cell over a wider range of current densities to investigate the effect of current density on reduction at the anode.

The platinum electrodes shown in Figure 7 are covered, in a later step, by a woven platinum wire screen (available commercially) from both sides of the cell and co-fired to impart intimate contact between the cell platinum electrodes and the platinum screens. The screens are intended to further enhance the coupon cell strength and to act as a bus for the current, thus reducing IR-losses.

3.4.2.2 CELL FIXTURE DESIGN

Three alternative design approaches for the fuel cell test fixture were worked out (or identified from the literature or through consultation with other research groups) and evaluated. Each design was directed toward use in conjunction with the cell coupon configuration described above. The designs are illustrated schematically in Figures 8, 9, and 10, respectively.

The criteria adopted for selection of a fixture design reflected program time and budget constraints; these criteria were: (i) simplicity, (ii) low cost, and (iii) reworkability. After extensive discussion with machinists, glass blowers, and users of existing cell designs, the solid electrolyte cell shown in Figure 10 (which is being used by the late Professor Mason's group at Stanford University) was selected for this program.

Both sides of the oxide electrolyte disc in this cell are coated with Pt or Au electrodes, and the disc is sandwiched between two flat gold rings (cut from gold films of 0.25 mm thickness) which serve as gasket seals and current collectors. This coupon cell is held between two alumina tubes, 12 feet in length, which are pushed against each other to prevent gas leakage from the joints and interfaces. Four metal rods, 36 inches in length, are spring-loaded to secure the gas-tight positions of the coupon cell and alumina tubes.

Although this geometrical arrangement and manipulation were essentially copied for use in the present program, the major difference is the thickness of the electrolyte layer. The oxide disc in Stanford's cell has a thickness of 1.0 to 1.5 mm, which is about 10 times that of the oxide tape that is employed in this program (see Section 3.5, below). As discussed earlier, the mechanical stresses that would be exerted on such thin ceramic tapes during the fabrication and assembly processes would inevitably cause sample fracture. Therefore, the reinforced, multilayer tape structure was devised so as to mimic the properties of the thick disc-type coupon (see Figure 7, above). The results obtained using these coupon structures and fixture design are discussed in Section 3.5.

FIGURE 8: SOLID-STATE FUEL CELL DESIGN

FIGURE 9: DOUBLE POROSITY CELL OF GORIN AND RECHT

FIGURE 10: SOLID ELECTROLYTE CELL

3.4.3 FACILITY ERECTION

Safety was the principal consideration in designing the facility for fuel cell tests. The entire test facility was placed in a large fume hood exclusively designated for flammable gas experiments. A hinged tube furnace in which the coupon cell was placed was monitored by a temperature-control console equipped with a safety valve that opens when the system malfunctions, allowing nitrogen gas to purge the system. The balance of the test fixture is mostly outside the tube furnace. Two metal rings were placed inside the furnace to keep the alumina tubes from tilting as a result of the end caps of the tubes (outside the furnace) being heavy.

The pre-mixed H_2 and CO gases (3:1 in volume) were passed through a bubbling container for H_2O addition; the container was heated at $45^\circ C$ in a water bath so that the final composition of the fuel gas was $H_2/CO/H_2O = 67:22:11$. The cathode gas was dry, pure air. The spent gases were led to a mass-spectrum-type gas analyzer. The whole facility, including the current and voltage measuring devices, was assembled and checked before installation of the coupon cell.

3.5 TASK I.5: PRELIMINARY COUPON CELL TESTS

In this section the procedures for preparation of solid oxide tapes, fabrication of cell coupons, and assembly into the test fixture and facility are reviewed.

3.5.1 TAPE CASTING

The preparation of solid electrolyte tapes first involves the drying of 395 g of OS-3 powder in a $120^\circ C$ oven for 46 hours to eliminate absorbed water. This material is then mixed with 132.4 g of Cladan binder CB73115 (33.5 wt.%) in a nalgene jar for 24 hours to ensure thorough mixing. The slip is placed in a vacuum oven for eight minutes to eliminate air bubbles.

The tape caster (Unique Model TC121) is set up by attaching a carrier film of silicone-coated polyester to the casting belt and adjusting the doctor blade height to 3 - 4 mils (0.076 - 0.102 mm) for the first run and 15 mils (0.381 mm) for the second run. The de-aired slip is poured into the cavity

and cast at a rate of 10 inches per minute. Green tape thicknesses are 1.6 mils (0.04 mm) and 8 mils (0.203 mm), respectively. All tapes are stored in a air-tight bags. Figure 11 shows a scanning electron micrograph of a green tape at 1000x.

3.5.2 COUPON FABRICATION

The 8-mil tape is cut into one-inch circles. Every circle is electroded on both sides with Metoramic Science, Inc. #71396 platinum ink in a keyhole shaped design (Figure 12). This design consists of a centered 5/8-inch circle with a 1/4-inch path from the circle to the edge of the tape that forms a path for current to be removed and measured. The ink is approximately 0.4-mil (10- μ m) thick, unfired.

A ring design is used to reinforce the thin ceramic electroded piece. Rings are obtained from the 8-mil tape by cutting 1-inch circles and removing a 5/8-inch circle from the center. Two rings are laminated to each electroded tape using a complex laminating die. A schematic of this die is shown in Figure 13. Lamination is carried out in a press with platens heated to 170°F (77°C) at a pressure of 5,000 pounds for 15 minutes.

Several sintering schedules were evaluated. The final sintering schedule adopted is as follows:

- a) room temperature to 600°C at 1°C/min
- b) hold at 600°C for 2 hours
- c) 600°C to 890°C at 3.3°C/min
- d) hold at 890°C for 1 hour
- e) furnace cool.

Steps a and b, the binder burnout steps, allow the binder to burn out slowly from the ceramic without causing damage (pores or cracks). Steps c and d produce the densified ceramic.

FIGURE 11: SCANNING ELECTRON MICROGRAPH OF
THE SURFACE OF AN UNFIRED TAPE

FIGURE 12: UNFIRED ELECTRODED TAPE

FIGURE 13: CROSS-SECTIONAL VIEW OF THE LAMINATING DIE:
 A) 1-IN. DIA., B) SILICONE-COATED POLYESTER,
 C) ELECTRODED GREEN TAPE, D) 2 RINGS,
 E) 5/8-IN. DIA., F) HOLLOW CYLINDER, 1-IN. DIA.

Materials on which the fuel cell coupons were placed included alumina, platinum foil, zirconia cloth, and Si/Al setters coated with zirconia. The platinum foil worked best when it did not contact the platinum ink. The alumina seemed to have reacted with the coupon during sintering and caused sticking. The zirconia cloth worked well, but the fibers adhered to the coupon, which could eventually lead to failure. The best overall setters were MSI LM-200, an Al/Si fiberboard coated with zirconia.

The surface of the platinum electrode is seen in the scanning electron micrograph of Figure 14; this shows open porosity, which is a desired property. The surface of the coupon without the platinum electrode (at the same magnification as in Figure 14) and with less porosity is seen in Figure 15. In the fracture surface shown in Figure 16, basically two kinds of pores are seen: an almost circular pore $\sim 1\text{-}\mu\text{m}$ in diameter and a tubular-shaped pore which may arise from the joining of several circular pores. Grains cannot be distinguished clearly in the fracture surface.

Optimization of fuel cell coupon fabrication should include a sintering study to determine the best heating rate for OS-3 material in tape-cast form, a cutting device designed to precisely cut the rings and circles, a permanent pattern designed on a screen for printing the platinum electrodes, and a study to find the best binder system for this powder. Despite some of these unknowns, acceptable coupons were fabricated for use in the test cell.

3.5.3 CELL ASSEMBLY

A number of electrolyte tapes having a working electrode area of $1.2\text{-}1.3\text{ cm}^2$ were prepared. The thickness of the central electroded area ranged from 0.13 to 0.35 mm (5 to 14 mil), and that of the ring area from 0.35 to 0.70 mm (14 to 28 mil). Tapes with even thicker rings were tried, but they cracked after sintering. In addition to the gold-ring gaskets, Fiber Frax 970 gasket papers were also placed at the edges of the tape between the gold ring and the alumina tube, providing, hopefully, some cushioning and additional sealing.

FIGURE 14: SCANNING ELECTRON MICROGRAPH OF
THE PLATINUM ELECTRODE SURFACE

FIGURE 15: SCANNING ELECTRON MICROGRAPH OF THE TOP SURFACE OF THE SOLID ELECTROLYTE

FIGURE 16: SCANNING ELECTRON MICROGRAPH OF A
SOLID ELECTROLYTE FRACTURE SURFACE

The first attempt was to mount the coupon cells within the pre-assembled test facility; accordingly, the alumina tubes with the two supporting metal rings were placed within the horizontal groove of the opened furnace. It was found that it was impossible to hold the components of the coupon cell in the correct position for the pressure to be uniformly distributed on the ring of the electrolyte tape when the alumina tubes were closed together and pressed upon the coupon. The reasons are as follows: 1) space for manipulation was limited by the presence of the surrounding metal rods, 2) the oxide tape tended to fall off-center, even when a sticky fluid with low boiling point was used as a glue reagent, and 3) the tubes were not held motionless. These problems resulted in several cracked or broken electrolyte coupons. Then the fixture was set up vertically outside the hood, and the outer alumina tubes and end caps were tightly clamped onto lab stands. Thus, the coupon cell could be mounted horizontally and rest on the lower outer alumina tube. The upper portion of the fixture was then loosened slightly and slowly lowered until the edge of the alumina tube touched the coupon. The eight screws of the four metal rods were then tightened to seal the tube/coupon interfaces. Unfortunately, this method also failed to yield intact coupons because 1) the method of clamping did not precisely align the upper and lower alumina tubes, and 2) tightening the screws caused the fixture to vibrate.

The crux of the problem is the extremely low tolerance of the thin oxide tapes to any mechanical stress. This material problem must be addressed before successful testing can be accomplished. A mechanical device must be designed such that the two outer alumina tubes can be concentrically aligned precisely as they are closed upon the coupon cell, while the mechanical force is being evenly distributed over the contact area. Also, two materials problems must be overcome - the thickness uniformity of the multilayer tapes (to allow uniform bearing of the mechanical force) and the thermal expansion coefficient match among the various components of the facility; the latter issue is critical in high-temperature processes. A decoupling method has been devised to solve these problems in subsequent efforts. Although actual testing of the coupon cells could not be accomplished because of the problems discussed above, ionic conductivity measurements on the sintered solid oxide tapes did demonstrate that high-quality electrolyte coupons possessing the required properties have been attained.

3.5.4 PRELIMINARY CELL TESTS

This subsection describes fuel cell characterization tests on electrolyte coupons made of the proprietary material OS-3. The coupon was placed in a simple cell holder attached to a gas manifold system. Power output density and sample voltage were measured as a function of current density at various temperatures. With the coupon at a constant temperature of 622°C, these same parameters were monitored as a function of time for over 44 hours. A detailed discussion of the experimental setup, experimental procedure and experimental results follows.

3.5.4.1 EXPERIMENTAL SETUP

The OS-3 coupons were comprised of disks with a diameter of 2.0 cm and a thickness of 0.025 cm and had been sintered at a temperature of 900°C by Martin Marietta Laboratories. Each face of each coupon was electroded with a circular pad of diameter 1.4 cm centered on the face. The electrodes were made using Engelhard A4731 platinum ink, which contains no frits. Around the electrode, an annulus of Engelhard A3360 gold ink was fired onto each side of the coupon. This annulus slightly overlapped the platinum electrode and provided a low-resistance current path to the external leads.

It should be noted that the coupons were made with powders sintered on a non-optimum firing schedule. Although the porosity of these coupons was not measured, previous experience would indicate that the coupons were about 90 percent dense.

Figure 17 shows the arrangement of the coupon in the cell holder. The cell holder was made of stainless steel, as were the screws holding the two parts of the cell together. On each side of the coupon there was an annulus of gold foil which matched the annulus of fired-on gold ink. Two silver wires (not shown) of 0.005-inch diameter were attached to each annulus of gold foil with Dupont 7092 silver paste (firing temperature 760°C). The wires exited the furnace through thermocouple tubes. Next to each annulus of gold foil was an annulus of padding made of alumina and dioxide silicon fibers (lytherm) which served to relieve the stress resulting from clamping the coupon between the two parts of the cell holder and was also intended to serve as a seal.

FIGURE 17: COUPON ARRANGEMENT IN CELL HOLDER

The cell holder was approximately 2 inches long and was connected to the gas manifold system with a Swagelok joint around the tube of the holder.

Figure 18 shows a schematic of the gas manifold system. Gas (nitrogen or fuel cell gas) flowed through the water-filled beaker into the inner of two concentric tubes which ended at the cell holder. Gas exited back down the larger concentric tube and was vented well away from the hot furnace. Fuel cell gas was burned off at this point, while nitrogen was vented directly into the room. The purpose of the water-filled beaker was to act as a safety barrier to prevent an accidental ignition of the fuel cell gas from backing into the storage tank. The combination of the regulator valve on each tank and the needle valve in the line were used to regulate the gas flow to the cell holder.

The lytherm gaskets on each side of the coupon did not completely seal the gas flow although they did act as a barrier. Thus, to maintain the proper conditions, the fuel cell gas was fed to the coupon at a pressure slightly above atmospheric. In addition, a small external air flow was maintained in the oven and directed onto the outside of the coupon to sweep the fuel cell gas away from the cathode side of the coupon and to prevent any build-up of fuel cell gas in the oven.

Figure 19 shows a schematic of the electronic data collection system. The temperature of the oven was monitored with a platinum thermometer placed next to the cell holder. Current to the thermometer was supplied by a constant current source and was monitored as the voltage drop across a 1000 ohm standard resistor. The coupon current was monitored as the voltage drop across a 1 ohm standard resistor. All voltages were measured with Keithley Model 181 DVMs that were interfaced with a computer through IEEE 488 lines. The external load in the coupon circuit consisted of the lead resistances (which were on the order of 1 ohm), the 1 ohm standard and a variable resistance box. Changing the resistance of the latter changed the load current. The four leads attached to the gold foil on either side of the coupon meant that a voltage measurement could be made across the coupon directly, eliminating lead resistance, but not the contact resistance between the foil, gold ink, and platinum electrode.

FIGURE 18: GAS MANIFOLD SYSTEM

FIGURE 19: ELECTRONIC DATA COLLECTION SYSTEM

3.5.4.2 EXPERIMENTAL PROCEDURE

After the cell was loaded into the manifold system and placed in the oven, the oven temperature was allowed to become stable with a small air flow through the oven. Initially, air flowed on both sides of the coupon, but after the operating temperature was reached, a small flow of nitrogen gas was delivered through the manifold to flush out the air space. The flow of nitrogen (or fuel cell gas) onto the coupon cooled the coupon to an unknown extent because the thermometer was located outside of the cell holder. The flow rate was kept low to minimize this cooling effect. After several minutes of the nitrogen flush, fuel cell gas flow was initiated. The dry gas from the tank initially consisted of 24.7 percent CO and 75.3 percent H₂. As the gas was bubbled through the water-filled safety flask, it also picked up some water vapor. Since the water in the flask was at room temperature, it is estimated that the final water content was 3 percent of the total gas volume.

At the time the fuel cell gas was initially introduced into the system, the variable load resistance was set so that at least 20 amps of current flowed in the load circuit. This magnitude of current had been previously calculated as being sufficient to prevent reduction of the electrolyte material by the harsh reducing atmosphere of the fuel cell gas.

From this point, two types of tests were run: a load curve of power density (P) vs. current density (J) and sample voltage (V) vs. J, as a longer term stability test. In both cases the data was taken using a computer program which read all four DVMs simultaneously at predetermined time intervals. When power curve data was being measured, the computer was set to read at 10-second intervals, which allowed enough time to change the variable resistance before the next reading. When long-term stability tests were being run, the time interval between the DVM readings was set much longer, e.g., 250 seconds. Data from each test run were analyzed with a second program to calculate the relevant parameters.

3.5.4.3 EXPERIMENTAL RESULTS

Figure 20 shows the power curves P versus J for 6 different temperatures from 429°C to 771°C. The curves for the two lowest temperatures in this graph

FIGURE 20: POWER DENSITY AS A FUNCTION OF CURRENT DENSITY FOR VARIOUS TEMPERATURES

are confined to the lower left corner. They are shown separately in Figure 21 on a different scale. Figure 22 shows V versus J for all 6 temperatures.

In order to evaluate these curves, it should first be noted that all the voltages in Figure 22 are much lower than would be expected. In particular, the open-circuit voltage (i.e., at J=0 in Figure 22) is 30 to 40 percent of the value expected from the Gibbs equation:

$$EMF = (RT/4F) \ln [p_{O_2} (\text{cath})/p_{O_2} (\text{anod})] \quad (1)$$

which would predict voltages between 0.9 - 1.1 V for the system. Even though the room temperature composition of the fuel cell gas was known, because of a problem discussed below, the composition of the gas at the coupon was problematic even in the absence of any leaks in the seals.

The cause of the low voltage is due to one or both of two reasons. It has previously been observed with both OS-3 and zirconia that improperly prepared platinum electrodes can result in a lower voltage than expected from Eq. 1. However, it is impossible to determine whether poor electrodes were a problem because of the existence of substantial leaks through the lytherm gaskets. These leaks could both lower the oxygen concentration on the cathode side and raise it on the anode side., These leaks are thought to be the most likely source of the lowered voltage.

The lower voltage causes the power output of the coupon to be lower than it would be if the full Gibbs voltage were present. Otherwise, the power curves show the expected behavior of increasing power output as the temperature increases and the internal resistance of the coupon decreases.

The peak in the power curve occurs when the external load resistance matches the internal resistance. In this situation, the external load resistance is the combination of variable resistance, 1 ohm standard, and lead resistance. The internal resistance is the combination of all resistances between the voltage leads and consists primarily of the OS-3 material resistance and contact resistances between the gold foil, gold ink, annulus, platinum electrode, and OS-3. If the variable resistance is reduced to zero,

FIGURE 21: POWER DENSITY AS A FUNCTION OF CURRENT DENSITY
FOR VARIOUS TEMPERATURES (DETAIL AT ORIGIN)

FIGURE 22: VOLTAGE AS A FUNCTION OF CURRENT DENSITY FOR VARIOUS TEMPERATURES

the load resistance is still at least approximately 2 ohms (1 ohm for the standard and ~1 ohm for the lead resistance). As can be seen in Figure 20, at the higher temperatures, the minimum load resistance of 2 ohms is greater than the internal resistance and therefore it is not possible to reach the peak in the power curve.

In Figure 20 it can be seen that the peaks at 558°C and 601°C occur at approximately $J=13$ mA and 38 mA, respectively. The total external load resistances at these points are approximately 6 ohms and 2 ohms, respectively. Calculating the internal resistance of the coupon from the equation

$$\sigma T = \sigma_0 \exp(-\theta/T) \quad (2)$$

where $\sigma_0 = 6.187 \times 10^7$ (K/ Ω cm) and $\theta = 1.234 \times 10^4$ (K) yields resistances of 0.6 and 0.3 Ω , respectively. This result indicates that the contact resistances at the coupon were on the order of several ohms and dominate the coupon internal resistance.

After the power curves were completed on one coupon, a long-term stability test was begun on this same coupon. The temperature was maintained at $622 \pm 8^\circ\text{C}$ over the period of the test. Initially, fuel cell gas as described above was run through the manifold and a load resistance was selected which provided a large enough oxygen "wind" through the coupon to prevent the coupon from reducing ($J=46$ mA/cm²). Figures 23 and 24 show graphs of power output versus time and coupon voltage versus time for this test. Several points on this graph are numbered in order to identify them clearly in the discussion below.

Initially, the power oscillated (refer to the region of point #1 in Figure 23) and then went into a decline before reaching a plateau (point #2 of Figure 23) at a greatly reduced power level. After running for ~19 hours overnight, it was observed the next morning that the flow rate of the fuel cell gas had dropped considerably and could not be increased by increasing the tank regulator pressure. This indicated that there was a blockage of the input tube of the manifold system. While the sample remained at temperature, the inner tube was withdrawn and was found to be tightly blocked with finely

FIGURE 23: POWER DENSITY VS. TIME

FIGURE 24: VOLTAGE VS. TIME

powdered carbon over a 3 - 4 cm length. The blocked region was inside the furnace, but upstream from the coupon. Apparently during the power curve testing and the initial stages of the long-term test, carbon had been precipitating from the CO in the fuel gas mixture. This precipitation was not only blocking the flow of gas to the coupon, it made it impossible to determine the nominal oxygen concentration at the coupon (even in the absence of leaks). After the tube was cleaned and reinserted into the oven, hydrogen gas was substituted for the fuel cell gas (point #3 on Figure 23) and the long-term test continued.

The power output rose immediately, but not nearly back to the initial level. After a short time, the power rose significantly for a short time (point #4 of Figure 23) and then fell again to a low value. The test was stopped after ~44 hours of total test time when the power dropped to very low values (point #5 on Figure 23).

After the coupon was cooled, the test apparatus was taken apart and examined. The coupon broke during disassembly, but had not broken during the test. Examination of the cross-section of the coupon with a hand lens revealed no degradation of the coupon which would be associated with reduction of the OS-3 in an adverse atmosphere. In other words, the "wind" of oxygen did protect (as predicted) the OS-3 from reducing in the presence of fuel cell gas and hydrogen.

There were also burn marks on the lytherm gaskets at the place the silver wires exited and at one other place on the gasket. These burn marks were due to flames of burning hydrogen leaking into the surrounding air and igniting spontaneously.

The anode electrode was blackened and there was some surface cracking which could be flaked off easily. It was not clear whether this flaked material was a carbon coating, or the platinum electrode or something else. In either case, the degradation of the anode surface probably contributed significantly to the power degradation either by blocking the electrode (if the blackening was a deposit), or by reducing the platinization area. Interestingly, the flaking was confined to the center of the coupon over a

circle with a diameter of ~0.5 cm. This indicates that the effects that caused the flaking were not uniform across the surface. The interactions of the leaky gaskets, carbon deposition, and electrode degradation is unknown at present, but could certainly be a significant contribution to the long-term power drop.

In addition, there was some noticeable discoloration of the gold ink annulus (recall it contains a glass frit) and the surface of the gold foil next to the ink. This discoloration is probably an indication of oxidation and contamination which would also lead to increased internal resistance and a power drop.

3.5.4.4 CONCLUSIONS

Although the test fixture was somewhat inadequate for providing sufficient pressure to seal the coupons without overstressing them, causing some to crack, modifications were made in an attempt to minimize the problem. This resulted in leakage next to the coupon which in turn was the likely cause of a significantly reduced open cell voltage. In spite of this drawback, very respectable output powers were obtained at relatively low temperatures.

It was also shown conclusively that under operating conditions, a "wind" of oxygen can adequately protect the OS-3 material in a highly reducing atmosphere. During the last 14 hours, the "wind" of oxygen was on the order of 6 - 8 mA/cm² which was significantly lower than the anticipated oxygen flow needed to inhibit reduction. It is possible that the surface flaking noted above was due to a layer of reduced OS-3 on the anode surface. It was noted that the cracking was confined to the center of the disk. If the oxygen flow was concentrated closer to the edges, the lower flow at the center could have resulted in some reduction of the OS-3 at the center of the coupon.

A significant amount of detail and pre-checkout activities should be applied to the testing cell itself in order to minimize leakage. Methods for reducing contact resistances should also be stressed in order to optimize performance of the cell under test conditions. In spite of these drawbacks in this test series, the potential for the material was demonstrated.

SECTION 4.0

CONCLUSIONS

This investigation has confirmed that certain material compositions from the new ceramic systems studied herein do indeed possess superior ionic conductivity characteristics in relation to other oxygen ion conducting materials that are candidates for fuel cell electrolytes (e.g., zirconia-based systems). These superior characteristics would provide excellent ionic conductivities at relatively low temperatures (600 - 850°C), thereby allowing a fuel cell system to take advantage of the enhanced voltage driving forces and start-up implications associated with these temperatures.

The attractive ceramic materials from an ionic conductivity point of view are a binary metal oxide system as well as a cross-doped (ternary) version of this system. However, when stability characteristics are taken into account (see below), the binary system is the material of choice at the present time. A certain composition range for this binary system has been identified as desirable for emphasis in follow-up studies.

The coefficient of the thermal expansion has been determined as a function of temperature for one of the attractive ceramic compositions that is a focus of attention in this investigation. The thermal expansion characteristics of this material were found to be reasonably compatible with those of various suitable sealing and structural materials over the temperature range of interest.

Thermogravimetric studies have shown that weight losses in a reducing atmosphere (hydrogen) are significant for the material compositions of interest. This is also the case where the reducing gas is humidified to a level that reflects typical inlet concentrations in fuel gases (e.g., steam-reformed natural gas). However, analysis has also shown that such tendencies can be suppressed in an operating fuel cell system. This can be accomplished by either sustaining a high H_2O/H_2 ratio at the fuel cell anode (e.g., by employing anode gas recycle) or maintaining the fuel cell current density

above certain minimum levels. The oxygen ion migration from cathode to anode in an operating fuel cell will tend to counteract the eductive loss of oxygen atoms from the metal oxide lattice at the anode; based on the thermogravimetric results of this study for one of the candidate electrolyte materials, it is estimated that the current density required to prevent reductive loss of oxygen atoms would be only 4-55 mA/cm² over the temperature range 600 to 850°C. This would represent but a small fraction of the current densities expected to be realizable with these materials; e.g., at a current density of 1000 mA/cm² at 800°C it is projected from the ionic conductivity data for the above material that the IR-loss across a 1-mil thick electrolyte layer would be only about 85.mV.

Methodology for applying electrode layers to both surfaces of ceramic electrolyte disks has been worked out successfully. Such layers have shown mechanical and chemical stability at operating temperature, good adhesion, and capability of carrying high current densities (1-2 A/cm²) over tens of hours with no degradation. Platinum layers deposited from a suspension of finely ground metal in an organic medium are currently the electrodes of choice. Suitable firing temperatures have been determined, and compromises between electronic conductivity and porosity have been explored. Further optimization is required, including establishment of acceptable platinum loading levels with regard to cost and the associated power density.

The designs of coupon-type cell structures and associated test fixtures have drawn upon experience acquired by other researchers in the ceramic electrolyte field; however, the mechanical integrity of the cell samples could not be maintained during this phase of the program because of (i) the extremely thin electrolyte layers (about 0 .001 inch) that are the target of this technical approach, (ii) thickness non-uniformity in the coupon cell, and (iii) differential thermal expansion among the components of the test apparatus (cell, fixture, and facility). Schemes for decoupling of these influences and allowing cells with such thin electrolyte layers to be tested have been proposed for implementation in follow-on studies.

The projected stability of the ceramic electrolyte materials in fuel cell anode environments under actual cell operating conditions could not be confirmed experimentally (as discussed above). On the other hand, the ceramic electrolyte sample preparation methodology per se was successfully applied, as evidenced by the attractive ionic conductivity results obtained. Nevertheless, rate-controlled sintering studies have shown that significant improvement in properties can be realized through optimization of preparation and sintering methodologies.

END

**DATE
FILMED**

01 / 23 / 92

()