DOE/ER/54115--T1

**ANNUAL TECHNICAL REPORT
for the DOE Research Grant**

DOE/ER/54115--T1

DE92 003397

**RADIATION EFFECTS AND MICROMECHANICS
OF
SiC/SiC COMPOSITES**

**DOE Grant No. DE-FG03-91ER54115
for the period
December 1, 1990 through November 14, 1991**

**Nasr M. Ghoniem
Principal Investigator**

**Mechanical, Aerospace and Nuclear Engineering Department
University of California, Los Angeles 90024-1597
Telephone: (213) 825-4866**

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

MASTER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

pp

1. SUMMARY OF OVERALL PROGRESS

The development and use of SiC/SiC composite structures will achieve the following benefits to the fusion program:

1. Improved high-temperature energy conversion in the blanket modules, resulting in improved cost of electricity;
2. Enhanced feasibility for passive safety features in case of operational or intentional accidents;
3. Reduced amount of radioactivity and beneficially changed decay characteristics.

We report here our progress made on fundamental understanding of displacement damage in SiC, and on microstructure evolution under fusion irradiation conditions.

1.1 Collision Cascade Simulations

The displacement-damage energies for the silicon and carbon atoms in silicon carbide were not known before we started this research effort. The directional bonding and differences in interatomic potentials of the silicon and carbon atoms result in unequal and anisotropic displacement-damage threshold energies. Since this basic knowledge does not exist, displacement-damage correlations can be highly uncertain, as are projections to fusion conditions.

The silicon and carbon are diamond-like structures, with atoms joined to four nearest neighbors at tetrahedral angles. The elements C and Si lack four electrons with respect to filled shells, and thus can have an attractive interaction associated with charge overlap.

Molecular Dynamics (MD) computer simulations of focused cascades along the $[111]$ direction at 10 K show that although the cascade is perfectly focused along the initial direction, replacement collision sequences are not likely to occur. Instead, the cascade displays a repetitive character along the focusing direction and the displaced atoms reside within the same unit cell in hexagonal interstitial sites.

In general, displacements are observed to take place through the $\langle 111 \rangle$ gaps only. Si atoms have significantly higher displacement thresholds than C atoms for the same direction. Figure 1 shows the displacement energies for Si (Fig. 1-a) and C (Fig. 1-b) PKA's for some selected directions within the $\langle 111 \rangle$ gap.

The major conclusions from this study are summarized below.

1. The propagation time of low energy cascades in β -SiC is about one order of magnitude shorter than similar cascades in metals. This can be interpreted in terms of a stiffer crystal binding potential in case of SiC, as compared to metals. The collisional phase of cascade evolution ends in about 0.03 to 0.04 ps.
2. The stability of the β -SiC crystal structure under cascade conditions is strongly dependent on the three-body contribution to the interatomic potential, because it brings in the covalent nature of the interatomic bonding.
3. The results have shown that under all conditions, displacements always take place through the $\langle 111 \rangle$ gaps. Focusing can contribute to point defect production but replacement collision sequences are not likely to occur.
4. In the case of a focused cascade, displaced atoms come to equilibrium within the same unit cell. The vacancy and interstitial can be separated by larger distances in case of non-focused cascades. In all cases, displaced atoms come to equilibrium in hexagonal interstitial sites.
5. The displacement threshold of a Si atom is significantly higher than that of a C atom. This results in additional C atoms being displaced by a Si PKA. The number of these additional C displacements depends on the PKA energy and the initial direction. Therefore, the final cascade configuration is expected to be highly non-stoichiometric with the majority of displaced atoms being of the carbon type.
6. The MD simulation results using Pearson potential predict that hexagonal sites are the most stable positions for interstitial atoms. This is in agreement with perturbation calculations reported for the zincblende-type structure using pseudo-potentials.
7. Our MD results agree with the irradiation experimental data for β -SiC. The interstitials come to equilibrium in the hexagonal sites between the (111) planes, where clustering of these atoms in the form of dislocation loops is possible. Such loops were observed in transmission electron micrographs of irradiated SiC.

1.2 Microstructure Evolution

Many experimental observations of radiation effects on microstructures have been made in a number of irradiation facilities. However, little data exist on the use of SiC composites for structural materials. Ongoing and planned irradiation experiments on SiC/SiC FRCs will provide this valuable data base to assess the radiation stability of this class of materials and to determine the feasibility of their use. Because purely empirical extrapolations to fusion-reactor conditions are unreliable, further development of higher performance composites must rely on an increased fundamental understanding of some of the most basic radiation-effects mechanisms.

We started an effort on modeling swelling in SiC under fusion conditions. The first step in this direction has been to model the radiation stability of cavities as a result of absorption of point defect and helium fluxes.

Nucleation and growth of helium-filled cavities is modelled by dynamical equations of the Langevin-type. The growth/shrinkage of a cavity is given in terms of two equations representing the rates of change of the net number of vacancies and of helium atoms inside the cavity. The equations describe the drift-diffusion motion of cavities in a two-dimensional phase-space under the influence of point defect and helium absorption, and include the stochastic effects of cascades. First, the linear stability of these equations are determined to identify the nature of the singular points in phase-space. Asymptotic equations are then derived for the separatrices around the singular points. Typical trajectories for cavity growth in SiC under fusion irradiation conditions are shown. In this regard, we give data evaluation considered for helium and displacement damage generation in SiC in different irradiation facilities. Equivalent Fokker-Planck equations are used to analyze the probabilities of bimodal distributions, and that of unstable cavity growth leading to excessive swelling rates. the appropriateness of fission and ion beam irradiation data to the simulation of cavity stability in anticipated fusion conditions will also be studied.

2. ANTICIPATED UNEXPENDED BALANCE

It is anticipated that no unexpended balance will exist at the end of the first year funding period (November 14, 1991). At the level of \$100,000 for the period November 15, 1991 through November 14, 1992, we expect delays in the implementation of the second year plan, which was originally approved at \$180,000.

As discussed with Dr. Wiffen at OFE, the experimental portion of the program will be shifted to the following fiscal year, or until other funding is made available during the 1991/1992 fiscal year.

3. LIST OF REPRINTS

1. A. El-Azab and N. M. Ghoniem, "Molecular Dynamics Simulations of Low Energy Cascades in β - SiC," presented at the IEA Workshop on the Use of Molecular Dynamics in Modeling Radiation Effects and Other Non-Equilibrium Phenomena, May 6-8, 1991, La Jolla, California, to appear in *Radiation Effects and Defects in Solids*.
2. A. El-Azab and N.M. Ghoniem "Stability of Frenkel Pairs in SiC," abstract accepted in the proceedings of the Fifth International Conference on Fusion Reactor Materials, (ICFRM-5).
3. N. M. Ghoniem, "High-Temperature Mechanical and Material Design for SiC Composites," *ibid*, ref. 2.
4. H. Huang and N.M. Ghoniem, "Linear Stability Analysis of Helium-Filled Cavities in SiC," *ibid*, ref. 2.

END

**DATE
FILMED**

12/13/191