Association for Information and Image Management
 1100 Wayne Avenue, Suite 1100
 Silver Spring, Maryland 20910
 301/587-8202

Centimeter

Inches

MANUFACTURED TO AIM STANDARDS
 BY APPLIED IMAGE, INC.

1 of 1

UHV-STEM STUDIES ON NUCLEATION AND GROWTH OF THIN METAL SILICIDE FILMS ON SILICON

DOE GRANT DE-FG02-87ER45322

J. Silcox and E.J. Kirkland, Co-PI's

Progress Report 6/12/90 - 12/31/92

CONTENTS

Summary	2
Accomplishments	4
References	17
Publications	18
Student Status	20
Reprints <i>Removed.</i>	21

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

MASTER

SUMMARY

The work carried out under this program centers on the exploitation of the multiple imaging and spectroscopy operating modes of an ultra-high vacuum scanning transmission electron microscope. In the proposal submitted in 1989 and as slightly modified in 1990 in response to new developments, three general topics were identified as research themes, i.e., single atom structures on silicon, grain boundaries in Ni_3Al and the simulations necessary to interpret the observations. In addition, two students were projected to complete Ph.D. studies and a changeover to new students was identified. We provide first a brief listing of the key advances reported since initiation of the current support and then review the work in somewhat more detail.

The key advances are:

- Development of a "frozen phonon" model for electron scattering and comparison with experimental energy filtered convergent beam electron diffraction measurements giving good agreement with calculated patterns (see reprint #1).
- Determination of the coefficient of spherical aberration C_s , and calibration of the defocus, $\Delta f(I)$, where I is the objective lens current, using bright field amorphous carbon images (supported partially by the Department of Energy).
- Use of both of the first two advances in studies of through focal series annular dark field images of (100) InP. These demonstrated first that the incoherent imaging model describes zone axis annular dark field imaging well in both experimental and simulated images and second that it is possible to extract

effects due to the instrument and to expect to retrieve image intensities with improved accuracy (see reprint #2).

- Continued simulation studies have indicated that effects in the atom site intensities are likely to be due to channeling peaks propagating unequal distances along the zone depending on the atomic numbers of the atoms making up the atomic column. Experiments under way support this view.

- Studies of the growth of gold and silver films on hydrogen passivated silicon surfaces reveals good epitaxial growth for silver on both (111) and (100) substrates. Gold grows on (111) Si with the (111) planes parallel with Si (111). Although the azimuthal Au(110) parallel to Si(110) is favored, domains with random azimuthal orientation are also present.

- Work on grain boundaries in nickel aluminum compounds has been initiated in collaboration with Professor S.L. Sass. We have demonstrated that boron is present at grain boundaries in appropriate material through electron energy loss spectroscopy. We have also detected and measured changes in the d-band density-of-states at the boundary. This represents proof that the experiments initially proposed are feasible.

- Two Ph.D. theses (P. Xu and R. Loane) were completed and approved. In addition, the software we have developed has attracted interest and it has been ported to the 'Electrotechnik' department at the University of Duisburg and to the Fritz Haber Institute in Berlin (both in Germany).

ACCOMPLISHMENTS

Over the past grant period, our scanning transmission electron microscopy studies have moved from the qualitative level to a quantitative level. While much still remains to be done, it is now evident that the key steps have now been successfully accomplished. The critical experimental step was accomplished during the grant period previous to this one when Dr. Kirkland completed interfacing our microscope to a VAX 3200 work station. The fruits of that move are evident in the work accomplished during this grant period. On the simulation side, the key step undertaken during this grant period was modification of the simulations to include thermal diffuse scattering. Comparison with experiments demonstrated that the simulations gave an excellent quantitative description of both diffraction and image intensities. With this basis, we can now develop quantitative approaches to determination of microstructural arrangements, microchemistry and microelectronic structure.

When the initial proposal on which the work described here is based was written, we based our simulation work (Kirkland, et al. (1987); Loane, et. al. (1988)) on multi-slice based calculations of a perfect lattice. Wang and Cowley, (1989) based on the work of Wang (1989), then pointed out that most (i.e. ~90%) of the intensity reaching the annular detector arises from thermal diffuse scattering rather than from Bragg scattering (i.e., from HOLZ lines, see e.g., Spence, et al. (1989)) and thus an accurate simulation should include this. Earlier comparisons between experiment and simulation that we had made (Kirkland, et al. (1989)) were consistent with this conclusion. We had judged this, i.e., including the effects in the simulation, to be a low priority objective since the evidence we had suggested that this was not a significant factor in the imaging intensities. We still think this may be true. However, these papers made it clear that our simulation effort had to include thermal diffuse scattering in

order to be taken seriously. Accordingly, we modified our initial proposal to include thermal diffuse scattering in the simulation .

We adopted a Monte Carlo approach in which the atoms were each displaced from the lattice points by a random amount consistent with the probability of displacement known from thermal diffuse scattering studies. This generates a disordered atomic array with the atoms displaced slightly from the perfect lattice. If the multislice calculation is now carried out, each calculation integrates that randomness over the number of slices in the model film. We found that 16 arrays were adequate to give an average scattering with a sufficiently low noise level for comparison with experiment. An Einstein model was used and excellent agreement was found. The first paper (Loane, et al. (1990) included as reprint #1 with this report) focused on obtaining a overall prediction of intensity levels covering a range of approximately four orders of magnitude. The logarithm of the intensities in the simulated and observed CBED patterns are displayed as false color patterns in reprint #1. Following this work, some troubling minor discrepancies (background levels and rocking point adjustments) were resolved (Xu, et al. (1991)) and the average atomic displacement, $\langle u \rangle$, found to be $0.0078 \pm 0.0002 \text{ nm}$ in agreement with the best X-ray value of $0.00764 \pm 0.00002 \text{ nm}$ reported by Alldred and Hart (1973). Figure 1 illustrates the nature of this agreement.

The approach taken within this calculation has a number of advantages for this program. It is well suited to a computational approach. Very few analytical approximations need be made. It automatically fits multi-phonon conditions provided that the incident electron wave packets have a sufficient energy spread (approximately 250 meV) to integrate over the full phonon spectrum or, as expressed in the paper, interact with the atom for a time significantly shorter than an atomic vibration period. The Einstein model is simple and minimizes the computational demands. The

Figure 1: Logarithmic plots of azimuthally integrated intensities measured for silicon (100) CBED patterns. The calculation curve was matched to the zero-loss curve by multiplying with a scaling constant. The unfiltered curve was right on top of the zero-loss curve and has been raised by a factor of x10 to better show the match between the calculation and the zero loss curves. From Xu (Ph.D. thesis, 1992). See also Loane, et al. (1992).

discrepancies due to neglect of the atomic displacement correlations seem minor (although in some circumstances they could be informative in determining the anisotropy or the correlation of atomic displacements) and can certainly be disregarded to first order in simulation studies of STEM imaging.

Encouraged by this we moved on to look carefully at annular dark field imaging (ADF) of zone axis crystals. The advantages of such an imaging mode have been widely discussed since the first atomic resolution images were obtained (e.g., Pennycook and Boatner (1988); Pennycook (1989)). These advantages include Z-contrast, independence of focal length and a much simpler interpretative basis. The advantage of higher spatial resolution than that available with the bright field phase contrast mode was demonstrated by work supported through this program during the period immediately prior to the current one (Xu, et al. , 1990). However, many questions really remain to be answered concerning ADF STEM. Does the imaging truly reflect the incoherent imaging model? There is no direct proof of this. How does the image change with defocus, particularly for a compound? With depth in the crystal? With orientation? And with detector configuration (particularly the inner angle)? In our view, the existing work was qualitative yet if a truly quantitative basis could be established and suitable limits placed on the imaging, such images would be very valuable.

The simplest of these questions to tackle was the effect of defocus. The primary results of this work (Loane, et al. (1992)) are included as reprint #2 in this package. Two questions were addressed in this work. How well are both the simulated and the experimental images described by the simple incoherent imaging model? If this is a good description , are these described well by an electron probe of the type normally calculated? The short answer to both of these questions is yes but this response does have some interesting and apparently unexpected implications.

Specifically, the electron probe can be described in terms of the normal model. To achieve this, it was first necessary to measure the coefficient of spherical aberration of the lens, C_s , and to calibrate the defocus, $\Delta f(I)$, as a function of the lens current. Although such measurements had been approached earlier by the use of Ronchigrams (Lin and Cowley (1986)), no measurements had been carried out by analysis of bright field phase contrast micrographs of amorphous carbon films which is the normal way of achieving this end in conventional transmission electron microscopy. The implementation of the unique VAX 3200 digital acquisition and recording system carried out previously in this program together with careful attention to the detector system to ensure a wide range of intensity recording, enabled us to record such images over a wide range of intensities. Recording the intensities directly into the computer permitted Fourier Transform analysis of the images almost immediately and an extensive determination of the operating parameters. Figure 2 illustrates the data obtained. During the course of this undertaking, a paper on similar work appeared (Hammel, et al. (1990)) but since it did not use a sufficiently small collection aperture (4 mrad as opposed to 0.6 mrad in our work) with correspondingly lower intensities, it did not achieve the analysis level reported here (Wong, et al. (1992)). All the active students in the group were involved in this as a training exercise. Hence support for this work was credited only partially to DOE.

Given the calibration of the instrumental performance as indicated in the previous paragraph, intensities as a function of defocus for zone axis images could then be determined. The specimen selected was (100) InP which in projection comprises two interpenetrating square lattices of In and P respectively. Under high resolution conditions, two spatial frequencies appear at $(2 \cdot 9 \text{ \AA})^{-1}$ and $(2 \cdot 1 \text{ \AA})^{-1}$ respectively. Both spacings are within our demonstrated resolution limit of $\sim 1 \cdot 8 \text{ \AA}$ (see Xu et al. (1990))

Figure 2: (a) The azimuthally integrated power spectrum of an amorphous carbon film image with the rings indexed. (b) n/k_n^2 plotted as a function of k_n^2 . See Wong, et al. (1992) for more details.

and the two atomic columns provide a significant Z difference of 49 (In) versus 15 (P). In principle, the phosphorus columns are within our spatial resolution limits. In fact, we did not resolve those columns because the signal from the neighboring In atoms swamped that from the phosphorus. We note that bright field phase contrast microscopy has already been used to image the phosphorus columns (Ourmazd, et al. (1986)). Thus it is not clear that ADF STEM is the answer to every problem. It is likely to be most powerful when used in concert with other techniques. We do find the ability to record bright field and dark field images simultaneously (and in perfect registration) to be of considerable value in general.

With specimens of this type, it has been possible to record through focal series containing a large number of images. Since the images are recorded directly into memory (and displayed only after recording) it is possible to undertake considerable analysis. For example, a power spectrum of each image in the sequence can be determined, thus determining the intensity in each spatial frequency for each defocus value. Figure 3 is an experimental plot showing the variation of the two fringe intensities as a function of defocus. The fringe intensities do undergo quasi-periodic changes with defocus and the two fringes behave differently. Thus, although ADF STEM is simpler than bright field phase contrast, it cannot be used without some image analysis if quantitative data is needed. A similar plot is shown in figure 4 for simulations of the same system. The lines running through this data are the predictions of the incoherent imaging model given the necessary parameters. This work provides primary evidence for the validity of the incoherent imaging mode (which lacks a really solid analytical foundation).

The primary contributors to most of the above work were R. Loane and P. Xu and the work was described in their Ph.D. theses. A review of this work has just

Figure 3: Fringe amplitudes extracted from the defocus series of ADF STEM images of indium phosphide (100). The top plot displays the two 2.9 Å crossed fringes. The bottom plot displays the two 2.1 Å crossed fringes. For more details, see Loane, et al. (1992).

Figure 4: Match between fringe amplitudes (data points) determined from simulations and the predictions of the incoherent model (solid lines) determined by the contrast transfer function for (a) the Scherzer imaging aperture and (b) a larger aperture. For more details, see Loane, et al. (1992).

appeared (Silcox, et al., 1993). Dr. Loane was responsible for much of the simulation work while Dr. Xu was responsible for most of the experimental work. In addition, Dr. Xu worked on the nucleation and growth of gold and silver films on silicon surfaces. As noted in our renewal proposal, the preparation chamber, as supplied by the company, was inadequate for the task and an improved version, built and designed at Cornell, had to be installed for this work to proceed successfully. During this grant period, that was accomplished and Dr. Xu completed a series of studies of the growth of Au and Ag films on hydrogen terminated surfaces (see attached reprint #3). Auger analysis was used in-situ to demonstrate that the initial surface had low contaminant levels (except for the hydrogen which could not be detected).

These results show that for these systems, the growth modes at room temperature and epitaxial relations for the H-passivated layer are very similar with the results obtained in UHV. Since these surfaces have potential application in silicon MBE, this was a useful result. More specifically the results indicate that the room temperature growth of gold on silicon is really a layer growth albeit imperfect. Silver still reflects a layer + island growth with however an island density as high as $4 \times 10^{12} \text{cm}^{-2}$. A good epitaxial relationship between the silver and the silicon was observed for both silicon (111) and (100) substrates whereas gold (111) grows on silicon (111) with azimuthally rotated grains.

Two students, David Muller and Sean Hillyard have joined the research program under this grant. Mr. Muller is supported directly as a research assistant whereas Mr. Hillyard holds a Department of Education graduate fellowship. Mr. Hillyard has become interested in following up on the work of Drs. Loane and Xu on the nature of the ADF imaging whereas Mr. Muller picked up on the problem of the chemical composition and electronic structure of grain boundaries in Ni_3Al proposed for study in

1989. Both students have made excellent beginnings which we review briefly here. Examples of the work are mostly left to the renewal proposal since they more properly illustrate the directions this work would take over the next years if the support is renewed.

Mr. Hillyard has picked up on Mr. Loane's Ph.D. thesis predictions that the electron probe at zone axis incidence is both channeled and scattered once inside the crystal. In the [100] indium phosphide, for example, the electron beam is channeled into peaks on either the phosphorus or indium atomic columns. If the beam is incident on the phosphorus column it propagates for a long distances whereas on the indium column it travels perhaps 100 to 200Å before it disappears. This result clearly reflects anomalous absorption and is significant in X-ray fluorescence microanalysis (see e.g. Chems, et al. 1973) as well as (most likely) electron energy loss spectroscopy studies. The effect is illustrated in Figure 5. It should show up in the annular dark field imaging since the ADF scattering from the indium atoms should saturate while that from the phosphorus should grow. The simulations are consistent with this conclusion and a discussion of this is in press (Hillyard, et al., 1993). Experimental evidence has very recently become available to confirm this analysis but has not yet been submitted for publication.

Mr. Muller has developed a valuable working relationship with Ms. S. Subramanian, a student in Prof. S.L. Sass' group and has made a number of studies of Ni_3Al containing boron. Specifically, he has learnt first that with clean surfaces, Ni_3Al damages very readily through the loss of aluminum. If coated by carbon elsewhere through contamination, however, extended observation of the sample is possible. Using X-ray fluorescence observations he has demonstrated nickel enrichment at a grain boundary in an amount approximately equivalent to one additional layer of nickel.

Figure 5: Simulated channeled intensity thickness series of indium phosphide (100) for two probe positions. Probe positioned on indium (left) and phosphorus (right). Thicknesses are (a,b) 35 Å, (c,d) 70 Å, (e,f) 106 Å, and (g,h) 211 Å. See Hillyard et al. (1993) for more details.

Boron has been detected within 1nm of the boundary through serial imaging electron energy loss spectroscopy. Finally, a difference in the nickel L_{2,3} edge at the boundary relative to the grain interior has been related to changes in the d-band density of states at the boundary. All of these were projected as feasible in the renewal proposal submitted in 1989 and have now been clearly demonstrated. Comparative studies on boron-free material will be undertaken prior to preparation of this material for publication.

The publications listed in the publications section of this report can be consulted for further details on the major steps forward cited briefly above on all of the areas suggested in the 1989 renewal proposal.

REFERENCES

- P.J.E. Aldred and M. Hart, *Proc. R. Soc., London A332*, 239 (1973).
- D. Cherns, A. Howie and M.H. Jacobs, *Z. Naturforsch* 28a, 565 (1973).
- M. Hammel, C. Colliex, C. Mory, H. Kohl and H. Rose, *Ultramicroscopy* 34, 257 (1990).
- S. Hillyard, R.F. Loane and J. Silcox, *Ultramicroscopy*, in press (1993).
- E.J. Kirkland, R.F. Loane and J. Silcox, *Ultramicroscopy* 23, 77 (1987).
- E.J. Kirkland, R.F. Loane, P. Xu and J. Silcox, in "Computer Simulation of Electron Microscope Diffraction and Images," Eds. W. Krakow and M. O'Keefe (Minerals, Metals and Materials Sci., New York, 13 (1989).
- J.A. Lin and J.M. Cowley, *Ultramicroscopy* 19, 31 (1986).
- R.F. Loane, E.J. Kirkland and J. Silcox, *Acta. Cryst. A44*, 912 (1988).
- R.F. Loane, P.J. Xu and J. Silcox, *Acta. Cryst. A47*, 267 (1991).
- R.F. Loane, P.J. Xu and J. Silcox, *Ultramicroscopy* 40, 121 (1992).
- A. Ourmazd, J.R. Reutschter and D.W. Taylor, *Phys. Rev. Lett.* 57, 3073 (1986).
- S.J. Pennycook and L.A. Boatner, *Nature* 336, 565 (1988).
- S.J. Pennycook, *Ultramicroscopy* 30, 58 (1989).
- S.J. Pennycook and D.E. Jesson, *Phys. Rev. Lett.* 64, 938 (1990).
- J. Silcox, P. Xu, and R.F. Loane, *Ultramicroscopy* 47, 173 (1992).
- J.C.H. Spence, J.M. Zuo and J. Lynch, *Ultramicroscopy* 31, 233 (1989).
- Z.L. Wang and J.M. Cowley, *Ultramicroscopy* 31, 437 (1989).
- Z.L. Wang, *Acta. Cryst. A45*, 636 (1989).
- K. Wong, E.J. Kirkland, P. Xu, R.F. Loane and J. Silcox, *Ultramicroscopy* 40, 139 (1992).
- P. Xu, R.F. Loane and J. Silcox, *Ultramicroscopy* 38, 127 (1991).
- P. Xu, E.J. Kirkland, J. Silcox and R. Keyse, *Ultramicroscopy* 32, 93 (1990).

PUBLICATIONS RECORD

P. Xu, "Imaging of Silicon (111) at 1.92Å Resolution Using a 100 keV STEM," Proc. XII International Congress for Electron Microscopy (San Francisco Press, 1990), p. 34.

R.F. Loane and J. Silcox, "Thermal Vibrations in Simulated ADF STEM," Proc. XII International Congress for Electron Microscopy (San Francisco Press, 1990), p. 396

E.J. Kirkland, "Computer Image and Spectrum Acquisition on an HB501A STEM," Proc. XII International Congress for Electron Microscopy (San Francisco Press, 1990) p. 148.

E.J. Kirkland, "An Image and Spectrum Acquisition System for a VG HB501 STEM Using a Color Graphics Workstation," Ultramicroscopy 32, 349-364 (1990).

R.F. Loane, P. Xu and J. Silcox, "Thermal Vibrations in Convergent Beam Electron Diffraction," Acta Cryst. A47, 267-78 (1991).

P. Xu, P. Miller and J. Silcox, "The Nucleation and Epitaxial Growth of Au and Ag on Thin Silicon Studied with a Scanning Transmission Electron Microscope," Proc. Mat. Res. Soc. 202, 19-24 (1991).

P. Xu, R.F. Loane and J. Silcox, "Energy Filtered Convergent Beam Electron Diffraction in STEM," Ultramicroscopy 38, 127-33 (1991).

P. Xu, R. Loane and J. Silcox, "Silicon Vibration Amplitude Determined by Energy-Filtered CBED," Proc. 49th Annual Meeting of the Electron Microscopy Society of America, ed. G.W. Bailey (San Francisco Press, 1991), pp. 790-91.

R.F. Loane, P. Xu and J. Silcox, "Incoherent Imaging of Zone Axis Crystals with ADF STEM," Ultramicroscopy, 40, 121-138 (1992).

K. Wong, E.J. Kirkland, P. Xu, R.F. Loane and J. Silcox, "Measurement of Spherical Aberrations in STEM," Ultramicroscopy, 40 139-150 (1992) [Partial D.o.E. Support].

J. Silcox, P. Xu and R.F. Loane, "Resolution Limits in Annular Dark Field STEM," Ultramicroscopy, 47, 173-186 (1992).

P. Xu, "Scanning Transmission Electron Microscopy Studies of Silicon and Epitaxial Growth of Gold and Silver on H-Terminated Silicon," Ph.D. Thesis, May 1991.

R.F. Loane, "Annular Dark Field Scanning Transmission Electron Microscopy of Crystals," Ph.D. Thesis, August 1991.

S. Hillyard, R.F. Loane and J. Silcox, "Annular Dark Field Images of Crystals," Proc. 50th Annual Meeting of the Electron Microscopy Society of America, ed. G.W. Bailey (San Francisco Press, (1992), 1222-1223.

S. Hillyard, R.F. Loane and J. Silcox, "Annular Dark Field Imaging: Resolution and Thickness Effects," *Ultramicroscopy*, to appear (1993).

Invited Lectures 2/1/90 - 12/31/92

"A(nnular) D(ark) F(ield) STEM: A New Mode of Imaging," J. Silcox, Case Western Reserve University, Department of Materials Science and Engineering, Fall 1990 Colloquium Series, September 4, 1990.

"Resolution Limits in Annular Dark-Field STEM," J. Silcox, 49th Meeting of the Electron Microscopy society of America, San Jose, August 1991.

"The Many Faces of STEM in Materials Science," J. Silcox, 49th Meeting of the Electron Microscopy Society of America, San Jose, August 1991.

"Nanoscopic Studies of Ceramics," J. Silcox, The International Workshop on Science and Technology of Thin Films for the 21st Century, Northwestern University, July 1991.

"Annular Dark Field Images of Crystals," J. Silcox, 50th Meeting of the Electron Microscopy Society of American, Boston, August 1992

"Analytical Electron Microscopy," J. Silcox, Workshop on Quantitative Electron Microscopy, Berkeley, August 1992.

"Scanning Transmission Electron Microscopy for Materials," J. Silcox, Workshop on Grain Boundaries in High T_c Superconducting Oxides, Madison, Wisconsin, Sept. 1992.

"Towards Quantitative STEM," J. Silcox, Symposium in Honor of Sir Peter B. Hirsch, Oxford, U.K., Sept. 1992.

Graduate Student Status

Graduated Students

P.Xu: Thesis title: "Scanning Transmission Electron Microscopy Studies of
 Ph.D. Silicon and Epitaxial Growth of Gold and Silver on H-Terminated Silicon"
 May 1991 Current Position: Research Associate with Prof. L. Marks, Northwestern
 University

R. Loane: Thesis title: "Annular Dark Field Scanning Transmission Electron
 Ph.D. Microscopy of Crystals"
 August 1991 Current Position: One of two co-founders of a software company,
 "Password, Inc." in Baltimore, Maryland

New Students

D. Muller: B.Sc., M.Sc., University of Sydney, Australia. Co-authored seven articles
 during B.S. and M.S. residency. Double major in physics and computer
 science.
 Estimated Graduation Date: Summer, 1995

S. Hillyard: B.S. Caltech. Holds a Department of Education Fellowship. Partial
 association with the program.
 Estimated Graduation Date: Summer, 1994

REPRINTS

1. R.F. Loane, P. Xu and J. Silcox, "Thermal Vibrations in Convergent Beam Electron Diffraction," Acta Cryst. A47, 267-78 (1991).
2. R.F. Loane, P. Xu and J. Silcox, "Incoherent Imaging of Zone Axis Crystals with ADF STEM," Ultramicroscopy, 40, 121-138 (1992).
3. P. Xu, P. Miller and J. Silcox, "The Nucleation and Epitaxial Growth of Au and Ag on Thin Silicon Studied with a Scanning Transmission Electron Microscope," Proc. Mat. Res. Soc. 202, 19-24 (1991).

**DATE
FILMED**

8 / 19 / 93

END