DOE/PC/90176--T50
1

DEC 3

DOE/PC/90176--T50

DE92 004186

FINAL TECHNICAL REPORT
September 1, 1990 through August 31, 1991

Project Title: Ultrasound-Promoted Chemical
Desulfurization of Illinois Coals

DE-FG 22-90PC 90176

Principal Investigator: Dr. Sherman S. Chao, IGT
Co-Investigator: Mr. Michael C. Mensinger, IGT
Project Manager: Dr. Daniel D. Banerjee, CRSC

ABSTRACT

To meet the stringent requirements of State and Federal regulations on the emissions of sulfur oxides from coal combustion facilities, the sulfur content of Illinois basin coals must be reduced considerably before the coal can be utilized. Many processes that claim to remove both pyritic and organic sulfur generally operate at relatively severe conditions, which destroys a fraction of the more desirable coal material. Ultrasound has been shown to increase the rates of some chemical reactions by many orders of magnitude at conditions much less severe than if the process were conducted without ultrasound. The overall objective of the work was to determine the efficacy of ultrasound for promoting chemical reactions that remove sulfur from coal in liquid phase at relatively mild conditions.

Two model compounds (dibenzyl sulfide [DBS] and dibenzothiophene [DBT]) impregnated on a carbon substrate and the IBC-101 coal from the Illinois Basin Coal Sample Program were used in this study. A number of agents, oxidizing chemicals and hydroperoxide precursors, were employed to react with sulfur species in a variety of liquid-phase media. Most of the desulfurization tests were conducted in a low-intensity ultrasonic bath unit and a pressurized bench-scale high-intensity ultrasonic unit.

The results of tests with model coals showed that DBS can be oxidized to its oxides more readily than DBT. As much as 70% of the DBS and 9% of the DBT can be converted to their oxides at 75°C. Of the reagents tested, hydrogen peroxide (H_2O_2) and tert-butyl hydroperoxide (TBPO) in acetic acid (HOAc) solution with $Mo(CO)_6$ catalyst were the most effective for oxidation of DBS and DBT.

Two most promising aqueous reagent systems for coal desulfurization were identified. They are H_2O_2 /HOAc and TBPO/NaOH. An ultrasonic reactor run under 100 psig air pressure resulted in a reduction of 92% pyrite sulfur, 12% organic sulfur and 33% total sulfur. Hydroperoxide precursors as non-aqueous solvents, such as tetralin, with ultrasound under 100-200 psig oxygen pressure also convert a large amount of pyrite and remove a small amount of organic sulfur.

Ultrasound apparently promotes desulfurization reactions through its kinetic effect of transporting oxidants onto the sulfur sites of the sample, although no specific sonochemical mechanisms are identified. A 40% to 50% increase in the rate of DBT conversion was observed. Potential ultrasonic desulfurization schemes were selected for future studies. The developed processes provide effective means for partial sulfur removal with only a slight alteration in the coal properties.

MASTER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

(This project is funded by the Illinois Department of Energy and Natural Resources as part of its cost-shared program with the U. S. Department of Energy.)

EXECUTIVE SUMMARY

This report presents the results of work conducted by the Institute of Gas Technology (IGT) from September 1, 1990 through August 31, 1991 on the program "Ultrasound-Promoted Chemical Desulfurization of Illinois Coals." The work was sponsored by the Center for Research on Sulfur in Coal (CRSC) under Contract No. CRSC90-08. The overall objectives of the program were to determine the efficacy of ultrasound for promoting chemical reactions that remove organic sulfur from coal in liquid phase at relatively mild conditions, and to evaluate sonochemical coal desulfurization schemes under mild conditions through a fundamental understanding of the reaction mechanisms and kinetics.

To meet the stringent State and Federal standards for clean air and regulations on the atmospheric emission of sulfur dioxide from coal combustion facilities, extensive research has been conducted on methods for removing sulfur, particularly organic sulfur, from coal prior to combustion. Illinois basin coals (IBC) contain relatively high concentrations of sulfur, most of which must be removed before the coal can be used. Currently, quantitative removal of organic sulfur by physical, chemical, and microbial means is neither feasible nor effective, except under severe processing conditions, which destroy the desirable coal structure and reduce its calorific value.

Ultrasound has been shown to increase the rates of some chemical reactions by many orders of magnitude at conditions much less severe than if the process were conducted without ultrasound. Ultrasound also provides an effective way to physically disintegrate, segregate and remove finely disseminated pyrite crystals and other minerals from the coal, exposing additional sulfur sites for chemical reaction. Microstreaming, one of the phenomena associated with ultrasonic irradiation, transports chemical reagents onto the sulfur sites, eliminating the need to use concentrated reagents for desulfurization. Ultrasonic cavitation generates intense shock waves and localized heating on particle surfaces, which may direct specific reactions on S-heteroatoms in the organic structure through alternative pathways, depending on thermodynamic properties and reaction kinetics. The appropriate application of ultrasonic energy could direct and accelerate desulfurization reactions under conditions much milder than those normally required, thus retaining much of the original coal properties.

Through the oxidation mechanisms, the organically bound sulfur can be transformed to sulfoxides and sulfones and, subsequently, to solvent-extractable sulfur-containing species, or ideally, to water-soluble sulfites and sulfates.

During the program, IGT conducted over 200 ultrasound-promoted coal desulfurization experiments with a laboratory-scale low-intensity ultrasonic bath unit, a medium-intensity ultrasonicator, and a high-intensity bench-scale ultrasonic reactor.

The tests were conducted on model coals (C-DBT and C-DBS) and on the IBC-101 coal from the Illinois Basin Coal Sample Program (IBCS). The model coals were composed of dibenzothiophene (DBT) and dibenzyl sulfide

(DBS) impregnated onto a pure carbon substrate. The samples of the model and IBC coals were crushed and screened to -20 and -80 mesh.

Several relatively inexpensive oxidizing agents, which do not contaminate the coal, were tested including: oxygen, hydrogen peroxide (H_2O_2), ozone (O_3), tert-butyl hydroperoxide (TBPO), and hydroperoxide precursors such as cyclohexane, peroxy carbonate, tetralin, and decalin. The batch tests were conducted with samples of C-DBT and C-DBS and IBC-101 coal in dilute acetic acid (HOAc) or sodium hydroxide (NaOH) solutions with oxidant added. Molybdenum hexacarbonyl [$\text{Mo}(\text{CO})_6$] was added to the solution as a catalyst at 0.01 weight percent. The period of ultrasonic irradiation was 30 to 60 minutes. The focus of the work was on oxidative desulfurization; however, a reductive desulfurization test was also conducted with hydrogen for comparison.

Of the agents tested, H_2O_2 and TBPO in HOAc solution have been the most effective for oxidizing DBS and DBT. DBS can be oxidized to sulfoxide and sulfone at 30°C more readily than DBT. At 75°C , as much as 70% of the DBS can be converted to DBS oxides (mainly DBS sulfone) in the ultrasonic bath with H_2O_2 /HOAc. About 9% of the DBT was converted to DBT sulfoxide (no sulfone). Ultrasonic irradiation appears to promote the oxidative reactions of DBS and DBT through its kinetic effect of transporting oxidants onto the DBS and DBT sites on the carbon substrate.

In one test, the oxidant TBPO demonstrated a unique property by oxidizing 16% of the DBS in 1% NaOH directly to water-soluble sulfur species. Only a small amount of DBS sulfone was detected, which indicates the occurrence of a simultaneous hydrolysis of sulfone - the proposed second reaction step.

In ultrasonic bath tests with -80 mesh IBC-101 coal conducted at 75°C , approximately 60% of the pyritic sulfur (or 18% of the total sulfur) can be removed directly. Some organic sulfur may also have been converted to the corresponding sulfur oxides, which were not soluble in water and may be further converted to water-soluble sulfur species by hydrolysis. The hydrolysis of the IBC-101 coal product from the ultrasonic desulfurization tests produced more water-soluble sulfur compounds. But it is not known whether this results from the hydrolysis of oxidized sulfur components, the further decomposition of pyrite, or the solubilization of the coal itself.

In general, the results from the bench-scale unit with C-DBT coal were similar to those from the ultrasonic bath unit at 75°C . H_2O_2 converted more DBT, but only formed DBT sulfoxide. TBPO, however, transformed DBT to both sulfoxide and sulfone, which is supposedly easier to hydrolyze, forming water-soluble sulfite. Increasing the reactor pressure to 100 psig did not affect the overall DBT conversion. Hydroperoxide precursors, such as tetralin and decalin (used neat), under 100 psig oxygen pressure, however, did convert a small amount of DBT to its sulfoxide. This result suggests that hydroperoxide can be produced by the reaction of tetralin or decalin with oxygen.

The results of ultrasonic tests with the -20 mesh C-DBT model coal are similar to those obtained with the -80 mesh C-DBT model coal. The sulfur conversion achieved with the larger particle sizes were somewhat less than those with the smaller sizes. Increasing the concentration of H_2O_2 or acetic acid can increase the yield of DBT oxides. Formic acid, a solvent known to retain peroxide species well, was used instead of acetic acid for conversion, but did not improve the efficiency of the sulfur removal.

At 75°C in the ultrasonic bench reactor under 100 psig oxygen pressure, a maximum of 92% of the pyritic sulfur or 33% of the total sulfur can be removed directly from a sample of -20 mesh IBC-101 coal. Some organic sulfur may be converted to the corresponding sulfur oxides, which are not soluble in water and may be further converted to produce water-soluble sulfur species by hydrolysis. By comparison with a blank/control test without ultrasound (BK011), it was found that more pyrite and organic sulfur can be removed with ultrasound although the effect was less than expected.

In summary, ultrasonic energy does promote the oxidation of sulfur significantly through its kinetic effect of transporting oxidants onto the sulfur sites on model and IBC-101 coals, although no preferred specific sonochemical mechanisms have been identified. Experiments on model coals have shown a consistent 40% to 50% increase of the conversion rate of DBT to its oxides. This rate increase due to ultrasonic irradiation is expected to be higher when a sample with a larger particle size is tested.

Both dilute H_2O_2 /acetic acid and tert-butyl peroxide (TBPO)/NaOH systems with $Mo(CO)_6$ catalyst are effective for oxidation of sulfur moieties on coal. Hydroperoxide precursors, such as tetralin used neat, with ultrasound under 100-200 psig oxygen pressure can convert most of the pyrite and particle organic sulfur with a longer reaction time (60min). These processes, especially the latter, deserve more study, because of the moderate cost of oxidants and solvents used for desulfurization.

More research is also needed to identify the presence of oxidized sulfur species on the coal product after ultrasonic desulfurization using new analytical techniques, such as sulfur K-edge X-ray absorption fine structure spectroscopy (XAFS), and to research on converting the oxidized sulfur species to easily removable forms, possibly through hydrolysis or mild pyrolysis.

The results of proximate/ultimate and calorific value determinations showed that all desulfurized IBC-101 coal products have heating values (HV) 4% to 6% lower than that of the raw coal, lower ash contents and higher volatile matter (VM) contents, with the exception of the coal products from the tests with TBPO/NaOH, which have higher ash and lower VM contents. The results suggest that the developed ultrasound-promoted desulfurization processes may alter the properties of the coal to a relatively small degree.

OBJECTIVES

The overall objectives of the program were to investigate the use of ultrasound to promote coal desulfurization reactions and to evaluate chemical coal desulfurization schemes under mild conditions through a fundamental understanding of their reaction mechanisms and kinetics. The ultimate goal was to develop an economically feasible mild chemical process to reduce the total sulfur content of Illinois Basin Coals, while retaining their original physical characteristics, such as calorific value and volatile matter content.

During the program, potential chemical reactions with coal were surveyed under various ultrasonic irradiation conditions for desulfurization, to formulate preliminary reaction pathways, and to select a few of the more promising chemical processes for more extensive study.

INTRODUCTION AND BACKGROUND

To meet the increasingly stringent State and Federal regulations on the atmospheric emission of sulfur dioxide from coal combustion facilities, extensive research is being conducted on methods of removing sulfur from coal prior to combustion. Coals from the Illinois Basin contain relatively high concentrations of sulfur. Some 30% to 50% is organic sulfur and the rest is pyritic sulfur. Much of the pyritic sulfur is in microscopic form, which is difficult to remove by conventional coal cleaning processes. The organic sulfur is bound chemically to coal maceral components in organic molecules such as alkyl or aryl sulfides, mercaptans, disulfides, thiophenes, and sulfonic acids. Quantitative removal of sulfur by chemical means is generally ineffective except under severe processing conditions, which destroy some of the organic compounds present in the coal and reduce its calorific value.

Most desulfurization methods for coal may be classified into three categories: thermal decomposition, reduction, and oxidation.¹⁻³ Thermal treatment can be conducted at 400°C or higher to decompose sulfide and mercaptan bonds. However, at these temperatures, other coal macromolecules, such as amines, ethers, acids, and C-O bonds, are also disrupted, severely degrading the coal. To overcome this disadvantage, a catalytic approach to pyrolytically decompose only organic sulfur moieties must be developed. Reductive methods that are effective for removing sulfur from coal use molecular hydrogen, hydrogen-donor systems, or carbon monoxide. These methods often produce hydrogen sulfide (H₂S), hydrogen polysulfide, and elemental sulfur by-products, which are blended with liquid and gaseous hydrocarbons, creating additional separation and environmental problems. Oxidation methods are the favored approach, because the final product, sulfites or sulfates, can be easily separated and disposed.

Processes that remove sulfur from coal via chemical oxidation also oxidize other coal components through competing reactions. For example, phenolic hydroxyl groups can be oxidized to ketones, which, upon further oxidation, form carboxylic acid groups. Nitrogen heterocyclic compounds can form nitrogen oxides. Some activated unsaturated sites, such as double bonds, can also react further to form dicarboxylic acids. These

reactions decrease the fuel value and volatility of the coal. Therefore, to be effective, an oxidative process must be specific to sulfur functional groups and is best conducted under mild conditions.

In the oxidative approach, the organically bound sulfur compounds are modified chemically to solvent-extractable, sulfur-containing species, or, ideally, to water-soluble sulfates. A fraction of the pyritic sulfur will be converted to sulfate as well. The following equations depict the mechanism of the oxidative decomposition of pyrite and the model sulfur compounds DBS and DBT.⁴⁻⁷ In the first reaction step of the DBT oxidation (3a), DBT is converted to dibenzothiophene 5,5-dioxide. In the second reaction step (3b), the sulfoxide is converted to 2-phenylphenol and sulfites in alkaline solution at 300°C.

PYRITE

BENZYL SULFIDE

DIBENZOTHIOPHENE

Irradiation of liquid-phase systems with ultrasonic waves has been shown to initiate and sustain some chemical reactions at much lower temperatures and pressures than those normally needed when ultrasonic irradiation is not applied⁸⁻⁹. Factors that affect sonochemistry - the phenomena associated with ultrasonic irradiation of a liquid - include acoustic intensity, static or total pressure, thermal conductivity of the gas, and vapor pressure of the liquid. Frequency has not been demonstrated to significantly affect sonochemistry over the typical range used for ultrasonic research - 10^4 to 10^6 Hz.

Cavitation - one of the sonochemical phenomena important to heterogeneous catalysis - occurs when alternating cycles of expansion and compression of the sound waves cause tiny vapor filled bubbles or voids to form in the liquid, grow to resonant size, and collapse. Cavitation bubbles of air formed in water irradiated by ultrasound at a frequency of 20 kHz have a resonant radius of about 150 microns. Cavitation occurs at frequencies ranging from about 20 kHz to the low-megahertz range.

If the liquid contains dissolved, noncondensable gases, the cavitation bubbles formed will be filled predominantly with the noncondensable gas. During the compression phase of the ultrasonic wave, the bubbles collapse, generating powerful shock waves that give rise to temperatures on the order of several thousand degrees Fahrenheit and pressures up to 10,000 atmospheres. These shock waves are very short-lived, typically lasting only a few nanoseconds. Thus, even though the bulk liquid may be at room temperature and pressure, the net effect, on a microscopic scale, is to conduct the reaction at high temperature and pressure.

Other phenomena associated with ultrasonic irradiation of liquid-phase media include cavitation near surfaces, microstreaming, and interparticle collisions. Microstreaming increases the movement of material both to and from the area of cavitation, thereby increasing mass transfer and observed reaction rates. Accelerations as high as 10^5 gravities may be generated by a transducer vibrating at 20 kHz with a 50-micron peak displacement. Shock waves formed by cavitation and intense acceleration can degrade macromolecules and fracture crystals. Interparticle collisions result from shock waves generated during ultrasonic cavitation. Particles collide with tremendous force, generating local high temperatures and significant particle attrition.

Ultrasound can be used to promote selected chemical desulfurization processes. It provides an effective way to physically disintegrate and segregate the finely disseminated pyrite crystals that are physically bound to the organic coal skeleton, exposing more sulfur sites for chemical reaction. It transports chemical reagents effectively onto the sulfur sites, eliminating the need to use concentrated chemical reagents for desulfurization. Furthermore, ultrasonic cavitation generates intense localized heating on particle surfaces and may direct specific reactions on heteroatoms in the organic structure through alternative pathways. It is believed that chemical desulfurization can be conducted with ultrasound at conditions much less severe than those typically needed in conventional chemical desulfurization.

At least a part of the phenomena associated with ultrasonic irradiation, sonochemistry, is the generation of free radicals and excited states. A significant amount of hydrogen peroxide or excited oxygen species can be generated directly from water and oxygen (10). These regenerable oxidants can be used to oxidize the sulfur species in coal.

(1) Generation of radicals

(2) Generation of excited states

EXPERIMENTAL EQUIPMENT AND PROCEDURES

The program focused on the basic chemistry of coal desulfurization and the effects of ultrasonic irradiation. Simple model compounds were used to facilitate the investigation of the feasibility and effectiveness of ultrasound-promoted chemical reactions with sulfur-containing compounds and the determination of optimum conditions of these reactions. Actual coal samples were used to realize the side effects caused by the presence of other function groups in the coal matrix and to demonstrate the overall feasibility of the more promising coal desulfurization schemes. However, their use for the preliminary study was limited because complex coal reaction chemistry could have obscured the elucidation of reaction mechanisms and kinetics.

The initial survey tests were conducted with a limited number of chemical analyses to verify the degree of success and to evaluate the effects of ultrasonic irradiation on desulfurization. The variables studied include chemical agents, media, temperature, and pressure. Additional experiments were conducted with the more promising reagents under various conditions to collect preliminary information on the reaction mechanisms and kinetics.

A number of agents, oxidizing chemicals and hydroperoxide precursors, were selected for testing with a variety of aqueous and nonaqueous media to react with sulfur species. These agents and media are listed below. All reagent employed are of technical grade. Ozone was generated by a UV light with emission at 185 nm.

Reagents: Oxygen, air, hydrogen peroxide, t-butyl hydroperoxide, ozone, peroxycarbonate, calcium peroxide, cyclohexane, tetralin, decalin, t-butyl alcohol.

Media: Water, acetic acid (1-2.5%), formic acid (1%), sodium hydroxide (1%), toluene, Therminol 66

Three types of ultrasonic equipment were employed for desulfurization experiments. They are;

- Branson Model B-220 H (50-55 kHz and 185 watts)
- Branson Model 188 P (20 kHz and 1550 watts)
- Heat System XL2020 (20 kHz and 550 watts)

The ultrasonic bath is a commercially available unit typically used for cleaning laboratory equipment. A description of IGT's high-intensity bench-scale ultrasonic reactor follows.

IGT's Bench-Scale Ultrasonic Unit

The overall assembly of the power supply, converter, and ultrasonic horn and reactor are shown in Figure 1. The power supply (Branson Sonic Power Model 188 P) is rated for 1800 watts of power. However, because of inefficiencies in the converter and losses at the various connections, the maximum power that can be delivered to the horn is 1550 watts. The power supply converts 220 volts AC to 500 volts DC to drive the converter. The horn, constructed from a solid piece of 1-inch diameter titanium rod, was machined to 0.9375 inch in diameter at the tip (surface area of 0.69 inch², 4.45 cm²) and 9 1/8-inches long. The horn is machined to accept replaceable titanium tips. The tips are used until worn and then replaced.

The horn is connected to a specially machined catenoidal piece, which is in turn connected to a booster horn. For the tests conducted in this program, the 1.5X booster horn was used and the J-4 Power Controller was set at 70%. For these conditions, the amplitude of the horn face oscillations is 55 microns. The booster horn attaches directly to the converter. The heart of the converter is a stack of 3 disks (2-1/4-inches in diameter by 1/4-inch thick) of piezoelectric material (lead zirconate titanate) that drive the horn.

The bench-scale unit is constructed of 316 stainless steel and has a capacity of about 1 liter. It is capable of operating at temperatures up to 300°C and pressures up to 1200 psig. An internal cooling coil can be used to moderate the temperature in the slurry undergoing irradiation within a range of +/-10°C.

Process control was achieved by local temperature and pressure controllers. Feed gas flows were controlled by mass flow controllers.

The range of operating conditions tested in the low-intensity laboratory ultrasonic bath unit and the high-intensity bench-scale ultrasonic reactor are listed below:

888050222

Figure 1. SCHEMATIC DIAGRAM OF BATCH ULTRASONIC REACTOR FOR COAL DESULFURIZATION TESTS

Temperature, °C	Pressure, psia	Ultrasonic		
		Frequency, kHz	Power, W	Duration, min
25 to 100	15 to 200	20 to 55	200 to 1100	10 to 60

Analysis of Coal Model and Coal Samples

The fate of sulfur types in coal, the distribution of sulfur types in solid and liquid products, and their mass balances are of importance in evaluating the success of each experiment. Solid and liquid samples were collected for analysis by the techniques listed below.

Model Coals Solids: Total sulfur by LECO SC-132; Methylene chloride extraction with GC-ITD and GC-AED analysis
Liquids: Total sulfur by ICP

IBC-101 Coal Solids: Sulfur-by-Types, Ultimate and Proximate Analyses, Calorific Value, Particle Size
Liquids: Total sulfur by ICP

For liquid samples, an ion chromatograph (IC) can be used with an inductively coupled plasma emission spectrometer (ICP) to determine total sulfur and sulfite/sulfate concentrations. Total organic carbon in the liquid can be determined in some cases to measure the extent of coal solubilization or degradation.

For model coal samples, quick and simple techniques were to be adopted and employed to screen the products for initial comparison and experimental evaluation. One such method, the Diffuse Reflectance Fourier Transform Infrared Technique (DRIFT), was used to examine the formation of sulfoxide and sulfone groups on carbon substrates impregnated with model compounds with little success.

An EPA-approved ultrasonic extraction technique (EPA SW846-3550) was employed to determine the concentrations of DBS and DBT and their derivatives, sulfoxides and sulfones. A Heat Systems sonicator (Model XL2020) purchased for this work was used for the extractions. Each sample (300 mg) was extracted with methylene chloride three times with the ultrasonic microprobe pulsed at 165 watts for 2 minutes (1 second on and 0.5 second off). 2-Ethylanthracene was used as an internal standard for the extraction and analysis of DBT. Hexadodecane was used as an internal standard for the DBS analysis. GC-ITD (ion trap detector) and GC-AED (atomic emission detector) were used to analyze the methylene chloride extracts.

For solid samples, determining the types of sulfur present, including organic and inorganic sulfides and sulfate, is difficult, especially after desulfurization. The commonly used procedure outlined in ASTM D2492 quantifies organic sulfur indirectly and is neither precise nor accurate enough for this work. Therefore, a modification of the ASTM procedure developed by IGT¹¹⁻¹³ for sulfides (pyrrhotite and troilite), sulfates, pyrite, and organic sulfur was used to analyze the solid products. Further, all solid samples were analyzed for total sulfur using a LECO SC-132 analyzer. Selected coal samples were analyzed for

ash and carbon, hydrogen, and nitrogen contents with a LECO CHN-600 analyzer. Proximate information was obtained with a LECO TGA-500 analyzer. The calorific value of selected coal and treated products was determined using the ASTM D2105 procedure.

RESULTS AND DISCUSSION

Task 1. Preparation and Characterization of Model and Illinois Coal Samples

The objective of this task was to prepare model coals (C-DBS and C-DBT) and coals from the IBCSP for use in ultrasound-promoted desulfurization tests (Task 2).

Two organic sulfur-containing compounds were selected: dibenzothiophene (DBT) and dibenzyl sulfide (DBS), which represent major S-containing functional groups in the coal. Each of these compounds was dissolved into an organic solvent and impregnated onto a selected carbon substrate (NA G-216 activated carbon). The use of a single chemical compound enabled us to focus on the ultrasound-promoted chemical decomposition of specific sulfur bonds. The use of the activated carbon - a low-sulfur coconut charcoal, permitted us to simulate the study of heterogeneous reactions occurring in a real coal desulfurization process. Furthermore, the microstructure of the activated carbon was similar to that of coal.

Both toluene and methanol were used to impregnate the selected model compounds onto the activated carbon. Methanol was found to be a better solvent, because of its volatility and it can be easily stripped off the carbon. It is also a good wetting agent capable of transporting the model compound effectively into the microstructure of the carbon. The sample preparation procedure is described as follows: 100 grams of G-216 carbon (-80 and -20 mesh) was dried *in vacuo* for 2 hours at 60°C. 15 g of DBT or DBS in 150 ml methanol was quickly added onto the carbon under vacuum with occasional shaking to assure homogeneous impregnation. The mixture was then pressurized with nitrogen at 30 psig for 5 minutes and separated using a centrifuge. The carbon separated was finally vacuum-dried to remove residual methanol.

One sample of IBC-101 coal from the IBCSP was obtained and prepared. The sample was ground to -20 and -80 mesh and stored under nitrogen until needed for testing. Proximate, ultimate and sulfur-by-type analyses of these model and IBC-101 coal samples were performed and the results reported in Table 1.

Task 2. Sonochemical Coal Desulfurization Tests

The objective of this task was to modify ultrasonic equipment as needed for the chemical desulfurization experiments and to conduct sonochemical coal desulfurization tests.

During the program, a total of about 100 tests were conducted in the low-intensity ultrasonic bath unit (Branson Model B-220H, 50 to 55 kHz, 185 watts) at room temperature and at 75°C. A recirculating water bath

Table 1. ANALYSIS OF IBC COAL AND MODEL COAL SAMPLES

Sample	IBC-101		MODEL (G-216)			
	<u>-80mesh</u>	<u>-20mesh</u>	<u>+ DBT</u>		<u>+DBS</u>	
			<u>-80m.</u>	<u>-20m.</u>	<u>-80m.</u>	<u>-20m.</u>
Proximate Analysis, wt % as received						
Moisture Content	13.63	11.46	6.89	1.41	2.21	0.83
Volatile Matter	34.32	34.69	13.36	5.79	17.62	7.35
Ash	9.18	8.90	2.31	2.73	2.40	2.56
Fixed Carbon	<u>42.87</u>	<u>44.95</u>	<u>77.44</u>	<u>90.07</u>	<u>77.77</u>	<u>89.26</u>
Total	100.00	100.00	100.00	100.00	100.00	100.00
Ultimate Analysis, wt % dry basis						
Ash	10.14	9.57	1.73	2.77	1.74	2.58
Carbon	68.79	68.66	95.24	88.53	93.14	88.81
Hydrogen	4.74	4.82	1.53	0.54	1.80	0.74
Nitrogen	1.49	1.25	0.24	0.33	0.21	0.43
Sulfur	4.50	4.53	2.01	2.25	1.84	1.42
Oxygen (by diff.)	11.34	11.17	0.25	5.58	2.27	6.02
Sulfur by Type, wt % dry basis as S						
Sulfide	0.02	ND*	ND	<0.01	ND	<0.01
Sulfate	0.11	ND	ND	<0.02	ND	0.03
Pyritic	1.19	ND	ND	ND	ND	ND
Organic (by diff.)	3.18	ND	ND	2.23	ND	1.38

* Not determined.

was used to maintain the solution temperature at 75°C. For each test, 2 grams of sample were mixed with 50 ml of reaction medium. Molybdenum hexacarbonyl $[\text{Mo}(\text{CO})_6]$ was added as a catalyst in some of the tests at 0.01 weight percent. The operating conditions and results of selected tests from the series with model coals are presented in Tables 2 and 3. The operating conditions and results of selected tests from the series with IBC-101 coal are presented in Table 4.

The oxidizing agents tested included 1% H_2O_2 or TBPO in aqueous solutions of 1% NaOH or HOAc. Also, t-butanol, cyclohexane, tetralin, peroxy carbonate, ozone, calcium hydroxide, and calcium peroxide were tested. The bath unit tests were conducted at 55 KHz in an open vessel under low intensity ultrasonic irradiation.

A medium-intensity ultrasonic horn system (Heat Systems Ultrasonics Corp.) was purchased to conduct additional survey tests under more intense ultrasonic irradiation than provided by the bath unit. Some tests were carried out with sonication operated at a pulse mode for comparison. Additional reagents, which were not tested in ultrasonic bath experiments, were also tested using this unit. A total of about 45 tests were conducted with C-DBS and C-DBT, and IBC-101 coal samples. The results from control and pulsed tests are presented in Tables 5 through 7.

A number of experiments were conducted to simulate the proposed second step reaction mechanism (Equation 3b) and verify the possible transformation of sulfone-containing compounds to the water-soluble sulfite. DBT sulfone and DBS sulfone and some coal products obtained from ultrasonic desulfurization tests were used. A microwave oven was used to produce heat for hydrolysis at 100 psig. Table 8 presents the results from the hydrolysis of model sulfone compounds impregnated on the G-216 carbon.

A total of 72 tests were conducted in the high-intensity bench-scale ultrasonic unit (20 KHz and up to 1550 watts): 48 with C-DBT model coal and 24 with IBC-101 coal. Some of the tests were conducted at 100 psig (0.8 MPa) to determine the effect of pressure on ultrasonic coal desulfurization. The operating conditions and results of selected tests from these series are presented in Tables 9 through 11.

The bench-scale tests were carried out at 20 KHz and 70% input power in a 250-ml tall-form Pyrex beaker. Four or six grams of sample were used in each test with 100 or 150 ml of reaction medium. In the ambient pressure tests, the tall-form beaker was placed inside a 1-liter beaker filled with water to quench the reaction medium and prevent boiling. A thermocouple was used to monitor the solution temperature throughout the experiment, which typically rose to about 55°C within 2 minutes and reached the maximum temperature (85°C) within 20 minutes. In the tests conducted at 100 psig, the solution was placed inside a stainless steel sleeve and then inserted into the high-pressure reactor. This facilitated recovery of the sample after the test. A flow of cooling water was maintained in a coil inserted into the solution during some of the later experiments to prevent overheating and localized boiling at the horn face. The bench-scale ultrasonic tests were conducted in 1%

Table 2. ULTRASONIC DESULFURIZATION BATH TESTS ON THE C-DBS MODEL COAL

Test	Oxidant/ Solvent	Ultra- sound	Reaction Time (min)	Temp. (°C)	Analysis Results			
					Soluble (as in solid) S%	Residues (s%)		Total
						MeCl ₂ -extractabl	DBSulfone	
				(C-DBS, -80 mesh)		DBS		
						1.45	<0.002	1.84
UB028	H ₂ O ₂ /HOAc	on	30	30	.007	.74	ND	1.89
UB079	H ₂ O ₂ /HOAc *	on	30	77	.125	.02	1.29	1.70
UB080	H ₂ O ₂ /HOAc *	off	30	76	.094	.02	.98	1.81
UB081	H ₂ O ₂ /HOAc	on	30	77	.063	.17	.10	1.83
UB082	TBPO/HOAc *	on	30	71	.093	.02	.22	1.69
UB083	TBPO/HOAc *	off	30	71	.082	.08	.28	1.66
UB084	TBPO/HOAc	on	30	73	.159	.11	.010	1.72
UB086	TBPO/NaOH	on	30	74	.300	.28	.005	1.50

Note 1. Other reagents tested without avail include t.butanol, cyclohexane, tetralin in HOAc; peroxy carbonate; CaO₂; Ozone in HOAc & NaOH; H₂O₂ in NaOH or Ca(OH)₂

2. 2g/50ml, 1% reagent, purge with O₂ before testing, 50-55 KHz/185 W

3. DBS sulfoxide decomposes and cannot be detected.

* Catalyst : 0.01% Mo(CO)₆

ND: not determined

Table 3. ULTRASONIC DESULFURIZATION BATH TESTS ON A C-DBT MODEL COAL

Test	Oxidant/Solvent	Ultra- sound	Reaction Time (min)	Temp. (°C)	Analysis Results (SZ)				
					Soluble (as in solid)	Solid Products (dry basis)		Total	
						CH2Cl2-Extractable DBT	Sulfoxide Sulfone		
				(C-DBT coal)	1.39	<.002	<.002	2.01	
UB022	H ₂ O ₂ /HOAc	on	60	31	<.005	1.11	<0.002	<0.002	2.01
UB034	TBPO/HOAc	on	60	30	<.005	1.10	<0.002	<0.002	1.96
UB032	TBPO/NaOH	on	60	30	<.005	1.10	<0.002	<0.002	1.93
UB058	TBPO/NaOH *	on	30	76	<.005	1.33	<0.002	<0.002	1.91
UB062	H ₂ O ₂ /HOAc *	on	30	78	<.005	.57	.18	<.002	1.98
UB063	H ₂ O ₂ /HOAc *	off	30	74	<.005	.73	.16	<.002	1.97
UB064	H ₂ O ₂ /HOAc	on	30	79	<.005	1.06	<0.002	<0.002	2.01
UB065	TBPO/HOAc *	on	30	80	<.005	.94	.04	<0.002	1.90
UB066	TBPO/HOAc *	off	30	74	<.005	.95	.04	<0.002	1.92
UB067	TBPO/HOAc	on	30	79	<.005	1.40	<0.002	<0.002	1.82
UB068	t.butanol:O ₂ /HOAc *	on	30	80	<.005	.96	<0.002	<0.002	1.95
UB069	Cyclohexane:O ₂ /HOAc *	on	30	77	<.005	1.34	<0.002	<0.002	1.94
UB071	Tetralin:O ₂ /HOAc *	on	30	76	<.005	1.38	<0.002	<0.002	2.05
UB073	Peroxy carbonate/H ₂ O	on	30	77	<.005	1.19	<0.002	<0.002	2.04
UB076	O ₃ /HOAc	on	30	78	<.005	.99	<0.002	<0.002	2.02
UB099	Calcium peroxide/H ₂ O	on	30	79	<.005	1.34	<0.002	<0.002	1.92

Notes: 1. Other agents tested without avail include ozone, tetralin and cyclohexane in 1% NaOH, and ozone and hydrogen peroxide in saturated Ca(OH)₂ solution
 2. 2g/50ml, 1% reagent, 50-55 KHz/185W, oxygen purge where indicated
 * 0.01% Mo(CO)₆ catalyst

Table 4. ULTRASONIC DESULFURIZATION BATH TESTS ON -80 MESH ILLINOIS IBC-101 COAL

Test	Oxidants/ Solvent	Ultrasound Reaction (min)	Temp. (°C)	Analysis Results						Z Removal	
				Coal Residues						-----	
				Soluble S%	Sulfide S%	Sulfate S%	Pyritic S%	Organic S%	Total S%	Pyritic sulfur	Total sulfur
				(IBC-101 coal)	.02	.11	1.19	3.18	4.50		
UB046	H ₂ O ₂ /NaOH	60	32	.68	<0.02	.09	.65	2.95	3.71	45	18
UB047	H ₂ O ₂ /HOAc	60	31	.63	<0.02	.12	.47	3.19	3.80	61	16
UB049	TBPO/NaOH	60	32	.36	<0.03	.06	.76	3.01	3.86	36	14
UB050	TBPO/HOAc	60	32	.34	<0.03	.20	.60	3.23	4.06	50	10
UB095	H ₂ O ₂ /HOAc	30	80	.63	<0.02	.15	.49	3.01	3.67	59	18
UB096	H ₂ O ₂ /HOAc	0	76	.64	<0.02	.16	.46	3.02	3.65	61	19
UB097	TBPO/HOAc	30	78	.48	<0.02	.18	.47	3.06	3.73	61	17
UB098	TBPO/HOAc	0	75	.38	<0.02	.18	.62	3.09	3.91	48	13

Notes: 50-55 KHz/185 watts max., 2 g/50ml solvent

H₂O₂: 1%; HOAc: 1% Acetic acid; TBPO: 1 wt% Tertiary butyl peroxide; NaOH: 1%

Table 5. EFFECTS OF ULTRASOUND ON OXIDATION OF THE C-DBS MODEL COAL

Test	Oxidant/Solvent	Ultra-sound (min)	Pulse (on:off) sec.	Reaction Time (min)	Maximum Temp. (°C)	Analysis Results (SZ)		
						Solid Products (dry basis)		
						CH ₂ Cl ₂ -Extractable DBS	Total sulfoxides	
				-20 mesh C-DBS :		1.05	<0.01	1.41
US002	1% H_2O_2 : O_2 /2.5%HOAc *	on		10	70	.38	.52	1.34
US002b		off		10	75	.38	.47	1.33
US002c		off		25	75	.35	.55	1.35
US002p		pulse	1:0.5	15	65	.36	.49	1.38
US002pr		pulse	1:0.5	15	75	.28	.66	1.28
US008	2.5%TBPO: O_2 /2.5%HOAc *	on		10	70	.55	.23	1.25
US008b		off		10	75	.60	.21	1.30
US008c		off		25	75	.51	.23	1.31
US008p		pulse	1:0.5	15	65	.52	.28	1.31
US008pr		pulse	1:0.5	15	75	.42	.27	1.23
US009	2.5%TBPO: O_2 /1%NaOH *	on		10	70	.73	.02	1.20
US009b		off		10	75	.83	.03	1.21
US009c		off		25	75	.83	<0.01	1.16
US009p		pulse	1:0.5	15	65	.81	.02	1.16

Notes: 5g C-DBT/100ml solvent, Heat system sonicator operated at 20 KHz/110 watts.

* .01% $\text{Mo}(\text{CO})_6$ catalyst

Table 6. EFFECT OF ULTRASOUND ON OXIDATION OF THE C-DBT MODEL COAL

Test	Oxidant/Solvent	Ultra-sound (min)	Pulse (on:off) sec.	Reaction Time (min)	Maximum Temp. (°C)	Analysis Results (SZ)		
						Solid Products (dry basis)		
						CH ₂ Cl ₂ -Extractable DBT	Total sulfoxides	
-20 mesh C-DBT :						1.09	<0.01	2.20
US022	1% H ₂ O ₂ :O ₂ /2.5% HOAc *	on		10	70	.91	.13	2.10
US022b		off		10	75	.96	.10	1.99
US022c		off		25	75	.77	.28	2.03
US022p		pulse	1: .5	15	65	.73	.21	2.09
US022pr		pulse	1: .5	15	75	.59	.38	2.03
US029	2.5% TBPO:O ₂ /2.5% HOAc *	on		10	70	.91	.04	1.99
US029b		off		10	75	.94	.04	1.88
US029c		off		25	75	.94	.04	1.86
US029p		pulse	1: .5	15	65	.85	.05	2.04
US029pr		pulse	1: .5	15	75	.91	.07	2.06
US030	2.5% TBPO:O ₂ /1% NaOH *	on		10	70	1.03	<0.01	1.92
US030b		off		10	75	.96	<0.01	1.88
US030c		off		25	75	1	<0.01	1.91
US030p		pulse	1: .5	15	65	1.05	<0.01	1.88

Notes: 5g C-DBT/100ml solvent, 20 KHz/110 watts

* 0.01% Mo(CO)₆ catalyst

Table 7. EFFECTS OF ULTRASOUND ON DESULFURIZATION OF ILLINOIS IBC-101 COAL

Test	Oxidants /Solvents	Ultrasound Pulse (on:off) sec.	Reaction Time (min)	Max. Temp. (°C)	Analysis Results					
					Coal Residues					
					Soluble S%	Sulfide S%	Sulfate S%	Pyritic S%	Organic S%	Total S%
			(IBC-101, -20 mesh)		<0.02	.11	1.19	3.18	4.50	
US052	[2.5% H_2O_2 : O_2	on	10	70	.80	<0.02	.14	.32	3.11	3.57
US052b	/2.5%HOAc	off	10	75	.80	<0.02	.16	.31	3.11	3.46
US052c	/Mo(CO) $_6$]	off	25	75	.80	<0.02	.11	.37	3.18	3.66
US052p		on	1:1.5	65	.83	<0.02	.14	.27	3.18	3.59
US056	[2.5%TBPO: O_2	on	10	70	.38	<0.02	.20	.40	3.25	3.85
US056b	/2.5%HOAc	off	10	75	.33	<0.02	.19	.51	3.23	3.93
US056c	/Mo(CO) $_6$]	off	25	75	.43	<0.02	.18	.41	3.21	3.80
US056p		on	1:1.5	65	.45	<0.02	.20	.38	3.21	3.79
US057	[2.5%TBPO: O_2	on	10	70	.49	<0.02	.15	.46	3.10	3.71
US057b	/1%NaOH	off	10	75	.44	<0.02	.16	.46	3.12	3.74
US057c	/Mo(CO) $_6$]	off	25	75	.56	<0.02	.12	.39	3.04	3.55
US057p		on	1:1.5	65	.52	<0.02	.11	.39	3.03	3.53

Notes: Heat System sonicator was operated at 20 KHz, 5g/100ml solvent
0.01% Mo(CO) $_6$ catalyst was used.

Table 8. HYDROLYSIS TESTS ON CONVERSION OF SULFONES

Test	Reagent	S % in Residue	
		C-DBTsulfone	C-DBSsulfone
	(original)	1.91	1.44
1	1% NaOH	1.90	1.08
2	2 % KOH	1.87	1.29
3	2 % KOH + sat'd $\text{Ca}(\text{OH})_2$	1.91	1.20
4	2 % KOH + sat'd CCl_4	1.89	1.23
5	2 % KOH + 5% butanol + sat'd CCl_4	1.93	1.21

Notes: Tests were conducted under 100 psig in microwave sample containers for 30 min.

Table 9. ULTRASONIC DESULFURIZATION REACTOR TESTS ON A C-DBT MODEL COAL

Test	Load	Oxidant/Solvent	Pressure (Psig)	React. Time (min)	Maximum Temp. (°C)	Analysis Results (SZ)				
						Soluble (calc.on a solid basis)	Solid Products (dry basis) CH ₂ Cl ₂ -Extractable (DBT) (oxides)(sulfone)			Total
			(C-DBT coal, -80 mesh)				1.39	<.002	<.002	2.01
UR008A	4g/100ml	1%H ₂ O ₂ /1%HOAc *	ambient	30	90	.006	.45	.17	<.002	2.02
UR009	4g/100ml	1%H ₂ O ₂ /1%NaOH *	ambient	30	84	.004	1.19	<.002	<.002	1.92
UR011	4g/100ml	1%H ₂ O ₂ :O ₂ /1%HOAc *	ambient	30	88	<0.003	.51	.15	<.002	1.97
UR013	4g/100ml	1%TBPO/1%HOAc/O ₂ *	ambient	30	91	<0.003	1.02	.24	.07	1.85
UR014	4g/100ml	1%TBPO:O ₂ /1%NaOH *	ambient	30	92	.006	1.33	.00	<.002	1.84
UR016	4g/100ml	1%H ₂ O ₂ /H ₂ O/Air *	100	30	88	.038	.93	.12	<.002	1.79
UR017	4g/100ml	1%H ₂ O ₂ /1%HOAc/Air *	100	30	78	.022	.68	.11	<.002	1.64
UR019A	6g/150ml	1%TBPO/1%HOAc/Air *	100	30	63	.004	.93	.22	.06	1.88
UR020	6g/150ml	1%TBPO/1%NaOH/Air *	100	30	71	.008	1.04	<.002	<.002	1.89
UR027	6g/150ml	Tetralin/Decalin/O ₂ *	100	30	98	ND	.86	.05	<.002	1.87
UR028	6g/150ml	1%H ₂ O ₂ /1%HOAc/Air *	100	30	59	<0.003	.71	.17	<.002	1.90
			(C-DBT coal, -20 mesh)				.87			
UR041	6g/150ml	1%H ₂ O ₂ /1%HOAc/O ₂ *	100	30	57	ND	.85	.10	ND	2.10
UR042	6g/150ml	1%H ₂ O ₂ /2.5%HOAc/O ₂ *	100	30	63	ND	.68	.24	ND	2.07
UR043	6g/150ml	2.5%H ₂ O ₂ /2.5%HOAc/O ₂ *	100	30	59	ND	.41	.53	ND	1.92
UR044	6g/150ml	1%H ₂ O ₂ /2.5%HOFO/O ₂ *	100	30	58	ND	.84	.09	ND	2.14
UR056	6g/150ml	1%t-BuOH/1%NaOH/O ₂ *	100	30	57	ND	1.02	<.002	ND	2.03
UR057	6g/150ml	cyclohexane/O ₂ *	100	30	67	ND	.90	<.002	ND	1.93

Notes: Ultrasonic reactor was operated at 20 KHz/200 or higher Watts

Other reagents tested without avail include CaO₂ and tetralin in HOAc and NaOH, Peroxycarbonate in water, hydrogen peroxide in saturated Ca(OH)₂ solution.

* Catalyst: Mo(CO)₆ 0.01 wt% ; TBPO: t-butyl peroxide; HOAc: acetic acid; HOFo: formic acid.

Table 10. ULTRASONIC DESULFURIZATION REACTOR TESTS ON GROUND ILLINOIS IBC-101 COAL

Test	Oxidants/Solvents	Ultra- sound Reaction (min)	Temp. (°C)	Solu- ble [#]	Analysis Results (SX)					% Removal	
					Coal Residues					Pyrite sulfur	Total sulfur
					Sulfide	Sulfate	Pyrite	Organic	Total		
(Feed coal:IBC-101)					<0.02	.11	1.19	3.18	4.50		
(IBC-101 -80 mesh)											
UR029	1%H ₂ O ₂ /1%HOAc/Air	30	79	.51	<0.02	.14	.44	3.02	3.62	63	20
(IBC-101 -20 mesh)											
UR030	2.5%H ₂ O ₂ /1%HOAc/O ₂ *	30	56	.91	<0.02	.14	.14	2.85	3.13	88	30
UR031	2.5%H ₂ O ₂ /2.5%HOAc/O ₂ *	30	29	.89	<0.02	.15	.13	2.96	3.24	89	28
UR031r	1.25%H ₂ O ₂ /2.5%HOAc/O ₂ *	30	57	.72	<0.02	.16	.26	3.06	3.48	78	23
UR032	4%H ₂ O ₂ /2.5%HOAc/O ₂ *	30	60	1.26	<0.02	.15	.09	2.78	3.02	92	33
BK011	(blank: stirred 30min)	0	83	ND	<0.02	.14	.24	3	3.38	80	25
UR033	2.5%TBPO/1%HOAc/O ₂ *	30	63	.45	<0.02	.19	.18	3.03	3.40	85	24
UR034	2.5%TBPO/1%NaOH/O ₂ *	30	32	.76	<0.02	.09	.29	2.70	3.08	76	32
UR035	Cyclohexane/O ₂ *	30	84	ND	<0.02	.28	.51	3.08	3.87	57	14
UR036	Decalin/air *	30	111	ND	<0.02	.47	.62	2.69	3.80	43	8
UR037A	Tetralin/air *	12	121	ND	<0.02	.62	.26	2.55	3.44	76	18
UR037	Tetralin/O ₂ *	30	68	ND	<0.02	.49	.44	2.71	3.64	59	11
UR038	Toluene+50%Tetralin/O ₂ *	30	84	ND	<0.02	.47	.63	2.93	4.03	44	4
UR039	Tetralin/O ₂ (150psi) *	30	84	ND	<0.02	.58	.20	2.65	3.43	80	10

Notes: Ultrasonic reactor was operated at 20 KHz under 100 psig oxygen or air.

[#] calculated on a raw coal basis

* denotes that 0.01% catalyst $Mo(CO)_6$ was used.

6g/150 ml was used for all tests except UR029 where 2g/50 ml was used.

Results in Italics were calculated from the total s% of MeOH-washed coal and the SBT results of the unwashed coal.

Table 11. ULTRASONIC DESULFURIZATION REACTOR TESTS ON ILLINOIS IBC-101 COAL AS RECEIVED

Test	Oxidants/Solvents	Ultra- sound Reaction (min)	Temp. (°C)	Solu- ble [#]	Analysis Results (SZ)					% Removal	
					(IBC-101 coal)	Coal Residues				Pyrite sulfur	Total sulfur
						Sulfide	Sulfate	Pyrite	Organic	Total	
						<0.02	.11	1.19	3.18	4.50	
										3.43	
<u>6g/150ml Tests</u>											
UR040	2.5% H_2O_2 /2.5%HOAc/ O_2 *	30	68	1.11		<0.02	.15	.22	2.91	3.28	82
BK012	(Blank: stirred 30min)			.01		<0.02	.17	.51	3.08	3.76	57
UR103	1.0%HOAc/ H_2 /NiB ₂ *	30	54	ND		<0.02	.11	.87	3.21	4.19	27
UR104	Tetralin/ H_2 /NiB ₂ *	30	83	ND		<0.02	.48	.60	2.88	3.96	50
UR105	TCE/ O_2 *	30	54	ND		<0.02	.44	.38	3.26	4.08	68
UR106	1%cyclohexane/TCE/ O_2 *	30	83	ND		<0.02	.50	.67	3.11	4.28	44
<u>30g/150ml Tests</u>											
UR100	3% H_2O_2 /2.5%HOAc/ O_2 *	30	65	1.11		<0.02	.21	.66	3.07	3.96	45
BK001	(Blank: stirred 30min)		69			<0.02	.24	.70	3.22	4.16	41
UR101	2.5%TBPO/1%NaOH/ O_2 *	30	71	1.11		<0.02	.11	.44	3.04	3.59	63
BK002	(Blank: stirred 30min)						.21	.59	3.05	3.85	50
UR102	Tetralin/ O_2 (200psi) *	60	88	.16		<0.02	.52	.36	2.17	3.05	70
	(after 2nd MeOH wash)						.61	.48	2.89	3.98	60
BK003	(Blank: stirred 60min)					<0.02	.47	.64	2.92	4.03	46
UR108	3.3% H_2O_2 /1%HOAc/ O_2 *	30	107	.04		<0.02	.08	.61	3.29	3.98	49
UR109	3.3%TBPO/1%NaOH/ O_2 *	30	108	.18		<0.02	.14	.59	2.97	3.70	50
UR110	Tetralin/ O_2 (200psi) *	30	100	.15		<0.02	.43	.53	2.58	3.54	55

Notes: Ultrasonic reactor was operated at 20 KHz under 100 psig air or oxygen.

Results in Italics were from control tests without ultrasound.

6g/30ml was used in all control tests except the BK001 where 6g/150ml was used.

* 0.01% catalyst $\text{Mo}(\text{CO})_6$

calculated on a raw coal basis

Table 12. EFFECTS OF ULTRASOUND ON PARTICLE SIZE REDUCTION

Particle Size Distribution (mesh)	IBC-101 as recd.	IBC-101 residue	
		Stirred (2.5%TBPO/1%NaOH)	Ultrasound
> 6	2.73	1.21	0
6 - 12	42.40	23	7.44
12 - 20	24.50	22.80	28.10
20 - 40	13.20	22.10	28.90
40 - 60	6.24	12.10	13.60
60 - 80	3.14	5.35	5.97
80 - 100	1.48	2.42	2.42
100 - 140	1.94	3.80	3.55
140 - 200	1.29	2.76	2.58
200 - 230	.42	1.55	2.42
230 - 270	.46	.35	.32
270 - 325	.32	1.21	.81
< 325	1.85	1.38	3.71

Table 13. COAL PROPERTIES AFTER ULTRASONIC DESULFURIZATION

Analysis	IBC-101	IBC-101 residue			
	as recd	UR032 (4% H_2O_2 - 2.5%HOAc)	UR034 (2.5%TBPO- 1%NaOH)	UR040 (2.5% H_2O_2 - 2.5%HOAc)	UR037 (tetralin- oxygen)
<u>Proximate Analysis</u>					
Moisture %	13.63	5.43	7.27	5.94	4.81
Volatile matter %	34.32	39.48	33.49	38.86	41.17
Ash %	9.18	9.24	13.16	8.84	9.09
Fixed carbon %	42.87	45.85	46.08	46.36	44.93
<u>Ultimate Analysis</u> (dry basis)					
Ash%	10.14	9.74	12.26	9.35	9.30
(SO3% in ash)	4.54	.34	13.60	.51	2.65
Carbon %	68.79	66.37	66.03	67.57	66.88
Hydrogen %	4.74	4.46	4.51	4.50	4.80
Nitrogen %	1.49	1.28	1.30	1.28	1.09
Sulfur %	4.50	3.19	3.32	3.49	3.82
(Sulfate S%)	.11	.15	.09	.15	.54
Oxygen % (diff)	10.34	14.96	12.58	13.81	14.11
<u>Heating value</u> (BTU/Lb, calc.)	12235	11458	11545	11727	11801

HOAc or NaOH solutions with reagents and oxidants similar to those in the ultrasonic bath unit.

After each bath or bench-scale unit test, the treated solution was separated into liquid and solid fractions by filtration through a 0.45 μm membrane filter. The liquid was analyzed for total sulfur content by ICP. All solid products from model coal tests were analyzed for total sulfur with a LECO sulfur analyzer and then extracted three times with methylene chloride for subsequent quantitative determination of all sulfur species. An EPA-approved ultrasonic extraction technique (described previously) was adopted to determine the concentration of DBS and DBT that remained on the carbon, and their derivatives, sulfoxides and sulfones. A GC-ITD instrument complemented with a GC-EAD was used for qualitative and quantitative analysis. DBS sulfoxide cannot be determined directly, because it decomposes at the GC injection port. Although DBS cannot be completely recovered from carbon by extraction, only about 65% of the DBT can be recovered from the C-DBT coal using the current ultrasonic extraction technique. The repeatability of the extraction is sufficient to allow the process evaluation based on the relative abundance of each component.

The solid products from the tests with IBC-101 coal were analyzed for all sulfur types. Some of ultrasonic desulfurization coal products were analyzed using automated proximate/ultimate and screen analysis procedures to evaluate their properties. The selected results are shown in Tables 12 and 13.

Task 3. Data Analysis and Reporting

The objectives of this task were to analyze all of the data generated from the tests conducted in Task 2 and to formulate preliminary reaction pathways for some of the more promising desulfurization agents identified if possible.

The results presented in the data tables 2 and 3 show that H_2O_2 and TBPO are the most effective agents for oxidation of DBS and DBT. Both are more effective in HOAc medium. With these chemicals, the oxidation of the C-DBS model coal at 30°C resulted in a very small percentage of DBS converted to water-soluble sulfur compounds with little change in the total sulfur concentration. The quantitative measurement of the methylene chloride-extractable DBS revealed that DBS can be converted almost completely to its oxidized products at about 75°C. H_2O_2 appears to be a better oxidant than TBPO, based on the fraction of DBS sulfone formed. About 70% of the sulfur in the C-DBS model coal was converted to DBS sulfone in one test (UB079) using 1% H_2O_2 in 1% HOAc at 77°C for 30 minutes. In a 1% NaOH solution, TBPO oxidized 16% of the DBS directly to water-soluble sulfur species with only a small amount of DBS sulfone produced (UB086). This indicates the occurrence of the simultaneous hydrolysis of sulfone by NaOH - the proposed second reaction step.

$\text{Mo}(\text{CO})_6$ was found to be an excellent catalyst for oxidation of C-DBS model coals. More DBS and less DBS sulfone were found in the residual product resulting from tests using $\text{H}_2\text{O}_2/\text{HOAc}$ or TBPO/HOAc without this

catalyst (compare the results of tests UB079 with UB081 and UB082 with UB084).

Ultrasonic irradiation was found to promote the oxidation reaction of DBS. In Test UB079 (with ultrasound), 70% of the DBS was converted to DBS sulfone. In Test UB080 (no ultrasound), only 53% was converted.

Other oxidants, including ozone, peroxycarbonate and calcium peroxide, and hydroperoxide precursors, such as t-butanol, tetralin and cyclohexane, did not show any reactivity toward the DBS under the current experimental conditions using the ultrasonic bath unit.

The results (Table 3) obtained from tests conducted with C-DBT have shown that DBT is much more difficult to oxidize than DBS. This is evident since no water-soluble sulfur is formed and a relatively smaller amount of oxidized products are present in the residual C-DBT sample. About 9% of DBT was converted to DBT sulfoxide (no sulfone).

Table 4 shows the results of ultrasonic bath desulfurization on the IBC-101 coal. A significant amount (60%) of pyrite and no organic sulfur were removed at 30°C after 60 minutes of reaction. It was found that hydrogen peroxide gave the highest pyrite-removal efficiency.

The tests conducted with the Heat System ultrasonicator were designed to obtain information on the effect of ultrasound on oxidation of sulfur species and on the effect of ultrasonic pulsation. The results shown in Tables 5 and 6 indicates that both H_2O_2 /HOAC and TBPO/HOAC reagents are superior to the TBPO/NaOH reagent for conversion of DBS and DBT, with the former the best. However, TBPO is more effective while it is used with NaOH instead of acetic acid for coal desulfurization (Table 7). Ultrasound and higher temperature only improve the desulfurization reaction to a small degree. The reaction seems to be slightly benefited by ultrasound operated at pulse mode. More tests must be conducted to confirm this finding.

Tests on microwave-promoted hydrolysis of sulfoxides and sulfones were conducted to gain information on their stability and to devise a simple procedure to hydrolyze oxidized sulfur organic species to sulfite and sulfate as in the reaction mechanism described in Equation 3b. The experiments were conducted at 100 psig for 30 minutes. The residue was analyzed for sulfur on the LECO analyzer. The results show that DBS sulfoxide can be easily decomposed to water-soluble species. DBS sulfone can be partially converted under the experimental conditions (Table 8). But, DBT sulfone can not be hydrolyzed by any of the reagents in the experiments conducted to date.

The hydrolysis of the IBC-101 coal product from the ultrasonic desulfurization tests produced more water-soluble sulfur compounds. It is not known whether this is a result of the hydrolysis of oxidized sulfur components, the further decomposition of pyrite, or the solubilization of coal itself.

The results of the bench-scale ultrasonic reactor tests (Table 9) were similar to those obtained from bath unit tests on the C-DBT coal at am-

bient pressure and 75°C. Pressure does not have an obvious effect on the oxidation of DBT. Again, both H_2O_2 and TBPO were effective oxidizing agents. The former converted more DBT, but only formed DBT sulfoxide. The latter transformed DBT to sulfoxide as well as sulfone, which is supposedly easier to hydrolyze according to Equation 3b, forming water-soluble sulfite. Other oxidants and hydroperoxide precursors, such as tetralin and cyclohexane, did not show any reactivity toward the DBT under the current experimental conditions in aqueous solvents. The addition of purge air has no obvious effect.

Therminol 66 (a mixture of terphenyl compounds) and decalin were also tested as the ultrasonic reaction medium. They partially solubilize and remove DBT from the model coal during the reaction, complicating the subsequent analyses and evaluation. A small amount of DBT sulfoxide (3% of DBT), however, was found in the residual product from Test UR027 using tetralin, decalin and oxygen. This result suggests that hydroperoxide can be produced by the reaction of tetralin or decalin with oxygen at 100 psig.

The results from ultrasonic tests with the -20 mesh C-DBT model coal are similar to those obtained from tests on the -80 mesh C-DBT model coal. The sulfur conversion achieved with the larger particle sizes were somewhat less than those with the smaller sizes. Increasing the concentration of H_2O_2 or acetic acid seems to increase the yield of DBT oxides (see Test results UR041, UR042 and UR043). Formic acid, a solvent known to retain peroxide species well, can be used instead of acetic acid for conversion with a same efficiency.

The results of bench reactor tests conducted with the IBC-101 coal are presented in Table 10 and 11. Both the $\text{H}_2\text{O}_2/\text{HOAc}$ and TBPO/NaOH systems work well in converting sulfur. In one test (UR032) conducted with -20 mesh IBC-101 coal in a solution of 4% $\text{H}_2\text{O}_2/2.5\%\text{HOAc}$ under 100 psig oxygen pressure, 92% of pyrite or 33% of the total sulfur was removed. By comparison with a blank/control test without ultrasound (BK011), it is found that more pyrite and organic sulfur can be reduced with ultrasonication although the effect of ultrasound on the removal is not as prominent as we have thought.

Tetralin seems to be a better hydroperoxide precursor than cyclohexane and decalin. The results reported in tests UR037A - UR039 are not precise or accurate enough for quantitative estimation of the sulfur removal efficiency from coal because of the difficulty to remove the residual tetralin from the coal. However, it is evident that a good percentage of organic sulfur and pyrite can be converted, partially forming sulfate, which is retained in the coal product. The sulfate is considered inert, which does not contribute to the sulfur emission and can be removed easily with water washing.

More tests (Table 11) on the IBC-101 coal originally received from IBCSP using the same selected agents produce results similar to those obtained from tests on two ground IBC-101 coal samples. The lower sulfur reduction found in four 30g/150ml tests (UR100, UR101, UR108 and UR109) suggests that the reduction efficiency is directly related to the ratio of the amount of the oxidant to the weight of coal. The amount of the

oxidant used in these tests is only sufficient to react with some pyrite and little organic sulfur. The tests using tetralin and oxygen (UR102 & UR110) produce the same results reported previously. The oxygen supply under 100-200 psig oxygen seems to surpass the need for the oxidative desulfurization reactions even when a larger sample is used.

A few ultrasound-promoted reductive desulfurization tests were conducted with a NiB_2 catalyst. No significant sulfur removal was found. Tetrachloroethylene was also tested on the IBC-101 coal under 100 psig oxygen pressure with ultrasound. A large percentage of pyrite (~65%) was removed and partially converted to sulfate. No organic sulfur was removed by dissolution.

Under the influence of ultrasound, particles in a slurry are subjected to intense shock waves, interparticle collisions and microstreaming. Significant particle size reduction can occur during prolonged exposure to ultrasound. Similarly, exposure to NaOH can also effectively reduce particle size through dissolution of organic material. The effects of a 30-minute ultrasonic exposure or stirring on particles of IBC-101 coal in a slurry are demonstrated in Table 12. The results show that the particle size distribution for the stirred and sonicated slurries are significantly different. This suggests that ultrasound may promote the desulfurization reactions through its physical power to dissociate larger particles, facilitating the transportation of oxidants onto the coal sulfur sites. Experiments on model coals have shown a consistent 40% to 50% increase of the conversion rate of DBT to its oxides.

The results of chemical and calorific value determinations made on raw and sonicated samples of IBC-101 coal are presented in Table 13. The results show that the calorific values of the sonicated samples are approximately 4% to 6% lower than that of the raw coal. Of the sonochemically treated coal samples, the ash contents and the SO_3 contents of the ash are lower than those of the raw coal, except for those from the test with TBPO/NaOH. The volatile matter contents are higher except the TBPO/NaOH test product. This analytical information suggests that the developed ultrasound-promoted oxidative desulfurization processes may alter the properties of the coal to a relatively small degree.

CONCLUSIONS AND RECOMMENDATIONS

During the project, two model coals impregnated with sulfur model compounds, DBT and DBS, and one IBC coal (IBC-101) were subjected to ultrasonic irradiation to promote desulfurization reactions. The tests were conducted in a low-intensity ultrasonic bath unit, a medium-intensity ultrasonicator, and IGT's high-intensity pressurized bench-scale ultrasonic reactor.

Tests on model compounds showed that H_2O_2 and TBPO are the two most effective chemicals tested to date for oxidation of DBS and DBT. They work better in an acetic acid medium. DBS can be readily oxidized by them under mild conditions in 1% HOAc solution with $\text{Mo}(\text{CO})_6$ catalyst. As much as 70% of the DBS can be converted to DBS oxides at 75°C. There

is no conversion of DBT to DBT oxides at 30°C. However, 9% of DBT can be oxidized at 75°C in 30 minutes.

Mo(CO)_6 serves as an excellent catalyst for oxidative desulfurization of C-DBS and C-DBT model coals.

Ultrasonic energy does promote the sulfur oxidation significantly through its kinetic effect of transporting oxidants onto the sulfur sites on model and IBC-101 coals, although no preferred specific sonochemical mechanisms have been identified. Experiments on model coals have shown a consistent 40% to 50% increase of the conversion rate of DBT to its oxides. This rate increase due to ultrasonic irradiation is expected to be higher when a sample with larger particle sizes is used.

Both dilute $\text{H}_2\text{O}_2/\text{HOAc}$ and TBPO/NaOH systems with Mo(CO)_6 catalyst are effective for oxidation of sulfur moieties on coal. Using the former system an ultrasonic reactor run conducted under 100 psig air pressure resulted in maximum reduction of 92% pyrite sulfur, 12% organic sulfur and 33% total sulfur from a -20 mesh IBC-101 coal sample. Some organic sulfur may be converted to the corresponding organic sulfur oxides, which are not soluble in water and may be further converted to produce water-soluble sulfur species by hydrolysis. The results from all studies on model coals suggest that most of organic sulfur are probably oxidized, but remain as the organic sulfur in coal. More research is needed to identify those oxidized sulfur species on the coal product using new analytical techniques, such as sulfur K-edge X-ray absorption fine structure (XAFS) spectroscopy, and to research on converting the oxidized sulfur species to easily removable forms, possibly through hydrolysis or mild pyrolysis.

Hydroperoxide precursors, such as tetralin used neat, with ultrasound under 100-200 psig oxygen pressure convert a small amount of DBT to its oxide. Under the same conditions with a longer reaction time (60 min), most of the pyrite and a small amount of organic sulfur can be removed from the IBC-101 coal. These processes deserve more study, because hydroperoxides can be continuously regenerated with oxygen, an inexpensive oxidant.

The results of proximate/ultimate and calorific value determinations showed that all desulfurized samples of the IBC-101 coal have heating values (HV) 4% to 6% lower than that of the raw coal, lower ash contents and higher volatile matter (VM) contents, with the exception of the coal products from the tests with TBPO/NaOH, which have higher ash and lower VM contents. This information suggests a slight alteration in coal properties occurred during the developed ultrasonic oxidative desulfurization processes.

REFERENCES CITED

1. "Coal Desulfurization," R. A. Meyers, Marcel Dekker, 1977.
2. "Coal Structure," A. Attar and F. Dopuis, ACS Advances in Chemistry Series 192, edited by M. L. Gorbaty and K. Quchi, 1981, p. 239.
3. "Coal Desulfurization," T. D. Wheelock, Editor, ACS Symposium Series 64, 1977.
4. "Coal Desulfurization Chemical and Physical Methods," S. Friedman, R. B. Lacount, and R. P. Warzinski, p. 164, ACS Symposium Series 64, 1977.
5. "Oxidation of Dibenzothiophene and Reaction of Dibenzothiophene 5,5-Dioxide with Aqueous Alkali," R. B. Lacount and S. J. Friedman, Organic Chemistry, 42, p. 2751, 1977.
6. "Oxidations in Organic Chemistry," M. Hudlicky
7. "Advanced Organic Chemistry - Reactions, Mechanisms, and Structure," J. March, 3rd Ed., 1985, John Wiley & Sons.
8. "Cavitation," F. R. Young, published by McGraw Hill Book Company, 1989
9. "Ultrasound: Its Chemical, Physical and Biological Effects," edited by K. S. Suslick, published by VCH publisher
10. "Sonochemistry: The Uses of Ultrasound in Chemistry," edited by T. J. Mason, published by Royal Society of Chemistry, 1990
11. "Improved Methods for Determination of Ferrous Sulfides in Coal Char," S. S. Chao, D. M. Mason and A. Attari, Preprint, Fuel Chemistry Division of ACS, 32, No. 4, p. 412, 1987.
12. "Improved Methods for Determination of Ferrous Sulfides in Coal Char," S. S. Chao, IGT IR&D Project 20317 Final Report, July 1988.
13. "Analytical Chemistry of Iron and Sulfur Containing Species in Coal and Its Derivatives," S. S. Chao, A. Attari and D. M. Mason, presented at the 21st ACS Great Lake Regional Meeting, June 1987.

This work was prepared with the support, in part by grants, made possible by the Illinois Department of Energy and Natural Resources through its Coal Development Board and Center for Research on Sulfur in Coal, and by the U.S. Department of Energy (Grant Numbers DE-FG21-90MC27400 and DE-FG22-90PC9076). However, any opinions, findings, conclusions, or recommendations expressed herein are those of the author(s) and do not necessarily reflect the views of IDENR, CRSC, and the DOE.

PROJECT MANAGEMENT REPORT

(June 1, 1991 - August 31, 1991)

Project Title: Ultrasound-promoted Chemical Desulfurization of
 Illinois Coals

Principal Investigator: Dr. Sherman S. Chao, IGT
Co-Investigator: Mr. Michael C. Mensinger, IGT
Project Manager: Dr. Dan D. Banerjee, CRSC

COMMENTS

The project was completed on schedule. All objectives were met. The final report was submitted to the CRSC project manager for approval on August 31, 1991.

(This project is funded by the Illinois Department of Energy and Natural Resources as part of its cost-shared program with the U. S. Department of Energy.)

EXPENDITURES -- EXHIBIT B

Projected and Estimated Actual Expenditures by Quarter

Quarter*	Types of Cost	Direct Labor	Materials and Supplies	Travel	Major Equipment	Other Direct Costs	Indirect Costs	Total
Sept. 1, 1990	Projected	9,600	2,000				17,769	29,369
Nov. 30, 1990	Estimated Actual	3,317.2	108	200			6,017	9,443
Sept. 1, 1990	Projected	19,200	4,000	360			35,613	59,173
Feb. 28, 1991	Estimated Actual	11,785	800	187			21,505	34,277
Sept. 1, 1990	Projected	28,800	6,000	1,999			53,727	90,526
May 31, 1991	Estimated Actual	27,586	1,200	187			50,144	79,117
Sept. 1, 1990	Projected	38,730	7,000	2,359			71,959	120,048
Aug. 31, 1991	Estimated Actual	41,584	2,215	525			75,724	120,048

* Cumulative by quarter

COSTS BY QUARTER

ULTRASOUND-PROMOTED CHEMICAL
DESULFURIZATION OF ILLINOIS COAL

Months and Quarters

○ = Projected Expenditures	<u>\$120,048</u>
● = Actual Expenditures	<u>\$120,048</u>

Total CRSC Award \$ 120,048

SCHEDULE OF PROJECT MILESTONES

A. Prepare model and ICBSP coal samples for tests.

B. Complete sonochemical coal desulfurization tests.

C. Technical reports prepared and submitted.

D. Project management reports prepared and submitted.

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

END

**DATE
FILMED
01/30/92**

I