1 of 1

DOE/ER/45431--T1

ANNUAL TECHNICAL PROGRESS REPORT

(May 15, 1991)

Contract No.: DE-FG05-90ER45431

Project Title: First-Principles Studies of Phase Stability and the
Structural and Dynamical Properties of Metal Hydrides

Principal Investigator: M. Y. Chou
Georgia Institute of Technology
Atlanta, GA 30332
(404) 894-4688

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

MASTER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

JP

TABLE OF CONTENTS

	Page
PROGRESS REPORT (9/15/90 - 5/15/90)	1
a. Structural Properties of Yttrium	1
b. Calculation of Binding Properties of YH_x	2
SUMMARY OF FUTURE RESEARCH	4
a. Pairing and Hopping of Hydrogen in YH_x	4
b. Study of Hydrogen in Niobium and Palladium	5
c. List of Personnel	7
d. List of Other Federal Support	7
e. Budget (9/15/91 - 9/14/92)	8
f. Statement of Cost Sharing	9
APPENDICES	
A. Abstract Submitted for the 1990 SESAPS Meeting	
B. Abstract Submitted for the 1991 APS March Meeting	
C. Manuscript "Pseudopotential Plane-Wave Calculation of the Structural Properties of Yttrium"	

PROGRESS REPORT (9/15/90 - 5/15/91)

One graduate student joined this project last summer. We decided to investigate first the interaction of hydrogen with the 4d transition-metal series, with the first element being yttrium in the hexagonal close-packed (hcp) structure. It is well established that hydrogen dissolved in hcp rare-earth metals exhibits unusual short-ranged ordering, which is closely related to the high stability of the α phase at low temperatures. In addition, there have been quite a few neutron scattering results available for this system.

Because of the recent development of *soft* pseudopotentials, we chose to use the plane wave basis set to carry out the calculation. The advantages of using this complete and orthogonal basis set have been well recognized. Previous problems have been associated with the slow convergence in transition metals. Therefore we first tested the computational methods by studying the structural properties of elemental yttrium and the results were encouraging. We then started the calculation of YH_x with hydrogen occupying different interstitial sites. The results for these two calculations are summarized below:

a. Calculation of the Structural Properties of Yttrium

We have performed pseudopotential calculations of the structural properties of an early transition metal (hcp yttrium) using the plane wave basis set. With the newly proposed soft pseudopotential, good convergence is obtained with an energy cutoff of 30-40 Ry. This provided a test of the feasibility of using plane wave basis in calculating the properties of transition metals and their compounds. It is also found that special care is necessary to handle the outer core in these early transition metals. This can be handled either to include the outer core state as one of the valence states or to add the partial core correction in the exchange and correlation energy. The effect of using different exchange-correlation potentials are also investigated. We find that the calculated equilibrium volume

is underestimated by 10% if the Hedin-Lundqvist exchange-correlation potential is used. The Wigner correlation form gives better results for the hcp structural parameters: the equilibrium atomic volume, c/a ratio, cohesive energy, bulk modulus and Poisson's ratio are within 2%, 1%, 6%, 18% and 19% of experimental values, respectively.

Some of the above results were presented at the 1990 Annual Meeting of the Southeastern Section of the American Physical Society (SESAPS, paper DC13). A copy of the abstract is attached at the end of this report. The final paper entitled "Pseudopotential Plane-Wave Calculation of the Structural Properties of Yttrium" has been submitted to the Physical Review B. A copy of the manuscript is also attached.

b. Calculation of the Binding Properties of Yttrium Hydride

In this study, we consider first the hydride $YH_{0.5}$ with one hydrogen per unit cell occupying two different kinds of interstitial sites: the tetrahedral (T) and octahedral (O) sites. A lattice expansion of 6% is found in the system due to the presence of the hydrogen. The c/a ratio also increases by 3.8%, from 1.56 in pure yttrium to 1.62 in $YH_{0.5}$. The binding energies are calculated to be 4.27 eV and 4.10 eV for the tetrahedral and octahedral sites respectively, with a difference of about 170 meV. Our result also reveals that the tetrahedral site has a lower energy than the octahedral site. Thus, occupation of the tetrahedral sites is energetically more favorable. This is consistent with the conclusion from neutron scattering experiments.

The electronic structure is also investigated. When examining the density of states, we found an extra hydrogen band to split off from the bottom of the metal bands, which is just what we expected for transition-metal hydrides.

Interesting results are found when we move the hydrogen atom along the c -axis between two adjacent tetrahedral sites. The potential energy curve consists of two anharmonic wells with a barrier of about 190 meV. This double-well potential forms a 1-D quantum system

and we can calculate the eigenvalues by solving the Schrodinger equation for hydrogen. From these eigenvalues, the local vibrational modes can be identified. We found the fundamental frequency to be around 100 meV, which is in good agreement with the experimental observation. We are currently analyzing the spectrum in more details and hope to derive the higher frequency modes as well as the jumping rate between the two wells.

The above results were reported at the 1991 March Meeting of the American Physical Society in Cincinnati (paper Q19 3). A copy of the abstract is attached. We are currently in the final stage of analyzing the results and a paper is expected to be written in the summer.

SUMMARY OF FUTURE RESEARCH

a. Pairing and Hopping of Hydrogen in the YH_x system

One important problem in the HY_x system is whether hydrogen atoms form pairs within the metal matrix or they exist in the form of single atoms. There are some experimental indications that pairing may be mediated by the metal atoms. Since the pairing problem is closely related to the interesting fact that the disordered α phase extends down to zero temperature without precipitation, we like to investigate it from total energy calculations.

After the current study of $HY_{0.5}$, we will increase the size of the unit cell to mimic a system with lower concentration of hydrogen. Then the total energy for the systems with or without pairs will be calculated and compared. We will be able to answer the questions such as whether pairing is favorable and how large the energy gain is. With the binding information and interaction parameters available at low concentrations, we are then ready to study the phase stability as a function of temperature and concentration. It is expected the theoretical phase diagram can be determined and compared with experiment. In addition, the effect of pairing on local vibrational modes and diffusion can also be investigated.

Another interesting and special finding for the YH_x system is the rapid hopping of hydrogen between adjacent sites at low temperature which is much faster compared to the bulk diffusion. The quasielastic linewidth in neutron scattering experiments shows a pronounced minimum near 100 K and rises at lower temperature with approximately T^{-1} dependence. This seems to indicate certain nonadiabatic behavior that can be associated with weak coupling of hydrogen to the conduction electrons in the metal, as predicted by Kondo in the consideration of muon motion in solids. The increasing broadening with decreasing T should come from the electronic contribution. The fact that hydrogen is

the lightest impurity in solids makes it possible to have nonadiabatic coupling with the conduction electrons because of low excitation energies across the Fermi sea. Since we have obtained the double well potential as well as the detailed electronic structure in the previous study, we will be able to make contributions to the understanding of this novel phenomenon in a pure metal, i.e., the unusual nonadiabatic coupling between the proton and conduction electrons.

b. Study of Hydrogen in Niobium and Palladium

After the study of hydrogen in hcp yttrium, we will further investigate the hydrogen interaction with metals in the body-centered and face-centered cubic (bcc and fcc) structures. The prototype system will be niobium and palladium respectively. Both metals have stable binary hydrides and have extensive experimental data available. Since the three dimensional lattice will be changed, the optimal interstitial site for hydrogen will also be different. This will in turn affect the diffusion behavior, vibrational modes, possibility of ordering, and much more. The purpose of the study will be to identify the trend in various physical properties when the number of d electrons is increased and crystal structure changed.

The binding properties will be the first one we like to investigate using the pseudopotential method within the local-density functional formalism. Usually the octahedral site is favored in fcc metals while the tetrahedral site is favored in bcc metals. It may be explained by a solid sphere packing model with a fixed effective radius for the hydrogen atom. We wish to examine this question and study the physical basis of the success of this packing model from the information obtained in our first-principles studies for three different metals. In addition, a change of the hydrogen occupancy from the tetrahedral to the octahedral site occurs in the NbH_x system when the metal is compressed. This phase transition under high pressure is closely related to the incompressibility of hydrogen

in metals and is worth further studies. We can also look into the effect of uniaxial stress by decreasing the lattice constant in a chosen direction. In either case, the change in the electronic structure will be examined in details.

There are other interesting experimental results which require further theoretical investigations. For bcc metals such as niobium, the optical modes appear to be dispersionless and depend only weakly on the hydrogen concentration. These indicate that the restoring forces come mainly from the hydrogen-metal interaction and the hydrogen-hydrogen interaction is relatively weak. On the contrary, the optical modes observed in the H-Pd system are lower in energy and exhibit a very significant wave-vector dispersion. In our total energy studies, we can move the atoms freely and evaluate the energies and the Hellmann-Feynman forces for different atomic arrangements. This information can then be used to compute the phonon energy at high symmetry points by the frozen-phonon approximation or by solving for the atomic motion in a potential well. The results will shed some light on the physical origin of the difference in the interaction strength in different hydrides.

Hydrogen diffusion can be found over a large temperature range and for different isotopes with the largest possible mass ratios. These provide a good experimental data base for the development and testing of the quantum theory of diffusion in statistical mechanics. Because of the small mass of hydrogen, quantum effects are likely. A knowledge of the interactions between the interstitial hydrogen atoms and the metal host and among the hydrogen atoms themselves are essential in order to discuss the diffusion process. In particular, the room-temperature diffusion coefficient for hydrogen in niobium is 5-10 orders of magnitude larger than that for other interstitials like oxygen and nitrogen. This is expected to be related to small diffusion barriers which can only be reliably examined in a total energy study. We plan to map out the classical energy surface for the three metals in different crystal structures and investigate the difference. We can also easily examine the influence of hydrostatic pressure on this energy surface by changing the lattice scale. This

information, together with the vibrational spectra, will be the input for further statistical-mechanical model studies for the diffusion mechanism.

c. List of Personnel

Principal Investigator: M. Y. Chou

Graduate Student: Yan Wang (summer 1990 - present)

Postdoc Fellow: S. N. Sun (starting summer 1991)

d. List of Other Federal Support

Presidential Young Investigator Award from National Science Foundation (10/91 - 9/96): annual base grant of \$25,000 plus possible matching funds up to \$37,500 per year.

**DATE
FILMED**

8 / 24 / 93

END