**Task 2: Mild Gasification Technology
Development Process Research Unit
Tests Using Slipstream Sampling
February 1988 - March 1990**

Topical Report

**R.A. Knight
J. Gissy
M. Onischak
S.P. Babu
J.M. Wootten
R.G. Duthie**

MAR 15 1991

July 1990

Work Performed Under Contract No.: DE-AC21-87MC24266

For
U.S. Department of Energy
Office of Fossil Energy
Morgantown Energy Technology Center
Morgantown, West Virginia

By
Institute of Gas Technology
Chicago, Illinois

MASTER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise, does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

This report has been reproduced directly from the best available copy.

Available to DOE and DOE contractors from the Office of Scientific and Technical Information, P.O. Box 62, Oak Ridge, TN 37831; prices available from (615)576-8401, FTS 626-8401.

Available to the public from the National Technical Information Service, U.S. Department of Commerce, 5285 Port Royal Rd., Springfield, VA 22161.

**Task 2: Mild Gasification Technology
Development Process Research Units
Tests Using Slipstream Sampling
February 1988 - March 1990**

Topical Report

**R.A. Knight
J. Gissy
M. Onischak
S.P. Babu
J.M. Wootten
R.G. Duthie**

Work Performed Under Contract No.: DE-AC21-87MC24266

**For
U.S. Department of Energy
Office of Fossil Energy
Morgantown Energy Technology Center
P.O. Box 880
Morgantown, West Virginia 26507-0880**

**By
Institute of Gas Technology
3424 South State Street
Chicago, Illinois 60616**

July 1990

EXECUTIVE SUMMARY

Under U.S. DOE sponsorship, a project team consisting of the Institute of Gas Technology (IGT), Peabody Holding Company, Inc., and Bechtel Group is developing a process for the mild gasification of coal in a 100-pound/hour capacity isothermal process research unit (PRU) at IGT in Chicago. The IGT process is capable of converting bituminous coals to value-added co-products that can open new markets for the U.S. coal industry.

The conceptual IGT mild gasification process incorporates an integrated fluidized-/entrained-bed reactor supplying heat indirectly by a combination of char and gas recycle. The use of mild operating conditions (1000° to 1300°F), low pressures (<50 psig), and continuous operation in closed reactors, combined with the sale of value-added co-products, offer an environmentally sound and economical approach to advanced coal utilization.

The PRU consists of an 8-inch-ID x 8-foot-long fluidized-bed reactor closely coupled to a 4-inch-ID x 13-foot-long entrained-bed reactor. The PRU test results have demonstrated process performance, including the effect of coal type and temperature on mild gasification co-product yields and their properties. The fates of the heteroatoms have also been analyzed.

Data analysis from the successful PRU tests with Peabody's Illinois No. 6 and West Virginia coals shows that, in the temperature range of 1035° to 1390°F, coal conversion ranged from 33% to 46%, resulting in 54% to 76% char, 13% to 28% oils/tar, and 7% to 19% fuel gas. The test data with the Illinois coal show that an increasing reaction temperature increases the coal conversion, with a decreasing char yield. The oils/tar yields appear to maximize between 1100°F and 1200°F, while the gas yield increases steadily with an increasing temperature, primarily caused by the increasing secondary thermal cracking reactions. The highly aromatic oils and tars were characterized to estimate the light oil (<350°F), middle oil (350° to 590°F), heavy oil (590° to 750°F), and pitch (>750°F) distillation fractions. The predominance of secondary reactions is also evident in the effect of temperature on the amounts of various oils/tars produced. It was determined that with an increasing mild gasification temperature, the pitch fraction decreased with a corresponding increase in lighter fractions, particularly the light oil.

The fuel gas from mild gasification is rich in hydrogen and methane and it also contains other light hydrocarbons, carbon oxides, and hydrogen sulfide. An increasing temperature reduces methane and increases the hydrogen content. These effects are also attributable to secondary cracking and reforming reactions and to gas-phase C/H/O equilibria.

The char volatile matter content was in the range of 7% to 12%, reduced from the 37% volatile matter content of the dry Illinois No. 6 coal.

Analysis of the fate of sulfur with an increasing reaction temperature showed that the sulfur content in char and gases decreased while the sulfur content of oils/tars increased. In general, for Illinois coal, the char contained 36% to 54% of the sulfur, the oils and tars contained 9% to 15% of the sulfur, and the fuel gas contained 31% to 52% of the sulfur in the coal.

The implications of these observations, and conclusions on process evaluation, scale-up, and marketability of the co-products, will be analyzed and presented in subsequent project reports.

TABLE OF CONTENTS

	<u>Page</u>
OBJECTIVES	1
INTRODUCTION	3
PROJECT APPROACH	5
DESCRIPTION OF THE PROCESS RESEARCH UNIT	7
DESCRIPTION OF THE MILD GASIFICATION TESTS AND PRU MODIFICATIONS	15
Test Coals	15
Shakedown Operations	15
Mild Gasification Tests	21
DISCUSSION OF PRU TEST RESULTS	39
Introduction	39
Material Balances	39
Temperature Effects	83
Effects of Steam	93
Chemical Properties of Oils/Tars	93
Reproducibility of Data	101
Reactor/Process Configuration	104
CONCLUSIONS	107
REFERENCES CITED	111

LIST OF FIGURES

<u>Figure No.</u>		<u>Page</u>
1	Schematic Diagram of PRU System	8
2	Isometric View of PRU System	9
3	Slipstream Sampling System	11
4	Control Room Panel With Data Acquisition/ Control System	12
5	Fluidization Grid Modifications	31
6	Effect of Mild Gasification Temperature on Co-Product Yields	84
7	Effect of Mild Gasification Temperature on the Boiling-Point Fractions of Oils/Tars	85
8	Effect of Mild Gasification Temperature on the Heteroatoms in Oils/Tars	86
9	Effect of Mild Gasification Temperature on the H/C Atomic Ratio in Oils/Tars	87
10	Effect of Mild Gasification Temperature on Ash, Volatile Matter, and Sulfur Content of Char	88
11	Effect of Mild Gasification Temperature on Gas Composition	89
12	FIMS Spectrum of Test MG-3 Solvent Quench Tar	90
13	FIMS Spectrum of Test MG-3 THF Wash Tar	97
14	Vacuum Distillation Curve for Test MG-3 Solvent Quench Tar	98
15	Vacuum Distillation Curve for Test MG-3 THF Wash Tar	99
16	H-NMR Spectrum of Test MG-25 Oils/Tars	101

LIST OF TABLES

<u>Table No.</u>		<u>Page</u>
1	Properties of Coals and Coke Breeze Diluents	16
2	Summary of PRU Shakedown Tests	18
3	Summary of Mild Gasification PRU Tests	22
4	Analyses of Solids From Test SD-6	41
5	Analyses of Solids From Test MG-3	42
6	Analyses of Solids From Test MG-5	43
7	Analyses of Solids From Test MG-11	44
8	Analyses of Solids From Test MG-12	45
9	Analyses of Solids From Test MG-14	46
10	Analyses of Solids From Test MG-15	47
11	Analyses of Solids From Test MG-16	48
12	Analyses of Solids From Test MG-18	49
13	Analyses of Solids From Test MG-19	50
14	Analyses of Solids From Test MG-21	51
15	Analyses of Solids From Test MG-22	52
16	Analyses of Solids From Test MG-25	53
17	Analyses of Solids From Test MG-28	54
18	Analyses of Solids From Test MG-30	55
19	Oils/Tars Elemental Analyses and Simulated Distillation	56
20	Component Analyses of Full-Range Oils and Tars	60
21	Gas Compositions	64
22	Test SD-6 (1300°F) Material Balances	68
23	Test MG-3 (1325°F) Material Balances	69
24	Test MG-5 (1100°F) Material Balances	70
25	Test MG-11 (1390°F) Material Balances	71

LIST OF TABLES, Cont.

<u>Table No.</u>		<u>Page</u>
26	Test MG-12 (1252°F) Material Balances	72
27	Test MG-14 (1084°F) Material Balances	73
28	Test MG-15 (1034°F) Material Balances	74
29	Test MG-16 (1183°F) Material Balances	75
30	Test MG-18 (1178°F) Material Balances	76
31	Test MG-19 (1102°F) Material Balances	77
32	Test MG-21 (1109°F) Material Balances	78
33	Test MG-22 (1147°F) Material Balances	79
34	Test MG-25 (1134°F) Material Balances	80
35	Test MG-28 (1149°F) Material Balances	81
36	Test MG-30 (1050°F) Material Balances	82
37	Comparison of PAH Contents of Mild Gasification Tar and a Typical Coke Oven Tar	94
38	Comparison of Co-Product Yields With Coke Oven By-Product Yields	95
39	Comparison of PAH Production Levels Between Mild Gasification and a Typical Coke Oven Tar	95
40	FIMS Data on Test MG-3 Oils and Tars	100
41	Hydrogen Atom Distribution in Test MG-25 Oils and Tars	102

OBJECTIVES

The overall objective of this program is to develop mild gasification technology and co-product utilization with Eastern bituminous coal feedstocks. Specifically, the objective of Task 2 is to develop a technical data base for mild gasification technology through the operation of a 100-lb/h process research unit (PRU) with slipstream sampling. The operational data thus obtained can be used for the design of an integrated PRU with a total quench system and a larger (1-ton/hour) process development unit (PDU), ultimately leading to scale-up and commercialization of the process.

INTRODUCTION

The U.S. Department of Energy (DOE) is supporting the development of mild gasification technology to produce coal-derived fuels and value-added products such as chemical feedstocks. Mild gasification may be the most affordable route to increasing coal utilization in the present economic climate. This technology uses operating conditions of 1000° to 1500°F, near-atmospheric pressure, and inexpensive reactants to convert coal to a slate of co-products.

Mild gasification could be considered as an advanced low-temperature coal carbonization process. Low-temperature carbonization of coal was popular in the U.S. until natural gas became abundantly available, and it is still used on a commercial scale in some foreign countries. The old technology, however, has been improved to produce value-added co-products through the application of technical and scientific knowledge about coal conversion that has been developed over the past twenty-five years. Improvements in reactor and process design are being applied to significantly enhance the yield and quality of the co-products as well as the overall economics of the technology. Because of the mild operating conditions and process simplicity, mild gasification can use available materials of construction and conventional engineering design and construction practices. As a result, the capital and operating costs are expected to be low. In this context, by successfully developing and marketing the co-products to derive the value-added benefits, it should be possible to commercialize the technology within the next ten years.

With support of the U.S. DOE, a project team consisting of the Institute of Gas Technology, Peabody Holding Company, Inc., and Bechtel Group is developing a mild gasification process that uses a fluidized-/entrained-bed reactor. This reactor is designed to process caking bituminous coals over a wide range of particle sizes without oxidative pretreatment, and also without the use of oxygen or air as reactants. Process heat, in the conceptual commercial reactor, would be provided by recycled hot char or high-temperature fuel or flue gases derived from burning a portion of the process-derived fuel gases. The addition of an in-bed sulfur-capture agent such as calcium oxide to capture the hydrogen sulfide released during coal conversion is an option for processing high-sulfur coals. The co-product streams, consisting of char, fuel gas, water, and condensables, would be separated by conventional means such as cyclones, staged condensers, and recycle-oil scrubbers.

An isothermal process research unit (PRU) has been built at IGT, consisting of an 8-inch-ID, 8-foot-long fluidized-bed section and a 4-inch-ID, 13-foot-long entrained-flow section, externally heated by electrical heaters. The coal feed capacity is 100 lb/h, and the coal can be fed either to the fluidized bed or to the freeboard region above the fluidized bed and below the entrained section. The stainless steel reactor vessel is designed for operation at a maximum temperature and pressure of 1500°F and 50 psig, respectively.

This topical report summarizes the technology development work that has been performed in the PRU with slipstream sampling of the devolatilization products, using Illinois No. 6 and West Virginia coals. Operational data and extensive characterization data on oils and tars are discussed in the sections to follow.

PROJECT APPROACH

The mild gasification project consists of four major tasks:

- Task 1. Literature Survey of Mild Gasification Processes, Co-Products Upgrading and Utilization, and Market Assessment
- Task 2. Bench-Scale Mild Gasification Study
- Task 3. Bench-Scale Char Upgrading Study
- Task 4. System Integration Studies

The approach to the development of an advanced, mild gasification process was based, in Task 1 of this project, on a detailed literature survey and review of the state-of-the-art technology for coal conversion to readily saleable co-products. A market survey, conducted concurrently with the literature survey, identified the value-added priority end uses of the co-products. Based on this information, the basis for design of the reactor, the process operating conditions, and the methods of co-products upgrading were determined.

The results of the above approach were presented in the Topical Report on Task 1 of this project entitled, "Literature Survey of Mild Gasification Processes, Co-Products Upgrading and Utilization, and Market Assessment".¹ In Task 2 of the project, Bench-Scale Mild Gasification, IGT was directed by U.S. DOE to design, build, and operate an isothermal 100-lb/h bench-scale process research unit (PRU) to determine process performance and to obtain design information on the mild gasification of coals for process scale-up. Subsequently, a part of the work for Task 4, System Integration Studies, was directed to prepare a conceptual preliminary process design including material and energy balances for a 24-ton/day (1-ton/h) adiabatic process development unit (PDU).

DESCRIPTION OF THE PROCESS RESEARCH UNIT

As a part of Task 2, a 100-lb/h isothermal process research unit (PRU) system was designed, built, and operated. The PRU was mechanically designed to operate at temperatures up to 1500°F and pressures up to 50 psig, and was also designed to provide mechanical flexibility in reconfiguration of the feed locations, the inlet gas supply, and the char discharge locations. Figure 1 shows the components of the PRU reactor system in a block diagram and Figure 2 shows an isometric view of the installed PRU in an existing high-bay at IGT.

The reactor vessel consists of an 8-inch-ID fluidized bed that is 8 feet long with a 4-inch-ID entrained bed section above it that is 13 feet long. The reactor and piping is constructed of 316H, a high-carbon stainless steel suitable for temperatures above 1000°F. Several zones of split-shell electrical heaters surround the reactor vessel to maintain isothermal test conditions. Inlet fluidization gases are heated to the test temperature in electrically heated tubing coils. The fluidization gas, with or without the addition of steam, enters the bottom of the fluidized bed through a conical gas distribution grid. A portion of the inlet fluidization gas also enters through a center jet at the bottom of the conical grid to promote good mixing in the fluidized bed.

The coal feed is held in a large hopper with a capacity of 800 lb of feed. The coal is fed by a screw conveyor to either of two feed nozzle locations on the reactor. The coal can be fed to the mid-region, or freeboard, of the 8-inch-ID reactor or to the fluidized bed near the gas distribution grid. The entire feed hopper is supported from three load cells that continuously monitor the weight of the hopper and its contents. The feed screw is controlled by a variable-speed drive that is calibrated for each feed material before the test.

The mild gasification char in the fluidized bed can be discharged either from the bottom of the fluidized bed or from an overflow position about two feet above the gas distribution grid. The fluidized-bed height can be adjusted by controlling the rotational rate of a char discharge screw that conveys the char to the char lockhopper vessel. The finer mild gasification char is entrained from the reactor along with the product gas, and is

A9001016P

Figure 1. SCHEMATIC DIAGRAM OF PRU SYSTEM

Figure 2. ISOMETRIC OF PRU SYSTEM

separated by two cyclones installed in series. The cyclones are enclosed in an electrical split-shell furnace that maintains a temperature of about 1000°F to avoid condensation of any of the liquid co-products.

A slipstream consisting of approximately 5% of the hot product gas stream is sampled downstream of the cyclones prior to passing through the pressure letdown valves and entering the combustor. The sampling system withdraws a flow-controlled slipstream of hot gas that is filtered at 1000°F and then passes through a series of condensers. A schematic diagram of the dual-train sampling system is shown in Figure 3. One train is used from the beginning of the test at low flow for continuous on-line gas analysis, and the other train is activated only for the steady-state portion of the test, with the flow regulated to approximate isokinetic conditions for accurate entrained dust recovery. To capture tar aerosols, which are difficult to condense, a solvent injection and recovery system was devised. The solvent, methylene chloride, is pumped into the sample stream after it exits from the hot sintered-metal filters. Condensables-laden solvent (solvent quench) and condensed steam are recovered in water-cooled, ice-cooled, and dry ice/solvent-cooled traps. Any remaining tar aerosols are removed by a final coalescing filter.

Following each test, tar-laden solvent and aqueous condensate are drained from the system, and the vessels and lines are thoroughly washed with unstabilized tetrahydrofuran (THF) to complete the recovery of oils/tars and condensed water. Filters are cooled, and the collected dust is removed for determination of fines carryover. The oils/tars dispersed in methylene chloride (solvent quench) and the remaining oils/tars dispersed in THF (THF wash) are analyzed separately, and the data are combined to define the chemical characteristics of the entire oils/tars product.

The operation of the PRU system is controlled by an IBM-compatible PC-based process control and data acquisition software package called "Paragon Control", made by Intel Controls Corporation in Waltham, MA. Two CRT monitors installed in the control panel display multiple screens of real-time information about each system component during the startup, operation, and shutdown of the PRU system. All of the data from the field units are recorded and available for run-time or post-test viewing by the operator. Figure 4 shows the control room panel with the data acquisition/control system in operation.

Figure 3. SLIPSTREAM SAMPLING SYSTEM

Figure 4. CONTROL ROOM PANEL WITH DATA
ACQUISITION/CONTROL SYSTEM

Key operating data and calculated values -- such as fluidization and entrainment velocities at the test temperature and pressure, fluidized-bed height, individual and average temperatures in the reactor, differential pressure values in the fluidized bed, and the weight of feed remaining in the feed hopper -- are presented every 10 seconds. Various data values that deviate from specified ranges can trigger visual and audible alarms on the monitors, to allow operator action. The available graphics from this process control software system offer the operator simple and direct control of the operational and process parameters selected for the test. The three lockhoppers in the PRU system, one for the fluidized-bed char and two for the cyclones, are controlled by a separate programmable logic controller panel in the control room. The controller operates the main lockhopper solids-flow valves, the venting valves, and the repressurization valves. Either automatic or manual operation of the lockhoppers can be selected. The timed, sequenced operations of each lockhopper, with safety interlocks, can be programmed or changed as necessary.

An on-line gas chromatograph (GC) analyzes the dry gas composition every 12 minutes from startup to shutdown. The data from the GC are displayed on a separate dedicated monitor in the control room. This information is normalized and plotted against the time of the test to give the operator a view of the steady-state test period. Any deviation from steady-state conditions, such as a feed rate change or interruption, can be easily seen.

DESCRIPTION OF MILD GASIFICATION TESTS AND PRU MODIFICATIONS

Test Coals

Two coals were tested in the PRU operations: A -12 mesh Illinois No. 6 coal obtained from the Peabody Coal Company Randolph Preparation Plant in Baldwin, Illinois, and a metallurgical-grade blended coal consisting of 55% No. 2 Gas Seam and 45% Campbell's Creek Seam from the Peabody Coal Company Wells Complex in Wharton, West Virginia. The Illinois coal had a size consist of 60% below 40 mesh, and the West Virginia coal had a size consist of 90% below 40 mesh. Both of these coals were selected to be representative of high-moisture fines streams from the preparation plants. In most of the tests, the coal was also blended with coke breeze obtained from Mid-Continent Coal & Coke in Gary, Indiana. Two separate batches of the coke breeze were used, designated as Batch 1 and Batch 2. The analytical and physical property data obtained at IGT on the coals and coke breeze batches, following drying in a rotary drum dryer, are shown in Table 1.

Shakedown Operations

The design and procurement of the PRU system components were started in February 1988. Construction of the PRU system began in September 1988 and was completed in February, 1989, and a series of system proving tests was begun. Seven shakedown tests were conducted with coke breeze and Illinois No. 6 coal, and these tests are summarized in Table 2. The series of shakedown tests provided a variety of information on the PRU system operation, proving the operation and control of the system, validating certain design features, and demonstrating the quality of the data collected for the elemental and material balances. Various system modifications were identified in these tests to improve the PRU operation. The most important information acquired for control of the mild gasification process was identification of the values of key PRU parameters that must be monitored and regulated to control fluidization and, hence, the conversion of the coal particles. These parameters included: values of various input gas flow rates, temperatures of different PRU sections, differential pressures indicating the height and stability of the fluidized bed, hot fluidized-bed char discharge rates, overhead char rates collected by the cyclones, and minimum operating pressure to provide a sufficient gas flow through the slipstream sampling system.

Table 1. PROPERTIES OF COALS AND COKE BREEZE DILUENTS

	Illinois No. 6 ^a	West Virginia ^b	Coke Breeze	
			Batch 1 ^c	Batch 2 ^d
<u>Proximate</u>	----- wt% as fed to reactor -----			
Moisture	5.3	1.4	1.1	0.4
Volatile Matter	34.7	30.6	3.4	4.9
Ash	15.0	6.4	11.4	7.4
Fixed Carbon	45.0	61.6	84.1	87.3
Total	100.0	100.0	100.0	100.0
<u>Ultimate</u>	----- wt% dry basis -----			
Ash	15.8	6.4	11.6	7.4
Carbon	64.3	80.2	85.1	87.3
Hydrogen	4.2	5.0	0.4	1.2
Nitrogen	1.4	1.7	1.2	1.3
Sulfur	3.9	1.3	0.7	2.0
Oxygen (by diff)	10.4	5.4	1.0	0.8
Total	100.0	100.0	100.0	100.0
<u>Sulfur Forms</u>	----- wt% of total sulfur -----			
Pyritic	33.3	33.0	5.9	1.7
Sulfate	3.3	<1.0	3.5	1.1
Sulfide	0.0	0.0	6.8	1.7
Organic	63.4	67.0	83.8	95.5
Total	100.0	100.0	100.0	100.0
HHV, Btu/lb (dry)	11,599	14,535	12,504	13,385
Free Swelling				
Index	1½	5½	0	0

^aBaldwin No. 1, Marissa and River King No. 6 Mines; proximate and ultimate analyses are averages of 4 samples; sulfur forms are from analysis of Test MG-16 feed coal.

^b55% No. 2 Gas Seam/45% Campbell's Creek Seam; proximate and ultimate analyses are averages of 3 samples; sulfur forms are "typical" values from supplier.

^cProximate and ultimate analyses, average of 3 samples; sulfur forms, 1 sample; used in tests up to and including Test MG-30.

^dProximate and ultimate analyses, average of 4 samples; sulfur forms, 1 sample; used in Test MG-31.

Table 1, Cont. PROPERTIES OF COALS AND COKE BREEZE DILUENTS

	<u>Illinois No. 6</u>	<u>West Virginia</u>	<u>Coke Breeze</u> <u>Batch 1</u>	<u>Batch 2</u>
<u>Proximate</u>				
U. S. Screen Size	----- wt% retained on screen -----			
12	3.88	0.00	21.30	19.40
20	17.50	0.32	26.90	25.30
40	40.50	9.83	20.80	21.20
60	25.30	14.40	11.90	13.60
80	8.87	12.10	6.26	7.46
100	2.11	7.09	2.68	3.80
140	1.00	13.60	3.58	4.39
200	0.33	7.73	2.46	2.49
230	0.11	1.29	0.67	0.58
270	0.11	3.55	0.89	0.58
325	0.11	3.06	0.67	0.29
Pan	0.18	27.03	1.89	0.91
Total	100.00	100.00	100.00	100.00

Also, improvements were made to maintain non-condensing conditions in the hot filtration and connective piping sections of the slipstream sampling system and to improve quantitative recovery of co-product samples.

The system modifications that were made to the PRU were evaluated after each successive shakedown test. Physical modifications to the PRU system were relatively minor. Routine post-test inspection and cleanup procedures were also learned and implemented for all vessels to assure operational success and satisfactory material balances. A fiber optic probe was found to be very useful to quickly inspect the PRU vessels and shorten the turnaround time.

The modifications made to the PRU system during the shakedown tests included the following:

- A pressure equalizing line was installed between the feedhopper and the reactor, replacing the automatic system for feedhopper pressure and purge control which, during periods of pressure imbalance, caused occasional surges in the feed rate.
- Nitrogen blast taps were added to the continuously purged pressure differential taps in the fluidized bed and were used periodically to clear the ends of the taps.
- A similar blast tap was installed in the center char discharge pipe below the reactor to maintain a uniform flow of solids from the fluidized bed to the char discharge screw.

Table 2. SUMMARY OF MILD GASIFICATION SHAKEDOWN TESTS

	Test No.			
	SD-1	SD-2	SD-3	SD-4
Purpose of Test	To verify solids split between entrained and fluidized beds	To achieve stable operation with coal mixture feed	To achieve stable test with coal mixture at lower fluidization velocity	Repeat SD-3 with pressure equalizing line installed
Feed Material	coke	1:1 mixture coal ^a /coke	coal ^a	1:1 mixture coal ^a /coke
Feed Rate, lb/h	63.0/122.0	10.0	50.0	50.0
N ₂ Rate, lb/h ^b	64.0	112.3	50.1	42.9
Steam Rate, lb/h	0.0	22.1	0.0	0.0
Steam/Coal Ratio	0.00	4.42	0.00	0.00
Temperature, °F ^c	1100	1200	1350	1350
Pressure, psig	0.5	10	5	5
Feed Location	Freeboard	Freeboard	Freeboard	Freeboard
Fluidized-Bed Height, ft	--	--	--	--
Superficial Gas Velocity, ft/s	2.0	3.0	1.4	1.2
Solids Residence Time, min	--	--	--	--
Steady-State Period, h	--	--	--	--
Remarks	Solids carry-over and underflow split achieved	Fines blocked combustor inlet mixer	Pressure control upset of feed rate	Inadequate mixing in low-velocity fluidized bed

a Illinois No. 6 coal

b Not including purge nitrogen

c Average of four thermocouples

Table 2, (cont.). SUMMARY OF MILD GASIFICATION SHAKEDOWN TESTS

	Test No.		
	SD-5	SD-6	SD-7
Purpose of Test	To establish fluidized bed without starter coke in bed	To test feed to fluidized bed directly	Repeat SD-6 with coal
Feed Material	1:1 mixture coal ^a /coke	1:1 mixture coal ^a /coke	coal ^a
Feed Rate, lb/h	50.0	34.0	50.0
N ₂ Rate, lb/h ^b	41.1	91.4	115.6
Steam Rate, lb/h	0.0	12.4	0.0
Steam/Coal Ratio	0.00	0.73	0.00
Temperature, °F ^c	1275	1300	1225
Pressure, psig	5	10	10
Feed Location	Freeboard	Fluidized Bed	Fluidized Bed
Fluidized-Bed Height, ft	--	3.3	--
Superficial Gas Velocity, ft/s	1.1	2.4	2.4
Solids Residence Time, min	--	40	--
Steady-State Period, h	--	3.0	--
Remarks	High purge gas flow reduced char discharge from underflow	Good test with char underflow from fluidized bed	Low feed gas flow with feed, agglomerate growth under feed nozzle

a Illinois No. 6 coal

b Not including purge nitrogen

c Average of four thermocouples

- A continuous nitrogen purge was added to the "fire eye" combustor controller that keeps the flame free of dust accumulation.
- The threaded fittings on the frequently disassembled hot gas line to the conical gas distributor were replaced with the more durable "Graylok" fittings with a single seal-ring gasket.
- The ranges on all of the instrumentation transmitters were precisely calibrated after one certified transmitter was found to be mis-set from the factory.

To improve operator control and data quality, computer software parameters controlling the frequency of data acquisition were changed to more accurately collect and display critical test data and calculated values. Although this required about twice the amount of data storage capacity for each test, disk storage space was available. Two additional graphic screens of information, devoted entirely to the critical calculated fluidized-bed parameters and other system values, were created for display. The cycle times for the operation of the system's lockhoppers were shortened to 20 minutes so that more char samples could be obtained at shorter intervals during each test.

Another purpose of the series of shakedown tests was to identify the values of superficial gas and entrainment velocities required to achieve different fractional splits of the various particle sizes of the coal feed when the feed was introduced into the freeboard region above the fluidized bed. The PRU entrainment velocity could be adjusted with an auxiliary nitrogen input to the freeboard section, to increase the velocity in the 4-inch-ID entrained section while maintaining an ideal superficial gas velocity in the fluidized bed. This feature was installed on the reactor to test different material size splits for different coal types and sizes tested in the same mild gasification reactor.

The process options of either feeding to the freeboard or splitting the coal feed between the fluidized bed and the entrained section both depend on a stable fluidized bed operation. Shakedown Test SD-6 was the first PRU test operated with feeding to the fluidized bed. The test continued for 3 hours of steady-state operation with a 1:1-weight-ratio mixture of Illinois No. 6 coal and coke breeze.

The coal feed material used in the shakedown tests was the Illinois No. 6 coal. This coal was also tested in all of the mild gasification tests up to MG-26. Tests MG-27 through MG-31 were performed with the West Virginia metallurgical-grade coal. The mild gasification tests in the PRU operated satisfactorily with the Illinois No. 6 coal when blended in a 1:1 weight ratio with a non-caking non-reacting coke breeze. A key operational fact-learned about the 8-inch-ID PRU was that the amount of devolatilized char present in the fluidized bed is very important for the dilution and distribution of the incoming caking coal until the coal loses its caking tendency through devolatilization. Previous experience at IGT in operating the 3-foot-ID U-GAS coal gasification pilot plant showed that caking coals could be fed without blending if the ratio of the feed rate of caking coal to the weight of char in the fluidized bed is equal to or less than 1:1. Blending the feed coal with coke breeze assures that this ratio is maintained in the 8-inch-ID PRU.

This information learned from PRU operations is important for process scale-up of the mild gasification process with caking coals. Fluidized beds larger than the 8-inch-ID PRU would be expected to have a sufficient char inventory so that the feed blending practiced in the PRU tests may not be necessary in larger reactors. That information, however, has to be developed further in Task 4, studying system integration and process scaleup. In a scaled-up reactor, blending of the feed coal with a hot recycled char may be required to supply heat for the mild gasification process.

Mild Gasification Tests

The mild gasification tests began after the seven shakedown tests. Thirty-one tests were conducted, and these are summarized in Table 3. A brief description of the test purpose and results follows. The operational performance of the test coals was determined under a variety of mild gasification test conditions and several modifications were made to the PRU to improve its performance.

The first mild gasification tests were planned to use fluidized-bed freeboard feeding of 100% Illinois No. 6 coal, and subsequent tests were planned for feeding into the fluidized bed. In Tests MG-1 and MG-2, 100% Illinois No. 6 coal was fed to the freeboard. Small, lightly agglomerated clumps of material formed and blocked the char discharge pipe located in the bottom-center of the gas distribution grid. The contributing cause identified

Table 3, Part 1. SUMMARY OF MILD GASIFICATION PRU TESTS

	Test No.			
	MG-1	MG-2	MG-3	MG-4
Purpose of Test	Test feed nozzle extended 2 inches into fluidized bed	Test 4-inch screen over gas distributor to stop blockage	Test lime-stone as diluent with coal	Test with coke diluent and lower fluidized-bed height
Feed Material	coal ^a	coal ^a	1:1 mixture coal ^a /lime-stone	1:1 mixture coal ^a /coke
Feed Rate, lb/h	50.0	50.0	62.5	50.0
N ₂ Rate, lb/h ^b	91.6	89.1	136.4	110.9
Steam Rate, lb/h	14.2	15.8	0.0	16.4
Steam/Coal Ratio	0.57	0.63	0.00	0.66
Temperature, °F ^c	1325	1325	1325	1325
Pressure, psig	10	10	10	10
Feed Location	Freeboard	Freeboard	Fluidized Bed	Fluidized Bed
Fluidized-Bed Height, ft	--	--	2.5	1.3
Superficial Gas Velocity, ft/s	2.5	2.5	3.0	3.0
Solids Residence Time, min	--	--	15	--
Steady-State Period, h	--	--	4	--
Remarks	Char lump blocked underflow discharge	Inadequate mixing in fluidized bed	Successful test, but no steam due to faulty transmitter	Small clumps formed on screen over grid

a Illinois No. 6 coal

b Not including purge nitrogen

c Average of four thermocouples

Table 3, Part 2. SUMMARY OF MILD GASIFICATION PRU TESTS

	Test No.			
	MG-5	MG-6	MG-7	MG-8
Purpose of Test	Test center gas jet for better mixing 1.6-inch jet diameter	Repeat test MG-5 with 100% coal	Repeat test MG-6 with smaller jet diameter of 0.875-inch	Test raised gas grid and center jet, use -40 mesh sized coal
Feed Material	1:1 mixture coal ^a /coke	coal ^a	coal ^a	coal ^a
Feed Rate, lb/h	109.0	70.0	25.0	29.4
N ₂ Rate, lb/h ^b	216.7	129.3	119.5	51.0
Steam Rate, lb/h	11.2	11.2	17.5	5.3
Steam/Coal Ratio	0.21	0.32	1.40	0.36
Temperature, °F ^c	1100	1200	1200	1320
Pressure, psig	10	10	10	10
Feed Location	Fluidized Bed	Fluidized Bed	Fluidized Bed	Fluidized Bed
Fluidized-Bed Height, ft	2.0	2.0	2.0	1.25
Superficial Gas Velocity, ft/s	4.5	3.0	3.0	1.3
Solids Residence Time, min	10	--	--	--
Steady-State Period, h	3	--	--	--
Remarks	Successful test operation	Poor mixing, coal found on top of bed	Inlet gas superheater shorted, still poor mixing	High fines carryover, plugged lines, cyclone inlet velocity too low

a Illinois No.6 coal

b Not including purge nitrogen

c Average of four thermocouples

Table 3, Part 3. SUMMARY OF MILD GASIFICATION PRU TESTS

	Test No.			
	MG-9	MG-10	MG-11	MG-12
Purpose of Test	Test -40 mesh coal feed with fine coke breeze starter bed	Test -12 mesh feed with larger central jet diameter	Repeat MG-10 at higher temperature	Repeat MG-11 at lower temperature
Feed Material	coal ^a	1:1 mixture coal ^a /coke	1:1 mixture coal ^a /coke	1:1 mixture coal ^a /coke
Feed Rate, lb/h	22.1	23.9	20.5	22.7
N ₂ Rate, lb/h ^b	60.0	156.7	154.9	150.9
Steam Rate, lb/h	5.4	10.7	12.4	12.4
Steam/Coal Ratio	0.49	0.90	1.21	1.09
Temperature, °F ^c	1320	1320	1390	1252
Pressure, psig	10	10	10	10
Feed Location	Fluidized Bed	Fluidized Bed	Fluidized Bed	Fluidized Bed
Fluidized-Bed Height, ft	1.25	1.25	1.25	1.25
Superficial Gas Velocity, ft/s	1.5	3.8	4.0	3.6
Solids Residence Time, min	--	--	32	29
Steady-State Period, h	--	--	3.25	3.25
Remarks	Fines plugged sample system, lost starter bed before coal feed	Reactor heat element short uneven thermal expansion	Successful test operation	Successful test operation

a Illinois No.6 coal

b Not including purge nitrogen

c Average of four thermocouples

Table 3, Part 4. SUMMARY OF MILD GASIFICATION PRU TESTS

	Test No.			
	MG-13	MG-14	MG-15	MG-16
Purpose of Test	Test higher coal-to-coke ratio	Repeat MG-12 at lower temp and relocated pressure taps	Repeat MG-12 at about 1000 °F	Test deeper fluidized bed with higher feed rate
Feed Material	2:1 mixture coal ^a /coke	1:1 mixture coal ^a /coke	1:1 mixture coal ^a /coke	1:1 mixture coal ^a /coke
Feed Rate, lb/h	14.0	23.2	19.5	32.4
N ₂ Rate, lb/h ^b	146.7	173.1	172.2	153.2
Steam Rate, lb/h	12.4	14.1	14.0	12.4
Steam/Coal Ratio	1.32	1.22	1.44	0.77
Temperature, °F ^c	1260	1084	1034	1183
Pressure, psig	10	10	10	10
Feed Location	Fluidized Bed	Fluidized Bed	Fluidized Bed	Fluidized Bed
Fluidized-Bed Height, ft	1.25	1.25	1.25	2.0
Superficial Gas Velocity, ft/s	3.5	3.7	3.6	3.5
Solids Residence Time, min	--	28	33	20
Steady-State Period, h	--	2.25	3.0	3.0
Remarks	Cake buildup on reactor wall covered pressure taps	Successful test operation	Successful test operation	Successful test operation

^a Illinois No.6 coal

^b Not including purge nitrogen

^c Average of four thermocouples

Table 3, Part 5. SUMMARY OF MILD GASIFICATION PRU TESTS

	Test No.			
	MG-17	MG-18	MG-19	MG-20
Purpose of Test	Test -40 mesh feed to entrained bed	Operate with deeper bed, greater char inventory, higher steam rate	Greater bed height, higher feed rate, higher steam rate	High feed rate test
Feed Material	coal ^a fines (-40 mesh)	1:1 mixture coal ^a /coke	1:1 mixture coal ^a /coke	1:1 mixture coal ^a /coke
Feed Rate, lb/h	20.0	48.2	90.8	93.8
N ₂ Rate, lb/h ^b	149.4	162.8	189.7	221.9
Steam Rate, lb/h	12.4	23.4	23.7	15.9
Steam/Coal Ratio	1.24	0.97	0.52	0.34
Temperature, °F ^c	1200	1178	1102	1120
Pressure, psig	10	10	10	10
Feed Location	Freeboard	Fluidized Bed	Fluidized Bed	Fluidized Bed
Fluidized-Bed Height, ft	--	2.5	3.0	1.8
Superficial Gas Velocity, ft/s	(entrained vel = 13.8)	4.0	4.4	4.8
Solids Residence Time, min	0.02	28	14	--
Steady-State Period, h	3.0	2.0	2.0	--
Remarks	Char found in bed, velocity too low	Successful test operation	Successful test operation	Start test at 100 lb/h, bed defluidized at 200 lb/h

a Illinois No.6 coal

b Not including purge nitrogen

c Average of four thermocouples

Table 3, Part 6. SUMMARY OF MILD GASIFICATION PRU TESTS

	Test No.			
	MG-21	MG-22	MG-23	MG-24
Purpose of Test	Repeat of Test MG-19 with reduced steam rate	Operate test without steam	Use recycled MG-21 char as diluent	Entrained test, feed in bed nozzle, residence time longer
Feed Material	1:1 mixture coal ^a /coke	1:1 mixture coal ^a /coke	1:1 mixture coal ^a /MG char	coal ^a fines (-40 mesh)
Feed Rate, lb/h	94.0	95.2	77.0	27.7
N ₂ Rate, lb/h ^b	230.0	233.1	194.1	372.6
Steam Rate, lb/h	8.5	0.0	15.7	18.2
Steam/Coal Ratio	0.18	0.00	0.41	1.31
Temperature, °F ^c	1109	1147	1100	1180
Pressure, psig	10	10	10	10
Feed Location	Fluidized Bed	Fluidized Bed	Fluidized Bed	Fluidized Bed Nozzle
Fluidized-Bed Height, ft	2.0	1.8	2.3	--
Superficial Gas Velocity, ft/s	4.7	4.6	4.2	(entrained vel = 8.1)
Solids Residence Time, min	10	8	--	--
Steady-State Period, h	3.5	2.5	--	--
Remarks	Successful test operation	Successful test operation	Bed defluidized 15 minutes after start	Discharge from feed hopper restricted

a Illinois No.6 coal

b Not including purge nitrogen

c Average of four thermocouples

Table 3, Part 7. SUMMARY OF MILD GASIFICATION PRU TESTS

	Test No.			
	MG-25	MG-26	MG-27	MG-28
Purpose of Test	Repeat MG-23 conditions using MG-21 char as diluent	Feed coal mixed with calcium oxide	First test with West Virginia coal	Repeat MG-27 with feed sweep gas at lower temp and higher flow
Feed Material	1:1 mixture coal ^a /MG char	1:1 mixture coal ^a /lime	1:2 mixture coal ^b /coke	1:2 mixture coal ^b /coke
Feed Rate, lb/h	100.3	83.0	64.1	51.9
N ₂ Rate, lb/h ^c	223.1	140.5	160.7	173.4
Steam Rate, lb/h	11.1	7.5	8.2	8.2
Steam/Coal Ratio	0.22	0.18	0.38	0.47
Temperature, °F ^d	1134	1140	1225	1149
Pressure, psig	10	10	10	10
Feed Location	Fluidized Bed	Fluidized Bed	Fluidized Bed	Fluidized Bed
Fluidized-Bed Height, ft	3.0	1.9	2.2	1.4
Superficial Gas Velocity, ft/s	4.7	3.0	3.6	3.7
Solids Residence Time, min	8	--	--	15
Steady-State Period, h	2.0	--	1.0	3.5
Remarks	Successful test operation	Bed defluidized 15 min after start	Plug at end of feed nozzle to bed	Successful test operation

^a Illinois No. 6 coal

^b West Virginia coal

^c Not including purge nitrogen

^d Average of four thermocouples

Table 3, Part 8. SUMMARY OF MILD GASIFICATION PRU TESTS

	Test No.		
	MG-29	MG-30	MG-31
Purpose of Test	Repeat MG-28 at lower temperature	Repeat MG-28 at lower temperature	Repeat MG-30 with 1:1 feed mixture
Feed Material	1:2 mixture coal ^a /coke	1:2 mixture coal ^a /coke	1:1 mixture coal ^a /coke
Feed Rate, lb/h	54.3	67.2	70.6
N ₂ Rate, lb/h ^b	183.2	183.4	181.6
Steam Rate, lb/h	8.2	8.2	8.2
Steam/Coal Ratio	0.45	0.37	0.23
Temperature, °F ^c	990	1050	1048
Pressure, psig	10	10	10
Feed Location	Fluidized Bed	Fluidized Bed	Fluidized Bed
Fluidized-Bed Height, ft	2.4	2.4	3.75
Superficial Gas Velocity, ft/s	3.5	3.7	3.6
Solids Residence Time, min	--	17	19
Steady-State Period, h	--	3.0	2.75
Remarks	Feed line plug at reactor stopped test	Successful test operation	Successful test but char overflow interruption

a West Virginia coal

b Not including purge nitrogen

c Average of four thermocouples

in these tests was a lack of good mixing in the fluidized bed with the freeboard-fed coal floating at the top of the bed and preventing sufficient feed penetration into the fluidized bed. Also, a downward growing "beard" aggregation formed on the reactor wall in the freeboard just under the feed nozzle. A higher feed nozzle gas injection velocity prevented the formation of the growth in subsequent tests. In Test MG-3, Illinois No. 6 coal blended with dolomitic limestone was fed to the fluidized bed. The test operated successfully for a 4-hour steady-state period. The purpose of the limestone used in Test MG-3 was to investigate the fluidization-mixing-reaction dynamics with a non-carbonaceous diluent, and limestone was readily obtainable.

Test MG-4 was an attempt to repeat Test MG-3 conditions using diluent coke instead of limestone. Small clumps of material formed at the bottom of the fluidized bed on the one-half-inch screen added over the center char discharge nozzle, which was placed to prevent the blockage of the char discharge nozzle. The screen was removed after Test MG-4.

Various diameters of the center gas jet were tried in Tests MG-5, MG-6, and MG-7, with coal/coke mixtures and coal alone, to see if mixing in the fluidized bed could be improved. Following these tests, a significant modification was made to promote better mixing and dispersal of the incoming coal particles to the fluidized bed. The distance between the feed inlet nozzle and the fluidized bed conical gas distributor grid was shortened to 3 inches from the previous 12 inches, as indicated in Figure 5. The grid assembly and its associated piping were modified to allow a portion of the hot fluidization gas to enter the fluidized bed through a center pipe, along with the fluidization gas entering through the holes in the conical grid itself. As shown in Figure 5, the coal feed nozzle was relocated 12 inches below the char overflow port and 3 inches above the outer edge of the conical gas distributor. This arrangement introduces the coal deep into the bed in a zone of high turbulence, thus increasing the mixing of the incoming coal particles in the fluidized bed. With the particles dispersed quickly throughout the fluidized bed, the frequency of collisions between the sticky particles is reduced and fluidization stability is increased.

In conjunction with the grid modification to improve mixing in the fluidized bed, tests with smaller coal particles, without the diluent coke, were attempted to see if the higher heat-up rate of the smaller particles and

Figure 5. FLUIDIZATION GRID MODIFICATIONS

subsequent rapid devolatilization would lead to improvements in fluidization stability and coal conversion. Test MG-8 was conducted to test the operation of the reactor with the relocated gas distributor. Also, the 100% Illinois No. 6 coal feed was screened to -40 mesh to facilitate rapid particle heat-up. During this test, system pressure upsets eventually led to fluidized bed instability and early shutdown. The cause of the upset was found to be an excessive carry-over of char fines that led to plugging in the pressure equalizing line between the reactor and the feed hopper, together with the malfunction of a pressure letdown valve actuator mechanism. Ultimately, the excessive fines carry-over resulted from the fact that the lower superficial gas velocity necessary for fluidizing the -40-mesh coal particles caused the cyclones to operate at a low collection efficiency.

Test MG-9 was conducted, again with the -40 mesh coal, but with a start-up fluidized bed of coke breeze screened to -40 mesh to match the superficial gas velocity of the fine feed coal in the startup and steady-state periods. The test was stopped as fines plugged the slipstream condensate sampling system in the line to the hot gas filter. A high entrainment rate of the fine coke breeze from the starter fluidized bed was also evident from the observation of fluidized bed differential pressure values before the coal feed was begun.

In Test MG-10, the feed size was returned to -12 mesh, and the 1:1 coal-to-coke weight ratio mixture was used. For this test, the diameter of the central jet in the gas distributor was increased from 0.5 to 1 inch. The test had to be aborted when a reactor heating element in the fluidized-bed zone grounded against a pressure tap fitting, causing a loss of temperature control in the fluidized-bed section. The feed upper load cells at this time also gave a false reading of the feed weight, indicating an incorrect feed rate. It was determined that both problems were the results of an unbalanced thermal expansion between the feed system and the reactor. The impact of this situation in subsequent tests was eliminated by welding additional steel supports to immobilize the feed screw housing and by adding a guide to the vertical feed line to prevent lateral movement.

Following the repair of the heater and the feed line support modifications, Test MG-11 was operated successfully at conditions similar to Test MG-10, but at a temperature of 1390°F. Test MG-12 was conducted at conditions similar to Test MG-11, but at a lower temperature of 1252°F.

Test MG-13 was conducted with a feed mixture containing a 2:1 ratio of coal to coke breeze to increase the coal input to the PRU. The test was interrupted prior to the steady-state period because of a buildup of caked coal on the reactor walls, which covered the pressure taps and blocked the feed and overflow discharge ports. The pressure taps were relocated away from the feed inlet region for subsequent tests.

Test MG-14 was conducted successfully with the 1:1 coal-to-coke mixture at 1084°F. Test MG-15 was a repeat of the same test operation at a lower temperature of 1034°F. Test MG-16 was successfully conducted with a higher feed rate and a deeper fluidized bed of about 24 inches. The bed height in this test was increased to a point above the 15-inch location of the char overflow nozzle by reducing the speed of the char discharge screw, thus allowing the bed to build up above the discharge opening. The Illinois No. 6 coal feed was screened to remove the -40 mesh fines fraction. This was done to restrict mild gasification to the fluidized-bed section by minimizing the entrainment of coal. The test temperature was 1183°F.

Test MG-17 was then conducted, using only the -40 mesh feed coal fines, to investigate the performance of the entrained reaction zone separately from the fluidized bed. The -40 mesh fraction represents about one-third of the -12 mesh size coal stream from the Peabody coal preparation plant. Therefore, the 1:1 mixture of -40 mesh coal and coke was fed to the freeboard at 20 lb/h at a test temperature of 1200°F. The test achieved steady operation and was voluntarily shut down. After the test, about 36 lb (60%) of the total feed was found to have collected in the fluidized-bed region rather than having elutriated from the reactor.

Test MG-18 was operated with a higher steam rate and a higher fluidized-bed height to increase the char inventory in the fluidized bed. The char was discharged successfully as in Test MG-16, but shortly after the conclusion of the one-hour slipstream sampling period, a small one-inch plug of material blocked the feed line to the reactor.

Test MG-19 was conducted to repeat the higher feed rate conditions of Test MG-5, but with a deeper fluidized bed of 36 inches. This test also ran smoothly and parametric data were obtained in completing about two hours of operation until another pressure upset occurred during the repressurization of the first cyclone's lockhopper. The cause of the pressure upsets was found to

be a plugged instrumentation line to a differential pressure switch that allows operation of the lockhopper solids dump valve after the lockhopper is sufficiently vented. During repressurization, the system over-pressurized the lockhopper and the pulse affected the fluidized-bed operation. All of the system tubing lines for venting, pressurization, and pressure equalization were inspected and cleaned prior to the following test.

The goal for Test MG-20 was to increase the feed rate to 200-lb/h, to achieve the design coal feed rate of 100-lb/h. The test began normally with a smooth startup and steady operation at an initial feed rate of 93.8-lb/h for 45 minutes. At that time, the feed rate was increased to about 200-lb/h. After ten minutes at this rate, the fluidized bed became defluidized and char stopped discharging from the bed. After the test, a clump of material was found in the fluidized-bed, indicating that too much feed coal was entering the fluidized-bed reactor compared to the volume of bed char.

Test MG-21 and MG-22 were conducted at the same conditions as Test MG-19 but with different steam inputs to the fluidized bed. These three tests were designed to analyze the effects of steam upon mild gasification and the production and quality of the co-products. For these three comparative tests, the feed rate was maintained from 91 to 95 lb/h and the temperature from 1100° to 1150°F.

Test MG-23 was conducted with the purpose of reducing the amount of inert coke diluent used in the feed mixture for the tests. This was achieved by blending the feed coal with fluidized-bed char collected from Test MG-21. An equal amount of Illinois No. 6 coal was blended with char from Test MG-21 to reduce the weight percentage of coke in the feed mixture from 50% to an estimated 32%. In this way, the Illinois No. 6 coal-derived char in the feed mixture more closely simulates mild gasification with a recycle char stream. The char collected from this test was intended for subsequent blending with coal in later tests to further reduce the amount of coke in the feed mixture; however, about one half-hour after feeding of the mixture was begun, a heater zone in the fluidized-bed zone failed and the fluidized-bed temperature declined, leading to test shutdown.

Test MG-24 was conducted to investigate entrained-flow mild gasification while waiting for a replacement heater element for the fluidized bed. In this test, the -40 mesh fines fraction of the coal was fed to the fluidized-bed

nozzle rather than to the freeboard nozzle, to gain additional solids residence time. The entraining gas velocity in the 8-inch section was set at 8-ft/s and, based on a gas-solids flow correlation, the solids residence time in the 8-inch-ID, 8-foot-long entrained section was calculated to be about 1.2 seconds. The 4-inch piping above the 8-inch zone added another 0.4 second for a total solids residence time of 1.6 seconds.

This arrangement of the fines feed location was designed to improve upon Test MG-17, in which the coal fines were fed to the 8-inch-ID freeboard section above the fluidized bed. The fluidization velocity in Test MG-17 had been 3-ft/s in the 8-inch section. This was too low to entrain the fines and thus they fell on the top of the fluidized bed and did not mix into it. In Test MG-24, however, the feedhopper stopped discharging the fine particles after 35 minutes of feeding. Inspection after the test showed that fine particles were plugging the pressure equalizing line between the feedhopper and the reactor and two instrumentation lines connected to the cyclone-lockhopper system.

Test MG-25 was conducted to repeat the aborted Test MG-23, using the coal and recycle char from Test MG-21 to reduce the amount of diluent coke in the feed mixture. The blended feed mixture was fed at 100-lb/h for two hours and the steady-state sampling period was completed before the feed was interrupted from the feedhopper. A plug in the feed line prevented the resumption of feeding and the test was stopped.

Test MG-26 investigated the addition of calcium oxide to the feed to react with hydrogen sulfide in the product gas and possibly to reduce the sulfur content of the condensables. The coal and calcium oxide were mixed in a 1:1 weight ratio without any diluent coke material to simplify analysis of the data. The feed rate was 85-lb/h and the fluidized-bed temperature was set at 1140°F. Calcium oxide is known to be reactive with moisture and it has a high heat of hydration. Thus, the mixture for Test MG-26 was prepared one hour before the test to avoid a temperature rise or change in physical characteristics of the mixture. In spite of this, the temperature of the mixture in the drum did rise to about 250°F in the center and the mixture was difficult to pour out of the drum. The test ran for 15 minutes when the bed began to de-fluidize. After 50 minutes of trying to fluidize the bed, the feed rate of the mixture from the hopper could not be maintained uniformly.

Batch premixing of the 58-moisture coal and calcium oxide could be avoided in the PRU system with the addition of a second hopper and screw feeder for the calcium oxide or other additive. Mixed in small quantities and introduced quickly to the PRU, the effect of the hydration reaction can be minimized. Prior to Test MG-26, a five-gallon bucket of coal and calcium oxide was prepared and tested in a 6-inch cold flow fluidization test column, and then stored for 48 hours afterwards. In this small quantity, no temperature rise was noted and the mixture was free-flowing and easy to pour after 48 hours. This suggests that mixing at the point of feeding would be successful.

Test MG-27 was the first test conducted to evaluate the mild gasification performance of the metallurgical-grade coal obtained from Peabody's preparation plant in West Virginia. The coal as received had a finer size consist than the Illinois No. 6 coal, as shown in Table 1. The coal was mixed with diluent coke for the first set of tests in a 1:2 weight ratio, because of its higher fines content and higher free swelling index compared to the Illinois No. 6 coal. This was done with the intent of increasing the coal/coke ratio for subsequent tests. The test proceeded well through two hours, after which the sampling period began; however, five minutes into the sampling period, the feed line into the reactor became blocked. The blockage was temporarily relieved by isolating the feedhopper and increasing the feed sweep gas flow through the nozzle. The blockage, however, developed again and the test was stopped. Inspection of the reactor, cyclones, and piping showed that everything was clean and the blockage was restricted to a one-half inch plug in the feed line at the point where it enters the reactor. To eliminate this occurrence in the next test, the feed sweep gas temperature was reduced from 690° to 500°F and the sweep gas velocity was increased.

Test MG-28 was conducted to repeat the conditions of Test MG-27. The temperature was 1170°F and the feed rate was 51.9 lb/h. The test operated well for over 3.5 hours with a very steady flow of fluidized-bed char discharge and steady fluidized-bed differential pressure values. Solids recovered from the reactor after the test were free-flowing.

Test MG-29 was operated with West Virginia coal under conditions similar to those of MG-28, but at a lower temperature of 990°F. In spite of the reduced feed sweep gas temperature, a small plug in the coal feed line at the

entrance to the reactor occurred one hour after the start of coal feeding. The 1/2-inch-thick blockage in the one-inch pipe caused a shutdown of the test prior to steady state. The solids drained from the reactor after the test were free-flowing. The material from the feed line plug was composed of very fine coal particles that had agglomerated and built up in that area. Following the test, a movable rod-probe was installed in the feed pipe using a packing-gland fitting for a seal. This probe was designed to clear feed line blockages if required during subsequent tests.

Test MG-30 was successfully operated with the West Virginia coal at 1050°F, using the 1:2 coal/coke feed mixture, repeating the conditions of Test MG-29. The mixture feed rate was 67.2 lb/h. Steady-state operation was maintained for 3 hours, and slipstream samples were collected after the second hour. Solids drained from the reactor after the test were free-flowing. About 200 grams of material agglomerated around the thermocouples that protrude into the reactor.

In Test MG-31, the ratio of coal to coke was increased to 1:1. An erroneous reading from one of the bed thermocouples, which was later traced to agglomeration of coal on the thermocouple, showed a bed temperature of 600°F. The readings from the remaining three bed thermocouples indicated an average bed temperature of 1050°F, which was reported for the test. Interruptions in the overflow char discharge during the sampling period occurred, resulting in a fluctuating bed height and difficulties in obtaining representative char samples and determining a char discharge rate. Although the system continued to operate until a voluntary shutdown, post-test examination of the material balance data led to the conclusion that the lack of steady-state conditions during sampling rendered the data from this test unacceptable. The char discharged from the fluidized bed was noticeably larger, about 1/8-inch particle diameter, and more nearly uniform in size than bed material from previous tests.

These tests were beneficial in identifying several mechanical design and operational modifications for successful processing of caking bituminous coals.

Integrated PRU tests conducted while preparing this report have identified a very important problem in feeding the coal/coke mixture into the 8-foot-tall feedhopper. The long drop of the mixture was observed to promote

segregation of coal at the bottom of the feedhopper, thus increasing the chance of feeding coal-rich mixtures at the beginning of a test. This increases the probability of feed agglomeration and early termination of the test, and may also have significant impact upon the material and elemental balance data for tests that continue to completion. This issue will be discussed further in the following section on PRU test results. The operational modifications implemented to avoid segregation of coal in the feed, and its effect on PRU operation, will be presented in subsequent project reports.

DISCUSSION OF PRU TEST RESULTS

Introduction

Analyses of char, oils and tars, and gas from the PRU reactor and slipstream sampling system were completed for the successful Illinois No. 6 coal Tests SD-6, MG-3, MG-5, MG-11, MG-12, MG-14, MG-15, MG-16, MG-18, MG-19, MG-21, MG-22, MG-25, and the West Virginia coal Tests MG-28 and MG-30. The data from these tests were used to construct material balances and to examine the effects of mild gasification system temperature and fluidizing gas steam content on the yield and quality of co-products. The analyses of solids are given in Tables 4 through 18. Oils and tars analyses are shown in Tables 19 and 20, and gas analyses are given in Table 21. The normalized material balances for the tests listed above are tabulated, and a description of the data normalization procedure is given in the following section.

Material Balances

The raw and adjusted material balances for successful PRU tests are presented in Tables 22 through 36. These balances have been normalized in a logical fashion to provide a consistent basis for comparison of the tests. The major measurable streams of carbon and ash were usually better than 90% in balance from the raw data.

For material balance calculations, the coke breeze used as diluent was assumed to be non-reacting, based on the initial on-line gas analyses during start-up with coke breeze only. The stepwise data normalization procedure that was applied is summarized as follows:

- 1) The ash in the output streams was balanced with ash in the input feed by adjusting the weight of fluidized-bed char collected during the test.
- 2) The carbon in the output streams was balanced by adjusting the amount of oils and tars collected, assuming that the heavy components coating pipes in the slipstream sampling system cannot be quantitatively collected, and also that the sintered metal filter used to separate char from the gas stream provides an active surface that promotes thermal cracking of a portion of the heavier tars, resulting in deposition of tar-based carbon in the filter pores. In cases where the carbon balance after step 1 was in excess of 100%, no adjustment was made.
- 3) Sulfur gases react reversibly with stainless steel system components, thus introducing a random error in PRU sulfur balances; unaccounted sulfur was balanced by assuming its presence as hydrogen sulfide.

- 4) Unaccounted nitrogen from the coal was assumed to form ammonia in the condensate stream. An analysis was performed for ammonia, but the volatility of that species at the low pH of the aqueous condensate makes it probable that a significant portion is lost during sampling and sample transport and storage.
- 5) The net chemical water make was determined by difference from a 100% total material balance. In some tests, the net water make is a negative number. It is unlikely that steam is actually consumed in the test, and the negative value for net water is probably the result of an accumulation of experimental error.

In five of the 15 successful tests (MG-5, MG-18, MG-21, MG-22, and MG-25), the required adjustments for the ash and carbon balances were in opposing directions. Consequently, the forcing of the ash balance caused the required adjustment to oils/tars for the carbon balance to be very large. The reason for this situation may lie in the question of feed material homogeneity during the course of the test, which was discussed earlier in the section describing PRU operations. For these tests, the material balances are considered to be less reliable, and, although reported for completeness, the data will be marked separately for purposes of interpretation in subsequent sections. Aside from material balances, the characterization data from these tests are used for interpretation of test parameters on co-product quality.

Table 4. ANALYSES OF SOLIDS FROM TEST SD-6
(Test Temperature = 1300°F)

	Feed Mixture	Coal	Diluent	Fluid Bed Char	1st Cyclone Char	1st Cyclone Char	Carry Over Char
<u>Proximate Analysis</u>							
	wt%						
Moisture	3.08	5.33	1.12	0.24	0.52	0.76	ND
Volatile matter	20.83	34.71	3.44	5.09	6.42	7.43	ND
Ash	13.76	15.01	11.44	17.45	14.88	14.63	ND
Fixed carbon	<u>62.33</u>	<u>44.95</u>	<u>84.00</u>	<u>77.22</u>	<u>78.18</u>	<u>77.18</u>	ND
Total	100.00	100.00	100.00	100.00	100.00	100.00	ND
<u>Ultimate Analysis</u>							
	dry wt%						
Carbon	73.72	64.33	85.12	78.56	79.79	79.31	ND
Hydrogen	2.61	4.22	0.35	0.37	0.93	1.03	ND
Sulfur	2.21	3.90	0.70	1.35	1.81	1.90	ND
Nitrogen	1.37	1.37	1.21	1.32	1.64	1.65	ND
Oxygen (by diff.)	5.89	10.35	1.05	0.91	0.87	1.37	ND
Ash	<u>14.20</u>	<u>15.83</u>	<u>11.57</u>	<u>17.49</u>	<u>14.96</u>	<u>14.74</u>	ND
Total	100.00	100.00	100.00	100.00	100.00	100.00	ND
Heating Value, Btu/lb	ND	11,599	12,504	ND	ND	ND	ND
Particle Density, g/cm ³	ND	1.46	1.82	ND	ND	ND	ND
<u>Particle Size Distribution</u>							
U. S. Mesh	wt% retained on screen						
6	ND	0.00	0.00	ND	ND	ND	ND
12	--	3.88	21.30	--	--	--	--
20	--	17.50	26.90	--	--	--	--
30	--	--	--	--	--	--	--
40	--	40.50	20.80	--	--	--	--
60	--	25.30	11.90	--	--	--	--
70	--	--	--	--	--	--	--
80	--	8.87	6.26	--	--	--	--
100	--	2.11	2.68	--	--	--	--
120	--	--	--	--	--	--	--
140	--	1.00	3.58	--	--	--	--
170	--	--	--	--	--	--	--
200	--	0.33	2.46	--	--	--	--
230	--	0.11	0.67	--	--	--	--
270	--	0.11	0.89	--	--	--	--
325	--	0.11	0.67	--	--	--	--
PAN	--	<u>0.18</u>	<u>1.89</u>	--	--	--	--
	--	100.00	100.00	--	--	--	--

ND = analysis not done

Table 5. ANALYSES OF SOLIDS FROM TEST MG-3
(Test Temperature = 1325°F)

	Feed Mixture	Coal	Diluent	Fluid Bed Char	1st Cyclone Char	1st Cyclone Char	Carry Over Char
<u>Proximate Analysis</u>							
	wt%						
Moisture	2.72	5.33	NA ^a	0.28	1.02	1.07	ND
Volatile matter	41.40	34.71	NA	34.60	22.08	29.02	ND
Ash	36.24	15.01	NA	43.75	25.67	34.41	ND
Fixed carbon	19.64	44.95	NA	21.37	51.23	35.50	ND
Total	100.00	100.00	NA	100.00	100.00	100.00	ND
<u>Ultimate Analysis</u>							
	dry wt%						
Carbon	37.67	64.33	NA	33.60	60.43	49.23	ND
Hydrogen	1.51	4.22	NA	0.17	1.04	0.71	ND
Sulfur	1.64	3.90	NA	0.82	1.56	1.37	ND
Nitrogen	0.66	1.37	NA	0.52	1.31	1.09	ND
Oxygen (by diff.)	21.27	10.35	NA	21.02	9.73	12.82	ND
Ash	37.25	15.83	NA	43.87	25.93	34.78	ND
Total	100.00	100.00	NA	100.00	100.00	100.00	ND
Heating Value, Btu/lb	5036	11,599	NA	3429	8903	6753	ND
Particle Density, g/cm ³	ND	1.46	ND	ND	ND	ND	ND
<u>Particle Size Distribution</u>							
U. S. Mesh	wt% retained on screen						
6	--	0.00	ND	0.09	--	--	ND
12	1.92	3.88	--	7.00	--	0.25	--
20	8.55	17.50	--	20.40	--	--	--
30	--	--	--	--	--	--	--
40	33.90	40.50	--	47.60	0.66	--	--
60	26.80	25.30	--	20.00	5.25	0.25	--
70	--	--	--	--	--	--	--
80	13.70	8.87	--	3.69	7.55	1.24	--
100	6.09	2.11	--	0.65	6.57	1.24	--
120	--	--	--	--	--	--	--
140	6.09	1.00	--	0.46	14.10	4.98	--
170	--	--	--	--	--	--	--
200	1.66	0.33	--	0.11	15.30	55.70	--
230	0.37	0.11	--	--	6.24	11.70	--
270	0.21	0.11	--	--	8.05	5.72	--
325	0.11	0.11	--	--	6.73	7.21	--
PAN	0.60	0.18	--	--	29.55	11.71	--
	100.00	100.00	--	100.00	100.00	100.00	--

ND = analysis not done

NA = not applicable

a The diluent in this test was limestone

Table 6. ANALYSES OF SOLIDS FROM TEST MG-5
(Test Temperature = 1100°F)

	Feed Mixture	Coal	Diluent	Fluid Bed Char	1st Cyclone Char	1st Cyclone Char	Carry Over Char
<u>Proximate Analysis</u>							
	wt%						
Moisture	4.95	5.33	1.12	0.59	0.94	1.70	6.01
Volatile matter	18.92	34.71	3.44	18.24	9.08	13.54	21.03
Ash	12.71	15.01	11.44	18.50	13.21	29.25	35.96
Fixed carbon	<u>63.42</u>	<u>44.95</u>	<u>84.00</u>	<u>62.67</u>	<u>76.77</u>	<u>55.51</u>	<u>37.00</u>
Total	100.00	100.00	100.00	100.00	100.00	100.00	100.00
<u>Ultimate Analysis</u>							
	dry wt%						
Carbon	75.20	64.33	85.12	70.26	79.34	60.40	54.19
Hydrogen	2.45	4.22	0.35	2.18	1.17	1.53	0.95
Sulfur	2.17	3.90	0.70	2.72	1.57	1.90	3.15
Nitrogen	1.47	1.37	1.21	1.37	1.54	1.78	1.37
Oxygen (by diff.)	5.34	10.35	1.05	4.86	3.04	4.63	2.08
Ash	<u>13.37</u>	<u>15.83</u>	<u>11.57</u>	<u>18.61</u>	<u>13.34</u>	<u>29.76</u>	<u>38.26</u>
Total	100.00	100.00	100.00	100.00	100.00	100.00	100.00
Heating Value, Btu/lb	ND	11,599	12,504	ND	ND	ND	ND
Particle Density, g/cm ³	ND	1.46	1.82	ND	ND	ND	ND
<u>Particle Size Distribution</u>							
U. S. Mesh	wt% retained on screen						
6	ND	0.00	0.00	--	--	--	ND
12	--	3.88	21.30	7.36	0.12	--	--
20	--	17.50	26.90	26.00	3.44	--	--
30	--	--	--	--	--	--	--
40	--	40.50	20.80	46.58	15.85	0.45	--
60	--	25.30	11.90	15.00	23.05	0.45	--
70	--	--	--	--	--	--	--
80	--	8.87	6.26	3.30	16.00	0.45	--
100	--	2.11	2.68	0.88	8.60	0.45	--
120	--	--	--	--	--	--	--
140	--	1.00	3.58	0.66	10.70	6.79	--
170	--	--	--	--	--	--	--
200	--	0.33	2.46	0.22	7.62	49.82	--
230	--	0.11	0.67	--	2.46	33.90	--
270	--	0.11	0.89	--	2.95	2.26	--
325	--	0.11	0.67	--	2.21	4.07	--
PAN	--	<u>0.18</u>	<u>1.89</u>	<u>--</u>	<u>7.00</u>	<u>1.36</u>	--
	--	100.00	100.00	100.00	100.00	100.00	--

ND = analysis not done

Table 7. ANALYSES OF SOLIDS FROM TEST MG-11
(Test Temperature = 1390°F)

	Feed Mixture	Coal	Diluent	Fluid Bed Char	1st Cyclone Char	1st Cyclone Char	Carry Over Char
<u>Proximate Analysis</u>							
	wt%						
Moisture	2.21	3.30	1.12	0.24	0.41	1.57	2.95
Volatile matter	19.09	34.73	3.44	3.82	5.62	8.09	13.91
Ash	13.28	15.12	11.44	15.87	15.80	16.55	44.28
Fixed carbon	<u>65.42</u>	<u>46.85</u>	<u>84.00</u>	<u>80.07</u>	<u>78.17</u>	<u>73.79</u>	<u>38.86</u>
Total	100.00	100.00	100.00	100.00	100.00	100.00	100.00
<u>Ultimate Analysis</u>							
	dry wt%						
Carbon	75.05	64.98	85.12	81.08	79.41	76.54	47.47
Hydrogen	2.37	4.38	0.35	0.31	0.70	1.24	0.73
Sulfur	2.33	3.95	0.70	1.15	1.57	1.58	6.28
Nitrogen	1.36	1.51	1.21	1.32	1.43	1.64	1.18
Oxygen (by diff.)	5.31	9.59	1.05	0.23	1.03	2.19	0.00
Ash	<u>13.58</u>	<u>15.59</u>	<u>11.57</u>	<u>15.91</u>	<u>15.86</u>	<u>16.81</u>	<u>44.34</u>
Total	100.00	100.00	100.00	100.00	100.00	100.00	100.00
Heating Value, Btu/lb	ND	11,599	12,504	ND	ND	ND	ND
Particle Density, g/cm ³	ND	1.46	1.82	ND	ND	ND	ND
<u>Particle Size Distribution</u>							
U. S. Mesh	wt% retained on screen						
6	ND	0.00	0.00	0.30	0.00	0.00	--
12	--	3.88	21.30	35.10	0.00	0.00	--
20	--	17.50	26.90	37.50	0.22	0.00	--
30	--	--	--	--	--	--	--
40	--	40.50	20.80	22.35	5.64	0.83	--
60	--	25.30	11.90	3.75	23.95	3.31	--
70	--	--	--	--	--	--	--
80	--	8.87	6.26	0.42	16.65	9.09	--
100	--	2.11	2.68	0.12	8.92	1.65	--
120	--	--	--	--	--	--	--
140	--	1.00	3.58	0.12	12.50	5.79	--
170	--	--	--	--	--	--	--
200	--	0.33	2.46	0.00	10.50	5.79	--
230	--	0.11	0.67	0.00	3.75	0.83	--
270	--	0.11	0.89	0.00	4.27	1.65	0.00
325	--	0.11	0.67	0.12	3.56	1.65	25.00
PAN	--	<u>0.18</u>	<u>1.89</u>	<u>0.22</u>	<u>10.04</u>	<u>69.41</u>	<u>75.00</u>
	--	100.00	100.00	100.00	100.00	100.00	100.00

ND = analysis not done

Table 8. ANALYSES OF SOLIDS FROM TEST MG-12
(Test Temperature = 1252°F)

	Feed Mixture	Coal	Diluent	Fluid Bed Char	1st Cyclone Char	1st Cyclone Char	Carry Over Char
<u>Proximate Analysis</u>							
	wt%						
Moisture	2.22	3.32	1.12	0.58	0.91	2.14	7.54
Volatile matter	19.34	35.23	3.44	5.20	6.51	12.41	31.28
Ash	12.78	14.11	11.44	16.33	14.54	18.97	42.96
Fixed carbon	<u>65.66</u>	<u>47.34</u>	<u>84.00</u>	<u>77.89</u>	<u>78.04</u>	<u>66.48</u>	<u>18.22</u>
	100.00	100.00	100.00	100.00	100.00	100.00	100.00
<u>Ultimate Analysis</u>							
	dry wt%						
Carbon	75.28	65.43	85.12	80.60	80.06	74.44	53.54
Hydrogen	2.39	4.43	0.35	0.39	0.87	1.35	NA
Sulfur	2.26	3.81	0.70	1.27	1.64	1.49	NA
Nitrogen	1.25	1.28	1.21	1.29	1.44	1.41	NA
Oxygen (by diff.)	5.75	10.49	1.05	0.02	1.32	1.93	NA
Ash	<u>13.07</u>	<u>14.56</u>	<u>11.57</u>	<u>16.43</u>	<u>14.67</u>	<u>19.38</u>	<u>46.46</u>
	100.00	100.00	100.00	100.00	100.00	100.00	100.00
Heating Value, Btu/lb	ND	11,599	12,504	ND	ND	ND	ND
Particle Density, g/cm ³	ND	1.46	1.82	ND	ND	ND	ND
<u>Particle Size Distribution</u>							
U. S. Mesh	wt% retained on screen						
6	ND	0.00	0.00	0.00	0.00	0.00	ND
12	--	3.88	21.30	15.70	0.00	0.00	--
20	--	17.50	26.90	43.40	0.19	0.00	--
30	--	--	--	--	--	--	--
40	--	40.50	20.80	31.60	2.64	0.00	--
60	--	25.30	11.90	6.82	19.20	1.59	--
70	--	--	--	--	--	--	--
80	--	8.87	6.26	1.14	17.50	1.59	--
100	--	2.11	2.68	0.45	9.62	0.00	--
120	--	--	--	--	--	--	--
140	--	1.00	3.58	0.45	14.20	1.59	--
170	--	--	--	--	--	--	--
200	--	0.33	2.46	0.23	12.10	1.59	--
230	--	0.11	0.67	0.00	4.42	0.00	--
270	--	0.11	0.89	0.00	5.19	1.59	--
325	--	0.11	0.67	0.00	3.65	0.00	--
PAN	--	<u>0.18</u>	<u>1.89</u>	<u>0.21</u>	<u>11.29</u>	<u>92.05</u>	--
	--	100.00	100.00	100.00	100.00	100.00	--

ND = analysis not done

Table 9. ANALYSES OF SOLIDS FROM TEST MG-14
(Test Temperature = 1084°F)

	Feed Mixture	Coal	Diluent	Fluid Bed Char	1st Cyclone Char	1st Cyclone Char	Carry Over Char
<u>Proximate Analysis</u>							
	wt%						
Moisture	2.36	3.60	1.12	0.91	0.86	2.37	7.79
Volatile matter	19.62	35.80	3.44	6.34	7.42	10.30	26.27
Ash	13.48	15.52	11.44	16.99	13.89	18.22	46.60
Fixed carbon	<u>64.54</u>	<u>45.08</u>	<u>84.00</u>	<u>75.76</u>	<u>77.83</u>	<u>69.11</u>	<u>19.34</u>
	100.00	100.00	100.00	100.00	100.00	100.00	100.00
<u>Ultimate Analysis</u>							
	dry wt%						
Carbon	74.42	63.72	85.12	77.31	79.13	73.53	ND
Hydrogen	2.34	4.33	0.35	0.66	1.05	1.19	ND
Sulfur	2.25	3.80	0.70	1.45	1.74	1.42	ND
Nitrogen	1.17	1.13	1.21	1.19	1.33	1.16	ND
Oxygen (by diff.)	6.01	10.97	1.05	2.24	2.74	4.04	ND
Ash	<u>13.81</u>	<u>16.05</u>	<u>11.57</u>	<u>17.15</u>	<u>14.01</u>	<u>18.66</u>	<u>50.54</u>
	100.00	100.00	100.00	100.00	100.00	100.00	100.00
Heating Value, Btu/lb	ND	11,599	12,504	ND	ND	ND	ND
Particle Density, g/cm ³	ND	1.46	1.82	ND	ND	ND	ND
<u>Particle Size Distribution</u>							
U. S. Mesh	wt% retained on screen						
6	ND	0.00	0.00	0.98	0.00	0.00	ND
12	--	3.88	21.30	34.60	0.00	0.00	--
20	--	17.50	26.90	34.80	0.07	0.00	--
30	--	--	--	--	--	--	--
40	--	40.50	20.80	20.60	1.85	0.30	--
60	--	25.30	11.90	5.39	18.05	1.56	--
70	--	--	--	--	--	--	--
80	--	8.87	6.26	1.23	19.10	1.56	--
100	--	2.11	2.68	0.49	10.75	0.97	--
120	--	--	--	--	--	--	--
140	--	1.00	3.58	0.74	14.85	2.32	--
170	--	--	--	--	--	--	--
200	--	0.33	2.46	0.25	11.80	3.00	--
230	--	0.11	0.67	0.25	4.20	0.97	--
270	--	0.11	0.89	0.25	4.72	1.94	--
325	--	0.11	0.67	0.25	3.53	1.94	--
PAN	--	<u>0.18</u>	<u>1.89</u>	<u>0.17</u>	<u>11.15</u>	<u>85.44</u>	--
	--	100.00	100.00	100.00	100.00	100.00	--

ND = analysis not done

Table 10. ANALYSES OF SOLIDS FROM TEST MG-15
(Test Temperature = 1034°F)

	Feed Mixture	Coal	Diluent	Fluid Bed Char	1st Cyclone Char	1st Cyclone Char	Carry Over Char
<u>Proximate Analysis</u>							
	wt%						
Moisture	1.98	2.84	1.12	0.46	0.70	1.59	4.54
Volatile matter	17.85	32.26	3.44	5.31	7.98	11.18	26.68
Ash	12.27	13.09	11.44	14.71	13.17	19.08	64.57
Fixed carbon	<u>67.90</u>	<u>51.81</u>	<u>84.00</u>	<u>79.52</u>	<u>78.15</u>	<u>68.15</u>	<u>4.21</u>
	100.00	100.00	100.00	100.00	100.00	100.00	100.00
<u>Ultimate Analysis</u>							
	dry wt%						
Carbon	76.56	67.99	85.12	80.28	79.91	73.09	32.36
Hydrogen	2.38	4.40	0.35	0.65	1.21	1.24	ND
Sulfur	1.99	3.28	0.70	1.32	1.68	1.21	ND
Nitrogen	1.34	1.46	1.21	1.34	1.52	1.37	ND
Oxygen (by diff.)	5.21	9.41	1.05	1.63	2.42	3.70	ND
Ash	<u>12.52</u>	<u>13.46</u>	<u>11.57</u>	<u>14.78</u>	<u>13.26</u>	<u>19.39</u>	<u>67.64</u>
	100.00	100.00	100.00	100.00	100.00	100.00	100.00
Heating Value, Btu/lb	ND	11,599	12,504	ND	ND	ND	ND
Particle Density, g/cm ³	ND	1.46	1.82	ND	ND	ND	ND
<u>Particle Size Distribution</u>							
U. S. Mesh	wt% retained on screen						
6	ND	0.00	0.00	0.00	0.00	0.00	ND
12	--	3.88	21.30	18.90	0.00	0.00	--
20	--	17.50	26.90	50.76	0.14	0.00	--
30	--	--	--	--	--	--	--
40	--	40.50	20.80	23.00	2.63	0.00	--
60	--	25.30	11.90	4.61	14.42	0.88	--
70	--	--	--	--	--	--	--
80	--	8.87	6.26	1.03	15.62	0.88	--
100	--	2.11	2.68	0.43	10.21	0.88	--
120	--	--	--	--	--	--	--
140	--	1.00	3.58	0.51	16.32	0.88	--
170	--	--	--	--	--	--	--
200	--	0.33	2.46	0.26	13.42	0.88	--
230	--	0.11	0.67	0.08	4.85	0.00	--
270	--	0.11	0.89	0.18	5.40	0.88	--
325	--	0.11	0.67	0.08	3.88	0.88	--
PAN	--	<u>0.18</u>	<u>1.89</u>	<u>0.16</u>	<u>13.11</u>	<u>93.84</u>	--
	--	100.00	100.00	100.00	100.00	100.00	--

ND = analysis not done

Table 11. ANALYSES OF SOLIDS FROM TEST MG-16
(Test Temperature - 1183°F)

	Feed Mixture	Coal	Diluent	Fluid Bed Char	1st Cyclone Char	1st Cyclone Char	Carry Over Char
<u>Proximate Analysis</u>							
	wt%						
Moisture	2.44	3.36	1.12	0.33	0.58	1.36	2.48
Volatile matter	18.28	33.12	3.44	4.76	6.06	10.55	23.17
Ash	14.58	15.60	11.44	18.76	13.47	14.99	74.35
Fixed carbon	64.70	47.92	84.00	76.15	79.89	73.10	0.00
	100.00	100.00	100.00	100.00	100.00	100.00	100.00
<u>Ultimate Analysis</u>							
	dry wt%						
Carbon	74.49	63.86	85.12	78.36	82.12	77.27	23.74
Hydrogen	2.17	3.99	0.35	0.36	1.05	1.39	ND
Sulfur	2.15	3.60	0.70	1.22	1.68	1.39	ND
Nitrogen	1.27	1.33	1.21	1.15	1.53	1.63	ND
Oxygen (by diff.)	6.06	11.07	1.05	1.85	0.47	3.29	ND
Ash	13.86	16.15	11.57	17.06	13.15	15.03	76.26
	100.00	100.00	100.00	100.00	100.00	100.00	100.00
Heating Value, Btu/lb	ND	11,599	12,504	ND	ND	ND	ND
Particle Density, g/cm ³	ND	1.46	1.82	ND	ND	ND	ND
<u>Particle Size Distribution</u>							
U. S. Mesh	wt% retained on screen						
6	0.00	0.00	0.00	0.00	0.00	ND	ND
12	11.30	3.88	21.30	20.80	0.00	--	--
20	26.90	17.50	26.90	59.10	0.25	--	--
30	--	--	--	--	--	--	--
40	36.70	40.50	20.80	17.60	8.17	--	--
60	17.60	25.30	11.90	1.73	17.10	--	--
70	--	--	--	--	--	--	--
80	4.64	8.87	6.26	0.16	7.18	--	--
100	1.19	2.11	2.68	0.16	3.71	--	--
120	--	--	--	--	--	--	--
140	0.83	1.00	3.58	0.16	7.92	--	--
170	--	--	--	--	--	--	--
200	0.24	0.33	2.46	0.16	8.17	--	--
230	0.12	0.11	0.67	0.00	4.46	--	--
270	0.12	0.11	0.89	0.00	5.69	--	--
325	0.12	0.11	0.67	0.00	4.70	--	--
PAN	0.24	0.18	1.89	0.13	32.65	--	--
	100.00	100.00	100.00	100.00	100.00	--	--

ND = analysis not done

Table 12. ANALYSES OF SOLIDS FROM TEST MG-18
(Test Temperature = 1178°F)

	Feed Mixture	Coal	Diluent	Fluid Bed Char	1st Cyclone Char	1st Cyclone Char	Carry Over Char
<u>Proximate Analysis</u>							
	wt%						
Moisture	3.59	6.53	0.65	0.21	0.77	1.29	0.00
Volatile matter	17.36	31.05	3.67	5.50	7.25	11.34	43.03
Ash	11.83	11.44	12.22	15.71	15.64	16.22	17.58
Fixed carbon	<u>67.22</u>	<u>50.98</u>	<u>83.46</u>	<u>78.58</u>	<u>76.34</u>	<u>71.15</u>	<u>39.39</u>
	100.00	100.00	100.00	100.00	100.00	100.00	100.00
<u>Ultimate Analysis</u>							
	dry wt%						
Carbon	77.07	70.27	83.87	80.44	78.21	74.36	70.81
Hydrogen	2.26	4.08	0.44	0.49	1.09	1.85	1.20
Sulfur	1.98	3.21	0.75	1.15	1.92	2.19	1.53
Nitrogen	1.36	1.49	1.23	1.28	1.44	1.66	1.28
Oxygen (by diff.)	5.06	8.71	1.41	0.90	1.58	3.51	7.60
Ash	<u>12.27</u>	<u>12.24</u>	<u>12.30</u>	<u>15.74</u>	<u>15.76</u>	<u>16.43</u>	<u>17.58</u>
	100.00	100.00	100.00	100.00	100.00	100.00	100.00
Heating Value, Btu/lb	ND	11,599	12,504	ND	ND	ND	ND
Particle Density, g/cm ³	ND	1.46	1.82	ND	ND	ND	ND
<u>Particle Size Distribution</u>							
U. S. Mesh	wt% retained on screen						
6	0.00	0.00	0.00	0.00	0.00	0.00	0.00
12	14.90	3.88	19.30	8.32	0.14	0.00	0.00
20	30.30	17.50	31.40	35.90	2.43	0.65	0.00
30	--	--	--	--	--	--	--
40	33.20	40.50	37.00	50.40	23.20	4.58	0.00
60	14.70	25.30	11.90	4.85	27.20	11.10	0.00
70	--	--	--	--	--	--	--
80	4.27	8.87	0.17	0.17	5.00	3.92	0.00
100	1.20	2.11	0.00	0.00	2.57	1.31	0.00
120	--	--	--	--	--	--	--
140	0.68	1.00	0.00	0.17	4.46	3.92	0.00
170	--	--	--	--	--	--	--
200	0.34	0.33	0.00	0.00	5.68	3.27	0.00
230	0.17	0.11	0.17	0.00	2.84	0.65	0.00
270	0.00	0.11	0.00	0.00	3.78	1.31	0.00
325	0.00	0.11	0.00	0.00	3.51	1.96	0.00
PAN	<u>0.34</u>	<u>0.18</u>	<u>0.06</u>	<u>0.19</u>	<u>19.19</u>	<u>67.33</u>	<u>100.00</u>
	100.00	100.00	100.00	100.00	100.00	100.00	100.00

ND = analysis not done

Table 13. ANALYSES OF SOLIDS FROM TEST MG-19
(Test Temperature = 1102°F)

	Feed Mixture	Coal	Diluent	Fluid Bed Char	1st Cyclone Char	1st Cyclone Char	Carry Over Char
<u>Proximate Analysis</u>							
	wt%						
Moisture	4.02	6.92	1.12	0.57	0.92	ND	3.93
Volatile matter	18.29	33.14	3.44	5.99	12.63	--	31.43
Ash	12.17	12.90	11.44	15.00	16.53	--	61.07
Fixed carbon	<u>65.52</u>	<u>47.04</u>	<u>84.00</u>	<u>78.44</u>	<u>69.92</u>	--	<u>3.57</u>
	100.00	100.00	100.00	100.00	100.00	--	100.00
<u>Ultimate Analysis</u>							
	dry wt%						
Carbon	77.18	69.24	85.12	80.09	73.27	ND	36.43
Hydrogen	2.43	4.51	0.35	0.81	1.97	--	ND
Sulfur	2.04	3.38	0.70	1.43	2.68	--	ND
Nitrogen	1.39	1.57	1.21	1.41	1.51	--	ND
Oxygen (by diff.)	4.28	7.51	1.05	1.17	3.89	--	ND
Ash	<u>12.68</u>	<u>13.79</u>	<u>11.57</u>	<u>15.09</u>	<u>16.68</u>	--	<u>63.57</u>
	100.00	100.00	100.00	100.00	100.00	100.00	100.00
Heating Value, Btu/lb	ND	11,599	12,504	ND	ND	ND	ND
Particle Density, g/cm ³	ND	1.46	1.82	ND	ND	ND	ND
<u>Particle Size Distribution</u>							
U. S. Mesh	wt% retained on screen						
6	0.00	0.00	0.00	0.00	0.00	ND	ND
12	11.30	3.88	21.30	20.80	0.00	--	--
20	26.90	17.50	26.90	59.10	0.25	--	--
30	--	--	--	--	--	--	--
40	36.70	40.50	20.80	17.60	8.17	--	--
60	17.60	25.30	11.90	1.73	17.10	--	--
70	--	--	--	--	--	--	--
80	4.64	8.87	6.26	0.16	7.18	--	--
100	1.19	2.11	2.68	0.16	3.71	--	--
120	--	--	--	--	--	--	--
140	0.83	1.00	3.58	0.16	7.92	--	--
170	--	--	--	--	--	--	--
200	0.24	0.33	2.46	0.16	8.17	--	--
230	0.12	0.11	0.67	0.00	4.46	--	--
270	0.12	0.11	0.89	0.00	5.69	--	--
325	0.12	0.11	0.67	0.00	4.70	--	--
PAN	<u>0.24</u>	<u>0.18</u>	<u>1.89</u>	<u>0.13</u>	<u>32.65</u>	--	--
	100.00	100.00	100.00	100.00	100.00	--	--

ND = analysis not done

Table 14. ANALYSES OF SOLIDS FROM TEST MG-21
(Test Temperature = 1109°F)

	Feed Mixture	Coal	Diluent	Fluid Bed Char	1st Cyclone Char	1st Cyclone Char	Carry Over Char
<u>Proximate Analysis</u>							
	wt%						
Moisture	3.46	5.79	1.12	0.38	0.74	1.23	7.46
Volatile matter	17.34	31.24	3.44	6.03	13.15	13.59	25.42
Ash	11.39	11.34	11.44	14.40	13.98	15.28	51.31
Fixed carbon	<u>67.81</u>	<u>51.63</u>	<u>84.00</u>	<u>79.19</u>	<u>72.13</u>	<u>69.90</u>	<u>15.81</u>
	100.00	100.00	100.00	100.00	100.00	100.00	100.00
<u>Ultimate Analysis</u>							
	dry wt%						
Carbon	77.70	70.27	85.12	80.09	74.75	73.93	44.55
Hydrogen	2.27	4.19	0.35	0.74	2.21	2.14	ND
Sulfur	1.89	3.07	0.70	1.39	2.49	2.07	ND
Nitrogen	1.51	1.81	1.21	1.50	1.79	1.88	ND
Oxygen (by diff.)	4.83	8.64	1.05	1.82	4.68	4.51	ND
Ash	<u>11.80</u>	<u>12.02</u>	<u>11.57</u>	<u>14.46</u>	<u>14.08</u>	<u>15.47</u>	<u>55.45</u>
	100.00	100.00	100.00	100.00	100.00	100.00	100.00
Heating Value, Btu/lb	ND	11,599	12,504	ND	ND	ND	ND
Particle Density, g/cm ³	ND	1.46	1.82	ND	ND	ND	ND
<u>Particle Size Distribution</u>							
U. S. Mesh	wt% retained on screen						
6	0.00	0.00	0.00	0.00	0.00	0.00	ND
12	16.30	3.88	19.30	18.20	0.00	0.00	--
20	29.80	17.50	31.40	54.20	0.00	0.00	--
30	--	--	--	--	--	--	--
40	34.00	40.50	37.00	23.60	5.36	0.57	--
60	14.00	25.30	11.90	2.40	11.10	2.27	--
70	--	--	--	--	--	--	--
80	3.51	8.87	0.17	0.40	5.16	1.70	--
100	0.84	2.11	0.00	0.20	3.37	1.14	--
120	--	--	--	--	--	--	--
140	0.70	1.00	0.00	0.20	7.94	2.27	--
170	--	--	--	--	--	--	--
200	0.28	0.33	0.00	0.20	11.30	3.41	--
230	0.14	0.11	0.17	0.20	5.16	2.27	--
270	0.14	0.11	0.00	0.20	7.74	4.55	--
325	0.14	0.11	0.00	0.00	6.75	2.27	--
PAN	<u>0.15</u>	<u>0.18</u>	<u>0.16</u>	<u>0.20</u>	<u>36.12</u>	<u>79.55</u>	--
	100.00	100.00	100.00	100.00	100.00	100.00	--

ND = analysis not done

Table 15. ANALYSES OF SOLIDS FROM TEST MG-22
(Test Temperature = 1147°F)

	Feed Mixture	Coal	Diluent	Fluid Bed Char	1st Cyclone Char	1st Cyclone Char	Carry Over Char
<u>Proximate Analysis</u>							
	wt%						
Moisture	3.49	5.86	1.12	0.25	0.54	0.69	1.76
Volatile matter	17.88	32.31	3.44	5.88	12.17	12.52	30.88
Ash	11.89	12.33	11.44	15.56	15.56	14.61	64.92
Fixed carbon	66.74	49.50	84.00	78.31	71.73	72.18	2.44
	100.00	100.00	100.00	100.00	100.00	100.00	100.00
<u>Ultimate Analysis</u>							
	dry wt%						
Carbon	76.63	68.14	85.12	78.90	73.66	74.54	33.92
Hydrogen	2.26	4.16	0.35	0.73	1.89	2.12	NA
Sulfur	2.00	3.30	0.70	1.45	2.51	2.49	NA
Nitrogen	1.38	1.55	1.21	1.39	1.65	1.70	NA
Oxygen (by diff.)	5.41	9.79	1.05	1.93	4.66	4.44	NA
Ash	12.32	13.06	11.57	15.60	15.63	14.71	66.08
	100.00	100.00	100.00	100.00	100.00	100.00	100.00
Heating Value, Btu/lb	ND	11,599	12,504	ND	ND	ND	ND
Particle Density, g/cm ³	ND	1.46	1.82	ND	ND	ND	ND
<u>Particle Size Distribution</u>							
U. S. Mesh	wt% retained on screen						
6	0.00	0.00	0.00	0.14	0.00	0.00	ND
12	15.05	3.88	19.30	16.13	0.00	0.00	--
20	29.70	17.50	31.40	59.97	0.10	0.00	--
30	--	--	--	--	--	--	--
40	34.05	40.50	37.00	20.23	7.39	1.87	--
60	14.80	25.30	11.90	1.79	17.00	7.46	--
70	--	--	--	--	--	--	--
80	3.98	8.87	0.17	0.38	7.39	4.10	--
100	1.06	2.11	0.00	0.19	4.43	3.36	--
120	--	--	--	--	--	--	--
140	0.71	1.00	0.00	0.26	9.15	4.85	--
170	--	--	--	--	--	--	--
200	0.30	0.33	0.00	0.32	10.90	11.90	--
230	0.00	0.11	0.17	0.13	5.17	1.49	--
270	0.12	0.11	0.00	0.20	6.75	7.84	--
325	0.00	0.11	0.00	0.07	6.19	2.99	--
PAN	0.23	0.18	0.16	0.19	25.53	54.14	--
	100.00	100.00	100.00	100.00	100.00	100.00	--

ND = analysis not done

Table 16. ANALYSES OF SOLIDS FROM TEST MG-25
(Test Temperature = 1134°F)

	Feed Mixture	Coal	Diluent	Fluid Bed Char	1st Cyclone Char	1st Cyclone Char	Carry Over Char
<u>Proximate Analysis</u>							
	wt%						
Moisture	2.86	5.34	0.38	0.27	0.38	0.34	0.67
Volatile matter	16.27	26.51	6.03	7.44	15.33	14.80	22.72
Ash	12.92	11.44	14.40	16.63	17.34	16.36	22.29
Fixed carbon	<u>67.95</u>	<u>56.71</u>	<u>79.19</u>	<u>75.66</u>	<u>66.95</u>	<u>68.50</u>	<u>54.32</u>
	100.00	100.00	100.00	100.00	100.00	100.00	100.00
<u>Ultimate Analysis</u>							
	dry wt%						
Carbon	76.21	72.33	80.09	76.56	69.67	70.89	77.56
Hydrogen	2.16	3.58	0.74	1.05	2.38	2.35	ND
Sulfur	2.09	2.79	1.39	1.84	2.99	3.04	ND
Nitrogen	1.38	1.26	1.50	1.44	1.67	1.64	ND
Oxygen (by diff.)	4.86	7.90	1.82	2.43	5.88	5.66	ND
Ash	<u>13.30</u>	<u>12.14</u>	<u>14.46</u>	<u>16.68</u>	<u>17.41</u>	<u>16.42</u>	<u>22.44</u>
	100.00	100.00	100.00	100.00	100.00	100.00	100.00
Heating Value, Btu/lb	ND	11,599	12,504	ND	ND	ND	ND
Particle Density, g/cm ³	ND	1.46	1.82	ND	ND	ND	ND
<u>Particle Size Distribution</u>							
U. S. Mesh	wt% retained on screen						
6	ND	0.00	0.00	ND	ND	ND	ND
12	--	3.88	19.30	--	--	--	--
20	--	17.50	31.40	--	--	--	--
30	--	--	--	--	--	--	--
40	--	40.50	37.00	--	--	--	--
60	--	25.30	11.90	--	--	--	--
70	--	--	--	--	--	--	--
80	--	8.87	0.17	--	--	--	--
100	--	2.11	0.00	--	--	--	--
120	--	--	--	--	--	--	--
140	--	1.00	0.00	--	--	--	--
170	--	--	--	--	--	--	--
200	--	0.33	0.00	--	--	--	--
230	--	0.11	0.17	--	--	--	--
270	--	0.11	0.00	--	--	--	--
325	--	0.11	0.00	--	--	--	--
PAN	--	<u>0.18</u>	<u>0.16</u>	--	--	--	--
	--	100.00	100.00	--	--	--	--

ND = analysis not done

Table 17. ANALYSES OF SOLIDS FROM TEST MG-28
(Test Temperature = 1149°F)

	Feed Mixture	Coal	Diluent	Fluid Bed Char	1st Cyclone Char	1st Cyclone Char	Carry Over Char
<u>Proximate Analysis</u>							
	wt%						
Moisture	0.80	0.16	1.12	0.17	0.19	0.02	1.58
Volatile matter	9.23	20.81	3.44	3.94	7.92	17.37	13.46
Ash	11.55	11.77	11.44	12.77	16.10	31.56	8.31
Fixed carbon	<u>78.42</u>	<u>67.26</u>	<u>84.00</u>	<u>83.12</u>	<u>75.79</u>	<u>51.05</u>	<u>76.65</u>
	100.00	100.00	100.00	100.00	100.00	100.00	100.00
<u>Ultimate Analysis</u>							
	dry wt%						
Carbon	83.02	78.82	85.12	83.51	77.05	57.54	91.56
Hydrogen	1.49	3.77	0.35	0.64	1.83	2.24	ND
Sulfur	0.98	1.54	0.70	0.95	1.52	0.18	ND
Nitrogen	1.29	1.45	1.21	1.36	1.34	1.40	ND
Oxygen (by diff.)	1.58	2.64	1.05	0.75	2.13	7.07	ND
Ash	<u>11.64</u>	<u>11.78</u>	<u>11.57</u>	<u>12.79</u>	<u>16.13</u>	<u>31.57</u>	<u>8.44</u>
	100.00	100.00	100.00	100.00	100.00	100.00	100.00
Heating Value, Btu/lb	ND	14,535	12,504	ND	ND	ND	ND
Particle Density, g/cm ³	ND	ND	1.82	ND	ND	ND	ND
<u>Particle Size Distribution</u>							
U. S. Mesh	wt% retained on screen						
6	ND	0.00	0.00	ND	ND	ND	ND
12	--	0.00	19.30	--	--	--	--
20	--	0.32	31.40	--	--	--	--
30	--	--	--	--	--	--	--
40	--	9.83	37.00	--	--	--	--
60	--	14.40	11.90	--	--	--	--
70	--	--	--	--	--	--	--
80	--	12.10	0.17	--	--	--	--
100	--	7.09	0.00	--	--	--	--
120	--	--	--	--	--	--	--
140	--	13.60	0.00	--	--	--	--
170	--	--	--	--	--	--	--
200	--	7.73	0.00	--	--	--	--
230	--	1.29	0.17	--	--	--	--
270	--	3.55	0.00	--	--	--	--
325	--	3.06	0.00	--	--	--	--
PAN	--	<u>27.03</u>	<u>0.16</u>	--	--	--	--
	--	100.00	100.00	--	--	--	--

ND = analysis not done

Table 18. ANALYSES OF SOLIDS FROM TEST MG-30
(Test Temperature = 1050°F)

	Feed Mixture	Coal	Diluent	Fluid Bed Char	1st Cyclone Char	1st Cyclone Char	Carry Over Char
<u>Proximate Analysis</u>							
	wt%						
Moisture	0.88	0.40	1.12	0.23	0.53	0.59	0.59
Volatile matter	9.88	22.76	3.44	4.55	9.04	21.84	19.77
Ash	11.23	9.85	11.44	12.21	14.70	43.20	4.62
Fixed carbon	<u>78.01</u>	<u>66.99</u>	<u>84.00</u>	<u>83.01</u>	<u>75.73</u>	<u>34.37</u>	<u>75.02</u>
	100.00	100.00	100.00	100.00	100.00	100.00	100.00
<u>Ultimate Analysis</u>							
	dry wt%						
Carbon	82.15	76.21	85.12	82.71	77.40	44.02	95.47
Hydrogen	1.51	3.83	0.35	0.82	1.78	2.23	ND
Sulfur	0.96	1.48	0.70	0.94	1.40	1.01	ND
Nitrogen	1.34	1.60	1.21	1.39	1.35	0.98	ND
Oxygen (by diff.)	3.03	6.99	1.05	2.17	3.49	10.79	ND
Ash	<u>11.01</u>	<u>9.89</u>	<u>11.57</u>	<u>11.97</u>	<u>14.58</u>	<u>40.97</u>	<u>4.53</u>
	100.00	100.00	100.00	100.00	100.00	100.00	100.00
Heating Value, Btu/lb	ND	14,535	12,504	ND	ND	ND	ND
Particle Density, g/cm ³	ND	ND	1.82	ND	ND	ND	ND
<u>Particle Size Distribution</u>							
U. S. Mesh	wt% retained on screen						
6	ND	0.00	0.00	ND	ND	ND	ND
12	--	0.00	19.30	--	--	--	--
20	--	0.32	31.40	--	--	--	--
30	--	--	--	--	--	--	--
40	--	9.83	37.00	--	--	--	--
60	--	14.40	11.90	--	--	--	--
70	--	--	--	--	--	--	--
80	--	12.10	0.17	--	--	--	--
100	--	7.09	0.00	--	--	--	--
120	--	--	--	--	--	--	--
140	--	13.60	0.00	--	--	--	--
170	--	--	--	--	--	--	--
200	--	7.73	0.00	--	--	--	--
230	--	1.29	0.17	--	--	--	--
270	--	3.55	0.00	--	--	--	--
325	--	3.06	0.00	--	--	--	--
PAN	--	<u>27.03</u>	<u>0.16</u>	--	--	--	--
	--	100.00	100.00	--	--	--	--

ND = analysis not done

Table 19, Part 1. OILS/TARS ELEMENTAL ANALYSES AND SIMULATED DISTILLATION

Test Number	SD-6	MG-3	MG-5	MG-11
Test Temperature, °F	1300	1325	1100	1390
Elemental Analysis of				
<u>Oils and Tars^a</u>	----- dry wt% -----			
Ash ^b	0.57	0.09	0.17	0.53
Carbon	78.71	80.98	78.18	82.29
Hydrogen	6.87	6.17	7.32	6.08
Nitrogen	ND	1.32	0.96	1.26
Sulfur	2.28	2.21	1.99	3.21
Oxygen (by diff.)	ND	9.23	11.38	6.63
Total	ND	100.00	100.00	100.00
H/C Atomic Ratio	1.04	0.91	1.12	0.88
Simulate Distillation				
by Gas Chromatography ^c				
<u>Cumulative Wt% Recovered</u>	----- Boiling Point, °F -----			
5	435	365	367	340
10	498	416	440	390
15	540	462	498	437
20	575	506	550	482
30	637	590	645	568
40	693	672	735	652
50	747	758	826	739
60	802	856	926	831
70	864	995	1057	939
EP (end point) ^d	1093	1068	1068	1093
% Residue at EP	13.7	27.6	29.4	20.3

a Determined by evaporation at 100°F, 15-20 mm Hg; light oils boiling below approximately 300°F are not included.

b Corrected for THF-soluble FeCl₃ which was determined to be a contaminant from corrosion of stainless steel exposed to the hot methylene chloride quench solvent.

c Correction applied for heteroatom content of coal liquids, which is not accounted for in standard simulated distillation method for petroleum-based liquids.

d Characteristic of chromatographic column and method, not necessarily true end point of distillation.

Table 19, Part 2. OILS/TARS ELEMENTAL ANALYSES AND SIMULATED DISTILLATION

Test Number	MG-12	MG-14	MG-15	MG-16
Test Temperature, °F	1252	1084	1034	1183
Elemental Analysis of				
<u>Oils and Tars^a</u>	----- dry wt% -----			
Ash ^b	0.36	0.25	0.65	0.42
Carbon	75.74	77.97	73.86	74.24
Hydrogen	6.21	6.76	6.85	6.74
Nitrogen	1.27	0.98	0.79	0.78
Sulfur	2.03	1.83	1.57	1.60
Oxygen (by diff.)	<u>14.39</u>	<u>12.21</u>	<u>16.28</u>	<u>16.22</u>
Total	100.00	100.00	100.00	100.00
H/C Atomic Ratio	0.98	1.03	1.11	1.08
Simulate Distillation				
by Gas Chromatography ^c				
<u>Cumulative Wt% Recovered</u>	----- Boiling Point, °F -----			
5	353	388	351	343
10	433	487	408	404
15	506	576	466	459
20	573	661	525	510
30	705	840	652	610
40	844	--	810	713
50	1023	--	--	833
60	--	--	--	--
70	--	--	--	--
EP (end point) ^d	1093	1093	1093	1093
% Residue at EP	47.6	60.6	53.4	41.4

- a Determined by evaporation at 100°F, 15-20 mm Hg; light oils boiling below approximately 300°F are not included.
- b Corrected for THF-soluble FeCl₃ which was determined to be a contaminant from corrosion of stainless steel exposed to the hot methylene chloride quench solvent.
- c Correction applied for heteroatom content of coal liquids, which is not accounted for in standard simulated distillation method for petroleum-based liquids.
- d Characteristic of chromatographic column and method, not necessarily true end point of distillation.

Table 19, Part 3. OILS/TARS ELEMENTAL ANALYSES AND SIMULATED DISTILLATION

Test Number	MG-18	MG-19	MG-21	MG-22
Test Temperature, °F	1178	1102	1109	1147
Elemental Analysis of				
<u>Oils and Tars^a</u>				
	----- dry wt% -----			
Ash ^b	0.29	0.00	0.47	0.00
Carbon	76.57	77.98	77.57	77.56
Hydrogen	6.71	7.06	6.88	6.90
Nitrogen	1.00	0.92	1.00	0.85
Sulfur	1.74	1.93	1.93	1.84
Oxygen (by diff.)	<u>13.68</u>	<u>12.11</u>	<u>12.15</u>	<u>12.84</u>
Total	100.00	100.00	100.00	100.00
H/C Atomic Ratio	1.04	1.08	1.06	1.06
Simulate Distillation				
by Gas Chromatography ^c				
<u>Cumulative Wt% Recovered</u>	<u>Boiling Point, °F</u> -----			
5	358	351	359	359
10	418	438	430	425
15	475	509	492	484
20	530	572	550	541
30	644	690	661	650
40	771	810	776	765
50	960	954	912	909
60	--	--	--	--
70	--	--	--	--
EP (end point) ^d	1068	1068	1068	1068
% Residue at EP	48.3	44.9	43.0	44.7

a Determined by evaporation at 100°F, 15-20 mm Hg; light oils boiling below approximately 300°F are not included.

b Corrected for THF-soluble FeCl₃ which was determined to be a contaminant from corrosion of stainless steel exposed to the hot methylene chloride quench solvent.

c Correction applied for heteroatom content of coal liquids, which is not accounted for in standard simulated distillation method for petroleum-based liquids.

d Characteristic of chromatographic column and method, not necessarily true end point of distillation.

Table 19, Part 4. OILS/TARS ELEMENTAL ANALYSES AND SIMULATED DISTILLATION

Test Number	MG-25	MG-28	MG-30
Test Temperature, °F	1134	1149	1050
Elemental Analysis of			
<u>Oils and Tars^a</u>	----- dry wt% -----		
Ash	0.17	1.14	0.77
Carbon	78.45	79.60	82.04
Hydrogen	7.09	7.09	7.34
Nitrogen	0.85	0.86	0.82
Sulfur	2.18	0.83	0.74
Oxygen (by diff.)	<u>11.26</u>	<u>10.48</u>	<u>8.29</u>
Total	100.00	100.00	100.00
H/C Atomic Ratio	1.08	1.06	1.07
Simulate Distillation			
by Gas Chromatography ^b			
<u>Cumulative Wt% Recovered</u>	----- Boiling Point, °F -----		
5	374	376	313
10	449	465	428
15	511	542	516
20	567	615	593
30	672	754	730
40	776	904	861
50	897	1068	995
60	--	--	--
70	--	--	--
EP (end point) ^c	1068	1068	1068
% Residue at EP	41.6	51.8	45.0

a Determined by evaporation at 100°F, 15-20 mm Hg; light oils boiling below approximately 300°F are not included.

b Correction applied for heteroatom content of coal liquids, which is not accounted for in standard simulated distillation method for petroleum-based liquids.

c Characteristic of chromatographic column and method, not necessarily true end point of distillation.

Table 20, Part 1. COMPONENT ANALYSES OF FULL-RANGE OILS/TARS

Test Number	SD-6	MG-3	MG-5	MG-11
Test Temperature, °F	1300	1325	1100	1390
<u>Component</u>				
	----- Wt% of total oils/tars ^a -----			
Benzene	1.7	2.2	0.9	8.7
Toluene	2.0	0.2	1.6	5.5
Xylenes	1.8	1.1	1.4	2.8
Ethylbenzene	0.2	0.1	0.3	2.2
Indene	1.4	1.3	0.2	2.0
Styrene	0.8	0.6	0.3	1.2
Other Light Oils	<u>2.2</u>	<u>4.8</u>	<u>1.3</u>	<u>1.4</u>
Total Light Oil ^b	10.1	10.2	6.0	23.8
Phenol	4.4	2.3	2.0	2.8
Cresols	6.4	3.1	2.8	2.0
Xylenols	3.1	1.7	0.8	0.6
Naphthalene	1.2	1.2	0.3	2.0
Other Middle Oils	<u>2.1</u>	<u>15.7</u>	<u>13.3</u>	<u>13.6</u>
Total Middle Oil ^c	17.2	24.0	19.2	21.0
Heavy Oil ^d	26.5	17.9	17.4	15.3
Pitch ^e	<u>46.2</u>	<u>47.9</u>	<u>57.4</u>	<u>39.9</u>
Total Oils and Tars	100.0	100.0	100.0	100.0

a Includes light oils that are not included in the oils and tars of Table 19.

b Atmospheric boiling point < 360°F; estimated from simulated distillation data.

c Atmospheric boiling point 360° to 590°F

d Atmospheric boiling point 590° to 750°F

e Atmospheric boiling point > 750°F

Table 20, Part 2. COMPONENT ANALYSES OF FULL-RANGE OILS/TARS

Test Number	MG-12	MG-14	MG-15	MG-16
Test Temperature, °F	1252	1084	1034	1183
<u>Component</u>				
	----- Wt% of total oils/tars ^a -----			
Benzene	1.2	0.9	0.5	0.6
Toluene	1.3	1.5	0.8	0.9
Xylenes	0.8	0.5	0.5	0.6
Ethylbenzene	0.6	0.1	0.1	0.1
Indene	0.4	0.2	0.1	0.2
Styrene	0.3	0.2	0.2	0.1
Other Light Oils	<u>4.3</u>	<u>6.0</u>	<u>5.4</u>	<u>6.0</u>
Total Light Oil ^b	8.9	9.4	7.6	8.5
Phenol	1.0	1.2	0.3	0.9
Cresols	1.4	1.7	1.7	2.2
Xylenols	0.6	1.4	1.3	2.1
Naphthalene	0.5	0.1	0.1	0.1
Other middle oils	<u>11.8</u>	<u>6.9</u>	<u>15.7</u>	<u>15.9</u>
Total Middle Oil ^c	15.3	11.3	19.1	21.2
Heavy Oil ^d	11.7	8.8	11.1	15.0
Pitch ^e	<u>64.1</u>	<u>70.5</u>	<u>62.2</u>	<u>55.3</u>
	100.0	100.0	100.0	100.0

a Includes light oils that are not included in the oils and tars of Table 19.

b Atmospheric boiling point < 360°F; estimated from simulated distillation data.

c Atmospheric boiling point 360° to 590°F

d Atmospheric boiling point 590° to 750°F

e Atmospheric boiling point > 750°F

Table 20, Part 3. COMPONENT ANALYSES OF FULL-RANGE OILS/TARS

Test Number	MG-18	MG-19	MG-21	MG-22
Test Temperature, °F	1178	1102	1109	1147
<u>Component</u>				
	----- Wt% of total oils/tars ^a -----			
Benzene	0.7	0.1	0.5	0.8
Toluene	0.8	0.3	0.4	0.7
Xylenes	0.5	0.2	0.3	0.4
Ethylbenzene	0.1	0.04	0.1	0.1
Indene	0.3	0.1	0.1	0.2
Styrene	0.2	0.1	0.1	0.1
Other Light Oils	<u>4.8</u>	<u>5.4</u>	<u>4.8</u>	<u>4.7</u>
Total Light Oil ^b	7.4	6.2	6.3	7.0
Phenol	0.8	0.6	0.6	0.8
Cresols	2.1	1.6	1.6	2.1
Xylenols	1.9	1.6	1.9	2.3
Naphthalene	0.5	0.3	0.1	0.4
Other Middle Oils	<u>14.4</u>	<u>11.8</u>	<u>14.1</u>	<u>13.4</u>
Total Middle Oil ^c	19.7	15.9	18.3	19.0
Heavy Oil ^d	12.9	13.5	14.1	14.0
Pitch ^e	<u>60.1</u>	<u>64.4</u>	<u>61.3</u>	<u>60.0</u>
Total Oils and Tars	100.0	100.0	100.0	100.0

a Includes light oils that are not included in the oils and tars of Table 19.

b Atmospheric boiling point < 360°F; estimated from simulated distillation data.

c Atmospheric boiling point 360° to 590°F

d Atmospheric boiling point 590° to 750°F

e Atmospheric boiling point > 750°F

Table 20, Part 4. COMPONENT ANALYSES OF FULL-RANGE OILS/TARS

Test Number	MG-25	MG-28	MG-30
Test Temperature, °F	1134	1149	1050
<u>Component</u>			
	----- Wt% of total oils/tars ^a -----		
Benzene	0.3	0.5	0.3
Toluene	0.5	0.7	0.6
Xylenes	0.4	0.5	0.6
Ethylbenzene	0.1	0.1	0.1
Indene	0.1	0.2	0.1
Styrene	0.1	0.05	0.1
Other Light Oils	<u>4.2</u>	<u>7.3</u>	<u>8.7</u>
Total Light Oil ^b	5.7	9.3	10.5
Phenol	0.8	0.4	0.4
Cresols	1.9	1.0	1.0
Xylenols	3.8	1.6	1.3
Naphthalene	0.1	0.6	0.1
Other Middle Oils	<u>11.0</u>	<u>9.7</u>	<u>9.7</u>
Total Middle Oil ^c	17.6	13.3	12.5
Heavy Oil ^d	15.2	10.8	11.2
Pitch ^e	<u>61.5</u>	<u>66.6</u>	<u>65.8</u>
Total Oils and Tars	100.0	100.0	100.0

a Includes light oils that are not included in the oils and tars of Table 19.

b Atmospheric boiling point < 360°F; estimated from simulated distillation data.

c Atmospheric boiling point 360° to 590°F

d Atmospheric boiling point 590° to 750°F

e Atmospheric boiling point > 750°F

Table 21, Part 1. GAS COMPOSITIONS

Test Number	<u>SD-6</u>	<u>MG-3</u>	<u>MG-5</u>	<u>MG-11</u>
Test Temperature, °F	1300	1325	1100	1390
<u>Component</u>	----- Mol % in gas, nitrogen-free -----			
H ₂	52.1	30.3	17.8	44.3
CO	15.3	18.0	15.1	17.0
CO ₂	8.1	8.6	16.0	9.1
CH ₄	19.3	29.9	31.4	18.8
C ₂ H ₄	1.7	5.9	7.5	6.0
C ₂ H ₆	2.7	3.0	5.1	1.1
C ₃ H ₆	0.6	3.6	5.0	1.2
C ₃ H ₈	0.2	0.7	2.1	0.1
H ₂ S	<u>NA</u>	<u>NA</u>	<u>NA</u>	<u>2.4</u>
Total	100.0	100.0	100.0	100.0
Molecular Weight	13.6	18.7	23.4	16.0
Higher Heating Value, Btu/scf	508	712	810	546

Table 21, Part 2. GAS COMPOSITIONS

Test Number	<u>MG-12</u>	<u>MG-14</u>	<u>MG-15</u>	<u>MG-16</u>
Test Temperature, °F	1252	1084	1034	1183
<u>Component</u>	----- Mol % in gas, nitrogen-free -----			
H ₂	37.5	28.4	29.5	33.6
CO	16.1	13.0	10.6	12.7
CO ₂	8.7	10.3	12.9	10.1
CH ₄	23.3	28.1	28.1	28.1
C ₂ H ₄	6.3	6.5	5.8	4.7
C ₂ H ₆	2.5	4.3	4.7	3.7
C ₃ H ₆	2.1	2.7	2.5	2.5
C ₃ H ₈	0.2	1.0	0.6	1.5
H ₂ S	<u>3.3</u>	<u>5.7</u>	<u>5.3</u>	<u>3.1</u>
Total	100.0	100.0	100.0	100.0
Molecular Weight	17.5	19.9	19.9	18.4
Higher Heating Value, Btu/scf	626	719	694	689

Table 21, Part 3. GAS COMPOSITIONS

Test Number	<u>MG-18</u>	<u>MG-19</u>	<u>MG-21</u>	<u>MG-22</u>
Test Temperature, °F	1178	1102	1109	1147
<u>Component</u>	----- Mol % in gas, nitrogen-free -----			
H ₂	40.4	17.1	18.6	23.1
CO	11.5	13.4	13.6	13.1
CO ₂	9.5	9.5	10.0	7.5
CH ₄	26.0	40.2	38.3	37.1
C ₂ H ₄	4.8	5.7	5.9	5.7
C ₂ H ₆	3.2	7.4	6.7	5.9
C ₃ H ₆	2.2	3.0	3.0	3.8
C ₃ H ₈	0.5	1.3	1.4	1.3
H ₂ S	<u>1.9</u>	<u>2.4</u>	<u>2.5</u>	<u>2.5</u>
Total	100.0	100.0	100.0	100.0
Molecular Weight	16.5	21.2	21.1	19.8
Higher Heating Value, Btu/scf	640	841	823	824

Table 21, Part 4. GAS COMPOSITIONS

Test Number	<u>MG-25</u>	<u>MG-28</u>	<u>MG-30</u>
Test Temperature, °F	1134	1149	1050
<u>Component</u>	----- Mol % in gas, nitrogen-free -----		
H ₂	17.4	27.1	18.9
CO	15.1	3.8	1.9
CO ₂	11.3	8.2	8.9
CH ₄	34.9	45.2	51.3
C ₂ H ₄	4.7	5.3	5.9
C ₂ H ₆	5.4	5.4	6.6
C ₃ H ₆	3.0	2.6	2.9
C ₃ H ₈	1.1	1.0	2.0
H ₂ S	<u>7.1</u>	<u>1.4</u>	<u>1.6</u>
Total	100.0	100.0	100.0
Molecular Weight	22.2	17.6	19.3
Higher Heating Value, Btu/scf	769	830	922

Table 22. TEST SD-6 (1300°F) MATERIAL BALANCES

	UNADJUSTED						
	<u>C</u>	<u>H</u>	<u>O</u>	<u>N</u>	<u>S</u>	<u>Ash</u>	<u>Total</u>
<u>Input</u>							
Feed Mixture	24.17	0.86	1.93	0.45	0.72	4.66	32.79
Steam + Moisture	--	1.52	12.08	--	--	--	13.60
Total	24.17	2.38	14.01	0.45	0.72	4.66	46.39
<u>Output</u>							
Char Mixture	21.13	0.12	0.26	0.37	0.39	4.55	26.82
Product Gas	1.32	0.46	1.02	--	NA	--	2.80
Oils/Tars	2.19	0.17	0.20	0.03	0.03	0.00	2.62
Aqueous Condensate	--	0.87	6.87	0.00	0.00	--	7.74
Total	24.64	1.62	8.35	0.40	0.42	4.55	39.98
Out/In	1.02	0.68	0.60	0.89	0.59	0.98	0.86
	ADJUSTED						
	<u>C</u>	<u>H</u>	<u>O</u>	<u>N</u>	<u>S</u>	<u>Ash</u>	<u>Total</u>
<u>Input</u>							
Feed Mixture	24.17	0.86	1.93	0.45	0.72	4.66	32.79
<u>Output</u>							
Char Mixture	21.64	0.13	0.26	0.38	0.40	4.66	27.47
Product Gas	1.31	0.46	1.03	--	0.29	--	3.09
Oils/Tars	2.19	0.17	0.20	0.02	0.04	0.00	2.62
Aqueous Condensate	--	-0.05	-0.39	0.05	0.00	--	-0.39
Total	25.14	0.71	1.10	0.45	0.73	4.66	32.79
Out/In	1.04	0.83	0.57	1.00	1.00	1.00	1.00

DILUENT-FREE CO-PRODUCT YIELDS, WT % COAL

	<u>dry</u>	<u>maf</u>
Char	66.7	59.8
Gas	19.4	23.3
Oils/Tars	16.4	19.8
Water	-2.5	-2.9
Total	100.0	100.0

Table 23. TEST MG-3 (1325°F) MATERIAL BALANCES

	UNADJUSTED						
	<u>C</u>	<u>H</u>	<u>O</u>	<u>N</u>	<u>S</u>	<u>Ash</u>	<u>Total</u>
<u>Input</u>							
Feed Mixture	22.50	0.90	13.13	0.39	0.97	22.98	60.87
Steam + Moisture	--	0.18	1.45	0.00	0.00	--	1.63
Total	22.50	1.08	14.58	0.39	0.97	22.98	62.50
<u>Output</u>							
Char Mixture	18.82	0.19	10.67	0.34	0.57	22.62	53.21
Product Gas	1.79	0.35	0.82	--	0.37	--	3.33
Oils/Tars	2.37	0.18	0.28	0.04	0.06	0.00	2.93
Aqueous Condensate	--	0.43	3.37	0.00	0.00	--	3.80
Total	22.98	1.15	15.14	0.38	1.00	22.62	63.27
Out/In	1.02	1.06	1.04	0.98	1.03	0.98	1.01
	ADJUSTED						
	<u>C</u>	<u>H</u>	<u>O</u>	<u>N</u>	<u>S</u>	<u>Ash</u>	<u>Total</u>
<u>Input</u>							
Feed Mixture	22.50	0.89	13.13	0.39	0.97	22.98	60.87
<u>Output</u>							
Char Mixture	19.11	0.19	10.84	0.35	0.58	22.97	54.04
Product Gas	1.79	0.35	0.82	--	0.33	--	3.29
Oils/Tars	2.37	0.18	0.27	0.04	0.06	0.01	2.93
Aqueous Condensate	0.00	0.07	0.56	0.00	0.00	--	0.63
Total	23.27	0.79	12.49	0.39	0.97	22.98	60.89
Out/In	1.03	0.89	0.95	1.00	1.00	1.00	1.00

DILUENT-FREE CO-PRODUCT YIELDS, WT % COAL

	<u>dry</u>	<u>maf</u>
Char	76.9	71.7
Gas	11.1	13.6
Oils/Tars	9.9	12.1
Water	2.1	2.6
Total	100.0	100.0

Table 24. TEST MG-5 (1100°F) MATERIAL BALANCES

	UNADJUSTED						
	C	H	O	N	S	Ash	Total
<u>Input</u>							
Feed Mixture	77.91	2.54	5.53	1.52	2.25	13.85	103.60
Steam + Moisture	--	1.86	14.74	--	--	--	16.60
Total	77.91	4.40	20.27	1.52	2.25	13.85	120.20
<u>Output</u>							
Char Mixture	60.06	1.24	3.00	1.15	1.66	13.20	80.31
Product Gas	1.26	0.28	0.82	0.00	0.15	--	2.51
Oils/Tars	3.97	0.37	0.58	0.05	0.10	0.01	5.08
Aqueous Condensate	0.00	2.05	16.25	0.00	0.00	--	18.30
Total	65.29	3.94	20.65	1.20	1.91	13.21	106.20
Out/In	0.84	0.90	1.02	0.79	0.85	0.95	0.88
	ADJUSTED						
	C	H	O	N	S	Ash	Total
<u>Input</u>							
Feed Mixture	77.91	2.54	5.53	1.52	2.25	13.85	103.60
<u>Output</u>							
Char Mixture	62.97	1.30	3.15	1.21	1.74	13.84	84.21
Product Gas	1.26	0.28	0.82	0.00	0.16	--	2.52
Oils/Tars	13.67	1.29	2.00	0.18	0.36	0.03	17.53
Aqueous Condensate	0.00	-0.09	-0.71	0.14	0.00	0.00	-0.66
Total	77.90	2.78	5.26	1.53	2.26	13.87	103.60
Out/In	1.00	1.09	0.95	1.00	1.00	1.00	1.00

DILUENT-FREE CO-PRODUCT YIELDS, WT % COAL

	<u>dry</u>	<u>maf</u>
Char	63.0	56.4
Gas	4.8	5.7
Oils/Tars	33.5	39.3
Water	-1.3	-1.4
Total	100.0	100.0

Table 25. TEST MG-11 (1390°F) MATERIAL BALANCES

	UNADJUSTED						
	<u>C</u>	<u>H</u>	<u>O</u>	<u>N</u>	<u>S</u>	<u>Ash</u>	<u>Total</u>
<u>Input</u>							
Feed Mixture	15.04	0.47	1.07	0.27	0.46	2.73	20.04
Steam + Moisture	--	1.44	11.41	--	--	--	12.85
Total	15.04	1.91	12.48	0.27	0.46	2.73	32.89
<u>Output</u>							
Char Mixture	14.36	0.08	0.09	0.24	0.26	2.95	17.98
Product Gas	0.81	0.22	0.61	0.00	0.07	--	1.71
Oils/Tars	1.02	0.08	0.07	0.01	0.04	0.01	1.23
Aqueous Condensate	0.00	0.70	5.55	0.00	0.00	--	6.25
Total	16.19	1.08	6.32	0.25	0.37	2.96	27.17
Out/In	1.08	0.57	0.51	0.93	0.81	1.08	0.83
	ADJUSTED						
	<u>C</u>	<u>H</u>	<u>O</u>	<u>N</u>	<u>S</u>	<u>Ash</u>	<u>Total</u>
<u>Input</u>							
Feed Mixture	15.04	0.47	1.07	0.27	0.47	2.72	20.04
<u>Output</u>							
Char Mixture	13.12	0.08	0.09	0.22	0.24	2.72	16.47
Product Gas	0.81	0.23	0.61	0.00	0.19	--	1.84
Oils/Tars	1.11	0.08	0.08	0.02	0.04	0.00	1.34
Aqueous Condensate	0.00	0.04	0.33	0.03	0.00	--	0.40
Total	15.04	0.43	1.11	0.27	0.47	2.72	20.04
Out/In	1.00	0.92	1.04	1.00	1.00	1.00	1.00

DILUENT-FREE CO-PRODUCT YIELDS, WT % COAL

	<u>dry</u>	<u>maf</u>
Char	63.9	57.3
Gas	18.6	22.0
Oils/Tars	13.5	15.9
Water	4.0	4.8
Total	100.0	100.0

Table 26. TEST MG-12 (1252°F) MATERIAL BALANCES

	UNADJUSTED						
	C	H	O	N	S	Ash	Total
<u>Input</u>							
Feed Mixture	8.91	0.28	0.68	0.14	0.26	1.54	11.81
Steam + Moisture	--	0.77	6.14	--	--	--	6.91
Total	8.91	1.05	6.82	0.14	0.26	1.54	18.72
<u>Output</u>							
Char Mixture	7.01	0.05	0.04	0.12	0.12	1.49	8.83
Product Gas	0.35	0.09	0.21	0.00	0.03	--	0.68
Oils/Tars	0.88	0.07	0.16	0.01	0.02	0.00	1.14
Aqueous Condensate	0.00	0.42	3.37	0.00	0.00	0.00	3.79
Total	8.24	0.63	3.78	0.13	0.17	1.49	14.45
Out/In	0.92	0.60	0.55	0.94	0.65	0.97	0.77
	ADJUSTED						
	C	H	O	N	S	Ash	Total
<u>Input</u>							
Feed Mixture	8.91	0.28	0.68	0.14	0.26	1.54	11.81
<u>Output</u>							
Char Mixture	7.26	0.06	0.04	0.12	0.12	1.54	9.14
Product Gas	0.35	0.09	0.21	0.00	0.12	--	0.77
Oils/Tars	1.30	0.10	0.24	0.02	0.02	0.00	1.68
Aqueous Condensate	0.00	0.02	0.19	0.00	0.00	--	0.21
Total	8.91	0.27	0.68	0.14	0.26	1.54	11.81
Out/In	1.00	0.96	1.00	1.00	1.00	1.00	1.00

DILUENT-FREE CO-PRODUCT YIELDS, WT % COAL

	<u>dry</u>	<u>maf</u>
Char	54.3	46.4
Gas	13.1	15.4
Oils/Tars	28.9	33.8
Water	3.7	4.4
Total	100.0	100.0

Table 27. TEST MG-14 (1084°F) MATERIAL BALANCES

	UNADJUSTED						
	C	H	O	N	S	Ash	Total
<u>Input</u>							
Feed Mixture	15.45	0.48	1.24	0.25	0.47	2.87	20.76
Steam + Moisture	--	1.50	11.94	--	--	--	13.45
Total	15.45	1.98	13.18	0.25	0.47	2.87	34.21
<u>Output</u>							
Char Mixture	13.03	0.13	0.39	0.21	0.26	2.77	16.79
Product Gas	0.41	0.10	0.22	0.00	0.07	--	0.80
Oils/Tars	1.01	0.09	0.15	0.01	0.02	0.00	1.28
Aqueous Condensate	0.00	0.84	6.66	0.00	0.00	0.00	7.50
Total	14.45	1.16	7.39	0.22	0.35	2.77	26.37
Out/In	0.94	0.58	0.56	0.88	0.74	0.97	0.77
	ADJUSTED						
	C	H	O	N	S	Ash	Total
<u>Input</u>							
Feed Mixture	15.45	0.49	1.25	0.24	0.47	2.87	20.76
<u>Output</u>							
Char Mixture	13.45	0.13	0.41	0.21	0.26	2.87	17.34
Product Gas	0.41	0.11	0.22	0.00	0.17	--	0.90
Oils/Tars	1.59	0.14	0.24	0.02	0.04	0.00	2.03
Aqueous Condensate	0.00	0.05	0.42	0.01	0.00	--	0.49
Total	15.45	0.43	1.29	0.24	0.47	2.87	20.76
Out/In	1.00	0.89	1.04	1.00	1.00	1.00	1.00

DILUENT-FREE CO-PRODUCT YIELDS, WT % COAL

	<u>dry</u>	<u>maf</u>
Char	66.6	60.2
Gas	8.8	10.5
Oils/Tars	19.9	23.6
Water	4.7	5.7
Total	100.0	100.0

Table 28. TEST MG-15 (1034°F) MATERIAL BALANCES

	UNADJUSTED						
	<u>C</u>	<u>H</u>	<u>O</u>	<u>N</u>	<u>S</u>	<u>Ash</u>	<u>Total</u>
<u>Input</u>							
Feed Mixture	14.63	0.46	1.00	0.26	0.38	2.40	19.13
Steam + Moisture	--	1.61	12.77	--	--	--	14.38
Total	14.63	2.07	13.77	0.26	0.38	2.40	33.51
<u>Output</u>							
Char Mixture	13.53	0.14	0.32	0.24	0.24	2.54	17.01
Product Gas	0.41	0.11	0.25	0.00	0.08	--	0.85
Oils/Tars	1.20	0.11	0.26	0.01	0.02	0.01	1.61
Aqueous Condensate	0.00	0.95	7.53	0.00	0.00	0.00	8.48
Total	15.14	1.31	8.36	0.25	0.34	2.55	27.95
Out/In	1.03	0.63	0.61	0.97	0.89	1.06	0.83
	-----ADJUSTED-----						
	<u>C</u>	<u>H</u>	<u>O</u>	<u>N</u>	<u>S</u>	<u>Ash</u>	<u>Total</u>
<u>Input</u>							
Feed Mixture	14.63	0.45	1.00	0.26	0.38	2.39	19.11
<u>Output</u>							
Char Mixture	12.64	0.13	0.30	0.22	0.22	2.38	15.89
Product Gas	0.41	0.11	0.25	0.00	0.12	--	0.89
Oils/Tars	1.58	0.15	0.34	0.02	0.03	0.01	2.13
Aqueous Condensate	0.00	0.02	0.16	0.02	0.00	--	0.20
Total	14.63	0.41	1.05	0.26	0.38	2.39	19.11
Out/In	1.00	0.90	1.05	1.00	1.00	1.00	1.00

DILUENT-FREE CO-PRODUCT YIELDS, WT % COAL

	<u>dry</u>	<u>maf</u>
Char	66.0	60.9
Gas	9.4	10.9
Oils/Tars	22.4	25.8
Water	2.2	2.4
Total	100.0	100.0

Table 29. TEST MG-16 (1183°F) MATERIAL BALANCES

	UNADJUSTED						
	<u>C</u>	<u>H</u>	<u>O</u>	<u>N</u>	<u>S</u>	<u>Ash</u>	<u>Total</u>
<u>Input</u>							
Feed Mixture	23.60	0.68	1.92	0.40	0.68	4.39	31.67
Steam + Moisture	--	1.47	11.70	--	--	--	13.17
Total	23.60	2.15	13.62	0.40	0.68	4.39	44.84
<u>Output</u>							
Char Mixture	18.91	0.11	0.39	0.29	0.31	4.03	24.04
Product Gas	0.67	0.18	0.37	0.00	0.07	--	1.29
Oils/Tars	1.35	0.12	0.29	0.01	0.03	0.01	1.81
Aqueous Condensate	0.00	0.78	6.21	0.00	0.00	0.00	6.99
Total	20.93	1.19	7.26	0.30	0.41	4.04	34.13
Out/In	0.89	0.55	0.53	0.75	0.60	0.92	0.76
	ADJUSTED						
	<u>C</u>	<u>H</u>	<u>O</u>	<u>N</u>	<u>S</u>	<u>Ash</u>	<u>Total</u>
<u>Input</u>							
Feed Mixture	23.59	0.69	1.92	0.40	0.68	4.39	31.67
<u>Output</u>							
Char Mixture	20.52	0.12	0.43	0.31	0.33	0.38	26.11
Product Gas	0.67	0.19	0.37	0.00	0.29	--	1.52
Oils/Tars	2.39	0.22	0.52	0.02	0.05	0.01	3.22
Aqueous Condensate	0.00	0.09	0.69	0.06	0.00	--	0.84
Total	23.59	0.62	2.01	0.40	0.68	4.40	31.69
Out/In	1.00	0.90	1.05	1.00	1.00	1.00	1.00

DILUENT-FREE CO-PRODUCT YIELDS, WT % COAL

	<u>dry</u>	<u>maf</u>
Char	64.4	57.6
Gas	9.7	11.6
Oils/Tars	20.5	24.4
Water	5.4	6.4
Total	100.0	100.0

Table 30. TEST MG-18 (1178°F) MATERIAL BALANCES

	UNADJUSTED						
	<u>C</u>	<u>H</u>	<u>O</u>	<u>N</u>	<u>S</u>	<u>Ash</u>	<u>Total</u>
<u>Input</u>							
Feed Mixture	26.86	0.79	1.76	0.47	0.69	4.28	34.85
Steam + Moisture	--	2.11	16.75	--	--	--	18.86
Total	26.86	2.90	18.51	0.47	0.69	4.28	53.71
<u>Output</u>							
Char Mixture	22.96	0.18	0.32	0.38	0.38	4.53	28.75
Product Gas	0.75	0.22	0.43	0.00	0.05	--	1.45
Oils/Tars	1.41	0.12	0.25	0.02	0.03	0.01	1.84
Aqueous Condensate	0.00	1.43	11.36	0.01	0.00	0.00	12.80
Total	25.12	1.95	12.36	0.41	0.46	4.54	44.84
Out/In	0.94	0.67	0.67	0.87	0.67	1.06	0.83
	ADJUSTED						
	<u>C</u>	<u>H</u>	<u>O</u>	<u>N</u>	<u>S</u>	<u>Ash</u>	<u>Total</u>
<u>Input</u>							
Feed Mixture	26.86	0.79	1.76	0.47	0.69	4.28	34.85
<u>Output</u>							
Char Mixture	21.54	0.17	0.30	0.36	0.35	4.25	26.97
Product Gas	0.75	0.22	0.43	0.00	0.24	--	1.64
Oils/Tars	4.57	0.39	0.81	0.06	0.10	0.03	5.96
Aqueous Condensate	0.00	0.02	0.21	0.05	0.00	0.00	0.28
Total	26.86	0.80	1.75	0.47	0.69	4.28	34.85
Out/In	1.00	1.02	0.99	1.00	1.00	1.00	1.00

DILUENT-FREE CO-PRODUCT YIELDS, WT % COAL

	<u>dry</u>	<u>maf</u>
Char	53.3	47.0
Gas	9.7	11.0
Oils/Tars	35.3	40.1
Water	1.7	1.9
Total	100.0	100.0

Table 31. TEST MG-19 (1102°F) MATERIAL BALANCES

	UNADJUSTED						
	<u>C</u>	<u>H</u>	<u>O</u>	<u>N</u>	<u>S</u>	<u>Ash</u>	<u>Total</u>
<u>Input</u>							
Feed Mixture	67.26	2.12	3.73	1.21	1.78	11.05	87.15
Steam + Moisture	--	3.06	24.25	--	--	--	27.31
Total	67.26	5.18	27.98	1.21	1.78	11.05	114.46
<u>Output</u>							
Char Mixture	54.63	0.64	1.02	0.98	1.08	10.57	68.92
Product Gas	1.40	0.34	0.59	0.00	0.09	--	2.42
Oils/Tars	6.26	0.57	0.96	0.07	0.15	0.00	8.01
Aqueous Condensate	0.00	1.60	12.71	0.01	0.00	0.00	14.32
Total	62.29	3.15	15.28	1.06	1.32	10.57	93.67
Out/In	0.93	0.61	0.55	0.88	0.74	0.96	0.82
	ADJUSTED						
	<u>C</u>	<u>H</u>	<u>O</u>	<u>N</u>	<u>S</u>	<u>Ash</u>	<u>Total</u>
<u>Input</u>							
Feed Mixture	67.26	2.12	3.73	1.21	1.78	11.05	87.15
<u>Output</u>							
Char Mixture	57.14	0.67	1.04	1.02	1.12	11.05	72.04
Product Gas	1.40	0.36	0.59	0.00	0.44	--	2.79
Oils/Tars	8.72	0.79	1.35	0.10	0.21	0.00	11.17
Aqueous Condensate	0.00	0.12	0.95	0.09	0.00	--	1.16
Total	67.26	1.94	3.93	1.21	1.78	11.05	87.16
Out/In	1.00	0.92	1.05	1.00	1.00	1.00	1.00

DILUENT-FREE CO-PRODUCT YIELDS, WT % COAL

	<u>dry</u>	<u>maf</u>
Char	64.2	58.5
Gas	6.6	7.7
Oils/Tars	26.4	30.7
Water	2.8	3.1
Total	100.0	100.0

Table 32. TEST MG-21 (1109°F) MATERIAL BALANCES

	UNADJUSTED						
	C	H	O	N	S	Ash	Total
<u>Input</u>							
Feed Mixture	59.94	1.75	3.74	1.16	1.46	9.09	77.14
Steam + Moisture	--	1.11	8.83	--	--	--	9.94
Total	59.94	2.86	12.57	1.16	1.46	9.09	87.08
<u>Output</u>							
Char Mixture	50.33	0.57	1.34	0.96	0.94	9.61	63.75
Product Gas	1.32	0.32	0.59	0.00	0.09	--	2.32
Oils/Tars	5.65	0.50	0.87	0.07	0.14	0.03	7.26
Aqueous Condensate	0.00	0.56	4.43	0.00	0.00	0.00	4.99
Total	57.30	1.95	7.23	1.03	1.17	9.64	78.32
Out/In	0.96	0.68	0.57	0.89	0.80	1.06	0.90
	ADJUSTED						
	C	H	O	N	S	Ash	Total
<u>Input</u>							
Feed Mixture	59.94	1.75	3.74	1.16	1.46	9.09	77.14
<u>Output</u>							
Char Mixture	47.31	0.54	1.26	0.90	0.88	9.03	59.92
Product Gas	1.32	0.32	0.59	0.00	0.30	--	2.53
Oils/Tars	11.31	1.00	1.74	0.14	0.28	0.06	14.53
Aqueous Condensate	0.00	0.00	0.03	0.12	0.00	0.00	0.15
Total	59.94	1.86	3.62	1.16	1.46	9.09	77.13
Out/In	1.00	1.06	0.97	1.00	1.00	1.00	1.00

DILUENT-FREE CO-PRODUCT YIELDS, WT % COAL

	<u>dry</u>	<u>maf</u>
Char	54.3	48.2
Gas	6.7	7.6
Oils/Tars	38.6	43.7
Water	0.4	0.5
Total	100.0	100.0

Table 33. TEST MG-22 (1147°F) MATERIAL BALANCES

	UNADJUSTED						
	<u>C</u>	<u>H</u>	<u>O</u>	<u>N</u>	<u>S</u>	<u>Ash</u>	<u>Total</u>
<u>Input</u>							
Feed Mixture	70.40	2.07	4.98	1.26	1.84	11.31	91.86
Steam + Moisture	--	<u>0.37</u>	<u>2.96</u>	--	--	--	<u>3.33</u>
Total	70.40	2.44	7.94	1.26	1.84	11.31	95.19
<u>Output</u>							
Char Mixture	57.74	0.64	1.67	1.04	1.16	11.72	73.97
Product Gas	2.01	0.51	0.78	0.00	0.14	--	3.44
Oils/Tars	6.25	0.56	0.99	0.07	0.14	0.00	8.01
Aqueous Condensate	<u>0.00</u>	<u>0.24</u>	<u>1.90</u>	<u>0.00</u>	<u>0.00</u>	<u>0.00</u>	<u>2.14</u>
Total	66.00	1.95	5.34	1.11	1.44	11.72	87.56
Out/In	0.94	0.80	0.67	0.88	0.78	1.04	0.92
	ADJUSTED						
	<u>C</u>	<u>H</u>	<u>O</u>	<u>N</u>	<u>S</u>	<u>Ash</u>	<u>Total</u>
<u>Input</u>							
Feed Mixture	70.40	2.07	4.98	1.26	1.84	11.31	91.86
<u>Output</u>							
Char Mixture	55.72	0.62	1.61	1.00	1.12	11.31	71.38
Product Gas	2.01	0.51	0.78	0.00	0.14	0.00	3.74
Oils/Tars	12.67	1.14	2.01	0.14	0.28	0.00	16.24
Aqueous Condensate	<u>0.00</u>	<u>0.05</u>	<u>0.36</u>	<u>0.12</u>	<u>0.00</u>	<u>0.00</u>	<u>0.53</u>
Total	70.40	2.32	4.76	1.26	1.84	11.31	91.89
Out/In	1.00	1.12	0.96	1.00	1.00	1.00	1.00

DILUENT-FREE CO-PRODUCT YIELDS, WT % COAL

	<u>dry</u>	<u>maf</u>
Char	54.3	47.4
Gas	8.3	9.6
Oils/Tars	36.2	41.7
Water	<u>1.2</u>	<u>1.3</u>
Total	100.0	100.0

Table 34. TEST MG-25 (1134°F) MATERIAL BALANCES

	UNADJUSTED						
	<u>C</u>	<u>H</u>	<u>O</u>	<u>N</u>	<u>S</u>	<u>Ash</u>	<u>Total</u>
<u>Input</u>							
Feed Mixture	61.88	1.75	3.95	1.12	1.69	10.80	81.19
Steam + Moisture	--	1.30	10.35	--	--	--	11.65
Total	61.88	3.05	14.30	1.12	1.69	10.80	92.84
<u>Output</u>							
Char Mixture	55.44	0.86	2.01	1.06	1.42	12.26	73.05
Product Gas	1.57	0.37	0.84	0.00	0.32	--	3.10
Oils/Tars	6.68	0.60	0.92	0.07	0.18	0.01	8.46
Aqueous Condensate	0.00	1.09	8.66	0.02	0.00	0.00	9.77
Total	63.69	2.92	12.43	1.15	1.92	12.27	94.38
Out/In	1.03	0.96	0.87	1.03	1.14	1.14	1.02
	ADJUSTED						
	<u>C</u>	<u>H</u>	<u>O</u>	<u>N</u>	<u>S</u>	<u>Ash</u>	<u>Total</u>
<u>Input</u>							
Feed Mixture	61.88	1.75	3.95	1.12	1.69	10.80	81.19
<u>Output</u>							
Char Mixture	48.76	0.76	1.77	0.93	1.25	10.78	64.25
Product Gas	1.57	0.37	0.84	0.00	0.13	0.00	2.91
Oils/Tars	11.55	1.04	1.59	0.12	0.31	0.02	14.63
Aqueous Condensate	0.00	-0.08	-0.61	0.07	0.00	0.00	-0.62
Total	61.88	2.09	3.59	1.12	1.69	10.80	81.17
Out/In	1.00	1.19	0.91	1.00	1.00	1.00	1.00

DILUENT-FREE CO-PRODUCT YIELDS, WT % COAL

	<u>dry</u>	<u>maf</u>
Char	57.2	51.3
Gas	7.4	8.4
Oils/Tars	37.0	42.0
Water	-1.5	-1.7
Total	100.0	100.0

Table 35. TEST MG-28 (1149°F) MATERIAL BALANCES

	UNADJUSTED						
	<u>C</u>	<u>H</u>	<u>O</u>	<u>N</u>	<u>S</u>	<u>Ash</u>	<u>Total</u>
<u>Input</u>							
Feed Mixture	42.74	0.77	0.82	0.66	0.51	5.99	51.49
Steam + Moisture	--	0.97	7.66	--	--	--	8.63
Total	42.74	1.74	8.48	0.66	0.51	5.99	60.12
<u>Output</u>							
Char Mixture	42.59	0.32	0.40	0.69	0.48	6.52	51.00
Product Gas	0.82	0.24	0.25	0.00	0.03	--	1.34
Oils/Tars	2.89	0.26	0.36	0.03	0.03	0.00	3.57
Aqueous Condensate	0.00	0.37	2.92	0.00	0.00	0.00	3.29
Total	46.30	1.19	3.93	0.72	0.54	6.52	59.20
Out/In	1.08	0.68	0.46	1.09	1.06	1.09	0.98
	-----ADJUSTED-----						
	<u>C</u>	<u>H</u>	<u>O</u>	<u>N</u>	<u>S</u>	<u>Ash</u>	<u>Total</u>
<u>Input</u>							
Feed Mixture	42.74	0.77	0.82	0.66	0.51	5.99	51.49
<u>Output</u>							
Char Mixture	39.10	0.30	0.35	0.64	0.44	5.99	46.82
Product Gas	0.82	0.24	0.25	0.00	0.03	--	1.34
Oils/Tars	2.82	0.25	0.35	0.03	0.03	0.00	3.48
Aqueous Condensate	0.00	-0.02	-0.12	-0.01	0.00	--	-0.15
Total	42.74	0.77	0.83	0.66	0.50	5.99	51.49
Out/In	1.00	1.00	1.02	1.00	1.00	1.00	1.00

DILUENT-FREE CO-PRODUCT YIELDS, WT % COAL

	<u>dry</u>	<u>maf</u>
Char	73.0	69.4
Gas	7.8	8.8
Oils/Tars	20.1	22.8
Water	-0.9	-1.0
Total	100.0	100.0

Table 36. TEST MG-30 (1050°F) MATERIAL BALANCES

	UNADJUSTED						
	<u>C</u>	<u>H</u>	<u>O</u>	<u>N</u>	<u>S</u>	<u>Ash</u>	<u>Total</u>
<u>Input</u>							
Feed Mixture	54.72	1.00	2.02	0.90	0.64	7.34	66.62
Steam + Moisture	--	0.98	7.81	--	--	--	8.79
Total	54.72	1.98	9.83	0.90	0.64	7.34	75.41
<u>Output</u>							
Char Mixture	47.30	0.47	1.24	0.79	0.55	6.85	57.20
Product Gas	0.73	0.21	0.19	0.00	0.03	--	1.16
Oils/Tars	3.58	0.32	0.35	0.03	0.03	0.00	4.31
Aqueous Condensate	0.00	0.84	6.68	0.01	0.00	0.00	7.53
Total	51.61	1.84	8.46	0.83	0.61	6.85	70.20
Out/In	0.94	0.93	0.86	0.92	0.95	0.93	0.93
	ADJUSTED						
	<u>C</u>	<u>H</u>	<u>O</u>	<u>N</u>	<u>S</u>	<u>Ash</u>	<u>Total</u>
<u>Input</u>							
Feed Mixture	54.72	1.01	2.02	0.89	0.64	7.34	66.62
<u>Output</u>							
Char Mixture	50.66	0.50	1.33	0.85	0.58	7.34	61.26
Product Gas	0.73	0.21	0.19	0.00	0.03	--	1.16
Oils/Tars	3.58	0.32	0.35	0.03	0.03	0.00	4.31
Aqueous Condensate	0.00	-0.01	-0.11	0.01	0.00	--	-0.11
Total	54.97	1.02	1.76	0.89	0.64	7.34	66.62
Out/In	1.00	1.02	0.87	1.00	1.00	1.00	1.00

DILUENT-FREE CO-PRODUCT YIELDS, WT % COAL

	<u>dry</u>	<u>maf</u>
Char	76.0	73.4
Gas	5.2	5.7
Oils/Tars	19.3	21.4
Water	-0.5	-0.5
Total	100.0	100.0

Temperature Effects

With the available analyzed data for the PRU tests described above, an evaluation of the effect of temperature on the co-product yields and other selected properties has been completed. These data are presented graphically in Figures 6 to 12.

Figure 6 shows the effect of mild gasification temperature on the yields of char, gas, oils and tars, and net water from the fifteen tests listed at the beginning of this section, with the exception of Test MG-3. Test MG-3 was omitted because the use of limestone as a diluent constitutes a significantly different system condition, and thus the MG-3 data should not be included in a discussion of temperature effects using coal-derived diluents. Best-fit regression curves for Illinois No. 6 coal tests were constructed through the data points selected for the quality of the material balance data, shown as solid circles. Those tests (MG-5, MG-18, MG-21, MG-22, and MG-25) which required large adjustments to the char and/or oils and tars yields, based on the material balance normalization procedure, are shown as open circles on the plots, and were not included in calculation of the regression curves. This approach gives a conservative interpretation of oils/tars yields, and is consistent with accepted practice in statistical data analysis which allows rejection of data points that deviate substantially from the main body of the data. As shown, the gas yield increases with temperature, whereas the maximum oils/tars yield appears between 1100° and 1200°F. Char yield decreases as expected with increasing temperature, and the chemical water production appears fairly constant. Also shown on these plots for comparison are data from the two tests with West Virginia coal, displayed as asterisks. For the two test temperatures studied, this coal produced more char and less of oils/tars, gas, and water, on a dry-coal basis. This difference should be interpreted cautiously, however, because the West Virginia coal had substantially more fines, which may have affected the fluidization behavior and residence time in the fluidized bed. West Virginia coal will be used more extensively in Task 4 integrated system tests.

Also shown for comparison in Figure 6 are pilot-plant data from the COED² and Occidental Flash Pyrolysis³ processes and laboratory data from CSIRO.⁴ The COED data was obtained with Illinois No. 6 coal, the Occidental data with Kentucky No. 9 coal, and the CSIRO data with Australian Liddell B bituminous

● IGT PRU data, Illinois coal; ○ IGT PRU data, Illinois coal (not included in regression curve);

* IGT PRU data, West Virginia coal; △ Occidental Flash Pyrolysis (ref. 5);

□ COED 2nd stage (ref. 7); — CSIRO fluidized bed, Liddell B coal (ref. 6).

Figure 6. EFFECT OF MILD GASIFICATION TEMPERATURE ON CO-PRODUCT YIELDS
(based on adjusted material balances)

Figure 7. EFFECT OF MILD GASIFICATION TEMPERATURE ON THE BOILING-POINT FRACTIONS OF OILS/TARS

closed points = Illinois coal; open points = West Virginia coal

Figure 8. EFFECT OF MILD GASIFICATION TEMPERATURE ON HETEROATOMS IN OILS/TARS

closed points = Illinois coal; open points = West Virginia coal

Figure 9. EFFECT OF MILD GASIFICATION TEMPERATURE
ON H/C ATOMIC RATIO IN OILS/TARS

closed points = Illinois coal; open points = West Virginia coal

Figure 10. EFFECT OF MILD GASIFICATION TEMPERATURE ON ASH, VOLATILE MATTER, AND SULFUR CONTENT OF CHAR

Figure 11. EFFECT OF MILD GASIFICATION TEMPERATURE ON GAS COMPOSITION

Figure 12. FIMS SPECTRUM ON TEST MG-3 SOLVENT QUENCH TAR

coal. Both of the latter coals are similar in ash and volatile matter content and in swelling/caking behavior to the Illinois No. 6 coal used in the PRU tests.

Citations in the literature have generally shown, in laboratory studies, increasing oils/tars yields with temperatures up to at least 1500°F; however, these data were usually obtained in experimental systems that minimized the extent of secondary reactions.⁵⁻⁷ Pilot-plant data from the entrained-flow Occidental Flash Pyrolysis process with Kentucky bituminous coal showed higher oils/tars yields than in our tests in three out of ten of their test runs, but the diluent solid used was a low-surface-area non-reactive petroleum coke.³ Occidental data with recycled pyrolysis char gave much lower liquid yields, and even with the petroleum coke, seven of their ten reported tests gave oils/tars yields similar to those from the mild gasification PRU. Pyrolysis in fluidized beds, while providing rapid particle heating, cannot avoid secondary reactions, and thus there is a temperature at which the equilibrium between condensables production and destruction reactions results in a decreasing yield. The PRU liquid yield data shown in Figure 6 is in good agreement with the CSIRO fluidized-bed data, from which the maximum oils/tars yields were reported to be at about 1100°F, regardless of the coal rank.⁴ The mild gasification liquid yields are slightly higher than those reported for Illinois No. 6 coal in the first two stages of the COED process, which operated at a lower temperature of 800°F and required oxidative pretreatment and the use of multiple staged reactors.²

The use of a fluidized/entrained reactor rather than a simple fluidized bed was designed to allow fine particles that would normally elutriate from the bed to undergo devolatilization in the entrained section. The data from the PRU tests are not conclusive regarding the role of the entrained section on the co-product yields. Nevertheless, the observed yields of oils and tars are comparable to those obtained from the Occidental entrained reactor, and greater than those reported by COED, suggesting that the PRU reactor configuration may have some positive influence on oils/tars yields.

Figure 7 shows the effect of the process temperature on the cumulative boiling-range distribution of the oils and tars. It appears from these data that the principal change in the volatility of the condensables with an increasing mild gasification temperature consists of an increase in light oils

substantial aliphatic content, the latter pathway may be significant, explaining the increase in pitch content with increasing temperature in those processes. In rapid-heating processes such as the IGT mild gasification process, the presence in low-temperature oils/tars of primarily aromatic structures with abundant aliphatic side chains and phenolic hydroxyl groups shows that the former pathway may be more significant. This is also consistent with the observation of loss of oxygen from the oils/tars at increasing mild gasification temperatures. The quality of binder pitches is closely correlated with high aromaticity.

Figure 10 shows the ash, volatile matter, and sulfur content of the mild gasification char with process temperature. These data quantify the increasing devolatilization and carbon conversion of the feed coal as mild gasification temperature increases. Sulfur content is 20% to 35% lower than that of the feed coal, and decreases slowly with increasing temperature.

The product gas composition is also affected by process temperature, as shown in Figures 11a and 11b. In these plots, the West Virginia coal data have been omitted for clarity. The Illinois No. 6 coal data for hydrogen, methane, and C₂ hydrocarbons (ethane + ethylene) are shown in Figure 11a, and have been grouped into "low-steam" (steam/coal weight ratio of 0.0 to 0.5) and "high-steam" (steam/coal weight ratio of 0.7 to 1.4) tests, in order to illustrate the effects of steam and temperature on these components. A similar treatment of carbon monoxide, carbon dioxide, and hydrogen sulfide is shown in Figure 11b. Best-fit regression curves were calculated for these data, and are shown as solid lines for the high-steam tests and dotted lines for the low-steam tests.

The dry, nitrogen-free concentrations of hydrogen and carbon monoxide increase with temperature, whereas carbon dioxide and hydrocarbon gases decrease. These trends are consistent with well-known devolatilization and gas-phase equilibrium data. The hydrogen sulfide content of the gas also decreases with temperature, at least for the high-steam tests, and it appears that, even when the increased gas yield at higher temperature is taken into account, the amount of sulfur released as hydrogen sulfide decreases with temperature. The effects of steam on the gas composition are discussed in more detail below.

Effects of Steam

PRU mild gasification Tests MG-19, MG-21, and MG-22 were conducted at similar conditions ($1125 \pm 23^\circ\text{F}$, 10 psig, 4.55 ± 0.15 ft/s gas velocity, 93.0 ± 2.2 lb/h feed rate of 1:1 Illinois No. 6 coal and coke breeze) except for steam input rates. The steam rates varied from zero in Test MG-22 to 23.7 lb/h (steam/coal ratio of 0.522) in Test MG-19. The intermediate steam rate in Test MG-21 was 8.5 lb/h (steam/coal ratio of 0.180). Some previous Illinois No. 6 coal tests were conducted at even higher steam/coal ratios; Tests SD-6, MG-11, MG-12, MG-14, MG-15, MG-16, and MG-18 used steam rates which resulted in steam/coal weight ratios of 0.7 to 1.4. The highest steam/coal ratio was 1.44 in Test MG-15.

Gas compositions were affected by steam, as indicated by the data in Figures 11a and 11b. The hydrogen concentration is seen to be consistently lower in the low-steam than in high-steam tests, while the hydrocarbon and CO levels are higher in the low-steam tests. The CO_2 and H_2S concentrations do not appear to be significantly affected by steam rate. These observations can be explained by the thermodynamics and kinetics of competing gas-phase reactions (steam-carbon, shift, and steam-methane reforming). An increase in the steam content of the fluidizing gas drives all three of these reactions toward the direction of hydrogen production, while tending to consume hydrocarbons via reforming. The steam-carbon reaction produces carbon monoxide, which in turn reacts with additional steam to make carbon dioxide. No attempt was made to compare the gas compositions with equilibrium compositions since, in fact, it is unlikely that the products were at equilibrium at the reactor exit.

The effect, if any, of the steam/coal ratio on the overall co-product yield structure could not be determined from these tests. Examination of oils/tars quality did not show any identifiable differences among Tests MG-19, MG-21, and MG-22 with respect to boiling-point fraction distribution, sulfur content, nitrogen content, oxygen content, or H/C ratio. No effects on char ash, volatile matter, or sulfur content were observed for these three tests.

Chemical Properties of Oils/Tars

Other properties of the oils and tars are of interest, and have been investigated for selected tests. Table 37 shows a comparison of selected

Table 37. COMPARISON OF PAH CONTENT OF MILD GASIFICATION TAR
WITH A TYPICAL COKE OVEN TAR⁹

	Mild Gasification (Test MG-25) ----- wt % of tar -----	Coke Oven -----
Biphenyl	0.010	0.420
Acenaphthene	0.011	1.280
Fluorene	0.027	2.560
Phenanthrene/Anthracene	0.066	2.870
2-Methylphenanthrene	0.083	0.700
1-Methylphenanthrene	0.064	0.750
Fluoranthene	0.003	0.531
Pyrene	0.015	0.520
Benz(a)anthracene	0.019	0.304
Chrysene/Triphenylene	not detected	0.221
Benzo(b,k)fluoranthene	not detected	0.354
Benzo(a)pyrene	0.017	0.293
Dibenzo(a,h)anthracene	0.009	0.039
Benzo(g,h,i)perylene	not detected	0.171

polyaromatic hydrocarbons, determined by capillary GC-MS, in the tar from Test MG-25 (process temperature of 1130°F) with a typical coke oven tar.⁹ As seen, the mild gasification tar contains at least an order of magnitude less of these compounds, some of which are known carcinogens and environmentally sensitive, compared to conventional coke oven tar.

In Table 38, a comparison of the co-product yields from mild gasification and a typical coking process shows the major expected difference in the yield of oils/tars. Combining the values in Tables 37 and 38 reveal that the absolute quantities of environmentally sensitive PAH compounds, as well as their percentages in the total liquids, are lower in the mild gasification oils/tars. This is shown in Table 39 expressed as pounds per ton of dry coal.

Other methods of analysis that were applied to PRU oils/tars samples included field ionization mass spectroscopy (FIMS) and H-NMR (hydrogen nuclear magnetic spectroscopy).

The FIMS analysis was applied early in the program to the +360°F fraction from the Test MG-3 slipstream oils/tars samples collected in methylene chloride during the test (solvent quench condensate) and in tetrahydrofuran by post-test rinsing of the sample vessels and lines (THF wash). This method characterizes the components in the liquid with minimal molecular fracture, unlike standard MS which breaks down large molecules into smaller fragments.

Table 38. COMPARISON OF CO-PRODUCT YIELDS WITH COKE OVEN BY-PRODUCT YIELDS⁹

	<u>Mild Gasification</u>	<u>Coke Oven</u>
	----- wt % maf coal -----	-----
Product Gas	11.6	13.9
Oils/Tars	24.4	4.5
Water	6.4	14.1
Char or Coke	57.6	67.5

Table 39. COMPARISON OF PAH PRODUCTION LEVELS BETWEEN MILD GASIFICATION AND A TYPICAL COKE OVEN TAR

	<u>Mild Gasification</u>	<u>Coke Oven</u>
	(Test MG-25)	
	----- lb/ton dry coal -----	-----
Biphenyl	0.049	0.378
Acenaphthene	0.055	1.152
Fluorene	0.128	2.304
Phenanthrene/Anthracene	0.315	2.583
2-Methylphenanthrene	0.398	0.630
1-Methylphenanthrene	0.306	0.675
Fluoranthene	0.015	0.478
Pyrene	0.070	0.468
Benz(a)anthracene	0.091	0.274
Chrysene/Triphenylene	0.000	0.199
Benzo(b,k)fluoranthene	0.000	0.319
Benzo(a)pyrene	0.079	0.264
Dibenzo(a,h)anthracene	0.044	0.035
Benzo(g,h,i)perylene	0.000	0.154

Consequently, the FIMS method can identify the parent molecules and derive a molecular weight distribution for a major part of the high-boiling oils and tars. It can also show important structural data. Test MG-3 was performed in the PRU at 1325°F with Illinois No. 6 coal and limestone as a diluent. The two oils/tars samples from the test were analyzed in a FIMS device at SRI International, and interpretation of the data was provided by Dr. Ripudaman Malhotra of SRI. In this device, the sample is volatilized under vacuum using a programmed temperature ramp ranging from -58° to 842°F.

Figures 12 and 13 show, respectively, the FIMS spectra of the Test MG-3 oils/tars in methylene chloride, representing the condensables dissolved in the run-time quench solvent, and of the Test MG-3 oils/tars washed from the sample lines with THF. Figures 14 and 15 show the vacuum evaporation curves from the apparatus, and indicate that the quantities of the oils/tars represented by the FIMS spectra are approximately 95% and 88% of the total oils/tars mass for the two samples. Therefore, the FIMS data represent the majority of each sample, with a minimal loss of high-boiling unrecovered material. As indicated by the spectra, the bulk of the material falls in the 100 to 500 molecular weight range, with the THF wash containing a higher proportion of high-molecular weight compounds. Table 40 lists some of the major components (up to molecular weight 246) in the two FIMS spectra by molecular weight, their relative ion intensities, and some overall characteristics of the samples. From these data, it is seen that the oils/tars are composed primarily of aromatic nuclei, but the C₁- and C₂-alkyl derivatives of many of the components (e.g., phenol, naphthol, fluorene, anthracene/phenanthrene) are more abundant than the parent aromatic. This is reflective of the low temperature of mild gasification, and is in general agreement with the standard GC analyses of the co-products that were performed at IGT. The ratio of odd/even ions in the spectra is an indication of the relative nitrogen content of the sample, because nitrogen, at mass 7, is the usual source of an odd-numbered ion molecular weight. Based on this interpretation, the THF wash, which contains a higher proportion of higher-molecular-weight components, also contains more nitrogen. This is corroborated by the elemental analyses of the samples.

The FIMS analysis confirms the aromatic nature of the mild gasification oils/tars and its potential to produce pitch that is a high-market-value

Figure 13. FIMS SPECTRUM ON TEST MG-3 THF WASH TAR

Figure 14. VACUUM DISTILLATION CURVE FOR TEST MG-3
SOLVENT QUENCH TAR

Figure 15. VACUUM DISTILLATION CURVE FOR TEST MG-3
THF WASH TAR

Table 40. FIMS DATA ON TEST MG-3 OILS AND TARS

Mol wt	Major Peaks		
	Possible compound(s)	CH ₂ Cl ₂ Quench	THF Wash
94	phenol	407	473
108	cresols	1056	1498
122	xlenols	653	1008
142	naphthols	774	874
156	C ₁ -naphthols	886	865
166	fluorene	1157	984
168	dibenzofuran	550	527
170	C ₂ -naphthols	683	627
178	anthracene/phenanthrene	762	667
180	C ₁ -fluorenes	1378	1027
182	C ₁ -dibenzofurans	964	805
184	dibenzothiophene	571	524
192	C ₁ -anthracenes/phenanthrenes	1505	994
196	C ₂ -dibenzofurans	918	732
202	pyrene	661	415
204	phenylnaphthalene	987	591
206	C ₂ -anthracenes/phenanthrenes	1645	895
216	C ₁ -pyrenes	1751	834
218	C ₁ -phenylnaphthalenes	1369	789
230	C ₂ -pyrenes	1861	894
232	C ₂ -phenylnaphthalenes	1611	917
244	C ₃ -pyrenes	1301	697
246	C ₃ -phenylnaphthalenes	1349	738
Number average molecular weight		261	275
Weight average molecular weight		289	315
Ratio of odd/even mass peaks		0.228	0.324

product. In contrast, the low-temperature carbonization tars from conventional slow-heating processes (Coalite, Disco, etc.) were not considered suitable for production of binder pitches because of their high aliphatic content. The mild gasification liquid does not show any significant quantities of aliphatic parent compounds. Virtually all of the aliphatic content is comprised of short alkyl side chains on aromatic nuclei. If desired, a simple thermal treatment may be adequate to remove these aliphatic constituents and increase the aromaticity of the resulting pitch to acceptable levels for use as electrode binders.

H-NMR analysis was applied to the mild gasification tar from Test MG-25 (test temperature 1134°F). The NMR spectrum is shown in Figure 16, and shows the following distribution of H-atoms in the combined oils/tars (combined solvent quench and THF wash samples):

ONE-PULSE SEQUENCE

P2= 10.00 USEC
 A DE= 312 USEC
 D2= AT
 D5= 5.00 SEC

NS = 800
 SIZE = 8192
 AT = 1.28 SEC
 ADL ON GPO ON = 1
 ADC= 10 BITS AT= 6
 SW= +/- 1602.56 DW= 912
 F2= 200.059001
 DF= 1188.42
 SF= 200.059001
 EM= .90
 FA= 272.9
 PD= 98.6

SCALE= 94.25 HZ/CM
 = .4711 PPM/CM

Figure 16. H-NMR SPECTRUM OF TEST MG-25 OILS/TARS

Table 41. HYDROGEN ATOM DISTRIBUTION IN TEST MG-25 OILS AND TARs

<u>Hydrogen Functional Type</u>	<u>Percent of Total Hydrogen</u>
Aromatic + phenolic	35
Hydrogen on C α - to two rings	5
Hydrogen on C α - to one ring	35
Naphthenic methylene (hydroaromatic) + methane	5
Methylene β - or more remote from ring + methyl β - to ring	14
Methyl Γ - or further from ring	4

These data show that the hydrogen in the mild gasification liquids is contained largely in alkyl groups, primarily methyl, attached to aromatic rings. The methyl, ethyl, and propyl or longer chain hydrogen can be estimated to be in the ratio of 5.25:2.5:1. Only a small amount, 5%, of hydrogen is in methylene bridges between rings, and a similarly small percentage is associated with hydroaromatic structures. These characteristics are typical of a rapid-heating low-temperature carbonization liquid, and are consistent with the FIMS data discussed above, which showed that alkyl derivatives of aromatic nuclei were abundant in the Test MG-3 oils/tars.

Reproducibility of Data

Most of the PRU tests conducted under Task 2 were performed at different temperatures to evaluate the effect of temperature. The reproducibility can thus be evaluated from the degree of scatter of the data from the regression curves derived therefrom. Of all the PRU tests, Tests MG-5, MG-9, and MG-21 were conducted at essentially the same system temperature ($1104 \pm 5^\circ\text{F}$), but varied in other respects, as system modifications were implemented primarily to increase the coal feed rate and improve gas-solids mixing. Test MG-14 was operated at a similar temperature, 1084°F , but at a much higher steam/feed ratio, a lower superficial gas velocity, and a longer coal residence time than the other tests, and thus is not included in the assessment of reproducibility.

In view of these considerations, it can be stated that the unadjusted co-product yields for these three tests covered the following ranges: char, 58.7 ± 4.1 wt %; oils/tars, 16.0 ± 4.4 wt %; and gas, 5.5 ± 0.5 wt % of dry coal. The error limits given are simple standard deviations. The relative standard deviations based on these data are 6.9%, 27.5%, and 9.8% for char, oils/tars, and gas yields, respectively. The low standard deviation in char yield indicates that the degree of devolatilization is controlled primarily by temperature. The scatter in the oils/tars yield data is probably because the oils/tars sample recovery techniques were steadily improved over the course of the investigation, resulting in a greater percentage of the produced condensables accounted for in the later tests (19.0 wt % and 19.3 wt % of dry coal unadjusted in Tests MG-19 and MG-21, compared to 9.8 wt % in Test MG-5). The relatively large standard deviation in gas yield may reflect the differences in steam rate, superficial gas velocity, and other process conditions which varied among the three tests. The effect of steam rate on gas composition has already been discussed, and was shown graphically in Figure 7.

From the adjusted material balance data, the following ranges of yields were observed for the three tests: char, 60.5 ± 4.4 wt %; oils/tars, 32.8 ± 5.0 wt %; and gas, 6.0 ± 0.9 wt % of dry coal, respectively. The relative standard deviations for these co-products were, in the order just given, 7.3%, 15.2%, and 14.9%. The reproducibility of char yield was essentially unchanged, while the deviation was lower for oils/tars and higher for gases, compared to the unadjusted data.

Properties of oils/tars for the three tests were assessed for reproducibility. The distribution of oils/tars boiling-range fractions showed the following ranges and standard deviations: light oils, 6.2 ± 0.1 wt %; middle oils, 17.8 ± 1.4 wt %; heavy oils, 15.0 ± 1.7 wt %; and pitch, 61.0 ± 2.9 wt % of the total oils/tars. The relative standard deviations ranged from 2.0% to 11.4%. Sulfur content of the oils/tars was 1.9 ± 0.04 wt %, nitrogen content was 1.0 ± 0.05 wt %, and oxygen content was 11.9 ± 0.4 wt % of the total condensables. These data show relative standard deviations of 2.4% to 4.9%. The H/C atomic ratio for the oils/tars from the three tests was 1.09 ± 0.02 , giving a relative standard deviation of 2.3%.

These analyses show that, for the limited number of tests operated under similar conditions, the reproducibility of data was quite acceptable, especially with respect to the oils/tars quality. More comprehensive reproducibility data will be available following the completion of Task 4, System Integration Studies, because long-duration tests at constant reactor conditions will have been performed and that data will be integrated with the data already obtained under Task 2.

Reactor/Process Configuration

The operational flexibility designed into the fluidized/entrained bed isothermal PRU allows different process conditions and configurations to be evaluated. The resulting "preferred" process conditions identified from PRU data must be further evaluated in an adiabatic process development unit (PDU) that --

- Has no limiting hydrodynamic or wall effects on the fundamental conversion, heat, and mass transfer processes
- Provides a practical heat supply for adiabatic operation.

The main limitations of the IGT PRU is associated with its 8-inch inside diameter and the effects associated with the process heat coming through the metal walls of the reactor. This is especially important when caking coals are processed in the reactor. The relationship of the hydrodynamic characteristics of the PRU fluidized bed to those of larger units is also in the forefront of scale-up decisions, in terms of achieving proper mixing, gas distribution, and solids residence times.

Fluidized-Bed Section: For caking coals, the size of the PRU fluidized bed does not provide a sufficiently large volume of bed char to maintain the agglomerates in motion until they dissipate, avoiding their buildup in the bed or on the reactor walls. It is understood that low feed rates of caking coal will be quickly dispersed into a bed of devolatilized coal char and diminish the size of caked agglomerates. In the U-GAS project, IGT operated a 3-ft-ID fluidized bed that successfully fed caking Illinois No. 6 and Kentucky No. 9 coals. From this experience, a mathematical relationship of coal feed rate to fluidized-bed char volume was developed. This information was applied in the mild gasification PRU test operations, but agglomerates that still formed in the PRU did not have enough space or bed volume to dissipate before contacting

other sticky groups of particles or the reactor wall. Rather than considering any form of coal pretreatment such as air oxidation, we selected to operate the PRU with caking coal by mixing a surrogate bed char (coke breeze) with the incoming coal feed to achieve the required dilution of sticky particles to allow their complete devolatilization. Coal was also mixed with limestone in one test in the PRU, achieving non-agglomerating operation.

This approach allowed the PRU to operate and obtain material-balanced process data over a temperature range of 1035° to 1390°F, as previously discussed. Furthermore, upon analysis of the process for scale-up to an adiabatic PDU, coal feeding with hot recycled char and gas was determined to be economically beneficial. Therefore, operation of the PDU or larger reactors with caking coals will not be limited by the agglomeration tendency of the coal, because of the sufficiently large diameter and volume of char to promote rapid dispersion and mixing of the feed coal.

Entrained-Bed Section: The PRU feed point for the entrained-bed feed was located in the 8-inch-ID freeboard section with the intent of adding auxiliary hot nitrogen just below the freeboard feed point. The operational results showed that a significant amount of the feed coal particles were not entrained and fell into the fluidized bed. It was determined that the particles formed agglomerates as they entered the 8-inch-ID section, and could not be entrained at the employed gas velocities. The auxiliary hot gas flow for entrainment was distributed in the 8-inch diameter of the PRU through 12 holes drilled through the reactor wall. These radial jets of gas caused turbulence just below the feed point. The length of the entrained section from the feed point to the auxiliary nitrogen feed point was not sufficient to establish a well-distributed gas flow for proper entrainment. In addition, agglomerates from softening coal particles stuck to the hot metal walls of the reactor, resulting in a solid buildup on the walls.

To refine the design of the entrained bed, two steps should be taken:

- The PRU feed point should be relocated to the 4-inch-ID section where the flow velocity will be higher and can be properly established, and
- The feed nozzle should direct the injected particles in an upward direction with the gas stream, rather than downward and counter to the gas stream.

The key operation, however, of the IGT mild gasification process is the operation of the fluidized bed. The fluidized bed has operated with a caking Illinois No. 6 coal and a higher fluidity West Virginia coal. The successful operation involves superficial gas velocities higher than those traditionally used, and requires a gas distribution cone arrangement with a central gas jet to promote solids mixing near the coal feed point. In the IGT PRU, a higher fraction of particles were therefore elutriated from the fluidized bed. As revealed in Tables 4 through 18, the fine char from the system cyclones was less extensively devolatilized than the bed char, which increases the desirability of recycling the fine char to the fluidized bed. The less-devolatilized char could also be suitable for forming briquettes.

Maintaining the present reactor configuration and splitting the feed between the fluidized bed and the entrained bed in the adiabatic PDU design will capitalize on these observations. The discussion of a detailed PDU reactor configuration and its operational flexibility will be continued in the Topical Report for Task 4, System Integration Studies. The equipment design choices and advantageous processing refinements will be discussed.

CONCLUSIONS

The isothermal PRU system consisting of the fluidized/entrained bed reactor system was designed, constructed, installed and successfully shaken down. Two bituminous coals obtained from the Peabody Holding Co., Inc. (-12 mesh Illinois No. 6 coal and a -40 mesh West Virginia coal fines) were tested in the PRU to develop the process performance data for engineering evaluation and scale-up purposes. The PRU test data are obtained from slip-stream sampling of the condensable and gaseous products while the bulk of the co-products are disposed of in a combustor.

In the initial tests, dried coal fines were fed to the mid-region of the reactor, anticipating a size separation by the fluidizing nitrogen and subsequent mild gasification of coarse particles in the fluidized bed and of fines in the entrained bed section. The wall effects of the 8-inch ID reactor and the externally heated hot metal walls promoted caking of coal, leading to involuntary test shutdown. The caking problem was solved by mixing the coal with a diluent char and feeding the mixture into the fluidized-bed reactor section. Based on previous gasification studies with bituminous coals in process research and process development units, it is expected that caking coals can be successfully processed in large diameter reactors that contain an adequate proportion of well-mixed devolatilized char that limits the agglomeration of coal and ensures uninterrupted operation of the reactor. Feeding a mixture of coal and char could also be interpreted as a simulation of supplying energy for the endothermic mild gasification reactions by char recycle.

In the PRU tests, preheated nitrogen was used as the fluidizing medium. The superficial gas velocity was maintained at about 4 ft/s in the fluidized section and about 16 ft/s in the entrained section. Data analysis from the successful PRU tests show that, in the temperature range of 1035° to 1390°F, Illinois No. 6 coal conversion ranged from 33% to 46%, resulting in 54% to 67% char, 14% to 29% oils/tar, and 7% to 19% fuel gas. The test data with the Illinois coal show that increasing the reaction temperature increased coal conversion with a decreasing char yield. The oils/tar yields appear to reach a maximum in the region of 1100° to 1200°F, while the gas yield increased steadily with increasing temperature, partially because of the increasing secondary thermal cracking reactions. From the limited data with West

Virginia coal, it appears that the gas, oils/tars, and water yields were lower, and the char yield higher, than for the Illinois No. 6 coal. It is not known at this time whether the difference in particle size distribution may have played a role in the different results from the two coals, because of the difference in fluidization/entrainment behavior.

The highly aromatic oils and tars were characterized to estimate the light oil (<350°F), middle oil (350° to 590°F), heavy oil (590° to 750°F), and pitch (>750°F) fractions. The predominance of secondary reactions is also evident in explaining the effect of temperature on the distribution of oil fractions. It was determined that with an increasing mild gasification temperature, the pitch fraction decreased with a corresponding increase in light oils. There was no significant change in the yield of middle or heavy oils with temperature. With respect to the heteroatom content in the oils/tars, sulfur and nitrogen increased slightly with process temperature, while oxygen in the liquids decreased rapidly with increasing temperature. This indicates that deoxygenation reactions may play a role in the change in distribution of boiling-range fractions in the oils/tars. The aromaticity also increased with process temperature, as indicated by the decreasing atomic H/C ratio in the condensables. Trends were similar for the two coals tested, although the West Virginia coal tests did not cover as wide a range of temperatures, and thus these conclusions can only be tentatively applied to that coal at present.

Characterization of the diluent-free char from the PRU tests showed a monotonically increasing ash content accompanied by a decrease in volatile matter content. The char volatile matter content was in the range of 7% to 12% compared to the 37% volatile matter content of the dry Illinois No. 6 coal. The decrease in volatile matter was approximately linear with respect to process temperature. Sulfur content in the char showed a very slight decrease with mild gasification temperature, and was approximately 33% lower than the sulfur content of the parent coal for Illinois No. 6 coal. For West Virginia coal, the sulfur content of the char was not significantly lower than that of the coal, but the trends in ash and volatile matter content were similar to those for the Illinois coal.

The fuel gas from mild gasification is rich in hydrogen and methane and also contains other light hydrocarbons, carbon oxides, and hydrogen sulfide.

Increasing temperature reduces methane and increases hydrogen content, which are also attributable to the secondary cracking and reforming reactions.

Analysis of the fate of sulfur with an increasing reaction temperature showed that the sulfur content in both char and oils/tars decreased while the sulfur content of oils and tars increased. In general for Illinois coal, the char retained 36% to 54% of the sulfur, oils and tars contained 9% to 15% of the sulfur, and the fuel gas contained 31% to 52% of the sulfur from the coal.

The implications of these observations and conclusions on process evaluation, scale-up and the marketability of the co-products will be analyzed and presented in subsequent project reports.

REFERENCES CITED

1. Wootten, J. M., Nawaz, M., Duthie, R. G., Knight, R.A., Onischak, M., Babu, S. P. and Bair, W. G., "Development of an Advanced, Continuous Mild Gasification Process for the Production of Co-Products," DOE Contract No. DE-AC21-87MC24266; Topical Report on Task 1, August 1988.
2. Scotti, L. J. et al., "Char Oil Energy Development Interim Report No. 5", Dept. of Energy Report No. FE-1212-5, August 1975.
3. Che, S. C. et al., "Flash Pyrolysis Coal Liquefaction Process Development", Final Report for July 1976 -- June 1978, Dept. of Energy Report No. FE-2244-26, 1978.
4. Tyler, R. J., "Flash Pyrolysis of Coals. Devolatilization of Bituminous Coals in a Small Fluidized Bed Reactor", Fuel, 59:4, 218-226, April 1980.
5. Solomon, P. R. and Colket, M. B., "Coal Devolatilization", Proc. of 17th Int'l Symp. on Combustion, Leeds, U.K., 131-143, 1979.
6. Suuberg, E. M. et al., "A Comparison of the Rapid Pyrolysis of a Lignite and a Bituminous Coal", ACS Div. of Petr. Chem. Preprints, 23:1, 175-182, 1978.
7. Knight, R. A., Koncar, G. J., Martin, K. A., Babu, S.P. and Chao, S. S. "Mild Gasification Studies with Illinois Coals", Annual Report to Center for Research on Sulfur in Coal (September 1988 -- August 1989), CRSC Subgrant Agreement No. 88-139, September 1989.
8. Khan, M. R., "Prediction of Sulphur Distribution in Products During Low Temperature Coal Pyrolysis and Gasification", Fuel 68:11, 1439-49, 1989.
9. McNeil, D., "High-Temperature Coal Tar", Chemistry of Coal Utilization, 2nd Suppl. Vol., Chap. 17, 1003-1082, 1981

RPP/5-3peg
7WP/RPP/5-3peg

END

DATE FILMED

04 / 10 / 91