DOE/PC/90045--T6

NOV 25 1992

QUARTERLY REPORT

DOE/PC/90045--T6

Report Period

DE93 007561

April 1, 1992 to June 30, 1992

FOR

**CATALYST AND PROCESS DEVELOPMENT FOR
SYNTHESIS GAS CONVERSION TO ISOBUTYLENE**

Submitted to

**United States Department of Energy
Pittsburgh Energy Technology Center**

**July 27, 1992
(Approved September 2, 1992)**

by

**Rayford G. Anthony and Aydin Akgerman
Kinetics, Catalysis and Reaction Engineering Laboratory
Department of Chemical Engineering
Texas A&M University
College Station, TX 77843-3122**

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

UNDER DOE CONTRACT NO. DE-AC22-90PC90045

(Texas A&M Research Foundation Project No. 6722)

MASTER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

CATALYST AND PROCESS DEVELOPMENT FOR SYNTHESIS GAS CONVERSION TO ISOBUTYLENE

DOE CONTRACT NO. 90PC90045

TEXAS A&M RESEARCH FOUNDATION PROJECT NO. 6722

Quarterly Report

Report Period: 4/1/92 to 6/30/92

PROJECT OBJECTIVES

The objectives of this project are to develop a new catalyst, the kinetics for this catalyst, reactor models for trickle bed, slurry and fixed bed reactors, and simulate the performance of fixed bed trickle flow reactors, slurry flow reactors, and fixed bed gas phase reactors for conversion of a hydrogen lean synthesis gas to isobutylene.

JUSTIFICATION FOR THE PROJECT

Isobutylene is a key reactant in the synthesis of methyl tertiary butyl ether (MTBE) and of isooctanes. MTBE and isooctanes are high octane fuels used to blend with low octane gasolines to raise the octane number required for modern automobiles. The production of these two key octane boosters is limited by the supply of isobutylene. MTBE when used as an octane enhancer also decreases the amount of pollutants emitted from the exhaust of an automobile engine.

Hydrogen-rich synthesis gas has been converted to isobutylene using a zirconia based catalyst. However, the productivity and yields are low, and the ability of the catalyst to convert a hydrogen-lean synthesis gas to isobutylene with high productivity and yields, and without excessive deactivation is unknown.

PROPOSED PROCESS

A hydrogen-lean synthesis gas with a ratio of H_2/CO of 0.5 to 1.0 is produced from the gasification of coal, lignite, or biomass. This hydrogen-lean synthesis gas can be processed in a "shift reactor" with steam to convert the hydrogen-lean synthesis gas to a hydrogen-rich synthesis gas. But, this processing step is inefficient and consumes considerable energy. If the hydrogen-lean synthesis gas could be converted directly to isobutylene, a significant increase in

process efficiency will be the result. We envision a reactor system and catalyst that will selectively and efficiently convert hydrogen-lean synthesis gas to isobutylene. The catalyst, based on past work published in the literature, will most likely be zirconia or thoria based, and will contain components to promote the water-gas shift reaction and increase the selectivity of isobutylene.

GOALS FOR THE QUARTER

The goals for the quarter include 1) Filing the necessary reports, 2) Completing the experiments on sodium impregnated zirconia. 3) Conducting experiments with the AE MSBTR 900 on a thoria-zirconia prepared hydrothermally. 4) Continue work to synthesize a zirconate with a layered structure. The objective is to determine if changing the crystal structure will affect the catalysts activity and selectivity. 5) Continue the microkinetic modelling. This approach is finally beginning to produce some useful results. 6) Continue the empirical modelling.

ACCOMPLISHMENTS FOR THE QUARTER

Filing of necessary reports

The quarterly report for the period of January 1, 1992 to March 31, 1992 was filed and approved. Monthly reports for March, April, and May were also filed.

Microkinetic Model

Table 1 presents a calculated product distribution using the microkinetic model and the reaction sequence presented in Table 1 of the last quarterly. We are predicting the production of more isobutylene than is being produced experimentally. We believe that further analysis and changes required to match the experimental data will lead to the design of improved catalysts.

Experimental Program

Substantial progress has been made in the synthesis of new catalysts. Zirconia has been prepared by precipitation with ammonium hydroxide or sodium hydroxide from zirconyl nitrate, by a modified sol gel method, and by a hydrothermal method. Catalyst prepared by these methods are labelled as ppt, sol gel and HT, respectively. In one case, a hydrous sodium zirconium oxide prepared by sol gel method was ion exchanged to produce a cesium/zirconia catalyst. This catalysts as labelled as sol gel/IE.

A catalyst with 2% Th on zirconia was prepared by precipitating zirconia followed by impregnating with thorium nitrate, drying and calcining at 500 °C for 5 hours. A 10% Th on zirconia was prepared by a hydrothermal method. The XRD pattern of this catalyst indicated a tetragonal structure, which did not change on calcination. Zirconia was prepared with 1.6% Na by using sodium hydroxide and ammonium hydroxide to precipitate zirconyl nitrate. Zirconia and zirconia/silica with a molar ratio of 4:1 Zr:Si were prepared using a modified sol gel procedure. A 1.6wt%Na/10.3wt%Ti/ZrO₂ prepared hydrothermally had a tetragonal structure. The HZrO₂0.25Si(HCl) as prepared was amorphous and after calcination at 500 °C the structure was tetragonal. The remaining catalysts were monoclinic after calcining them at 500 °C for 5 hours. Data currently available on the surface areas and XRD patterns are presented in Table 2. The XRD powder patterns are also presented in the appendix.

Figure 1 shows a comparison at 400 °C of catalytic activities for zirconia prepared by precipitation using ammonium hydroxide, zirconia with 1.6% sodium prepared by co-precipitation of zirconyl nitrate with sodium hydroxide and ammonium hydroxide, and a 1.6 wt% sodium 10.3 wt% titanium/zirconia with a tetragonal structure prepared by hydrothermal synthesis. The 1.6% Na on zirconia is more active than zirconia, which is more active than the 1.6% Na: 10.3% Ti on zirconia. The product from the latter catalysts contain 31.2% i-C₄s and no linear C₄s. The activities of these catalysts are ranked as 1.6%Na/ZrO₂(ppt) > ZrO₂(ppt) > 1.6%Na10.3%Ti/ZrO₂.

Figure 2 shows the fit of the data for a 1:2 H₂:CO feed at 95 atm and the rate equations for CO consumption for the 1.6% Na/ZrO₂ and ZrO₂. The inhibition of the rate by CO₂ and the overall effect of pressure of 1.5 order is illustrated. The curves in Figure 2 were generated by integrating the rate equation for a plug flow reactor, and assuming the stoichiometry such that 0.5 moles of hydrogen were consumed per mole of CO consumed and 0.5 moles of CO₂ were produced per mole of CO consumed, i.e.

or

Utilizing the rate equation for CO consumption is a useful way to compare the activities of various catalysts in terms of kinetic expressions. Because of the complexity of the reactions

occurring to produce hydrocarbons, a good estimate of the activation energy has not been obtained.

Figure 3 shows a comparison at 450 °C of the catalytic activities of 2 wt%Th/ZrO₂ prepared by precipitating the ZrO₂ to form a gel and impregnating with thorium nitrate, a 10 wt%Th/ZrO₂ prepared hydrothermally, HZrO₂-HCl 0.25Si prepared by sol gel and zirconia prepared by precipitation. The catalysts were washed with water and acetone, dried and calcined at 500°C. The activities are ranked as 2%Th/ZrO₂ > ZrO₂ > 10%Th/ZrO₂ ≥ HZrO₂-HCl 0.25Si.

Figure 4 illustrates the effect of temperature on the mean rate of consumption of CO for catalysts studied at more than one temperature. The slopes for the lines plotted in Figure 4 are proportional to activation energies, which are changing for the different catalysts. However, additional data are required to determine if a variation in activation energies is statistically valid. However, the plot is useful for comparing catalyst activities and indicates the 10%Th/ZrO₂, HT is as active as zirconia prepared by precipitation.

The overall ranking of catalytic activities is 2%Th/ZrO₂ > 1.6% Na/ZrO₂ > ZrO₂ (by ppt.) ≥ 10%Th/ZrO₂ (by hydrothermal) ≥ HZrO₂-HCl 0.25Si (by sol gel) > 1.6% Na 10.3% Ti/ZrO₂. The data for the different temperatures were combined by using zirconia prepared by precipitation as the reference catalyst for the two temperature ranges. Differences in these catalysts are due to the method of preparation, and the type and amount of additive.

A Cs/ZrSi_{0.25} with 4.5% Cs was evaluated and found to have an activity less than the above list, and the product distribution was predominately methane. Table 3 presents the data for this catalyst. The support used in the preparation of the cesium catalysts was the prepared using the sol gel method, and is the HZrO₂Si_{0.25}O₂ discussed in the previous paragraph. Hydrocarbon distribution for the sol gel catalyst is presented in Table 4.

Isobutylene yields for all of the catalysts were on the order of 10 to 25 wt% of the total hydrocarbons produced. Hence, improvement in the activities for converting CO to hydrocarbons and an increase in the selective to isobutylene will result in a higher production rate of isobutylene.

Figures 5 through 8 show the rates of production of isobutylene and total hydrocarbons. These figures show that the rate of production of isobutylene and hydrocarbons decrease as the

CO conversion increases because of the longer space times (Figures 1 and 3) required to increase the CO conversion. A major goal in isosynthesis is to obtain a catalyst of sufficient activity to operate the reactor at low temperatures and low pressures with high CO conversions and high selectivities and production rates of isobutylene.

Tables 3 through 10 present hydrocarbon distributions and activity data obtained for some of the catalysts, and Figures 9 through 13 present the trends obtained for sodium titanium zirconia. Figure 9 illustrates the effect of pressure and space time on the conversion of CO. At a constant pressure the conversion increases with increase in space time, which is to be expected. However, the production rates will decrease substantially because of the reduction of space velocity required to obtain the long space times. Figure 10 illustrates the increase in methane production with an increase in pressure. Isobutylene production rate has not changed substantially for pressures above 50 atm, but the production of methane for this catalyst increases substantially. For a space time of 60 seconds Figure 11 illustrates the continual increase in isobutylene with the increase in pressure up to 70 atm. Above 70 atm, only methane and C_3^+ are increasing. Figures 12 and 13 compare the performance of the ZrO_2 (ppt.), 1.6%Na/ Zr_2 (ppt) and the 1.6%, 10.3%Ti/ ZrO_2 (HT). The effect of the Ti in the catalyst is to increase the production of iso compounds, and to decrease the amount of C_3^+ while increasing the production rate of methane.

Figures 14 and 15 illustrate the relationship between space velocity and space time. Space time for a constant density system is the same as residence time. Whereas, space velocity is the flow rate at 0 °C and 1 atm divided by the volume of catalyst. Hence, space velocity is a measure of catalyst utilization. The kinetics however are controlled by the residence time which is closely approximated for this system by the space time.

In addition to the XRD powder patterns presented in the Appendix, figures illustrating typical temperature profiles in the tubular reactors are presented. The catalyst is loaded in the isothermal region of the temperature profile.

SIGNIFICANT ACCOMPLISHMENTS AND CONCLUSIONS

A rate equation for carbon monoxide consumption showing first order in CO and 0.5 order in hydrogen indicates the rate controlling step involves dissociated hydrogen. The inhibition of the rate with carbon dioxide is also shown. Examination of the hydrocarbon

distributions indicates a see-saw effect with the C_4 s representing the fulcrum and methane and C_5^+ the end points. The shift in the distributions tends to be towards the C_5^+ for high pressures and long residence times. This distribution can be shifted by incorporating Ti into the catalysts, but the optimum amount of Ti needs to be determined. The sol gel method of preparing the catalysts tends to produce a less active catalyst than by precipitation of a zirconyl salt. The most active catalyst contained approximately 2% Th/ZrO₂.

GOALS FOR THE NEXT QUARTER

The goals for the next quarter include: 1. Preparation of the presentation and manuscript for the DOE Contractors Meeting in September. 2. Evaluation of an alumina/zirconia catalyst prepared by a revised modified sol gel method. We anticipate an increase in the surface area and activity using this method of preparation. 3. Prepare a sodium/titanium/thorium/zirconia catalysts using precipitation with sodium/titanium/thorium weight percents of 0.8, 2 and 2 on zirconia. Also, prepare a catalyst with the same composition using the sol gel and hydrothermal method. 4. Attempt to stabilize the high d₀-zirconate to maintain the high surface area of the material in the as prepared state. 5. Evaluate the catalytic activity of the new catalytic materials.

WORK SCHEDULE STATUS REPORT

The work schedule status report is attached. Significant progress is shown on Tasks 1,2 and 3 with some progress on Tasks 4 and 5.

Table 1. Simulation of Production Distribution Using the Microkinetic Model
 For Zirconia (sol gel)
 (50 atm., 698 K, $\tau = 70$ s, Space vel. = 1006 h⁻¹)

Component	Mole Fractions	
	Experimental	Model
CO ₂	3.23×10^{-2}	1.07×10^{-2}
CH ₄	7.44×10^{-3}	6.00×10^{-3}
ethane	3.29×10^{-4}	4.49×10^{-8}
ethylene	1.26×10^{-3}	7.06×10^{-6}
propane	2.73×10^{-4}	4.48×10^{-8}
propylene	3.48×10^{-4}	2.2×10^{-6}
isobutylene	5.31×10^{-4}	37.8×10^{-4}
2-butene	5.58×10^{-4}	2.80×10^{-4}
1-butene	6.1×10^{-5}	1.37×10^{-5}
n-butane	2.45×10^{-4}	1.74×10^{-6}
isobutane	8.57×10^{-4}	6.31×10^{-4}

Table 2. Surface Areas and XRD Pattern

Catalyst	Surface Area m ² /g Before Reaction cal. at 500 °C	Surface Area m ² /g After Reaction	XRD Pattern Before Reaction calcined 500°C	XRD Pattern After Reaction
2%Th/ZrO ₂ (ppt)	N/A	83	N/A	N/A
1.6%Na/ZrO ₂ (ppt)	58	N/A	Monoclinic	N/A
ZrO ₂ (ppt)	55	42	Monoclinic	Monoclinic
10%Th/ZrO ₂ (Hydrothermal)	N/A	N/A	Monoclinic	N/A
Zr _{0.8} Si _{0.2} O ₂ (HCl-sol gel)	N/A	73	Tetragonal	N/A
1.6%Na10.3%Ti/Zr O ₂ (HT)	88	N/A	Tetragonal	N/A
Si _{0.2} Zr _{0.8} O ₂ (HT)	128	N/A	Tetragonal	N/A
4.5%Cs/Si _{0.2} Zr _{0.8} O ₂ (sol gel/IE)	216 (prior to calcination)	N/A	Amorphous (prior to calcination)	N/A
ZrO ₂ (sol gel)	92	N/A	Tetragonal	N/A

XRD Powder Patterns are presented in the appendix.

Table 3. Activity Data and Product Distribution for Cs-Zr-Si_{0.26}
Prepared by Ion Exchange

Catalyst ID	Cs-Zr-Si _{0.26}
Catalyst volume (cc)	3.6
Catalyst weight (g)	5.27
CO/H ₂ molar ratio	1
Reactant flow rate (cc/min STP)	226.6
Average reaction temperature (°C)	445 (718 K)
Reaction pressure (psig)	1008 (68.6 atm)
Space time, volume of catalyst/volumetric flow rate of feed at reaction condition, (second)	24.8 Space vel.* = 3840 h ⁻¹
CO conversion (%)	4.7
Product distribution (wt%)	
Carbon dioxide	49.27
Dimethylether	0.665
Methanol	0
Hydrocarbons	50.07
Hydrocarbon production rate, g/hr/kg catalyst	37.9
Hydrocarbon distribution (wt%)	
Methane	40.68
Ethylene	2.937
Ethane	11.47
Propane	3.605
Propylene	3.309
iso-Butane	1.009
n-Butane	2.557
1-Butene	1.984
iso-Butene	1.886
trans-Butene	1.526
cis-Butene	0.894
C ₅₊	28.15

*Space Velocity is calculated at 0 °C and 1 atm.

Table 4. Activity and Product Distributions for
 $\text{Si}_{0.25}\text{ZrO}_{2.5}$ (HCl-sol gel)

Catalyst ID	$\text{Zr}_{0.8}\text{Si}_{0.2}\text{O}_2$
Catalyst volume (cc)	4.6
Catalyst weight (g)	4.88
CO/H ₂ molar ratio	1
Reactant flow rate (cc/min STP)	270.0
Average reaction temperature (°C)	450 (723 K)
Reaction pressure (psig)	1013 (70 atm)
Space time, volume of catalyst/volumetric flow rate of feed at reaction condition, (second)	26.05 Space Vel [*] = 3649 h ⁻¹
CO conversion (%)	13.38
Product distribution (wt%)	
Carbon dioxide	66.43
Dimethylether	0.010
Methanol	0.004
Hydrocarbons	33.56
Hydrocarbon production rate, g/hr/kg catalyst	93.2
Hydrocarbon distribution (wt%)	
Methane	9.839
Ethylene	2.209
Ethane	1.635
Propane	3.396
Propylene	2.933
iso-Butane	4.201
n-Butane	0
1-Butene	0.830
iso-Butene	12.62
trans-Butene	0.945
cis-Butene	0.671
C ₅ -	60.73

*Space Velocity is calculated at 0 °C and 1 atm.

Table 5. Activity and Selectivity Data for 1.6%Na on ZrO₂ Results

Run	T (°C)	P (atm)	CO/H ₂ Ratio	Space Time (sec)	CO ₂ /CO Conversion	Isosynthesis Profile wt. mol.	Branched/Linear C4 wt. mol.	i-C ₄ H ₈ / CH ₄ wt. mol.	i-C ₄ H ₈ / C5* wt.	i-C ₄ H ₈ / All C4's wt. mol.	i-C ₄ H ₈ / i-C ₄ H ₁₀ wt. mol.
SA	400	21	1/3	10	0.0516 0.0011*	4.382 2.434 0.518 0.271	2.623 2.623 0.678 0.678	3.242 0.927 0.469 0.134	0.375 0.025	0.724 0.724 0.051 0.051	very large
SB	400	50	1/1	15	0.0744 0.0003	6.226 3.591 0.283 0.170	3.469 3.465 0.265 0.265	4.817 1.377 0.123 0.035	0.169 0.010	0.751 0.752 0.010 0.010	~30 2
SC	400	50	1/1	30	0.1157 0.0022	5.024 2.865 0.491 0.296	3.415 3.408 0.090 0.090	3.381 0.967 0.653 0.187	0.199 0.007	0.730 0.731 0.005 0.005	16.7 2.0
SD	400	50	1/1	45	0.1473 0.0016	6.066 3.411 0.199 0.097	3.574 3.565 0.270 0.269	3.605 1.031 0.023 0.007	0.203 0.015	0.726 0.727 0.009 0.009	13.4 1.5
SE	400	50	1/1	60	0.1704 0.0019	5.720 3.238 0.210 0.111	3.306 3.299 0.085 0.085	3.168 0.906 0.174 0.050	0.224 0.002	0.705 0.707 0.007 0.006	11.1 1.5

* The second line in the Tables is the estimated error in the number reported.

Table 5 - (Continued) Activity and Selectivity Data for 1.6 wt. % Na on ZrO₂

Run	T (°C)	P (atm)	CO/H ₂ Ratio	Space Time (sec)	CO ₂ /CO Conversion (%)	Isosynthesis Profile wt. mol.	Branched/Linear C ₄ wt. mol.	i-C ₄ H ₈ / CH ₄ wt. mol.	i-C ₄ H ₈ / C ₅ ⁺ wt.	i-C ₄ H ₈ / All C ₄ 's wt. mol.	i-C ₄ H ₈ / i-C ₄ H ₁₀ wt.
SI	400	21	1/3	10	5.02 0.04*	5.671 2.857 0.747 0.378	4.219 4.219 0.089 0.089	0.906 0.259 0.080 0.023	0.288 0.002	0.808 0.808 0.003 0.003	∞
SM	400	21	1/3	10	5.00 0.11	2.570 1.432 0.219 0.132	4.375 4.370 0.503 0.502	0.390 0.112 0.048 0.014	0.318 0.019	0.784 0.785 0.015 0.015	26.80
SJ	400	95	2/1	15	6.19 0.04	4.914 2.792 0.156 0.090	4.007 3.996 0.171 0.170	1.308 0.374 0.028 0.008	0.100 0.002	0.740 0.741 0.007 0.007	11.57
SK	400	95	2/1	30	10.33 0.06	4.098 2.382 0.130 0.071	4.205 4.190 0.052 0.052	1.281 0.366 0.025 0.007	0.123 0.005	0.729 0.731 0.002 0.002	9.40
SL	400	95	2/1	45	13.79 0.13	4.166 2.450 0.063 0.047	3.638 3.627 0.032 0.032	1.228 0.351 0.027 0.008	0.148 0.002	0.713 0.715 0.002 0.002	9.82
SN	400	95	2/1	60	14.70 0.11	4.451 2.602 0.047 0.028	3.319 3.311 0.087 0.087	0.917 0.262 0.033 0.010	0.091 0.001	0.679 0.681 0.005 0.005	7.60
SO	400	95	2/1	75	16.74 0.01	4.508 2.634 0.097 0.051	3.390 3.381 0.036 0.036	0.880 0.252 0.029 0.008	0.094 0.005	0.675 0.678 0.003 0.003	6.98
SP	400	95	1/1	60	17.36 0.27	4.609 2.719 0.033 0.012	3.192 3.185 0.134 0.134	0.629 0.180 0.058 0.017	0.161 0.004	0.645 0.648 0.008 0.008	5.42

* the number below each result indicates the estimated error in that result.

Table 6 -- Hydrocarbon Distributions (wt.) for 1.6 wt % Na-ZrO₂

Run	SA	SB	SC	SD	SE	SF	SG	SH	SI	SJ	SK	SL	SM	SN	SO	SP
Methane	0.101	0.042	0.066	0.063	0.076	0.068	0.119	0.119	0.183	0.062	0.074	0.088	0.343	0.079	0.083	0.164
Ethane	0.007	0.004	0.010	0.008	0.010	0.005	0.014	0.012	0.004	0.002	0.006	0.006	0.011	0.005	0.005	0.007
Ethylene	0.045	0.016	0.020	0.018	0.020	0.019	0.028	0.027	0.032	0.012	0.014	0.015	0.037	0.010	0.010	0.013
Propane	0.000	0.003	0.003	0.004	0.004	0.006	0.005	0.006	0.000	0.002	0.003	0.006	0.003	0.003	0.003	0.006
Propylene	0.022	0.010	0.012	0.009	0.010	0.009	0.016	0.013	0.000	0.006	0.009	0.009	0.015	0.067	0.007	0.008
Iso-butane	0.000	0.003	0.006	0.008	0.010	0.005	0.009	0.012	0.000	0.007	0.010	0.011	0.005	0.010	0.011	0.019
n-Butane	0.000	0.000	0.000	0.000	0.001	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.001	0.001	0.004
1-butene	0.031	0.015	0.021	0.019	0.021	0.021	0.022	0.019	0.016	0.012	0.014	0.016	0.014	0.011	0.011	0.016
Iso-butylene	0.198	0.124	0.135	0.138	0.146	0.143	0.165	0.176	0.166	0.081	0.094	0.108	0.134	0.072	0.073	0.103
trans-2-butene	0.028	0.012	0.010	0.011	0.013	0.006	0.016	0.015	0.012	0.005	0.005	0.007	0.009	0.006	0.006	0.009
cis-2-butane	0.019	0.011	0.012	0.013	0.015	0.009	0.015	0.016	0.011	0.005	0.005	0.009	0.008	0.007	0.007	0.010
C5+'s	0.549	0.760	0.705	0.708	0.675	0.708	0.592	0.585	0.576	0.806	0.765	0.725	0.420	0.791	0.784	0.642

Table 7 - Activity and Selectivity Data for 1.6 wt. % Na, 10.30 wt. % Ti on ZrO_2

Run	T (°C)	P (atm)	CO/H ₂ Ratio	Space Time (sec)	CO ₂ /CO Conversion (%)	Isosynthesis Profile wt. mol.	Branched/Linear C ₄ wt. mol.	i-C ₄ H ₈ / CH ₄ wt. mol.	i-C ₄ H ₈ / C ₅ ⁺ wt.	i-C ₄ H ₈ / All C ₄ 's wt. mol.	i-C ₄ H ₈ / i-C ₅ H ₁₀ wt.
TA	400	21	1/3	10	2.84 0.04*	3.032 1.937 0.102 0.066	∞	0.371 0.106 0.017 0.005	0.219 0.040	0.619 0.627 0.010 0.009	1.63
TB	400	21	1/1	30	4.45 0.08	2.945 1.893 0.060 0.045	∞	0.624 0.178 0.016 0.005	0.519 0.014	0.619 0.627 0.007 0.007	1.63
TC	400	21	1/1	40	5.03 0.10	3.196 2.050 0.132 0.088	∞	0.565 0.161 0.036 0.010	0.601 0.009	0.556 0.564 0.005 0.005	1.25
TD	400	21	1/1	50	5.95 0.01	2.926 1.864 0.043 0.032	∞	0.491 0.140 0.026 0.008	0.743 0.039	0.507 0.516 0.011 0.011	1.03
TE	400	21	1/1	60	6.76 0.06	2.717 1.718 0.085 0.071	∞	0.417 0.119 0.009 0.003	0.749 0.022	0.447 0.456 0.004 0.004	0.81
TF	400	35	1/1	60	8.45 0.03	3.015 1.937 0.036 0.025	∞	0.434 0.124 0.011 0.003	0.673 0.014	0.457 0.466 0.002 0.002	0.84
TG	400	35	1/1	90	11.14 0.02	3.223 2.064 0.027 0.018	34.22 33.52 5.62 5.51	0.370 0.106 0.004 0.001	0.578 0.021	0.399 0.408 0.001 0.001	0.70
TH	400	50	1/1	60	8.83 0.01	3.117 2.008 0.060 0.047	∞	0.359 0.103 0.006 0.002	0.465 0.012	0.429 0.438 0.001 0.001	0.75
TI	400	50	1/1	150	16.66 0.27	3.191 2.048 0.042 0.030	41.24 40.93 4.98 4.92	0.283 0.081 0.003 0.001	0.471 0.011	0.345 0.352 0.001 0.001	0.55
TJ	400	70	1/1	60	9.01 0.02	3.058 1.956 0.070 0.046	56.07 54.90 0.50 0.50	0.277 0.079 0.010 0.003	0.185 0.006	0.390 0.399 0.004 0.004	0.66
TK	400	70	1/1	210	21.19 0.09	3.210 2.061 0.027 0.016	45.71 45.35 0.53 0.52	0.197 0.056 0.005 0.001	0.376 0.011	0.294 0.302 0.005 0.005	0.43
TL	400	95	1/1	60	9.36 0.00	2.978 1.890 0.042 0.028	19.98 19.57 0.49 0.48	0.230 0.066 0.002 0.001	0.169 0.004	0.386 0.393 0.003 0.003	0.68
TM	400	95	1/1	300	28.54 0.12	3.163 2.023 0.023 0.016	18.68 18.45 0.42 0.41	0.126 0.036 0.003 0.001	0.266 0.006	0.223 0.229 0.005 0.005	0.31

* The number below each result indicates the estimated error in that result.

Table 8 -- Hydrocarbon Distributions (wt.) for 1.6 wt% Na 10.3 wt% Ti on ZrO_2

	TA	TB	TC	TD	TE	TF	TG	TH	TI	TJ	TK	TL	TM
Run	0.287	0.281	0.306	0.338	0.353	0.344	0.350	0.348	0.373	0.291	0.416	0.317	0.451
Methane													
Ethane	0.000	0.012	0.014	0.021	0.025	0.023	0.2365	0.021	0.025	0.016	0.025	0.016	0.025
Ethylene													
	0.019	0.022	0.020	0.021	0.022	0.016	0.014	0.012	0.010	0.009	0.007	0.009	0.006
Propane	0.008	0.018	0.021	0.027	0.029	0.027	0.028	0.025	0.031	0.017	0.030	0.016	0.032
Propylene	0.030	0.045	0.042	0.043	0.045	0.041	0.036	0.036	0.030	0.025	0.024	0.023	0.018
	0.065	0.108	0.138	0.161	0.182	0.177	0.186	0.166	0.194	0.122	0.191	0.107	0.185
Iso-butane													
	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.003	0.000	0.003	0.000	0.005
n-Butane													
	0.000	0.000	0.000	0.000	0.000	0.000	0.009	0.000	0.004	0.004	0.003	0.009	0.004
1-butene													
	0.106	0.176	0.173	0.166	0.147	0.149	0.130	0.125	0.106	0.081	0.082	0.073	0.057
Iso-butylene													
	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.002
trans-2-butene													
	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.002
cis-2-butene													
	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.002
C5 + 's	0.485	0.339	0.287	0.223	0.197	0.222	0.224	0.269	0.224	0.435	0.218	0.431	0.214

Table 9. Activity and Selectivity Data for Thoria on Zirconia

Catalyst	Run No.	T (°C)	flow ^a cc/min	P (psig)	Space Time (sec)	CO Conversion	wt. frac. CO ₂	HC-Prod. rate, kg/s kg	i-C ₄ H ₁₀ /CH ₄ (wt)	i-C ₄ H ₁₀ /All C ₄ 's (wt%)
10% Th on ZrO ₂ by insitu method. 5cc, 7.879 g	041192	450	223	1012	38.18	17.85 ± 0.28	0.666	0.199	1.03 ± 0.05	60.80 ± 1.74
	040292	450	446	1012	19.04	11.73 ± 0.11	0.555	0.218	1.24 ± 0.01	69.74 ± 0.52
	040392a	450	334.5	1012	25.41	13.79 ± 0.21	0.727	0.252	0.873 ± 0.022	64.78 ± 0.37
	040392b	450	111.5	1009	76.25	24.12 ± 0.84	0.504	0.102	0.689 ± 0.02	49.35 ± 0.05
	040392c	450	669	1016	12.69	9.49 ± 0.16	0.521	0.248	0.837 ± 0.031	72.60 ± 4.66
	040492a	420	334.5	1014	26.61	10.46 ± 0.01	0.545	0.143	0.735 ± 0.037	89.89 ± 2.27
	040492b	400	334.5	1014	27.40	7.96 ± 0.05	0.562	0.112	0.726	89.64
	040592a	400	240.7	730	27.46	6.75 ± 0.34	0.577	0.0703	0.792 ± 0.110	64.10
	040592b	450	240.7	730	25.12	15.96	0.550	0.158	0.752 ± 0.006	61.30 ± 1.44
	040592c	470	240.7	730	24.93	15.96	0.760	0.219	0.638 ± 0.013	52.56 ± 0.55
	040692a	470	334.5	1009	24.70	17.36 ± 0.13	0.439	0.436	0.553 ± 0.013	51.17 ± 0.65
2% Th on ZrO ₂ by impregnation. 5cc, 6.733 g	122191a	420	223	997	39.19	15.79 ± 0.35	0.690	0.182	1.94 ± 0.02	62.82 ± 0.72
	122191b	450	223	1002	37.60	23.19 ± 0.36	0.642	0.249	1.21 ± 0.24	51.99 ± 2.21
	122291	450	223	1168	43.56	26.99 ± 0.07	0.520	0.245	0.775 ± 0.003	45.89 ± 0.01

^aAt 0 °C and 1 atm.

Table 10. Hydrocarbon Distribution for 2% Th/ZrO₂

T (°C)	420	455	455
P (atm, gauge)	67.8	68.2	79.5
H ₂ :CO, molar	1	1	1
Space time (s)	39.2	37.6	43.6
CO conversion (%)	15.7	23.0	27.0
isosynthesis profile (wt)	4.73	3.44	3.84
i-C ₄ */all C ₄ 's (wt%)	62.8	54.8	45.9
CH ₄ in hydrocarbons (wt%)	10.7	18.2	30.4
i-C ₄ */CH ₄ (wt)	1.95	1.21	0.78
MeOH+DME/hydrocarbons (wt)	0.35	<0.01	<0.01
Distribution among hydrocarbons			
C ₁	10.7	18.2	30.4
C ₂	4.259	9.601	8.0
C ₃	2.664	5.837	5.5
C ₄	33.30	48.29	51.6
C ₅ +	49.92	18.07	4.6

Figure 1. Comparison of Activity at 400 °C and 1/1 CO/H₂.

Figure 2. Simulation of 1.6% Na (▲) and ZrO₂ ppt. (◆) at 400 °C, 95 atm and 2/1 CO/H₂. Rate is mol/sec*kg-cat.

Figure 3. Comparison of Catalytic Activity at 450 °C and 1/1 CO/H₂.

Figure 4. Effect of Temperature on Reaction Rate.

Figure 6. Total Hydrocarbon Production Rate at 400 °C, 50 atm and 1/1 CO/H₂.

Figure 7. Isobutylene Production Rate at 450 °C, 70 atm and 1/1 CO/H₂.

Figure 8. Total Hydrocarbon Production Rate at 450 °C, 70 atm and 1/1 CO/H₂.

Changes in Conversion with Space Time and Pressure at 400 °C and 1:1 CO:H₂ Feed Ratio over Na-Ti-ZrO₂

Figure 9. Effect of Space Time and Pressure on CO Conversion For 1.6%Na10.3%TiZrO₂
(400 °C, 1:1 CO:H₂ Feed Ratio)

Production Rates at 400 °C and 1:1 CO:H₂ Feed Ratio for the Higher Conversion Runs over Na-Ti-ZrO₂

Figure 10. Effect of Space Time and Pressure on Production Rates For 1.6%Na10.3%Ti/ZrO₂
(400 °C, 1:1 CO:H₂ Feed Ratio)

Changes in Production Rates with Pressure at 400 °C, 1:1 CO:H₂ Feed Ratio, and 60 sec Space Time over Na-Ti-ZrO₂

Figure 11. Effect of Pressure on Production Rates For 1.6%Na10.3%Ti/ZrO₂ (400 °C, 1:1 CO:H₂ Feed Ratio, Space Time, τ , = 60 s)

Comparison of Hydrocarbon Distributions at 400 C, 21 atm, 1:3 CO:H₂, 10 sec tau,
and ~5.0% CO Conversion

Figure 12. Effect of Sodium on Hydrocarbon Distributions at 5% CO Conversion
(21 atm., 400 °C, 1:3 CO:H₂ Feed Ratio, τ = 10 s)

Comparison of Hydrocarbon Distributions at 400 °C, 1:1 CO:H₂ Feed Ratio, 35 atm,
and ~10.8% CO Conversion

Figure 13. Effect of Sodium on Hydrocarbon Distributions at 10.8% CO Conversion
(35 atm., 400 °C, 1:1 CO:H₂ Feed Ratio)

Figure 14. Relationship Between Space Velocity and Space Time at 400 C, 1:1 CO:H₂ Feed Ratio, and 50 atm for the Na-Ti-ZrO₂ Catalyst

Figure 15. Relationship Between Space Velocity and Pressure at 400 C, 1:1 CO:H₂ Feed Ratio, and 60 sec Space Time for Na-Ti-ZrO₂ Catalyst.

APPENDIX

*milestones
removed.
ds*

Figure A1. XRD pattern for 1.6% Na/ZrO₂ (ppt) calcined at 500°C

Figure A2. XRD pattern for ZrO_2 (ppt) calcined at 500°C

Figure A3. XRD pattern for ZrO_2 (ppt) after reaction

Figure A4. XRD pattern for 10% Th/ZrO₂ (hydrothermal) calcined at 500°C

Figure A5. XRD pattern for $\text{Zr}_{0.8}\text{Si}_{0.2}\text{O}_2$ (HCl-sol gel) calcined at 500°C

Figure A6. XRD pattern for 1.6%Na 10.3%Ti/ZrO₂ (HT) calcined at 500°C

Figure A7. XRD pattern for $\text{Si}_{0.2}\text{Zr}_{0.8}\text{O}_2$ (HT) calcined at 500°C

Figure A8. XRD pattern for 7%Cs/Si_{0.2}Zr_{0.8}O₂ (sol gel/IE) prior to calcination

Figure A9. XRD pattern for ZrO_2 (sol gel) calcined at 500°C

END

**DATE
FILMED**

3 / 22 / 93