DOE/PC/89760-770

A NOVEL APPROACH TO HIGHLY DISPERSING CATALYTIC
MATERIALS IN COAL FOR GASIFICATION

DOE/PC/89760--T10

DE92 019729

Second Quarterly Report

for the Period

January 1, 1990 - March 31, 1990

Godfried M.K. Abotsi and Kofi B. Bota

Principal Investigators

Research Center for Science and Technology

Clark Atlanta University

Atlanta, Georgia 30314

PREPARED FOR

UNITED STATES DEPARTMENT OF ENERGY

UNDER CONTRACT NO. DE-FG22-89PC89760

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

MASTER

db
DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

DISTRIBUTION

Dr. Jagdish L. Malhotra
U.S. Department of Energy
Morgantown Energy Technology Center
P.O. Box 880
Morgantown, WV 26505

Marilyn Keane
PM-40, MS922-206
U.S. Department of Energy
Pittsburgh Energy Technology Center
P.O. Box 10940
Pittsburgh, PA 15236

Cynthia Y. Mitchell
Contract Specialist
AD-22, 921-165
U.S. Department of Energy
Pittsburgh Energy Technology Center
P.O. Box 10940
Pittsburgh, PA 15236

Kay Downey
Office of Technology Transfer
U.S. Department of Energy
Mail Stop 58-M217
Pittsburgh Energy Technology Center
P.O. Box 10940
Pittsburgh, PA 15236

ABSTRACT

This project seeks to develop a technique, based on coal surface properties, for highly dispersing catalysts in coal for gasification and to investigate the potential of using potassium carbonate and calcium acetate mixtures as catalysts for coal gasification. The lower cost and high catalytic activity of the latter compound will produce economic benefits by reducing the amount of K_2CO_3 required for high coal char reactivities.

The work is focused on the elucidation of coal-catalyst precursor interactions in solution and the variables which control the adsorption and dispersion of coal gasification metal catalysts. In order to optimize coal-metal ion interactions and hence maximize catalyst activity, the study examines the surface electrochemistry of a lignite, a subbituminous, and a bituminous coals and their demineralized and oxidized derivatives prior to loading with the catalytic materials. The surface electrical properties of the coals are investigated with the aid of electrophoresis, while the effects of the surface charge on the adsorption of K^+ and Ca^{2+} are studied by agitating the coals with aqueous solutions of potassium or calcium.

Zeta potential studies show that the surfaces of the lignite are negatively charged between about pH 2 to 11, the negative charge density increasing with increase in pH. Highly alkaline media promoted calcium adsorption due to

high negative charge on the coal, while calcium uptake was inhibited in strongly acidic solutions.

TECHNICAL PROGRESS REPORT

INTRODUCTION

Prior to its catalytic gasification, coal is generally loaded with catalytic materials by mechanically mixing the coal with a solid catalyst precursor, by impregnation with a solution containing the catalyst precursor (incipient wetness technique), or by ion-exchange of the catalyst precursor metal ions with protons on the coal (1-3). For the same catalytic material, the various techniques typically produce different coal char reactivities under identical reaction conditions. The disparities in catalyst performance has been attributed to differences in catalyst dispersion, induced by differences in coal-catalyst contact.

Despite their significant influence on catalyst activity, the effects of interfacial phenomena on the adsorption of coal gasification metal catalysts has not been previously investigated. This report describes the effects of surface charge on a lignite on the adsorption of calcium ions from solution.

EXPERIMENTAL

The coals currently under investigation are a lignite (PSOC 1482) and a subbituminous coal (PSOC 1485), both of which were sealed in argon and supplied by the Penn State Coal Sample Bank. The ultimate and proximate analyses of the coals are provided in Table 1.

The surface charge properties of the coals were measured at room temperature using a Pen Kem Model 501 Lazer Zee Meter zeta potential instrument. Slurries were prepared by dispersing 300mg samples of each coal (equal proportions of -20 and -80 U.S. mesh sizes) in a liter of deionized water containing 10^{-3} moles l^{-1} $AgNO_3$ for ionic strength control. After the coal particles have been well-dispersed by agitation in an ultrasonic bath, the sediments were separated from the suspended particles, the latter fraction was divided into 50.0 cm^3 portions, and the pH's of the dispersions were varied with nitric acid or ammonium hydroxide solutions. After 4h equilibration (by mechanical agitation), each sample was transferred to the zetameter and the zeta potentials of the coal particles were measured.

The effect of coal surface charge on the adsorption of calcium ions was determined by dispersing 1.0g samples of coal in an aqueous solution containing 10^{-2} moles l^{-1} of Ca^{2+} . The samples were conditioned by shaking for 24h after

which they were filtered and the filtrates analyzed for calcium with atomic absorption spectrophotometry. Metal uptake was calculated as the difference in calcium content of the solutions prior to and after adsorption.

RESULTS AND DISCUSSION

The zeta potential results given in Figure 1 show that the surfaces of the lignite coal particles are negatively charged over a wide range of pH and that the isoelectric point (iep) occurs at about pH 1.9, the surfaces of the coal particles being positively and negatively charged, respectively, below and above this pH value. A review of the iep's of coals shows that the iep for coals occurs in the acidic range (4).

A striking feature of Figure 1 is that the negative charge density increases with increase in pH. A similar trend was observed for the subbituminous coal. These observations can be explained in terms of the surface functional groups on coal. It is well known that the surfaces of low-rank coals are dominated by oxygenated surface groups. Several studies [5-7] have shown that the surface chemistry of these coals is determined by these groups, although inorganic species also play a role [6]. In aqueous and basic environments, these acidic groups dissociate and the coal particles acquire negative charges, whereas the surface groups are

protonated in acidic medium, reducing the negative charge density, and the surface may become positively charged in strongly acidic media [5,6]. The formation of surface charge on coals is depicted by equations (1)-(4) for carboxyl (COOH) and hydroxyl (OH) functional groups:

where the subscript(s) designates the coal surface. Such reactions have also been reported for carbon surface oxygen functionality (8-10).

Figure 2 shows the quantities of calcium adsorbed by the lignite as a function of pH. It is observed that calcium uptake is not only inhibited in strongly acidic media (pH < 4), but calcium is actually extracted from the coal into solution, as indicated by the negative calcium values. However, calcium adsorption progressively increased as the pH's of the coal slurries increase. These trends are consistent with the surface charge properties of the coals. As the coal particles become more negatively charged, coal-

Calcium ion interactions become more pronounced as a result of electrostatic interaction between the cations (Ca^{2+}) and the anionic coal surface.

In synopsis, for the first time, it has been shown from the current study that coal surface charge exerts a predominant influence on the adsorption of coal gasification metal ions (Ca^{2+}) from solution. Metal ion adsorption is favored in highly alkaline solution, while it is suppressed in strongly acidic environments. Thus, efficient catalyst impregnation and improved catalyst dispersion and activity may be obtained by controlling the pH and the surface charge on coals.

REFERENCES

1. Wood, B. J., Sancier, K. M., Catal. Rev. - Sci. Eng. 1984, 26 (2), 233.
2. Radovic, L. R., Walker, Jr., P. L., Jenkins, R. G., Fuel 1983, 62, 209.
3. Johnson, J. L. In *Fundamentals of Coal Utilization: 2nd Supplementary Volume*, Elliot, M. A., Ed.; John Wiley: New York, 1981.
4. Quast, K. B., Readett, D. J. Adv. Coll. Int. Sci. 1987, 27(3-4), 169.
5. Kelebek, S. Salman, T.: Smith, G. W. Canad. Metal. Quart. 1982, 21, 205.
6. Fuerstenau, D. W.; Rosenbaum, J. M.; Laskowski, J. Coll. Surf. 1983, 8, 137.
7. Laskowski, J. s., Parfitt, G. D., In "Interfacial Phenomena in Coal Technology," Botsaris, G. D. Glazman, Y. M., Eds., Marcel Dekker, New York, 1988 p. 279.
8. Abotsi, G. M. K.; Scaroni, A. W. Carbon '88 Proceedings of Soc. Chem. Ind. (London), 1988, 422.
9. Abotsi, G. M. K.; Scaroni, A. W. Carbon 1990, 28, 000.
10. Abotsi, G. M. K., Osseo-Asare, K., Int. J. Miner. Process. 1986, 18, 217.

Table 1. Properties of Coals Used

Penn State Sample Number	PS0C-1482	PS0C-1485
Seam	Hagel	Rosebud
State	N. Dakota	Montana
Rank	Lignite	Subbit. B
Ultimate Analysis (daf, %)		
Carbon	71.34	75.78
Hydrogen	4.5	5.30
Nitrogen	1.14	1.19
Total Sulfur	0.79	0.99
Oxygen (by diff.)	22.24	16.75
Proximate Analysis (As Rec'd, %)		
Moisture	34.45	25.37
Volatile Matter	28.18	27.43
Fixed Carbon	31.80	38.67
Ash	5.57	8.54

Figure 1: Dependence of Zeta Potential on pH for North Dakota (Hagel) Lignite (PSOC 1482). Ionic strength was controlled with 10^{-3} moles l^{-1} $AgNO_3$.

Figure 2: Calcium Adsorption as a Function of pH by Hagel Lignite (PSOC 1482).

END

**DATE
FILMED**

10 / 22 / 92