000976

10F1

THEORETICAL STUDIES OF SURFACE REACTIONS
ON METALS AND ELECTRONIC MATERIALS

Progress Report

for Period October 1, 1990 - January 31, 1993

J. L. Whitten

Department of Chemistry

North Carolina State University

Raleigh, N.C. 27695

January 31, 1993

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

MASTER

EP
REPRODUCTION OF THIS DOCUMENT IS UNLIMITED

Report to
U.S. Department of Energy
Current Grant DE-FG05-90ER45436

RECEIVED

MAR 24 1993

OSTI

Theoretical Studies of Surface Reactions on Metals and Electronic Materials

Jerry L. Whitten

I. Scope

This research is part of a theoretical program on the structure and reactivity of molecules adsorbed on transition metal substrates and electronic materials. The work focuses on molecular processes at the surface: adsorbate bonding, coadsorption and surface reactions. Electronic structures are described by an *ab initio* embedding formalism that permits an accurate determination of reaction energetics and adsorbate structure. Surface reactions and the reaction of coadsorbed species are calculated on transition metals and silicon surfaces. These studies of surface phenomena relate to two different areas: the properties of electronic materials and catalytic processes.

II. Overview of Progress

This section contains a brief overview of work during the past two and one-half years of the project. A more detailed compilation of results and abstracts of papers are included in Section III.

Studies of a variety of adsorbates on nickel have now been completed leading to a better understanding of surface sites at which reactions occur. Adsorption energies as a function of surface adsorption site have now been determined for CH, CH₂, CH₃, H, NH₃, H₂O and C₆H₆ on Ni(111) including adsorbate geometry optimization. Lone pair electron species are found to adsorb preferentially at atop Ni sites, but energy differences between the 3-fold, bridge and atop sites are calculated to be small. These results are in sharp contrast to those for hydrocarbon and H atom fragments for which 3-fold symmetry sites are preferred. Structural parameters and adsorption energies for optimized structures have been published for these systems.

The following reactions have now been studied in detail on Ni(111):

Studies of the latter two reactions were completed during the past two years with the main effort focused on the dissociation of methane on Ni(111), $\text{CH}_4 = \text{CH}_3 + \text{H}$. These studies are the first reports of *ab initio* calculations of such surface reactions on a transition metal surface.

A refined calculation of the reaction of methane with nickel, involving a more sophisticated treatment of multiple electronic states was completed. The preferred dissociation site on Ni(111) involves CH_4 atop Ni; this site allows the CH_3 and H products access to separated three-fold sites. The simultaneous participation of two low-lying nickel states, allowed by configuration interaction, turns out to be important in the transition state geometry where there are strong d contributions to the bonding. Analysis of the energetics of the dissociation products shows that fragment adsorption in separated three-fold sites is strongly preferred, i.e., across atom coadsorption sites are much more stable than across bridge sites. This means that CH_4 dissociation occurs most favorably atop Ni, or nearby, since only such sites provide access to stable product sites on the surface. Examination of reaction pathways yields a transition state with activation energy of 16 kcal/mol. corresponding to a stretched C..H bond geometry.

Other studies completed recently include the investigation of H_2 and SiH_4 adsorption and decomposition on silicon surfaces. This work and the investigation of the reconstruction of Si(100) and the monohydride (100) surface were carried out in order to better understand factors that influence surface layer growth. In mechanistic studies of silane decomposition on the Si(100)-2x1 surface, a low energy pathway is found for the reaction $\text{SiH}_4 = \text{SiH}_3 + \text{H}$. It involves two separate steps: scission of one Si-H bond and formation of two new bonds to SiH_3 and H from two surface dangling bonds. The energy barrier, calculated to be 9 kcal/mol, occurs in the first step; the overall reaction, $\text{SiH}_4 = \text{SiH}_3 + \text{H}$, on the surface is calculated to be 2.8 eV exothermic. Quantum tunneling is found to be significant at room temperature.

The discrepancy between first-principles calculations of the Si-Si dimer bond length on the Si(100) surface and LEED measurements was examined by performing *ab initio* calculations on ten previously reported structures. The present work suggests that a correlated wavefunction is necessary to describe the weak second bond of the dimer. When electron correlation is included by configuration interaction, the dimer bond length calculated is in good agreement with LEED values. Reconstruction of the monohydride surface was also investigated. Mechanistic studies of H_2 desorption from Si(100)2x1H

reveal that a symmetric desorption pathway gives the lowest desorption energy barrier; however, the barrier is 1.0 eV higher than experiment. A multi-step desorption mechanism which involves a delocalized process for forming a dihydride, SiH_2 , is proposed to explain the experimental observations.

Reaction of fluorinated substances with silicon are important in materials processing. During the past year, activation energy barriers were determined for the reaction of CH_4 and CH_3F with $\text{Si}(1\bar{1}1)$. A new interpretation of supersonic beam experimental data is proposed based on the kinetic energy of two-atom components of the molecules colliding with the surface. Abstracts of this study and a corresponding study of molecular reactions involving $\text{CH}_{4-n}\text{F}_n$ and SiH_3 are included.

During this period, studies were also begun on the deposition of carbon on $\text{Ni}(111)$, a surface nearly commensurate with that of diamond. Subsurface Na is found to stabilize tetrahedrally bonded carbon whereas subsurface C facilitates the formation of planar configurations of CH_3 and C_6H_6 adsorbed on nickel. An abstract of the first phase of this work dealing with the effect of Na, H and C subsurface species on the bonding of carbon to the nickel surface is included in the next section.

New directions were explored for the reaction of methane with transition metal surfaces. Work was recently completed on the reaction of methane with a nickel (111) surface containing a substitutional iron atom. The presence of the surface Fe atom is found to lower the energy barrier to CH_4 dissociation by decreasing the energy required for undistorted CH_4 to approach the surface. Subsequent activation of the CH bond stretch is similar to that for the nickel surface. These studies are related to the use of methane as a source for syntheses of other hydrocarbons.

An embedding model of the $\text{Fe}(110)$ surface was developed. In collaborative work with P. Cremaschi, studies are underway on hydrogen interactions with $\text{Fe}(110)$ in which vibrational excitations and dissociation probabilities on H_2 collision with a Fe wall will be calculated.

III. Results and Abstracts of Papers (October 1, 1990 - January 31, 1993)

1. The Adsorption of NH_3 on Nickel

A. Chattopadhyay, H. Yang and J. L. Whitten, *J. Phys. Chem.*, **94**, 6379 (1990).

Abstract. The adsorption of ammonia on the [111] surface of Ni is treated using a many-electron embedding theory to describe the electronic bonding, modelling the lattice as a 28-atom, three layer cluster. *Ab initio* valence orbital CI calculations carried out on a local surface region permit an accurate description of bonding at the surface. Molecular NH_3 adsorbed on the Ni(111) surface at an atop atom site and a fcc three-fold site as well as a bridge site are of comparable stability, with adsorption energies of 19.4, 18.4 and 17.3 kcal/mol and with Ni-N equilibrium distances of 2.12, 2.78 and 2.74 Å, respectively; ammonia bonds to the substrate via the N atom with the H's pointing away from the surface. The equilibrium geometry of NH_3 is calculated to have a pyramidal configuration with the molecular axis normal to the substrate, but tilting the molecular axis or rotating the molecule about the surface normal requires little energy. Calculated frequencies of the surface- NH_3 group vibration, perpendicular to the Ni(111) surface, are between 460 and 500 cm^{-1} and the H-N stretching frequency in NH_3 on the surface is 3340 cm^{-1} . The work function decreases by ~ 0.6 eV on NH_3 adsorption.

2. Adsorption of Benzene on Ni(111)

Z. Jing and J. L. Whitten, *Surf. Sci.*, **250**, 147 (1991).

Abstract. Using a many-electron embedding theory, the present work treats the adsorption of benzene on Ni(111) by modeling the lattice as a 28-atom, three layer cluster. *Ab initio* valence orbital CI calculations carried out on a local surface region permit an accurate description of bonding at the surface. Benzene is found to be adsorbed molecularly, parallel to the surface, at a three fold site, bonding primarily through its pi electron system. The equilibrium distance is 2.2 Å from the surface. The calculations show no distortion of the benzene ring, other than a 2 percent expansion. C-H bonds tilt away from the surface 8.5 deg. The adsorption energy is calculated to be 1.2 eV. Adsorption at the three fold hollow site gives a slightly higher energy than the hcp site, but the difference may be within the uncertainty of the calculation. The energy of the bridge adsorption site is higher than that of hcp site, by 0.8 eV. Atop atom sites were not investigated. Due to the limited number of geometries investigated, particularly those involving Kekule and buckling distortions, some aspects of the benzene geometry and energetics of different sites remain uncertain.

3. *Ab Initio* Studies of Silane Decomposition on Si(100)

Z. Jing and J. L. Whitten, Phys. Rev. B **44**, 1741 (1991).

Abstract. The mechanism of silane decomposition on the Si(100)-2x1 surface is investigated in the context of a many-electron theory that permits the accurate computation of molecule-solid surface interactions at an *ab initio* configuration interaction level. The adsorbate and local surface region are treated as embedded in the remainder of the lattice electronic distribution which is modelled as a three-layer, 19-Si plus 21-H cluster. A possible energetic pathway is found for the reaction $\text{SiH}_4 \rightarrow \text{SiH}_3 + \text{H}$ on the surface. It involves two separate steps: (1) scission of one Si-H bond; (2) formation of two new bonds to SiH_3 and H from two surface dangling bonds. The energy barrier, which is calculated to be 9 kcal/mol, occurs in the first step at a distance of 3.6 Å from the Si in SiH_4 to a Si surface atom with a Si-H bond aligned with a surface dangling bond direction. The overall dissociation process $\text{SiH}_4 \rightarrow \text{SiH}_3 + \text{H}$ on the surface is found to be 2.8 eV exothermic. Quantum tunneling is found to play an important role in the process at room temperature. A symmetrical Eckart potential is used to estimate the quantum tunneling effect and the reaction probability is calculated to be small (on the order of 10^{-5}) and relatively insensitive to the silane temperature.

4. *Ab Initio* Chemisorption Studies of CH_3 on Ni(111)

H. Yang and J. L. Whitten, J. Am. Chem. Soc., **113**, 6442 (1991).

Abstract. The adsorption of methyl on the (111) surface of nickel is treated using a many-electron embedding theory to describe bonding, modelling the lattice as a 28-atom, three layer cluster. *Ab initio* valence orbital configuration interaction (multiple parent) calculations carried out on a local surface region permit an accurate description of bonding at the surface. Calculated adsorption energies for CH_3 on the Ni(111) surface are 39 kcal/mol at the three-fold sites, 36 and 34 kcal/mol at the bridge and the atop atom sites with the equilibrium Ni-C distances of 2.35, 2.34 and 2.03 Å, respectively. Calculated CH_3 -(Ni surface) perpendicular stretching frequencies are 369, 296 and 416 cm^{-1} for the three-fold, bridge and atop sites. In the equilibrium geometry methyl hydrogens are in a plane parallel to the surface with a nearly tetrahedral structure. A low C-H vibrational frequency is calculated at 2627 cm^{-1} if one of the hydrogens is tilted to give a C-H bond parallel to the surface, and CH_3 is shifted away from the three-fold center by 0.67 a.u. which puts one of the hydrogens directly above a Ni atom. This geometry is only 1.6 kcal/mol higher in energy than the calculated equilibrium geometry

for which normal C-H vibrational frequencies of around 3000 cm^{-1} are calculated. The reaction of chemisorbed $\text{CH}_2(\text{ads}) + \text{H}(\text{ads}) = \text{CH}_3(\text{ads})$ on the surface is 13 kcal/mol exothermic. An energy barrier occurs when CH_2 and H are moved from infinite separation to form CH_3 . A combination of covalent-*s* and -*d* bonding characterizes the bonding of CH_3 to the nickel surface.

5. Chemisorption of Atomic H and CH_x Fragments on Ni(111)

H. Yang and J. L. Whitten, Surf. Sci. 255, 193 (1991).

Abstract. The adsorption of atomic hydrogen, methyldyne, methylene and methyl on the (111) surface of nickel is treated using a many-electron embedding theory to describe bonding, modelling the lattice as a 28-atom, three layer cluster. *Ab initio* valence orbital configuration interaction (multiple parent) calculations carried out on a local surface region permit an accurate description of bonding at the surface. All adsorbed species are found to bind strongly to the Ni(111) surface at three-fold and bridge sites with adsorption energies ranging from 1.5 eV to 3.1 eV. Atop Ni adsorption sites are significantly higher in energy. Bond lengths, angles and vibrational frequencies for adsorbates on the surface are calculated. The geometries of the adsorbed species and the nature of the bonding to the surface are discussed.

6. Dissociative Chemisorption of CH_4 on Ni(111)

H. Yang and J. L. Whitten, J. Chem. Phys. 96, 5529 (1992).

Abstract. The dissociative chemisorption of methane at an atop-atom site on a (111) surface of nickel is treated using a many-electron embedding theory to describe bonding, modelling the lattice as a 41-atom, three layer cluster. *Ab initio* valence orbital configuration interaction (multiple parent) calculations carried out on a local surface region permit an accurate description of bonding at the surface. Ni 3d orbitals are explicitly included on seven nickel atoms on the surface. The calculated activation energy of CH_4 adsorbed at an atop Ni site to produce CH_3 and H coadsorbed at separated 3-fold sites is 17 kcal/mol. The dissociation of CH_4 to $\text{CH}_3(\text{ads}) + \text{H}(\text{ads})$ is predicted to be 2.8 kcal/mol exothermic. The Ni 3d orbitals contribute to the bonding by directly mixing with methane C-H orbitals during the dissociation process and through a direct interaction of $3d^9$ and $3d^{10}$ configurations at the transition state. The dissociation pathway and the bonding properties of adsorbed CH_4 and coadsorbed CH_3 and H are discussed.

7. Theoretical Studies of Surface Reactions on Metals: Clusters and Embedding Theory

J. L. Whitten, chapter in Cluster Models for Surface and Bulk Phenomena, G. Pacchioni and P. S. Bagus, eds., Plenum, (1992).

Abstract. This research concerns the structure of molecules adsorbed on solid surfaces and dissociative chemisorption with emphasis on transition metal substrates and electronic materials. Cluster models are discussed and results are analyzed to demonstrate cluster boundary artifacts and basis imbalance effects. Electron localization techniques are used to establish a many-electron embedding model for treating surface reactions. The Fe(110) surface is used as an example.

8. Dissociation of Methane on Adatom Ni(111)

H. Yang and J. L. Whitten, Bull. Am. Phys. Soc. 37, 106 (1992); 203rd ACS National Meeting in San Francisco, 1992.

Abstract. The dissociation of methane on a Ni(111) surface with a Ni adatom is treated using a many-electron embedding theory to describe bonding, modelling the lattice as a 42-atom, three layer cluster. *Ab initio* valence orbital configuration interaction (multiple parent) calculations carried out on a local surface region permit an accurate description of bonding at the surface. Ni 3d orbitals are explicitly included on a Ni adatom and five Ni atoms on the surface. The lowest calculated activation energy of CH₄ to produce CH₃ and H coadsorbed on the surface is 10 kcal/mol. The dissociation of CH₄ to CH₃(ads) + H (ads) is predicted to be 2.8 kcal/mol exothermic. The Ni 3d orbitals contribute to the bonding by directly mixing with methane C-H orbitals during the dissociation process. Several dissociation pathways are calculated. In comparison with a flat Ni(111) surface, the presence of Ni adatom is effective in activating CH₄.

9. Chemical Induction Effects: O-incorporation in, and Substitutional Doping of a-Si:H

G. Lucovsky, Z. Jing and J. L. Whitten, J. of Non-Cryst. Solids, (1991).

Abstract. This paper identifies several important non-statistical bonding environments in alloyed and doped a-Si:H that derive from chemical effects during film deposition. These include O-Si-H linkages in a-Si₂O:H alloys, and the P⁺-Si-H and Si-B⁻-H linkages that play a significant role in the doping processes in a-Si:H. We present the experimental evidence for these local bonding arrangements, and a chemical bonding model that accounts for their creation during film deposition.

10. Dissociative Chemisorption of CH₄ on Ni(111)

H. Yang and J. L. Whitten, J. Chem. Phys. **96**, 5529 (1992)

Abstract. The dissociative chemisorption of methane at an atop-atom site on a (111) surface of nickel is treated using a many-electron embedding theory to describe bonding, modelling the lattice as a 41-atom, three layer cluster. *Ab initio* valence orbital configuration interaction (multiple parent) calculations carried out on a local surface region permit an accurate description of bonding at the surface. Ni 3d orbitals are explicitly included on seven nickel atoms on the surface. The calculated activation energy of CH₄ adsorbed at an atop Ni site to produce CH₃ and H coadsorbed at separated 3-fold sites is 17 kcal/mol. The dissociation of CH₄ to CH₃(ads) + H (ads) is predicted to be 2.8 kcal/mol exothermic. The Ni 3d orbitals contribute to the bonding by directly mixing with methane C-H orbitals during the dissociation process and through a direct interaction of 3d⁹ and 3d¹⁰ configurations at the transition state. The dissociation pathway and the bonding properties of adsorbed CH₄ and coadsorbed CH₃ and H are discussed.

11. Effects of Subsurface Na, H and C on CH₃ Adsorption on Ni(111)

H. Yang, J. L. Whitten, R. E. Thomas, R. A. Rudder, and R. J. Markunas, Surf. Science, **277**, L95 (1992).

Abstract. *Ab initio* valence orbital configuration interaction calculations are used to study the energy effect of Na, H and C atom subsurface species on CH₃ chemisorption at a hollow 3-fold site on Ni(111). The lattice is modeled as an embedded three layer cluster of 41 atoms. Ni 3d orbitals are explicitly included on seven nickel atoms on the surface. The calculated chemisorption energies of pyramidal CH₃ on Ni(111) are 38 for the clean surface and 50, 47, and 17 kcal/mol for the Na, H, and C implants, respectively. The energies required to distort tetrahedral CH₃ into a planar structure are 22 kcal/mol on clean Ni(111), 30 kcal/mol with the Na implant, 24 kcal/mol with the H implant, and 12 kcal/mol with the C implant, respectively. Thus, Na below the surface may stabilize a carbon overlayer to a tetrahedral diamond structure. CH₃-surface distances, C-H stretching and surface-CH₃ vibrational frequencies are also reported.

12. Si-H Bonds in O-Substitutional doping of a-Si:H

Z. Jing, J. L. Whitten and G. Lucovsky, Phys. Rev., **B45**, 13978 (1992).

Abstract. *Ab initio* CI theory is used to study Si-H bonds in the a-Si:H and O doped a-Si:H:O systems. The a-Si:H is modelled by a finite Bethe lattice containing 13 Si atoms and 28 H atoms with a local configuration of 3Si-SiH. By the incorporation of three O atoms in the cluster, the a-Si:H:O system is modelled to have a local configuration of 3O-SiH. The H dissociation energy is calculated to be 3.55 eV in 3Si-SiH and 4.11 eV in 3O-SiH. A 1.5% decrease in the Si-H bond length and 5.1% increase in the Si-H stretching frequency are found with the incorporation of three O atoms. Incorporation of O atoms increases the electron loss from the Si atom of the SiH group strengthening the SiH bond.

13. *Ab Initio* Studies of Si(100) Surface Reconstruction

Z. Jing and J. L. Whitten, *Surface Sci.*, **274**, 106 (1992).

Abstract. The reconstruction of Si(100) surface is studied by a cluster method at several theoretical levels. It is found that the calculated surface dimer bond length is very sensitive to the level of theoretical treatment. A single-determinant SCF treatment gives a closed-shell singlet state higher in energy than the triplet state and a dimer length for the singlet of 2.21 Å, 0.26 Å shorter than the triplet. The correct ground state is a singlet, but a multi-determinant wavefunction is required for its description. At the CI level, the surface dimer in the ground state is found to be symmetrical with a dimer bond length of 2.40 Å and the energy decrease for dimer formation with respect to the ideal Si(100) 1x1 surface is 1.98 eV per dimer. The total energies of 10 alternative structural models are also calculated. It is found that, in general, those models with very short dimer lengths (<2.25 Å) and/or with large buckling are less stable than those models with longer dimer lengths (~2.40 Å) and with little or no buckling.

14. *Ab Initio* Studies of H Chemisorption on Si(100)

Z. Jing and J. L. Whitten, *Phys. Rev.*, **B46**, 9544 (1992).

Abstract. *Ab initio* CI theory is used to study the chemisorption of hydrogen on the Si(100) 2x1 reconstructed surface in the monohydride and dihydride phases. A three-layer cluster which consists of 12 silicon atoms and 20 hydrogen saturators is used to simulate the major features of surface reconstruction. The chemisorption of H atoms changes the surface reconstruction slightly in the monohydride phase, shifting the dimer length from 2.401 Å in an H-free surface to 2.466 Å and 2.472 Å for a dimer bonded with one and two H atoms, respectively. The Si-H bond energy is calculated to be 3.50 eV for

the chemisorption of the first H atom and 3.58 eV for the chemisorption of the second H atom, including the zero-point vibrational energy. The Si-H stretch frequency is computed to be 2099 cm^{-1} . In forming the dihydride phase, the chemisorption of H atoms destroys surface dimers and changes the reconstructed 2×1 surface to the unreconstructed 1×1 surface. The interactions between surface SiH_2 groups are found to be repulsive. The desorption of H_2 from the monohydride and dihydride phases is also discussed.

15. Dissociative Adsorption of H_2 on Ni(111)

H. Yang and J. L. Whitten, "J. Chem. Phys., accepted (1992).

Abstract. *Ab initio* configuration interaction calculations are performed to study the dissociative adsorption of H_2 on a Ni(111) surface. The lattice is modeled as an embedded three-layer, 41-atom cluster. Ni 3d orbitals are explicitly included on seven Ni atoms on the surface. H is preferentially chemisorbed at a 3-fold site on Ni(111) and the calculated binding energy of 62 kcal/mol, H-Ni distance of $1.86\text{ \AA}$, and H vibrational frequency of 1176 cm^{-1} are in excellent agreement with experimental data. H adsorbed at bridge and on-top Ni sites is 2.5 and 8.1 kcal/mol less stable, respectively. The heat of reaction $\text{H}_2(\text{gas}) \rightarrow 2\text{H}(\text{ads})$ is calculated to be 22.0 kcal/mol exothermic. When two H atoms are adsorbed as nearest neighbors to the same Ni atom, 3-fold sites are preferred with H atoms adsorbed at fcc-fcc, hcp-hcp or across atom fcc-hcp sites. These structures are consistent with the observed $(2\times 2)\text{-}2\text{H}$ LEED pattern. The average adsorption energy per H is calculated to be 62 kcal/mol for the across atom case. Adsorption of H at a 3-fold site on Ni(111) has a tendency to block adsorption at adjacent 3-fold sites; coadsorbed H atoms at adjacent sites are unbound by 15.5 kcal/mol relative to H_2 at infinite separation. For three H atoms chemisorbed at separated 3-fold sites sharing a Ni atom with the equal H-H lateral distances of $2.48\text{ \AA}$, the calculated average adsorption energy is 60 kcal/mol per H. Dissociation of H_2 at an on-top Ni site has the lowest activation barrier of 1.6 kcal/mol. For the transition state, the H-H bond length, H-surface height, and H-H vibrational frequency are $1.22\text{ \AA}$, $1.38\text{ \AA}$, and 2506 cm^{-1} , respectively. Molecular H_2 adsorbed over an on-top site is bound by 3.4 kcal/mol with a slightly stretched H-H bond length of $0.79\text{ \AA}$, H-surface height of $1.85\text{ \AA}$, and H-H stretching frequency of 3396 cm^{-1} .

16. Reaction of CH_4 and CH_3F with Si(111)

H. Yang, Z. Jing and J. L. Whitten, manuscript (1992).

Abstract. *Ab initio* configuration interaction theory coupled with cluster model calculations is used to study the reactions of CH_4 and CH_3F on a $\text{Si}(111)$ surface. The lattice is modeled as a three layer cluster of 13 Si atoms plus 27 H atoms. The calculated heat of reaction for $\text{CH}_4 + \text{Si}(111) \rightarrow \text{CH}_3 + \text{H-Si}(111)$ is endothermic by 13 kcal/mol, with an energy barrier of 24 kcal/mol. The reaction $\text{CH}_3\text{F} + \text{Si}(111) \rightarrow \text{CH}_2\text{F} + \text{H-Si}(111)$ is calculated to be 12 kcal/mol endothermic, with an energy barrier of 20 kcal/mol. The reaction $\text{CH}_3\text{F} + \text{Si}(111) \rightarrow \text{CH}_3 + \text{F-Si}(111)$ is calculated to be 24 kcal/mol exothermic, with an energy barrier of 19 kcal/mol. F, H, CH_3 , and CH_2F species are found to bind very strongly to the $\text{Si}(111)$ surface, with adsorption energies of 132, 86, 78, and 76 kcal/mol, respectively. Equilibrium geometries for F, H, CH_3 , and CH_2F on $\text{Si}(111)$, vibrational frequencies and transition state geometries for the transfer of H and F in reactions of CH_4 and CH_3F with $\text{Si}(111)$ are reported.

17. Dissociative Chemisorption of CH_4 on a Substitutional Fe/Ni(111) Surface

H. Yang and J. L. Whitten, C&EN, March 2, 63 (1992), the 203rd ACS National Meeting in San Francisco; Surf. Sci. accepted (1992).

Abstract. The dissociative chemisorption of methane at an atop Fe site on a substitutional Fe/Ni(111) surface is treated using a many-electron embedding theory to describe bonding, modelling the lattice as a 41-atom, three layer cluster. *Ab initio* valence orbital configuration interaction (multiple parent) calculations carried out on a local surface region permit an accurate description of bonding at the surface. Ni 3d orbitals are explicitly included on the central Fe atom and six nearest neighbor of Ni atoms on the surface. The calculated activation energy of CH_4 adsorbed at an atop Fe site to produce CH_3 and H coadsorbed at separated 3-fold sites is 5.7 kcal/mol, compared with 16.7 kcal/mol on clean Ni(111). The dissociation of CH_4 to $\text{CH}_3(\text{ads}) + \text{H}(\text{ads})$ is predicted to be 3.9 kcal/mol exothermic on Fe/Ni(111) surface. The Fe and Ni 3d orbitals contribute to the bonding by directly mixing with methane C-H orbitals during the dissociation process. In comparison with a flat Ni(111) surface, the substitutional Fe/Ni(111) surface is strongly effective in activating CH_4 .

18. Pathway of H_2 Desorption from Dihydride $\text{Si}(100)$

Z. Jing and J. L. Whitten, manuscript, (1992).

Abstract. Two possible mechanisms for H_2 desorption from a dihydride Si(100) surface are investigated:

The first mechanism, which involves the recombination of two H atoms bonded to the same surface silicon atom, is found to be 48 kcal/mol endothermic. The minimum energy desorption pathway has an activation energy of 53 kcal/mol. In the second mechanism, desorption of H_2 by recombination of hydrogen atoms on adjacent silicons is found to have a desorption energy approximately zero and a activation energy of 70 kcal/mol for the symmetric pathway. A three-layer cluster which consists of 12 silicon atoms and 20 hydrogen saturators is used to simulate the Si(100) surface and *ab initio* SCF and CI theory is used to treat the cluster and desorption reactions.

19. Reaction of $\text{CH}_{4-n}\text{F}_n$ with SiH_3

Z. Jing and J. L. Whitten, manuscript, (1992).

Abstract. The present paper studies the transfer of H and F between $\text{CH}_{4-n}\text{F}_n$ ($n = 0, 4$) and SiH_3 , which is a process closely related to the fluorination of a Si(111) surface. Structures of the reaction fragments and transition states are optimized and total energies are calculated using SCF plus second-order Moller-Plesset perturbation theory. The C-H bond dissociation energies in $\text{CH}_{4-n}\text{F}_n$ are nearly constant, varying only slightly from CH_4 to CHF_3 . They are 12-17 kcal/mol stronger than the Si-H bonds in SiH_4 . The C-F bonds are 18-40 kcal/mol weaker than the Si-F bonds. Thus, transfers of H are endothermic and that of F exothermic. Energy barriers are nearly constant (~24 kcal/mol) for the transfer of H and increase steadily for the transfer of F from 27 kcal/mol to 45 kcal/mol with increasing of number of F atoms bonded to C. Calculations on the reaction of CH_4 with a cluster model of Si(111) illustrate the similarity of this process to the transfer of H from CH_4 to SiH_3 .

20. Mechanism of H_2 Desorption from Monohydride Si(100)2x1H

Z. Jing, G. Lucovsky and J. L. Whitten, Phys. Rev. Lett, submitted, (1992).

Abstract. Most recent experimental work on H_2 desorption from the monohydride Si(100) surface seems to point to a pairwise desorption mechanism involving the concerted desorption of two hydrogen atoms on different Si atoms of a single dimer. Using *ab initio* SCF and CI theory and a cluster model of the surface, the present work

finds that the lowest energy pathway is symmetric rather than asymmetric. The desorption energy barrier is calculated to be 3.7 eV. Compared with an experimental value of 2.6 eV, the large barrier suggests that this direct desorption mechanism is not applicable. A multi-step desorption mechanism which involves a delocalized process in the formation of dihydride SiH_2 and a localized desorption of H_2 is proposed and is shown to explain the experimental observations.

Personnel Supported by DOE Grant

Postdoctoral Research Associate, Z. Jing, 10/1/90 - present.

Postdoctoral Research Associate, H. Yang, 10/1/910- present.

Visiting scientist Dr. P. Cremaschi, no cost.

Principal investigator J. L. Whitten, no cost.

END

**DATE
FILMED**
4/9/93