DOE/PC/90055--T6

DEC 22 1992

RECEIVED
DEC 02 1993
GPO

TECHNOLOGY DEVELOPMENT FOR IRON FISCHER-TROPSCH CATALYSTS

Contract DE-AC22-90PC90055

Technical Progress Report No. 5
9/26/91 - 12/26/91

DOE/PC/90055--T6

DE93 008105

by

R. R. Frame and H. B. Gala

UOP
Des Plaines, Illinois

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

PATENT CLEARED BY CHICAGO

OPC ON October 20, 1992

MASTER

REPRODUCTION OF THIS DOCUMENT IS UNLIMITED

TECHNOLOGY DEVELOPMENT FOR IRON FISCHER-TROPSCH CATALYSTS

Contract DE-AC22-90PC90055

**Technical Progress Report No. 5
9/26/91 - 12/26/91**

by

Robert R. Frame and Hemant B. Gala

**UOP
25 E. Algonquin Road
Des Plaines, Illinois**

CONTRACT OBJECTIVE

The objectives of this contract are to develop a technology for the production of active and stable iron Fischer-Tropsch catalysts for use in slurry-phase synthesis reactors and to develop a scaleup procedure for large-scale synthesis of such catalysts for process development and long-term testing in slurry bubble-column reactors. With a feed containing H_2 and CO in the molar ratio of 0.5 to 1.0 to the slurry bubble-column reactor, the catalyst performance target is 88% $CO + H_2$ conversion at a minimum space velocity of 2.4 NL/hr/gFe. The desired sum of methane and ethane selectivities is no more than 4%, and the conversion loss per week is not to exceed 1%.

CONTRACT TASKS

Task 1.0: Catalyst development

- 1.1: Technology assessment**
- 1.2: Precipitated catalyst preparation method development**
- 1.3: Novel catalyst preparation methods investigation**
- 1.4: Catalyst pretreatment**
- 1.5: Catalyst characterization**

Task 2.0: Catalyst testing

Task 3.0: Catalyst aging studies

Task 4.0: Preliminary design and cost estimate of a catalyst synthesis facility

SCOPE OF WORK DURING THE REPORTING PERIOD

Task 1.3

Work is under way to prepare novel iron catalysts from oxalates. The preparation method developed can be modified to prepare iron metal catalyst, iron oxide catalyst precursors, and iron carbide catalysts. The method consists of mixing iron (II) acetate with minor amounts of copper (II) and potassium acetates (see Appendix A). To this mixture is added sufficient methanol and water (5:1 by volume) to bring about solution, and then a slight excess of oxalic acid is added. The resulting precipitate is recovered by filtration. Scanning electron microscopy of the precipitate indicates an intimate mixture of the oxalates. Evidence indicates that vacuum heat treatment causes this material to lose mass in a stepwise fashion:

1. Surface-bound H_2O ($< 100^\circ\text{C}$)
2. Water of hydration (about 125°C)
3. Oxide(s) of carbon ($> 200^\circ\text{C}$)

Iron oxalate is known to thermally decompose to iron metal. The material prepared by the method described above is pyrophoric, and so the presence of zero valent metal is indicated.

Task 2.0

A catalyst prepared by United Catalysts, Inc. (UCI) was evaluated in UOP's slurry autoclave plant. This catalyst was prepared as a prototype for a larger batch to be used in the slurry bubble-column reactor demonstration run at Air Product's LaPorte facility. This four-component catalyst contains Fe, Si, Cu, and K in the following weight ratio: 100:8.06:4.38:8.58. The slurry autoclave reactor is operated inside a hot box, which is maintained at 160°C . Feed is added continuously below the liquid level in the reactor. Overhead gas is removed continuously from the reactor and taken first in a trap in the hot box (160°C , about 5 psi less than the plant operating pressure) and then into a 0°C trap (50 psig) followed by a -78°C trap (atmospheric pressure). A slipstream of the gas exiting the 160°C hot box is analyzed by an on-line GC analyzer, which performs a boiling-point type of analysis. A slipstream of the gas exiting the 0°C trap is analyzed by an on-line GC analyzer, which performs a gas analysis (CO , CO_2 , H_2 , A, C_1 , C_2 , C_3). The liquid level in the

autoclave is maintained at a constant level by periodic withdrawals of wax. This wax is also taken into the hot box trap; any material that does not condense in this trap is taken into the two traps that are outside the hot box.

A single run (Run 44) was performed with this catalyst. The catalyst testing procedure and conversion-selectivity calculations are described in the Technical Progress Report covering the period from 4/1/90 to 6/30/90 of a previous UOP Fischer-Tropsch contract, DE-AC22-87PC79812.

Run 44

The autoclave was loaded with 72.7 g of as-received UCI catalyst and 290 g of a C-30 oil obtained from the Ethyl Corporation.

The pretreatment was 12 hr long. During this time, the normal feed, which is a blend of H_2 , CO, and A in the molar ratio 0.7:1.0:0.1, was used. Argon is an internal standard. The feed rate, temperature, and pressure were 2 NL/hr/gFe, 280°C, and 153 psig, respectively. These conditions are the same as those used in all of UOP's recent work and are based on pretreatment conditions used by previous workers. During the remainder of the run, the feed rate, temperature, and pressure were 2.4 NL/hr/gFe, 265°C, and 290 psig, respectively.

Run 44 results are summarized in the figures and table in Appendix B. Figure 1 summarizes CO conversion. As was found with previous runs, the conversion fell rapidly right after the activation period and then fell more slowly. By about 400 hr on-stream, the CO conversion appeared to stabilize at 60%. Activity loss also occurred before apparent stabilization with UOP's three component catalyst (Fe, Cu, K). Figure 2 compares the CO, H_2 , and CO+ H_2 conversions along with the H_2 and CO usage, which was constant throughout the run at 0.55. Figure 3 contains a summary of CO₂ selectivity, which was as high as expected for an iron-based catalyst.

A step down in activity was noted when a new feed (Feed B) was used. A small amount of the previous feed (Feed A) was available. When it was reintroduced, the catalyst activity seemed to recover somewhat; however, not enough of this feed was available to run long enough to definitely conclude that the activity loss with the second feed was fully reversible. Attempts were

made to determine if the second feed had any impurities. Both feeds were analyzed for trace amounts of sulfur (total) and oxygen (Table 1); however, in both feeds, these elements were below the limits of the detectability of the analytical instruments.

The UCI catalyst was formulated to produce low levels of light ends. Figures 4, 5, and 6 summarize the C_1 to C_3 hydrocarbon selectivities from the on-line gas analysis. These selectivities are as low as expected. Near the end of the run, these selectivities appeared to be lining out; at that point, the sum of the C_1 and C_2 paraffin selectivities was 5.2%.

Figures 7 to 13 summarize C_1 to C_{10} selectivities as calculated from boiling point GC analysis. Figure 14 is a plot of log mole fraction at a given carbon number vs. carbon number at 450 hr on-stream (Schulz-Flory plot). The plot was constructed from data in Figures 1 to 13. The data show an apparent linear relation up to C_6 ; past C_6 , the curve appears to break away from linearity. The historic Schulz-Flory mechanism rationalizes Fischer-Tropsch product distribution using Flory's mathematical treatment of polymerization chemistry. A constant, α , is employed. This constant is the probability that a chain of a given length will grow by one carbon unit. A plot such as the one in Figure 14 is predicted to be linear for all carbon numbers; the slope of this plot should be $\log \alpha$. Satterfield and others have attributed deviations from linearity to a mechanism in which two α 's are operative: α_1 , which dominates at low carbon numbers, and α_2 , which dominates at high carbon numbers.¹ A double- α plot has apparently linear portions (actually asymptotic) at low and high carbon numbers and a curved portion connecting the two asymptotes. Satterfield developed a nonlinear regression method, which gives α_1 and α_2 . He says values of α calculated from linear regression analysis of the asymptotic parts of the curve are within 5 to 10% of the nonlinear regression α 's. Linear regression analysis of the data in Figure 14 provided a value for α of 0.69.

The weight of products collected in the various traps is summarized in Table 2 and Figure 15. Not much material was in the hot-box trap for the first several periods, largely because the initial wax products were allowed to remain in the autoclave so that the autoclave liquid level could build to the target level. Figure 15 contains a plot of autoclave liquid level vs. hours on-stream. The rate of wax production can be estimated by the weights collected in the hot box trap. Apparently, the wax production decreased slowly during the run, most likely because of the conversion loss.

CONCLUSIONS

A mixed oxalate of iron, copper, and potassium was prepared. Characterization work has begun, and eventually, a catalyst will be prepared from this material, which may also be used to make pure iron carbides.

An evaluation run was performed on an iron-based UCI catalyst, which was prepared as a prototype for the LaPorte run scheduled for the summer of 1992. This catalyst was designed to produce a low level of light ends, particularly C₁ and C₂ paraffins. UOP's test confirmed that the UCI catalyst produces low levels of C₁ and C₂ paraffins. For instance, at the end of the run, when the catalyst was converting 60% of the CO, the C₁ and C₂ paraffin selectivities were 4.2 and 1.0, respectively.

REFERENCE

1. T. J. Donnelly, I. C. Yates, and C. N. Satterfield, *Energy and Fuels*, 1988, 2, 734-739.

Figure 1

UCI CATALYST

PLT 700B RUN 44 $H_2:CO$ feed=0.7, 1100 rpm

100g Fe : 4.32 Cu : 8.63 K : 7.92 Si : 72.7g CAT. In 290 g C₃₀ oil

TEMP., °C

280

265

FEED, NL/H g Fe

2.0

2.4

PRESSURE, PSIG

153

290

FEED LOT #

←

A

→

B

←

B

→

CO
CONVERSION

Figure 2

UCI CATALYST

PLT 700B RUN 44 $H_2:CO$ feed=0.7, 1100 rpm

100g Fe : 4.32 Cu : 8.63 K : 7.92 Si ; 72.7g CAT. In 290 g C_{30} oil

Figure 3

UCI CATALYST

PLT 700B RUN 44 $H_2:CO$ feed=0.7, 1100 rpm

100g Fe : 4.32 Cu : 8.63 K : 7.92 Si ; 72.7g CAT. In 290 g C_{30} oil

Figure 4

UCI CATALYST

PLT 700B RUN 44 $H_2:CO$ feed=0.7, 1100 rpm

100g Fe : 4.32 Cu : 8.63 K : 7.92 Si ; 72.7g CAT. In 290 g C_{30} oil

TEMP., °C

280

265

FEED, NL/H g Fe

2.0

2.4

PRESSURE, PSIG

153

290

FEED LOT #

A

B

A

B

CO
CONVERSION

GC2 C1
SELECTIVITY

H_2/CO
OUTLET

$CO + H_2$
CONVERSION

Figure 5

UCI CATALYST

PLT 700B RUN 44 $H_2:CO$ feed=0.7, 1100 rpm

100g Fe : 4.32 Cu : 8.63 K : 7.92 Si : 72.7g CAT. In 290 g C_{30} oil

TEMP., °C

280

265

FEED, NL/H g Fe

2.0

2.4

PRESSURE, PSIG

153

290

FEED LOT #

←

A

↔

B

→

A

←

B

→

GC2 C2
PAR SELECTIVITY

GC2 C2
PAR SELECTIVITY

H_2/CO
OUTLET

$CO + H_2$
CONVERSION

HOURS ON STREAM

Figure 6

UCI CATALYST

PLT 700B RUN 44 H₂:CO feed=0.7, 1100 rpm

100g Fe : 4.32 Cu : 8.63 K : 7.92 Si : 72.7g CAT. In 290 g C₃₀ oil

Figure 7

UCI CATALYST

PLT 700B RUN 44 $H_2:CO$ feed=0.7, 1100 rpm

100g Fe : 4.32 Cu : 8.63 K : 7.92 Si : 72.7g CAT. in 290 g C_{30} oil

Figure 8

UCI CATALYST

PLT 700B RUN 44 $H_2:CO$ feed=0.7, 1100 rpm

100g Fe : 4.32 Cu : 8.63 K : 7.92 Si ; 72.7g CAT. In 290 g C_{30} oil

Figure 9

UCI CATALYST

PLT 700B RUN 44 H₂:CO feed=0.7, 1100 rpm

100g Fe : 4.32 Cu : 8.63 K : 7.92 Si : 72.7g CAT. In 290 g C₃₀ oil

TEMP., °C

280 ————— 265

FEED, NL/H g Fe

2.0 ————— 2.4

PRESSURE, PSIG

153 ————— 290

FEED LOT #

← A ————— B ————— A ————— B ————— →

CO + H₂
CONVERSION

GC1 C10
PAR SELECTIVITY

GC1 C9
PAR SELECTIVITY

GC1 C8
PAR SELECTIVITY

HOURS ON STREAM

Figure 10

UCI CATALYST

PLT 700B RUN 44 H₂:CO feed=0.7, 1100 rpm

100g Fe : 4.32 Cu : 8.63 K : 7.92 Si ; 72.7g CAT. In 290 g C₃₀ oil

TEMP., °C

280

265

FEED, NL/H g Fe

2.0

2.4

PRESSURE, PSIG

153

290

FEED LOT #

←

A

→

B

←

B

→

GC1 C5
GC1 C4
GC1 C3
GC1 C2
OLE SELECTIVITY OLE SELECTIVITY OLE SELECTIVITY OLE SELECTIVITY

Figure 11

UCI CATALYST

PLT 700B RUN 44 H₂:CO feed=0.7, 1100 rpm

100g Fe : 4.32 Cu : 8.63 K : 7.92 Si : 72.7g CAT. In 290 g C₃₀ oil

TEMP., °C

280

265

FEED, NL/H g Fe

2.0

2.4

PRESSURE, PSIG

153

290

FEED LOT #

A

B

B

GC1 C9
GC1 C8
GC1 C7
GC1 C6
OLE SELECTIVITY OLE SELECTIVITY OLE SELECTIVITY OLE SELECTIVITY

UCI CATALYST

100g Fe : 4.32 Cu : 8.63 K : 7.92 Si : 72.7g CAT. In 290 g C₃₀ oil

280

265

20

-24-

153

-290

— 12 —

— 2 —

GC1 C4

661 33

CC1 C2

GC1 C10

ROLE SELECTIVITY ALC SELECTIVITY ALC SELECTIVITY ALC SELECTIVITY

Figure 13

UCI CATALYST

PLT 700B RUN 44 H₂:CO feed=0.7, 1100 rpm

100g Fe : 4.32 Cu : 8.63 K : 7.92 Si : 72.7g CAT. In 290 g C₃₀ oil

TEMP., °C

280

265

FEED, NL/H g Fe

2.0

2.4

PRESSURE, PSIG

153

290

FEED LOT #

A

B

A

B

GC1 C8

GC1 C7

GC1 C6

GC1 C5

ALC SELECTIVITY ALC SELECTIVITY ALC SELECTIVITY ALC SELECTIVITY

Figure 14

SCHULZ-FLORY PLOT FROM ONLINE ANALYSES

RUN 44

265 DEG C

• ALL PRODUCTS

Figure 15

Weight of Liquid in Hot Trap Box Run 44 - UCI Catalyst

Figure 16

LIQUID LEVEL Vs. HOURS ON STREAM PLANT 700B RUN 44

APPENDIX A

Summary Report of Al Van Til on Oxalate Route to Fischer-Tropsch Catalysts

Date: 1 MAY 92
From: Alan E. van Til
To: George J. Antos

Subject: Fischer-Tropsch (10158-0069), #8

A vacuum TGA was run on the K,Cu,Fe oxalate made earlier. N2 BET data was also obtained on the same material after various pretreatments as listed in TABLE 1. A N2 BET for a Cu,Fe oxalate run under the same conditions is also listed there. The combined BET & TGA data is shown in Figure 1. There, we see an initial loss of surface moisture, then a sharp mass loss due to the two waters of hydration being abstracted at slightly above 100 °C. In contrast to many oxalates containing divalent ions such as Mg, iron oxalate decomposes at a lower temperature, less than 400 °C by two steps, and goes all the way to the metal in vacuum rather stopping at the oxide. The mass loss after water abstraction up to ca. 200 °C would fit with CO loss to make carbonate. However, I will immediately add that the the sure assignment would either come by adding a QPMS to look for CO and CO₂ during a TGA run or take a sample up to that stage and have an XRD analysis done. The last final mass loss may be a complex one whose simplistic assignment would be CO+CO₂ removal to form metal. The final mass losses for the surface area measurements samples are given in TABLE 1. That we have the metal is confirmed by the pyrophoric behaviour of several samples when contacted with air at the end of the run. Because we have an oxalate that decomposes by two steps opens the possibility of first vacuum calcining it up to 200 °C to remove H₂O and partially decompose the oxalate to open its pore structure and then finish the job in air to obtain a high surface oxide. That this approach is feasible is supported by two items. First, the mass loss data listed in TABLE 1 for the 175 °C treated sample and, second, the mid point mass loss temperatures of the transitions in FIGURE 1 are ca. 175 °C apart. From the work done so far using only vacuum calcination, we can obtain Fe metal either doped or surface covered with Cu & K having a surface area of nominally 60-75 m²/g when the oxalate is heated at 300-325 °C for 40-64 hours. By being able to calcine the material in air for the second stage, we would avoid the problem of having to CAREFULLY adding low O₂ containing N₂ at the end of the vacuum calcination to passivate the Fe metal surface.

Next, I plan to try an experiment in the Mettler TGA in which a sample is initially vacuum calcined to ca. 200 °C, then calcined to ca. 400 °C in air and then checked as to its BET surface area. Also, a somewhat larger sample will be calcined in a separate vacuum system for XRD as part of scaling up the preparation of a sufficient material for a pilot plant run.

Arrangements are in progress to obtain clearance from the Safety Department for using CO in carbiding experiments scheduled in the Mettler TA-2 Thermal analyzer system of various F-T catalysts. A CO monitor must be bought and installed in B-2-R-156 before clearance can be granted. (AEvT)

Table 1
Surface Area of Vacuum Calcined Fe Oxalates

S #	[K], [Cu], [Fe]	Temp, °C	Time, hr	% Mass Loss	S.A. (m ² /g)	P.V., cc/g	m PD, A
6753-27	K=0	300-325	40	68.18	61.4	0.028	8.7
6753-33	0.75, 4.16, 100	25		12.4	1.5		
-33	SAME	175	3	30.1	44	0.019	7.7
-33	SAME	300	20	70.09	63.5	0.028	7.9
-33	same	300	64	71.28	73.9	0.037	10.9
-33	same	350	5	67.38	37.2	0.016	7.4
-33	same	350	16	68.30	42.6	0.020	9.5

VACUUM TGA OF K,Cu,Fe OXALATE

P= 0.2 torr, S#E753-33, i.s.w.=108.62 mg

APPENDIX B

Summary of Plant 700B, Run 44

Table 1

**Analysis of Feeds
Run 44 (UCI Catalyst)**

Component	Feed A	Feed B
CO, mole %	56	56
H ₂ , mole %	37	37
A, mole %	6	6
N ₂ , mole %	0.17	0.32
Total S, wppm	<1	<1
O ₂ , WPPM 2	<50	<50

**UOP
3/19-20/1992**

Table 2

FISCHER-TROPSCH IRON CATALYST PROJECT
 PLANI 700B TRAP PRODUCT LOG
 Run 44 U.C.I catalyst

RUN	HOS	TRAP	PRODUCT	RECORDED WEIGHT	COMMENTS	--- DATE OF --- DISTRBTN RESULTS
44	12	Hot	Wax w/drwl	35 g		
		Ice	Hydrocrbn	4 g		
		Ice	Aqueous	11 g		
		Cryo	Both	5+4 g		
	24	Hot	Wax w/drwl	10 g		
		Ice	Hydrocrbn	7 g		
		Ice	Aqueous	5 g		
		Cryo	Both	5+0 g		
	48	Hot	Wax w/drwl	23 g		
		Ice	Hydrocrbn	18 g		
		Ice	Aqueous	14 g		
		Cryo	Both	7 g		
4	72	Hot	Wax w/drwl	179 g		
		Ice	Hydrocrbn	28 g		
		Ice	Aqueous	15 g		
		Cryo	Both	24 g		
	96	Hot	Wax w/drwl	147 g		
		Ice	Hydrocrbn	28 g		
		Ice	Aqueous	16 g		
		Cryo	Both	19 g		
	120	Hot	Wax w/drwl	148 g		
		Ice	Hydrocrbn	28 g		
		Ice	Aqueous	19 g		
		Cryo	Both	23+11 g		
6	144	Hot	Wax w/drwl	172 g		
		Ice	Hydrocrbn	20 g		
		Ice	Aqueous	17 g		
		Cryo	Both	14+3 g		
	168	Hot	Wax w/drwl	159 g		
		Ice	Hydrocrbn	27 g		
		Ice	Aqueous	14 g		
		Cryo	Both	20 g		
	192	Hot	Wax w/drwl	168 g		
		Ice	Hydrocrbn	26 g		
		Ice	Aqueous	16 g		
		Cryo	Both	20 g		
10	216	Hot	Wax w/drwl	189 g		
		Ice	Hydrocrbn	30 g		
		Ice	Aqueous	18 g		
		Cryo	Both	25+8 g		
	240	Hot	Wax w/drwl	131 g		
		Ice	Hydrocrbn	24 g		
		Ice	Aqueous	18 g		
		Cryo	Both	14+3 g		
	264	Hot	Wax w/drwl	114 g		
		Ice	Hydrocrbn	35 g		
		Ice	Aqueous	16 g		
		Cryo	Both	2+1 g		

Table 2 (Cont)

FISCHER-TROPSCH IRON CATALYST PROJECT
 PLANT 700B TRAP PRODUCT LOG
 Run 44 U.C.I catalyst

RUN	HOS	TRAP	PRODUCT	RECORDED WEIGHT	COMMENTS	--- DATE OF --- DISTRBTN RESULTS
14	288	Hot	Wax w/drwl	130 g		
		Ice	Hydrocrbn	28 g		
		Ice	Aqueous	14 g		
		Cryo	Both	22 g		
	312	Hot	Wax w/drwl	164 g		
		Ice	Hydrocrbn	32 g		
		Ice	Aqueous	14 g		
		Cryo	Both	22 g		
	336	Hot	Wax w/drwl	93 g		
		Ice	Hydrocrbn	18 g		
		Ice	Aqueous	28 g		
		Cryo	Both	17 g		
	360	Hot	Wax w/drwl	95 g		
		Ice	Hydrocrbn	16 g		
		Ice	Aqueous	33 g		
		Cryo	Both	18 g		
18	384	Hot	Wax w/drwl	163 g		
		Ice	Hydrocrbn	29 g		
		Ice	Aqueous	7 g		
		Cryo	Both	13 g		
	408	Hot	Wax w/drwl	128 g		
		Ice	Hydrocrbn	37 g		
		Ice	Aqueous	15 g		
		Cryo	Both	32 g		
	432	Hot	Wax w/drwl	90 g		
		Ice	Hydrocrbn	35 g		
		Ice	Aqueous	13 g		
		Cryo	Both	27 g		
	456	Hot	Wax w/drwl	169 g		
		Ice	Hydrocrbn	34 g		
		Ice	Aqueous	15 g		
		Cryo	Both	19+5 g		
	480	Hot	Wax w/drwl	97 g		
		Ice	Hydrocrbn	34 g		
		Ice	Aqueous	13 g		
		Cryo	Both	8+2 g		
	504	Hot	Wax w/drwl	150 g		
		Ice	Hydrocrbn	37 g		
		Ice	Aqueous	13 g		
		Cryo	Both	17 g		
	EOR	Hot	Wax			
	EOR	Hot	Wax			

END

DATE
FILMED
3/19/93