SRI International

DOE/PC/91039--T5

JAN 20

DE93 011449

Quarterly Report No. 5 - 2 December 1992

HIGHLY DISPERSED CATALYSTS FOR COAL LIQUEFACTION

By: Albert S. Hirschon and Robert B. Wilson

SRI Project 2760

Period Covering August 23, 1992 through November 22, 1992

Prepared for:

United States Department of Energy
Pittsburgh Energy Technology Center
P.O. Box 10940
Pittsburgh, PA 15236

Contract No. DE-AC22-91PC91039

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

MASTER

333 Ravenswood Avenue • Menlo Park, CA 94025-3493 • (415) 326-6200 • FAX: (415) 326-5512 • Telex: 334486

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

SUMMARY

The objectives of this project are to study the effect of pretreatment methods on the two-stage liquefaction process. In particular, the effects of dispersed catalysts and carbon monoxide atmospheres on a coal liquefaction process. The project is divided into three technical tasks. Task 1 and 2 deal with the analyses and liquefaction experiments, respectively, whereas Task 3 deals with the economic impact of utilizing the pretreatment methods. This quarter we concentrated on Tasks 1 and 2, which are summarized below.

Task 1. Analytic Support

In this support task, the fractionated products from the coal liquefaction experiments conducted in Task 2 were analyzed for C, H, and N content. A very low H/C ratio for these products was found, and is most likely due to the low H/C ratio of the Black Thunder recycle solvent used in these liquefaction experiments. Also, during this quarter an on-line gas chromatograph was integrated into the autoclave system.

We also conducted some experiments to determine the ease of activation of potential coal liquefaction catalysts. For these experiments the technique of NO chemisorption was used to determine the active catalytic MoS₂ sites on coals impregnated with organometallic Mo precursors. We found that these organometallic Mo clusters easily activated to MoS₂ sites.

Task 2. Laboratory Scale Operation

During this quarter we continued our base-line screening experiments in the 300 mL autoclaves. Last quarter iron oxide and iron carbonyl catalysts were compared using an atmosphere of hydrogen with 3% H₂S. This quarter we included a comparison of liquefaction with iron oxide where we added an additional atmosphere of 20% carbon monoxide and found that this addition increased the conversion yields to soluble products. All of the carbon monoxide was accounted for as either unconverted carbon monoxide or as carbon dioxide. No evidence of conversion of the carbon monoxide to methane or Fischer-Tropsch type reactions were observed.

INTRODUCTION

Integrated processes to liquefy coal have evolved to the current two-stage close coupled catalytic configurations now being used at Wilsonville.¹⁻⁴ Recent estimates (1990) indicate that two-stage conversion of coal to liquids has a product cost in the area of \$38 per barrel and the improved quality of the liquids makes them equivalent to oil costing \$33 per barrel. Several areas in the conversion technology have been identified that, if improved, should make coal converted to oil more cost competitive with petroleum products. These areas include pretreatment and cleaning methods, choice of feedstock, novel catalysts, and processes to improve hydrocarbon recovery. The objective of this project is to address possible methods of improving the efficiency of these and other steps in the integrated process so that the overall conversion will show increased cost effectiveness. This work will concentrate on individual steps and technoeconomic evaluations to provide information on their relative effectiveness toward the overall goal of \$25 per barrel.

So far, most work at Wilsonville has involved bituminous coals, which are much easier to convert than lower-rank coals such as Wyodak and lignites.⁵ The lower-rank coals are more abundant and cheaper, and conversions lead to a higher quality product with less heteroatom content.⁶ However, the yield of liquid products is low. The low conversion of these coals has been attributed to their high oxygen content, and the carboxyl groups are thought to cause retrograde reactions by free radical processes.^{7,8} Additionally, phenolics often are associated with retrograde reactions leading to polymeric furans.^{9,10} Developing a process for utilizing these coals in high conversions would greatly improve the economics of coal conversion. Several approaches, including highly dispersed catalysts and coal pretreatment techniques, have been suggested to overcome these detrimental reactions. In recent work we have studied both of these approaches to enhance the convertibility of coal and minimize the retrogressive reactions.

This project is designed to evaluate the feasibility of using low-rank coals such as Wyodak and lignite in a two-stage liquefaction pilot demonstration unit (PDU). The primary objectives are to (1) synthesize and impregnate coal with high activity, highly dispersed catalysts (dispersed on the molecular scale); (2) develop an understanding of these catalysts in terms of their reactivities toward hydrogenation and hydrogenolysis, especially in terms of removing phenolics and carboxylates, which are thought to cause

most retrogressive reactions; (3) monitor the activities and physical properties of these catalysts during coal liquefaction processes and compare them with those of other types of catalysts; and (4) evaluate process cost improvements that might be realized through the use of low-rank coals, dispersed catalysts, and CO/H₂ for coal liquefaction in a two-stage close coupled configuration.

TASK 1: ANALYTICAL SUPPORT

ANALYSES FROM COAL CONVERSIONS

The objectives of this task are to provide analytic support for the laboratory conversion studies conducted in Task 2. During this quarter the fractionated products for the coal liquefaction experiments were analyzed for C, H, and N content. In addition, a gas chromatograph (GC) was put on-line with the autoclaves for analysis of the light gases formed during the coal conversions. We also investigated the technique of chemisorption of catalysts to help determine the degree of activation of catalysts impregnated onto coal.

Table 1 lists the analyses of fractionated products derived from conversions of Black Thunder Coal and the corresponding recycle solvent. The products analyzed in this table are THF-insoluble, THF-soluble/Toluene-insoluble, referred to as preasphaltenes and Toluene-soluble/Hexane-insoluble, referred to as asphaltenes. The hexane-soluble fractions, or oils, will be analyzed at a later date using our apparatus for volatile samples.

As discussed under Task 2, these first stage screening liquefaction experiments were conducted at low hydrogen pressures (850 psig cold, which translates to about 2000 psig at coal conversion conditions). In past work, using good solvents such as tetralin and good catalysts such as those based on molybdenum metals, we were able to achieve high conversions. But with a poor solvent such as Black Thunder recycle solvent with a low H/C ratio of 1.0 and catalysts such as iron oxide, there is a very poor hydrogen utilization and therefore the yields are quite low and the product slate has a low H/C ratio as observed in Table 1. Nevertheless, a good catalyst or process system will be more easily observed in this system.

Table 2 lists the light gas slate from these runs as determined by GC analysis. There was some difficulty in getting a good hydrogen analysis, but by difference we estimate it to be in the range of 120 to 150 mmoles of hydrogen, compared to 530 mmoles in the initial charge. As seen in this table, the majority of the gas formed from conversion consists of methane, with small amounts of carbon dioxide, ethane and C3 gases. In the reaction with additional carbon monoxide, (120 mmoles), the equivalent amount of carbon dioxide was formed, with no evidence of hydrogenation of the carbon monoxide to methane, or any types of Fischer-Tropsch type chemistry to form higher hydrocarbons.

Table 1. Analyses of Conversion Products^a

Material	% C	% H	H/C
Black Thunder	63.56	4.96	0.930
Recycle	88.08	7.09	1.055
No Catalyst			
THF-Insol	66.71	3.03	0.542
Preasphaltene	90.60	4.44	0.583
Asphaltene	85.78	6.23	0.866
Fe ₂ O ₃			
THF-Insol	72.97	2.89	0.471
Preasphaltene	71.49	4.73	0.788
Asphaltene	81.31	6.56	0.961
Fe(CO) ₅			
THF-Insol	64.56	2.70	0.499
Preasphaltene	89.32	4.20	0.560
Asphaltene	83.46	6.00	0.856
Fe ₂ O ₃ /20%CO ^b			
THF-Insol	51.50	2.16	0.501
Preasphaltene	90.75	4.72	0.619
Asphaltene	85.89	6.40	0.887

^aReaction conducted in a 300-mL autoclave with 20g Black Thunder Wyodak coal, 1.4 g iron metal in catalyst, 50 g Recycle solvent and 850 psig H₂ (3% H₂S) for 60 min at 425°C.

^b1000 psig total pressure (18% CO, 3% H₂S)

Table 2. Gas Analyses^a

Catalyst	CO₂	CO	CH₄	C₂H₆	C₃
None	37	—	148	48	0.5
Fe ₂ O ₃	20	—	148	41	0.5
Fe ₂ O ₃ /20% CO	116	44	130	4	0.6

^aGases reported in mmoles.

CATALYST PRECURSOR CHARACTERIZATIONS

A common question when using precursors to dispersed catalysts is at what conditions are the precursors converted into an active catalyst. In order to help answer this question we conducted some experiments using a probe molecule to determine the density of active catalytic sites. For hydrotreating catalysts these sites are thought to be defects in the crystalline lattice. In particular, in MoS_2 based catalysts. Several workers have found that carbon monoxide and nitric oxide absorption experiments are useful to determine the density of active sites, with nitric oxide being used primarily to study sulfided hydrotreating catalysts.¹¹ We have successfully used nitric oxide as a probe to correlate with our ruthenium promoted hydrotreating catalysts in past work.¹²

For these experiments we investigated an organometallic catalyst precursor used in our past work derived from $(\text{C}_5\text{H}_5)_2\text{Mo}_2\text{S}_4$, referred to as $[\text{Mo}(\text{OM})]$. Note that this is a soluble sulfided molybdenum precursor which has the same stoichiometry of the active catalyst MoS_2 . In our past work we compared dispersed molybdenum catalysts made from this organometallic precursors $[\text{Mo}(\text{OM})]$ with conventional dispersed catalysts such as from ammonium molybdate salts $[\text{MoS}_4^{2-}]$, and showed that the $\text{Mo}(\text{OM})$ gave much higher yields of liquid products.¹³ For this work we investigated the ease of activation of the $\text{Mo}(\text{OM})$ catalyst impregnated on a Wyodak coal using NO as probe for active sites, where it is assumed that the number of active catalytic sites is proportional to the amount of NO that can be adsorbed on the catalyst, or in this case, the coal impregnated with the catalyst precursor. The experiment was conducted as follows: First the impregnated coal was treated with a flowing mixture of 1% nitric oxide in helium at 100°C and the desorption curve as analyzed by mass spectroscopy. Then the impregnated coal was treated with hydrogen to activate the catalyst if necessary, and another adsorption/desorption sequence was initiated. The process was repeated at 200, 300, and 400°C to determine at what point the catalyst became activated for the absorption of NO. As seen in Figure 1, the results suggest that the $\text{Mo}(\text{OM})$ catalyst precursor begins to activate to catalytically active MoS_2 at temperatures above 200°C , and is mostly converted at 400°C . It is difficult to compare with the MoS_4 since it first decomposes to MoS_3 , which also absorbs NO. However, its transformation to MoS_2 is known to take place only at much more strenuous conditions.¹⁴ We hope to use such a method to evaluate our iron based catalysts in future work.

Figure 1a. NO Desorption of Mo(OM) After 200°C Activation.

Figure 1b. NO Desorption of Mo(OM) After 300°C Activation.

Figure 1c. NO Desorption of Mo9OM) After 400°C Activation.

TASK 2: LABORATORY SCALE OPERATIONS

The objectives of the first phase of this task are to evaluate the effects of dispersed catalysts and carbon monoxide atmospheres in the first stage of a 2-stage liquefaction process. We are continuing our work to evaluate the base-line first-stage reaction conditions. The experiments are being run at 425°C for 1 hour in a 300 mL autoclave with a slow heat-up period (approximately 45 minutes) in order to incorporate any possible preconversion benefits at lower temperatures. The feedstock consisted of 2.5 parts by weight of recycle solvent from Wilsonville run #263 to 1 part Black Thunder coal. Last quarter we compared the conventional catalysts Fe_2O_3 (received from Wilsonville) and iron carbonyl. The reaction atmosphere was 850 psia of hydrogen containing 3% hydrogen sulfide. We found that the iron oxide catalyzed reaction appeared to have an exotherm around 350°C, making the reactor momentarily overshoot the final temperature by at least 25°C. The combination of the overshoot and the inability of the catalyst to efficiently utilize hydrogen most likely attributed to the low conversions. Furthermore as seen in Table 3, when we ran a conversion with no catalyst the yields were actually higher than those with iron oxide. Also of interest, is when we used iron oxide as a catalyst and added an additional 20% carbon monoxide, so the total reaction pressure was 1000 psia, much better yields of soluble products were achieved. As shown in Table 2 in Task 1, the addition of the carbon monoxide was essentially converted to carbon dioxide and not to methane or any higher hydrocarbons. Thus even though the coal was dried prior to use and no additional water was added, the carbon monoxide can be effectively utilized in coal conversion. The net atmosphere used for this experiment was 1000 psia compared to 850 psi for the hydrogen conversion, and thus we plan to compare this reaction using 1000 psia hydrogen pressure next quarter.

Table 3. Wt% Yields of Fractionated Products^a

Catalyst	THF Insol	Preasphaltene	Asphaltene	Oils
No Catalyst	33.4	7.3	23.5	12.8
Fe ₂ O ₃	59.9	0.2	2.4	4.0
Fe(CO) ₅	35.1	5.9	27.1	12.9
Fe ₂ O ₃ /CO ^b	26.0	9.3	25.5	16.2

^aReaction conducted in a 300-mL autoclave with 20g Black Thunder Wyodak coal, 1.4 g iron metal in catalyst, 50 g Recycle solvent and 850 psig H₂ (3% H₂S) for 60 min at 425°C.

^b1000 psig total pressure (18% CO, 3%H₂S).

REFERENCES

1. S. N. Rao, H. D. Schindler, and G. V. McGurl, ACS Fuel Preprints, (1988) **33**(3), 145-156.
2. J. M. Lee, O. L. Davies, T. E. Pinkston, and J. R. Gough, ACS Fuel Reprints, (1988) **33**(3), 157-171.
3. D. Gray and G. Tomlinson, ACS Fuel Preprints (1988) **33**(3), 172-179.
4. S. V. Gollakota, J. M. Lee, O. L. Davies, and T. E. Pinkston, DOE Direct Liquefaction Contractors' Review Meeting, Pittsburgh, Pennsylvania, October 1988.
5. R. Neavel, Phil. Trans. R. Soc. Lond. A, (1981) **300**, 141.
6. E. C. Moroni, ACS Fuel Preprints, (1986) **31**(4), 294-299.
7. E. M. Suuberg, D. Lee, and J. W. Larsen, Fuel, (1985) **64**, 1668.
8. G. V. Deshpande, P. Solomon and M. A. Serio, ACS Fuel Preprints, (1988) **33**(2), 310.
9. E. C. Moroni, ACS Fuel Preprints, (1988) **33**(1), 384-386.
10. C.-L. Li, Z.-r Xu, and B. Gates, Ind. Eng. Chem. Prod. Res. Dev., (1985) **24**, 92-97.
11. N-Y Topsoe and H. Topsoe, J. Cat. (1982) **75**, 354-374.
12. A. Hirschon, 1992, unpublished data.
13. A. S. Hirschon and R. B. Wilson Jr., Fuel, (1992) **71**, 1025-1031.
14. D. Huntley, T. Parham, R. Merrill, and M. Sienko, Inorg. Chem. (1983), **22**, 4144.

END

DATE
FILMED

5/03/93