**STANDARD AND MODIFIED ELECTRODE ENGINEERING-SCALE
IN SITU VITRIFICATION TESTS**

L. E. Thompson
R. G. Winkelman^(a)
J. S. Tixier

September 1992

Prepared for
the U.S. Department of Energy
under Contract DE-AC06-76RLO 1830

Pacific Northwest Laboratory
Richland, Washington 99352

(a) Geosafe Corporation, Richland, Washington

MASTER

EB

SUMMARY

This report describes engineering-scale in situ vitrification (ISV) electrode tests conducted by Pacific Northwest Laboratory (PNL) for the U.S. Department of Energy (DOE).^(a) The purpose of these tests was to establish baseline data to serve as a foundation on which to improve the design of standard graphite rod electrodes, which are currently used in all applications. Changes in electrode design are proposed as one method to increase ISV melt depths that typically reach about 5 m. Melt depths of 10 m are needed to remediate some contaminated soil sites within the DOE complex.

To establish baseline data, we performed a thermal distribution analysis and tested three electrode designs: 1) the standard graphite rod electrodes, 2) a modified design referred to as the composite graphite/molybdenum electrode, and 3) a second modified design, the dilated-tip graphite electrode. In total we performed six tests, two of each design.

Within the scope of these tests, there were four specific objectives. Our first objective was to determine the influence of electrode design on monolith mass and shape. Our second objective was to determine the correlation between the actual test results and the results of the numerical heat distribution analysis using the TEMPEST code. Our third objective was to qualitatively evaluate the melt resistance and the electrode contact resistance that resulted from the three electrode designs. Finally, our fourth objective was to verify the reproducibility of the engineering-scale test results.

The following observations are based on the test results and on the heat distribution analysis.

1. With regard to monolith mass and shape, there was significant variability between the three pairs of monoliths. Based on the differences in the monoliths and operational data collected during the tests, we believe the information learned from these tests can be exploited to develop improved electrode designs.

(a) This work was funded by the Office of Technology Development through the In Situ Vitrification Integrated Program.

2. The engineering-scale test results were difficult to correlate with the computer simulations since the heat flux meters malfunctioned, and there were only two type C thermocouples used in each test.
3. The measured single-phase resistance of the various melts exhibited noticeable degrees of variability between electrode designs.
4. The variability between pairs of monoliths was negligible, except for the dilated-tip electrode tests. The variability in this case was attributable to an interruption in power during one of the two tests.

Additional research planned for FY 1993 will build upon the information gained from this effort and will include, in part, development and testing of an engineering-scale hot-tip electrode. The hot-tip electrode concept involves an electrode that delivers the electrical power only at the bottom of the melt; the upper regions of the electrode are electrically insulated to prevent power dissipation through the upper regions of the melt. The hot-tip electrode concept has been identified as a means to achieve greater melt depths. Although the hot-tip electrode was not tested at the engineering scale, the numerical modeling conducted using the TEMPEST code included the hot-tip design. Modeling of three electrode designs revealed that the greatest degree of heating at the melt bottom was achieved with a hot-tip electrode. TEMPEST results revealed that heating at the melt bottom increased by greater than a factor of two (relative to standard graphite electrodes) when using hot-tip electrodes in an engineering-scale test.

ACKNOWLEDGMENTS

The authors wish to thank Chuck Bigelow, Randy Garcia, and Roger Fichter at Pacific Northwest Laboratory for their dedication and knowledge in completing these tests in an accurate and timely manner. The authors would also like to thank Patrick Lowery for his assistance in completing the modeling simulations. The authors would also like to thank Geosafe Corporation for assistance and for the use of its facilities.

CONTENTS

SUMMARY	iii
ACKNOWLEDGMENTS	v
1.0 INTRODUCTION	1.1
1.1 BACKGROUND	1.1
1.1.1 ISV Process Description	1.1
1.1.2 ISV Equipment Description	1.3
1.2 TEST OBJECTIVES	1.4
2.0 SUMMARY OF OBSERVATIONS	2.1
3.0 ELECTRODE DESIGN BASIS	3.1
3.1 ELECTRODE DESIGN CONSIDERATIONS	3.1
3.2 COMPUTER SIMULATION	3.2
4.0 TEST DESCRIPTION	4.1
4.1 TEST EQUIPMENT	4.1
4.2 TEST OPERATIONS	4.4
4.2.1 Standard Graphite Rod Electrode Tests	4.5
4.2.2 Graphite/Molybdenum Composite Electrode Tests	4.6
4.2.3 Graphite Dilated-Tip Electrode Tests	4.6
4.3 RESISTIVITY MEASUREMENTS	4.6
4.4 POSTTEST ACTIVITIES	4.7
5.0 TEST RESULTS	5.1
5.1 STANDARD ELECTRODE TEST RESULTS AND DISCUSSION	5.1
5.2 COMPOSITE ELECTRODE TEST RESULTS AND DISCUSSION	5.3
5.3 DILATED-TIP ELECTRODE TEST RESULTS AND DISCUSSION	5.5
5.4 GENERAL OBSERVATIONS	5.7

5.5	HEAT FLUX	5.8
5.6	SINGLE-PHASE RESISTANCE	5.8
6.0	REFERENCES	6.1

FIGURES

1.1	ISV Operating Sequence	1.2
3.1	Heat Flux Distribution for Three Electrode Designs Based on TEMPEST Code Modeling	3.5
4.1	Side View of Engineering-Scale Test Configuration	4.2
4.2	Top View of Engineering-Scale Test Configuration	4.3
4.3	Diagram of the Composite and Dilated-Tip Electrode Designs	4.4
5.1	Average Electrode Insertion Depths vs. Time for the Six Tests	5.2
5.2	Type C Thermocouple Data from Baseline Test 1 and 2	5.2
5.3	Type C Thermocouple Data from Composite Electrode Test 1 and 2	5.5
5.4	Type C Thermocouple Data from Dilated-Tip Electrode Test 1 and 2	5.7
5.5	Single-Phase Resistance from the Six Tests	5.9

TABLES

3.1	Computer Simulation Cases	3.3
5.1	Physical Dimensions of the Six Monoliths Resulting from the Engineering-Scale Tests	5.4

1.0 INTRODUCTION

1.1 BACKGROUND

In situ vitrification (ISV) is a waste remediation technology currently under development by the U.S. Department of Energy (DOE) for application to radioactive and mixed-waste contaminated soils. The process was invented in 1980 by researchers at DOE's Pacific Northwest Laboratory (PNL)^(a) (Brouns, Buelt, and Bonner 1983). Although the process has been developed primarily at PNL, collaborative development efforts have been undertaken between PNL, Oak Ridge National Laboratory, and the Idaho National Engineering Laboratory in recent years. Geosafe Corporation, the only commercial supplier for ISV remedial services, has been involved in the DOE development program and is actively providing technical services to private industry, including treatability tests in advance of full-scale remedial operations.

The DOE is currently emphasizing development of ISV technology for applications to contaminated soils. Deployment to remediate soil contamination is contingent on the resolution of a few remaining technical issues, one being the problem of inadequate melt depth. Many of the DOE sites require remediation of contaminated soil to a depth of 10 m, but current ISV processing has been demonstrated to a 5-m depth. The work described in this report is an important step toward increasing melt depth and increasing the number of sites that could be treated by ISV.

1.1.1 ISV Process Description

Figure 1.1 illustrates the ISV process. An array of four graphite electrodes is inserted into the ground to a depth typically equal to one to two electrode diameters. Because soil is not electrically conductive when its moisture has been driven off, a conductive mixture of flaked graphite and glass frit is placed among the electrodes to serve as a starter path. An electrical potential is applied to the electrodes to establish an electrical

(a) Pacific Northwest Laboratory is operated by Battelle Memorial Institute for the U.S. Department of Energy under Contract DE-AC06-76RLO 1830.

FIGURE 1.1. ISV Operating Sequence

current in the starter path. The flow of current heats the starter path and surrounding soil to well above the initial soil-melting temperatures of 1100° to 1400°C. The graphite starter path is eventually consumed by oxidation, and the current is transferred to the molten soil, which is processed at temperatures between 1450° and 2000°C.

An electrode feed system allows the electrodes to be inserted downward as the melt progresses. Although the electrodes generally rest on the bottom of the melt, the electrodes can be retracted. For example, retraction of electrodes a few centimeters from the bottom of the melt is often necessary during operations involving buried metal, since molten metal forms pools at melt bottom and can short-circuit the electrodes.

As the melt grows in size, nonvolatile radionuclides and inorganics are incorporated into the molten soil, and portions of semi-volatile and volatile inorganic species are also incorporated into the molten soil. The high processing temperature destroys organic nonvolatile components by pyrolysis. The pyrolyzed byproducts migrate to the surface of the vitrified zone, where they combust in the presence of air. An off-gas confinement hood placed over the area being vitrified directs the gaseous effluents to an off-gas treatment

system. Those portions of volatile and semi-volatile inorganic species that are not incorporated into the melt are also released into the off gas and removed by the off-gas treatment system. After power is terminated and the melt cools, the solidified glass and crystalline monolith is highly resistant to leaching and considered stable for geologic periods. For remediation of expansive contaminated areas, adjacent ISV process settings can be employed to form a single contiguous monolith.

1.1.2 ISV Equipment Description

Three scales of processing equipment have been developed: engineering, pilot, and large scale. The DOE's engineering-scale ISV system, operated by PNL, includes the following: a 1.8-m melt containment vessel suitable for producing large glass blocks weighing over 1000 kg, a variety of electrical transformers to support 2-, 3-, 4-, or 6-electrode configurations, at various power levels, an electrode feed system, and a complex off-gas treatment system with sufficient flexibility to test a variety of prototypical off-gas treatment components. Engineering-scale equipment is used only in the laboratory and operates at power levels up to 50 kW. The equipment was designed with significant flexibility to allow testing of alternative electrical and process equipment configurations and to permit development of new operating techniques. In addition, the system is rated to withstand overpressures of several psig to support testing of energetic materials and sealed containers. Essentially all developmental testing is conducted in the laboratory at engineering-scale.

The engineering-scale system used to conduct the six tests described in this report belongs to Geosafe Corporation. The Geosafe system has capabilities similar to the system operated by PNL, except that the Geosafe system uses a smaller melt containment system (110-gal test vessel) and has a single 25 kW Scott connected power supply.

The DOE pilot-scale equipment, also operated by PNL, consists of a complete processing system in a single semi-trailer including a 500 kW transformer, an off-gas treatment system, an electrode feed system, and process controls. A separate off-gas containment hood is used to cover the treated area. The pilot-scale system can produce blocks weighing up to 50 tons and

achieve melt depths of 2 to 3 m. At approximately 1/7 the power of the large-scale system, the pilot-scale system is suited to acquire near-full scale performance data in the field.

The DOE large-scale system, again operated by PNL, is considered full scale and is mounted on three semi-trailers. This system comprises a 3.75 MW transformer, a double-contained off-gas treatment system, an off-gas containment hood, an electrode feed system, and a process control system. The large-scale system was designed to include redundant safety systems for remediation of radioactive waste. This system can produce blocks weighing from 700 to 900 tons and has demonstrated maximum melt depths of 5.2 m (Buel, Timmerman, and Westsik 1989).

1.2 TEST OBJECTIVES

This report describes engineering-scale ISV electrode tests conducted by PNL for DOE. Our purpose in performing these tests was to collect data to establish a baseline foundation on which to improve the design of standard^(a) graphite rod electrodes, which are currently used in all applications. Changes in electrode design are proposed as one method to increase ISV melt depths that typically reach about 5 m. For ISV to achieve its full application potential within the DOE complex, the technology must be able to melt to depths of at least 10 m.

To establish baseline data, we performed a thermal distribution analysis using the TEMPEST code and tested three electrode designs: 1) the standard graphite rod electrodes, 2) a modified design referred to as the composite graphite/molybdenum electrode, and 3) a second modified design, the dilated-tip graphite electrode. In total we performed six tests, two of each design.

There were four specific objectives for this test. Our first objective was to determine the influence of electrode design on monolith mass and shape. By evaluating the resulting monolith, especially mass and melt depth, effectiveness of the various electrode designs could be determined. Our second

(a) The figures included in this report use the term "baseline" to describe the standard graphite electrode test results.

objective was to determine to what degree the engineering-scale results correlated with the computer modeling results. The computer modeling consisted of thermal distribution analyses of the tops, sides, and bottoms of melts produced using dilated-tip, hot-tip, and standard graphite electrodes. The composite electrode design was not simulated because the contact resistance value was unknown for the graphite/molybdenum combination. The analyses incorporated these particular electrode designs to determine the theoretical maximum amount of heat flux through the melt bottom. Although a quantitative comparison of experimental and modeling results is impossible due to insufficient test data, our model suggests depth enhancement is achievable through modified electrode concepts.

Our third objective was to qualitatively evaluate the melt resistance and the electrode contact resistance that resulted from the three electrode designs. Since molten soil does not wet graphite electrodes (in the same way as metallic electrodes), an increase in electrical resistance at the surface of the graphite electrodes is observed (Stanek 1977). Therefore, the allowable ampacity of graphite electrodes is much lower than for metal electrodes. This contact resistance results in significant heating at the surface of the electrodes. Improved electrode designs may benefit from selective exploitation of this contact resistance phenomenon.

Our fourth objective was to verify the reproducibility of the engineering-scale test results. Variability between monoliths produced under identical operating conditions has not been previously evaluated within the ISV development program. Quantification of the degree of variability between monoliths produced using identical electrodes under identical operating conditions is a necessary precursor to evaluating the variability in monoliths produced using different electrode designs under identical operating conditions.

2.0 SUMMARY OF OBSERVATIONS

The six ISV engineering-scale tests were completed successfully. All three electrode designs, including the two modified designs, appeared to function properly. The following observations are based on our test results.

1. With regard to monolith mass and shape, as well as melt rate, there was significant variability between the three pairs of monoliths.

The degrees of variability in monoliths and operational data were sufficient to provide valuable information. For example, the monolith mass of the second dilated-tip test was 170.1 kg: 11.8% smaller in mass and about 9% less in melt depth compared to the monoliths produced by the standard graphite electrodes (each 192.8 kg). The monolith mass (each 194 kg) produced by the composite electrodes was similar to the results of the standard electrodes.

The operational data showed that melt rates, as determined by the electrode insertion rates, were very similar for the standard graphite and composite electrode tests. However, the initial melt rates associated with the dilated-tip electrodes were approximately 37% less than the initial melt rates established for the other four tests. (Detailed discussion in subsection 5.3.) By evaluating the variations between monoliths and considering the test performance data such as melt rate and electrical resistance, we believe we can develop enhanced electrode designs.

2. The engineering-scale test results were difficult to correlate with computer simulations since the heat flux meters malfunctioned.

The experimental test results of the standard graphite electrodes and the dilated-tip electrodes did not correlate to the simulation data, since the heat flux meters failed. The actual mass and depth achieved with standard electrodes were slightly greater than with the dilated-tip electrodes. The dilated tips distributed the electric field over a greater surface area, which resulted in less heat generation per unit volume. In addition, we assumed the electrode surface was somewhat cooler since the dilated-tip electrodes would have exhibited less contact resistance than the standard graphite electrodes due to the larger surface area. Consistent with the increased surface area of the dilated-tip design, a larger volume of soil must melt adjacent to and

below the electrode before downward melt progression can be achieved. Consequently, the melt rates during the initial stages of the dilated-tip tests were slower than for the initial stages of the other four tests. Since the computer simulation did not analyze melt progression but only evaluated a steady-state, fully developed melt, the mass and physical dimensions of the monoliths could not be used to correlate the simulation data with the experimental results. Additional work will be necessary to quantify the heat distribution in the melt and in the corresponding heat flux to validate the computer model.

3. The measured apparent single-phase resistance of the various melts exhibited noticeable degrees of variability between the electrode designs.

As expected, the dilated-tip electrodes exhibited the lowest degree of electrical resistance, and each pair of tests produced very similar resistance values. The low resistance can be attributed to 1) an effectively shorter separation distance between electrodes, and 2) the larger surface area that minimized the effective contact resistance.

The composite electrodes composed of the graphite rod with the molybdenum tips theoretically should offer less resistance than the standard graphite rod electrodes. This expectation is due to the nonwetting nature of molten soil on graphite. Graphite exhibits a higher degree of contact resistance relative to a metal such as molybdenum (Stanek 1977). However, the resistance values obtained during the tests for the composite electrodes were higher than expected, and there was a greater degree of variability between the two composite tests relative to the other electrode designs. We suspect that the higher resistance, and the variability in resistance in the two tests, may be due to variability in the molybdenum/graphite joint caused by the differences in thermal expansion of the two materials. Although the joint was designed to be compatible at temperatures up to 1200°C, the higher melt temperatures (1600°C) may have decreased the contact at the interface of the two materials. Assuming the composite electrode joints exhibited high resistance, the effect would likely have been less efficient heating in the lower regions of the melt, and a corresponding smaller volume of vitrified soil would have been produced.

The variability measured during the single-phase resistance tests that were conducted as part of each of the six tests is important for future electrode designs. Future electrode designs can exploit the information gained from these types of tests to get a more effective heat distribution in the melt.

4. The variability of the monoliths produced under identical operating conditions was negligible.

Comparison of the physical size of the monoliths produced with the standard graphite electrodes and the composite graphite/molybdenum electrodes showed that each pair of monoliths was essentially equal in the mass and shape. There was only a 0.5% increase in the mass of the monoliths produced from the composite electrode tests relative to the standard graphite rod electrode tests. Each of the two monoliths produced with the standard graphite electrodes weighed 192.8 kg, while the two monoliths produced with the composite graphite/molybdenum electrodes weighed 199.6 kg (including the weight of the molybdenum components which combined to weigh 5.6 kg).

The two dilated-tip electrode tests yielded monolith sizes of 176.9 and 170.1 kg. We suspected the smaller mass of these monoliths resulted from less efficient processing, which was caused by the increased surface area of the dilated-tip electrodes. Although the dilated-tip electrodes had a larger surface area than the other electrode designs, the amount of power they transmitted remained equal to the amounts transmitted by the other types of electrodes. Comparatively, then, the current density and corresponding heat generated from contact resistance were reduced. These reductions in current density and temperature occurred because the electric field was distributed over a larger surface area.

There was greater variability between the two monoliths produced with the dilated-tip electrodes. The size difference was due to an interruption of power during the first of the two tests. The larger monolith from the dilated-tip test series was produced during test 1, which experienced 35 min of downtime. Consequently, test 1 was operated for 35 additional minutes to compensate for the interruption. Although the heat flux from the melt into

the adjacent soil diminished when power was terminated, the heat flux continued. During the downtime, the heat emanating from the melt continued to dry surrounding soil and to melt adjacent soil to a limited degree. Consequently, the larger monolith produced in test 1 can be attributed to an effectively longer processing time.

3.0 ELECTRODE DESIGN BASIS

3.1 ELECTRODE DESIGN CONSIDERATIONS

We tested the standard (5-cm-dia) graphite electrodes to establish a baseline from which the subsequent modified electrode tests could be evaluated. Additionally, the baseline test results will be useful in future efforts to compare the performance of depth enhancement techniques or other applications involving different soils or inclusions.

The composite electrode, with the molybdenum tip attached to a graphite rod at the bottom of the electrode, was evaluated to determine the relative effect of electrical contact resistance. We postulated that if contact resistance is a significant contributor to the heat generation in the melt, a large fraction of the heat could potentially be dissipated at the electrodes rather than distributed throughout the melt in the form of joule heating. If the fraction of heating due to contact resistance from graphite is significant, then the molybdenum tip, with its inherently lower contact resistance, would result in a path of least resistance through the melt. Consequently, the composite electrodes were evaluated to determine if the molybdenum tip would effectively serve as a hot-tip electrode whereby the current travels down the electrode and is dissipated at the electrode base in the lower regions of the melt.

The dilated-tip electrode design results in a narrower gap between the electrode tips than between the upper portions of the electrodes. Therefore, we evaluated the dilated-tip design to determine if increased electrical conduction would occur in the lower regions of the melt due to the narrower gap between electrodes. If we assume all regions of the melt are equal in temperature and resistance, then the dilated-tip electrode should result in increased conduction at the base of the melt. However, if the melt is not in thermal equilibrium (due to factors such as convection and buoyancy), and the melt is hotter in the upper regions as predicted by TEMPEST, the increased conductivity in the upper regions of the melt would negate the narrower gap at the bottom of the melt.

A second consideration for the dilated-tip design again involved the contribution of electrical contact resistance. With the increased electrode surface area provided by the dilated tips, the effect of contact resistance could be evaluated. In part, electrical contact resistance is a function of the surface area of the electrode. With a greater surface area, the measured resistance in the melt, in the circuit that includes the melt and the electrode, should be less than for the standard graphite electrodes.

3.2 COMPUTER SIMULATION

We performed a series of computer simulations to study the effects of electrode design on the thermal and fluid dynamic performance of an ISV melt. The computer simulations were similar to other ISV-related thermal and fluid dynamic modeling efforts conducted previously by Lessor, Eyler, and Lowery (1991). The computer simulations were conducted to aid in the design of electrodes able to enhance melt depth and to provide verification of actual engineering-scale test data. All of the computer simulations were performed with the EL9 version of the TEMPEST code (Trent and Eyler 1989).

According to our model, standard graphite rod electrodes deliver approximately 50% of the electrical energy to the upper 30% of the melt. This energy distribution is caused by thermal gradients in the melt that are established by convection heat transfer in the fluid; the hotter region being near the melt top, and the cooler region near the melt bottom. To increase melt depth, more of the delivered energy must be distributed to the melt bottom. The redistribution of electrical current from melt top to melt bottom will cause increased heat generation at the melt bottom, which will enhance melt rate and melt depth. To simulate energy redistribution, we modeled an insulated hot-tip electrode design (unlike the composite electrode used in the engineering-scale tests), a graphite dilated-tip electrode design, plus the standard graphite electrode design. Parameters such as computational domain geometry, boundary conditions, physical soil characteristics, electrode separation, and power level were consistent in all the analyses. Table 3.1 describes the six cases and their specific parameters.

TABLE 3.1. Computer Simulation Cases

<u>Case</u>	<u>Parameter Values</u>
Case 1 ^(a) Base Case	5.1-cm-dia. graphite electrodes Electrode separation: 30.5 cm Melt width: 70.1 cm Melt depth: 51.8 cm Power input: 25 kW
Case 2 ^(a)	5.1-cm-dia. electrodes Electrode separation: 30.5 cm 17.8-cm-long hot tip at bottom of electrodes Hot-tip length to melt depth ratio: 1/3 Insulated above hot tip Power input: 25 kW
Case 3	5.1-cm-dia. electrodes Electrode separation: 30.5 cm 17.8-cm-long hot tip at bottom of electrodes Hot-tip length to melt depth ratio: 1/3 Insulated above hot tip with Al ₂ O ₃ Power input: 25 kW
Case 4	5.1-cm-dia. graphite electrodes 8.9-cm-dia. molybdenum hot tip Electrode separation: 30.5 cm 8.9-cm-long Al ₂ O ₃ insulating ring above hot tip Hot-tip length to melt depth ratio: 1/12 Power input: 25 kW
Case 5	5.1-cm-dia. graphite electrode 4.4-cm-dia. molybdenum hot tip Electrode separation: 30.5 cm 4.4-cm-long Al ₂ O ₃ insulating ring above hot tip Hot-tip length to melt depth ratio: 1/12 Power input: 25 kW
Case 6 ^(a)	5.1-cm-dia. graphite electrodes 10.2-cm-dia. by 8.9-cm-long dilated tips Electrode separation: 30.5 cm Power input: 25 kW

(a) Simulation results are represented in Figure 3.1.

Figure 3.1 depicts the heat transfer distribution predicted by the model for comparison of the hot-tip and dilated-tip electrodes with the standard graphite electrodes. This corresponds to cases 2, 6, and 1, respectively, from Table 3.1. The hot-tip modeling was setup to simulate a variety of hot-tip concepts including cases in which some or all of the electrode above the energized tip was electrically insulated from the melt. The dilated-tip simulation consisted of a 10.2-cm-dia by 8.9-cm-long graphite dilated tip, with the remainder of the 5-cm-dia electrode shaft composed of graphite.

Analysis of the results indicated that the hot-tip and dilated-tip electrodes distributed more energy through the melt bottom than the standard electrode. Specifically, the heat transfer through the melt bottom for the hot-tip, dilated-tip, and standard simulations was calculated to be 36%, 20%, and 16%, respectively. Based on these results, we conclude that some degree of enhanced melt depth is possible using modified electrode designs. However, because the heat flux meters failed, the modeling results did not correlate with the actual engineering-scale test results.

In spite of the difficulties with the heat flux meters, we have confidence in our model-based conclusions. In interpreting these conclusions, note that the modeling results should not be correlated with monolith shape and mass or melt rate because the heat flux simulations were only representative of a steady-state analysis of a fully-developed engineering-scale melt. The model did not simulate a moving melt front, account for electrode contact resistance, nor simulate the effect of larger diameter dilated tips on initial melt rates. These factors are important influences on melt shape and melt rate.

FIGURE 3.1. Heat Flux Distribution for Three Electrode Designs Based on TEMPEST Code Modeling. (The composite electrode design was not modeled.)

4.0 TEST DESCRIPTION

4.1 TEST EQUIPMENT

Each of the six engineering-scale tests was configured as shown in Figures 4.1 and 4.2 (side and top view, respectively). Hanford soil ranging from 1 to 2 wt% water was placed in Geosafe's 110-gal test vessel. Type K and type C thermocouples were placed in the soil to monitor melt progress. An array of nine type K thermocouples and two type C thermocouples was placed along the vertical centerline of the test vessel. Beginning at the 10.2-cm depth from grade, the thermocouples were spaced in 5.1-cm increments to a depth of 61 cm. The two type C thermocouples were placed at the 35.6-cm and 50.8-cm depths. An additional type K thermocouple was placed at the 68.6-cm depth. In addition, four arrays of three type K thermocouples were placed at the 40.6-cm depth to monitor lateral growth. Electrode spacing of 25.4 cm was consistent for all six tests.

Along with the thermocouples, six model B heat flux meters (manufactured by the Thermal Instrument Company) were installed for each of the standard electrode tests and for one of the composite electrode tests. The purpose of these meters was to quantify the heat flux exiting the melt through the soil. Three heat flux meters were installed at the 40.6-cm depth. The fourth heat flux meter was placed at the 50.8-cm depth to permit monitoring of variances in the heat flux at the 40- and 50-cm depths. In addition, two heat flux meters were placed at the 68.6-cm and 71.1-cm depths to monitor heat exiting the melt bottom.

Figure 4.3 illustrates the composite graphite/molybdenum electrode design. A 5.1-cm-diameter by 5.1-cm-long molybdenum tip was selected because it was easily attached to the standard 5.1-cm graphite electrode. The molybdenum tip was cut from the end of a molybdenum rod having a standard female unitrode thread, which fit easily and snugly into a male-threaded graphite section thereby ensuring electrical conduction. Coefficient of thermal expansion calculations at 1200°C were performed to verify compatibility of the graphite/molybdenum joint. The molybdenum section was designed 5.1-cm long

FIGURE 4.2. Top View of Engineering-Scale Test Configuration

due to the calculated ampacity of 243 A, which is considerably higher than the maximum amperage limits for all electrical taps on the engineering-scale transformer. Also, a 5.1-cm length of molybdenum ensured the entire molybdenum section was underground during start-up, which minimized air oxidation of the molybdenum portion of the electrode.

Figure 4.3 also illustrates the graphite dilated-tip electrode design. A 10.2-cm-diameter by 10.2-cm-long graphite rod was selected to compromise

FIGURE 4.3. Diagram of the Composite and Dilated-Tip Electrode Designs

between establishing a reasonable edge-to-edge distance between the electrodes, while maintaining a relatively high current flux capacity. The dilated tip was machined to a standard female unitrode thread that coupled with a male-threaded graphite section. The edge-to-edge distance between the electrodes was 15.2-cm, while the calculated ampacity was 97 A per electrode. This value did not include a 4.7 A per centimeter ampacity of the 5.1-cm-diameter graphite upper shaft; thus, as the melt progressed, the electrode ampacity limit increased to well above the maximum amperage limits for all electrical taps on the engineering-scale transformer.

4.2 TEST OPERATIONS

Each of the three electrode designs was the subject of two separate tests, all of which were performed at the Geosafe facility at the University of Washington (Seattle). Process variables in the tests were minimized to the extent possible. The soil moisture content, soil density and composition, soil instrumentation, and electrode spacing were held constant for all tests. Operating time and power levels were held constant as control variables.

After equipment preparations were complete for each test, 1 kW per phase of electrical power was initiated. The rate of power increase was expected to be 1 kW per phase per 5 min, however, the rate of power increase for each test fluctuated slightly. Once a stable power level was achieved, the power was held at a constant 11 kW per phase of the two-phase power supply for a total power level of 22 kW. Power fluctuations were relatively minor during the start-up phase, and the calculated total energy input was 188.8 kWh for each test.

The following data points were recorded manually every 30 min:

- thermocouple readings
- heat flux data
- A- and B-phase amps, volts, resistance, and total power
- melt depth based on the electrode insertion depths.

The power was terminated for all tests when an elapsed time of 9 h, 5 min had passed.

4.2.1 Standard Graphite Rod Electrode Tests

The two standard graphite rod electrode tests were conducted on September 4 and 5, 1991. Initially, a controlled variable for the tests was a melt depth of 61 cm. However, during the first test, the melt rate began to decrease at run time 6 h (45.7-cm melt depth) and slowed to essentially zero at run time 8 h (50.8-cm melt depth). The test was then terminated at a depth of approximately 50 to 55 cm and at an elapsed time of 9 h, 5 min. Due to the excessive amount of time required to melt to 61 cm, operating time was chosen to replace melt depth as a controlled variable for the five remaining tests.

With the exception of the first hour of operation, the power input was consistently 22 kW throughout the test for a total energy input of 188.8 kWh. There were no significant problems experienced in either of the two standard graphite electrode tests. At 9 h, 5 min of run time for both tests, the 50.8-cm type K thermocouple had burned out indicating at least a 50.8-cm melt depth. At the time power was terminated, the 55.9-cm type K thermocouple indicated temperatures of 160°C and 537°C for test 1 and 2, respectively.

4.2.2 Graphite/Molybdenum Composite Electrode Tests

The two composite electrode tests were performed on September 6 and 18, 1991. Each of the tests was conducted without disruption at a consistent power input level of 22 kW and with a total energy input of 188.8 kWh. At 9 h, 5 min of run time for both tests, the 50.8-cm type K thermocouple had burned out for both tests, while the 55.9-cm type K thermocouple recorded 616°C and 860°C for test 1 and 2, respectively. There were no significant problems experienced in either test.

4.2.3 Graphite Dilated-Tip Electrode Tests

The two graphite dilated-tip electrode tests were completed on September 16 and 17, 1991. During test 1, power was unexpectedly interrupted at 2 h, 25 min of run time because an off-gas equipment problem caused near zero vacuum in the containment vessel. The vacuum problem was caused by plugging of the heat exchanger. The heat exchanger was removed, cleaned, and reinstalled. When vacuum levels returned to normal, power was restored. Because the delay cost 35 min, an equal period of time was added to the test duration resulting in an elapsed time of 9 h, 40 min, of which 9 h, 5 min constituted the powered phase. There were no other significant occurrences in either of the tests. Each test had 9 h, 5 min of powered run time with a consistent power input level of 22 kW and a total energy input of 188.8 kWh per test. During the tests, 50.8-cm type K thermocouples burned out, indicating at least a 50.8-cm melt depth. The 55.9-cm thermocouples recorded 165°C and 525°C for test 1 and 2, respectively. Note that the cooler of the two temperatures from the 55.9-cm thermocouple in all three cases corresponds to a greater degree of apparent subsidence listed in Table 5.1 (subsection 5.2). We suspect this lower temperature is due to a greater heat loss from the melt surface as a result of a thinner cold cap.

4.3 RESISTIVITY MEASUREMENTS

At the completion of each test, (9 h, 5 min) a series of melt resistance measurements was taken by applying 8 kW across only one of the two secondary phases on the power supply. The two powered electrodes were then systematically raised in 5.1-cm increments up to a depth of 20.3 cm, while electrical

measurements of current and voltage were taken. Using this technique, data were collected to enable us to quantify the contact resistance for each electrode design.

4.4 POSTTEST ACTIVITIES

To terminate each test, we shut off the chart recorder and the off-gas blower and stopped the water flow to the heat exchanger. Then electrodes were broken away from the monolith and the test vessel was moved out to the excavation area and allowed to cool. After the monolith cooled sufficiently, dirt was manually removed from around the monolith until lifting chokers could be placed around the monolith to remove it from the test vessel. Loose soil adhering to the monolith was brushed off. The physical dimensions of the monolith were measured and recorded, and photographs were taken. The monolith was then broken into several pieces so that the electrodes could be examined.

5.0 TEST RESULTS

Our test results are presented in terms of melt efficiency, melt rate, thermal distribution, and physical characteristics (mass and dimensions) of each monolith. Melt efficiency is simply an expression of the total power used divided by the mass of the resulting monolith expressed in terms of kWh/kg. In large-scale tests, melt efficiencies are quite high, usually about 0.7 kWh/kg, while engineering-scale tests typically range from 1 to 1.1 kWh/kg (Buel et al. 1987). Melt rate is an important factor in remedial operations because it strongly influences the economic efficiency of the ISV process. In this report, melt rate is discussed in terms of electrode insertion depths per unit time.

Thermal distribution within an ISV melt is significant because it affects achievable melt depth. Thermal distribution analysis using TEMPEST can predict the existence of thermal gradients in a large-scale melt, where the cooler regions occur at the melt bottom (Lessor 1991). Although such thermal gradients are expected to be minimal or nonexistent at the engineering-scale, during each of the six tests, we collected temperature data at two locations with type C thermocouples as shown in Figures 4.1 and 4.2 to determine if thermal gradients do indeed exist in engineering-scale melts. Data on monolith mass and physical dimensions permit an assessment of the effectiveness of any given electrode design. A monolith that exhibits a deeper melt depth compared to the other monoliths would indicate a more effective electrode design.

5.1 STANDARD ELECTRODE TEST RESULTS AND DISCUSSION

During each of the standard graphite electrode tests, the process exhibited a very consistent melt efficiency. The two standard electrode tests each demonstrated a melt efficiency of 0.97 kWh/kg soil melted. Regarding melt rate, Figure 5.1 illustrates the electrode depth vs. run time for the six tests. The graph indicates the melt rates for the standard electrode tests were practically identical at an average of 6.1 cm/h.

FIGURE 5.1. Average Electrode Insertion Depths vs. Time for the Six Tests

Figure 5.2 depicts the type C thermocouple temperatures in the melt vs. run time for the standard electrode tests. As described in Section 4, the

FIGURE 5.2. Type C Thermocouple Data from Baseline Test 1 and 2

type C thermocouples were placed at the 35.6-cm and 50.8-cm depths from grade for each test. Based on the data from these thermocouples, the hotter portions of the two melts appeared to be located at the upper elevations, although the limited test data are inconclusive. These thermal distributions were consistent with expectations.^(a)

Each of the baseline tests yielded a monolith mass of 192.8 kg and electrode depths of 55.9 and 53.3 cm, respectively. The monoliths shared the same circumference (180.3 cm). Table 5.1 lists the physical dimensions for each monolith.

5.2 COMPOSITE ELECTRODE TEST RESULTS AND DISCUSSION

The melt efficiency was 0.97 kWh/kg for each composite electrode test, the same as for the standard graphite rod electrode tests. The electrode depth vs. run time graph (Figure 5.1) indicates that melt rate for each composite electrode test was practically identical to the standard electrode tests at an average of 6.1 cm/h.

Figure 5.3 depicts the type C thermocouple temperatures vs. run time for the composite electrode tests. As in the standard electrode tests, the higher temperatures again appear to be nearer the 35.6-cm-deep type C thermocouple relative to the 50.8-cm-deep type C thermocouple. The difference in the melt temperature was likely due, in part, to a lower temperature directly adjacent to the molybdenum section compared to the graphite section. Since molten soil

(a) When a melt is heated via joule heating, a temperature gradient forms that causes a gradient in fluid density. A convective flow is established from joule heating and from contact resistance at the electrodes. As the temperature of the molten soil increases, density decreases, and the molten soil rises toward the top of the melt. Numerous studies have been conducted worldwide over the past 30 years to quantify the convective flow in molten glass systems, especially as a function of electrode and container configuration (Stanek 1977; Curran 1973; Stanek 1969). Convective flows at the engineering scale occur to a much lesser extent than at the large scale. Consequently, the smaller engineering-scale melts would not be expected to show significant variances in temperature except at the electrode surface.

TABLE 5.1. Physical Dimensions of the Six Monoliths Resulting from the Engineering-Scale Tests

	<u>Weight (kg)</u>	<u>Height (cm)</u>	<u>Width (cm)</u>	<u>Circumference (cm)</u>	<u>Apparent Subsidence^(a) (cm)</u>
Standard Design					
Test 1	192.8	55.9	53.3	180.3	14.0
Test 2	192.8	53.3	55.9	180.3	5.1
Composite Design					
Test 1	199.6	54.6	53.3	180.3	10.2
Test 2	199.6	53.3	58.4	180.3	8.9
Dilated-Tip Design					
Test 1	176.9	52.1	50.8	180.3	14.0
Test 2	170.1	50.8	50.8	175.3	8.9

(a) Apparent subsidence relates to the thickness of the cold cap (frozen glass layer) covering the surface of the melt. A smaller apparent subsidence value implies that more gas bubbles were entrapped, resulting in a thicker cold cap.

wets to molybdenum better than to graphite, the electrical contact resistance was less at the molybdenum/molten soil interface than at the graphite/molten soil interface.

Molybdenum can withstand current densities of 1 to 3 A/cm², while the allowable current density for graphite is only 0.1 to 0.3 A/cm² (Stanek 1977). Consequently, the melt temperature would be lower in the lower regions of the melt adjacent to the molybdenum, considering only the effects of electrical contact resistance. Graphite reacts aggressively with many metal oxides in molten soil. The reduction of these oxides generates carbon dioxide and carbon monoxide. These gases contribute to increased electrical contact resistance (Smith 1982). This phenomenon is supported by physical evidence from examinations of posttest vitrified soil samples collected from locations adjacent to the electrodes. Typically, there is evidence of reduced metals and the presence of numerous bubbles (<1-mm-dia) directly at the interface.

FIGURE 5.3. Type C Thermocouple Data from Composite Electrode Test 1 and 2

Each of the composite electrode tests yielded a monolith mass of 199.6 kg and an electrode depth of approximately 55.9 cm. Again, the physical dimensions of both monoliths were similar as indicated in Table 5.1. The monolith mass of 199.6 kg included the weight of the four molybdenum tips, which combined to weigh 5.6 kg. The weight of the molybdenum tips was not included for calculation of the enhanced monolith growth; however, the graphite portions of the electrodes were included in the measurement to be consistent with the other four tests.

5.3 DILATED-TIP ELECTRODE TEST RESULTS AND DISCUSSION

The melt efficiency of the dilated-tip electrode tests varied slightly between tests, 1.06 kWh/kg and 1.11 kWh/kg for test 1 and 2, respectively.

Compared to the previous four tests, which averaged 0.97 kWh/kg, these values represent a decrease in melt efficiency; the reason can be attributed to the slow melt progression that occurred during the initial hours of the tests.

According to the electrode depth vs. run time plot (Figure 5.1) dilated-tip test 2 had a slightly lower melt rate than test 1. Collectively, the melt rates from both tests were significantly lower during the early hours than the melt rates for the standard electrode and composite electrode tests. The melt rates later in the dilated-tip tests had slopes similar to the other four tests, however, the lower melt rates early in the tests were never overcome during the latter stages. Therefore, the dilated-tip electrodes did not achieve as great a mass or melt depth as did the electrodes in the other four tests (Table 5.1). The lower melt rate can be attributed to three factors. First, the large diameter tips cannot move downward until all the soil adjacent and immediately below them is melted. Since this requires that more soil be melted than for the smaller diameter electrodes, the downward melt progression is delayed. Second, the soil furthest from the melt center adjacent to the backside of the tips would be cooler since it is further from the area of active melting between the electrodes. Third, the temperature difference due to the increased electrode surface area and correspondingly lower electrical contact resistance, may result in lower temperatures at the melt/dilated-tip electrode interface. Since the dilated-tip electrodes have a greater surface area than the standard electrodes, with an equal power level the current density on the dilated-tip electrodes was lower. Consequently, the temperature at the electrode/melt interface would be expected to be less than with standard graphite rods.

Figure 5.4 depicts the type C thermocouple temperatures vs. run time for the dilated-tip electrode tests. According to the figure, the temperature of the type C thermocouple at the 35.6-cm depths rose similarly between tests, but the temperature at the 50.8-cm depth thermocouple reached only 300°C during test 2, well below the fusion temperature of soil. Although test 2 data are inconclusive, test 1 type C thermocouple data indicate the melt was hotter in the upper region of the melt at approximately 8.4 h when both type C thermocouples were immersed in molten soil.

FIGURE 5.4. Type C Thermocouple Data from Dilated-Tip Electrode Test 1 and 2

The two dilated-tip electrode tests yielded monolith masses of 176.9 kg and 170.1 kg, respectively. The size variance can be attributed to a problem experienced during the operation of dilated-tip test 1, in which the power was terminated for 35 min at mid-test. To compensate for this downtime, power was left on for 35 additional minutes, which resulted in a monolith weighing 6.8 kg more than the monolith produced in test 2 (test 2 was completed on schedule without interruption). The physical dimensions of the two monoliths listed in Table 5.1 showed more variation than the monoliths produced in the previous four tests.

5.4 GENERAL OBSERVATIONS

Upon completion of each test, the resulting monolith was broken and examined. The modified electrodes from both the composite and dilated-tip electrode tests were examined upon recovery from the respective monoliths;

based upon a cursory review, those electrodes showed no evidence of excessive corrosion, oxidation, or arcing at the joints. All of the monoliths were symmetrical in shape and generally shared the same dimensions.

5.5 HEAT FLUX

As described in Section 4, we installed six heat flux meters in the two graphite rod electrode tests and in one of the composite electrode tests to assist in quantifying the heat distribution exiting the melt. Upon analysis, however, the heat flux meter data were judged invalid. The energy values given by the heat flux meters were essentially zero the majority of the time, with only a few intermittent spikes. During dilated-tip test 1, the standard instrument setup was modified so that two sacrificial heat flux meters were placed in the middle of the melt to determine if the earlier meter locations were the cause of the invalid data. But, the transmitted values were again essentially zero the majority of the time, even during the time when the melt approached the heat flux meters. A subsequent evaluation and discussions with the manufacturer did not reveal any conclusive causes for this instrument failure.

5.6 SINGLE-PHASE RESISTANCE

We performed a single-phase resistance test at the conclusion of each of the six engineering-scale tests.^(a) The data collected from these tests were used to quantitatively calculate both melt and contact resistance. We assumed that melt resistance and melt temperature would be equal in the six tests, since all tests used the same soil type, were conducted when the melts reached a similar size, and were measured in the same manner with a B-phase power level of 8 kW. These resistance tests were performed by holding B-phase power constant at 8 kW power input while A-phase was reduced to 0 kW. The

(a) The absolute values of these measured resistances are presented here for relative comparisons only. The data can be used in subsequent evaluations to quantify the specific effects and degree of electrical contact resistance. Selective exploitation of these types of electrical phenomenon can lead to enhanced electrode designs to help achieve greater melt depths.

test involved raising the B-phase electrodes from the final 55.9-cm melt depth to a 20.3-cm depth in 5.1-cm increments and calculating the resistance based on power data. Figure 5.5 graphs the resistance vs. electrode depth for each of the engineering-scale tests.

The data in Figure 5.5 provide both expected and unexpected results. First, the dilated-tip electrodes exhibited the lowest resistance relative to the other two electrode designs (approximately 1.5 ohms at a 36-cm electrode insertion depth). This relationship was expected and indicated that the effectively closer spacing between the electrodes resulted in less resistance. Due to the larger surface area of the dilated-tip electrodes, a correspondingly lower electrical contact resistance is also likely to have contributed to the lowered resistance values.

FIGURE 5.5. Single-Phase Resistance from the Six Tests

Second, the resistance data for the standard electrode tests reveals a similarly low resistance value of approximately 2 ohms at a 36-cm electrode insertion depths compared to the dilated-tip electrode tests. The relatively low resistance values were unexpected, since the electrode spacing was effectively larger and the surface areas of the electrodes were smaller relative to the dilated-tip design. The smaller surface area should have resulted in a higher electrical contact resistance.

Third, the composite electrode single-phase resistance tests revealed less precision than the dilated-tip test results because there was more variation in the resistance values between the two tests. The molybdenum tip electrodes should have had a lower resistance than the standard graphite electrodes since the contact resistance for the molybdenum portion was significantly less than for graphite alone (Stanek 1977). A possible reason for the variation in resistance could be the molybdenum/graphite joint. In this case, a male-threaded graphite electrode was screwed into a female-threaded molybdenum section. At temperature, the different coefficients of expansion could have caused the molybdenum to expand away from the graphite connecting pin, resulting in increased resistance in the joint.

6.0 REFERENCES

Brouns, R. A., J. L. Buelt, and W. F. Bonner. 1983. "In Situ Vittrification." U.S. Patent 4,376,598.

Buelt, J. L., C. L. Timmerman, K. H. Oma, V. F. FitzPatrick, and J. G. Carter. 1987. In Situ Vittrification of Transuranic Waste: An Updated Systems Evaluation and Applications Assessment. PNL-4800 Suppl. 1, Pacific Northwest Laboratory, Richland, Washington.

Buelt, J. L., C. L. Timmerman, and J. H. Westsik, Jr. 1989. In Situ Vittrification: Test Results for a Contaminated Soil-Melting Process. PNL-SA-15767, Suppl. 1, Pacific Northwest Laboratory, Richland, Washington.

Curran, R. L. 1973. "Electrodes Affect Convection Currents in Glass." The Glass Industry (May):14-15, (June):16-17.

Lessor, D. L., L. L. Eyler, and P. S. Lowery. 1991. "Joule Heat Calculations for Simulations of Multielectrode Glass Melters and In Situ Vittrification Systems." Glastechnische Berichte 64(1991):95.

Smith, M. A. 1982. "Graphite Electrodes for Glass Melting." Glass Industry, Corning Glass Works, Corning, New York.

Stanek, J., L. Sasek, and H. Meissnerova. 1969. "Flow of Glass in Furnaces Heated by Electricity." Glass Technology 10(2):43-49.

Stanek, J. 1977. Electric Melting of Glass. Elsevier Scientific Publishing Company, New York.

Trent, D. S., and L. L. Eyler. 1989. TEMPEST, A Three-Dimensional Time-Dependent Computer Program for Hydrothermal Analysis, Vol. 1: Numerical Methods and Input Instructions. PNL-4348, Vol. 1, Rev. 2, Pacific Northwest Laboratory, Richland, Washington.

DISTRIBUTION

No. of
Copies

No. of
Copies

OFFSITE

12 DOE/Office of Scientific and
Technical Information

21 DOE Office of Environmental
Restoration and Waste
Management

Trevion II Building
12800 Middlebrook Road
Germantown, MD 20874

ATTN: W. W. Alexander
T. D. Anderson
J. E. Baublitz
D. L. Biancasino
J. O. Boda
J. A. Coleman
S. P. Cowan
J. J. Fiore
C. W. Frank
K. O. Hain
J. M. Lankford
J. C. Lehr
S. C. Lein
J. E. Lytle
S. A. Mann
S. M. Prestwich
M. W. Shupe
C. H. Sink
L. H. Taylor
H. F. Walter
R. P. Whitfield

2 DOE Albuquerque Operations
Office

P.O. Box 5400
Albuquerque, NM 87115
ATTN: P. A. Saxman
D. H. Bandy

W. Holman
DOE San Francisco Field
Office
1333 Broadway
Oakland, CA 94612

J. Haugen
DOE Chicago Field Office
9800 South Cass Avenue
Argonne, IL 60439

J. Hall
DOE Nevada Field Office
P.O. Box 98518
Las Vegas, NV 89193-8518

R. Tyler
DOE Rocky Flats Office
DOE Building 116
Golden, CO 80402-0928

S. Ketola
DOE West Valley Project
P.O. Box 191
West Valley, NY 14171

W. Fitch
DOE Idaho Operations Office
785 DOE Place
Idaho Falls, ID 83402

M. O'Rear
DOE Savannah River Operations
Office
P.O. Box A
Aiken, SC 29801

4 DOE Oak Ridge Office
P.O. Box 2001
Oak Ridge, TN 37831
ATTN: J. Moore (2)
J. Sweeney (2)

3 Battelle Memorial Institute
505 King Avenue
Columbus, OH 43201
ATTN: W. A. Carbeiner
R. A. Nathan
Technical Library

No. of
Copies

Jesse L. Yow, Jr.
Lawrence Livermore National
Laboratory
7000 East Avenue
Livermore, CA 94550

M.A.H. Reimus
Los Alamos National Laboratory
P.O. Box 1663
Los Alamos, NM 87545

J. Koger
Martin Marietta Energy Systems
P.O. Box 2009
Oak Ridge, TN 37831-8097

P. T. Owen
Martin Marietta Energy Systems
P.O. Box 2003
Oak Ridge, TN 37831-7256

- 8 Oak Ridge National Laboratory
P.O. Box Y
Oak Ridge, TN 37830
ATTN: G. K. Jacobs (4)
M. Naney (2)
B. P. Spalding (2)

K. Nuhfer
Westinghouse Materials Co. of
Ohio
P.O. Box 398704
Cincinnati, OH 45239-8704

- 5 Sandia Laboratories
P.O. Box 5800
Albuquerque, NM 87185
ATTN: D. Berry
R. Knowlton
J. Phelan
L. D. Tyler
Technical Library

No. of
Copies

- 9 EG&G Idaho
P.O. Box 1625
Idaho Falls, ID 83415
ATTN: M. D. Herd
P. E. MacDonald
S. K. Merrill
D. F. Nickelson (5)
R. L. Norlund

L. Rogers
EG&G Energy Measurements, Inc.
P.O. Box 1912, MS RSL-11
Las Vegas, NV 89125

B. Haas
Ames Laboratory
7 Spedding Hall
Iowa State University
Ames, IA 50011

- 6 Westinghouse Savannah River
Company
P.O. Box 616
Aiken, SC 29801
ATTN: J. S. Haselow
C. M. Jantzen
M. J. Plodinec
J. F. Sproull
J. L. Steele
T. Walton

J. M. Pope
West Valley Nuclear
Services Co.
P.O. Box 191
West Valley, NY 14171

- 5 Geosafe Corporation
2950 George Washington Way #A
Richland, WA 99352-1615
ATTN: C. L. Timmerman (2)
B. E. Campbell
J. E. Hanson
R. G. Winkelman

No. of
Copies

ONSITE

13 DOE Richland Field Office

E. A. Bracken, A6-95
K. W. Bracken, A5-22
R. P. Carter, A5-21
P. K. Clark, A6-80
P. F. Dunigan, A6-95
J. K. Erickson, A5-19
R. D. Freeburg, A5-19
M. J. Furman, A6-80
R. E. Gerton, A6-80
J. D. Goodenough, A5-22
J. M. Hennig, A5-21
R. D. Izatt, A6-95
J. J. Sutey, A5-90

13 Westinghouse Hanford Company

W. C. Alaconis, L4-92
H. Babad, B3-68
J. D. Berger, L0-18
J. W. Cammann, H4-54
K. R. Fecht, H4-56
R. E. Lerch, B2-35
H. E. McGuire, B2-35
J. W. Shade, R4-03
D. A. Turner, R1-10
D. D. Wodrich, R1-48
R. D. Wojtasek, B2-15
B. A. Wolfe, L5-61
R. L. Gilchrist, L5-63

No. of
Copies

31 Pacific Northwest Laboratory

L. Ballou, P7-18
T. M. Bergsman, P7-41
W. F. Bonner, P7-44
J. L. Buelt, P7-41
H. C. Burkholder, P7-41
C. C. Chapman, P7-41
T. T. Claudson, K1-66
W. O. Heath, P7-41
C. H. Kindle, P7-41
W. L. Kuhn, P8-38
P. A. Lowery, K7-15
J. Luey, P7-41
J. L. McElroy, P7-46
M. E. Peterson, P7-41
T. D. Powell, P7-39
M. R. Shay, K6-25
S. C. Slate, K1-25
S. L. Stein, PNWD
L. E. Thompson, P7-41 (5)
J. S. Tixier, P7-41
S. L. Woosley, P7-41
Publishing Coordination
Technical Report Files (5)

END

**DATE
FILMED**

11 / 2 / 92