RECEIVED
DOE/PC/92149

93 MAR 23 PM 1:25

DOE/PC/92149--T1

DE93 013606

QUARTERLY TECHNICAL PROGRESS REPORT

~~DRAFT~~

COVERING OCTOBER 1 THROUGH DECEMBER 31, 1992

Contract No. DE-AC22-92PC92149

De-Ashing of Coal Liquids with Ceramic Membrane
Microfiltration and Diafiltration

Submitted by

CeraMem Corporation

Waltham, Massachusetts

To

U.S. Department of Energy

Pittsburgh Energy Technology Center

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

MASTER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

I. SUMMARY

A. Program Objectives

Removal of mineral matter from liquid hydrocarbons derived from the direct liquefaction of coal is required for product acceptability. Current methods include critical solvent de-ashing and filtration, both of which produce an ash reject stream containing up to 15% of the liquid hydrocarbon product.

This program is directed towards development of an improved process for de-ashing and recovery of coal-derived residual oil: the use of ceramic membranes for high-temperature microfiltration and diafiltration. Using laboratory-scale ceramic membrane modules, samples of a coal-derived residual oil containing ash will be processed by crossflow microfiltration, followed by solvent addition and refiltration (diafiltration). Recovery of de-ashed residual oil will be demonstrated.

Data from this program will be used to develop a preliminary engineering design and cost estimate for a demonstration pilot plant incorporating full-scale membrane modules. In addition, estimates for production system capital and operating costs will be developed to assess process economic feasibility.

The five program tasks include (1) ceramic membrane fabrication, (2) membrane test system assembly, (3) testing of the ceramic membranes, (4) design of a demonstration system using full scale membrane modules, and (5) development of estimates for microfiltration capital and operating costs and assessment of process economic feasibility.

B. Summary of Quarterly Progress

CeraMem made four ceramic microfilters appropriate for microfiltration and diafiltration of coal liquids. The permeation of waste oil through these membranes was measured at temperatures in the range of 300°F to 500°F using an apparatus constructed by CeraMem for a separate project. Two of these membranes gave fluxes that were reasonably stable and were high enough to be economically attractive in a coal liquids process.

The waste oil system was determined to be unsuitable for coal liquids testing. CeraMem concluded that the costs of assembling a test system to conduct the coal liquids filtration tests would be prohibitively expensive, primarily because of the hazard associated with coal liquid processing. CeraMem has sought an alternative test site to conduct the process trials and is now preparing to contract with Exxon Research and Engineering Company (ER+E) for these microfiltration and diafiltration tests (subject to DOE approval).

II. Task 1 -- Ceramic Membrane Fabrication

With CeraMem's standard ceramic substrate as the common starting point, microfiltration membranes were made with the following pore sizes and chemistries: 500Å, zirconia/alumina mixture; 100Å, silica; 50Å, alumina; and 30Å, silica. Microfiltration monoliths one inch in diameter and one foot long were made for tests of hot waste oil filtration described below.

III. Task 2 -- Membrane Test System Assembly

A. Hot Oil Test System at CeraMem

CeraMem's hot oil test system consisted of a high temperature recirculation pump, a heated, enclosed tank, the CeraMem ceramic membrane module, and the piping and valves associated with a closed-loop recirculating permeation apparatus (Figure 1).

B. Off-site Coal Liquids Test Facility

The costs and complexity of a coal liquids test system were discussed with potential system fabricators, hardware component suppliers, and oil industry personnel experienced in coal liquid processing. Also, on a related project, CeraMem retained a consultant experienced in test system design for both aqueous and hydrocarbon systems. Based on discussions with these sources, it became apparent that the costs for the test system and associated facilities required for coal liquids testing would be higher than that originally planned for the project. A significant expense would be involved with managing the hazardous materials concerns associated with coal-derived liquids.

Consequently, CeraMem began to pursue the possibility of testing offsite. The most promising prospect was the Synthetic Fuels Laboratory of Exxon Research and Engineering, Baton Rouge, LA. Exxon currently operates a 50 lb/day liquefaction facility. Exxon has its own source of ash-containing residuum (500°F melting point) and has obtained 3000 gallons of distillate (a vacuum gas oil with a boiling range of 500°F to 800°F) from Wilsonville when that facility was closed.

The Exxon liquefaction plant, known as "RECLU" (Exxon Coal Liquefaction Unit), processes 50 lb of coal per day and is designed to handle coal and coal-derived liquids in a safe and environmentally sound manner. In discussions with Exxon personnel, it became clear that a small bench-scale membrane test loop could be constructed near the RECLU and that this test loop could readily be made to the safety standards conventionally associated with coal liquid processing. CeraMem and Exxon agreed to pursue establishing a rational test program and a subcontract to Exxon to conduct the coal liquids testing.

Figure 1. Schematic of Hot Oil Test System

IV. Task 3 -- Testing of Ceramic Membranes

Membrane flux tests were performed on CeraMem's hot oil test facility by circulating waste motor oil through the system at temperatures between 300°F and 500°F. A pressure of approximately 40 psig was maintained on the feed side of the membrane. With the zirconia/alumina membrane, the flux varied with temperature in accord with a typical Arrhenius plot (Figure 2) and displayed an activation energy of approximately 3 kcal/mole, roughly the dependence of oil viscosity on temperature. The least fouling of the membranes was the 100Å silica membrane (Figure 3).

A batch concentration test was done with this membrane at 445°F, concentrating the original feed by a factor of nine (89% of the feed was permeated). This membrane was able to produce a permeate that was largely free of metals (Table 1). In addition, the permeate oil was much clearer than the feed. These results show that the permeate in a coal liquids test with this membrane is likely to be essentially ash free. This membrane would be the logical one to test at Exxon's RECLU.

V. Future Work

CeraMem intends to pursue establishing a subcontract with Exxon for the coal liquids testing. To prepare for this testing, a computer model will be developed that describes the mass balances associated with diafiltration. This model will allow for a rational design of the experimental program at Exxon.

Effect Of Temperature On Flux
Evergreen Waste Oil Sample
35 psig Operating Pressure

Figure 2

Membrane Flux vs. Time Waste Oil Sample #2 400°F; 40 psig; Various Membrane Types

Figure 3

Table 1

ANALYSES OF SAMPLES FROM BATCH CONCENTRATION TRIAL

<u>CONSTITUENT/ PROPERTY</u>	<u>FEED CONCENTRATION</u>	<u>PERMEATE CONCENTRATION</u>	<u>CONCENTRATE CONCENTRATION</u>
Phosphorus	0.97 ppm	0.07 ppm	5.0 ppm
Lead	26.0	2.0	467
Cadmium	0.44	0.03	14.0
Chrome	1.47	0.14	28.0
Iron	123	4.5	1272
Ash	0.6 wt %	0.02 wt %	4.88 wt %
Sulfur	0.67 wt %	0.49 wt %	2.03 wt %
AKV Viscosity @ 210°F	10.75 CS 66.9 SSU	6.21 CS 46.5 SSU	Solid Solid
API Gravity	27.8	29.8	Spg. 0.97

END

**DATE
FILMED
6/11/93**