DOE/ER/13612--6

DE93 012231

Annual Progress Report
Grant DE-FG02-86ER13612

December 1, 1989 to November 30, 1990

INFRARED STUDY OF CARBON DEPOSITS ON BIMETALLIC CATALYSTS

R. P. Eischens
Zettlemoyer Center for Surface Studies
Department of Chemistry
Lehigh University
Bethlehem, PA 18015

(215) 758-3600

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

Trans 8/2/90

MASTER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

Catalytic reforming, in which low octane gasoline is upgraded to high octane, is one of the world's most important catalytic processes. It is carried out on dual function catalysts in which the catalytic activity of the alumina support and the catalytic activity of the supported metal are both essential to catalytic performance. For several decades platinum/alumina was the catalyst of choice. This was supplanted by platinum-rhenium/alumina because this bimetallic was less susceptible to poisoning by carbon. More recently, platinum-tin/alumina has attained importance because it is better suited to current chemical engineering design which favors a continuous regeneration by removal of carbon. In this continuous regeneration the platinum-tin/alumina catalyst is circulated between treating and regeneration reactors.

Early work had shown that carboxylates $\begin{array}{c} \diagup \text{O} \\ \text{C} - \\ \diagdown \text{O} \end{array}$ are a constituent of coke on alumina and that rhenium lowers the production of carboxylate. Because of the increasing importance of tin in reforming catalysts, during the last year studies of tin were emphasized in our current DOE project. Previously it had been found that rhenium lowers the formation of carboxylate in the coke. This reduction of carboxylate was found for both rhenium/alumina and platinum-rhenium/alumina. In both of these cases the total coke was not affected. During the last period it was found that 3 wt% tin lowers both carboxylate formation and coke deposition by about 40% as compared to alumina. This is consistent with the

possibility that tin has a beneficial effect on coke production. However, study of 3% loadings of both tin and platinum showed a surprisingly strong synergistic effect in which total coke is increased by 300% and carboxylate production is doubled. This enhancement of coke deposition is not consistent with the use of platinum-tin bimetallics in commercial operation. In efforts to determine how tin affects platinum, it was found that at 3% loadings of both metals, the ability of platinum to chemisorb carbon monoxide is drastically decreased. Results with platinum-tin catalysts prepared at 1.0%, 0.6% and 0.3% loadings showed that the decrease in carbon monoxide chemisorption on platinum parallels the excess coke deposition. At 0.3% both effects are not detectable. These results show that the harmful synergistic effect depends on metal loadings. For catalysts, prepared on the specific alumina used here and the specific incipient wetness impregnation method used to prepare the catalysts, it is likely that the problem is not important at 0.3% loadings. However, the difficulty must be considered if other methods of preparing the catalysts are used. A paper presenting these results is attached. It has been accepted for publication in the Proceedings of the 5th International Symposium on Catalyst Deactivation.

It is apparent that an understanding of the manner in which second metals, added with platinum, such as rhenium, iridium and tin, affect carboxylate production requires a knowledge of the mechanism of the production of carbon-oxygen species under the reducing conditions of coke deposition. There are two possible

types of mechanism, i.e., the alumina is reduced or the surface hydroxyls of the alumina react with hydrocarbons to produce the carbon-oxygen species. The view that the surface hydroxyls are the source of the oxygen is the most reasonable and is supported by preliminary studies which show that surface hydroxyl concentration is decreased as carboxylates are formed during coke deposition. Unfortunately FTIR infrared spectrometers do not perform well in the hydroxyl stretching region. Thus it has not been possible to quantify these observations. Moreover, there are five different hydroxyls on alumina and it has not been possible to determine whether the more basic hydroxyls (highest frequency) or the more acidic hydroxyls are involved in carboxylate production. This study will be continued when a new mercury-cadmium-telluride detector is available.

Other studies which are underway, but not yet complete, involve the effect of catalyst acidity on carboxylate formation, the effect of platinum loadings on the proportion of carboxylate in the coke, the effect of preparation sequence, i.e., tin first or platinum first, and the migration of tin over the alumina surface.

END

DATE
FILMED

5 / 14 / 93