PROGRESS REPORT
for the period June, 1, 1992 through December 31, 1992

for DOE Contract
4242/ DE - FG - 02 - 92- ER - 14268

DOE/ER/14268--1
DE93 013390

THE RELATIONSHIP BETWEEN HYDROXYL GROUPS ON OXIDE
SURFACES
AND THE PROPERTIES OF SUPPORTED METALS

Submitted to:
The U.S. Department of Energy

by
James A. Schwarz

Professor of Chemical Engineering and Materials Sciences
Syracuse University, Syracuse, NY 13244

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

MASTER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

RESEARCH SCOPE AND OBJECTIVES

Supported metal catalysts are commonly prepared by depositing catalytic precursors from aqueous solutions of electrolytes onto high surface area oxides. This impregnation step has been the focus of a number a recent studies from our laboratory which seek to relate the effect of formulation procedures on the catalytic properties of supported metal catalyst systems. In our previous work we have extended well established principles of colloid chemistry to catalyst supports in contact with impregnation solutions.

A general conclusion of our previous studies was that the performance of the finished catalyst depends on the characteristic properties of the hydroxyl inventory on the surface of the oxide support, both in wet and in (pseudo)-dry conditions. Hydroxyl groups serve as adsorption or exchange sites during catalyst preparation. On the other hand, the configuration of hydroxyl groups still remaining on oxides after dehydration determines the acid-base characteristics of the catalyst, which is a major catalytic property.

The purpose of the present investigation is to characterize the relationship which we expect to exist between the complex hydroxyl inventory at the oxide/solution interface and the intrinsic acid/base properties of partially dehydroxylated oxides. We assume that the same structural models are operational in describing the local configuration of hydroxyl groups on (pseudo)-dry oxides as well as at the oxide/solution interfaces. This allows us to extend the concept of intrinsic heterogeneity of (pseudo)-dry oxide surfaces to the oxide/solution interface. We examined the consequences of that heterogeneity upon the impregnation step of catalyst preparation.

DESCRIPTION OF RESEARCH EFFORT

Main idea

The surface heterogeneity of oxides results from differences in coordination of oxygen atoms which differ from each other by the number and type of surrounding metal cations. These differences determine the occurrence of various types of hydroxyls on partially dehydrated surfaces,

as identified in IR spectra and characterized by their acid/base properties. Assuming that rehydration does not perturb the atomic order on oxide surfaces, the same categories of surface hydroxyls exist at the oxide/solution interface. They associate or dissociate protons according to their own proton affinity, which is structurally dependent.

Method

The 1-pK/multisites model - employed by us for the first time for the oxide/solution interface - pictures the surface as consisting of nonequivalent oxygen groups which are characterized by a continuous distribution of proton affinities. We assumed that the heterogeneity of acid/base properties can be accurately accessed from proton adsorption isotherms. We used potentiometric titration curves consisting of a large number of data points collected over a broad pH interval as allowed by the sample being titrated. This experimental method was used for a long time to study the charging behavior of oxides in electrolyte solutions, but now it was combined with a more powerful computational method for deconvolution of the measured isotherms.

The distribution of proton binding sites in regard with their proton affinity was calculated using the local solution of the adsorption integral equation. A smoothing spline procedure was used and a criterion for optimal smoothing was proposed and tested. As a first approximation, we neglected the electrostatic effects in the calculation of proton affinity constants. The distributions obtained in this way (so-called apparent distributions), though not exactly related to intrinsic properties, reflect the conditions under which the interface was studied and are free from the ambiguity of any particular electrostatic model. Using this simple approach, we were able to extract meaningful information about the acid-base properties of oxides studied. The proton affinity distributions were successfully correlated with the available structural models.

Results

As a prototype oxide for this study we used alumina, in view of its importance as a catalyst support and for comparison with the existing structural data. We also investigated several oxides, simple and composites, as well as their physical mixtures, such as silica, titania, ceria, alumina/silica, tungsten oxide/alumina. We show as an example in Figure 1 the proton affinity distribution of surface hydroxyls on the surface of

alumina. The four peaks obtained from the deconvoluted isotherm were assigned to four of the five categories of hydroxyl groups structurally allowed for a spinel type alumina surface. The corresponding protonation equilibria and the domains of predominance of various charge sites are also shown in the lower part of Figure 1.

The above assignment of local proton equilibria on alumina sites was confirmed by further experiments in which alumina was modified by adsorption of either anions (fluoride) or cations (palladium tetraammine) at pH 4-5 or 8-10, respectively. For fluoride modified alumina, an increase in acidity was found in proton affinity distribution, which results from the inductive effect of the electronegative fluoride on the neighbouring hydroxyls. The acidic sites which react around pH 4-5 originate from -OH groups in bridging positions between octahedral and tetrahedral Al ions (Figure 2). In the case of Pd/alumina catalysts, the effect of the impregnation pH on the reducibility of the palladium complex was found (Figure 3). It was explained by considering the quality and quantity of charged surface sites which develop at different pH's and serve as fixation centers for the catalytic precursor. A comparison of Temperature Programmed Reduction data for these catalysts (Figure 3) with the picture of surface speciation shown in Figure 1 illustrates the increase in contribution of -OH groups linked to octahedral Al cations in the adsorption of palladium cations, as the impregnation pH changes from 8 to 10.

The experiments with composite oxides also showed that deconvoluted proton adsorption isotherms well represent the heterogeneity of binding sites existing at oxide/solution interface. Thus, for the silica/alumina system, a new category of acid sites was observed at pH 3.5-4.5. These sites are most probably surface hydroxyls which link octahedral Al and tetrahedral Si in the composite oxide; their acidity increases because of the unbalanced electric charge (Figure 4). For the tungsten oxide/alumina system, we found that the buffering capacity of the surface replicates the buffer properties for protons of the precursor solution used in preparation of the composite, namely ammonium metatungstate (Figure 5).

Implications and future studies

The above examples show the existence of particular sites on the hydroxylated surface of commonly used supports; these sites act

specifically in adsorption of catalyst precursors during the wet impregnation step. They also show that the above sites are related to the intrinsic hydroxyl inventory of the surface.

These findings are extremely interesting and they could have some very important implications related to supporting metals on oxides for catalyst preparation. A comprehensive description of the intimate mechanism leading to the binding of catalytic precursors or additives on the surface of supports is still needed and recent literature continues to focus on this subject. Our results show that adsorption of anions (F^- , Cl^-) and cations ($Pd(NH_3)_4^{2+}$) from acidic and basic solutions, respectively, occurs on different types of surface sites, i.e. basic sites for anions and acidic sites for cations.

In future studies the effect of both cationic and anionic additives on the proton affinity distributions of selected supports will be systematically studied. By this way we will observe the inventory of hydroxyl groups on the surface which did not react with the adsorbed components. We plan to extend the systems investigated by including mixed oxides of various compositions, transition metal oxides supported on various carriers, families of commercial aluminas and silicas differing by their preparation procedures.

These results will be correlated with direct characterization of the donor/acceptor properties of (pseudo)-dry surface of the same oxides through the Inverse Gas Chromatography method. A direct confirmation of the location of adsorbed species on oxide surface will come in future studies from comparison of the infrared spectra of the stretching modes of surface hydroxyls of the original and modified supports.

PUBLICATIONS AND MANUSCRIPTS IN PRINT OR IN PREPARATION

R. Zhang and J. A. Schwarz

"Design of Inhomogeneous Metal Distributions Within Catalyst Particles"

Applied Catalysis, A, 91 (1992), 57-65.

Cr. Contescu, J. Jagiello and J. A. Schwarz

"Heterogeneity of Proton Binding Sites at the Oxide/Solution Interface"

Langmuir, submitted

J. A. Schwarz, Cr. Contescu and J. Jagiello

"The Thermodynamics and Adsorption Properties of Hydroxyl Groups on Oxide Surfaces in Aqueous Environments"

Catalysis, vol. 11, Specialist Periodical Report, Royal Society of Chemistry (London), Thomas Graham House, Cambridge, UK (invited contribution)

Cr. Contescu, J. Jagiello and J. A. Schwarz

"Interaction Chemistry of Protons at Oxide/Aqueous Solution Interfaces. 1. Alumina and Halides - Modified Alumina"

In preparation

Cr. Contescu, J. Jagiello and J. A. Schwarz

"Interaction Chemistry of Protons at Oxide/Aqueous Solution Interfaces. 2. Silica and Alumina/Silica Composite Oxides"

In preparation

Cr. Contescu, J. Jagiello and J. A. Schwarz

"Interaction Chemistry of Protons at Oxide/Aqueous Solution Interfaces. 3. Tungsten Oxide/Alumina Composite Oxides"

In preparation

PRESENTATIONS

J. A. Schwarz, Cr. Contescu and J. Jagiello

"Relationship Between the Hydroxyl Groups on Wet and Dry Oxide Surfaces"

Stanford University, Department of Chemical Engineering, October 1992 (Invited)

J. A. Schwarz, Cr. Contescu and J. Jagiello

"Relationship Between the Hydroxyl Groups on Wet and Dry Oxide Surfaces"

Catalytica, October 1992 (Invited)

J. A. Schwarz, Cr. Contescu and J. Jagiello

"The Chemical Properties of Hydroxyl Groups on Oxide Surfaces"

Air products, Allentown PA, November 1992 (Invited)

J. A. Schwarz

'The Thermodynamic Properties of Hydroxyl Groups on Oxide Surfaces in Aqueous Environments and their Relationship to Catalyst Preparation"

North American Catalysis Society, Pittsburgh PA, May 1993 (Invited
Keynote Speaker)

Figure 1

Figure 2

TPRd of a Pd/Al₂O₃ CATALYST

Figure 3

Figure 4

Figure 5

END

DATE
FILMED
6/11/93