A major purpose of the Technical Information Center is to provide the broadest dissemination possible of information contained in DOE's Research and Development Reports to business, industry, the academic community, and federal, state and local governments.

Although a small portion of this report is not reproducible, it is being made available to expedite the availability of information on the research discussed herein.

LA-UR--84-1525

DE84 012634

NOTICE

PORTIONS OF THIS REPORT ARE ILLEGIBLE. It has been reproduced from the best available copy to permit the broadest possible availability.

Los Alamos National Laboratory is operated by the University of California for the United States Department of Energy under contract W-7405-ENG-36.

TITLE: ANOMALOUS SURFACE IMPEDANCE IN REENTRANT FERROMAGNETIC SUPERCONDUCTORS

AUTHOR(S): C. Y. Huang, G. Kozlowski, F. Mancini, M. B. Maple, H. Matsumoto, C. E. Olson, H. Umezawa, and J. P. Whitehead

SUBMITTED TO: 17th International Conference on Low Temperature Physics, Aug. 15-22, 1984, Karlsruhe, West Germany

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

By acceptance of this article, the publisher recognizes that the U.S. Government retains a nonexclusive, royalty-free license to publish or reproduce the published form of this contribution, or to allow others to do so, for U.S. Government purposes.

The Los Alamos National Laboratory requests that the publisher identify this article as work performed under the auspices of the U.S. Department of Energy.

Los Alamos Los Alamos National Laboratory
Los Alamos, New Mexico 87545

ANOMALOUS SURFACE IMPEDANCE IN REENTRANT FERROMAGNETIC SUPERCONDUCTORS

C.Y. Huang*, G. Kozlowski†, F. Mancini**, M.B. Maple††, H. Matsumoto†, C. E. Olsen*, H. Umezawa†, and J.P. Whithead†

* Los Alamos National Laboratory, Los Alamos, New Mexico 87545, U.S.A.

† University of Alberta, Edmonton, Alberta, Canada T6G 2J1

** Università di Salerno, Istituto di Fisica, 84100 Salerno, Italy

†† University of California, San Diego, La Jolla, California 92093, U.S.A.

For ErRh₄B₄, owing to the critical spin fluctuations just above T_S (>T_{C2}), the critical temperature at which surface ferromagnetism appears, the reciprocal penetration depth, λ^{-1} , decreases smoothly as T decreases toward T_S. For Er_{0.5}Ho_{0.5}Rh₄B₄, the decrease in λ^{-1} for T > T_{C2} is very small, and λ^{-1} decreases abruptly at T_{C2}.

ErRh₄B₄ has been investigated intensively. It becomes superconducting at T_{C1} = 8.7 K and reenters the normal state at T_{C2} = 0.8 K. The persistent current screens the long-wave components of the exchange interaction between rare earth magnetic moments, giving rise to the onset of a spin-periodic phase at T_P (>T_{C2}). (1,2) However, due to the reduction of the persistent current screening in the neighborhood of the sample surface, it has been shown theoretically (3) that uniform ferromagnetism within a magnetic penetration depth of the surface appears below T_S (>T_{C2}). In view of the fact that microwaves sample a volume near a surface determined by the penetration depth, λ , they would be expected to provide a useful probe in the search for this surface ferromagnetic state.

We have employed a microwave spectrometer with a sample (~0.5 mm x ~2 mm x ~6 mm) glued to one side of a rectangular TE₁₀₁ cavity operated at ~9.3 GHz. The temperature dependence of λ changes the effective size of the cavity, and, hence, gives rise to the shift of the resonance frequency of the cavity, allowing λ to be obtained simply by measuring the frequency shift of the cavity. (4) Our system is stable enough to measure a frequency shift as small as ~50 Hz, which enables us to measure λ to an accuracy of a few Å. In addition to ErRh₄B₄, for comparison, we have also investigated Er_{0.5}Ho_{0.5}Rh₄B₄ (T_{C1} = 7.35 K), because only its Ho magnetic moments order ferromagnetically at T_{C2} (2.70 K) (5,6) with a mean-field type of transition. Figures 1 and 2 show our results. The effects of the absence of spin fluctuations in Er_{0.5}Ho_{0.5}Rh₄B₄ is clearly displayed by the sharp drop in λ^{-1} at T_{C2}, indicating that T_S < T_{C2}. The gradual decrease of λ^{-1} in ErRh₄B₄ as T is decreased toward T_{C2} is consistent with the prediction that T_{C2} < T_P < T_S. In a non-magnetic superconductor the surface

impedance may be expressed as a simple relation involving the London penetration depth. (7) However, this formula is no longer valid in a magnetic superconductor owing to the effect of the spin fluctuations. For our calculation, we consider a semi-infinite superconductor filling the half-space z > 0, with a surface at z = 0. From the definition of the surface impedance, we define the effective penetration depth as (7)

$$\lambda(\omega) = \text{Re} \int_0^\infty dz b(\omega; z)/h(\omega; 0),$$

where b and h are the amplitudes of B and H, respectively.

By assuming that the effects of the pair breaking associated with the spin fluctuations and the polarization of the superconducting electrons induced through the A-f interaction are negligible, the London penetration depth $\lambda_L(T)$ may be computed using the standard BCS formula. Utilizing the Maxwell equations, we obtain in the paramagnetic state

$$\lambda(\omega) = \text{Re} (F/G) \quad (1)$$

where

$$F = \lambda_L(T) [\alpha_+ \alpha_- (\alpha_+ + \alpha_- + i\mu\lambda_L(T) + \eta\mu\lambda_L(T))]$$

$$G = n [\alpha^2 + \alpha_+ \alpha_- + \alpha^2 + i\mu\lambda_L(T) (\alpha_+ + \alpha_-) - n]$$

Here α_+ and α_- are given by $\alpha_\pm^2 = (\epsilon + d) - i\epsilon_0\gamma \pm [(\epsilon - d) - i\epsilon_0\gamma)^2 - 4\epsilon_0 d]^2 / 2d$, in which $n = 1 - i(\lambda^2(T)/d^2)$, $d = D/T_m \lambda_L^2(T)$, $\epsilon = T/T_m - 1$, $\epsilon_0 = 4\pi C/T_m$ and $\gamma = \omega\tau/4\pi$. T_m is the normal state Curie temperature, C the Curie constant, and D the stiffness constant. Near T_S, $\lambda(0) \propto (T - T_S)^{-1}$.

In Fig. 1 we present the theoretical values for the inverse of the characteristic length $\lambda(\omega)$ (solid curve) calculated from Eq. (1) for ErRh₄B₄ together with the experimental values (circles). The physical parameters used are

$T_m = 1.0$ K, $d_0 = 0.2529 \times 10^{-2}$, and $T_p = 0.85$ K. This gives a value for $\lambda_L(0) = 908$ Å. We also present the result of the static limit (dash-dotted curve) using a non-local kernel (3,8) together with the parameters $\kappa_B = 4$, $d_0 = 0.4254 \times 10^{-2}$ and $\lambda_L(0) = 749$ Å. The dashed curve is the BCS $\lambda^{-1}(T)$ with the parameter choice $\lambda_L(0) = 1184$ Å. We note that the effect of the spin fluctuations, as evidenced by the departure of the data from the BCS fitting, is quite pronounced, particularly at low temperatures.

Fig. 1. Penetration depth $\lambda(\omega)$ for ErRh_4B_4 .

In Fig. 2 the experimental data of $\lambda^{-1}(\omega)$ for $\text{Er}_{0.5}\text{Ho}_{0.5}\text{Rh}_4\text{B}_4$ are presented (circles) together with the BCS $\lambda^{-1}(T)$ (dashed curve) with the parameter choice $\lambda_L(0) = 1186$ Å. The experimental $\lambda^{-1}(\omega)$ shows a mild deviation from the BCS result above T_{C2} and a discontinuous jump to its normal value at $T = T_{C2}$, indicating that there is no additional magnetic transition above T_{C2} (i.e., $T_S < T_{C2}$). C is given by the mean value of the values obtained in the Er and Ho case. The theory (solid curve) yields $d_0 = 1.0$, which is very large, indicating that T_S is well below T_{C2} . For comparison, the theoretical curve for $\gamma = 0$ (i.e., $\omega = 0$) is also presented, and shows a small decrease at lower temperature due to the fluctuation effect. Therefore, the present analysis suggests that the apparent suppression of the spin fluctuations in the superconducting state is due to $T_S \ll T_{C2}$ and also to the effect of the spin relaxation time.

Fig. 2. Penetration depth $\lambda(\omega)$ for $\text{Er}_{0.5}\text{Ho}_{0.5}\text{Rh}_4\text{B}_4$.

In summary, the effect of the spin fluctuations can play an important role in determining the surface impedance in magnetic superconductors. In particular, the surface impedance of ErRh_4B_4 clearly manifests the effect of the critical fluctuations in the surface magnetization around T_{C2} . The surface impedance of $\text{Er}_{0.5}\text{Ho}_{0.5}\text{Rh}_4\text{B}_4$ exhibits a rather smooth dependence on the temperature down to T_{C2} , where it changes abruptly due to the first order magnetic transition, indicating the suppression of the spin fluctuations in the superconducting state.

ACKNOWLEDGEMENTS

This work was supported by the U. S. Department of Energy and NSERC, Canada.

REFERENCES

- (1) S.K. Sinha, G.W. Crabtree, D.G. Hinks, and H. Mook, Phys. Rev. Lett. 48 (1982) 950.
- (2) H. Matsumoto, H. Umezawa and M. Tachiki, Solid State Commun. 31, (1979); 157 E.I. Blount and C.M. Varma, Phys. Rev. Lett. 42 (1979) 1079.
- (3) A. Kotani, M. Tachiki, H. Matsumoto, and H. Umezawa, Phys. Rev. B23 (1981) 5960.
- (4) F.J. Rachford, Ph.D. Thesis, Case Western Reserve University 1975 (unpublished).
- (5) S. Mackawa, J.L. Smith, and C.Y. Huang, Phys. Rev. B22 (1980) 164.
- (6) H.A. Mook, W.C. Koehler, M.B. Maple, Z. Fisk, D.C. Johnston, and L.D. Woolf, Phys. Rev. B25 (1982) 372.
- (7) T.E. Faber and A.B. Pippard, Proc. Roy. Soc. (London) A31 (1955) 336.
- (8) F. Mancini and M. Fusco-Girard, Phys. Lett. 95A (1983) 447.