DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

Technical Progress Report

DOE/PC/89789--T12

for the

DE93 007621

Twelfth Quarter

(June 1, 1992 - August 31, 1992)

Control of Pyrite Surface Chemistry in Physical Coal Cleaning

by

R-H. Yoon and P.R. Richardson

**Virginia Center for Coal and Minerals Processing
Department of Mining and Minerals Engineering
Virginia Polytechnic Institute and State University
Blacksburg, Virginia 24061-0258**

Grant Number:

DE-FG22-89PC89789

Program Officer

**Richard Read
U.S. Department of Energy
Pittsburgh Energy Technology Center
Pittsburgh, Pennsylvania**

U.S. DOE patent clearance is not required prior to publication of this document

MASTER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

ABSTRACT

Over the past 10 years, much research has provided convincing evidence that one major difficulty in using froth flotation to separate pyrite from coal is the "self-induced" flotation of pyrite. Self-induced flotation was first defined in 1977 (Heyes and Trahar). It relates to the high flotability that is exhibited by many sulfide minerals in the absence of conventional collectors. Heyes and Trahar recognized that self-induced flotation only occurs in slightly oxidizing conditions. Reducing conditions produce sulfide mineral surfaces that are free of oxidation products and are nonfloatable; strong oxidizing conditions produce metal oxides on sulfide surfaces and also depress flotation.

Numerous studies have attempted to identify reactions that occur under moderate oxidizing conditions, which lead to self-induced flotation, and to identify the oxidation products. It is widely recognized that oxidation processes occur by mixed potential, corrosion type reactions, where the sulfides undergo anodic oxidation, and oxygen is simultaneously reduced to maintain overall charge neutrality; however, the identity of the hydrophobic entity is still debated.

During the past two report periods, it was established that:

- (1) freshly fractured pyrite surfaces immediately assume, at fracture, an electrode potential several hundred millivolts more negative than the usual steady state mixed potentials. Within minutes after fracture, the electrodes oxidize and reach higher steady state potentials. It was also shown, by photocurrent measurements, that a negative surface charge (upward band bending) already exists on freshly fractured pyrite, and

- (2) particle bed electrodes can be used to control the oxidation of pyrite and to precisely determine the electrochemical conditions where flotation occurs, or is depressed. By circulating the solution phase to an ultraviolet spectrometer, soluble products produced on pyrite by oxidation and reduction can be determined, e.g., HS^- was identified as a soluble cathodic reduction product.

These and other studies have provided considerable information concerning the anodic oxidation of pyrite. Much less is known about the mechanism and kinetics of oxygen reduction, the other half of the mixed potential reaction. To better understand pyrite oxidation kinetics and determine if oxygen reduction is rate determining, studies have been conducted during this report period on the oxygen reduction reaction with pyrite. In addition, to provide further support that the potential of particle bed electrodes can be controlled, the electro-adsorption and desorption of an organic surfactant was studied.

TABLE OF CONTENTS

ABSTRACT	i
TABLE OF CONTENTS	iii
LIST OF FIGURES	iv
OBJECTIVE	1
BACKGROUND	1
EXPERIMENTAL	4
Materials	6
Reagents	6
RESULTS AND DISCUSSION	6
Oxygen reduction on pyrite	6
Cathodic decomposition of pyrite	7
Distribution of potential in particle beds	11
CONCLUSIONS	13
REFERENCES	15

LIST OF FIGURES

Figure 1:	Current-voltage curves for a rotating coal-pyrite disc electrode (top); Current at a gold ring held at 0 V during a linear potential sweep from 0 to -1.0 V on the electrode (bottom).	5
Figure 2:	Current-voltage curves for a rotating coal-pyrite disc electrode (top); Current at a gold ring held at 0 V during a linear sweep from 0 to -1.0 V on the electrode (bottom).	8
Figure 3:	Cyclic voltammetry curve for a pyrite disc electrode at a sweep-rate of 20 mV/s (top); Current at a gold ring held at 0 V during the voltammetric cycle (bottom).	9
Figure 4:	Ultraviolet spectra of the solution phase of a particle bed electrode of pyrite as a function of potential. Potential stepped and held at the values indicated in the figure.	12
Figure 5:	Ultraviolet spectra of the solution phase of a particle bed electrode of pyrite as a function of potential.	14

OBJECTIVE

The overall objective of this research is to advance the fundamental understanding of the surface properties of coal-pyrite sufficiently to foster the development of advanced physical coal cleaning (APCC) processes. This objective is being met by: 1) investigating the mechanisms responsible for the inefficient rejection of coal-pyrite, and 2) developing schemes for improving the rejection of coal-pyrite based on information gathered from 1.

The specific objectives of the research in this report period were to:

1. determine the mechanism and kinetics of oxygen reduction on coal- and ore-pyrite,
2. determine if soluble products could be identified as reaction products on pyrite using ring-disc electrode techniques,
3. confirm, by the adsorption of an organic reagent, that the potential of particulate bed electrodes can be controlled so that the majority of particles are at the control potential.

BACKGROUND

It is now known (Young *et al.*, 1988; Trahar, 1984; Buckley *et al.*, 1985) that sulfides oxidize through several different pathways, as indicated by the following reactions:

The reactions have been written for basic solution assuming the metal hydroxide is the stable cation product. The metal hydroxide may be soluble under some conditions and metal oxides or metal-hydroxide complexes may also be formed.

With respect to the oxidation of pyrite, the relevant reactions may be written as:

with sulfate and thiosulfates formed at higher potentials.

With regard to the hydrophobicity of pyrite, reactions 6-7 produce two products: one an oxidation product of the cation that is expected to be polar (Finkelstein *et al.*, 1975) and hydrophilic; the other corresponding to an increase in sulfur in one of three different forms: elemental sulfur (reaction 3), excess sulfur in the surface region due to a metal-deficiency (reaction 4), and a polysulfide (reaction 5). It is known that sulfur (Wark and Cox, 1935) and sulfur-rich surfaces (Gaudin, Miaw, and Spedden, 1957) are highly hydrophobic. Each of these has been proposed as the hydrophobic entity responsible for self-induced flotation.

Dissolved molecular oxygen is the most important oxidant in a number of metallurgical processes, including flotation, and the kinetics of its reduction on sulfides has been the subject of a number of studies (Biegler, Rand and Woods, 1975, 1976; Ahmed, 1978). Biegler, Rand and Woods (1975), from studies of the kinetics of oxygen reduction on

mineral-pyrite, found that in acid solutions the overall reaction involved four electrons,

Hydrogen peroxide was detected in solution and analysis of the current-voltage curves indicated the reaction proceeded via,

They also determined that the first electron step

was rate determining.

The presence of hydrogen peroxide, as an intermediate in oxygen reduction, is consistent with reports by Jones and Woodcock (1978) that hydrogen peroxide reacts with xanthates to form perxanthate ($ROCS_2O^-$) and that perxanthate is present in industrial concentrators. This is also consistent with observations of perxanthate in microflotation cells when sulfide minerals are potentiostated at negative potentials (Richardson *et al.*, 1984).

Coal-pyrite has been reported to be much more active in its oxidation than ore-pyrite. This study to compare oxygen reduction on coal- and ore-pyrite is an attempt to determine if it is the anodic oxidation reaction, the cathodic oxidation reaction, or both, that causes the increased activity of pyrite.

A rotating ring-disc technique was used to study the oxygen reduction reaction. Another objective of the research was to determine if the ring-disc could be used to detect soluble oxidation products being produced on pyrite by reactions 9-11.

EXPERIMENTAL

A rotating ring-disc electrode was used to study the reduction of oxygen on pyrite. Rotating-disc and ring-disc electrodes provide a hydrodynamic system in which the mass transfer of reactants to or from an electrode can be controlled and analytically calculated by solving the steady state diffusion equations. The maximum or limiting current to a rotating disc electrode is given by the Levich equation:

$$I_L = 0.62nFD^{2/3}\nu^{-1/6}C_b\omega^{1/2} \quad (12)$$

where n = number of electrons in the rate determining step; D = the diffusion constant for the relevant species undergoing oxidation or reduction; ν = the kinematic viscosity; C_b = the concentration of the electro-active species in the bulk solution; and ω = rotation rate of the electrode. This equation essentially expresses the way in which the stagnant boundary layer at the surface of a rotating electrode thins with increasing rotation rate. The limiting current I_L corresponds to the current when all of the species reaching the surface are reduced.

The ring electrode, usually constructed of a noble metal, is concentric with the disc and separated from the disc by a small gap. Convective mass transfer in the rotating disc system is such that soluble ions produced by an oxidation or reduction reaction at the disc convect parallel to the disc surface and the ring. By holding the ring at different potentials than the disc, oxidation (or reduction) products at the disc can be reduced (or oxidized) at the ring.

Ring-disc electrodes were made using both coal- and ore-pyrite. The ring was constructed from gold and the assembly was mounted using a non-conducting epoxy. A Pine RDE-4 double potentiostat and Pine rotating ring-disc assembly were used for rotating the electrodes. The cylindrical pyrite electrodes were constructed using diamond core drills and

Solution saturated with oxygen, pH 9.2

Figure 1: Current-voltage curves for a rotating coal-pyrite disc electrode (top); Current at a gold ring held at 0 V during a linear potential sweep from 0 to -1.0 V on the electrode (bottom).

contacted with a copper electrical lead. The electrode surfaces were abraded and polished using successively finer grades of silicon carbide paper, from 240 to 600 grade. The samples were cleaned with acetone, distilled water and hydrochloric acid before each experiment.

Materials

Large specimens of mineral, originating from Huanzala, Peru, were obtained through Ward's Scientific Co. The coal pyrite was from "sulfur balls" received from Sichuan, China. The sulfur balls were visually composed of relatively pure pyrite.

Reagents

The buffer solutions used in all tests were prepared using reagent grade chemicals with the following compositions:

pH 4.6; 0.5 M CH_3COOH and 0.5 M CH_3COONa

pH 6.8; 0.05 M KH_2PO_4 and 0.0224 M NaOH

pH 9.2; 0.05 M $\text{Na}_2\text{B}_4\text{O}_7$.

RESULTS AND DISCUSSION

Oxygen reduction on pyrite

Figure 1 shows linear potential sweeps from 0 to -1.0 V on a coal-pyrite disc electrode at pH 9.2 for rotation speeds of 1000 to 4000 rpm in a solution saturated with oxygen. At the beginning of the sweeps, the current is controlled by the electron transfer process (activation control) and is only slightly dependent on rotation rate. Plots of I_L vs. square root of the rotation speed are linear, as predicted by the Levich equation. Fig. 1 (bottom) shows the ring currents when the ring is held at 0 V during the linear sweeps on the

disc. The absence of a ring-current from 0 to -0.9 V indicates that the reduction of oxygen proceeds to water by the overall 4-electron process:

i.e. there is no intermediate soluble species during the oxygen reduction process.

The slight ring currents observed at potentials < -0.9 V are due to the cathodic decomposition of pyrite and will be discussed later.

Figure 2 shows similar linear sweeps from 0 to -1.0 V on a coal-pyrite electrode at pH 4.6 in a solution saturated with oxygen. In the activation controlled region, i.e., before the limiting currents are reached, there are two distinct cathodic reduction processes occurring, as evidenced by the change in slope of the curves at about -0.3 V. The ring, held at 0 V during the potential sweep on the disc, shows that an intermediate is produced beginning at about -0.3 V. This is attributed to hydrogen peroxide produced on the disc by the reaction:

followed by its re-oxidation on the ring. When the limiting current is reached, the overvoltage is sufficiently large that the intermediate hydrogen peroxide is also reduced at the disc to OH^- and hence the ring current drops. At the more negative potentials, cathodic decomposition of pyrite again occurs, and a distinct ring current is produced by a soluble product of pyrite decomposition. The data for ore-pyrite is currently being analyzed.

Cathodic decomposition of pyrite

Fig. 3 shows a voltammetry curve on pyrite in nitrogen sparged solution at pH 9.2.

Solution saturated with oxygen, pH 4.6.

Figure 2: Current-voltage curves for a rotating coal-pyrite disc electrode (top); Current at a gold ring held at 0 V during a linear sweep from 0 to -1.0 V on the electrode (bottom).

Nitrogen sparged solution, pH 9.2.

Figure 3: Cyclic voltammetry curve for a pyrite disc electrode at a sweep-rate of 20 mV/s (top); Current at a gold ring held at 0 V during the voltammetric cycle (bottom).

The anodic peak at -0.2 V has been attributed to the oxidation of pyrite to $\text{Fe}(\text{OH})_3$; the cathodic peak at -0.6 V to the reduction of the $\text{Fe}(\text{OH})_3$ to $\text{Fe}(\text{OH})_2$. In oxygen saturated solutions, currents due to these reactions are negligible when compared to the oxygen reduction current, thus these processes are not observable in Figs. 1 and 2. Figs. 1-3 show an additional process occurring at the more negative potentials. Fig. 3 also shows the ring current observed with the ring held at 0 V during a cyclic voltammetry sweep on the disc from 0 to -1.0 back to 0 V. A ring current is observable at -0.3 V which can be attributed to re-oxidation of the $\text{Fe}(\text{OH})_2$, produced at the disc on the negative sweep, back to $\text{Fe}(\text{OH})_3$ at the ring. At the most negative potentials, a further increase in ring current is observed. This can be attributed to oxidation at the ring of the reduction product produced at the disc at potentials < -0.9 V. The most likely reaction is:

Interestingly, on the anodic sweep, an additional oxidation current is observed on the ring. This implies that there is a soluble oxidation product produced at the disc on the positive going sweep, and that this oxidation product can be further oxidized at the ring. It is believed the reactions are:

Essentially, iron is produced on the pyrite disc electrode by cathodic decomposition at potentials < -0.9 V; during the return anodic scan, soluble ferrous hydroxide, or a ferrous-hydroxy complex is produced by reaction 16, which is then convected to the disc and undergoes further oxidation to ferric hydroxide.

It should be noted that a number of flotation studies on pyrite have been conducted at cathodic potentials where pyrite decomposes by reaction 15. Such negative potentials irreversibly alter the surface of pyrite so that the subsequent flotation behavior is unlikely to represent that of the mineral.

Distribution of potential in particle beds

In a previous project report, measurements on particle beds were presented and discussed. Voltammetry curves showed some of the same features as voltammograms on single mineral electrodes with the exception that the current peaks observed on bed electrodes are slightly broader than on single mineral electrodes. This is expected for particle bed electrodes because of the resistance associated with particle-to-particle contact. Thus, when a current flows, a part of the voltage represents contact resistance, broadening the current peaks.

During this report period, the adsorption characteristics of a known electro-active surfactant on pyrite was studied to determine if the particles were at the control potential. Bed currents were minimized by potentiostating the electrodes at constant potentials, rather than sweeping the potential as in the previous studies. Sodium ethyl xanthate was chosen as the electro-active species, because it is known that this common flotation collector only interacts with pyrite at potentials equal to or greater than the reversible potential for the xanthate/dixanthogen couple ($2X^- = X_2 + 2e^-$). Xanthates have well-defined chromophores in the ultraviolet region and the solution was monitored with a spectrometer. Thus, rather than study the currents on the particulate bed-electrode, the xanthate concentration in solution was monitored. Figure 4 shows the absorbance at 301 nm by ethyl xanthate obtained by holding the pyrite bed at -0.2 V when xanthate was added, then stepping and holding the

Surfactant, sodium ethyl xanthate, pH 9.2.

Figure 4: Ultraviolet spectra of the solution phase of a particle bed electrode of pyrite as a function of potential. Potential stepped and held at the values indicated in the figure.

potentials at positive values. The reversible potential for the xanthate dixanthogen couple is between 0 and 0.1 V, and the appearance of dixanthogen is indicated by the slope change between these limits. No dixanthogen is formed until the potential reaches 0.1 V, establishing that the potential of the particulate bed electrode has a narrow distribution under low current conditions.

Figure 5 shows the effect of stepping the potential from the region where dixanthogen is adsorbed on pyrite (curve labeled oxidized) to -0.7 V, where dixanthogen is desorbed (curve labeled reduced). The spectrum is that of xanthate ion in the solution phase. Dixanthogen is reduced back to xanthate ions, further confirming that the potential of the particle bed can be controlled by passing a current to the bed.

CONCLUSIONS

1. Hydrogen peroxide is detected as a product of oxygen reduction on coal pyrite electrodes at pH 4.6, but not at pH 9.2.
2. Pyrite undergoes cathodic decomposition at potentials < -0.9 V at pH 9.2 and this irreversibly alters the surface of pyrite. Studies relevant to flotation should probably use potentials more positive than this value.
3. Studies of the oxidation of an organic surfactant on particulate beds of pyrite under potentiostatic conditions establish that most of the particles in the bed experience the applied potential.

Surfactant, sodium ethyl xanthate, pH 9.2.

Oxidized: xanthate oxidized to dixanthogen;

Reduced: dixanthogen reduced at a more negative potential

Original; original xanthate concentration before oxidation.

Figure 5: Ultraviolet spectra of the solution phase of a particle bed electrode of pyrite as a function of potential.

REFERENCES

- Trahar, W.J., 1984, "The influence of pulp potential in sulfide flotation," in *Principles of Mineral Flotation*, (eds. M.H. Jones and J.T. Woodcock), The Australasian Institute of Mining and Mineral Processing, Victoria, Australia, 117-136.
- Finkelstein, N.P., Allison, S.A., Lovell, V.M., and Stewart, B.V., 1975, "Natural and induced hydrophobicity in sulfide mineral systems," in *Advances in Interfacial Phenomena of Particulate/Solution/Gas Systems, Applications to Flotation Research*, Am. Inst. Chem. Eng. Symp. Ser. No. 150, 71: 165-175.
- Young, C.A., Woods, R., and Yoon, R.-H., 1988, "A voltammetric study of chalcocite oxidation to metastable copper sulfides," in *Proc. Electrochemistry in Mineral and Metal Processing II*, (eds. P.E. Richardson and R. Woods), The Electrochemical Soc. Inc, 88-21: 3-17.
- Woods, R., 1971, "The oxidation of ethyl xanthate on platinum, gold, copper, and galena electrodes: Relation to the mechanism of mineral flotation," *Journal of Physical Chemistry*, 75(3): 354-362.
- Buckley, A.N., Hamilton, I.C., and Woods, R., 1985, "Investigation of the surface oxidation of sulphide minerals by linear potential sweep voltammetry and X-ray photoelectron spectroscopy," in *Flotation of Sulphide Minerals*, (ed. K.S.E. Forssberg), Elsevier Science Publishers, B.V.
- Heyes, G.W., and Trahar, W.J., 1977, "The natural floatability of chalcopyrite," *Int. J. Min. Proc.*, 4: 317-354.
- Gaudin, A.M., Miaw, H.L., and Spedden, H.R., 1957, "Native floatability and crystal structure," *Proc. 2nd Intern. Cong. Surf. Activity*, (ed. J.H. Schulman), 3: 202-219,

Butterworth & Co.

Wark, I.W. and Cox, A.B., 1935, "The physical chemistry of flotation, V. Flotation of graphite and sulphur by collectors of the xanthate type," *J. Phys. Chem.*, **39**: 551-559.

Biegler, T., Rand, D.A.J., and Woods, R., 1975, "Oxygen reduction on sulphide minerals Part I. Kinetics and mechanisms at rotated pyrite electrodes," *J. electroanal. Chem. Interfacial Electrochem.*, **60**: 151-162.

Biegler, T., Rand, D.A.J., and Woods, R., 1976, "Oxygen reduction on sulphide minerals Part II. Relations between activity and semiconducting properties of pyrite electrodes," *J. electroanal. Chem. Interfacial Electrochem.*, **70**: 265-275.

Ahmed, S.M., 1978, "Electrochemical studies of sulphides, I. The electro-catalytic activity of galena, pyrite and cobalt sulphide for oxygen reduction in relation to xanthate adsorption and flotation," *Int. J. Min. Proc.*, **5**: 163-174.

Ahmed, S.M., 1978, "Electrochemical studies of sulphides, II. Measurements of the galvanic currents in galena and the general mechanism of oxygen reduction and xanthate adsorption on sulfides in relation to flotation," *Int. J. Min. Proc.*, **9**: 175-182.

Jones, M.H., and Woodcock, J.T., 1978, "Perxanthates - a new factor in the theory and practice of flotation," *Int. J. Min. Proc.*, **5**: 285-296.

Richardson, P.E., Stout, III, J.V., Proctor, C.L., and Walker, G.W., 1984, "Electrochemical flotation of sulfides: chalcocite - ethyl xanthate interactions," *Int. J. Min. Proc.*, **12**: 73-93.

END

**DATE
FILMED**

3 / 12 / 93