Final Performance Report

on

**DIMENSIONAL, MICROSTRUCTURAL AND COMPOSITIONAL
STABILITY OF METAL FUELS**

Contract #DE-FG07-88ER12814

by

A.A. Solomon and M.A. Dayananda

Schools of Nuclear and Materials Engineering

Purdue University

West Lafayette, IN 47907

Submitted to

Frederick Sienko

U.S. Department of Energy

Chicago Field Office

9800 S. Cass Avenue

Argonne, IL 60439

March 15, 1993

**RECEIVED
APR 08 1993
OSTI**

MASTER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED *EB*

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

TABLE OF CONTENTS

I. Overview	1
II. Fuel Compressibility	2
III. Sodium Intrusion	3
IV. Fuel-Cladding Interdiffusion Studies	3
V. Lanthanide-Cladding Interdiffusion.....	5
VI. Appendices	7
A. Hot Isostatic Pressing of U-10Zr by Coupled Boundary Diffusion/Power-Law Creep Cavitation - Part I	
B. Hot Isostatic Pressing of U-10Zr by Coupled Boundary Diffusion/Power-Law Creep Cavitation - Part II	
C. Liquid Sodium Intrusion into Porous U-10Zr Fuel Alloy by Differential Capillarity	
D. Interdiffusion Between U-Zr Fuel and Selected Fe-Ni-Cr Alloys	
E. Interdiffusion Between U-Zr Fuel vs. Selected Cladding Steels	
F. Interdiffusion of Cerium in Fe-Base Alloys with Ni or Cr	

I. Overview

The projects undertaken in this investigation were intended to address two major and traditional areas of concern for metal-fueled fast reactors: (1) the metallurgical compatibility of the fuel and its fission products with the stainless steel cladding, and (2) the effects of the extensive porosity development in the fuel on fuel/cladding interactions, and on sodium penetration in the fuel.

All of these projects have been brought to successful conclusion and have either appeared in archival publications, or are in various stages of publication. In addition, the work has been presented at the 1990, 1992, and 1993 TMS-AIME meetings, at the 1992 American Nuclear Society meeting, and at the 1992 Powder Metallurgy World Congress. Three Ph.D. students (Sean McDeavitt, Dennis Keiser, and Weijun Liu) and one M.S. student (Peter Tortorici) have completed or are in progress of completing their degrees.

This project has also led to close interactions with colleagues at Argonne National Laboratory involved in the Integral Fast Reactor Program. Both Prof. A.A. Solomon and M.A. Dayananda have participated in annual programmatic review meetings at ANL, and have received ongoing support and the conclusion of the present program.

The technical results are described in detail in the appendices, and introductory descriptions are given in the following sections.

II. Fuel Compressibility

Metallic nuclear fuels swell primarily by a combination of anisotropic irradiation growth which causes grain boundary "tearing" at low temperatures, and by gaseous fission product precipitation into bubbles at higher temperatures. These phenomena produce a very large swelling component that must be accommodated in the design and performance of the fuel. In the Integral Fast Reactor or IFR fuel design, a large sodium-filled gap is provided between the fuel and cladding that permits heat removal as well as allowing sufficient volume for expansion. The aim is to have the fuel porosity interconnect at about the time the fuel contacts the cladding, so that the gas stabilizing the porosity can be released. Subsequent swelling can then be offset by hot-pressing of the fuel.

To study the ability of porous fuel to hot-press, a special powder metallurgy technique was developed to simulate porous U-10Zr fuels. Hot-pressing experiments were carried out in the $\alpha + \delta$ and γ phase fields as described in **Appendix A**. The results provide the only primary data available on this important phenomenon in metallic fuels, and indicate that the previously assumed models used in fuel modelling codes should be modified. Under the conditions studied, the process appears to follow a coupled mechanism of dislocation motion and vacancy transport as described in **Appendix B**. However the work raises a cautionary note because the compressibility of U-10Zr fuel appears to be quite restricted especially at low temperatures. The inability of the fuel to compress readily may be even more limited at high burnup when the solid fission products begin to occupy the available porosity. Thus the issue of fuel compressibility is not resolved.

III. Sodium Intrusion

Using our technique of producing porous U-10Zr fuel, we were able to address the considerable uncertainty in fuel thermal conductivity because of the uncertainty of the degree of sodium penetration into the porous fuel. Contrary to previous dissolution experiments conducted at Argonne National Laboratory, our results in **Appendix C** indicate virtually complete penetration of sodium into the available porosity. A new theory is developed to rationalize the gas release and subsequent penetration of sodium using the notion of "differential capillarity" caused by variations in pore sizes. At sufficiently high temperatures, sodium "wets" U-10Zr causing capillary attraction into all pores. However, when pores are of different sizes, the attraction into small pores is sufficiently strong that sodium as well as the entrapped gas is forced out of the larger pores. The theoretical criterion developed for gas release and the porosity size distributions in the specimens studied determined by mercury intrusion porosimetry are consistent with the amount of sodium that penetrated the specimens. Critical experiments performed on specimens with uniform drilled holes verified that no gas is released when pores are of uniform size.

IV. Fuel-Cladding Interdiffusion Studies

As part of interdiffusion studies relevant to fuel-cladding compatibility in the Integral Fast Reactors, systematic interdiffusion studies were carried out at 700°C with solid-solid diffusion couples assembled with a binary U-23 Zr (at.%) alloy fuel bonded to cladding alloys of selected compositions. The composition of the cladding alloys included pure Fe,

pure Ni, binary Fe-20Cr, Ni-16Cr, Fe-10Ni alloys and a ternary Fe-16Ni-10Cr alloy. The couples were examined and analyzed by SEM-EDAX analysis. These studies have identified the formation of several intermetallic phases such as $U_2(Ni,Fe)$, UNi_2 , U_5Ni_7 , $(U,Zr)Ni_2$, $U_6(Ni,Fe)$, $(Zr,U)_4Ni_5$, $(Zr,U)_2Ni$ in the diffusion zone of couples with Ni-base cladding alloys. A Zr-rich layer was observed to form as an intermediate diffusion layer in the couple assembled with Fe-16 Cr cladding alloy. The major intermetallic phases identified in the Fe-16 Ni-10Cr/fuel couple correspond to $U(Fe,Ni,Cr)_2$, $(Zr,U)(Fe,Ni,Cr)_2$, $U_6(Fe,Ni)$, $(Zr,U)_2(Fe,Ni)$ and are similar to those that develop in the Fe-10Ni/fuel and Fe-20Cr/fuel couples. These studies have clearly demonstrated that the diffusion layers that form on the cladding side of the couples are dictated by the interactions of Ni, Fe and Cr with U, while those that develop on the fuel side are governed by the type of intermetallics that can form between Zr and the cladding elements. The fuel/cladding interdiffusion structures can be understood in the framework of diffusion paths and phase diagrams. Average effective interdiffusion coefficients were also calculated over specific regions of the diffusion zone of selected diffusion couples. The details of this investigation are described in detail in the attached manuscript (**Appendix D**) entitled "Interdiffusion between U-Zr Fuel and Selected Fe-Ni-Cr Alloys" which is currently in print in the Journal of Nuclear Materials.

Interdiffusion studies were also made with a second set of diffusion couples assembled with the U-23 Zr fuel and selected commercial cladding steels, such as 316 stainless, D9, and HT9 and annealed at 700°C for 4 days. The diffusion layers and phases

developed in these couples were found to be consistent with those observed for the couples assembled with binary Fe-Ni, Fe-Cr, Ni-Cr and ternary Fe-Ni-Cr alloys. These studies have identified the beneficial role of Cr and shown that minimal interdiffusion occurs between fuel and cladding in the absence of Ni. HT9 is superior to D9 and 316 in fuel-cladding compatibility. The details of this study are presented in the attached manuscript (**Appendix E**) entitled "Interdiffusion between U-Zr Fuel

and vs. Selected Cladding Steels". This manuscript is submitted to Metallurgical Transactions for publication.

V. Lanthanide-Cladding Interdiffusion

One of the concerns in the IFR program deals with the interdiffusion behavior of lanthanide fission products (Ce,Nd,La,Pr) in the fuel and their interactions with the cladding alloys. At high burn-ups the lanthanide elements interdiffuse toward the fuel-cladding interface and interact with cladding alloys such as 316 stainless, D9 and HT9. Since the major components of the cladding alloys are Fe, Ni and Cr, the lanthanide interdiffusion into the cladding can develop low melting diffusion structures containing lanthanide intermetallics and adversely affect the fuel-cladding compatibility and the cladding life.

In order to explore the diffusion structure development as well as to calculate the interdiffusion data for lanthanide/cladding assemblies, two series of interdiffusion experiments were carried out with solid-solid diffusion couples. In the first series (Series I), couples were assembled with disks of Ce and pure Ni, pure Fe, and binary Fe-Ni, Fe-Cr and Ni-Cr alloys of selected compositions. The concentration of Ni in the Fe-rich alloys are selected in the range of 10-16 at.%, while that of Cr was in the range of 10-20 at.%. The alloys were homogenized at 1100°C and cut into disks. The second series of couples (Series II) was assembled with disks of pure Ce, and cladding steels, such as 316, D9 and HT9.

All couples were annealed in evacuated quartz capsules at 425°C for 4 days. The annealed couples were examined metallographically and analyzed for concentration profiles and diffusion structure information by SEM-EDAX techniques. Average effective interdiffusion coefficients of the individual components were evaluated over selected regions of the diffusion zones of selected couples. Intrinsic diffusion coefficients were also determined for phases such as Ni_3Ce_7 and Fe_2Ce developed in some of the couples. The diffusion structures were found to be consistent with phase diagrams and described with the aid of diffusion paths. The details of this study are described for selected couples in the attached manuscript (**Appendix F**) entitled "Interdiffusion of Ce in Fe-base Alloys with Ni or Cr".

APPENDIX A

Hot Isostatic Pressing of U-10Zr by Coupled Boundary
Diffusion/Power-Law Creep Cavitation - Part I

HOT ISOSTATIC PRESSING OF U-10Zr BY COUPLED BOUNDARY DIFFUSION/POWER-LAW CREEP CAVITATION - PART I

Sean M. McDeavitt and A.A. Solomon

*School of Nuclear Engineering, Purdue University,
West Lafayette, IN 47907, USA.*

Abstract

U-10Zr is a nuclear fuel proposed for use in the Integral Fast Reactor (IFR). Possible mechanical interaction between the swelling metal fuel and its cladding which may cause cladding failure is a safety and operational issue. Specimens prepared from uranium and zirconium powders (metal and hydride) were sintered in a purified argon atmosphere to entrap gas and simulate fission gas bubbles in irradiated fuel. The specimens were hot isostatically pressed to study the fuels' densification under external pressure. Hot-pressing was not detected at 600°C, but U-10Zr hot-presses at 700°C by a coupled creep/grain boundary diffusion mechanism. The measured stress dependence ($n=3.4\pm0.3$) indicates a dislocation creep mechanism and the measured activation energy (187 ± 10 KJ/mole) agrees with the reported value for grain boundary diffusion of γ -U. This is contrary to observations for UO₂ and other materials where hot-pressing is controlled by diffusion.

1. Introduction

Uranium - 10 wt. % zirconium (U-10Zr) is used as a driver fuel in the Experimental Breeder Reactor-II as part of the Integral Fast Reactor (IFR) program developed by Argonne National Laboratory^[1]. Metal nuclear fuels were previously investigated and rejected for breeder reactors due in part to fission gas induced swelling at relatively low burnup which caused severe Fuel-Cladding Mechanical Interaction (FCMI) and cladding rupture under normal operating conditions^[1]. IFR fuel pins are designed to accommodate swelling and gas release by providing a fuel/cladding gap filled with sodium and an enlarged gas plenum above the fuel which allows the fuel to swell and release its fission gas before coming into contact with the cladding^[1]. Swelling in uranium and uranium alloy fuels is generally assumed to be caused by accumulated fission products (primarily gases) and anisotropic irradiation growth which induces "tearing"^[2].

After cladding contact, which occurs at 1-2 atom percent burnup^[1], the compressibility of the highly porous fuel becomes an important safety issue, since it represents the fuels' ability to relax fuel/cladding contact stresses which arise from continued fuel swelling. Since the target burnup of the IFR exceeds 20 atom percent, this situation is potentially significant over the majority of the fuel's lifetime. FCMI is unavoidably present when fuel swelling is constrained by the current non-swelling cladding materials, and FCMI-induced strains are observed in the U-10Zr fuel rods used in EBR-II after relatively low burnup^[2]. Fission product accumulation and precipitation in the available porosity will impair the fuels compressibility at high burnup^[2]. Also, rapid temperature rises during reactor transients may generate large contact stresses due to differences in fuel/cladding thermal expansion and gas pressure increases that represent important safety issues.

To address these issues, hot-isostatic pressing (HIP) experiments have been carried out on unirradiated U-10Zr using an experimental procedure previously developed^[3] to investigate swelling and HIP in UO_2 ^[4-6] and other materials^[7-9]. The purpose of the experiments was to identify and quantify the rate-controlling HIP mechanism in U-10Zr. Pure, unirradiated material

was used to avoid ambiguities which could arise from solid fission product accumulation and non-equilibrium defect structures, as well as the difficulties involved with handling irradiated material.

HIP and swelling of porous material at elevated temperatures are stress and temperature dependent phenomena which, to a first approximation, are opposing directions of the same process if they do not involve irreversible fracture. Gas filled pores shrink or grow in response to non-equilibrium pressure conditions. It has been shown that models developed for creep cavitation under uniaxial stress are even more appropriate for HIP and swelling where the stress is hydrostatic, and excellent agreement between theory and experiment is obtained if the internal pore pressure and pore surface energy are included^[10]. A comprehensive review of several creep cavitation mechanisms has been presented by Svensson and Dunlop^[11].

This present paper will summarize the experimental procedures and HIP results for the sintered U-10Zr specimens. A subsequent paper (Part II) will discuss the comparison of the experimental results with theoretical creep cavitation models to identify and quantify the dominant U-10Zr HIP mechanism. These experiments and the results obtained are useful for the development and validation of fuel performance models for metal nuclear fuels, especially in the IFR program.

1.1 Creep cavitation models

Creep cavitation models may be classified into two categories based upon the invoked rate-controlling mechanism: 1) grain boundary diffusion-controlled cavitation, and 2) creep deformation-controlled cavitation.

Hull and Rimmer^[12] modeled diffusion-controlled creep cavity growth by defining the rate-controlling process as the stress-directed motion of vacancies from grain boundaries to cavity surfaces via grain boundary diffusion. The grain boundary is assumed to act as a perfect sink for atoms which move from uniformly sized and spaced cavities and are distributed uniformly over the grain boundary. Diffusion-controlled creep cavitation models have been presented, modified, and

improved by several authors^[11,13-18], with the model of Speight and Beere^[15] considered to “best represent” this phenomena^[19].

The Speight-Beere formulation^[15] for volumetric growth of individual cavities during tensile creep may be written as

$$\left(\frac{dV}{dt}\right)_{\text{pore}} = \frac{2\pi \Omega D_b \delta_b}{kT f\left(\frac{r_p}{\lambda}\right)} \left[\sigma - p + \frac{2\gamma}{r_p} \right] \quad (1)$$

where D_b is the boundary diffusion coefficient, δ_b is the boundary width, N_v is the pore number density, Ω is the atomic volume, k is Boltzman's constant, and T is temperature. The term in brackets represents the "driving force", F , for the process, where σ is the applied tensile load, p is the internal pore pressure, γ is the surface energy, and r_p is the pore radius. F is related to the stress-induced chemical potential difference between the pore surface and the grain boundary, according to Herring^[20]. The geometric "structure" factor, $f\left(\frac{r_p}{\lambda}\right)$, is a function of the pore size to spacing ratio given by

$$f\left(\frac{r_p}{\lambda}\right) = - \left[\ln\left(\frac{r_p}{\lambda}\right) + \frac{1}{4} \left(1 - \left(\frac{r_p}{\lambda}\right)^2 \right) \left(3 - \left(\frac{r_p}{\lambda}\right)^2 \right) \right] \quad (2)$$

where λ is the cavity half-spacing in the boundary. Assuming that all strain comes from the pore volume change during HIP, the pore volume rate of change in Equation 1 may be translated to a total linear strain rate according to^[10]

$$\dot{\epsilon} = \frac{1}{3} N_v \left(\frac{dV}{dt}\right) \quad (3)$$

where N_v is the cavity number density. Combining Equations 1 and 3, and substituting the external pressure, P , for the applied stress, yields the strain rate for diffusion-controlled HIP as

$$\dot{\epsilon}_{\text{diffusion}} = \frac{2\pi}{3} \frac{N_v \Omega D_b \delta_b}{kT f\left(\frac{r_p}{\lambda}\right)} \left[P - p + \frac{2\gamma}{r_p} \right] \quad (4)$$

Deformation-controlled cavity growth during creep has also been modeled by several authors^[21-23]. For these models, diffusion is considered unable to relax the applied load because either the grain boundary diffusivity is limited or the cavities do not reside on the grain boundary. The growth rate is therefore controlled by the creep of the material surrounding the cavity. This situation is not commonly observed for nuclear fuels^[10].

Beere and Speight^[21] proposed that both diffusion-controlled and deformation-controlled cavitation mechanisms operate during creep, and that the overall cavitation behavior is defined by the coupling of both mechanisms. A similar mechanism was proposed by Edward and Ashby^[24], but their model was applied toward the estimation of the time to failure and not toward the estimation of the cavity growth rate. The model of Beere and Speight^[21], Fig. 1, divides the grain boundary into two regions. The unit cell radius is the cavity half-spacing, λ , and b is the radius of Region I where grain boundary diffusion deposits atoms according to the Hull-Rimmer mechanism. In Region II, grain boundary diffusion is assumed negligible and creep generates compatible strains to maintain compatibility with Region I. Beere and Speight^[21] determine b from the solution of a complex system of physical equations, but they avoid the solution of the equations by suggesting that the rate of cavity volume change may be approximated by the direct sum of diffusion-controlled and deformation-controlled limiting solutions. This approximation has been discounted as an over-simplification by several authors^[19,25,26].

Chen and Argon^[19] derived a simple equation for the coupled cavitation mechanism based upon the displacement induced in Region I by the deposition of atoms. Their formulation matches very well with the cavity growth rate calculations by finite element analysis of Needleman and Rice^[26], and the exact solution of Beere and Speight^[21] based on the complex system of

equations^[19]. The size of the diffusion zone, designated as Λ in Fig. 1, may be directly estimated from the characteristic diffusion length, defined by Rice^[25], which is given by

$$\Lambda = \left(\frac{D_b \delta_b \Omega \sigma_\infty}{kT \dot{\epsilon}_\infty} \right)^{1/3} \quad (5)$$

where σ_∞ and $\dot{\epsilon}_\infty$ represent the far-field creep stress and creep rate, where $\dot{\epsilon}_\infty$ is equivalent to the material creep behavior, $\dot{\epsilon}_c$, which has the empirical form

$$\dot{\epsilon}_c = B \sigma^n \quad (6)$$

where B is an empirical constant, σ is the driving stress for creep, and n is the creep stress dependence. Λ may be used to distinguish which cavitation mechanism is dominant^[19] using the following criteria: 1) If $\Lambda > \lambda$, then diffusion is uninhibited in the grain boundary and a diffusion-controlled mechanism dominates, 2) If $\Lambda < r_p$, then diffusion is extremely limited and creep deformation dominates cavitation.

The cavity volume change for a coupled mechanism is then given as^[19],

$$\dot{\epsilon}_{\text{coupled}} = \frac{2\pi}{3} \frac{N_v \Omega D_b \delta_b}{kT f\left(\frac{r_p}{b}\right)} \left[P - p + \frac{2\gamma}{r_p} \right] \quad (7)$$

The difference between Equations 4 and 7 is the structure function. The form of $f\left(\frac{r_p}{b}\right)$ is still given by Equation 3, but $b (= \Lambda + r_p)$ is substituted for the cavity spacing, λ . Because of the strong stress dependence of Λ , the structure function and Equation 7 also have strong stress dependencies, in contrast to diffusion-controlled models, which have a linear stress dependence.

It should also be pointed out that all of the models described above require the assumption of uniform cavity sizes and spacings so that a single representative volume element can be analyzed. While such models may capture the basic physics, some important interactions are

omitted if pore sizes and spacings can vary. If sizes vary, diffusional fluxes from cavity to cavity cause coarsening^[27] which can greatly increase rupture time. For non-equilibrium cavities or pores ($F \neq 0$), elastic interactions can give rise to cavity repulsion^[27], and for variable spacings, plastic deformation may play an increasing role for widely-spaced pores^[28]. Thus the simplified models should only be expected to give order-of-magnitude agreement with measurements for most real microstructures.

1.2 Experimental background

The technique used for studying the behavior of non-equilibrium pores^[3] has been used to study the swelling behavior of Ni^[7], ZnO^[8], and UO₂^[5,6], as well as the HIP of UO₂^[4] and AlO₃^[9]. Experimental samples are produced by sintering powder compacts under pressure beyond pore closure to entrap gas. By changing the ambient external pressure, a driving force for HIP or swelling may be generated.

In previous studies^[7,8], the time-dependent strain rate behavior for HIP and swelling was characterized by the relation

$$\dot{\epsilon} \sim t^{-m} \quad (8)$$

where m is a constant. The m -value for *swelling* is predicted to be $m=2/5$ using the Hull-Rimmer model^[10], assuming that the internal pressure dominated the driving force so the external pressure and surface tension may be neglected. Previous swelling experiments on Ni and ZnO exhibit pore interconnection and eventually gas release at high driving forces, but at lower driving forces, the strain rates are observed to decrease with a well-defined time dependence shown to be^[7,8,10]

$$\dot{\epsilon} \sim t^{-1/3}, \quad (9)$$

in reasonable agreement with the above prediction for isolated widely-spaced pores.

It is evident in Eq. 4 that the HIP and swelling strain rate is linearly dependent upon the driving force for a diffusion-controlled mechanism. The measured driving force dependence, which is designated as n , was close to $n=1$ for the previous experiments. In nickel, the driving force dependence increased slightly from $n=1$ to $n=2$ as the swelling driving force became large, and it was argued that a coupled cavitation mechanism could be dominant at higher driving forces. The activation energy, Q , was near that for boundary diffusion for both Ni and ZnO swelling, which also strongly supports a boundary diffusion-controlled mechanism.

HIP experiments for UO_2 did not exhibit a well-defined time-dependence, unlike the above swelling experiments. There was a continuous decrease in the m -value, indicating that the simplifying assumptions made to predict m for swelling do not apply for HIP. However, the stress dependence was measured to be $n=1$, indicating diffusion control, but the activation energy was measured to be in agreement with uranium bulk diffusion in UO_2 . The microstructure indicated that the porosity was predominantly intragranular, and these experiments were concluded to be controlled by a volume diffusion HIP process.

HIP experiments for Al_2O_3 were done following a creep test, and not by the previously described procedure. Creep specimens were fabricated by slip-casting an alumina slurry and then sintering to high density^[9]. The alumina creep cavitation was observed to agree with the model of Speight and Beere^[15] for grain boundary diffusive cavitation. After creep, a specimen was hot-pressed using the previously described technique^[3], and there was good agreement between the creep cavitation rate and HIP rate. This affirmed the equivalence of creep cavitation and HIP mechanisms.

Une^[29] studied swelling in UO_2 through the internal oxidation of carbon at 1400°C and 1700°C to form CO or CO_2 bubbles on the boundary. However, this resulted in a non-homogeneous microstructure, where the porosity varied from 15% near the surface to 5% near the center. Driving force and activation measurements were not made, but the swelling time dependence indicated that grain boundary diffusion was again the most likely rate-controlling mechanism.

2. Experimental

U-10Zr HIP specimens were prepared from powder mixtures of uranium hydride (UH_3) and zirconium hydride (ZrH_2) and uranium metal spheres and zirconium metal. The powders are pyrophoric, requiring specimen fabrication to be completed in an inert atmosphere glovebox with a flowing atmosphere of purified argon. The processing methods developed for this study are described in detail in a previous paper^[30], but a brief summary will be presented here for clarity.

2.1 Hydride-derived specimens

Hydride powders (UH_3^* and $\text{ZrH}_2^\dagger$) were chosen to produce alloy specimens because of their fine particle size, compactability, ultimate sinterability, and low temperatures for decomposition to pure metals^[31]. The hydride-derived specimens were fabricated by mixing the two powders by hand in an alumina mortar to make the final product U-10 wt.% Zr. The powder mixture was then compacted into a cylindrical pellet of 0.7 cm diameter at 550 MPa to yield relative green density of over 60%, but relative to the metal alloy theoretical density (16.02 g/cm^3 ^[32]), the decomposed sample has a green density of only ~42%. This is usually too low for effective sintering, but the uranium hydride has a very fine particle size of ~1 μm which permitted sintering to ~93% T.D.

For sintering and HIP, the hydride powder compact is inserted in a thoriated tungsten pressure vessel which is sealed in the glovebox environment and removed to a high pressure, high temperature sintering system, such that the specimen is always under purified argon. The specimen rests between two tungsten slugs, which are relatively inert to uranium and zirconium at the sintering temperatures. A molybdenum rod rests on the upper tungsten slug transmitting specimen length changes to a Linear Variable Differential Transducer (LVDT) above the furnace.

* Courtesy of B. Lambdin, Oak Ridge National Laboratory.

† A.D. Mackay, Inc.

During the servo-controlled furnace ramp of 1 hour to the sintering temperature of 1100°C, UH_3 decomposes first between 250°C and 450°C under vacuum, and ZrH_2 decomposes between 600°C and 900°C under vacuum. The decomposition temperature ranges were monitored by a thermocouple vacuum gauge, and back diffusion of air was prevented by maintaining the vacuum above 100 microns during evacuation. After decomposition was complete, 1.7 MPa of purified argon was introduced into the system, and by the time the specimen temperature reached 1100°C, it had densified from to ~70% T.D. The process slowed dramatically after the first hour, but after 24 hours, the sintered density was near 93%, and the pores were closed.

The microstructure of the sintered hydride-derived specimens, Fig. 2, indicates the existence of a second phase occupying 25 vol. %. EDAX analysis showed only Zr in these phases, and Scanning Auger Microscopy (SAM) showed the presence of significant quantities of carbon, nitrogen, and oxygen^[30]. The second phases are uniformly distributed throughout all hydride-derived samples, indicating that manual mixing does not produce heterogeneous samples. Phases of this type are observed in cast IFR fuel rods^[2], but they are much more prevalent in the hydride-derived specimens. These phases are generally believed to be interstitial solid solutions which are stable above the melting point of the alloy^[2]. In an effort to characterize the source of the contamination, the microstructural evolution of the impurity phase was tracked through the sintering process, as detailed in the previous paper^[30]. It was concluded that the starting UH_3 powder was the primary source of contamination after all other potential sources (i.e. vacuum leaks, impure sintering environment, etc.) had been eliminated. As described below, the metal-derived specimens had a much lower impurity phase content (5 vol. %) and this permitted the effect of such phases on HIP to be examined.

2.2 Metal-derived specimens

The uranium metal spheres are much larger (~177 μm) than the hydride powder particles so sintering is less efficient and requires a higher specimen green density. The original powder had a

surface oxide layer which acts as a barrier to interdiffusion during sintering. The layer was removed by washing with a 20% nitric acid bath following Lloyd and Williams^[33]. The clean powder is rinsed with water and ethyl alcohol to remove residual acid and then dried in the glovebox by evaporation. This process does contaminate the glovebox atmosphere by releasing vapors, so care must be taken to minimize the duration of exposure to open liquids.

The dry uranium powder is manually mixed in the die, and compressed at 1100 MPa, forming a pellet near 80% T.D. The compaction pressure was twice that used for the hydride-derived samples because it is necessary for the zirconium to plastically flow around the uranium spheres to form a coherent network^[30,31]. After compaction, specimens are transferred to the pressure vessel system, which is evacuated and backfilled with purified argon several times between 100°C and 200°C to remove adsorbed impurities from the acid-washed powder surface.

The system is pressurized with 3.5 MPa of argon and heated to 1100°C in 1 hour, but in contrast with the hydride-derived powders, there is no observable shrinkage during the temperature ramp until the temperature exceeds ~1000°C. Then, the samples begin to shrink rapidly. Rothman^[32] reports that interdiffusion between uranium and zirconium does not occur until both elements are in their body-centered cubic, high temperature phase, which does not occur until 863°C. Since the specimen temperature lagged the furnace temperature by as much as 120°C during the furnace ramp, the above observations are consistent

After 6 hours at 1100°C, sintering stops and the alloy is well mixed (verified by EDAX spot analysis), but the porosity does not fully close. Because of this, the process was modified to hold the specimens at 1100°C for only 30 minutes and then raise the temperature to 1200°C for 6 hours. Samples cannot be taken directly to 1200°C because it is above the melting point of pure uranium (1132°C) and time must be allowed for diffusional alloying.

With this method, specimens were sintered to ~91% T.D., but the density was not as homogeneous as in the hydride-derived specimens, due to surface roughness generated during fabrication. Immersion density measurements indicate some open porosity, and specimen microstructures show limited regions of open porosity near the roughness. However, the density

measurements also indicate significant amounts of closed porosity, and the microstructure, shown in Figure 2, indicates that the interior region of a sintered specimen is closed. There is 5 vol. % of second-phase impurity particles.

2.3 HIP procedure

Following sintering at 1100°C and 1200°C for the hydride-derived and metal-derived samples, respectively, the temperature was lowered to 700°C for hot-pressing. This temperature is in the solid solution, body-centered cubic γ -phase field of the U-10Zr binary alloy, and is representative of fuel centerline temperatures in the IFR core^[1]. The specimens were held at the HIP temperature for 1 hour to verify that no further densification occurs. The ambient external pressure was then raised to induce a HIP driving force and the densification strain was recorded vs. time from the LVDT signal. Various magnitudes of ΔP were used to investigate the pressure/driving force dependence of the HIP process, as discussed in the next section.

In order for the HIP experiments to be compared with theoretical models, microstructural information is required from both types of specimens. Porosity and impurity particle size distributions were measured using a Macintosh IIfx-based image analysis system which captures digital images from a video camera through an optical microscope^[31]. Grain sizes were evaluated from optical micrographs of polished and etched specimens using standard lineal analysis, and this information was used to calculate the average pore spacing.

3. Results

3.1 HIP experiments

HIP experiments were completed on the hydride-derived specimens with ambient pressure increases (ΔP) of 3.5, 6.9, 10.5, 13.8, and 20.7 MPa, and the strain rate vs. time results for this

series are presented in Figure 4. The specimens densified from 93% up to 95-97% relative density, depending on the pressure conditions. Some of the 6.9 and 10.5 MPa transients have been truncated for clarity because of perturbations made to measure the activation energy and stress dependence, as described later. There are two distinct time-dependent regions for the strain rates shown in Figure 3, but the majority of the densification occurs in the first region.

For the tests with $\Delta P = 3.5, 6.9, 10.5$, and 13.8 MPa, the initial hot-pressing strain rate decreases with time as

$$\dot{\epsilon} \sim t^{-0.32}. \quad (10)$$

This is similar to observed time-dependent behavior in previous *swelling* experiments on Ni^[7] and ZnO^[8], and agrees with the theoretical time-dependence predicted for diffusion-controlled swelling^[10]. The experiment with $\Delta P = 20.7$ MPa, however, behaves differently exhibiting a time dependence of

$$\dot{\epsilon} \sim t^{-0.74}. \quad (11)$$

HIP experiments on the metal-derived specimens are presented in Fig. 5, again with some of the transients truncated. Two regions of time-dependent behavior are again evident, but in contrast to the hydride-derived specimens, the time-dependence of the initial HIP strain rate in the metal-derived specimens was

$$\dot{\epsilon} \sim t^{-0.13} \quad (12)$$

for all driving forces. This low time-dependencies has not been seen experimentally before and cannot be explained by the simplified swelling prediction. However, it is reproducible and consistent over the full range of HIP driving forces.

Two HIP experiments were attempted with the metal-derived samples at 600°C with $\Delta P = 17.3$ MPa to investigate the behavior of the $\alpha + \delta$ phase mixture, which corresponds to the phases present near the IFR fuel surface^[1]. The first experiment was annealed for 6 hours and the second for 50 hours to allow the two phase structure to form. It is reported that "no more than 48 hours" would be required to decompose the α' phase into the two-phase structure at this temperature^[34]. However, δ phase was not detected by SEM analysis, even after 50 hours. No HIP strains were detectable in either specimen at this temperature. To verify that the pressure driving force and closed porosity were typical of the previous specimens, 1 hour after the initial ΔP , the temperature of the first sample was raised to 700°C, and it began to hot-press very rapidly, indicating that the porosity was closed.

3.2 Specimen microstructure

Figures 6 and 7 show normalized frequency distributions for pore size and particle size in the metal-derived and hydride-derived samples, respectively. The distributions were measured from several representative, digital images of post-HIP samples using area analysis methods. The porosity has a log-normal distribution with modal pore diameters of 2.5 ± 0.1 μm and 1.7 ± 0.1 μm for the hydride and metal derived samples, respectively. The hydride-derived specimens are found to have slightly more porosity, with a total number density of $9.3 \times 10^{14} \text{ m}^{-3}$ and a volume fraction of 6.4% compared to $5.5 \times 10^{14} \text{ m}^{-3}$ and 4.2% in the metal-derived specimens.

The impurity particle distributions for both materials are similar, having a bi-modal distribution with an upper mode of 4.5 μm for both materials. However, the hydride-derived material has a much higher particle density of $5.0 \times 10^{15} \text{ m}^{-3}$ and a volume fraction of 25% versus $3.9 \times 10^{14} \text{ m}^{-3}$ and 4.8% for the metal-derived specimens. Because there are fewer impurities in the metal-derived specimens, the zirconium content in solution should be higher. This was verified by EDAX chemical analysis, which showed that the matrix compositions were 4.7 and 9.4 weight % Zr (11.5 and 21.3 atom %) for the hydride and metal-derived samples, respectively.

Using lineal analysis to measure the mean intercept length, and assuming the grain shape to be a space-filling tetrakaidecahedron (truncated octahedron)[35], the average grain size is found to be 34 ± 4 and 114 ± 12 μm for the hydride and metal derived specimens, respectively. Based upon the grain size and number densities, the pore spacings were calculated to be 10 and 7 μm ($\pm 10\%$) and the particle spacings were calculated to be 4 and 8 μm ($\pm 10\%$) for the hydride and metal derived specimens assuming all pores and particles are on grain boundaries.

3.3 HIP driving force dependence

The measured HIP strain rates shown in Figs. 4 and 5 were extrapolated in time to 1 minute to approximate the initial strain rate response to the HIP driving force. The extrapolated rates are shown vs. the initial diffusional driving force, F , in Fig. 8. The experimental parameter ΔP , used to characterize the transients in section 3.1, is not the same as the driving force F ($=P - p - 2\gamma/r$). The driving force is calculated based on the known external pressure and estimated values of the internal pressure and surface energy. The internal pore pressure is calculated from the estimated gas content in the pore at the end of sintering, adjusted for temperature and pore size changes. The U-Zr surface tension is taken as 1.5 J/m^2 , based upon data for pure U and Zr[30].

It is evident from the data in Figure 8 that the driving force dependence is non-linear ($n \neq 1$) and that the metal-derived specimens HIP at a lower rate than the hydride-derived specimens.. A power-law curve fit of the data yields a driving force dependence of $n=3.7\pm0.2$ for both the hydride-derived and metal-derived materials. This high n -value is not in agreement with the model predictions for grain boundary diffusion-controlled HIP.

A second measure of the driving force dependence is calculated from strain rate changes due to step changes in the external pressure during hot-pressing transients. Even though the structure in the specimen is evolving during a transient, by extrapolating the strain rate from before and after the step change to the time when the change is induced, the structure can be assumed to be constant and n may be evaluated from the relation[30,31]

$$n = \frac{\ln\left(\frac{\dot{\epsilon}_1}{\dot{\epsilon}_2}\right)}{\ln\left(\frac{F_1}{F_2}\right)}, \quad (14)$$

where the subscripts 1 and 2 indicate the strain rate and driving force conditions before and after the induced changes.

Two of each type of specimen were exposed to incremental ΔP steps of 1-3 MPa following initial ΔP 's of 10.5 and 13.8 MPa. The initial HIP transients before the ΔP steps are represented by the truncated curves in Figs. 4 and 5, and the full transients are shown in Figs. 9-12. F_1 and F_2 for the ΔP 's were calculated for use in Eq. 14 using the method described above applied to the point of pressure application instead of the beginning of the HIP transient.

The first hydride-derived specimen, Fig. 9, was exposed to four ΔP steps of ± 2.4 MPa, but there were unexpected large loading and unloading transients which caused an overestimation of the n -value. Such loading transients are typical for dislocation controlled processes in which a stress increase causes blocked dislocations to break free and a stress decrease causes dislocations to become blocked until their density can be reduced by recovery^[36]. Therefore, the second hydride-derived ΔP test was done with a single step of +1.9 MPa, Fig. 10, to allow the transient to dissipate, which yielded a driving force dependence of $n=3.2\pm 0.5$.

The first metal-derived ΔP test, Fig. 11 had a single step of +0.7 MPa. There was a slight loading transient with this experiment, but it was much smaller in magnitude and duration than the hydride-derived transients. Since the "dislocation" transients were less significant in the metal-derived samples, a second test was done with several ΔP increases of +1.7 MPa, Fig. 12. The driving force dependence is found to be $n=3.5\pm 0.5$ from the first test and $n=3.8\pm 0.6$, 3.1 ± 0.5 , and 3.2 ± 0.5 from the ΔP steps in the second test, yielding a mean value of 3.4 ± 0.3 for the metal derived specimens. The measured n -values show that both the hydride-derived and metal-derived

materials have essentially identical driving force dependencies, which deviate from the previously observed diffusional behavior.

3.4 HIP activation energy

The activation energy, Q , is calculated for U-10Zr from HIP strain rate changes resulting from controlled temperature steps using the relation^[30,31]

$$Q = \frac{-R}{\frac{1}{T_1} - \frac{1}{T_2}} \left[\ln\left(\frac{\dot{\epsilon}_1}{\dot{\epsilon}_2}\right) - n \ln\left(\frac{F_1}{F_2}\right) \right] \text{ kJ/mole ,} \quad (15)$$

where R is the gas constant (kJ/°K mole), T is temperature (°K), $\dot{\epsilon}$ is the linear strain rate (s⁻¹), F is the driving force (MPa), subscripts 1 and 2 indicate the before and after conditions, and n is the driving force exponent from the previous section. The second term in the brackets is a correction for the change in the driving force due to the change in internal pore pressure with temperature, where F_1 and F_2 are calculated as before.

The change in strain rate due to the ΔT was found by extrapolation in time as done in the previous section for the driving force dependence, as shown in Figs. 13-15. Two hydride-derived specimens and one metal-derived specimen were subjected to incremental ΔT changes of $\pm 25^\circ\text{C}$ during HIP. Assuming $n \approx 3$, Eq. 15 yields activation energies of 200 ± 14 kJ/mole (Fig. 13) and 181 ± 13 and 181 ± 13 kJ/mole (Fig. 14) for the hydride-derived transients and 180 ± 13 and 182 ± 13 kJ/mole (Fig. 15) for the metal-derived transients. The mean Q from all experiments is 187 ± 10 kJ/mole.

Although not many measurements were made, there is apparently no significant difference in the HIP kinetics between the two types of alloy specimens. The measured activation energies for hot-pressing are significantly higher than the reported value of 112 kJ/mole for bulk diffusion

in $\gamma(\text{U-10Zr})$ ^[32], but agrees well with the reported value of 186.6 kJ/mole for boundary diffusion of uranium in $\gamma\text{-U}$ ^[37].

4. Discussion

The results of the HIP experiments may be compared to the existing cavitation models to determine the dominant mechanism of pore shrinkage. If the U-10Zr specimens hot-press by a boundary diffusion-controlled mechanism, then the stress-dependent strain rates in Fig. 8 should be well represented by the Speight-Beere model, Eq. 4. The diffusion-controlled models predict a stress dependence of $n=1$, as seen experimentally for HIP and swelling in several materials^[4-10], but the measured stress dependence of $n\approx 3$ for U-10Zr is reproducible and was determined through two independent measures. However, there is excellent agreement between the measured activation energy (187 ± 10 kJ/mole) and the reported value for grain boundary diffusion (186.6 kJ/mole). The agreement in activation energy implies that grain boundary diffusion is significant in the HIP of U-10Zr, but the poor agreement in the n -value and the predicted strain rates indicates that a diffusion-controlled mechanism does not dominate the HIP process. Also, the observance of the loading and unloading transients in Figs. 9-12 indicate that a dislocation-controlled process is involved in the HIP of U-10Zr.

We earlier suggested a modification of the diffusion-controlled mechanism^[30,38], based upon the model of Ashby^[39] and Arzt, *et al.*^[40] which introduces effects of interface control by solute drag and second phase particle pinning effects on the grain boundary dislocations to rationalize the dislocation-control behavior and the high n -value. The presence of both zirconium as a solute and the impurity particles on the grain boundary are qualitatively consistent with this model. However, the second phase particles would have to generate a "threshold" stress of ~ 5 MPa and lower the measured driving force dependence down to the models predicted n -value of $n=2$ ^[30,31].

Using the model of Arzt, *et al.*^[40] and the microstructural information reported in section 3.2, the maximum threshold stress generated by the impurity particles would be 0.2 and 0.5 MPa for the metal-derived and hydride-derived specimens, respectively. These values are less than the ± 1 MPa uncertainty in the calculated driving forces, and much lower than the required value of 5 MPa. Also, the measured activation energy for this mechanism should agree with the activation energy for Zr solute diffusion, Q_s , which is composition dependent and ranges from 113 to 134 kJ/mole^[32], and the measured activation energy for U-10Zr HIP was consistent for both types of specimens, despite differences in the matrix Zr content. Therefore, interface controlled grain boundary diffusion is unlikely.

The lack of full agreement between the experimental results and the grain boundary diffusion-controlled models or the interface-controlled model described above implies that some other mechanism must be operating. Since cavitation by creep alone under hydrostatic stress is not expected for low stresses, a coupled grain boundary diffusion/power-law creep mechanism is likely, such as the one defined by Beere and Speight^[21]. The analysis of the various models for cavitation, as applied to the U-10Zr HIP conditions, will be presented in Part II of this study to quantitatively model the present experiments and determine the dominant HIP mechanism.

The results reported above have direct implications on fuel performance modeling for metal fueled reactors such as the IFR. Performance codes such as LIFE-METAL^[41] and FASTGRASS^[42] (developed at ANL) attempt to model the detailed physical phenomena of reactor fuel in the complex reactor environment. Both codes utilize HIP/swelling model which have a linear stress dependence, in contrast to the above observations. Although HIP is only one of many phenomena taking place in the fuel during irradiation, but the proper physics should be in place to provide accurate modeling of the process. It is apparent from the HIP experiments on U-10Zr presented above that the assumption of a diffusion-controlled mechanism for HIP and swelling of the high temperature γ -phases is inappropriate under the experimental conditions, especially at high driving forces.

5. Summary

UH₃ and ZrH₂ powders were compressed, decomposed under vacuum, and sintered at 1100°C for 24 hours under purified argon to a relative density of ~93% T.D. Approximately 50% of the zirconium was stabilized into an interstitial solution with carbon, nitrogen, and oxygen present in the starting UH₃ powders, forming second phase particles on the grain boundaries which occupied ~25 vol. % of each sample. Pure uranium and zirconium metal powders were then used to fabricate and sinter HIP specimens. The uranium metal was washed with nitric acid to remove surface oxidation. The powders were compressed and sintered under purified argon to a relative density of ~92% T.D. Second phase impurity particles were again found on the boundaries, but their presence was greatly reduced to ~5 vol. %.

The hydride and metal-derived samples were successfully HIPed at 700°C in a high-pressure sintering system. The driving force dependence of U-10Zr was found by stress change experiments to be $n=3.4\pm0.3$ for the metal-derived specimens and 3.2 ± 0.5 for the hydride-derived specimens. The driving force dependence was also found to be 3.7 ± 0.2 for both materials based upon the variation of the initial HIP rates with driving force. An average activation energy of 187 ± 10 KJ/mole was measured for both types of specimen by temperature cycling. The driving force dependence suggests power-law creep controlled cavitation, but the activation energy is consistent with boundary diffusion controlled cavitation. Both n and Q indicate that the hydride- and metal-derived specimens exhibit the same HIP mechanism.

The expected Hull-Rimmer boundary diffusion mechanism was rejected because the observed strain rates had a non-linear driving force dependence, and loading transients were observed during ΔP steps in the middle of the HIP experiments. The second phase particles on the boundary and solute Zr atoms in the matrix suggested that interfacial control of grain boundary diffusion *might* be a dominant feature, but it was shown that these phenomena could not dominate under the experimental conditions. Part II of this study will report on the further analysis of the

experimental results using creep cavitation models, especially in relation to nuclear reactor fuel performance.

References

- [1] Walters, L.C., Seidel, B.R., and Kittel, J.H., Nuclear Technology, v65, 1984, 202.
- [2] Hofman, G.L., Pahl, R.G., Lahm, C.E. and Porter, D.L., Metallurgical Transactions A, v21A, 1990, 517.
- [3] Abbott, R.C. and Solomon, A.A., Bull. of the Am. Cer. Soc., v58, 1979, 128.
- [4] Solomon, A.A., Cochran, K.M., and Habermeyer, J.A., NUREG/CR-2023, PUR-101, 1981.
- [5] Solomon, A.A., Casagrande, A., and Rest, J., Journal of Nuclear Materials, v154, 1988, 332.
- [6] Xu, A. and Solomon, A.A., in Ceramic Microstructures '86: Role of interfaces, Ed. Pask, J., 1986.
- [7] Hsu, F. and Solomon, A.A., Acta Metallurgica, v31, 1983, 453.
- [8] Solomon, A.A. and Hsu, F., J. Am. Cer. Soc., 63, 1981, 467.
- [9] Xu, A. and Solomon, A.A., J. American Ceramic Society, v75, 1992, 985.
- [10] Solomon, A.A., and Hsu, F., Sintering Processes, ed. Kuczynski, Plenum Press, 1980, 485.
- [11] Svensson, L.-E. and Dunlop, G.L., International Metal Reviews, v2, 1981, 109.
- [12] Hull, D. and Rimmer, D.E., Philosophical Magazine, v4, 1959, 673.
- [13] Speight, M.V. and Harris, J.E., Metal Science Journal, v1, 1967, 83.
- [14] Weertman, J., Scripta METALLURGICA, v7, 1973, 1129.
- [15] Speight, M.V. and Beere, W., Metal Science, v9, 1975, 190.
- [16] Vitovec, F.H., Journal of Material Science, v7, 1972, 615.
- [17] Raj, R. and Ashby, M.F., Acta Metallurgica, v23, 1975, 653.
- [18] Raj, R., Shih, H.M., and Johnson, H.H., Scripta METALLURGICA, v11, 1979, 265.
- [19] Chen, I.W. and Argon, A.S., Acta Metallurgica, v29, 1981, 1759.
- [20] Herring, C. Journal of Applied Physics, v21, 1950, 437.
- [21] Beere, W. and Speight, M.V., Metal Science, April, 1978, 172.
- [22] Wilkinson, D.S. and Ashby, M.F., University of Cambridge Report, CUED/C-Mats/TR.22, 1975.
- [23] Hancock, J.W., Metal Science, v10, 1976, 319.

- [24] Edward, G.H. and Ashby, M.F., Acta Metallurgica, v27, 1979, 1505.
- [25] Rice, J.R., Time-Dependent Fracture of Materials at Elevated Temperature, Ed. S.Wolf, USDOE report, CONF 790236 UC-25, Germantown MD, 1979, p. 130.
- [26] Needleman, A. and Rice, J.R., Acta Metallurgica, v28, 1980, 1315.
- [27] Davanas, K. and Solomon, A.A., Acta Metall. Mater., v38, 1990, 1905.
- [28] Dyson, B.F., Metals Science, v10, 1976, 349.
- [29] Une, K., Journal of Nuclear Materials, v158, 1988, 188.
- [30] McDeavitt, S.M. and Solomon, A.A., World Congress of Powder Metallurgy, v.6, Proceedings, San Francisco, June 1992.
- [31] McDeavitt, S.M., Ph.D. Thesis, Purdue University, Dec. 1992.
- [32] Rothman, S.J., "Diffusion in Uranium, Its Alloys, and Compounds," ANL-5700, Part C, Argonne National Laboratory, 1961.
- [33] Lloyd, H. and Williams J., Metallurgy and Fuels, v.3, Finniston, H.M. and Howe, J.P., ed., Pergamon Press, 1961.
- [34] Hansen, M. and Anderko, K., Constitution of Binary Alloys, McGraw-Hill, 1958, p.1250.
- [35] Mendelson, M.I., J. American Ceramic Society, v 52, 1969, 1269.
- [36] Solomon, A.A. and Nix, W.D., Acta Metallurgica, v18, 1970, 863.
- [37] Kaur, I, Gust, W., and Kozma, L., Handbook of Grain and Interphase Boundary Diffusion Data, v.2, Ziegler Press, Stuttgart, 1989, p.1345.
- [38] McDeavitt, S.M. and Solomon, A.A., ANS Transactions, v66, 1992, 189.
- [39] Ashby, M.F., Scripta METALLURGICA, v3, 1969,837.
- [40] Arzt, E., Ashby, M.F., and Verrall, R.A. Acta Metallurgica, v31, 1983, 1977.
- [41] Billone, M.C., Argonne National Laboratory, private communication
- [42] Rest, J., Journal of Nuclear Materials, v120, 1984, 195.

ACKNOWLEDGEMENTS

The authors express their appreciation to Nuclear Metals, Inc. for providing the uranium powder, to Oak Ridge National Laboratory for providing the uranium hydride powder, and to the U.S. Department of Energy for financial support under contract #DE-FG07-88ER12814.

Figure 1. Beere-Speight model geometry.

Figure 2. SEM backscatter image of hydride-derived U-10Zr sintered for 24 hours at 1100°C (1000x).

Figure 3. SEM backscatter image of sintered U-10Zr specimen produced from metal powders (500x).

Figure 4. HIP results at 700°C for hydride-derived U-10Zr specimens. Points lying on same curve indicate duplicate experiments.

Figure 5. HIP strain rates vs. time at $700^{\circ}C$ for metal-derived U-10Zr specimens. Points lying on same curve indicate duplicate experiments.

Figure 6. Normalized porosity and particle size distributions in the hydride-derived samples.

Figure 7. Normalized porosity and particle size distributions in the metal-derived samples.

Figure 8. Extrapolated strain rates at 1 minute vs. the initial driving force.

Figure 9. Hydride-derived specimen strain rate vs. time with ΔP steps of ± 2.4 MPa.

Figure 10. Hydride-derived specimen strain rate vs. time with a single ΔP step of 1.9 MPa.

Figure 11. Metal-derived specimen strain rate vs. time with a single ΔP step of 0.6 MPa.

Figure 12. Metal-derived specimen strain rates vs. time with ΔP steps of +1.7 MPa.

Figure 13. Hydride-derived sample strain rate vs. time with a single ΔT transient of $+25^\circ\text{C}$.

Figure 14. Hydride-derived sample strain rate vs. time with ΔT transients of $\pm 25^\circ\text{C}$.

Figure 15. Metal-derived sample strain rate vs. time with ΔT transients of $\pm 25^{\circ}C$.

APPENDIX B

Hot Isostatic Pressing of U-10Zr by Coupled Boundary
Diffusion/Power-Law Creep Cavitation - Part II

HOT ISOSTATIC PRESSING OF U-10Zr BY COUPLED BOUNDARY DIFFUSION/POWER-LAW CREEP CAVITATION - PART II

Sean M. McDeavitt and A.A. Solomon

*School of Nuclear Engineering, Purdue University,
West Lafayette, IN 47907, USA.*

Abstract

HIP experiments performed on porous U-10Zr nuclear fuel at 700°C are compared with theoretical creep cavitation models. The coupled cavitation model of Chen and Argon shows quantitative agreement with the measured HIP rates. This model also predicts, for the first time, an asymmetry in HIP and swelling for identical driving forces due to differences in grain boundary stress. A calculation of the time-dependent HIP behavior was made which shows a varying time dependence that is consistent with the observed HIP rates. The compressibility of U-10Zr is different from previously studied ceramics and metals and is significantly lower than U-5Fs, which appears to HIP by diffusive transport only. The differences could be due to higher grain boundary diffusivity and/or larger pore size-to-spacing ratios in U-5Fs causing diffusional growth to be rapid and dominant. The lack of detectable compressibility of U-10Zr in both the α' and $\alpha+\delta$ phases may lead to fuel/cladding mechanical interactions during normal and off-normal conditions, especially at high burnup when solid fission products occupy available porosity.

1. Introduction

Uranium - 10 wt. % zirconium (U-10Zr) is a driver fuel for the Experimental Breeder Reactor - II (EBR-II), which is being modified to operate as an Integral Fast Reactor (IFR); a fast reactor plant design developed by Argonne National Laboratory^[1]. The metal-fueled IFR has passive safety features which will prevent severe nuclear accidents under conditions which would normally be devastating for the standard pressurized water reactors^[2]. Metal alloys of uranium are attractive nuclear fuels because of their high thermal conductivity and high fissile atom density, but they were previously rejected due in part to fission gas induced swelling which caused Fuel-Cladding Mechanical Interaction (FCMI) and cladding rupture under normal operating conditions^[1].

IFR fuel pins are designed to accommodate swelling and gas release by providing a fuel/cladding gap filled with sodium and an enlarged gas plenum which will allow the fuel to swell and release its fission gas before it comes in contact with the cladding^[1]. After cladding contact at 1-2 atom % burnup, FCMI is unavoidably present because fuel swelling is constrained by the current non-swelling cladding materials. Also, solid fission product accumulation in available porosity will impair the fuels compressibility at high burnup^[3], and rapid temperature rises during reactor transients could generate large contact stresses due to differences in fuel/cladding thermal expansion and plenum pressure increases.

To address these issues, hot-isostatic pressing (HIP) experiments were carried out on unirradiated U-10Zr, as described in Part I of this reported work^[4]. U-10Zr HIP specimens were prepared in an inert atmosphere glovebox from powder mixtures of uranium metal spheres with zirconium metal powder and uranium hydride (UH₃) with zirconium hydride (ZrH₂) powders. The processing methods developed for this study are described in detail in elsewhere^[4-6]. The purpose of these experiments was to identify and quantify the rate-controlling HIP mechanism in U-10Zr using pure, unirradiated material to eliminate ambiguities from solid fission products, non-equilibrium defect structures, and other irradiation effects.

The hydride- and metal-derived samples were sintered in a purified argon atmosphere beyond the point of pore closure at 1100°C and 1200°C, respectively, to generate gas bubbles on the grain boundaries^[4]. Both types of specimens were successfully HIPed at 700°C, which is in the γ -phase field, using a high-pressure sintering system described elsewhere^[7]. Hot-pressing was attempted at 600°C, in the $\alpha+\delta$ phase field, but no densification was observed. HIP was accomplished through raising the external ambient pressure to create a driving force for densification. The HIP strains were monitored *in situ*, and the initial HIP rates are shown in Fig. 1 vs. the initial pressure driving force. The hydride-derived specimens HIPed at relatively higher strain rates, as compared to the metal-derived specimens.

It is apparent from the data in Fig. 1 that the driving force dependence of the HIP rate, which is denoted by the variable n , is non-linear. The n -value for both materials was found to be 3.7 ± 0.2 , based upon the variation of the initial rates with driving force^[4,6]. An independent measure of n was also made through small pressure perturbations during the HIP experiments, and the driving force dependence was found to be $n = 3.4 \pm 0.3$ for the metal-derived specimens and 3.2 ± 0.5 for the hydride-derived specimens^[4,6]. This non-linear driving force dependence was not seen previously in other HIP and swelling experiments on other materials^[8-14], and it suggests the possibility that power-law creep dominates the HIP process.

To quantify the kinetic behavior of the process, the HIP activation energy (Q) was measured for both types of specimen through temperature cycling during hot-pressing transients. Although relatively few data were generated, there was good agreement between the Q -values measured for the hydride- and metal-derived materials, with an overall mean Q -value of 187 ± 10 KJ/mole (45 ± 3 kcal/mole)^[4,6]. This value is consistent with the reported activation energy of 186.6 kJ/mole (44.6 kcal/mole) for grain boundary diffusion in uranium^[15], which suggests the possibility that grain boundary diffusion dominates the HIP process.

Despite the different implications of the measured n and Q values, the agreement between the hydride- and metal-derived data strongly supports the idea that both specimens exhibit the same HIP mechanism. The purpose of this paper is to consider the proposed HIP mechanisms and

rationalize the differences and similarities in the data through quantitative analysis using previously derived models. It has been established that the phenomena of HIP and swelling of porous material at elevated temperatures are well described by models developed for creep cavitation^[14]. The following sections will review the mechanistic models for creep cavitation and then apply them to simulate the conditions of the U-10Zr experiments presented in Part I in order to quantitatively determine the dominant HIP mechanism.

2. Creep Cavitation Models

2.1 Grain Boundary Diffusion Controlled Cavitation

Hull and Rimmer^[16] were the first to analyze grain boundary creep cavity growth by vacancy diffusion in response to a tensile stress. Cavities are assumed to reside on grain boundaries which are perpendicular to the applied tensile load. The stress-induced potential difference between the grain boundary and the cavity surface creates a driving force for vacancy diffusion from the boundary to the cavity surface, inducing cavity growth. Diffusion on the pore surface is assumed to be much more rapid than in the grain boundary, such that grain boundary diffusion is the rate-limiting cavity growth phenomena. It is also assumed that the grain boundary is a perfect sink for atoms which are deposited uniformly over the entire boundary to minimize lattice strains.

The original model from Hull-Rimmer has been modified by several authors^[17-22], but the fundamental concept has not changed. Important modifications have been made to the model geometry^[17-20] and the physical boundary conditions^[21,22]. A similar diffusive model was developed by Chuang, *et al.*^[23,24] for crack like cavity growth during creep when the pore surface diffusion is the rate limiting phenomenon. However, this model will be neglected because this type of cavity growth is not observed for HIP and swelling situations^[14].

Chen and Argon^[25] suggest that the diffusion-controlled model presented by Speight and Beere^[22] provides the most accurate and complete formulation. Fig. 2 shows a top view of the Speight-Beere model unit cell geometry for a planar grain boundary, which consists of a pore of radius r_p in a circular cell with radius λ . Physically, λ represents the pore half-spacing for equi-spaced, equi-sized cavities in the grain boundary. Assuming spherical cavities and including internal pore pressure, the Speight-Beere expression for the rate of cavity volume change under HIP or swelling conditions is given as^[20]

$$\left(\frac{dV}{dt}\right)_{\text{diffusion}} = \frac{2\pi \Omega D_b \delta_b}{kT f\left(\frac{r_p}{\lambda}\right)} \left[P - p + \frac{2\gamma}{r_p} \right], \quad (1)$$

where P is the external pressure, p is the cavity internal pressure, γ is the cavity surface energy, D_b is the grain boundary diffusion coefficient, δ_b is the effective width of the boundary, Ω is the atomic volume, k and T have their usual meanings, and $f\left(\frac{r_p}{\lambda}\right)$ is a geometric function given by^[20]

$$f\left(\frac{r_p}{\lambda}\right) = -\left[\ln\left(\frac{r_p}{\lambda}\right) + \frac{1}{4} \left(1 - \frac{r_p^2}{\lambda^2} \right) \left(3 - \left(\frac{r_p}{\lambda} \right)^2 \right) \right]. \quad (2)$$

2.2 Power-law Creep Deformation Controlled Cavitation

In the above diffusion-controlled models, it is assumed that the grains do not deform plastically (which is always true for HIP and swelling, but not for creep) and that diffusion occurs over the entire grain boundary. In practice, it is possible that diffusion only dominates the portion of the grain boundary adjacent to the pore and that dislocation creep is the dominant deformation mechanism over the remainder of the boundary^[5]. In the extreme situation where grain boundary diffusion is limited, creep deformation can control cavity growth.

This section will discuss two models for creep cavitation which are governed by plastic deformation^[26,27]. Both models assume that the material surrounding the cavity creeps according to the constitutive relation

$$\dot{\epsilon}_c = B\sigma_e^n \quad (3)$$

where B and n are constants and σ_e is an effective stress.

Beere and Speight^[26] consider the creep of a thin shell of material around the boundary which is approximately as thick as the pore diameter. They consider this effect to be in addition to the creep of the bulk, intragranular material. Although creep is a constant volume process, the deformation of the cavity as the surrounding material creeps is not. The pore growth rate due to the creep of the boundary shell is given by

$$\left(\frac{dV}{dt}\right)_{\text{creep}} = 2\pi r_p^3 \dot{\epsilon}_c \quad (4)$$

where $\dot{\epsilon}_c$ is the creep response to the stress acting on the boundary. This expression is derived by assuming a shell depth of $2r_p$ and a creeping pore volume of $(2r_p \cdot \pi r_p^2)$. This is effectively a cylindrical pore, but the model is limited because of the planar geometry.

A general creep-controlled HIP model was derived by Wilkinson and Ashby^[27] based upon the models of Murray, *et al.*^[28], Mackenzie and Shuttleworth^[29], and Wolfe^[30]. The model describes a 3-dimensional, even distribution of equisized pores with the unit cell geometry defined as a spherical pore in the center of a creeping spherical shell. Wilkinson and Ashby derive the stress field within the shell to estimate the effective stress, assuming an external hydrostatic pressure an internal pore pressure. They neglect the pressure effect of the surface energy of the pore, but this model was specifically derived for HIP conditions. They derive an expression for the rate of density change due to pore shrinkage which is given as^[27]

$$\dot{\rho} = \frac{3B}{2} \frac{\rho(1-\rho)}{[1 - (1-\rho)^{1/n}]^n} \left(\frac{3}{2n} (\Delta P) \right)^n \quad (5)$$

where ρ is the relative density of the material, ΔP represents the difference between the internal and external pressures, n is the creep stress dependence from Eq. 3, and B is a constant.

2.3 Coupled Grain Boundary Diffusion/Power-law Creep Controlled Cavitation

Several authors have considered coupled operation of creep and grain boundary diffusion, and the models are referred to as: 1) "constrained" cavitation, and 2) "enhanced" cavitation. The first case occurs when pores are isolated on a boundary surrounded by adjacent boundaries having no porosity. The growth of cavities under a tensile load requires long-range diffusion unless the material far from the cavities can creep^[31-33]. The surrounding material is considered to act as a "constraint" to diffusive cavitation and creep can relax this constraint. This case is equivalent to diffusional cavitation under variable pore spacing as described by Davanas and Solomon^[34]. These models will not be considered further for this study because the porosity generated in the U-10Zr samples is evenly distributed over all grain boundaries^[4,6].

The second case is equivalent to coupled grain boundary diffusion and power-law creep controlled cavitation^[25,26,35-37]. Beere and Speight^[20] considered this coupled mechanism for tensile loading by assuming that vacancy creation occurs predominantly near the cavity and negligibly over the rest of the boundary. The cavity growth rate is "enhanced" because the diffusional path length is shorter, as vacancies are created in the boundary closer to the cavity. The authors simplify the situation by assuming the boundary may be divided into two regions, as indicated in Figure 3(a). The unit cell of the model is circular for symmetry, where r_p is the pore radius, λ is the pore half-spacing, and b is the radius of the division between Regions I and II.

During diffusive cavity growth, the rigid grains move apart due to the plating of atoms on the grain boundary, and this process is called "jacking"^[22]. For the coupled model, jacking is

restricted to Region I, near the cavity, as indicated by the side view in Figure 3(b). The cell boundary displacement far from the cavity in Region II matches the jacking displacement through dislocation creep to maintain continuity. The vertical depth of the model is taken as $2b$, which is equivalent to assuming a hole exists in the material the size of the diffusion zone because all stresses are relaxed by diffusion and creep deformation does not occur.

The displacements in Region I due to jacking are matched by dislocation creep in Region II to maintain continuity. Beere and Speight derived a system of three equations to physically represent the situation, which may be used to calculate the parameters b , σ_I and σ_{II} , where σ_I is the average stress over region I (including the cavity) and σ_{II} is the stress on the boundary in Region II. Because the system of equations is complex, Beere and Speight presented an approximation for the pore rate of volume change by summing the two limiting cases where only diffusion ($b \geq \lambda$) or only creep ($b \leq r_p$) is dominant in the grain boundary. This approximation was later rejected as an oversimplification by several authors[25,35-37].

A significant improvement to the coupled model came from Chen and Argon[25], who advanced a similar, but more elegant, model and extended it to include non-equilibrium, crack-like pores, similar to the model of Chuang *et al.*[23-24]. The complex system of equations presented above become unnecessary because the size of the diffusion zone, b , may be directly calculated from the “diffusion distance” or “characteristic length” in a creeping material derived by Rice[36] as

$$\Lambda = \left(\frac{D_b \delta_b \Omega \sigma_\infty}{kT \dot{\epsilon}_\infty} \right)^{1/3}, \quad (6)$$

where σ_∞ and $\dot{\epsilon}_\infty$ represent the far-field creep stress and creep rate. Chen and Argon[25] estimate the diffusion zone radius, by $b = r_p + \Lambda$, and then calculate the pore growth rate due to the jacking of Region I. Therefore, the pore growth rate may be directly calculated from

$$\left(\frac{dV}{dt}\right)_{\text{diffusion}} = \frac{2\pi \Omega D_b \delta_b}{kT f\left(\frac{r_p}{b}\right)} \left[P - p + \frac{2\gamma}{r_p} \right] \quad (7)$$

which is equivalent to Equation 1, substituting b for λ . The structure function $f\left(\frac{r_p}{b}\right)$ is strongly stress dependent, which raises the stress dependence of the model from $n=1$ at low stresses to the creep exponent of the material at very high stresses. Chen and Argon compare their model with the exact calculation of Needleman and Rice and an exact solution of the system of equations derived by Beere and Speight, and show excellent agreement with both.

3. Comparison of Data with Theoretical Models

The above models will now be used to calculate the predicted HIP behavior for U-10Zr for each of the described models. The expressions presented for the rate pore volume change may be translated to an overall linear specimen HIP or swelling rate according to Solomon and Hsu^[14] using

$$\dot{\epsilon} = \frac{1}{3} N_v \left(\frac{dV}{dt}\right) \quad (8)$$

Spherical pores are assumed for this study, consistent microstructural observation of the U-10Zr samples^[4,6]. The measured values and physical parameters assumed for U-10Zr which were used in the models to calculate HIP behavior are summarized in Table 1.

3.1 Grain Boundary Diffusion Controlled HIP of U-10Zr

The Speight-Beere model (Equation 1) for grain boundary diffusion controlled cavity growth becomes

$$\dot{\epsilon}_{\text{diffusion}} = \frac{2\pi}{3} \frac{N_v \Omega D_b \delta_b}{kT f\left(\frac{r_p}{\lambda}\right)} \left[P - p + \frac{2\gamma}{r_p} \right] \quad (9)$$

when combined with Equation 8. The predicted driving force dependence of $n=1$ does not agree with the experimental values of 3 to 3.5^[4,6].

Figure 4 shows the predicted diffusion-controlled HIP behavior of U-10Zr as compared with the initial HIP rates shown in Figure 1 for the metal- and hydride-derived materials. These comparisons show the significance of the driving force dependence to the accuracy of model predictions. Although the model prediction and the measured HIP rates are within one order of magnitude at low driving forces, a change in the driving force from 5 to 30 MPa shifts the difference between the model and the data to almost 3 orders of magnitude. Therefore, a diffusion-controlled cavitation model does not adequately predict the HIP rates for U-10Zr under the observed conditions in spite of the excellent agreement between the measured activation energy (187 ± 10 kJ/mole) with the reported value for grain boundary diffusion (186.6 kJ/mole).

3.2 Power-law Creep Controlled HIP of U-10Zr

Before the creep-controlled cavitation models were applied to U-10Zr HIP conditions, an appropriate constitutive creep expression of the form given by Equation 3 was determined. The expression was determined using the empirical method of Stocker and Ashby^[38] and Derby and Ashby^[39], and the relation is given as

$$\dot{\epsilon}_c = (4 \times 10^{-10}) \sigma^5 \text{ s}^{-1} \quad (11)$$

The use of this expression is justified elsewhere^[6], but this justification is beyond the scope of this paper.

The Beere-Speight cavitation model is derived to represent the rate of pore volume change so it may also be translated to a HIP strain rate using Equation 8 to yield

$$\dot{\epsilon}_{\text{creep}} = \left[\frac{2\pi r_p^3}{3} N_v \right] \dot{\epsilon}_c(\sigma_{av}) , \quad (12)$$

where $\dot{\epsilon}_c$ is given by Equation 10 and σ_{av} is the average stress acting on the creeping boundary shell. To use this expression, an approximation for σ_{av} must be made, and based upon the free-body diagram in Figure 5, the average stress on the boundary may be written as

$$\sigma_{av} = \frac{P \lambda^2 + \left(\frac{2\gamma}{r_p} - p \right) r_p^2}{(\lambda^2 - r_p^2)} . \quad (13)$$

The model of Wilkinson and Ashby does not require this approximation for σ_{av} , since it was derived for HIP stress conditions. However, the model must be modified because it considers intragranular porosity homogeneously distributed throughout a material. The model predicts the rate of density change for a spherical unit cell, which may be translated to a HIP strain rate by considering the combined contribution of all pores to the density change, which yields a linear strain rate according to

$$\dot{\epsilon} = \frac{N_v}{3} \left(\frac{dV}{dt} \right)_{\text{unit cell}} = \frac{N_v}{3} \left(\frac{V}{\rho} \right)_{\text{unit cell}} \dot{\rho} . \quad (14)$$

This may be combined with the model in Equation 5 to yield

$$\dot{\epsilon}_{\text{creep}} = \frac{BN_v V}{2} \frac{(1-p)}{[1 - (1-p)^{1/n}]^n} \left(\frac{3}{2n} \right)^n \left[P - p + \frac{2\gamma}{r_p} \right]^n \quad (15)$$

where B is the coefficient of the creep correlation in Equation 3, and V is the volume of the model unit cell which is $(4/3)\pi\lambda^3$. The density, ρ , represents the relative unit cell density, not the relative material density, and it is given by[27]

$$\rho = 1 - \left(\frac{r_p}{\lambda}\right)^3. \quad (16)$$

Equation 15 is therefore applicable to HIP of grain boundary cavities if the unit cell densification is associated with the grain boundary pores. This effectively implies a “shell-like” layer of deforming material surrounding the grain boundaries, just as in the Beere-Speight model.

The power-law creep controlled cavitation models described above are both completely defined and may be evaluated for the HIP of U-10Zr using the data in Table 1. Figure 6 and compares the calculated HIP rates with the experimental data. The upper data set for each pair of curves represents the hydride-derived information, whereas the lower data set for each pair represents the metal-derived information. It is apparent that the Wilkinson-Ashby prediction is orders of magnitude lower than both the experimental data and the Beere-Speight model prediction.

Although it is evident that the Beere-Speight creep cavitation model provides the better prediction of HIP strain rate, it is not clear that this model best represents the HIP of U-10Zr. A network of creeping material around rigid grains, such as that proposed by a creeping shell model, will not maintain continuity. If the creeping shell decreases in volume under a HIP driving force, there would be a tendency for cavities to form within the grain unless the “rigid” interior of the grain accommodates the shell deformation. Therefore, deformation within the grain must occur to maintain continuity, and this is inconsistent with the hydrostatic nature of the HIP pressure driving force.

The above cavitation models are also inconsistent with the measured HIP activation energy of 187 ± 10 kJ/mole which matches well with the activation energy for grain boundary diffusion in uranium (186.6 KJ/mole). The activation energy for dislocation creep, equivalent to that for

volume diffusion, would be a combination of the activation energies for uranium and zirconium bulk diffusion. From the data in Table 1, Q for the above models should lie within $112 < Q < 134$ kJ/mole, dependent upon the zirconium concentration. All of the above factors imply that creep does not control the HIP mechanism in the U-10Zr experiments.

3.3 Coupled diffusion/power-law creep controlled HIP

The lack of full agreement between the U-10Zr HIP results and either the grain boundary diffusion controlled cavitation models or the power-law creep controlled cavitation models implies that a coupling of the two mechanisms is possible. This section will compare the coupled cavitation model of Chen and Argon^[28] with the experimental results. The coupled model may also be translated to a HIP strain rate using Equation 8, as done for the other pore growth models, with a resulting expression given as

$$\dot{\epsilon}_{\text{coupled}} = \frac{2\pi}{3} \frac{N_v \Omega D_b \delta_b}{kT f\left(\frac{r_p}{b}\right)} \left(P - p + \frac{2\gamma}{r_p} \right). \quad (17)$$

The structure function, $f\left(\frac{r_p}{b}\right)$, is the only difference between this equation and the diffusion controlled model described by Equation 9, but the calculation of the diffusion zone radius, b , requires several assumptions. First, the characteristic length, Λ , defined in Equation 6 must be evaluated. Using the parameters in Table 1 for U-10Zr at 700°C, Equation 6 becomes

$$\Lambda = 18.9 \sigma_{\infty}^{-4/3} \mu\text{m} \quad (18)$$

when σ_{∞} is given in MPa. For the calculation of the HIP rate in the U-10Zr specimens, σ_{∞} was taken to be σ_{av} , as defined by Equation 13. As stated previously, b is calculated as the sum of the pore radius and the characteristic length.

The variation of the diffusion zone radius, b , with external HIP pressure is shown in Figure 7 for the two types of U-10Zr specimens. The pore radii (r_p) and pore half-spacings (λ) are indicated along the vertical axis for reference. This calculation of b implies that a strongly coupled mechanism is likely for both types of U-10Zr specimens between external pressures of approximately 5 to 30 MPa. Below 5 MPa, b becomes greater than λ , indicating that the diffusion length is large enough for diffusion-controlled cavitation to dominate HIP. Above 30 MPa, b is nearly equivalent to r_p , indicating that the diffusion length is small and creep-controlled cavitation dominates HIP.

Figure 8 shows the comparison of the coupled model prediction vs. the experimental HIP data, indicating good agreement between model predictions and the data. Although the prediction of the magnitude of the strain rate is not as important as the prediction of the proper trends, the data and model do agree well in magnitude. The model predicts a variation in the stress dependence from $n=1$ to $n=5$ as the diffusion zone shrinks from $b=\lambda$ down to $b=r_p$. The U-10Zr HIP results were all generated between 5 and 30 MPa where the predicted n -value is between the two extremes^[4,6]. For the calculated HIP rates between 5 and 30 MPa, the predicted n -values are $n=3.6$ and $n=3.8$ for the metal and hydride-derived materials. This agrees well with the measured n -values reported earlier^[4,6].

The HIP activation energy should show a similar transition, as boundary diffusion becomes less dominant and power-law creep becomes dominant. All of the experimental measurements for Q were made at lower driving forces (~ 8 MPa) where diffusion is significant^[4,6]. Therefore the apparent agreement between the measured activation energy and the activation energy is consistent with the model. It should be noted, however, that according to Figure 7, the portion of the boundary which is deforming by creep is significant at the HIP pressures where Q was measured. It would therefore seem to indicate that the measured Q -values should be slightly lower under the conditions where the data were generated.

An important consequence of the coupled model and the assumptions described above is the prediction of asymmetrical HIP and swelling behavior for similar driving forces. The average

stress on the boundary, which is used to evaluate Λ , is dramatically different for HIP as compared to swelling. It is feasible for HIP to be controlled by a coupled mechanism because of the high stresses in the grain boundary while a similar driving force for swelling would be in the diffusion-controlled regime because σ_{av} is small and Λ is large. Evidence for this effect was not available from this present study, but there are indications that this does occur in the post-irradiation experiments discussed later. Considering the good agreement with the measured n -values and the qualified agreement with the measured Q -values, it can be concluded that the HIP of U-10Zr is best modeled by a coupled boundary diffusion/dislocation creep mechanism.

4. Discussion

4.1 Time dependence of the coupled HIP model

The model vs. data comparisons discussed above only consider the initial HIP rates vs. the initial pressure driving force. The pressure driving force for HIP will decrease with time as the pressure-filled cavity volume changes. Eventually, a new pressure equilibrium is achieved and HIP induced densification stops. This is also true for swelling, except when the driving force is so great that cavity interconnection and gas release occur before the new equilibrium is established. The HIP/swelling strain rate will therefore decrease with time.

In swelling experiments on other materials^[11,12], the strain rate was observed to follow

$$\dot{\epsilon} \sim t^{-m} \quad (19)$$

where m is the time dependence which was experimentally determined to be $m \approx 1/3$. This is in good agreement with the theoretical prediction of $m=2/5$ ^[14], which was made assuming that internal gas pressure and surface energy effects on the pressure driving force are negligible for swelling. However, these parameters should be very significant for HIP in establishing the new

equilibrium required to halt densification. The U-10Zr HIP results reported in Part I^[4] indicate that the m -value for HIP varies from as low as 0.1 up to 0.8, depending upon the HIP conditions.

To rationalize this difference, the coupled model of Chen and Argon was used to predict the time dependent HIP behavior of U-10Zr using a simple numerical integration method. A simple loop calculation is used to evaluate the specimen strain rate vs. time. The pore radius is decreased after a finite time step, Δt , by a linear first order approximation given by

$$(r_p)_{i+1} = (r_p)_i - \left(\frac{dr_p}{dt} \right)_i \Delta t, \quad (20)$$

where the radial shrinkage rate is calculated from the volume rate of change generated by the cavitation model. Equation 6 was used to calculate the characteristic length for each time step, Λ_i , which increases as the transient progresses and the pressure driving force decreases. When the calculated diffusion zone radius, b_i , exceeds the unit cell radius, λ , as the diffusion zone increases, the diffusion model of Speight and Beere^[22] was used for the remainder of the calculated transient.

Calculated HIP transients are shown in Figure 9. The calculations were made using the hydride-derived specimen parameters in Table 1, external pressure changes (ΔP) of 5, 10, 15, and 20 MPa, and time step intervals (Δt) of 10 seconds. The transients agree well in magnitude, duration, and initial m -value with the experimental HIP transients discussed in Part I, although they do slightly under predict the HIP rates by a factor of ~ 3 . This underprediction is consistent with the data in Figure 8, which shows a similar underprediction for the initial rates.

There is a continuous change with time-dependence (m) of the calculated strain rates, in contrast to the data, where two apparently distinct regions of constant time dependence are observed. It is therefore apparent that a single definitive m -value does not exist for HIP transients. The difference between model and experiment is likely due to an over-interpretation of the experimental data and not an error in the theoretical model.

To verify this, HIP conditions for a specific hydride-derived HIP transient ($P=12.7$ MPa) were duplicated using the above methodology, and the result is compared with the data in Figure

10. The calculated strain rates were again ~3 times lower than the measured strain rates, as expected, so the result was normalized to match the initial measured HIP rate. Despite potential inaccuracies in the boundary stress assumption and the calculation of Λ and b , this time-dependent calculation reproduces the HIP transient with reasonable accuracy. The calculated transient mirrors the experimental HIP transient through most of the test, but it drops off dramatically at extended time as the calculated driving force approaches 1 MPa. Below 1 MPa, the strain rates are low (approaching the resolution limit of the LVDT) and little specimen strain occurs. The overall calculated strain (1.31%) is similar to the measured strain for this particular sample (1.33%). The decrease in the calculated strain rate is due solely to the changing driving force from the rise of the internal gas pressure as the calculated pore radius decreases. The ability of this model to so accurately predict the time-dependent HIP behavior of U-10Zr has significant implications on the modeling of nuclear fuel behavior.

4.2 Irradiated metal fuel performance and modeling

A limited number of HIP and swelling experiments have been performed^[40] and analyzed^[6,40] on irradiated U-5Fs and U-10Zr nuclear fuels. The data is very limited, but estimates of n and Q for the two materials imply that HIP and swelling in irradiated U-5Fs is controlled by a grain boundary diffusion mechanism, whereas irradiated U-10Zr is controlled by a coupled mechanism, as found in this present study.

Figure 11 shows U-5Fs and U-10Zr post-irradiation transients along with present data for hydride- and metal-derived specimens at 700°C and $\Delta P=6.9$ MPa (1000 psi). The irradiated U-5Fs swelling data were generated at 600°C and has been adjusted for comparison at 700°C^[6]. HIP data were unavailable, but HIP and swelling were found to be reversible phenomena for U-5Fs^[40], so the comparison to the U-10Zr HIP results is valid. The irradiated U-10Zr HIP and swelling data were generated from Figure 5.11 for $\Delta P=33.8$ MPa for both cases. Both transients were adjusted for comparison at 6.9 MPa using $n=3.4$, based upon the present results. The asymmetry in the

HIP and swelling rates is consistent with the coupled model discussed above. Quantitative microstructural information was not available for either irradiated material^[6].

It is apparent that U-5Fs and U-10Zr do not exhibit similar HIP/swelling behavior. It would therefore be appropriate to investigate the reason this coupled mechanism is dominant in one uranium alloy and not the other, and also to examine pure uranium and other metal fuel alloys and the effect of fission products on U-10Zr. An estimation of Λ for both materials would aid in defining the difference between the two materials, but accurate microstructural, diffusion, and creep data would be required for both alloys, and such data is not available at this time. The difference between the hydride- and metal-derived HIP rates may be rationalized due to the differences in specimen microstructure. The difference in rates between the present experiments and the irradiated U-10Zr HIP rates could be the result of either microstructural differences, irradiation, or a combination of both, but such a determination is not possible without more information. It is evident that the microstructure has a strong effect on HIP or swelling rates.

The experimental and calculational results have direct implications on fuel performance modeling for metal fueled reactors such as the IFR. Performance codes such as LIFE-METAL^[41] and FASTGRASS^[42] attempt to model the detailed physical phenomena of fissioning reactor fuel in the complex reactor environment. Both codes assume a HIP/swelling model based on out-of-pile, diffusion-controlled growth formulations for non-equilibrium pores which have a linear stress dependence, in contrast to the present observations.

HIP is one of many phenomena taking place in the fuel during irradiation, but the proper physics should be in place to provide accurate modeling of the process. It is apparent from the HIP experiments on U-10Zr presented above that the assumption of a boundary diffusion mechanism for HIP and swelling is inappropriate for U-10Zr, in spite of the strong evidence from previous observations on UO₂, U-5Fs, and other materials. This is important because the coupled mechanism predicts initial strain rates which are orders of magnitude higher than the diffusion-controlled models, especially at high stresses, and has an inherent asymmetry in the HIP/swelling predictions.

4.3 Relevance of ex-reactor models and experiments to nuclear fuels

Despite all the previous assumptions concerning the relevance of ex-reactor models to in-reactor hot-pressing, the question of unique in reactor phenomena does exist. During irradiation, a supersaturation of vacancies and interstitials exists in the fuel which enhances atom mobility. However, *if* local equilibrium is maintained at the pore surfaces and the grain boundary sinks, then, as argued for radiation-induced creep^[44] and fission-induced densification^[45], enhanced diffusion cannot affect the de-cavitation (HIP) rate since the net flux of vacancies from source to sink is unchanged. However, as argued elsewhere^[45], if local equilibrium cannot be maintained under irradiation, effects of interface control may occur. There is also the possibility that the creep component *could* be enhanced by radiation^[44] causing an acceleration at high stresses and low temperatures, but there are no data available on the magnitude of this enhancement. For the outer region of the fuel which hot-presses very sluggishly, a radiation enhanced creep component could have an important effect on FCMI.

Another potential effect from vacancy and interstitial supersaturation during irradiation is the direct deposition of vacancies and atoms on grain boundary and pore surfaces from the matrix in response to a driving force for densification. It can be assumed that during steady state irradiation, the point defects are continuously moving to all available sinks, such as the grain boundaries. For a HIP or swelling transient, any *biased* defect diffusion to sinks due to the changes in the chemical potential of the pore surface or the grain boundary would be in competition with the presently proposed boundary de-cavitation mechanism.

If a HIP transient were generated by a rise in temperature in a fuel rod after fuel-cladding contact has occurred, the *local* chemical potentials for vacancies would rise on grain boundaries due to FCMI thermal contact stresses (grain jacking induced densification) and on pore surfaces due to internal pore pressure increases with temperature (pressure-induced swelling), whereas the *local* chemical potentials for interstitials will decrease on both the grain boundaries and pore

surfaces. This implies that supersaturated vacancy fluxes should dominate the transient. At the same time, the relative difference in chemical potentials will drive vacancies from pore surfaces to grain boundaries if the FCMI-induced potential difference in the boundaries is greater than the pressure-induced potential difference on the pore surfaces.

Thus, the de-cavitation mechanism proposed for HIP would be in competition with the bulk diffusion of vacancies toward sinks. The analysis of the irradiation-induced process would require a detailed kinetic calculation, but since vacancy diffusion is not enhanced by irradiation, it would appear that the kinetics of vacancy and atom transport along the grain boundaries would be more rapid than bulk diffusion. Also, the loss of vacancies to recombination and possible depletion near the grain boundary sinks during a transient lend more credence to the proposed mechanism. It is perhaps relevant that in-reactor densification can be accurately represented by ex-reactor sintering behavior^[45] which supports the relevance of ex-reactor densification measurements.

5. Summary

The results from hot Isostatic pressing experiments performed on sintered hydride- and metal-derived U-10Zr samples were analyzed to quantitatively determine the dominant HIP mechanism. It was found that the specimen hot-pressing behavior agreed with the model predictions of Chen and Argon^[22] for coupled grain boundary diffusion and power-law creep controlled cavitation. It was found that the coupled model predicts an asymmetry between HIP and swelling rates which were previously assumed to be completely reversible phenomena. The differences in HIP behavior between the hydride- and metal-derived samples could be rationalized from the differences in pore size-to-spacing ratios.

The model of Chen and Argon was used to predict the time-dependent HIP behavior of U-10Zr using numerical integration. The result showed that HIP should not exhibit a characteristic time-dependence, in contrast to swelling where an exponential time dependence of $m=2/5$ is

predicted. Comparison of a calculated HIP transient with a hydride-derived HIP experiment showed good agreement between the calculated HIP rates and the measured HIP rates over most of the experimental transient.

The present HIP experiments were compared with similar post-irradiation HIP/swelling experiments on U-10Zr and U-5Fs. The U-5Fs hot-pressed and swelled much more rapidly than the U-10Zr under similar conditions. Therefore, the experience gained with U-5Fs transient response may not be appropriate for U-10Zr. Fuel performance codes should be modified to reflect the coupled diffusion/creep mechanism using the diffusion length calculation, but accurate knowledge of the fuel microstructure is necessary to differentiate between the diffusion-only and coupled rate-controlling mechanisms.

References

- [1] Walters, L.C., Seidel, B.R., and Kittel, J.H., Nuclear Technology, v65, 1984, 202.
- [2] Till, C., Nuclear Engineering International, v30, 1985, 20.
- [3] Hofman, G.L., Pahl, R.G., Lahm, C.E. and Porter, D.L., Metallurgical Transactions A, v21A, 1990, 517.
- [4] McDeavitt, S.M. and Solomon, A.A., to be published.
- [5] McDeavitt, S.M. and Solomon, A.A., World Congress of Powder Metallurgy, 1992.
- [6] McDeavitt, S.M., Ph.D. Thesis, Purdue University, Dec. 1992.
- [7] Abbott, R.C. and Solomon, A.A., Bull. of the Am. Cer. Soc., v58, 1979, 128.
- [8] Solomon, A.A., Cochran, K.M., and Habermeyer, J.A., NUREG/CR-2023, PUR-101, 1981.
- [9] Solomon, A.A., Casagrande, A., and Rest, J., J. of Nuclear Materials, v154, 1988, 332.
- [10] Xu, A. and Solomon, A.A., in Ceramic Microstructures '86: Role of interfaces, Ed. Pask, J., 1986.
- [11] Hsu, F. and Solomon, A.A., Acta Metallurgica, v31, 1983, 453.
- [12] Solomon, A.A. and Hsu, F., J. American Ceramic Society, v63, 1981, 467.

- [13] Xu, A. and Solomon, A.A., J. American Ceramic Society, v75, 1992, 985.
- [14] Solomon, A.A. and Hsu, F., Sintering Processes, ed. Kuczynski, Plenum Press, 1980, 485.
- [15] Kaur, I, Gust, W., and Kozma, L., Handbook of Grain and Interphase Boundary Diffusion Data, v.2, Ziegler Press, Stuttgart, 1989, p.1345.
- [16] Hull, D. and Rimmer, D.E., Philosophical Magazine, v4, 1959, 673.
- [17] Speight, M.V. and Harris, J.E., Metal Science Journal, v1, 1967, 83.
- [18] Vitovec, F.H., J. of Material Science, v7, 1972, 615.
- [19] Raj, R. and Ashby, M.F., Acta Metallurgica, v23, 1975, 653.
- [20] Raj, R., Shih, H.M., and Johnson, H.H., Scripta METALLURGICA, v11, 1979, 265.
- [21] Weertman, J., Scripta METALLURGICA, v7, 1973, 1129.
- [22] Speight, M.V. and Beere, W., Metal Science, v9, 1975, 190.
- [23] Chuang, T.J. and Rice, J.R., Acta Metallurgica, v21, 1973, 1625.
- [24] Chuang, T.J., Kagawa, K.I., Rice, J.R., and Sills, L.B., Acta Metallurgica, v27, 1979, 265.
- [25] Chen, I.W. and Argon, A.S., Acta Metallurgica, v29, 1981, 1759.
- [26] Beere, W. and Speight, M.V., Metal Science, April, 1978, 172.
- [27] Wilkinson, D.S. and Ashby, M.F., University of Cambridge Report, CUED/C-Mats/TR.22, 1975.
- [28] Murray, P., Rodgers, E.P., and Williams, A.E., Trans. Brit. Ceram. Soc., v53, 1954, 474.
- [29] Mackenzie, J.K. and Shuttleworth, R., Proc. Roy. Soc. B, v62, 1949, 833.
- [30] Wolfe, R.A., Bettis Atomic Laboratory Report, WAPD-T-2021, 1967.
- [31] Dyson, B.F., Metals Science, v10, 1976, 349.
- [32] Rice, J.R., Acta Metallurgica, v29, 1981, 675.
- [33] Anderson, P.M. and Rice, J.R., Acta Metallurgica, v33, 1985, 409.
- [34] Davanas, K. and Solomon, A.A., Acta Metall. Mater., v38, 1990, 1905.
- [35] Edward, G.H. and Ashby, M.F., Acta Metallurgica, v27, 1979, 1505.
- [36] Rice, J.R., Time-Dependent Fracture of Materials at Elevated Temperature, Ed. S.Wolf, USDOE report, CONF 790236 UC-25, Germantown MD, 1979, p. 130.

- [37] Needleman, A. and Rice, J.R., Acta Metallurgica, v28, 1980, 1315.
- [38] Stocker, R.L. and Ashby, M.F., Scripta METALLURGICA, v7, 1973, 115.
- [39] Derby, B. and Ashby, M.F., Scripta METALLURGICA, v18, 1984, 1079.
- [40] Solomon, A.A., Hofman, G.L., and McDevitt, S.M., to be submitted for publication.
- [41] Billone, M.C., Argonne National Laboratory, private communication
- [42] Rest, J., Journal of Nuclear Materials, v120, 1984, 195.
- [44] Hesketh, R.V., Journal of Nuclear Materials, v35, 1970, 253.
- [45] Solomon, A.A., Journal of Nuclear Materials, v102, 1981, 346.
- [46] Rothman, S.J., "Diffusion in Uranium, Its Alloys, and Compounds," ANL-5700, Part C, Argonne National Laboratory, 1961.

ACKNOWLEDGEMENTS

The authors express their appreciation to Nuclear Metals, Inc. for providing the uranium powder, to Oak Ridge National Laboratory for providing the uranium hydride powder, and to the U.S. Department of Energy for financial support under contract #DE-FG07-88ER12814.

Figure 1. Initial HIP strain rates at 1 minute vs. the initial pressure driving force.

Figure 2. Speight-Beere model geometry.

- (a) Top view of Beere-Speight geometry. Region I is the diffusion zone, and Region II is the creep-dominated zone.

- (b) Side view of Beere-Speight geometry.

Figure 3. Beere-Speight model geometry.

Figure 4. Comparison of diffusion-controlled cavitation model with U-10Zr HIP rates.

Figure 5. Free-body diagram grain boundary stresses during HIP.

Figure 6. Comparison of creep-controlled cavitation models with U-10Zr HIP rates.

Figure 7. Variation of the diffusion zone radius with external pressure.

Figure 8. Comparison of coupled cavitation model of Chen and Argon with U-10Zr HIP rates.

Figure 9. Calculated time-dependence of hydride-derived U-10Zr HIP transients using the coupled model of Chen and Argon.

Figure 10. Comparison of a single hydride-derived HIP transient and a comparable, calculated HIP transient based upon identical conditions.

Figure 11. Comparison of U-5Fs and U-10Zr post-irradiation swelling rates with sintered U-10Zr HIP rates (700°C).

Table 1. Material properties of U, Zr, and U-Zr.

Property	Data	Source
Hydride-Derived:		
Cavity density, N_v (m^{-3})	9.3×10^{14}	McDeavitt ^[6]
Modal diameter, r_p (μm)	1.6 ± 0.1 †	McDeavitt ^[6]
Avg. Spacing, λ (μm)	10	McDeavitt ^[6]
Grain Size (μm)	34	McDeavitt ^[6]
Internal pressure, p (MPa)	1.7 †	McDeavitt ^[6]
Metal-Derived:		
Cavity density, N_v (m^{-3})	5.8×10^{14}	McDeavitt ^[6]
Modal diameter, r_p (μm)	1.3 ± 0.1 †	McDeavitt ^[6]
Avg. Spacing, λ (μm)	7	McDeavitt ^[6]
Grain Size (μm)	114	McDeavitt ^[6]
Internal pressure, p (MPa)	1.2 †	McDeavitt ^[6]
γ-U Boundary Diff.:		
Pre-exp, $(D_b\delta_b)_0$ (m^3/s)	3.24×10^{-11}	Kaur, Gust, and Kozma ^[15]
Act. Energy, Q (KJ/mole)	186.6	Kaur, Gust, and Kozma ^[15]
$D_b\delta_b$ @ 700°C (m^3/s)	3.1×10^{-21}	$D_b\delta_b = (D_b\delta_b)_0 \cdot \exp(-Q/RT)$
γ-U Volume Diff.:		
Pre-exp, $(D_v)_0$ (m^2/s)	1.12×10^{-7}	Rothman ^[46]
Act. Energy, Q (KJ/mole)	112	Rothman ^[46]
D_v @ 700°C (m^2/s)	1.2×10^{-13}	$D_v = (D_v)_0 \cdot \exp(-Q/RT)$
D_v(Zr) in U-Zr alloys:		
20 at.% Zr:		
Pre-exp, $(D_v)_0$ (m^2/s)	10^{-8}	Rothman ^[46]
Act. Energy, Q (KJ/mole)	113	Rothman ^[46]
D_v @ 700°C (m^2/s)	8.6×10^{-15}	$D_v = (D_v)_0 \cdot \exp(-Q/RT)$
10 at.% Zr :		
Pre-exp, $(D_v)_0$ (m^2/s)	10^{-7}	Rothman ^[46]
Act. Energy, Q (KJ/mole)	134	Rothman ^[46]
D_v @ 700°C (m^2/s)	6.5×10^{-15}	$D_v = (D_v)_0 \cdot \exp(-Q/RT)$

† denotes post-sintering values prior to HIP @ 700°C

APPENDIX C

Liquid Sodium Intrusion into Porous U-10Zr Fuel Alloy by Differential Capillarity

Final Report on
Liquid Sodium Intrusion into Porous U-10Zr Fuel Alloy
by Differential Capillarity

by Weijun Liu and Alvin A. Solomon

School of Nuclear Engineering
Purdue University

December, 1992

ABSTRACT

The objective of this study was to simulate the intrusion behavior of liquid sodium into porous irradiated metal fuel, using sintered U-10Zr alloy specimens. Specimens were fabricated with about ~30% open porosity, and an average pore diameter of $2\mu\text{m}$ to simulate the condition of bubble and tear interconnection at low burnup. The intrusion volumes determined from weight-gain measurement were measured at 150°C and 400°C in a pressure range of 20 to 800 psig. Sodium extrusion from pressurized pores was also measured to verify the existence of retained gases as a function of their pressure.

The intrusion results showed essentially complete gas release and intrusion for low pressures, but gas retention at the highest gas pressure within the pores. It is argued that the highest pressure test may be rationalized such that complete intrusion was likely for all specimens. A model for gas-release in wetting systems is developed based on capillary attraction into small pores and gas release from larger pores, a mechanism we call Differential Capillarity. The criterion for gas release is a function of the pore diameters and wetting angle. To test the model, two specimens made of fully-dense Brass and U-10Zr alloy with drilled holes were intruded at low pressure by Dioctyl phthalate (at 20°C) and sodium (at 400°C), respectively. The holes in the U-10Zr were tapered which permitted intrusion to occur as predicted, while the holes in the brass were of uniform diameter and no penetration was measured.

I. INTRODUCTION

1.1 BACKGROUND

Uranium-based nuclear fuels have historically been saddled with the problem of swelling caused primarily by the accumulated gaseous fission products and by anisotropic irradiation growth which leads to “tearing” or fracture at the grain boundaries. In the Integral Fast Reactor, IFR, fuel design, these inherent problems are addressed by providing a large, sodium-filled gap between the fuel and cladding which allows the fuel to swell ~25% and develop a network of interconnected open porosity at approximately the time the fuel contacts the cladding. Ideally, this network then either allows easy pathways for gas release, or provides a deformable structure to accommodate subsequent swelling caused by fission product accumulation. One major issue in this scenario is the significant decrease in fuel thermal conductivity with the development of the high porosity. The present investigation was undertaken to determine the extent to which sodium intrusion into the open porosity can ameliorate the loss in conductivity.

There is anecdotal, experimental and inferential evidence that sodium penetrates the fuel to some degree. Instrumented irradiations have shown a significant decrease in fuel temperature after pores interconnect and open^[1]. A decrease in sodium level is also observed^[2] and sodium is found present during sectioning of the fuel^[2]. Also, fuel temperatures inferred from post-irradiation microstructures suggest rather complete penetration of the Na at least into the outer regions of the fuel^[3].

In the only previous attempt to *quantify* the sodium penetration, Villarreal, measured the Na remaining in irradiated U-10Zr, U-8Pu-Zr and U-19Pu-Zr fuels after 10

to 12% burnup by dissolution of fuel segments in acid^[4]. There is some ambiguity in the results because he attempted to separate the sodium in the “gap” from the Na in the fuel by reacting and “washing off” the surface layer of Na and found for U-10Zr, a little less than half of the Na was in the gap. It is not clear how much of this should have properly been included in the fuel. If none of this sodium is included in the fuel, approximately 6 to 25 vol% of the porosity (calculated as volume increase) is occupied by sodium, and almost double that percentage if all the “gap” Na is included in the fuel. Thus, there is considerable uncertainty and scatter in the results, but at a maximum, 50vol% of the pores are predicted to be filled with sodium.

It can be assumed that early-on in the irradiation, when the irradiation tears and gas bubbles interconnect, all of the porosity is measured to be interconnected and therefore accessible to sodium penetration. In face, this penetration may prevent re-sintering of the porosity after gas release as measured in other systems^[5]. Therefore the present investigation focused on the critical event of pore interconnection, gas release and sodium penetration at low burnup. Simulated porous U-10Zr fuel was produced by sintering and penetration was examined as a function of temperature and ambient pressure. At high retained gas pressure, sodium was also extruded from the pores if the sodium was melted and the external pressure were reduced.

1.2 THEORY

Various studies have revealed that the penetration of a liquid into a porous solid depends on the pore structure, surface energies of all interfaces and external pressure applied to the liquid^[6]. In order to intrude gas-filled pores, the liquid/gas interface must come into mechanical equilibrium with the gas pressure, with the help or resistance of capillary force. Mechanical equilibrium requires that the pressure difference between the

penetrating liquid and gas be balanced by the surface tension of the curved liquid/gas interface. As shown in Fig.1, for a cylindrical pore with radius r , equilibrium can be established under the following condition [7]:

$$\Delta P = 2\gamma_{lg} / \frac{r}{\cos \theta} \quad \dots\dots\dots (1)$$

or

$$P_l = P_g - 2\gamma_{lg} / \frac{r}{\cos \theta} \quad \dots\dots\dots (2)$$

where P_g and P_l are the pressures of gas and liquid, respectively; $r/\cos\theta$ is the radius of curvature of the liquid/gas interface; γ_{lg} is surface tension of the interface and θ has the definition shown in Fig.1. It is necessary for a liquid to have a pressure higher than the P_l predicted from Eq(2) to intrude into the pores spontaneously. If the gas is trapped within the specimen, intrusion will stop when P_g has increased to satisfy Eq(2).

It should be noticed that γ_{lg} and r are positive, therefore, the sign of ΔP is determined only by the value of $\cos\theta$. For poorly wetting conditions $\cos\theta < 0$ (or $\theta > 90^\circ$), we have $\Delta P < 0$ or $P_l > P_g$, and an external pressure must be applied on the liquid to penetrate into the pores. For well-wetted conditions $\cos\theta > 0$ (or $\theta < 90^\circ$), Eq(2) gives the equilibrium pressures $P_l < P_g$. In this case, the capillary force induces intrusion of the liquid into the porous solid without additional external pressure.

The contact angle θ is related to the three surface tensions by the well-known Young's equation [8]:

$$\gamma_{lg} \cos\theta = \gamma_{sg} - \gamma_{sl} \quad \dots\dots\dots (3)$$

where γ_{sg} , γ_{sl} and γ_{lg} are the surface tensions of the solid-gas, solid-liquid and liquid-gas interfaces, respectively, and can be measured through simple experiments^[9]. Obviously, θ depends on the surface chemical composition of the three phases in the system as well as temperature. For liquid metals on solid metals with very low mutual solubility, it has been found that the equilibrium θ at the melting point of the liquid follows the empirical relation^[10]:

$$1 - \cos\theta = K(T_{m1}/T_{m2} - 1) \quad \dots\dots\dots (4)$$

where T_{m1} and T_{m2} are the melting temperatures of the solid and liquid, respectively, and K is a constant, whose theoretical value is 0.28^[11], and the experimental value is 0.36^[10]. By applying Eq(4) to the Na / U-10Zr system in which T_{m1} and T_{m2} are 1396K and 372K, respectively, we obtain $\theta=91^\circ$ at the melting point of sodium. This result, which means that liquid Na does not wet U-10Zr at about 100°C, is accordant with experimental observations^[12] and probably results from a presumably low solubility of oxide layers on U-10Zr in Na at low temperature.

Both temperature and time play important roles in the onset of wetting. Sodium has been found to not wet U-10Zr alloy when the temperature is lower than 200°C, but at 370°C and 400°C it appears to wet the alloy after 8 hours and 1 hour, respectively^[12]. Austenetic stainless steels exhibit a similar time/temperature dependence for wetting by Na^{[13][14]}. The observed time required for wetting suggests that wetting is a kinetic process involving the removal or dissolution of the oxide surface layers on the solid.

The temperature dependence of the contact angle has been found to be negligible after wetting has occurred in some sodium/metal and sodium/oxide systems^[14]. This result implies that, after the surface layer is removed and the liquid wets the solid, the

composition of the surface remains relatively stable with temperature and surface energies and contact angles do not change dramatically with temperature. Therefore, de-wetting in a clean (non-oxidizing) system is assumed not to occur when the temperature is subsequently reduced below the “wetting” temperature.

Unfortunately, contact angles are not available for the Na / U-10Zr system as a function of temperature. Dodds and Henslee^[11] estimated the contact angle to be 20°, which is the typical value for most metal(s)/metal(l) systems under wetting conditions^[15]. However, Bader and Busse^[14] showed that the contact angles for *sodium* on different pure metals (Ni, Ta, Nb, Mo, W), alloys (ss 304L, Inconel 600, RTG 36, and TZM) and oxides (Al₂O₃, sapphire, ZrO₂, Y₂O₃) ranged from <1.0° to 7.3° between 520°C and 720°C. In the absence of primary data, we have assumed a temperature-independent contact angle of 10° for Na / U-10Zr after wetting was achieved at 400°C for 1 hour.

The surface energy γ_{lg} may be different from γ_{lv} which is the surface energy of a liquid/vacuum interface. For active gases, the difference between γ_{lg} and γ_{lv} may be very great because the chemical reactions between the gas and liquid can change the composition of the liquid near the interface^[16]. However, for inert gases, it is expected that the difference is small especially when the gas pressure is low.

Several methods have been developed for measuring γ_{lv} ^[17], and data on liquid metals at the melting temperature are available^[18]. Some empirical rules have been established relating the surface tension γ_{lv} to other properties of the metals. Skapski^[19] suggested that γ_{lv} (in J/m²) and the heat of vaporization of the liquid metal ΔH_v (in J/mol) follow a linear relation:

$$\gamma_{lv} = K' \Delta H_v \quad \dots\dots\dots (5)$$

where K' is a proportionality constant with an experimental value of 0.15 to 0.16. Another relation was proposed by Allen^[18] who showed that the surface tension of pure liquids could be described by:

$$\gamma_{lv} = K'' T_m (M/\rho)^{-2/3} \quad \dots\dots\dots (6)$$

where T_m (K) is the melting temperature and M (g) and ρ (g/cm³) are the molecular weight and density of the liquid, respectively, and $K'' = 3.6 \times 10^{-7}$ J/K. For liquid sodium in which $T_m = 371$ K, $M = 23$ g and $\rho = 0.97$ g/cm³, Eq(6) yields γ_{lv} at the melting temperature of 0.162 J/m². This value is relatively close to the γ_{lg} of Na(l)-Ar(g) interface that is measured as 0.210 J/m²^[20]. The γ_{lv} of Na, K, Rb and Cs were found to decrease linearly with temperature. This trend for those liquid metals is in agreement with an analytical model of γ_{lv} for liquid metals by Lukabov^[21].

Time may still play an important role in the penetration process even when the surfaces are chemically stable because it takes time for a liquid to flow into a porous body. The flow resistance caused by the viscosity η of a liquid may be examined using a model by Semlak (1958). The distance x traveled by the liquid through a capillary of radius r after a time t under fixed ΔP can be estimated by the following equation^[22]:

$$4\eta x^2 = r^2 t (\Delta P + 2\gamma_{lg} \cos\theta/r) \quad \dots\dots\dots (7)$$

For liquid sodium at $T = 400^\circ\text{C}$ in Ar, the viscosity η and the surface tension γ_{lg} are 0.0284 N-s/m² and 0.179 J/m², respectively^[20]. Assuming $\Delta P = 0$ for minimum x , $r = 10^{-6}$ m (1 μm) and $\theta = 20^\circ$, we can estimate from Eq(7) that molten sodium will travel 13.3 mm after

1 minute, which makes viscous flow not an issue in the 5 mm diameter specimens used in the present investigation.

1.3 GAS RELEASE CRITERION

The equilibrium pressure difference ΔP between liquid and solid in both sides of the interface are determined only by the pore radius for a given system. From Eq(1) we can see that the smaller the radius, the larger is ΔP . For relatively small bubbles, the pressure head due to gravity is negligible. A porous body 10cm high immersed in sodium ($\rho=0.97 \text{ g/cm}^3$) has a pressure head of less than 0.1psi, which is very small compared to the pressure differential ($\sim 270\text{psi}$) caused by the pore size difference in the present specimens, and can not explain how the entrapped gases are released. .

If we rapidly immerse a solid with cylindrical pores of uniform diameter into a wetting liquid, the liquid will be drawn into all the pores by capillary force and compress the gas until the gas pressure equals to the equilibrium pressure P_g determined by Eq(2). Because there is no gas release during the intrusion process, the equilibrium volume of gas can be obtained by the relation $P_g V = \text{constant}$ at constant temperature. As discussed above, the initial P_g equals to the ambient pressure P_o , the equilibrium P_g can be calculated from Eq(2) and the initial gas volume is the open porosity of the solid.

For solids with pores of varying diameter, however, the equilibrium pressures are different. Pores with smaller radii will have higher equilibrium pressures consistent with their higher capillary forces. Therefore, liquid intrusion into smaller pores can push the liquid and gas from larger pores causing greater penetration of the liquid. We call this phenomenon *Differential Capillarity*. Now the question is: under what conditions would gas release occur?

Let us consider a simplified pore structure shown in Fig.2a, immersed in a wetting liquid under pressure P_l . Before any intrusion occurs, the gas pressure inside the pores P_g equals pressure in the liquid P_l which is held constant under an ambient gas pressure. At $t=0$, the gas pressure $P_g=P_l$ is lower than the equilibrium pressure for either pore, therefore, the liquid will start to penetrate into both pores. As the liquid intrudes, the volume of gas becomes smaller and the gas pressure increases. When the gas pressure reaches $P_2=P_l+2\gamma_{lg}\cos\theta/r_2$, the interface in pore 2 attains mechanical equilibrium and stops to propagate (Fig.2b). However, the gas pressure P_2 is still lower than the equilibrium pressure for pore 1, so the capillary force draws more liquid into pore 1 increasing the gas pressure. This higher gas pressure will then tend to push the liquid outward from pore 2 (Fig.2c) producing a gas bubble that will attempt to reduce its curvature to balance the pressure P_l (Fig.2c). The minimum radius the interface can have is the radius of the pore r_2 corresponding to a pressure P_c . If $P_l>P_c$, the gas bubble will then become unstable and presumably detach from the surface from buoyancy effects. Using Eq.2, the criterion for gas release can therefore be expressed as:

$$P_l+2\gamma_{lg}\cos\theta/r_1 > P_l+2\gamma_{lg}/r_2$$

which reduces to a simple criterion for gas to be released:

$$r_1/r_2 < \cos\theta \quad \dots\dots\dots (8)$$

For a completely wetting or spreading system ($\theta=0^\circ$), the liquid/gas interface inside pore 1 will always propagate until it fills with liquid. For a partially wetting system (where $0^\circ<\theta<90^\circ$), the interface propagation may continue and gas may release only when the difference in radius is large enough. If $\theta=60^\circ$, for example, r_1 must be smaller than half of

r_2 in order that gas can escape, leading to the condition shown in Fig.3a. If this is not the case, very little penetration will occur as shown in Fig.3b.

For a tapered pore with diameters r_1 and r_2 ($r_1 < r_2$) at its extremities, the liquid intrusion process is similar to the bi-size pore situation: the small side will fill with liquid and the other part of the pore will contain compressed gas (Fig.4). In this case, however, the curvature of liquid/gas interface, and hence its equilibrium pressure, is affected by the angle ϕ of the pore wall and becomes equal to $r_1/\cos(\theta+\phi)$, where r_1 is the pore radius at the point of contact, and Eq(8) reduces to

$$r_1 / r_2 = \cos(\theta+\phi) \quad \dots\dots\dots (9)$$

True pore structures are, of course, much more complicated than the two cases we have analyzed. First of all, even if the pores are cylindrical, the cross section of the pores may be any shape far from a circle. Mortensen and Cornie^[23] have used the First Law of Thermodynamics to equate the work done in advancing the liquid/gas interface, $-\Delta P \cdot \Delta V$, to the total surface energy change $(\gamma_{sg} - \gamma_{sl}) S^*$

$$(\gamma_{sg} - \gamma_{sl}) S^* = -\Delta P \cdot \Delta V \quad \dots\dots\dots (10)$$

where S^* is the wetted surface area per unit volume and ΔV is the intrusion volume. Combining Eq(1), (3) and (10) we obtain the effective radius of the pore:

$$\begin{aligned} r^* &= 2 \Delta V / S^* \\ \text{or} \quad r^* &= B / 2\pi \quad \dots\dots\dots (11) \end{aligned}$$

where B is the perimeter of the pore. We can then express the gas release criterion using the perimeter instead of radii of the pores. Eq(8) can be rewritten as:

$$B_1/B_2 < \cos\theta \quad \dots\dots\dots (12)$$

Thus, using Eq(8) or (12), for a solid in which the radii or perimeters of open pores vary in a very narrow range, most of the pores will not satisfy the gas-releasing criterion for partially wetting liquids, but for wide radius distributions, most of the pores will satisfy the criterion and fill with liquid, if they do not form the “gas pockets” discussed below, or lead to partial penetration as shown in Fig.3a.

For non-wetting liquids, their surface energy always act against the gas bubble forming on the external surface of the solid and therefore prevents gas release. Following the above analysis, it can be seen that there will *not* be gas release in non-wetting situations, if gravity or buoyancy forces are negligible. Thus, in mercury intrusion porosimetry, the specimen is always evacuated before attempting to penetrate with mercury.

A second effect, called the “inkwell effect” in mercury-intrusion porosimetry, concerns the difficulty of intruding pores with small openings. For wetting liquids, an analogous effect shown in Fig.5 may be called a “gas-pocket” effect. Small pores are readily intruded, but large pockets may prevent intrusion beyond some point and become stabilized by the retained gas. Thus the degree of liquid intrusion may depend sensitively on the detailed pore morphology. For a wetting liquid, such large pockets may represent the dominant volume fraction of porosity.

II. EXPERIMENT

Within the range of 20°C~400°C, both sodium and U-10Zr alloy can react with oxygen in very low oxygen partial pressures (less than 10^{-44} ppm)^[24]. Such reactions will produce oxides that change γ_{sl} and γ_{lg} . Therefore, commercial grade Ar, was purified by an oxygen trap[‡] and molecular sieve[#] during specimen preparation and sodium intrusion tests to minimize the oxidation of sodium and U-10Zr alloy with the gas phase. The partial pressure of oxygen in the purified Ar was measured at the exhaust at 400°C using a solid state oxygen sensor[¶] to be 10^{-8} ppm. This appeared to permit reproducible results and negligible weight loss during the experiment^{*}.

In producing the porous U-10Zr specimens, the method developed by McDeavitt and Solomon^[25] was followed. First, pure uranium hydride UH₃ and zirconium hydride ZrH₂ powders were mixed by hand in an alumina mortar and pestle for about two minutes inside a purified argon atmosphere ($P_{O_2} < 10^{-8}$ ppm) glovebox in a weight ratio of 8.9:1^[26] (which gives the desired weight ratio U:Zr = 9:1 after decomposition of the hydrides). The powders were then dry-pressed in a double-action punch and die under a pressure 550 MPa for 10 seconds to form cylindrical pellets with dimensions of 7.2mm and ~5.5mm in diameter and height, respectively. The geometrical green density was 6.20 g/cm³ or 57% T.D. The green body was then inserted into the sintering vessel and sealed within the glovebox to avoid exposure to the air before attaching to the sintering pressurization system^[25]. The specimens were then heated up at a rate of 16°C/min under rough vacuum.

‡ Oxy Absorbent, Alltech Associates, Inc.

Grade 514GT 4A, Fisher Scientific

¶ Thermox 1A, Ametek Corp.

* Higher oxygen levels caused significant weight loss.

The evolution of hydrogen during decomposition minimized back flow of air through the pump. After the hydrides had decomposed completely (250°C ~ 500°C for UH_3 and 600°C ~ 900°C for ZrH_2)^[25], the Ar pressure was increased to 250 psig and the specimens were sintered at 1100°C for 10 minutes, and then the vessel was cooled to room temperature in about 15 hours to yield a geometric relative density of 70%.

The immersion densities of the as-sintered specimens were determined using absolute ethyl alcohol. An electronic balance* with sensitivity of $\pm 0.000005\text{g}$ located outside the glovebox was used to measure the weights of the specimens before and after they were immersed into alcohol under vacuum. The pore-size distribution of an as-sintered specimen was obtained through mercury intrusion porosimetry#. Specimens for microstructural analysis were sectioned with diamond, mounted in epoxy, and polished to $1\mu\text{m}$ diamond and examined using scanning electron microscopy.

To perform the sodium intrusion experiments, the sodium was contained in a stainless steel beaker inside a Hastalloy C-276 alloy pressure vessel ^[27], which was designed to be capable of withstanding high temperature and pressure up to 400°C and 2000 psig, respectively, Fig.6. A thermocouple was inserted into the sodium to measure its temperature during the tests. The specimen holder shown in Fig.6 could be moved up and down through a Conax† fitting, without causing gas leakage into or out of the vessel which permitted specimen insertion and withdrawal from the molten sodium.

* Mettler H51AR, Mettler Instrument Corp.

Courtesy of Dr. D. Winslow , Purdue University

† Conax Buffalo Corp.

Because of the rapid reaction of the porous specimen in air, all assembly operations were performed in the inert atmosphere glovebox. To assemble the system, the specimen was first weighed with an electronic balance* of $\pm 0.0001\text{g}$ sensitivity, placed in the specimen holder and inserted into the pressure vessel. The pressure vessel was then sealed, removed from the glovebox and connected to the purified argon supply as shown in Fig.6, and the lines were evacuated. The pressure inside the pressure vessel was controlled by feeding gas from the accumulator or evacuating with the mechanical vacuum pump. The pressure or vacuum inside the pressure vessel was continuously monitored by a strain gage pressure sensor# or a thermocouple gauge, respectively.

To perform the experiments, the pressure of Ar inside the vessel was first set at an initial pressure $\sim 20\text{psig}$ to prevent in-leaks. Heating was begun at a rate of $5^\circ\text{C}/\text{min}$, and at 100°C the pressure was adjusted to P_0 and the specimen was lowered into the molten sodium. It was important to immerse the specimen under non-wetting conditions to prevent "wicking" of the sodium and displacement of the gas during immersion itself. After that, the vessel was closed to the gas supply and vacuum pump to minimize contamination and, therefore, the pressure in the vessel increased with temperature until it reached the testing temperature of $\sim 400^\circ\text{C}$ in about 40 minutes. The specimen was held at this temperature for 4 hours to allow wetting and intrusion. After intrusion, the hot plate was turned off and the vessel was allowed to air-cool to $\sim 100^\circ\text{C}$ in about one hour, and the specimen was withdrawn from the liquid sodium and allowed to cool to room temperature. The intruded Na was assumed to come into mechanical equilibrium with the ambient gas pressure that existed just before freezing (100°C).

* Mettler AJ100, Mettler Instrument Corp.

Sentra 280E, Sentra Systems Inc.

After the intrusion experiment, the specimen was taken out of the holder in the glovebox. The excess sodium adhering to the surface was removed with a stainless steel spoon and the specimen was weighed. The amount of intruded sodium in the open pores was determined from the weight gain. To verify that some gas was retained, two specimens with high pressure entrapped gas were then re-heated up to the melting temperature of Na inside the glovebox to observe bubbles forming on the surface. Because the pressures of the entrapped gas were higher than ambient pressure in the glovebox, some molten sodium was extruded from the pores. After this sodium had also been removed, the specimens were re-weighed to determine the amount of extruded sodium.

Our initial experiments, using chemical grade sodium (Mallinckrodt Inc.), showed that, fully dense U-10Zr alloy from Argonne National Laboratory ANL (Chicago, IL) would lose 3% of its weight after 4 hours at 400°C in purified Ar, and porous specimens showed a 1% weight loss instead of the expected weight gain due to sodium intrusion. Although the detailed mechanism is unknown, it is likely that the weight loss was caused by reactions between the impurities in the sodium and the alloy. Surface degradation was noted along with loss of material from the surface. (This degradation process could have important implications in safety, quality assurance, reprocessing and reactivity calculations.) To avoid this problem, reactor-grade sodium[¶] was used in subsequent intrusion tests. Some physical properties of sodium at different temperatures are listed in Table 1.

To confirm the chemical stability of the alloy in sodium and the testing environment as well as the technique of removing Na from the specimen surface, a fully- dense U-10Zr

[¶] courtesy of Paul Henslee and co-workers, Argonne National Laboratory.

specimen from ANL was tested at 400°C and 20 psig in the pressure vessel in the reactor-grade sodium. After 4 hours of testing the weight of the specimen was measured to be 1.4181g compared to the initial weight of 1.4186g. This result showed that, although some residual sodium could be seen on the surface, after scraping the surface with the spoon, the weight was identical to the original weight within experimental error. Compared to the normal weight gain (above 1%) from sodium intrusion, this weight loss is negligible. The result also implies that oxidation was negligible.

Several intrusion experiments were conducted under different temperature and pressure conditions. Two different testing temperatures, 150°C and 400°C, were selected to examine intrusion behavior under wetting and non-wetting conditions. Pressure effects on intrusion were measured in a pressure range from 10 mmHg to 1000 psig.

To virtually test the role of differential capillarity on intrusion behavior, identical size holes were drilled into specimens of fully-dense brass and fully-dense U-10Zr alloy from ANL. The geometry of the specimens and holes are showed in Fig.7. The brass specimen of $d=4.67\text{mm}$ had seven holes of a uniform 0.8mm diameter and 4.94mm length. It was intruded by 99% dioctyl phthalate[†] at room temperature. Dioctyl phthalate was selected because of the reported well-defined wetting angle on brass of 2° [28]. The holes in the U-10Zr alloy specimen of $d=4.92\text{mm}$ were found to be tapered with a maximum diameter of 0.90mm, a minimum diameter of 0.79mm, and a length of 4.74mm. (The unintentional tapering was apparently caused by "runout" of the carbide drills used, and was measured by inserting of drillrods closely varying diameter into the holes to various depths.) It was tested in sodium at 400°C exactly like the sintered specimens. The total

[†] from Aldrich Chemical Company, Inc.

pore geometric volumes were calculated to be 17.38mm^3 (21vol%) and 15.96mm^3 (18vol%) for brass and U-10Zr specimens, respectively. The weight changes before and after intrusion were measured and the volume percentages of intrusion over total hole volume were then calculated through the measured weight changes and the densities of dioctyl phthalate and sodium.

III. RESULTS

Porosities of the sintered U-10Zr specimens from immersion density and mercury intrusion measurements, listed in Table 2, showed good agreement with each other. In the following analysis, we take 30vol% as the open porosity of the sintered specimens. The original data obtained through mercury intrusion porosimetry, plotted in Fig.8, showed that the diameters of the pores were within the range of 0.4 to $3.6\mu\text{m}$, with an average diameter of $\sim 2.0\mu\text{m}$. Taking the derivative of Fig.8 shows the pore volume distribution in Fig.9. SEM microscopy (Fig.10) shows that the pores (dark area) were fairly uniformly distributed inside the specimen, and that an impurity phase of $\sim 25\text{vol}\%$ was found which had been earlier identified^[25] as zirconium stabilized with O, N and C impurities. For comparison, Fig.11 shows the pore structure of an irradiated U-10Zr[¶] at $\sim 30\text{vol}\%$ porosity.

The results of intrusion tests of the sintered U-10Zr alloy conducted at 150°C and 400°C under pressures of 20 psig to 800 psig are listed in Table 3, where P_0 represents the initial pressure at 100°C ; W_0 , W_1 and $\Delta W_1/W_0$ are the specimen weights before and after intrusion and weight gain fraction, respectively. It is obvious that in these highly porous

[¶] courtesy of Gerard Hofman, Argonne National Laboratory, Chicago, IL

specimens, the weight changes due to sodium intrusion ($>1.5\%$) were much higher than that of due to measurement error (about $\pm 0.04\%$); and weight changes under identical test conditions ($P_0=20$ psig and $T=400^\circ\text{C}$) were very reproducible.

The fractional intrusion volumes were also calculated and listed as $\Delta V_1/V_0$ in Table 3, based on the densities of sodium and the alloy, open porosity of the specimens as well as the weight gains. The results of sodium *extrusion* are also listed in Table 3, in which W_2 , $\Delta W_2/W_0$ and $\Delta V_2/V_0$ are the weight, %weight gain and fractional penetration, respectively, *after* extrusion. For specimen 1W tested at $P_0=100$ psig, 8.5% of the intruded sodium was extruded, and for specimen 1Z tested at $P_0=800$ psig, 65.6% was extruded, leaving the percentages of gas volume to total pore volume of 10.3% and 70.1%, respectively.

Sodium wettability was examined through immersion tests at 150°C and 400°C , with initial pressure $P_0=20$ psig. After treating at 150°C for 4 hours in molten sodium, the alloy surface remained sodium-free and showed no evidence of sodium/alloy contact at this temperature. For specimens held at 400°C for 4 hours and then cooled down to room temperature, however, sodium completely covered and adhered to the entire surface, which indicated small contact angle. Thus, once the surface has been wetted, there is no evidence of de-wetting at lower temperature under the conditions investigated. The effect of initial pressure P_0 on sodium intrusion was examined under wetting conditions at 400°C within a range from 20 psig to 800 psig which is plotted in Fig.7 from the data in Table 3.

The results of the intrusion tests for the specimens with drilled holes are listed in Table 4. The brass specimen was rapidly immersed in dioctyl phthalate to prevent wicking and exhibited a 0.00006g weight gain that represents 0.06mm^3 volume of dioctyl phthalate

intrusion. The U-10Zr alloy specimen exhibited a 0.0113g weight gain in sodium or an intruded volume of 11.65mm³.

IV. DISCUSSION

WETTING BEHAVIOR

The results of sodium intrusion into sintered specimens at low pressure (Table 3 and Fig.12) show a significant influence of capillarity on intrusion. Under wetting conditions (400°C), the porous specimens exhibited a 2.7% weight gain, whereas under non-wetting conditions (150°C) virtually no weight change was expected or detected. The fractional intrusion can be calculated from open porosity and weight gain of the specimen and the densities of U-10Zr alloy and sodium. It is found that at 400°C and low P_o , virtually completely intrusion (~99%) occurred. Thus for Na penetration to occur in nuclear fuels wetting is clearly a prerequisite. The effects of sodium purity and fuel surface condition on wettability are not known.

EFFECTS OF INITIAL PRESSURE ON INTRUSION

As discussed above, the gas pressures within the pores at 100°C equal $P_o + \Delta P$. According to Eq(2), ΔP depends on the surface energy γ_{lg} , contact angle θ and the pore size r . Using the assumed $\theta=10^\circ$, $r=1\mu\text{m}$ for the sintered specimens, and $\gamma_{lg}=0.210\text{J/m}^2$ for sodium at 100°C, we can obtain $\Delta P=60\text{psi}$ from Eq(2).

The lower curve in Fig.12, marked *0% Gas Release*, represents the effects of initial pressure on intrusion assuming no entrapped gas release from the pores. The relation

between the weight gain and the initial pressure P_0 can be obtained by considering an unit volume of specimen. For 1cm^3 of the sintered specimen the volumes of solid alloy and the open pore are $V_{\text{alloy}} = 0.7\text{cm}^3$ and $V_{\text{pore}} = 0.3\text{cm}^3$. Because there is closed porosity inside the solid alloy (see Table 2), the "apparent" solid density is $16.00 \times 0.947 = 15.15 \text{ g/cm}^3$ and, therefore, its weight before intrusion is $W_0 = 10.60\text{g}$ ($0.7\text{cm}^3 \times 15.15\text{g/cm}^3$). As discussed above, when the initial pressure is P_0 , the equilibrium pressure will be $P_e = (P_0 + 60)$ psi and the equilibrium volume of argon, V_e , can be obtained assuming $PV = \text{constant}$, or:

$$V_e = P_0 V_{\text{pore}} / (P_0 + 60)$$

The intrusion volume and weight of sodium, V_{Na} and W_{Na} , are:

$$V_{\text{Na}} = V_{\text{pore}} - V_e = 60V_{\text{pore}} / (P_0 + 60) = 18.0 / (P_0 + 60), \text{ cm}^3$$

$$W_{\text{Na}} = \rho_{\text{Na}} \cdot V_{\text{Na}} = 0.97 \times 18.0 / (P_0 + 60) = 17.46 / (P_0 + 60), \text{ g}$$

and the relation between the weight gain and P_0 is

$$\text{Weight Gain (\%)} = 100 \times W_{\text{Na}} / W_0 = 164.7 / (P_0 + 60) \quad \dots\dots (13)$$

In the situation in which all the gas releases from the pores, the volume of intruded sodium will equal to the volume of open porosity and there will be an 100% penetration, as shown in the dashed line marked as *100% Gas-Release* in Fig.12. Obviously, the initial pressure P_0 does not have any effect on intrusion when all the gas is released.

The solid points in Fig.12 represent the sodium intrusion results of sintered U-10Zr specimens at different temperatures and pressures. A decrease in penetration volume with pressure P_0 is apparently only at the highest pressure of 800 psig although complete penetration is never achieved.

EXTRUSION BEHAVIOR

After intrusion, one can calculate the percentages of pore volume occupied by the gas by assuming ideal gas behavior and no gas-release during the reheating and extrusion process. For specimen 1W ($P_0=115$ psia), the pressures of entrapped gas before and after extrusion test were 175 psia (115+60 psia) and 75 psia (15+60 psia), respectively, and the gas volume after extrusion was measured as 10.3vol% of the total pore volume; therefore, the volume percentage of entrapped gas before extrusion was only 4.4vol%. The same calculation procedure gives the volume percentage of entrapped gas in specimen 1Z ($P_0=815$ psia) before extrusion as 6.0vol%. These results suggest that the retained gas volume after intrusion was apparently independent of initial pressure P_0 , and it was about 5.2vol% for this particular material, liquid and testing condition.

The criterion for gas release, Eq.8, predicts that the penetrating liquid will occupy a pore of size d and the gas will be released if $d/d_{max} < \cos\theta$ is satisfied. The pore-size distribution measurement from mercury intrusion porosimetry showed that the maximum pore size was $d_{max}=3.6\mu\text{m}$ in the sintered specimens. So in the sintered specimens the maximum size of the pore that allowed sodium intrusion, at which the contact angle is 10°C , was

$$d^* = d_{max} \cos\theta = 3.6 \times \cos 10^\circ = 3.5 \mu\text{m}$$

From the pore-size distribution curve (see Fig.4), the volume of pores with sizes smaller than $3.5\mu\text{m}$ was 97.7% of the total volume which is in good agreement with the intrusion measurement and in fair agreement with the value of 5.2% of retained gas from the extrusion measurements.

MODEL EXPERIMENTS

The results of the intrusion tests in fully-dense brass and U-10Zr specimens with drilled holes, listed in Table 4, also supports the Differential Capillarity model. At 20°C, the density of dioctyl phthalate is 0.981 g/cm³; its contact angle on brass and surface energy in air are 2° and 0.0313 J/m², respectively^[21]. Therefore from Eq(2), the pressure difference across dioctyl-phthalate/air interface inside pores of 0.80mm diameter was a very small 0.023 psi. Because the diameters were constant in the brass specimen, the gas-release criterion is not satisfied, and no gas release is predicted during the intrusion process. The equilibrium gas volume can be calculated assuming ideal gas behavior. Thus for gas of 17.38 mm³ at an initial pressure of 14.70 psi, the equilibrium volume at a final pressure of 14.723 psi was 17.35 mm³ and the volume of intruded dioctyl phthalate should be 0.03 mm³. This compares well with the measured value of 0.06 mm³.

For the tapered holes in the U-10Zr specimens, the pressure differences across the sodium/argon interface were, from Eq(2), 0.13psi and 0.12psi for $d_1=0.79\text{mm}$ and $d_2=0.90\text{mm}$, respectively. If no gas had been released from the holes, the volume of sodium intrusion in this specimen should have been only 0.16mm³, based on the ideal gas behavior, rather than the measured 12.56mm³. According to the gas release criterion for tapered holes given in Eq(9), the ratio of d_1/d_2 , 0.88 for the tapered holes, was smaller than $\cos(\theta+\phi)$, 0.983 for $\theta=10^\circ$ and $\phi=0.7^\circ$. Therefore the release criterion was satisfied, and the diameter of the cross section to which liquid sodium can propagate from the smaller opening, d_i , was 0.88mm, from Eq(9); and the total intrusion volume of sodium was 12.75mm³ for this specimen, which is more accordance with the measured volume of 12.56 mm³.

The intrusion experiments conducted at $P_o < 115 \text{ psi}$ showed essentially complete logging of the specimens with sodium. Using the pore size distribution, only 2.3vol% of the pores would not satisfy the Differential Capillarity criterion, which is in reasonable agreement with the measurement of 4.9, 2.0 and 0.2vol%. However, the 800psig test showed an unexpected 44.6vol% of entrapped gas. In the subsequent extrusion test, if the entrapped gas had a pressure of 875psia ($815 + 60 \text{ psia}$), this gas should have expanded 520% when the pressure was reduced to 75psia, forcing all of the sodium from the pores. However, the gas only expanded to 70.1vol%. If the criterion for gas release is independent of pressure as predicted, some other explanation must be found for the low apparent intrusion and extrusion. One possibility is that the high pressure gas extruded the solidified sodium after the ambient high pressure was reduced, or there was a pressure leak in the system during cooling. If this occurred, the small volume of retained gas $\sim 5 \text{ vol\%}$ would have expanded to 58vol%, which is closer to what was measured, and the subsequent extrusion would be negligible as measured. If this explanation is correct, then the results indicate almost complete sodium intrusion in all U-10Zr specimens. However, it should be pointed out that other specimen morphologies with gas pockets or other irregularities may not exhibit such complete intrusion.

There is no simple explanation for the large discrepancy between the results of the present experiments and those of Villarreal^[4] which showed only small fractional penetration. The subsequent gas generation after the initial bubble interconnection and gas release should also have been released, since it is the *differential* pressures that cause the release. Also, the initial penetration of sodium should prevent resintering after gas release that might have trapped gas within the specimen. Even if one includes the “gap” sodium in Villarreal’s measurements, there is still only small increase in *total* sodium penetration. Several possible explanations for the discrepancy might be (1) a large gas-pocket effect in the central region, or (2) a significant change in wetting behavior or pore structure as the

fission product inventory increases, or (3) the build-up of the high density Zr-rich zone which prevents sodium penetration.

V. CONCLUSIONS

The results indicate that under wetting conditions, sodium penetrates sinter porosity readily and virtually completely at low retained gas pressure. The *differential capillarity* mechanism proposed quantitatively explains the process of gas release from such specimens, although the magnitude of the release will depend on the detailed pore morphology. Less penetration was measured at high retained gas pressure, and less extrusion of sodium was observed when the ambient pressure was reduced suggesting an inadvertent loss in external pressure during the experiment.

ACKNOWLEDGMENT

The authors are indebted to Dr. Sean McDevitt who originally suggested the possibility of Differential Capillarity.

REFERENCES

- [1] Beck, N. Private communication, 1991
- [2] Hofman, G. Private communication, 1991
- [3] Hofman, G.L. and Walters, L.C. "Materials Science and Technology" vol.10 Nuclear Materials (edited by B.R.T. Frost), Chapter 1, Metallic Fuels. (in press)
- [4] Villarreal, R. Memos to B. Pahe, Oct. 1987, Jan. 1988, Aug. 1988
- [5] Hsu, F. and Solomon, A.A. *Acta Metall.* v31, n.3, pp453-464, 1983
- [6] Delannay, F.; Froyen, L. and Deruyttere, A. *J. Mat. Sci.* v 22 pp1-16, 1987

- [7] Washburn, E.W. *Proc. Natl. Acad. Sci. U.S.* v7 pp115, 1921
- [8] Young, T. *Phil. Trans. R. Soc.* v 95 pp65, 1805
- [9] Deshpande, M.S.; Desai, P.D. and Solomon, A.A. "High Temperature Science"
vol.17, (The Humana Press Inc.) pp303-332, 1984
- [10] Eustathopoulos, N. and Pique, D. *Scripta Metall.* v14 pp1291, 1980
- [11] Guggenheim, E.A. *Trans. Far. Soc.* v41 pp150, 1945
- [12] Dodds, N.E. and Henslee, S.P. Private communication (1991)
- [13] Clark, R.B and Kruger, O.L. BMI 1868 ppA9-A15, 1969
- [14] Bader, M. and Busse, C.A. *J. Nuclear Materials* v67 pp295-300, 1977
- [15] Dokhov, M.P. *Izvestiya Akademii Nauk SSSR Metally* n.4 pp55, 1985
- [16] Delannay, F., Froyen, L. and Deruyttere, A. *J. Mat. Sci.* v22 pp1, 1987
- [17] Eustathopoulos, N. and Joud, J.C. "Current Topics in Material Science"
vol.4, edited by E.Kaldis (North-Holland, Amsterdam) pp281, 1980
- [18] Allen, B.C. "Liquid Metals: Chemistry and Physics" edited by S.Z. Beer
(Dekker, New York) pp161, 1972
- [19] Skapski, A.S. *J. Chem. Phy.* v16 pp869, 1948
- [20] "CRC Handbook of Chem. and Phys." 63rd Ed. edited by R.C. Weast and M.J.
Astle. CRC Press, Inc. 1983
- [21] Iakubov, I.T.; Khrapak, A.G.; Pogosov, V.V. and Trigger, S.A.
Solid State Communications v56 n.8 pp709-721, 1985
- [22] Semlak, K.A. and Rhines, F.N. *Trans. Met. Soc. AIME* (June) pp325, 1958
- [23] Mortensen, A. and Cornie, J.A. *Metall. Trans. A* v 18A pp1160, 1987
- [24] Darken, L.S. and Gurry, R.W. "Physical Chemistry of Metals " McGraw Hill,
New York, 1953
- [25] McDeavitt, S.M. and Solomon, A.A. to be published
- [26] Mueller, W.M., Blackledge, J.P., and Libowitz, G. G., "Metal Hydrides",
Academic Press, pp405, 1968

- [27] Pragna, B. M.S. Thesis, Purdue University. Dec. 1987
- [28] Fox, H.W.; Hare, E.F. and Zisman, W.A. *J. Phys. Chem.* v59 pp1097, 1950

[10]

Table.1 Physical Properties of Sodium

Temp (°C)	Density (g/cc)	Viscosity (poise)	Vapor Pressure (mm Hg)	Surface Energy (J/m ^2)
97.8	0.97			0.210
100	0.927	0.705		
127			2.23E-6	
200	0.904	0.450		0.021
227			0.00115	
300	0.882	0.345		0.191
327			0.0503	
400	0.859	0.284		0.179
427			0.881	
500	0.834	0.234		0.167
527			7.53	
600	0.809	0.210		0.154
627			39.98	

Table.2 Porosities of the Sintered U-10Zr Specimens

	Open Porosity	Closed Porosity
Immersion Method §	30.0 %	5.3 %
Mercury Intrusion	28.1 %	-

§ theoretical density (16.02 g/cc) was provided by Cerac Inc.

Table.3 Intrusion Data of Sintered U-10Zr Alloy and Brass

Specimen No.	Temp.(°C)	Po (psig)	Wo (g)	Intrusion Test			Extrusion Test		
				W1 (g)	$\Delta W_1/W_0$ (%)	$\Delta V_1/V_0$ (%)	W2 (g)	$\Delta W_2/W_0$ (%)	$\Delta V_2/V_0$ (%)
#1U	150	20	1.3872	1.3867	-0.04	0	-	-	-
	400	20	1.3867	1.4229	2.61	95.1	-	-	-
#1V	400	20	1.4715	1.5118	2.74	99.8	-	-	-
#1W	400	100	1.3028	1.3378	2.69	98.0	1.3348	2.46	89.6
#1Z	400	800	1.2740	1.2934	1.52	55.4	1.2845	0.82	29.9
Brass	20	0	0.61182	0.61188	0.01	0.35	-	-	-
#2A	20	0	1.1839	0.0113	0.95	73	-	-	-

Table.4 Intrusion Conditions and Results of Dense Specimens with Drilling Holes

Material	Liquid	Po (psia)	Temperature (°C)	Total Pore Volume (mm ³)	Intrusion Volume (mm ³)	
					Measured	Calculated
Brass	Dioctyl Phthalate	15	25	17.38	0.06	0.03
U-10Zr	Sodium	15	400	15.96	11.65	12.75

**FIG.1 SHAPES OF GAS BUBBLE INSIDE THE PORES
UNDER WETTING CONDITIONS**

FIG.2 ILLUSTRATION OF LIQUID INTRUSION PROCESS. (A) AT $t=0$ WHERE $P_g = P_o$;
 (B) AFTER INTRUSION OCCURS; (C) THE CRITICAL CONDITION FOR GAS RELEASE

(a) $r_1 / r_2 < \cos \theta$

(b) $r_1 / r_2 > \cos \theta$

FIG.3 THE EFFECT OF r_1/r_2 RATIO ON LIQUID PENETRATION

FIG.4 PENETRATION OF LIQUID INTO A TAPERED
PORE AT THE CRITICAL CONDITION

FIG.5 ILLUSTRATION OF THE GAS-POCKET EFFECT

FIG. 6 SYSTEM FOR SODIUM INTRUSION TEST

a) U-10Zr Alloy (x10)

b) Brass (x5)

FIG.7 CROSS-SECTIONS OF SPECIMENS WITH DRILLED HOLES

Fig.8 Average Mercury Intrusion vs. Pore Diameter

Fig.9 Normalized Pore Volume Distribution of Sintered U-10Zr Alloy

FIG.10 SEM MICROSCOPY OF SINTERED U-10Zr ALLOY

FIG.11 SEM MICROSCOPY OF AN IRRADIATED U-10Zr FUEL
(Courtesy of Gerard Hofman, ANL)

Fig.12 Weight Gain and Fractional Penetration of Sintered U-10Zr Alloy under Different Initial Pressure

APPENDIX D

Interdiffusion Between U-Zr Fuel and Selected Fe-Ni-Cr Alloys

Interdiffusion between U-Zr Fuel and Selected Fe-Ni-Cr Alloys

D. D. Keiser, Jr. and M. A. Dayananda
School of Materials Engineering
Purdue University, W. Lafayette, IN 47907

Abstract

As part of studies relevant to fuel-cladding compatibility in the Integral Fast Reactors, isothermal interdiffusion experiments were carried out at 700°C with solid-solid diffusion couples assembled with a U-23 at.% Zr alloy fuel and a series of cladding alloys of selected compositions in the Fe-Ni-Cr system. Besides pure Fe and pure Ni, the alloys included binary Fe-20.1 Cr, Ni-16.4 Cr, and Fe-10.1 Ni and a ternary Fe-16.4 Ni-9.4 Cr alloys (composition in at.%). The diffusion structures developed in the various couples were examined metallographically and by SEM-EDS analysis. The development of diffusion layers and their variation with compositional changes of the cladding alloys are discussed in the light of phase diagrams, intermetallic formation, the relative diffusion behavior of the various elements and the experimental diffusion paths. From the composition profiles, average effective interdiffusion coefficients are determined for specific regions in the diffusion structures of selected diffusion couples. Intrinsic diffusion coefficients are also calculated at the composition of a marker plane in a (U, Zr)Ni₂ phase layer.

1. Introduction

A new innovative nuclear reactor concept called the Integral Fast Reactor (IFR) which uses U-Pu-Zr metallic fuels with stainless steels as cladding alloys is being developed by Argonne National Laboratory [1]. The IFR exploits the good breeding performance, high burn-up potential, ease of fabrication, high thermal conductivity, and simple reprocessing characteristics of metallic fuels. At the reactor operating temperatures of 600° to 650°C, the metallic fuels have been shown to come into contact with the cladding [2]. This contact initiates interdiffusion between the fuel and the cladding and results in the development of diffusion structures that can adversely affect the structural integrity of the cladding alloy [3-8].

Early studies of fuel-cladding compatibility [9-12] with diffusion couples assembled with metal fuels and cladding alloys were unsatisfactory, as the couples suffered from poor bonding and oxide development. Such studies were carried out with cladding alloys such as stainless 304, 346, and Incoloy 800 and with U-5 wt.% Fs and U-Pu-Fs fuels, where Fs represents fission product consisting of 2.4 Mo, 1.9 Ru, 0.3 Rh, 0.2 Pd, 0.1 Zr, 0.01 Nb (by wt.%). Only limited diffusion studies have been reported for U- Pu-Zr alloys and cladding steels [8]. Hence, in order to assess the fuel-cladding compatibility for IFR fuels, it is essential to understand the relative interdiffusion behavior of the various elements in the fuel and cladding alloys and the type of intermetallic phases that can develop in fuel-cladding assemblies.

In this study, interdiffusion experiments were carried out at 700°C with a series of diffusion couples assembled with disks of a U-23 at.% Zr alloy and disks of pure Fe, pure Ni, selected binary Fe-Ni, Fe-Cr, and Ni-Cr alloys and an Fe-Ni-Cr ternary alloy. The binary U-23 at.% Zr alloy corresponds to an actual fuel used in reactor and the compositions of the cladding alloys are based on those of the commercial stainless steels. Experimental diffusion structures and diffusion paths for all diffusion couples are presented and discussed in the light of the relative diffusion behavior of the various elements and the intermetallic phases formed in the couples. From the composition profiles, average effective interdiffusion coefficients for the

For the description and representation of diffusion structure, experimental diffusion paths were generated from concentration profiles of Fe, Ni, Cr, U, and Zr as functions of distance for various diffusion couples. In multiphase regions only approximate average compositions could be determined. The diffusion path corresponds to the sequence of compositions developed within the diffusion zone of a solid-solid diffusion couple during isothermal diffusion. It is S-shaped when the compositions are plotted on a composition triangle and is independent of time since all concentration variables are considered to be functions of the Boltzmann parameter, λ , given by $x/\sqrt{t}$. For diffusion paths of couples with more than 3 components, the sum of the concentrations of Fe, Ni and Cr is taken as one concentration variable. The diffusion path is especially useful for describing the development of various diffusion layers in the context of phase equilibria and isotherms.

3.1.1. Couples *F(U-23 Zr) vs. Ni* and *F(U-23 Zr) vs. Ni-16.4 Cr*

Diffusion structures developed for the F vs. Ni and F vs. Ni-16.4 Cr couples are presented in Figures 1 and 2, respectively. The phases identified in the structures are similar to those expected on the basis of the binary phase diagrams. As can be seen in Fig. 1, the F vs. Ni couple exhibits single-phase layers of UNi_5 , UNi_{3-4} , U_5Ni_7 , and $(\text{U,Zr})\text{Ni}_2$. Adjacent to the $(\text{U,Zr})\text{Ni}_2$ are observed two contiguous two-phase layers; one contains U_6Ni and $(\text{Zr,U})_7\text{Ni}_{10}$ phases and the other U and $(\text{Zr,U})_2\text{Ni}$ phases. The designations of the individual phases are essentially based on the approximate ratios of concentrations of the individual elements. The diffusion structure for the F vs. Ni-16.4 Cr couple shown in Fig. 2 differs slightly from that for the F vs. Ni, as an additional $(\text{Cr} + \text{UNi}_5)$ two-phase layer appears on the alloy side of the diffusion structure.

The concentration profiles for the F vs. Ni-16.4 Cr couple are presented in Fig. 3 where the solid vertical lines represent boundaries between various phase layers or regions. The layers numbered 1-6 correspond to a $[\text{Cr} + \text{UNi}_5]$ two-phase layer, UNi_5 , UNi_{3-4} , U_5Ni_7 , and $(\text{U,Zr})\text{Ni}_2$ single-phase layers and a two-phase $[(\text{U,Zr})\text{Ni}_2 + \text{U}_6\text{Ni}]$ layer, respectively. Most

individual components have been calculated over selected regions of diffusion couples. Intrinsic diffusion coefficients have also been calculated for selected intermetallic phases.

2. Experimental

A series of diffusion couples was assembled with a U-23 at.% Zr alloy fuel (designated F) bonded to pure Fe, pure Ni, Ni-16.4 Cr, Fe-10.1 Ni, Fe-20.1 Cr, and Fe-16.4 Ni-9.4 Cr alloys (compositions in at.%). The binary and ternary alloys of the Fe-Ni-Cr system were prepared from pure Fe, Ni, and Cr by vacuum induction melting [13]. Charges were melted in alumina crucibles under argon atmosphere, and subsequently drawn up fused silica draw tubes, 10 mm in diameter. A steel chill was positioned inside the draw tube to act as the end of the mold. The alloy rods were sealed in quartz tubes under vacuum and then annealed at 1150°C for 7 days for homogenization. The U-23 at.% Zr was prepared by Argonne National Laboratory with depleted U by using conventional induction melting methods and casting into rods, 5 mm in diameter. A fuel rod furnished by ANL was homogenized at 900°C for 4 days.

Both fuel and cladding alloys were cut into slices about 0.5 cm thick. Their surfaces were metallographically polished through 0.05 micron alumina. During polishing, thickness measurements were made to ensure that both faces of the disks were flat and parallel to each other. Diffusion couples were assembled by sandwiching a disk of the U-23 at.% Zr alloy between disks of two selected cladding alloys in a low-expansion Kovar steel jig, which consisted of two end plates, 1/8" thick $\times$ 7/8" in diameter, and three threaded Kovar steel rods. Kovar steel was chosen for the jig due to its low coefficient of thermal expansion (5.27×10^{-6} in/in°C). The assembled couples were placed in a quartz tube, 9" long and 1" in diameter. Each quartz tube was flushed several times with hydrogen, evacuated to a pressure of less than 10^{-5} torr and sealed to form a capsule about 6" long.

All diffusion couples were annealed for 4 days at 700°C in a Lindberg heavy-duty three-zone tube furnace. The temperature gradient over the length of the capsule was less than 1°C

and the temperature controlled to $\pm 0.5^{\circ}\text{C}$. After annealing, the capsules were allowed to cool in air outside the furnace.

The diffused couples were removed from the quartz capsules and mounted in a cold-mount self-setting resin. Mounted couples were then cut with an Isomet cut-off wheel to expose sections parallel to the direction of diffusion. The exposed cross-section of each couple was metallographically polished through 0.05 micron alumina. The couples were analyzed by point-to-point counting techniques for concentration profiles and phase compositions with a JEOL 35CF scanning electron microscope equipped with a Tracor Northern Series II energy dispersive X-ray analyzer. Intensities of K_{α} X-radiations of Fe, Ni, and Cr identified at the energies of 6.403 KeV, 7.477 KeV, and 5.414 KeV, respectively, of Zr L_{α} X-radiation at 2.042 KeV and of U M_{α} X-radiation at 3.171 KeV were collected, stored on floppy discs and converted into compositions with the aid of elemental standards and a ZAF correction program. Secondary electron micrographs were taken of diffusion structures developed in the various couples.

3. Results

3.1. Diffusion structures and diffusion paths

On the basis of the U-Ni, U-Fe, Zr-Fe, and Zr-Ni phase diagrams [14], several intermetallic phases can form between U and Fe, U and Ni, Zr and Fe, and Zr and Ni, and these are listed in Table 1. In contrast to Ni and Fe, Cr has some solubility in U (up to 4 at.%) and does not form any intermetallic phase with U; only a single intermetallic compound is reported between Zr and Cr. For the U-Zr binary system, the intermetallic phase of interest is the δ phase, which appears as a precipitate in the as-received U-23 at.% Zr fuel. Intermetallic designations for specific phases in the diffusion structure are based on the ratio of concentrations of (U+Zr) to that of (Fe + Ni + Cr). The phases analyzed in the diffusion structures for each couple are presented in Table 2.

single-phase layers are only a few microns wide, and hence concentration variations in such layers could not be determined. In layers 5 and 6 where (U, Zr)Ni₂ phase appears, U manifests up-hill diffusion up its own concentration gradient, while Zr diffuses down its own concentration gradient. This observation implies that the activity of U is higher at higher Zr concentrations in the (U, Zr)Ni₂ layer and that Zr can increase the activity of U. This expectation agrees with the work of Pelton [15] who reported a positive deviation from Raoult's law for the U-Zr system.

Experimental diffusion paths drawn on the basis of concentration profiles for the F vs. Ni and F vs. Ni-16.4 Cr couples are presented in Fig. 4(a) and 4(b), respectively. The path segments crossing two-phase regions are represented by bold dashed lines, while path segments in single-phase regions are identified by solid lines. Thin dashed lines indicate schematic tie-lines for two-phase regions, and shaded areas represent approximate ranges of composition for single-phase regions. In Fig. 4(a) the path segment a-b passes through UNi₅, UNi₃₋₄, and U₅Ni₇ single-phase layers observed on the Ni-side of the diffusion structure for the F vs. Ni couple. Segment c-d represents the variation in compositions for the (U, Zr)Ni₂ single-phase layer. Path segment d-e covers the two-phase regions: [U₆Ni + (U, Zr)Ni₂], [U₆Ni + (Zr, U)₇Ni₁₀], [U + (Zr, U)₂Ni], and [U + δ]. The diffusion path in these regions crosses schematic tie-lines linking the approximate precipitate and matrix compositions.

The diffusion path presented in 4(b) for the F vs. Ni-16.4 Cr couple is constructed on the composition triangle with the concentrations of (Ni + Cr) taken together as one variable. Thus, at any point within the composition triangle, the sum of the concentrations (atom fractions) of all the elements in the cladding alloy when added to the concentrations of U and Zr is equal to one. Diffusion paths for couples involving more than 3 components can be still drawn on triangles and be compared for various couples. This procedure for the representation of diffusion paths is employed for all couples in this study. The path segment a-b includes the two-phase layer (Cr + UNi₅). This layer is a special feature which differentiates this couple from the F vs. Ni couple. This layer is denoted as layer 1 in Figs. 2(b) and 3. Except for the

appearance of layer 1, the concentration profiles, diffusion structures, and diffusion paths for the couples F vs. Ni and F vs. Ni-16.4 Cr are quite similar.

3.1.2. Couple *F(U-23 Zr) vs. Fe* and *F(U-23 Zr) vs. Fe-20.1 Cr*

The diffusion structure for the couple F vs. Fe is presented in Fig. 5. The interdiffusion between the fuel alloy and Fe is quite limited. However, a Zr layer was identified along the Fe/fuel interface. This reflects the decomposition of the δ precipitates which have Zr concentrations in the range 66-78 at.% and exist as part of the two-phase structure of the U-23 at.% Zr alloy. Adjacent to the Zr layer, there appears a region free of δ precipitates. Little Fe penetration into the fuel is observed and the overall size of the diffusion structure is small (≈ 10 -15 μm).

The diffusion structure for the F vs. Fe-20.1 Cr couple is presented in Fig. 6(a). It is 30 μm in width which is slightly larger than the diffusion structure exhibited for the F vs. Fe couple. However, it is small compared to the width of diffusion structures developed for couples with Ni-containing alloys. The diffusion structure consists of a $\text{U}(\text{Fe}, \text{Cr})_2$ phase layer, a Zr layer, and a two-phase region with U matrix and Zr precipitates. The concentration profiles for the couple are presented in Fig. 6(b).

In Fig. 4(c) is presented the experimental diffusion path for the F vs. Fe-20.1 Cr couple. The path bends toward the Zr corner of the ternary isotherm and differs from paths for the Ni-containing couples. Path segment a-c covers the single-phase layers of $\text{U}(\text{Fe}, \text{Cr})_2$ and Zr (> 97%), and segment c-d covers the two-phase regions, [U + Zr] and [U + δ].

3.1.3. Couples *F(U-23 Zr) vs. Fe-10.1 Ni* and *F(U-23 Zr) vs. Fe-16.4 Ni-9.4 Cr*

The diffusion structures for the two couples, F vs. Fe-10.1 Ni and F vs. Fe-16.4 Ni-9.4 Cr, are presented in Fig. 7 and Fig. 8, respectively. The diffusion structure of F vs. Fe-10.1 Ni

couple exhibits layers of $U(Fe, Ni)_2$ and $(Zr, U)(Fe, Ni)_2$ phases and of two-phase regions, one with $U_6(Fe, Ni)$ matrix and $(Zr, U)_2(Fe, Ni)$ precipitates and the other with U matrix and $(Zr, U)_2(Fe, Ni)$ precipitates. The overall width of the diffusion structure is around 70 μm .

The F vs. Fe-16.4 Ni-9.4 Cr couple develops single-phase layers of $U(Fe, Ni, Cr)_2$ and $(Zr, U)(Fe, Ni, Cr)_2$ along with two-phase regions, one containing $U_6(Fe, Ni)$ matrix and $(Zr, U)_2(Fe, Ni)$ precipitates and the other U matrix with $(Zr, U)_2(Fe, Ni)$ precipitates. A $(U, Zr)_9(Fe, Ni)$ phase appears on the fuel side of the diffusion structure. The widths of the diffusion zone of Fe and Ni are approximately 80 to 90 μm , while that of Cr is approximately 30 μm toward the fuel.

An experimental diffusion path for couple F vs. Fe-10.1 Ni is presented in Fig. 9(a). Path segments b-c and d-e represent the single-phase layers of $U(Fe, Ni)_2$ and $(Zr, U)(Fe, Ni)_2$, respectively. Segment c-d represents the two-phase region $[U(Fe, Ni)_2 + (Zr, U)(Fe, Ni)_2]$, while e-f covers the adjacent diffusion layers of $[U_6(Fe, Ni) + (Zr, U)(Fe, Ni)_2]$, $[U_6(Fe, Ni) + (Zr, U)_2(Fe, Ni)]$, and $[U + (Zr, U)_2(Fe, Ni)]$.

The experimental diffusion path for the couple F vs. Fe-16.4 Ni-9.4 Cr is presented on a composition triangle in Fig. 9(b). The diffusion path segment a-b cuts across tie-lines through a two-phase region between the $U(Fe, Ni, Cr)_2$ phase and the ternary terminal alloy. Segments b-c and d-e represent the single-phase layers of $U(Fe, Ni, Cr)_2$ and $(Zr, U)(Fe, Ni, Cr)_2$, respectively. Segment c-d represents the two-phase layer, $[U(Fe, Ni, Cr)_2 + (Zr, U)(Fe, Ni, Cr)_2]$, and segment e-f cuts across two-phase regions of $[U_6(Fe, Ni) + (Zr, U)(Fe, Ni, Cr)_2]$ and $[U_6(Fe, Ni) + (Zr, U)_2(Fe, Ni, Cr)]$. The appearance of a three-phase region in this couple requires the diffusion path to pass through a three-phase triangle on the composition triangle, and this corresponds to path segment f-g. $(U, Zr)_9(Fe, Ni)$, U and δ are all observed in this three-phase region.

3.2. Interdiffusion

Dayananda and Behnke [16] have presented an approach whereby effective interdiffusion coefficients and penetration depths for the individual components can be determined from the concentration profiles of a multicomponent diffusion couple. From this analysis, an average effective interdiffusion coefficient can be determined for each component over a range of concentrations selected in the diffusion zone. This analysis has been applied to the F vs. Ni-16.4 Cr and F vs. Fe-20.1 Cr diffusion couples.

3.2.1. Effective interdiffusion coefficients and penetration depths

The Onsager's formalism of Fick's law for interdiffusion in an n-component system is expressed by [17]:

$$\tilde{J} = - \sum_{j=1}^{n-1} \tilde{D}_{ij}^n \frac{\partial C_j}{\partial x} \quad (1)$$

where $\tilde{J}_i$ is the interdiffusion flux of component i on a laboratory-fixed frame and $\partial C_j / \partial x$ is the concentration gradient of component j. The $(n-1)^2$ interdiffusion coefficients, $\tilde{D}_{ij}^n$, are defined as functions of composition, and the superscript n refers to the component taken as the dependent concentration variable. To determine $\tilde{D}_{ij}^n$'s from Eq. (1), it is necessary to employ independent diffusion couples with intersecting diffusion paths [18,19] which is very difficult for systems with $n \geq 4$.

It is possible to calculate $\tilde{J}_i$ as a function of distance in a solid-solid diffusion couple directly from the concentration profiles without the need for the interdiffusion coefficients [20,21]. At time t, $\tilde{J}_i$ at any section x can be expressed by:

$$\tilde{J}_i(x) = \frac{1}{2t} \int_{C_i(\pm\infty)}^{C_i(x)} (x-x_0) dC_i \quad (i=1,2,\dots,n) \quad (2)$$

where $C_i(x)$ refers to the concentration of component i at any position x in the diffusion zone,

and $C_i(\pm\infty)$ refers to the concentrations of component i in the terminal alloys of the couple.
 x_0 refers to the Matano plane.

Integration of $\tilde{J}_i$ over x from $-\infty$ to x_0 yields the relation:

$$\int_{-\infty}^{x_0} \tilde{J}_i dx = \frac{1}{2t} \int_{C_i(-\infty)}^{C_i(x_0)} (x-x_0)^2 dC_i \quad (3)$$

where $C_i(x_0)$ refers to the concentration at x_0 . Eq. (3) can be used to derive expressions for average effective interdiffusion coefficients for individual components over selected ranges of concentrations. $\tilde{J}_i$ in Eq. (1) can be alternatively written as [16]:

$$\tilde{J}_i = - \tilde{D}_i^{\text{eff}} \frac{\partial C_i}{\partial x} \quad (4)$$

where

$$\tilde{D}_i^{\text{eff}} = \tilde{D}_{ii}^n + \frac{\sum_{j \neq i}^{n-1} \tilde{D}_{ij}^n \frac{\partial C_j}{\partial x}}{\frac{\partial C_i}{\partial x}} \quad (j \neq i) \quad (5)$$

The second term containing the cross interdiffusion coefficients in Eq. (5) accounts for the diffusional interactions among the diffusing species. Substitution of Eq. (4) in Eq. (3) yields:

$$\int_{C_i(-\infty)}^{C_i(x_0)} \tilde{D}_i^{\text{eff}} dC_i = \frac{1}{2t} \int_{C_i(-\infty)}^{C_i(x_0)} (x-x_0)^2 dC_i \quad (6)$$

or

$$\tilde{D}_{iL}^{\text{eff}} = \frac{\int_{C_i(-\infty)}^{C_i(x_0)} (x-x_0)^2 dC_i}{2t[C_i(x_0) - C_i(-\infty)]} \quad (7)$$

where $\tilde{D}_{iL}^{\text{eff}}$ is the average effective interdiffusion coefficient for component i over the concentration range $C_i(-\infty)$ to $C_i(x_0)$ on the left-hand side of the Matano plane. Similarly, an average effective interdiffusion coefficient $\tilde{D}_{iR}^{\text{eff}}$ for component i can be determined over the

concentration range $C_i(+\infty)$ to $C_i(x_0)$ on the right-hand side of the Matano plane.

Root-mean-square (r.m.s.) penetration depths can be determined for component i on either side of the Matano plane. The r.m.s. penetration depth $x_{i,L}$ to the left of the Matano plane can be calculated from [16]:

$$x_{i,L} = \sqrt{2\tilde{D}_{i,L}^{\text{eff}} t} \quad (8)$$

A similar relation may be employed to calculate $x_{i,R}$ and is given by

$$x_{i,R} = \sqrt{2\tilde{D}_{i,R}^{\text{eff}} t} \quad (9)$$

The concentration profiles for the couples r' vs. Ni-16.4 Cr and F vs. Fe-20.1 Cr were analyzed for average effective interdiffusion coefficients. For these couples, the location x_0 of the Matano plane could be determined by performing a mass balance for Cr from the concentration profiles. The location of x_0 has been identified on the concentration profiles for the F vs. Ni-16.4 Cr and F vs. Fe-20.1 Cr couples shown in Figs. 3 and 6(b).

Equations (7) and (8) were employed to calculate the average effective interdiffusion coefficients and the effective penetration depths for the components for couples, F vs. Ni-16.4 Cr and F vs. Fe-20.1 Cr. For each of the couples, the average effective interdiffusion coefficients, $\tilde{D}_{i,L}^{\text{eff}}$, over the concentration ranges of each component i on the cladding side of the Matano plane were calculated on the basis of Eq. (7); these are reported in Table 3. Effective penetration depths for the components calculated from Eq. (8) are also included in Table 3.

3.3. Intrinsic Diffusion

Intrinsic diffusion fluxes, J_i , refer to atomic migration relative to the lattice-fixed or Kirkendall frame of reference. For component i in an n -component system, J_i is expressed by

$$J_i = - \sum_{j=1}^{n-1} D_{ij}^n \frac{\partial C_j}{\partial x} \quad (i=1,2,\dots,n) \quad (10)$$

where D_{ij}^n 's are the intrinsic diffusion coefficients.

From couples with inert markers, intrinsic diffusion coefficients can be determined at the marker plane from appropriate areas under the concentration profiles in binary alloys [22] and multicomponent alloys [23]. The cumulative intrinsic flux, A_i , of component i past a marker plane moving parabolically with time at a constant composition in a ternary couple is obtained by integrating Eq. (10) over t ; thus,

$$A_i = \int_0^t J_i dt = - \int_0^t \sum_{j=1}^2 D_{ij}^3 \left[\frac{\partial C_j}{\partial x} \right] dt \quad (11)$$

$$A_i = - 2t \left[D_{i1}^3 \frac{\partial C_1}{\partial x} + D_{i2}^3 \frac{\partial C_2}{\partial x} \right]_{\text{marker plane}} \quad (i=1,2,3) \quad (12)$$

where D_{i1}^3 and D_{i2}^3 are the intrinsic diffusion coefficients, and C_i 's are functions of the Boltzmann parameter, $x/\sqrt{t}$. A_i is graphically determined from appropriate areas under the composition profiles.

The inert markers placed at the original interface of the F vs. Ni-16.4 Cr couple are identified after diffusion at the plane x_m within the (U, Zr)Ni₂ phase in Fig. 3. On the basis of Eq. (12), values of selected intrinsic diffusion coefficients D_{NiZr}^U , D_{ZrZr}^U , and D_{UZr}^U have been calculated at the marker plane and are presented in Table 3.

4. Discussion

4.1. Phase Layers

Diffusion layers that developed in the various couples consisted of intermetallic phases similar to those listed in Table 1 on the basis of binary phase diagrams. This similarity is

reflected in the ratio of sum of U and Zr concentrations to that of Fe, Ni and Cr for the various phases. In Table 2 the various phases identified in the couples are listed; it is apparent that similar types of intermetallic layers and regions are recognized in more than one couple. Alloys containing Ni develop more number of intermetallic phases with U and Zr than alloys without Ni. In general, the diffusion layers formed in the couples on the side of the cladding alloy correspond to those dictated by the interaction of U with Ni, Fe and Cr. The phases that are found on the fuel side of the couples correspond to the type of intermetallic phases that can form between Zr and Fe, Ni and Cr.

Several diffusion layers are observed for couples F vs. Ni and F vs. Ni-16.4 Cr. The layers include single-phase layers of UNi_5 , UNi_{3-4} , U_5Ni_7 , and $(\text{U}, \text{Zr})\text{Ni}_2$ and two-phase layers of $[(\text{U}, \text{Zr})\text{Ni}_2 + \text{U}_6\text{Ni}]$, $[\text{U}_6\text{Ni} + (\text{Zr}, \text{U})_7\text{Ni}_{10}]$, and $[\text{U} + (\text{Zr}, \text{U})_2\text{Ni}]$. The main difference between the diffusion structures of the two couples lies in the development of a two-phase $(\text{Cr} + \text{UNi}_5)$ layer on the cladding alloy side of the diffusion structure for the F vs. Ni-16.4 Cr couple. As Ni diffuses out of the Ni-16.4 Cr alloy, the alloy becomes more Cr-rich and a two-phase layer containing a high Cr matrix and UNi_5 precipitates develops.

The diffusion structure developed for the F vs. Ni couple is much more complicated than that reported for a binary U-Ni diffusion couple by Kimmel [24]. The binary couple developed U_6Ni , UNi_5 and U_7Ni_9 phases. The ternary F vs. Ni couple shows not only the development of single-phase layers but also two-phase layers with phases containing Zr, as identified in Fig. 1.

The diffusion zone of couple F vs. Fe exhibits minimal interdiffusion and the addition of Cr and Ni to Fe increases the number of diffusion layers and the depth of interdiffusion. From the diffusion structure of couple F vs. Fe-20.1 Cr (Fig. 6a) it is apparent that Cr increases the depth of interdiffusion and the number of diffusion layers. In the absence of Ni, Cr may affect the activity of Zr and cause the decomposition of δ precipitates, since a Zr-rich phase (mostly Zr), not observed in any other couple, forms as an intermediate layer adjacent to the $\text{U}(\text{Fe}, \text{Cr})_2$ layer. The Zr layer may act as a barrier to interdiffusion. A comparison of the diffusion

structures of couples F vs. Fe and F vs. Fe-10-1 Ni (Figs. 5 and 7) indicates that the presence of Ni in the cladding alloy results in an increase in the width of the diffusion structure and in the formation of several intermetallic phases.

From a comparison of the diffusion structures of F vs. Fe-10.1 Ni and F vs. Fe-16.4 Ni-9.4 Cr couples, it is apparent that the phases in both couples are quite similar. This is consistent with the fact that Cr does not form any intermetallic phases with U and forms only one intermetallic phase with Zr.

4.2. Relative diffusion behavior of fuel and cladding elements

The intrinsic diffusion coefficients for the (U, Zr)Ni₂ phase reported in Table 3 give insight on the diffusion behavior of U and Ni as affected by the presence of Zr. $D_{U,Zr}^U$, which is the cross intrinsic diffusion coefficient for U is positive and indicates that when U diffuses down a Zr gradient, the intrinsic diffusion flux of U is increased. The negative value for the cross intrinsic diffusion coefficient, $D_{Ni,Zr}^U$, implies that the diffusion flux of Ni gets reduced down a Zr gradient. The absolute values of these cross coefficients are over an order of magnitude greater than the main coefficient $D_{Zr,Zr}^U$ and indicate that the diffusional interactions among the components cannot be ignored. The small $D_{Zr,Zr}^U$ implies small Zr intrinsic diffusion fluxes in the (U, Zr)Ni₂ phase.

The average effective interdiffusion coefficients reported in Table 3 for the couple F vs. Ni-16.4 Cr are for the diffusion structure covering the diffusion layers 1 through 5 to the left of x_0 in Fig. 3. These layers include the intermetallic phases between U and Ni and the phase (U, Zr)Ni₂. Since $\tilde{D}_{U,L}^{eff}$ and $\tilde{D}_{Ni,L}^{eff}$ are an order of magnitude larger than $\tilde{D}_{Zr,L}^{eff}$, U and Ni interdiffuse much faster than Zr and the effective penetration depths of U and Ni are 2-3 times larger than that of Zr. The average effective interdiffusion coefficients for U, Fe and Cr calculated from the couple F vs. Fe-20.1 Cr correspond to the phase U(Fe, Cr)₂ and are comparable to each other. However, they are 3 orders of magnitude smaller than those for the

U-Ni intermetallic phases. Hence, U interdiffuses much faster in intermetallic phases containing Ni than those without it.

The interdiffusion behavior of the various elements can also be appreciated with the aid of diffusion paths in Figs. 4 and 9. The path segments a-b for the various couples lie almost parallel to the U-cladding alloy side of the composition triangles and indicate very low Zr concentration levels. This implies that the interdiffusion of U with the cladding elements dominates the cladding alloy side of the couples. On the other hand, the diffusion path segments on the fuel side of the couples pass through one or more intermetallic phases typical of those that can form between Zr and Fe, Ni and Cr. For Ni-rich cladding alloys, the interaction of Ni with U and Zr dominates the diffusion structure, while for Fe-rich cladding alloys, the interaction of Fe with U and Zr appears to govern the diffusion layers.

5. General Comments and Conclusions

On the basis of the interdiffusion experiments carried out at 700°C with a U-23 at.% Zr alloy fuel (F) bonded to pure Fe, pure Ni and selected binary and ternary cladding alloys of the Fe-Ni-Cr system, the following comments and conclusions are made.

1. The diffusion layers that developed in the couples are consistent with the type of intermetallic phases expected between U and Ni, U and Fe, Zr and Ni, and Zr and Fe depending on the cladding alloy composition.
2. For couples assembled with pure Ni or Ni-16.4 Cr alloy, a large number of phases is observed and the diffusion layers include UNi_5 , UNi_2 , U_5Ni_7 , $(U, Zr)Ni_2$, U_6Ni , $(Zr, U)_4Ni_5$ and $(Zr, U)_2Ni$ and U-rich phases. U exhibits uphill diffusion in the $(U, Zr)Ni_2$ phase where the cross intrinsic diffusion coefficient D_{UZr}^U is positive and more than an order of magnitude larger than the main coefficient D_{ZrZr}^U for Zr. Based on the average effective interdiffusion coefficients, the effective penetration depths of Ni, U and

Zr on the cladding alloy side of the F vs. Ni-16.4 Cr couple are approximately in the ratio of 3:2:1.

3. Minimal interdiffusion is observed between the fuel and Fe. For the couple with Fe-20.1 Cr alloy, diffusion layers of $U(Fe, Cr)_2$ and Zr develop in the diffusion zone. The average effective interdiffusion coefficients for U, Fe and Cr in the $U(Fe, Cr)_2$ phase are comparable to one another and the effective penetration depths on the cladding alloy side of the couple are less than a couple of micrometers.
4. In the F vs. Fe-16.4 Ni-9.4 Cr couple, all the major intermetallic phases identified in the F vs. Fe-10.1 Ni and F vs. Fe-20.1 Cr couples are also observed without the Zr-rich phase. These phases include $U(Fe, Ni, Cr)_2$, $(Zr, U)(Fe, Ni, Cr)_2$, $U_6(Fe, Ni)$ and $(Zr, U)_2(Fe, Ni)$.
5. Diffusion structures developed in the various couples could be described by the aid of diffusion paths plotted on composition triangles with concentrations of U, Zr and the sum of the concentrations of Fe, Ni and Cr taken as concentration variables.
6. In general, the diffusion layers formed on the cladding alloy side of the couples are dictated by the interactions of Ni, Fe and Cr with U. The phases observed on the fuel side of the couples correspond to the type of intermetallic phases that can form between Zr and the elements in the cladding alloy.

Acknowledgment

This paper is based on a dissertation submitted by D. D. Keiser, Jr. to Purdue University in partial fulfillment of the requirements for the Ph.D. degree. The research was supported by the U. S. Department of Energy under contract DE-FG07-88ER12814. Additional support by the Argonne National Laboratory under the award No. 80000MOD1 is gratefully acknowledged.

References

1. C. H. Till and Y. I. Chang, in: *Proceedings of the American Power Conference* (Chicago, IL, 1986) p. 688.
2. G. L. Hofman, *Nucl. Tech.* 47 (1980) 7.
3. R. E. Einziger and B. R. Seidel, *Nucl. Tech.* 50 (1980) 25.
4. B. R. Seidel, L. C. Walters and Y. I. Chang, *J. Metall.* 39 (1987) 10.
5. B. R. Seidel and L. C. Walters, *Trans. of ASME* 103 (1981) 612.
6. L. C. Walters and J. H. Kittle, *Nucl. Tech.* 48 (1980) 273.
7. C. E. Lahm, et al., *Nucl. Engr. and Design* 101 (1987) 25.
8. G. L. Hofman, et al., in: *Proc. of the Int. Conf. on Reliable Fuels for Liquid Metal Reactors* (Tucson, AZ, 1986) p. 4-121.
9. S. Thomas Zegler, et al., *Compatibility of Uranium 5 w/o Fissium Alloy with Types 304L and 316 stainless Steel*, Argonne National Laboratory, ANL-7596 (September 1969).
10. C. M. Walters, *Interdiffusion Between Uranium 5 w/o Fissium Alloy and Type 304 Stainless Steel*, Argonne National Laboratory, ANL-6816 (March 1964).
11. S. T. Zegler and C. M. Walters, *Nucl. Mat.* 13 (1967) 335.
12. J. H. Kittel, *Layer Formation by Interdiffusion Between Some Reactor Construction Metals*, Argonne National Laboratory, ANL-4937 (June 1949).
13. J. G. Duh, Ph.D. Thesis (Purdue University, 1983) p. 96.
14. *Binary Alloy Phase Diagrams*, ASM publication, Edited by T. B. Massalski, H. Okamoto, P. R. Subramanian, L. Kacprzak, (1990).
15. L. Leibowitz, et al., *J. Nucl. Mater.* 154 (1988) 145.
16. M. A. Dayananda and D. A. Behnke, *Scripta Met.* (1991) 2187.
17. L. Onsager, *New York Acad. of Sciences* 46 (1945) 241.
18. J. S. Kirkaldy, *Can. J. Phys.*, 35 (1957) 435.
19. T. O. Ziebold and R. E. Ogilvie, *TMS-AIME*, 233 (1965) 1287.
20. M. A. Dayananda and C. W. Kim, *Metall. Trans.* 10A (1979) 1333.
21. M. A. Dayananda, *Metall. Trans.* 14A (1983) 1851.
22. T. Heumann, *Z. Phys. Chem.* 201 (1952) 168.
23. J. Philibert and A. G. Guy, *Comptes Rendus* 227 (1963) 2281.
24. G. Kimmel, et al., *Trans. ASM* 61 (1968) 703.

Table 1. Possible intermetallic phases for various binary combinations from phase diagrams [14].

	U	Zr
Fe	UFe ₂ , U ₆ Fe	ZrFe ₃ , ZrFe ₂ , Zr ₃ Fe, Zr ₂ Fe
Ni	U ₆ Ni, U ₇ Ni ₉ , U ₅ Ni ₇ , UNi ₂ , UNi ₅ , δ , ϵ	Zr ₂ Ni, ZrNi, ZrNi ₃ , Zr ₈ Ni ₂₁ , Zr ₂ Ni ₇ , ZrNi ₅ , Zr ₉ Ni ₁₁ , Zr ₇ Ni ₁₀
Cr	solubility of Cr in U (< 4 at.%)	ZrCr ₂

Table 2. Phases identified in diffusion couples.

Diffusion Couple	Phases‡
F vs. Ni	UNi ₅ *, UNi ₃₋₄ *, U ₅ Ni ₇ *, (U,Zr)Ni ₂ , U ₆ Ni*, (Zr,U) ₇ Ni ₁₀ , (Zr,U) ₂ Ni
F vs. Fe	Zr
F vs. Ni-16.4 Cr	UNi ₅ *, UNi ₃₋₄ *, U ₅ Ni ₇ *, (U,Zr)Ni ₂ , U ₆ Ni*, (Zr,U) ₇ Ni ₁₀ , (Zr,U) ₂ Ni, Cr
F vs. Fe-20.1 Cr	U(Fe,Cr) ₂ , Zr
F vs. Fe-10.1 Ni	U(Fe,Ni) ₂ , U ₆ (Fe,Ni), (Zr,U)(Fe,Ni) ₂ (Zr,U) ₂ (Fe,Ni)
F vs. Fe-16.4 Ni-9.4 Cr	U(Fe,Ni,Cr) ₂ , U ₆ (Fe,Ni), (Zr,U)(Fe,Ni,Cr) ₂ , (Zr,U) ₂ (Fe,Ni), (U,Zr) ₉ (Fe,Ni)

‡ The intermetallic designations of the phases are based on the ratio of concentrations of (U + Zr) to that of (Fe + Ni + Cr).

* In the phases with binary designations, the presence of negligibly small concentrations of Zr is ignored.

Table 3. Average effective interdiffusion coefficients, intrinsic diffusion coefficients, and effective penetration depths for the F(U-23 Zr) vs. Ni-16.4 Cr and F(U-23 Zr) vs. Fe-20.1 Cr couples annealed at 700°C for 4 days.

Couple	$(x_m - x_o)$	Average Effective Diffusion Coefficients $\tilde{D}_{i,L}^{eff} \text{ (cm}^2\text{s}^{-1}\text{)}$	Effective Penetration Depths $x_{i,L} \text{ (}\mu\text{m)}$	Intrinsic Diffusion Coefficients for (U,Zr)Ni ₂ $D_{ij}^U \text{ (cm}^2\text{s}^{-1}\text{)}$
F vs. Ni-16.4 Cr	9.2 μm	$\tilde{D}_{U,L}^{eff} = 8.21 \times 10^{-12}$ $\tilde{D}_{Zr,L}^{eff} = 1.74 \times 10^{-12}$ $\tilde{D}_{Ni,L}^{eff} = 1.73 \times 10^{-11}$	$x_{U,L} = 23.8$ $x_{Zr,L} = 11.0$ $x_{Ni,L} = 34.6$	$D_{UZr}^U = 1.70 \times 10^{-11}$ $D_{ZrZr}^U = 8.94 \times 10^{-13}$ $D_{NiZr}^U = -5.29 \times 10^{-11}$
F vs Fe-20.1 Cr	1.4 μm	$\tilde{D}_{U,L}^{eff} = 4.10 \times 10^{-14}$ $\tilde{D}_{Fe,L}^{eff} = 5.33 \times 10^{-14}$ $\tilde{D}_{Cr,L}^{eff} = 1.57 \times 10^{-14}$	$x_{U,L} = 1.7$ $x_{Fe,L} = 1.9$ $x_{Cr,L} = 1.0$

Figure 1. SEM micrographs showing several diffusion layers with intermetallic phases developed for the F(U-23Zr) vs. Ni couple annealed at 700°C for 4 days; (a) and (b) are at two different magnifications.

Figure 2. SEM micrographs showing the diffusion structure developed for the F(U-23Zr) vs. A(Ni-16.4Cr) couple on annealing at 700°C for 4 days; (a) and (b) are at two different magnifications.

Figure 3. Concentration profiles of Ni, Cr, U, and Zr for the F(U-23Zr) vs. Ni-16.4Cr couple. Layers 1-6 represent: 1-(Cr + UNi₅), 2-UNi₅, 3-UNi₃₋₄, 4-U₅Ni₇, 5-(U, Zr)Ni₂, and 6-[(U, Zr)Ni₂ + U₆Ni]; x_0 and x_m refer to the locations of the Matano plane and marker plane, respectively.

Figure 4. Experimental diffusion paths on composition triangles at 700°C for the couples (a) F vs. Ni, (b) F vs. Ni-16.4Cr, and (c) F vs. Fe-20.1Cr. Phase designations are based on relative ratios of concentrations and the tie-lines in two-phase regions are schematic.

Figure 5. Diffusion structure for the F(U-23Zr) vs. Fe couple annealed at 700°C for 4 days.

Figure 6. (a) Diffusion structure and (b) concentration profiles for the F(U-23Zr) vs. (Fe-20.1Cr) couple annealed at 700°C for 4 days.

Figure 7. SEM micrographs showing the diffusion structure for the F(U-23Zr) vs. (Fe-10.1Ni) couple annealed at 700°C for 4 days; (a) and (b) are at two different magnifications.

Figure 8. SEM micrographs showing the diffusion layers and intermetallic phases developed for the F(U-23Zr) vs. (Fe-16.4Ni-9.4Cr) couple annealed at 700°C for 4 days; (a) and (b) are at two different magnifications.

Figure 9. Experimental diffusion paths on composition triangles at 700°C for the couples (a) F vs. Fe-10.1Ni and (b) F vs. Fe-16.4Ni-9.4Cr. Phase designations are based on relative ratios of concentrations and the tie-lines in two-phase regions are schematic.

APPENDIX E

Interdiffusion Between U-Zr Fuel vs. Selected Cladding Steels

Interdiffusion Between U-Zr Fuel vs. Selected Cladding Steels

D. D. Keiser, Jr. and M. A. Dayananda
School of Materials Engineering
Purdue University, W. Lafayette, IN 47907

Abstract

To understand better fuel-cladding compatibility issues as affected by diffusion processes in the Integral Fast Reactors, interdiffusion studies were carried out with solid-solid diffusion couples assembled with a U-23 at.% Zr alloy and cladding steels, such as 316, D9, and HT9. All diffusion couples were annealed at 700°C and examined metallographically and by SEM-EDS analysis for diffusion structure development. The development of diffusion layers in the couples for various cladding steels are compared and discussed in the light of the relative diffusion behavior of the individual elements, intermetallic formation and experimental diffusion paths. In the context of fuel-cladding compatibility, HT9 is considered superior to 316 and D9, as it developed the smallest diffusion zone with the fewest number of phases.

I. Introduction

The structural integrity of a fuel element is of paramount importance during operation of a nuclear reactor. During reactor operation with the metallic fuel elements used as part of Argonne National Laboratory's Integral Fast Reactor program, the fuel has been shown to come into contact with the cladding alloy between 0.5 and 1.0 at.% burnup. Such contact between the fuel and cladding alloy results in interdiffusion [1-7] and in the development of strength reducing diffusion zones, which can cause a premature breach of a fuel element. In addition, low melting layers can form as a result of interdiffusion and affect the structural integrity of a fuel element. Therefore, to understand the compatibility of a fuel and the cladding alloy, it is important to understand diffusion behavior for various cladding steels.

In the recent paper [8] were presented results of interdiffusion studies with a set of diffusion couples assembled with a U-23 at.% Zr fuel and Fe, Ni and selected binary and ternary alloys of the Fe-Ni-Cr system. In this paper interdiffusion in couples assembled with the U-23 at.% Zr fuel bonded to selected cladding steels namely 316SS, HT9, and D9 is investigated. Diffusion structures and experimental diffusion paths for the couples are presented and the fuel-cladding compatibility is examined in the context of diffusion structure development for these couples. The interdiffusion behavior of the fuel with cladding steels is discussed in the light of the diffusion structures, diffusion paths, and the intermetallic phases as affected by variations in the composition of cladding alloys of the Fe-Ni-Cr system [8].

II. Experimental

The U-23 at.% Zr fuel (designated F) as well as the cladding steels 316, HT9, D9 used in this investigation were provided by the Argonne National Laboratory. The compositions of the cladding steels are listed in Table I. The U-23 at.% Zr alloy was prepared at the Argonne National Laboratory with depleted U by using conventional induction melting methods and casting into rods, 5 mm in diameter. A fuel rod furnished by ANL was homogenized at 900°C

for 4 days.

Both fuel and cladding steels were cut into disks about 0.5 cm thick. Their surfaces were metallographically polished through 0.05 micron alumina. Thickness measurements were made during polishing to ensure that both faces of the disks were flat and parallel to each other. Diffusion couples were assembled by sandwiching a disk of the U-Zr at. % Zr alloy between two disks of selected cladding steels. These "sandwiches" were clamped together in a (Kovar) jig which consisted of two end plates, 1/8" thick x 7/8" in diameter, and three threaded Kovar rods. Kovar steel was chosen for the jig due to its low coefficient of thermal expansion (5.27×10^{-6} in/in $^{\circ}\text{C}$). The assembled couples were placed in a quartz tube, 9" long and 1" in diameter. Each quartz tube was flushed several times with hydrogen, evacuated to a pressure of less than 10^{-5} torr and sealed to form a capsule about 6" long.

All diffusion couples were annealed for 4 days at 700°C in a Lindberg heavy-duty three-zone tube furnace. The temperature gradient over the length of the capsule was less than 1°C and the temperature controlled to $\pm 0.5^{\circ}\text{C}$. After annealing, the capsules were allowed to cool in air outside the furnace.

The diffused couples in the Kovar jigs were removed from the quartz capsules and mounted in cold-mount self-setting resin. Mounted couples were then cut with an Isomet cut-off wheel to expose sections parallel to the direction of diffusion. The exposed cross-section of each couple was metallographically polished through 0.05 micron alumina. The couples were analyzed by point-to-point counting techniques for concentration profiles and compositions of phases with a JEOL 35 CF scanning electron microscope equipped with a Tracor Northern Series II energy dispersive X-ray analyzer. Intensities of K_{α} x-radiations of Fe, Ni, and Cr identified at the energies of 6.403 KeV, 7.477 KeV, and 5.414 KeV, respectively, of Zr L_{α} x-radiation at 2.042 KeV and of U M_{α} x-radiation at 3.171 KeV were collected and stored on floppy discs and converted into compositions with the aid of elemental standards and a ZAF correction program. Secondary electron micrographs were taken of diffusion structures

developed in the various couples. Individual phases analyzed in the diffusion zones of the various diffusion couples are listed in Table 2 where intermetallic designations are used to represent the measured concentration ratios.

III. Results

The various phases identified in the diffusion structures of the 3 couples investigated in this study are listed in Table II. The intermetallic designations of the phases are based on the ratio of the (U + Zr) concentration to that of (Fe + Ni + Cr). The details on the diffusion structures and their representation by experimental diffusion paths are presented below.

A. Diffusion Structures

The diffusion structure developed for the couple F(U-23 Zr) vs. 316 is shown in Fig. 1 and is around 100 μm wide. In multiphase layers, the phases which appear as the matrix are U-rich, while the precipitates are Zr-rich. The primary single-phase layer for this couple is $\text{U}(\text{Fe}, \text{Ni}, \text{Cr})_2$. The other phases that appear in the diffusion structure include $(\text{Zr}, \text{U})(\text{Fe}, \text{Cr}, \text{Ni})_{2-3}$, $(\text{Zr}, \text{U})_2(\text{Fe}, \text{Cr}, \text{Ni})$, $\text{U}_6(\text{Fe}, \text{Ni})$, and $(\text{U}, \text{Zr})_9(\text{Fe}, \text{Ni})$.

The diffusion structure for the couple F(U-23 Zr) vs. D9 is presented in Fig. 2. It exceeds 175 μm in width and contains phases with similar compositions ratios as those found in the F vs. 316 couple. These phases include: $\text{U}_6(\text{Fe}, \text{Ni})$, $\text{U}(\text{Fe}, \text{Ni}, \text{Cr})_2$, $(\text{Zr}, \text{U})(\text{Fe}, \text{Ni}, \text{Cr})_2$, $(\text{Zr}, \text{U})_2(\text{Fe}, \text{Cr}, \text{Ni})$, and $(\text{U}, \text{Zr})_9(\text{Fe}, \text{Ni}, \text{Cr})$. A high Zr phase (> 80%) is observed in this couple along with a phase whose composition is similar to that of the σ phase of the Fe-Cr binary system. In a region adjacent to the high Zr phase, the $(\text{Zr}, \text{U})(\text{Fe}, \text{Ni}, \text{Cr})_2$ precipitates exhibit high Cr concentrations (≈ 35 at.%). Comparatively, the $(\text{Zr}, \text{U})(\text{Fe}, \text{Ni}, \text{Cr})_2$ phase in the F vs. 316 couple contains approximately 16 at.% Cr. For the $(\text{Zr}, \text{U})_2(\text{Fe}, \text{Cr}, \text{Ni})$ precipitates, Fe concentrations increase and Ni concentrations decrease in the diffusion zone towards the fuel-side of the diffusion structure, while the U and Zr concentration levels stay relatively constant.

The diffusion structure for the couple F vs. HT9 is approximately 30 μm wide and is shown in Fig. 3. Phase layers of UFe_2 , and a Zr-rich phase developed on the cladding-side of the diffusion structure. A two-phase region with a U-rich matrix and Zr-rich precipitate developed on the fuel side of the diffusion structure. Fe levels of 2-3 at.% are apparent for around 90 μm towards the fuel side of the diffusion structure, and a point-by-point analysis of the precipitates indicated that Fe is preferentially present in the precipitates as opposed to the matrix. The diffusion structure for this couple is much narrower and contains fewer diffusion layers and fewer phases than the F vs. 316 vs. D9 couples.

B. Diffusion Paths

For the description of diffusion structures of the multicomponent diffusion couples of this study with experimental diffusion paths on composition triangles, the sum of the concentrations of Fe, Ni and Cr is taken as one concentration variable, while U and Zr represent the other two. Thus, at any point within the triangle, the sum of the concentrations (atom fractions) of the cladding elements Fe, Ni, or Cr when added to those of the elements U and Zr will equal one. A diffusion path constructed on this basis from the concentration profiles can be used to describe the diffusion structure and is helpful in comparing the diffusion structures of the various couples. The diffusion path segments crossing a two-phase region are represented by bold dashed lines, while bold solid lines show path segments in single-phase regions. Thin dashed lines indicate schematic tie-lines for two-phase regions, and shaded areas represent approximate ranges of composition for single-phase regions. This procedure for the representation of diffusion path is employed for all couples.

The diffusion path for the couple F(U-23 Zr) vs. 316 is presented in Fig. 4(a). The path segment a-b corresponds to the two-phase region with U(Fe, Ni, Cr)_2 precipitates distributed in the Fe-Ni-Cr austenitic matrix. The various segments of the diffusion path are identified on the diffusion structure of the couple in Fig. 1. Segments b-c and d-e represent the single-phase layers U(Fe, Ni, Cr)_2 and $(\text{Zr, U})(\text{Fe, Ni, Cr)}_2$, respectively. Segment c-d represents the $[\text{U(Fe, Ni, Cr)}_2]$ phase.

$\text{Ni, Cr}_2 + (\text{Zr, U})(\text{Fe, Ni, Cr}_2)$ two-phase layer. The diffusion path cuts across tie-lines in these regions which link the matrix and precipitate compositions. Path segment e-g crosses regions where two and three phases are present in the diffusion zone. Phases identified in these regions include: $\text{U}_6(\text{Fe, Ni})$ and U which are matrices, and $(\text{Zr, U})(\text{Fe, Cr, Ni})_{2-3}$, $(\text{Zr, U})_2(\text{Fe, Cr, Ni})$ and $(\text{U, Zr})_2(\text{Fe, Ni})$ which appear as precipitates. Segment f-g represents the $[(\text{U, Zr})_9(\text{Fe, Ni}) + \text{U} + \delta]$ three-phase layer.

In Fig. 4(b) is presented the experimental diffusion path for the F vs. D9 couple. It is similar to the diffusion path observed for the F vs. 316 couple except that the path segment a-b extends closer to the U corner of the composition triangle; this is because of the two and three-phase layers that appear adjacent to the $\text{U}(\text{Fe, Ni, Cr})_2$ single-phase layer. These layers correspond to $[\text{U}_6(\text{Fe, Ni}) + \text{Zr}(> 80\%)]$, $[\text{U}_6(\text{Fe, Ni}) + \text{Zr}(> 80\%) + (\text{Zr, U})(\text{Fe, Ni, Cr})_2]$, and $[\text{U}_6(\text{Fe, Ni}) + (\text{Zr, U})(\text{Fe, Ni, Cr})_2]$. A $(\text{U, Zr})_9(\text{Fe, Ni})$ phase appears as a single-phase layer on the fuel side of the diffusion structure and it is represented by path segment f-g.

The experimental diffusion path for couple F vs. HT9 is presented in Fig. 4(c). The path extends closer towards the Zr corner of the triangle compared to the F vs. D9 and F vs. 316 diffusion couples. Path segment b-c describes the single-phase layer $\text{U}(\text{Fe, Cr})_2$ and segment d-e represents the Zr-phase. e-f describes the two-phase layer where U is the matrix and Zr the precipitate.

IV. Discussion

A. On Diffusion Layers

The intermetallic phases developed for the couples F vs. 316 and F vs. D9 as listed in Table II are very similar. The Ni bearing diffusion couples, F vs. 316 and F vs. D9, show very similar diffusion structures (Fig. 1 and 2) with comparable width (over 100 μm) and similar phases. The major difference between the two couples is the development of a $(\text{U, Zr})_9(\text{Fe, Ni})$ single-phase layer observed only in the F vs. D9 couple. The HT9 couple which contains

negligibly small amounts of Ni has a diffusion structure (Fig. 3) that is different from these of the F vs. 316 and F vs. D9 couples. In the presence of very low concentration of Ni, many metallic phases are not observed in the F vs. HT9 couple, which develops the smallest diffusion structure of all the couples assembled with cladding steels.

Even though Fe and Ni play the dominant role in the development of diffusion structures, Cr is crucial with regard to the development of Zr layers. From the diffusion structure for the F vs. HT9 couple where a Zr layer develops, Cr can be expected to affect the activity of Zr in the δ precipitates and cause them to become unstable and to yield a Zr layer. The Zr layer may impede the interdiffusion of fuel and cladding elements. When Cr is in the presence of approximately 15 at.% Ni, a large diffusion structure develops as is apparent for the F vs. D9 couple in Fig. 2. In this couple, Cr seems to affect the activity of Zr in Zr-rich precipitates as was observed for the F vs. HT9 couple. A region of high-Zr precipitates is observed in the diffusion structure of the F vs. D9 couple near phase regions containing $(\text{Zr}, \text{U})(\text{Fe}, \text{Ni}, \text{Cr})_2$ phases with relatively high Cr levels. The $(\text{Zr}, \text{U})(\text{Fe}, \text{Ni}, \text{Cr})_2$ phase for the F vs. D9 couple has higher levels of Cr than the corresponding phase observed for other couples (~ 35 at.% compared to 16 at.%). In addition, from the cladding side of the $\text{U}(\text{Fe}, \text{Ni}, \text{Cr})_2$ layer towards the high-Zr precipitate side, Cr levels are observed to increase (from 12 to 22 at.%). Therefore, as indicated for the F vs. HT9 couple, high Cr levels in the couple F vs. D9 are considered to give rise to the formation of high-Zr phases. The effect of Cr on the activity of Zr may cause the $(\text{Zr}, \text{U})(\text{Fe}, \text{Ni}, \text{Cr})_2$ phase to decompose resulting in the formation of a high-Zr phase. This is similar to the decomposition of δ precipitates in the F vs. HT9 couple resulting in the formation of a high-Zr layer.

The differences in the diffusion layers of the various couples are reflected in their diffusion paths. The F vs. 316 and F vs. D9 diffusion couples have similar diffusion paths (Figs. 4(a) and 4(b)) that extend through the same types of phase layers. The diffusion structure for the F vs. D9 couple does not contain a well-defined $(\text{Zr}, \text{U})(\text{Fe}, \text{Ni}, \text{Cr})_2$ single-phase layer like the F vs. 316, and as a result the diffusion path for the F vs. D9 couple extends closer

towards the U corner of the composition triangle. The diffusion path for the F vs. HT9 couple (Fig. 4(c)) differs from the diffusion paths for both the F vs. D9 and F vs. 316 couples. It extends closer towards the Zr-corner of the isotherm than any of the Ni bearing couples and includes only one intermediate phase layer. Therefore, the presence of 10 to 15 at.% Ni appears to play a deciding role in determining the phase layers that form in the diffusion structure and hence in the development of diffusion paths.

B. The interdiffusion behavior of Fe, Ni, and Cr

The results of interdiffusion studies with a U-23 at.% Zr fuel assembled with Fe, Ni, Fe-20.1 Cr, Ni-16.4 Cr, Fe-10.1 Ni, and Fe-15.4 Ni-9.4 Cr were reported in a recent paper [8]. On the basis of this work, Ni is considered to play a major role in the interdiffusion of fuel and cladding components; Ni containing alloys are more susceptible to forming intermetallics phases with U and Zr than alloys without Ni. In general, the diffusion layers formed on the cladding side of the couples are dictated by the Ni, Fe, and Cr interactions with U, and the phases on the fuel side of the couple are influenced by the type of intermetallic phases that can form between Zr and the cladding elements. Cr influences the interdiffusion behavior by affecting the activities of U and Zr in the δ precipitates of the binary U-Zr fuel resulting in the development of a Zr-rich layer, which can reduce interdiffusion of fuel and cladding elements. These observations are consistent with the types of phases observed in the diffusion structures of the couples in the present study.

Cladding steels have more elements available for interdiffusion than Fe, Ni, and Cr. Yet, the diffusion structures and the types of intermetallics observed for the couples with cladding steels are essentially dictated by the interactions of Fe, Ni, and Cr with U and Zr and other elements appear to play a minor role. U is a faster diffuser and the diffusion layers on the cladding side of the couples are dictated by Fe, Ni, and Cr interactions with U. Phases on the fuel side of the couples are influenced by the type of intermetallics that can form between Zr and the cladding elements. As reported for the couples in [8], the diffusion layers that

developed are consistent with the type of intermetallic phases identified between U and Ni, U and Fe, Zr and Ni, and Zr and Fe on the basis of phase diagrams. Since Cr does not form intermetallics with U and Zr, its role appears to be indirect in affecting Zr activity in high-Zr precipitates. Of all the cladding elements, Fe and Ni penetrate deepest into the fuel for all diffusion couples investigated in this study.

5. Conclusions

In the light of the relative diffusion behavior of the fuel and cladding elements and their roles in determining the intermetallic formation, HT9 is considered to be the most favorable choice for a cladding material in the context of fuel-cladding compatibility. HT9 has the lowest Ni concentration of all the cladding steels and forms the smallest diffusion structure with the fewest number of phases. It exhibits the smallest amount of interdiffusion between fuel and cladding elements possibly due to the formation of a Zr-rich layer, and the number of observed phases is minimal relative to those observed for Ni bearing couples. Since Fe and Ni penetration into the fuel is appreciably smaller with HT9 than with D9 or 316 as the cladding steel, the formation of low melting phases or strength reducing structures is less likely with HT9. Hence, it is concluded that the structural integrity of the cladding can be maintained for a longer period of time during reactor operation with HT9 than with 316 or D9. The diffusion structures observed for the couples with the commercial cladding steels are consistent with those observed for couples with binary and ternary alloys of the Fe-Ni-Cr system.

Acknowledgments

This research was supported by the U. S. Department of Energy under contract DE-FG07-88ER12814. Additional support by the Argonne National Laboratory under the award No. 80000MOD1 is gratefully acknowledged.

References

1. G. L. Hofman, Nucl. Tech., 47 (1980) 7.
2. R. E. Einziger and B. R. Seidel, Nucl. Tech., 50 (1980) 25.
3. B. R. Seidel, L. C. Walters, and Y. I. Chang, J. Metall., 39 (1987) 10.
4. B. R. Siedel and L. C. Walters, Trans of ASME, 103 (1981) 612.
5. L. C. Walters and J. H. Kittel, Nucl. Tech., 48 (1980) 273.
6. C. E. Lahm, et al., Nucl. Engr. and Design, 101 (1987) 25.
7. G. L. Hofman, et al., in: Proc. of the International Conference on Reliable Fuels for Liquid Metal Reactors, Tucson, AZ (1986) pp. 4-121.
8. D. D. Keiser, Jr. and M. A. Dayananda, J. Nucl. Mat., 1993 (in print).

Table I. Typical compositions of cladding steels (at.%) employed by ANL.

	HT9	D9	316
Fe	Bal	Bal	Bal
Cr	12.02	13.45	16.30
Ni	0.57	15.61	10.50
Mo	1.03	1.65	2.11
Ti	0.002	0.32	0.0
V	0.34	> 0.01	0.0
W	0.51	> 0.01	0.0
Mn	0.50	2.05	1.47
Si	0.22	0.85	0.67
C	0.21	0.034	0.05
N	0.0037	0.0051	0.0612
O	0.0058	0.0062	0.0075

Table II. Phases identified in diffusion couples.

Diffusion Couple	Phases*
F vs. 316	$U(Fe,Ni,Cr)_2$, $U_6(Fe,Ni)$, $(Zr,U)(Fe,Ni,Cr)_2$, $(Zr,U)_2(Fe,Ni)$, $(U,Zr)_9(Fe,Ni)$
F vs. D9	$U(Fe,Ni,Cr)_2$, $U_6(Fe,Ni)$, $(Zr,U)(Fe,Ni,Cr)_2$, $(Zr,U)_2(Fe,Ni)$, $(U,Zr)_9(Fe,Ni)$, Zr-rich phase, σ
F vs. HT9	$U(Fe,Cr)_2$, Zr-rich phase, σ

*The intermetallic designations of the phases are based on the relative concentrations of the individual elements.

Fig. 1. SEM micrographs showing the diffusion layers and intermetallic phases developed for the F(U-23 Zr) vs. 316 couple annealed at 700°C for 4 days; (a) and (b) are at two different magnifications.

Fig. 2. SEM micrographs showing the diffusion layers and intermetallic phases developed for the F(U-23 Zr) vs. D9 couple annealed at 700°C for 4 days; (a) and (b) are at two different magnifications.

Fig. 3. SEM micrographs showing the diffusion layers and intermetallic phases developed for the F(U-23 Zr) vs. HT9 couple annealed at 700°C for 4 days; (a) and (b) are at two different magnifications.

Figure 4. Experimental diffusion paths on composition triangles at 700°C for the couples (a) F vs. 316, (b) F vs. D9, and (c) F vs. HT9. Diffusion layer designations are based on relative ratios of concentrations. The phase boundaries are approximate and schematic.

APPENDIX F

Interdiffusion of Cerium in Fe-Base Alloys with Ni or Cr

INTERDIFFUSION OF CERIUM IN Fe-BASE ALLOYS WITH Ni OR Cr

**P. C. Tortorici and M. A. Dayananda
Purdue University, W. Lafayette, IN 47907-1289, USA**

ABSTRACT

Isothermal interdiffusion studies relevant to lanthanide interactions with cladding alloys in the Integral Fast Reactor program were carried out at 425°C by employing solid-solid diffusion couples assembled with disks of Ce and disks of Fe, Ni, and Fe-10.1 Ni, and Fe-20.1 Cr, binary alloys (composition in at. %). The diffusion structures and intermetallic layers which developed in the various couples during the diffusion anneal were metallographically examined and analyzed by SEM-EDS techniques for concentration profiles. Computer programs were developed to construct profiles of concentrations and to evaluate interdiffusion fluxes and effective interdiffusion coefficients for the individual components over selected regions of the diffusion zones of the various couples. Intrinsic diffusion data were calculated at marker planes in the Ni_3Ce_7 and Fe_2Ce phases developed in the Ni vs. Ce and Fe vs. Ce couples, respectively. The intermetallic phases and diffusion layers observed in the various couples are discussed in the light of phase diagrams and experimental diffusion paths.

1. Introduction

The main features underlying the Integral Fast Reactor (IFR) concept which is being developed at Argonne National Laboratory include the use of U-Pu-Zr metallic fuel, liquid sodium cooling, a pool type reactor configuration, and the reprocessing of fuel [1]. The metallic U-Pu-Zr fuel offers high thermal conductivity, ease of fabrication, good irradiation behavior, high burn-up potential, among other benefits.

During irradiation, the U-Pu-Zr fuel swells and comes into contact with the stainless steel cladding enclosing the fuel element. Also during the irradiation process, a number of fission products including lanthanides (Ce, La, Pr among others) are generated. The migration of the lanthanides through the fuel towards the fuel/clad interface can result in their chemical interaction with the stainless steel cladding materials. Such interactions can result in the formation of intermetallic phases and low melting eutectics, which adversely affect the structural integrity of the cladding alloy as a result of localized melting.

The extent of the interaction between the fuel containing lanthanides and cladding alloys is among the major issues that are currently being investigated in the context of fuel/clad compatibility and assessment of acceptable fuel/cladding combinations. In this study, interdiffusion experiments were carried out at 425°C with solid-solid diffusion couples assembled with disks of Ce and disks of Fe, Ni, and Fe-10.1 Ni, and Fe-20.1 Cr binary alloys. The diffusion layers that developed in the various couples are examined for the identification of intermetallic phases, analyzed for average effective interdiffusion coefficients for the individual components, and described with the aid of phase diagrams and diffusion paths.

2. Experimental Procedure

Ce, Ni and Fe (99.9% pure) were obtained from Rhone-Poulenc Inc, Alpha Products Inc, and Goodfellow Inc., respectively. Binary alloys with compositions of Fe-10.1 Ni, and Fe-20.1 Cr were fabricated at by vacuum induction melting [2]. Charges were melted in alumina

crucibles under an argon atmosphere, and drawn up fused silica draw tubes, 10 mm in diameter. All alloys were homogenized at 1150°C for 7 days in an evacuated quartz capsule.

Diffusion disks, approximately 5 mm in diameter and 5 mm thick, were sectioned from Ce, Ni, Fe and various alloys. The disk surfaces were ground through 600 grit SiC paper to ensure parallel faces. The disks were metallographically polished through 1 μm diamond paste in an Aldrich atmosbag with flowing helium (99.9%). This procedure was employed to ensure that the surfaces were free from an oxide layer; the helium environment was especially required for cerium whose reactivity with air and water based solvents is severe. The polished disks were employed in assembling sandwich couples inside a Kovar steel jig consisting of two end plates and three threaded Kovar steel rods. The couples consisted of a Ce disk sandwiched by selected alloy disks, one on either side. Kovar steel (54 Fe-29 Ni-17 Co at.%) was chosen for the jig due to its low coefficient of thermal expansion.

The assembled couples were then placed in quartz capsules which were sealed at one end under a constant flow of helium gas. The capsule was then attached to a vacuum system, evacuated and backfilled with hydrogen gas several times. After a final evacuation, the capsule was sealed and annealed in a horizontal Lindberg three-zone tube furnace at 425°C for 4 days.

The annealed capsules were quenched in an ice water bath after the diffusion anneal. The couples with the Kovar jigs were removed and cold-mounted in a clear epoxy resin. The mounted couples were sectioned with an Isomet diamond saw to expose surfaces parallel to the diffusion direction. The exposed sections were then mechanically polished on 600 grit SiC paper and through 1 μm diamond paste on a cloth wheel with dehydrated ethyl alcohol used as a lubricant in all steps.

The polished sample was immediately transferred to a JEOL 35CF scanning electron microscope (SEM), equipped with a Tracor Northern Series II energy dispersive X-ray analyzer. The couples were analyzed by point-to-point counting techniques for concentration profiles and phase identification. The intensities of X-ray K_{α} lines for Fe (6.403 keV), Ni (7.477 keV), Cr

(5.414 keV), and L_{α} line for Ce (4.839 keV) were collected and stored on floppy disks, then converted into compositions with the aid of pure elemental standards and a ZAF correction program. Secondary electron micrographs were taken to record the diffusion structure and intermetallic layers developed in the various couples.

3. Results

3.1. Diffusion structures and intermetallic phases

The phase layers identified in the diffusion structures of the various couples in this study are listed in Table 1. The intermetallic designations of the phase layers in Table 1 are entirely based on compositional analysis by EDS ignoring the trace impurities such as C, O, and N. The designation for a phase layer corresponds to the ratio of the Ce concentration to the sum of all the other elements analyzed in the layer and is not based on any intermetallic structural data. Based on the counting statistics, the uncertainty in the EDS analysis of the major elements Ce, Fe, Ni, and Cr is within ± 0.5 at.%. On the basis of the Ni vs. Ce and Fe vs Ce phase diagrams [3] presented in Figs 1(a) and 1(b), respectively, six possible intermetallic compounds are observed between Ce and Ni, while only two can form between Ce and Fe. Ce and Cr have negligible solubility in each other and form no intermetallic compounds [3].

3.1.1. Binary Couples: Ni vs. Ce and Fe vs. Ce

The diffusion structure and the concentration profile for the Ni vs. Ce couple are presented in Fig. 2(a) and 2(b), respectively. Two diffusion layers developed in this couple and correspond to Ni_2Ce and Ni_3Ce_7 phases in the phase diagram in Fig. 1(a). The intermetallic designation of the phases are based on the approximate ratio of Ni concentration to that of Ce. The approximate widths of the Ni_2Ce and Ni_3Ce_7 layers are 10 μm and 240 μm , respectively. The Matano plane for the couple determined on the basis of mass balance is identified at x_0 and a marker plane is identified at x_m in the Ni_3Ce_7 phase.

A secondary electron micrograph and the concentration profile for the Fe vs. Ce couple are presented in Fig. 3. Only one diffusion layer, approximately 20 μm wide, develops as can be seen in Fig. 3(a); the layer corresponds to Fe_2Ce phase on the basis of the phase diagram in Fig. 1(b). The width of the diffusion zone of the Fe vs. Ce couple is appreciably smaller than that of Ni vs. Ce couple. The interdiffusion of Ni in Ce is much more rapid than that of Fe in Ce. A marker plane is identified in the Fe_2Ce phase in Fig. 3(b).

3.1.2. Ternary Couples: Fe-10.1 Ni vs. Ce, Fe-20.1 Cr vs. Ce

In Fig. 4 (a) and 4(b) are presented the diffusion structure and the concentration profiles for the Fe-10.1 Ni vs. Ce couple. Two diffusion layers observed in the micrograph in Fig. 4(a) correspond to $(\text{Fe} + \text{Ni})_2\text{Ce}$ and $(\text{Ni} + \text{Fe})_3\text{Ce}_7$ phases. The width of the diffusion zone is of the order of 25 μm and is similar to that observed for the Fe vs. Ce couple.

The diffusion structure and the concentration profiles for the Fe-20.1 Cr vs. Ce ternary couple are presented in Fig. 5. Two diffusion layers corresponding to $(\text{Fe} + \text{Cr})_7\text{Ce}_3$ and Fe_2Ce phases are observed in the diffusion zone whose width is approximately 20 μm . The $(\text{Fe} + \text{Cr})_7\text{Ce}_3$ layer developed in the couple does not correspond to any phase on the binary Fe-Ce diagram. The layer identified as Fe_2Ce has negligible amounts of Cr, as can be seen from the Cr concentration profile in Fig. 5(b). In addition, Cr appears to build up in the $(\text{Fe} + \text{Cr})_7\text{Ce}_3$ layer.

The diffusion paths for all the ternary couples are presented on composition triangles in Fig. 6. The paths are S-shaped as required for solid-solid couples. The single phase layers developed in the various couples are identified by the shaded areas on the composition triangles. In Fig. 6(a) the dashed line segments, ab, cd and ef of the diffusion path for the Fe-10.1 Ni vs. Ce couple represent tie lines for two-phase equilibria at the interfaces between Ce and $(\text{Ni} + \text{Fe})_3\text{Ce}_7$ phases, $(\text{Ni} + \text{Fe})_3\text{Ce}_7$ and $(\text{Fe} + \text{Ni})_2\text{Ce}$ phases, and $(\text{Fe} + \text{Ni})_2\text{Ce}$ and Fe-10.1 Ni phases, respectively. Similarly, the path segments, ab, cd and ef in Fig. 7(b) correspond to

two-phase equilibria at the interfaces between Ce and Fe₂Ce phases, Fe₂Ce and (Fe + Cr)₇Ce₃ phases and (Fe + Cr)₇Ce₃ and Fe-20.1Cr phases, respectively.

3.2. Average Effective Interdiffusion Coefficients

On the basis of an analysis by Dayananda [4,5], average effective interdiffusion coefficients and root-mean-square penetration depths can be determined for individual components in binary and multicomponent diffusion couples. This analysis is employed to calculate an effective interdiffusion coefficient for each component over selected ranges of concentrations in the diffusion zones of the diffusion couples investigated in this study.

On the basis of Onsager's formalism [6] of Fick's law, the interdiffusion flux $\tilde{J}_i$ of component i in an n -component alloy is expressed by [4]:

$$\tilde{J}_i = -\tilde{D}_i^{\text{eff}} \frac{\partial C_i}{\partial x} \quad (1)$$

where

$$\tilde{D}_i^{\text{eff}} = \tilde{D}_{ii}^n + \sum_j^{n-1} \frac{\tilde{D}_{ij}^n \partial C_j / \partial x}{\partial C_i / \partial x} \quad (j \neq i) \quad (2)$$

For component i , $\tilde{D}_{ii}^n$ is the main interdiffusion coefficient, and the second term in Eq. (2) incorporates cross interdiffusion coefficients, $\tilde{D}_{ij}^n$. For an isothermal diffusion couple assembled with two alloys of initial concentrations, C_i^+ and C_i^- , and diffusion annealed for time t , the interdiffusion fluxes based on a laboratory fixed frame can be determined directly from the concentration profiles on the basis of the relation [7,8]:

$$\tilde{J}_i = \frac{1}{2t} \int_{C_i^+ \text{ or } C_i^-}^{C_i(x)} (x - x_0) dC_i \quad (3)$$

where x_0 refers to the Matano plane. Upon integration of $\tilde{J}_i$ over x from $+\infty$ to x_0 , one derives the following relation [4]:

$$\int_{-\infty}^{x_0} \tilde{J}_i dx = - \frac{1}{2t} \int_{C_i^+}^{x_0} (x - x_0)^2 dC_i \quad (4)$$

A substitution of Eq. (1) into Eq. (4) yields:

$$\tilde{D}_{i,R} = \frac{1}{2t} \frac{\int_{C_i^+}^{x_0} (x - x_0)^2 dC_i}{[C_i^0 - C_i^+]} \quad (5)$$

where C_i^0 refers to the concentration at the Matano plane and $\tilde{D}_{i,R}$ is termed the average effective interdiffusion coefficient for component i to the right of the Matano plane, over the range C_i^+ to C_i^0 . From Eq. (5) an effective penetration depth for component i on the right-hand side of the Matano plane can be determined by:

$$\bar{x}_{i,R} = \sqrt{2\tilde{D}_{i,R}t} \quad (6)$$

where $\bar{x}_{i,R}$ corresponds to the root-mean-square value of $\sqrt{(x - x_0)^2}$. A similar procedure can be applied to the concentration profile on the left-hand side of the Matano plane for the determination of an average effective interdiffusion coefficient, $\tilde{D}_{i,L}$, and an effective penetration depth, $\bar{x}_{i,L}$. Effective interdiffusion coefficients and penetration depths for the individual components were evaluated over selected phase layers on either side of the Matano plane for the Ni vs. Ce, Fe vs. Ce, Fe-10.1 Ni vs. Ce, and Fe-20.1 Cr vs. Ce couples and are reported in Table 2.

3.2.2. Intrinsic Diffusion in Ni_3Ce_7 and Fe_2Ce Phases

For the Ni vs. Ce and Fe vs. Ce binary diffusion couples, marker planes were identified after diffusion in the Ni_3Ce_7 and Fe_2Ce phase layers, respectively, as indicated at x_m in Figs. 2(b) and 3(b). The cumulative intrinsic flux, A_i , of component i past a marker plane moving parabolically with time at a constant composition is obtained by integrating the intrinsic flux J_i over time t [9]; thus,

$$A_i = \int_0^t J_i dx$$

$$= - 2t D_i \left. \frac{\partial C_i}{\partial x} \right|_{x_m} \quad (i=1,2) \quad (7)$$

where D_i is the intrinsic diffusion coefficient for component i . A_i is determined graphically from appropriate areas under the concentration profiles. For the ratio of cumulative intrinsic fluxes, Eq. (7) yields:

$$\left| \frac{A_1}{A_2} \right| = \frac{D_1}{D_2} \quad (8)$$

On the basis of Eq. (8), the ratio $\frac{D_{Ni}}{D_{Ce}}$ of intrinsic diffusion coefficients in the Ni_3Ce_7 phase was determined to be 15, while a value of 4 was obtained for the ratio of $\frac{D_{Fe}}{D_{Ce}}$ for the Fe_2Ce phase.

4. Discussion

4.1. Phase Layer Development

As reported in Table 1, the phase layers that developed in the binary Ni vs. Ce and Fe vs. Ce couples include only a few of the various intermetallic phases which can form on the basis of the binary phase diagrams in Fig. 1. Among the six possible intermetallic phases between Ni and Ce, only two phases, Ni_2Ce and Ni_3Ce_7 , were observed in the Ni vs. Ce couple. The Ni_3Ce_7 phase is expected to form on the Ce side, as there exists some solubility of Ni in Ce. The growth of the Ni_3Ce_7 phase occurs faster towards the Ce side than in the opposite direction towards the Ni side, as can be seen in Fig. 2(b) by the location of the Matano plane. This observation is consistent with the fact that Ni intrinsically diffuses nearly 16 times faster than Ce in the Ni_3Ce_7 phase, as calculated on the basis of Eq. (8). The small thickness of the Ni_2Ce

layer relative to that of Ni_3Ce_7 indicate that the velocities of $\text{Ni}/\text{Ni}_2\text{Ce}$ and $\text{Ni}_2\text{Ce}/\text{Ni}_3\text{Ce}_7$ interfaces in the direction towards Ni are quite similar. Among the two phases, $\text{Fe}_{17}\text{Ce}_2$ and Fe_2Ce that can form between Fe and Ce on the basis of the phase diagram in Fig. 1(b), only the Fe_2Ce phase was observed as a thin layer in the Fe vs. Ce couple. Not all phases based on the phase diagram need to form in a multiphase diffusion couple, as the appearance of a phase in the diffusion zone is influenced by nucleation barriers, incubation time, and interdiffusion behavior in the adjacent phases [10].

From a comparison of the widths of the diffusion zones for the Ni vs. Ce and Fe vs. Ce binary couples, it is apparent that the interdiffusion of Ni with Ce is appreciably faster than that of Fe with Ce. The phases, Ni_3Ce_7 and Fe_2Ce , formed in the two couples form eutectics with Ce at 477°C and 592°C , respectively. In the context of lanthanide interactions with clad alloys, the formation of the Ni_3Ce_7 and Fe_2Ce phases can be considered undesirable.

The layers of $(\text{Fe} + \text{Ni})_2\text{Ce}$ and $(\text{Ni} + \text{Fe})_3\text{Ce}_7$ intermetallics developed in the ternary Fe-10.1 Ni vs. Ce couple shown in Fig. 4 are comparable to the Fe_2Ce and Ni_3Ce_7 phases identified in the binary couples. In the $(\text{Fe} + \text{Ni})_2\text{Ce}$ phase, the Ni concentration is about 3 at.%, while the concentration of Fe is about 3 at.% in the $(\text{Ni} + \text{Fe})_3\text{Ce}_7$ phase. Hence, the compositions of these phases are quite close to Fe-Ce and Ni-Ce edges of the composition triangle as indicated on the diffusion path in Fig. 6(a). The important thing to note is that the presence of 10 at.% Ni in the Fe-base terminal alloy of the couple is enough to cause the formation of a layer of Ni_3Ce_7 type phase containing a few at.% Fe, although the thickness of the layer is quite limited as indicated in Table 1.

The ternary Fe-20.1 Cr vs. Ce couple which developed the layers of $(\text{Fe} + \text{Cr})_7\text{Ce}_3$ and Fe_2Ce as shown in Fig. 5 provides an insight into the effect of Cr addition to Fe on the development of diffusion structure. The Fe_2Ce layer has little Cr and is similar to that developed for the Fe vs. Ce binary couple. This observation implies that Cr has little solubility in the Fe_2Ce phase. On the other hand, the $(\text{Fe} + \text{Cr})_7\text{Ce}_3$ phase has appreciable Cr, as can be

seen in Fig. 5(b) and Fig. 6(b). This is a new ternary phase not reported earlier, and there is no analogous binary Fe_7Ce_3 phase on the Fe-Ce phase diagram.

4.2. Interdiffusion Behavior of the Elements in Various Couples

The relative interdiffusion behavior of the individual elements in the various couples can be appreciated from the average effective interdiffusion coefficients reported in Table 2. $\tilde{D}_{\text{Ni,R}}^{\text{eff}}$ calculated for the diffusion zone on the right-hand-side of the Matano plane for the Ni vs Ce couple in Fig. 2(b) involves essentially the Ni_3Ce_7 phase and is larger than $\tilde{D}_{\text{Ni,L}}^{\text{eff}}$ calculated for the left-hand-side which includes the Ni_2Ce layer. Hence, the interdiffusion coefficient of Ni or Ce for the Ni_3Ce_7 phase is larger than that for the Ni_2Ce phase. Similarly, $\tilde{D}_{\text{Ni,R}}^{\text{eff}}$ for the Fe-10.1 Ni vs. Ce couple is large and is for the diffusion zone including the $(\text{Ni} + \text{Fe})_3\text{Ce}_7$ phase, which is the ternary extension of the binary Ni_3Ce_7 phase. Lower values of average effective interdiffusion coefficients are observed specifically for Fe over the diffusion zones involving the Fe_2Ce layer in the Fe vs. Ce and Fe-20.1 Cr vs. Ce couples and the $(\text{Ni} + \text{Fe})_3\text{Ce}_7$ layer in the Fe-10.1 Ni vs. Ce couple. Fe interdiffusion in the $(\text{Ni} + \text{Fe})_3\text{Ce}_7$ layer is slower than that in the $(\text{Fe} + \text{Ni})_2\text{Ce}$ layer where the interdiffusion behavior of Ni appears comparable to that of Ce.

The interdiffusion of Cr in the Fe-20.1 Cr vs. Ce couple is of special interest. As can be seen in Fig. 5(b), Cr concentration builds up in the $(\text{Fe} + \text{Cr})_7\text{Ce}_3$ phase, while negligible Cr appears in the adjacent Fe_2Ce phase. From the Cr concentration profile, the interdiffusion flux, $\tilde{J}_{\text{Cr}}$, can be calculated as a function of x on the basis of Eq. (3). The calculated $\tilde{J}_{\text{Cr}}$ is found to be negative and appreciable in magnitude in the $(\text{Fe} + \text{Cr})_7\text{Ce}_3$ phase; on the other hand $\tilde{J}_{\text{Cr}}$ is negligibly small in the Fe_2Ce layer. This observation implies that to the left of the $(\text{Fe} + \text{Cr})_7\text{Ce}_3/\text{Fe}_2\text{Ce}$ interface Cr interdiffuses in the $(\text{Fe} + \text{Cr})_7\text{Ce}_3$ phase in the direction towards the Fe-20.1 Cr alloy, while the Cr flux towards the Ce side on the right-hand-side of the interface is negligible. Hence, Cr transfer across the Matano plane is negligible. Cr is considered to exhibit a flux reversal at the $(\text{Fe} + \text{Cr})_7\text{Ce}_3/\text{Fe}_2\text{Ce}$ interface. Such flux reversals of a component have been reported for multicomponent diffusion couples within single phase

layers or at interfaces [11] and have been discussed by Dayananda in the context of the phenomenon of zero-flux planes and flux reversals [7,8]. A negative effective interdiffusion coefficient $\tilde{D}_{Cr,L}^{eff}$ for Cr reported in Table 2 implies a back-flow and build-up of Cr in the diffusion zone on the left-hand-side of the Matano Plane.

In the present study, the major emphasis has been placed on the development of phase layers due to interdiffusion between Ce and the elements Fe, Ni and Cr. The presence of trace impurities such as O and N would be minimal because of the use of the atmosbag and the He environment employed in the assembly of diffusion couples. The active role of O and N in the development of diffusion structures is considered insignificant in the present study. Systematic assessment of the role of O and N on the interdiffusion process between Ce and Fe-based alloys with Ni and Cr would be of interest in the context of exploring possible barriers that would prevent the development of undesirable low melting eutectic mixtures involving intermetallic layers such as Ni_3Ce_7 and Fe_2Ce .

5. Conclusions

The following are the main conclusions of this study on interdiffusion of Ce in Ni, Fe, Fe-10.1 Ni and Fe-20.1 Cr alloys carried out at 425°C for 4 days.

1. Only a few of the phases expected on the basis of the binary phase diagrams develop in the Ni vs. Ce and Fe vs. Ce diffusion couples. A large diffusion zone with layers of Ni_2Ce and Ni_3Ce_7 intermetallics is observed in the Ni vs. Ce couple, while a thin layer of Fe_2Ce phase forms in the Fe vs. Ce couple.
2. The intrinsic diffusion coefficient of Ni is 15 times larger than that of Ce in the Ni_3Ce_7 phase. Fe intrinsically diffuses 4 times as fast as Ce in the Fe_2Ce phase.
3. The addition of 10 at.% Ni to Fe is sufficient to form the ternary $(Ni + Fe)_3Ce_7$ phase analogous to the binary Ni_3Ce_7 phase.

4. The presence of Cr in the Fe-20.1 Cr vs. Ce couple results in the formation of a ternary $(\text{Fe} + \text{Cr})_7\text{Ce}_3$ phase not previously reported. In addition, Cr exhibits the phenomenon of flux reversal at the $(\text{Fe} + \text{Cr})_7\text{Ce}_3/\text{Fe}_2\text{Ce}$ interface. The back-flow and build-up of Cr in the $(\text{Fe} + \text{Cr})_7\text{Ce}_3$ layer yields a negative effective interdiffusion coefficient for Cr over the diffusion zone on the alloy side of the couple.
5. In the context of lanthanide/cladding interactions, the development of a large Ni_3Ce_7 type layer is undesirable, as it forms a low melting eutectic with Ce at 477°C . Such phases can be avoided with Fe-base alloys containing little Ni. The Fe-20.1 Cr alloy is comparable to pure Fe in the formation of a Fe_2Ce layer which forms a eutectic with Ce at a higher temperature of 592°C .

Acknowledgments

The support for this research was provided by the U. S. Department of Energy under contract DE-FG07-88ER12814 and by the Argonne National Laboratory under the award No. 80000MOD1 and is gratefully acknowledged. This paper is based on a dissertation submitted by P. C. Tortorici to Purdue University in partial fulfillment of the requirements for the M.S. degree in Metallurgical Engineering. Special thanks are given to M. C. Petri at Argonne National Laboratories for assistance with the experimental techniques and sample preparation.

References

1. C. H. Till and Y. I. Chang, Proc. of the American Power Conference 48 (1986) p. 688.
2. M. A. Dayananda and J. G. Duh, Diffusion and Defect Data, 39 (1985) 1.
3. T. B. Massalski [Ed], Binary Alloy Phase Diagrams (ASM International, Materials Park, OH 1986).
4. M. A. Dayananda and D. A. Behnke, Scripta Met., 25 (1991) 2187.
5. M. A. Dayananda: in Ordered Intermetallics-Physical Metallurgy and Mechanical Behavior, C. T. Liu et al. (eds), Kluwer Academic Publishers, (1992), p. 465.
6. L. Onsager, Annals New York Academy of Sciences, 46 (1945) 241.
7. M. A. Dayananda and C. W. Kim, Metall. Trans. A., 10A (1979) 1333.

8. M. A. Dayananda and C. W. Kim, Metall. Trans. A., 14A (1983) 1851.
9. T. Heumann, Z. Phys. Chem., 201 (1958) 168.
10. J. Philibert, Atom Movements Diffusion and Mass Transport in Solid, Les Edition de Physique, France, (1991) p. 420.
11. M. A. Dayananda, Mater. Sci. and Eng., A121 (1989) 351.

Figure 1. The phase diagrams for the (a) Ni vs. Ce and (b) Fe vs. Ce binary systems adapted from ref [3].

Figure 3 (a) Diffusion structure and (b) concentration profiles for the Fe vs. Ce couple annealed at 425°C for 4 days. x_0 and x_m refer to the locations of the Matano plane and the marker plane, respectively.

Figure 4 (a) Diffusion structure and (b) concentration profiles for the Fe-10.1Ni vs. Ce couple annealed at 425°C for 4 days. x_0 refers to the location of the Matano plane.

Figure 6 Experimental diffusion paths on composition triangles at 425°C for the couples (a) Fe-10.1Ni vs. Ce, and (b) Fe-20.1Cr vs. Ce. The phase designations are based on ratios of concentrations.

Table 2. Average effective interdiffusion coefficients and root-mean-square penetration depths for the various couples annealed at 425 °C for 4 days.

Diffusion Couple Assembly	$\tilde{D}_{i,L}^{\text{eff}} \left(\frac{\text{m}^2}{\text{sec}} \right)$	$\tilde{D}_{i,R}^{\text{eff}} \left(\frac{\text{m}^2}{\text{sec}} \right)$	$\bar{x}_{i,L} (\mu\text{m})$	$\bar{x}_{i,R} (\mu\text{m})$
Ni vs. Ce	$\tilde{D}_{\text{Ni or Ce},L}^{\text{eff}} = 7.3 \times 10^{-15}$	$\tilde{D}_{\text{Ni or Ce},R}^{\text{eff}} = 4.9 \times 10^{-14}$	$\bar{x}_{\text{Ni},L} = 70.8$	$\bar{x}_{\text{Ni},R} = 184.8$
Fe vs. Ce	$\tilde{D}_{\text{Fe or Ce},L}^{\text{eff}} = 2.7 \times 10^{-16}$	$\tilde{D}_{\text{Fe or Ce},R}^{\text{eff}} = 8.4 \times 10^{-17}$	$\bar{x}_{\text{Fe},L} = 13.7$	$\bar{x}_{\text{Fe},R} = 7.6$
Fe-10.1Ni vs. Ce	$\tilde{D}_{\text{Fe},L}^{\text{eff}} = 1.4 \times 10^{-16}$	$\tilde{D}_{\text{Fe},R}^{\text{eff}} = 3.4 \times 10^{-17}$	$\bar{x}_{\text{Fe},L} = 9.4$	$\bar{x}_{\text{Fe},R} = 4.7$
	$\tilde{D}_{\text{Ni},L}^{\text{eff}} = 2.6 \times 10^{-16}$	$\tilde{D}_{\text{Ni},R}^{\text{eff}} = 2.9 \times 10^{-15}$	$\bar{x}_{\text{Ni},L} = 13.0$	$\bar{x}_{\text{Ni},R} = 9.6$
	$\tilde{D}_{\text{Ce},L}^{\text{eff}} = 2.3 \times 10^{-16}$	$\tilde{D}_{\text{Ce},R}^{\text{eff}} = 1.3 \times 10^{-16}$	$\bar{x}_{\text{Ce},L} = 12.1$	$\bar{x}_{\text{Ce},R} = 9.2$
Fe-20.1Cr vs. Ce	$\tilde{D}_{\text{Fe},L}^{\text{eff}} = 7.5 \times 10^{-16}$	$\tilde{D}_{\text{Fe},R}^{\text{eff}} = 8.1 \times 10^{-17}$	$\bar{x}_{\text{Fe},L} = 22.7$	$\bar{x}_{\text{Fe},R} = 7.5$
	$\tilde{D}_{\text{Cr},L}^{\text{eff}} = -6.9 \times 10^{-17}$	$\tilde{D}_{\text{Cr},R}^{\text{eff}} = \text{-----}$	$\bar{x}_{\text{Cr},L} = 6.9$	$\bar{x}_{\text{Cr},R} = 0$
	$\tilde{D}_{\text{Ce},L}^{\text{eff}} = 2.9 \times 10^{-16}$	$\tilde{D}_{\text{Ce},R}^{\text{eff}} = 7.7 \times 10^{-17}$	$\bar{x}_{\text{Ce},L} = 14.0$	$\bar{x}_{\text{Ce},R} = 7.3$

Table 1. Phase layers and their thicknesses in the various couples annealed at 425 °C for 4 days.

Couple	Phases Observed *	Layer Thickness (μm)
Ni vs. Ce	Ni_2Ce	10
	Ni_3Ce_7	240
Fe vs. Ce	Fe_2Ce	20
Fe-10.1Ni vs. Ce	$(\text{Fe}+\text{Ni})_2\text{Ce}$	10
	$(\text{Ni}+\text{Fe})_3\text{Ce}_7$	10
Fe-20.1Cr vs. Ce	$(\text{Fe}+\text{Cr})_7\text{Ce}_3$	10
	Fe_2Ce	10

* The designation of a phase layer is based on the ratio of concentration of Ce to the sum of the concentrations of the other elements present in the phase layer.

END

**DATE
FILMED**

5 / 11 / 93