QUARTERLY PROGRESS REPORT

DOE/MC/26365--3174

DE93 006201

Date: July 8, 1992

Reporting Period: April 1, 1992 - June 30, 1992

Project Title: Hydrogen Separation by Ceramic Membranes in Coal Gasification

Identification Number: DE-AC21-90MC26365

Institution: California Institute of Technology

Principal Investigator: G. R. Gavalas

Received by OSTI

JAN 21 1993

I. Project Objectives

Develop hydrogen-permselective ceramic membranes for water-gas shift membrane-reactor suitable for hydrogen production from coal gas. Evaluate the technical and economic potential of the membrane-reactor.

II. Work Performed During Reporting Period

Tasks 1 and 2. Membrane Deposition and Stability Testing

In the last report we described a two-stage membrane preparation technique. The first stage utilizes two-phase interfacial reaction between liquid H_2O and liquid $SiCl_4-CCl_4$ mixture. It will be recalled that the liquid water was held within the pores of Vycor, while the $SiCl_4-CCl_4$ solution was placed either on the bore or outside of the tube. Reaction between $SiCl_4$ and H_2O generates $Si(OH)_xCl_{4-x}$ which further condense and hydrolyze to form dimers and higher condensed species which are soluble in the aqueous phase. Eventually a product layer of silica gel is formed within the Vycor tube wall. After drying and calcining the tube, CVD with gaseous $SiCl_4$ and H_2O is used to seal the pores of the silica gel layer. The permeance of the membrane is clearly inversely proportional to the thickness of the silica gel layer, therefore, the silica layer should be as thin as possible. Another requirement is that the silica gel layer must have relatively high density to prevent penetration of $SiCl_4$ and H_2O reactants in the untreated part of the Vycor support tube during the second stage. During the reporting period experiments were carried out to determine the effect of preparation variables on the properties of the silica gel layer formed by the first stage of the process (interfacial liquid-liquid reaction). Experiments were performed using Vycor tubes (5 mm ID, 7 mm OD, 40 Å mean pore diameter) either closed at the one end or open at both ends.

(a) Tubes Closed at One End

These experiments followed the following procedure:

- (i) The tubes were heated in air at $600^\circ C$ for one hour, and, after cooling, the tube permeance was measured at room temperature.

MASTER

SB

- (ii) A solution of 20% glycerol-water was poured into the tube and quickly imbibed into the pore walls. The solution was then drained, but the liquid within the pores remained by capillarity. The tube was then exposed to the laboratory air for a specified time period.
- (iii) The tube was immersed into a 50% $\text{SiCl}_4\text{-CCl}_4$ solution for a certain period of time and then left to dry in the laboratory atmosphere.
- (iv) The tube was then heated slowly to 600°C and kept at that temperature for one hour under nitrogen flow. After cooling to room temperature, still under nitrogen, the tube permeance to nitrogen and hydrogen was measured.

During the reaction period, when the tube was immersed in the $\text{SiCl}_4\text{-CCl}_4$ mixture, numerous gas bubbles were observed on the $\text{H}_2\text{O-SiCl}_4$ interface, indicating the formation and evolution of HCl (the product of SiCl_4 hydrolysis). In those experiments where the drying period in step (ii) was less than one half hour, a thin loose layer of SiO_2 formed on the external surface--the reaction site. When the drying period in step (ii) was about one hour, or more, no loose layer of SiO_2 formed on the external surface. In either case, however, the tube permeance at the end of step (iv) was the same as that of the untreated tube indicating a very low resistance of the SiO_2 layer formed, either due to very small thickness or very low density, or both.

An additional experiment was carried out under different conditions. A tube that had been standing for a long time in the laboratory was subjected directly to steps (iii) and (iv), omitting steps (i) and (ii). This tube contained some condensed water due to capillarity--at equilibrium with atmospheric humidity. At the end of step (iv) the permeance of this tube to N_2 and H_2 was about one half as that of the untreated tube indicating substantial deposition of SiO_2 during step (iii). The ratio of the two permeances remained at the Knudsen value.

(b) Tubes Open at Both Ends

The procedure for these tubes was as follows:

- (i) The tubes were heated to 600°C and left overnight at that temperature in a stream of 3% $\text{O}_2\text{-N}_2$. The tubes were then cooled down to ambient temperature under dry N_2 flow to prevent readsorption of moisture.
- (ii) A 40% glycerol-water mixture was poured into the bore of the tube and kept there for several hours. The liquid was then drained and a dry N_2 stream was passed at $100\text{ cm}^3/\text{min}$ through the bore for a specified length of time, while the outside of the tube was open to the laboratory air.
- (iii) A 50% $\text{SiCl}_4\text{-CCl}_4$ solution was introduced in the bore of the tube and maintained there for a specified length of time.
- (iv) After draining the reactant mixture and washing with CCl_4 , the tube was dried in the laboratory air for one day at room temperature.
- (v) The tube was slowly heated to 600°C and left at that temperature for one hour. After cooling to room temperature, the tube permeances to hydrogen and nitrogen were measured.

The tube permeances measured at the end were sensitive to several of the experimental details, in particular to the reaction time during step (iii). As expected, the permeance decreased with reaction time. For reaction time of 7 minutes, the permeances of H₂ and N₂ were the same as those of the untreated tube. When the reaction time was increased to 15%, the permeances decreased only slightly, less than 5%. The drying time in step (ii) also seemed to have an effect on the final permeances, but the results so far have not exhibited a consistent pattern. Considerable experimentation is required to delineate the role of the experimental variables and assess the potential of this preparation technique.

**DATE
FILMED**

3 / 2 / 93