Metals and Ceramics Division

**CERAMIC TECHNOLOGY PROJECT DATABASE:
MARCH 1990 SUMMARY REPORT**

B. L. P. Keyes

July 1992

NOTICE: This document contains information of a preliminary nature. It is subject to revision or correction and therefore does not represent a final report.

Prepared for the
U.S. Department of Energy
Assistant Secretary for Conservation and Renewable Energy
Office of Transportation Technologies
EE 51 01 00 0

Prepared by the
OAK RIDGE NATIONAL LABORATORY
Oak Ridge, Tennessee 37831-6285
managed by
MARTIN MARIETTA ENERGY SYSTEMS, INC.
for the
U. S. DEPARTMENT OF ENERGY
under contract DE-AC05-84OR21400

MASTER

de
DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

TABLE OF CONTENTS

	<u>Page</u>
ABSTRACT	1
1. INTRODUCTION	1
2. SYSTEM STATUS UPDATE.	2
3. DATA SUMMARY	5
4. SYSTEM ACCESS	6
5. FUTURE PLANS	8
6. ACKNOWLEDGMENTS	8
7. REFERENCES	9
APPENDIX A: MATERIAL CHARACTERIZATION AND BACKGROUND INFORMATION.	11
Section 1. Test Background Information	13
Section 2. General Text Information	14
Section 3. Densities.	15
Section 4. Hardness Measurements.	16
APPENDIX B: TEST RESULTS.	21
Section 1. Test Background Information	24
Section 2. Cyclic Fatigue Data.	26
Section 3. Fracture Toughness Data	27
Section 4. interrupted Fatigue Data	29
Section 5. Modulus of Rupture 4-Point Bend Data	31
Section 6. Modulus of Elasticity Data	82
Section 7. Tensile Data	85
Section 8. Thermal Expansion Data.	91
Section 9. Modulus of Rupture Properties of Brazed Specimens	93
Section 10. Shear Strength Properties of Brazed Specimens	99

**CERAMIC TECHNOLOGY PROJECT DATABASE:
MARCH 1990 SUMMARY REPORT***

B. L. P. Keyes

ABSTRACT

This report is the fifth in a series of semiannual data summary reports on information being stored in the Ceramic Technology Project (CTP) database. The overall system status as of March 31, 1990, is summarized, and the latest additions of ceramic mechanical properties data are given for zirconia, silicon carbide, and silicon nitride ceramic mechanical properties data, including some properties on brazed specimens.

1. INTRODUCTION

Unlike the previous reports,¹⁻⁴ which concentrated on one class of ceramics per report, this summary contains new test results on several classes of ceramic materials, including zirconias, silicon carbides, and silicon nitrides. Primary sources for information in this report are the semiannual and bimonthly CTP progress reports, ORNL/TM-6513, ORNL/5612, a data disk from M. K. Ferber of Oak Ridge National Laboratory (ORNL), and a package of test results from N. L. Hecht of the University of Dayton Research Institute.

The addition of several new files during this period has further enhanced the usefulness of the overall system. Brazed-specimen bend [modulus of rupture (MOR) four-point], fracture toughness, and shear strength tests, which require more

*Research sponsored by the U.S. Department of Energy, Assistant Secretary for Conservation and Renewable Energy, Office of Transportation Technologies, as part of the Ceramic Technology Project of the Materials Development Program, under contract DE-AC05-84OR21400 with Martin Marietta Energy Systems, Inc.

characterization than tests on non-joined specimens, are now included in the database. A hardness measurement file and an extended comments file for individual test results were also appended to the system.

A hard-copy guide to using the database has also been completed through the first draft. This guide will serve as instructions on using the database until the computerized interface is completed in 1991.

2. SYSTEM STATUS UPDATE

The database presently contains about 5,497 test results on over 320 different batches of ceramic materials. Approximately 46% of these are on zirconia-based ceramics, 9% are on silicon carbides, 21% are on silicon nitrides, 5.7% are on whisker-reinforced silicon nitrides, 16.3% are on alumina-based ceramics (including whisker-reinforced aluminas and mullites), and 2% are on other ceramics. Table 1 provides a more detailed overview of the data presently stored in the system.

Several new files, including three which store brazed-specimen test data, were added to the database during this summary period. Although the testing procedures for unjoined and joined specimens may be the same, additional information is needed to characterize the joint and all the materials used to create it. Often, dissimilar materials are brazed together, as in the case of the MS-PSZ and nodular, cast-iron joints made at ORNL and Battelle Columbus Laboratories. To characterize such a joint would require two material fields and two batch code fields, along with the information on the filler material, the brazing method used, heat treatments, etc. The database now contains files on MOR four-point bend strength tests, shear strength tests, and fracture toughness tests performed on brazed specimens.

TABLE 1. CTP DATABASE SUMMARY AS OF MARCH 31, 1990

Material Class	----- Brazed Specimens -----			Creep	Cyclic Fatigue	Density	Dynamic Fatigue	Elasticity	Fracture Toughness	Hardness	Interrupted Fatigue	Material Characteristics
	MOR	4 Pt Bend	Shear Str. Toughness									
Alumina				1	15		9	24	20			19
Alumina + reinforcing fibers						7			39			91
Alumina + Zirconia												
Mullite								2				2
Mullite + reinforcing fibers								11	16			48
Silicon Carbide						10	13	15	24	27		7
Silicon Nitride			3	27	19	28	16	24	85	112		29
Silicon Nitride + reinforcing fibers					15	2		16	31			44
Zirconia	123	58	2		51	158		92	54		239	37
Zirconia + reinforcing fibers												5
Other									3	27		
Total records	123	61	2	28	100	205	38	184	272	166	239	282

3

Material Class	----- Brazed Specimens -----			Creep	Cyclic Fatigue	Density	Dynamic Fatigue	Elasticity	Fracture Toughness	Hardness	Interrupted Fatigue	Material Characteristics
	MOR	4 Pt Bend	Shear Str. Toughness									
Alumina				1	15		9	24	20			19
Alumina + reinforcing fibers						7			39			91
Alumina + Zirconia												
Mullite								2				2
Mullite + reinforcing fibers								11	16			48
Silicon Carbide			3	27	19	28	16	24	85	112		29
Silicon Nitride					15	2		16	31			44
Silicon Nitride + reinforcing fibers					51	158		92	54		239	37
Zirconia	123	58	2		51	158		92	54		239	37
Zirconia + reinforcing fibers												5
Other									3	27		
Total records	123	61	2	28	100	205	38	184	272	166	239	282

Grand total test result records on file: 5497

Another new file contains the results of various hardness tests. Averaged hardness values are found in the material characteristics file, but the new file provides the user with a better idea of the actual measurements.

Comments on some of the test results exceed the short field space allotted in the test results records. For example, occasionally, a specimen breaks in the grips or the electrical power is interrupted during the test, thus causing abnormal results, or some other out-of-the-ordinary occurrence takes place that affects the outcome of the results. Such details are important and need to be taken into consideration before analyzing the data. These additional comments are stored in DATATXT, an extended comments file whose records contain details pertaining to one test, rather than to a whole set of tests from a single reference. Only those tests containing a "Y" or "T" in the SEETEXT field in the test results record will have entries in this file.

Although the database is physically located in a microcomputer, direct access to users is very limited to protect the integrity of the database. Changes, additions, and deletions are made by one person to avoid jeopardizing the entire system through misuse or abuse by those not familiar with the files. User access is limited to downloaded files on floppy disks in the user's choice of formats. The database itself is a collection of related files created in dBASE IV structure, which can be linked by a set of parameters. However, no formal computerized interface currently exists to provide automatic linking of these files, although plans for one are in progress. To aid the user with downloaded files, a hard-copy version of a database guide has been prepared so the user will have adequate information on file contents, general terminology, and interfile linkage until a computerized interface becomes available. The guide includes file maps, field definitions and characteristics, linkage maps, and a recent database contents overview and will be sent to each person requesting data.

3. DATA SUMMARY

This report covers eight different batches of four zirconia ceramics, two batches of two silicon carbides, and nine batches of six silicon nitrides. This report also contains the first data to be stored in the database on the mechanical properties of brazed ceramics. M. L. Santella of ORNL initially succeeded in brazing a partially stabilized zirconia to nodular cast iron by coating the zirconia with titanium and the cast iron with copper. Work at Battelle Columbus Laboratories on this same topic yielded a brazing procedure where no copper coating was needed to produce a stable, strong joint. Additional data from Battelle has been requested but has not yet been received.

Much of the bend strength data on zirconias in this report were produced by a study of diesel engine environmental effects on the strength of partially stabilized zirconias. In that study, Nilcra MS-PSZ and TS-PSZ specimens were: (1) exposed to one of the two diesel engine combustion chamber environments for 100 h, (2) aged for 100 h at temperatures ranging from 700 to 800°C, or (3) remained in the as-fabricated condition prior to testing to failure. All specimens were broken in a four-point bend fixture in air at room temperature. Strength comparisons and Weibull plots accompany the data tables for this study, found in Appendix B.

Tracking down background information for a specific batch of a material is a time-consuming, often frustrating, experience that is often necessary to confirm the validity of the data. Keeping assigned batch numbers with the material as it goes through testing frequently appears to be a neglected task. Some of the data in this report include the original batch codes assigned to the materials by the fabricators. When no batch identifier is mentioned, a code is assigned by database personnel based upon the source (report code) and the company, laboratory, or individual who reported the data. It is possible for material with a known batch code to be the same as a material with a locally assigned (by database personnel) batch code if, for example, data for the material were reported

without the original fabricator's code. Unless the unknown-batch-code data are exact duplicates of known-batch-code data, the unknown-batch-code data are assigned a unique identifier to distinguish them from other batches of the same material.

All Weibull analyses shown in this report were performed using the rank regression method, in which a least-squares fit to the data is used to estimate the modulus. Specifically, the data were sorted and the X-Y coordinates, $\ln(\text{MOR strength})$ and $\ln \ln [1/(1-F)]$, were calculated using Microsoft EXCEL™ (version 2.0) on an Apple Macintosh computer. The data were then transferred to Cricket Graph™ (version 1.3.1), where they were plotted with the best-fit line, using Cricket Graph's built-in, curve-fitting routines.

Data tables for this report are organized according to type of data: Appendix A contains available background information on the ceramics presented in this report; Appendix B contains the experimental text data arranged in sections by property type. Some of the test data listed in Appendix B may not be represented by materials in Appendix A but will be included in a later report (if and when such information becomes available). It is the policy for this database to store the available information for future use, whether or not a complete set of information is available on a material. However, complete sets are preferred and sought as time permits.

4. SYSTEM ACCESS

Direct access to the master database is very limited to protect the integrity of the master files. Past experience has shown that major disasters often occur when too many people have direct access to unprotected files at the microcomputer level. Since most users would prefer to have the data in a familiar format, to subset, analyze, and rearrange to suit their needs, this method satisfies both situations; the master files are protected, and the user gets the data in a readily consumable form. While direct access is faster, the

process of downloading across phone lines can be time consuming and hazardous to the integrity of the data being transmitted. This database was designed as a repository, not a full-function analytical tool.

Access to the data is attained by calling the database administrator and requesting all files or just those pertaining to certain materials or test types. The CTP database is a microcomputer-based system of files organized in the dBASE IV structure. Access to the data can be provided by calling the database personnel during working hours (7 a.m. to 3:20 p.m., Eastern time) at 615-574-5113. The information requested by the user (in the user-designated format, including software and disk type) will then be downloaded from the master files, reformatted (if necessary), and sent out to the user as soon as possible. No plans are being considered for direct access from outside systems at this time. Direct transfer is also available by special arrangement but may be time consuming due to the sizes and numbers of files. No guarantee is given for the validity of data transmitted directly because of possible phone line problems. Until a computerized interface becomes available, the *CTP Database User's Guide* will also be sent to all first-time users when the document becomes available.

Several file formats, other than dBASE IV, are available for files downloaded for users. These formats have been categorized as either Apple Macintosh-compatible files (on 3.5-in. floppy disks) or IBM PC-compatible files (on 3.5-in. floppy disks up to 1.44 MB or 5.25-in. floppy disks from 360 KB to 1.44 MB). When requesting information from the database, users should indicate disk size and density as well as file type.

Macintosh file types available are Microsoft EXCEL; SYL; and plain, printable ASCII. IBM file types are Lotus 1-2-3, Microsoft EXCEL, DIF, SDF, SYLK, plain ASCII, delimited ASCII, and dBASE III+. Other formats may be available by special arrangement with database personnel.

With computer diseases becoming so rampant, users should be aware that precautions are taken to ensure that the disks they receive from the database are disease

free. Only new disks are used for transmittals to avoid spreading any computer diseases that might be hiding. No recycled, reformatted disks are sent to users. Both the master system (IBM PC/AT) and the Macintosh IICx are checked regularly for such illnesses, and none have been found so far. Use of both computers is limited to one person who screens incoming software carefully to avoid contamination of either system. No information is downloaded from public bulletin boards to either system. Both systems have virus detection software installed, and all efforts are made to ensure both systems stay disease free. If users have problems with disks received from the database, they should inform database personnel immediately so that steps can be taken to correct the problems.

5. FUTURE PLANS

The sixth database summary report is scheduled for completion in September 1990 and will feature the latest additions of data to the database. Plans are currently being made to write a computerized user interface using the dBASE IV programming language. The interface will link the database's many files together, providing better access to information in the system. This interface will be available to all users of the database who request it.

6. ACKNOWLEDGMENTS

The author thanks M. L. Santella, C. R. Brinkman, M. K. Ferber, and N. L. Hecht for contributing data, Bob Swindeman and Mike Jenkins for reviewing this document, and Kathy Spence for editing and Mary Upton for preparing the final draft for publication.

7. REFERENCES

1. M. K. Booker, "Ceramics Technology for Advanced Heat Engines Project Data Base: A Summary Report," ORNL/M-462, Martin Marietta Energy Systems Inc., Oak Ridge Natl. Lab.
2. B. L. P. Booker, "Ceramics Technology for Advanced Heat Engines Project Data Base: September 1988 Summary Report," ORNL/M-755, Martin Marietta Energy Systems Inc., Oak Ridge Natl. Lab., March 1989.
3. B. L. P. Keyes, "Ceramics Technology for Advanced Heat Engines Project Data Base: March 1989 Summary Report," ORNL/M-1098, Martin Marietta Energy Systems, Inc., Oak Ridge Natl. Lab., April 1990.
4. B. L. P. Keyes, "Ceramics Technology for Advanced Heat Engines Project Database: September 1989 Summary Report," ORNL-M/1286, Martin Marietta Energy Systems, Inc., Oak Ridge Natl. Lab., October 1990.

APPENDIX A. MATERIAL CHARACTERISTICS AND BACKGROUND INFORMATION

SECTION 1. MATERIAL CHARACTERISTICS INFORMATION

SECTION 1. MATERIAL CHARACTERISTICS INFORMATION									
MATERIAL	BATCH CODE	MATERIAL CLASS	FABRICATOR	PRIMARY MATRIX	ADDITIVES	SOURCE			
CVD-SiC*	CVD/UDRI/SA9	SIC	CVD Inc.	Sic		ORNL/TM-10705,p.309			
HEXOLOYS A*	UDRI-SA9	ALPHA SIC	SOHIO Engineered Materials	alpha Sic	B, Al	ORNL/TM-10705,p.285+			
HEXOLOYS A	SOHIO/UDRI/1	ALPHA SIC	SOHIO Engineered Materials	alpha Sic	B, Al	BM11/87, p.70			
CERAMLOY 147-3	CERADYNE/UDRI/2	SIN, ISOPR	Ceradyne	Si3N4	Y2O3,Al2O3				
EC-152	NGK/UDRI/1	SIN, SINT	NGK Spark Plug	Si3N4		BM10/88, p.91			
NT-154	NORTON/UDRI/2	SIN, SINT&HP	Norton/TRW	Si3N4		BM10/88, p.90			
NT-154	NORTON/ORN/1	SIN, SINT&HP	Norton/TRW	Si3N4		BM12/88, p.19			
SN-252	KYOCERA/UDRI/2	SIN, ISOPR	Kyocera	Si3N4	Yb2O3,Y2O3,Al2O3	BM11/87, p.21			
SN-4	HOWMET/UDRI/1	SIN, ISOPR	Howmet	Si3N4	10% Y2O3, Al2O3	BM10/88, p.90			
GTE PY6	GTEL/UDRI/1	SIN, HP	GTE Laboratories	beta Si3N4	6w%Y2O3	BM11/87, p.70			
GTE PY6*	UDRI-SA9	SIN, HP	GTE Laboratories	beta Si3N4	6w%Y2O3	ORNL/TM-10705,p.285+			
TS-PSZ*	NILCRA/UDRI/1	ZRO PSZ	Nilcra Ceramics	ZrO2	3w%MgO	ORNL/TM-10308,p.256			
MS-PSZ*	NILCRA/UDRI/1	ZRO PSZ	Nilcra Ceramics	ZrO2	3w%MgO	ORNL/TM-10308,p.256			
Z-201*	KYO1985/MTL	ZRO PSZ	Kyocera	ZrO2	Y2O3	ORNL/TM-10308,p.217			
MATERIAL	BATCH CODE	DENSITY g/cm^3	MOE GPa	HARDNESS TEST	HARDNESS VALUE	THERMAL EXPANSION COEFFICIENT 1.E-06/°C	POISSONS RATIO	KIC MPa√m	
CVD-SiC*	CVD/UDRI/SA9		470.0	VICKERS	2600 kg/mm2		0.230	2.600	
HEXOLOYS A*	UDRI-SA9	3.17	300.0	VICKERS	2740 kg/mm2	4.500		4.000	
HEXOLOYS A	SOHIO/UDRI/2	3.17	427.0	VICKERS	2539 kg/mm2	5.400		2.000	
CERAMLOY 147-3	CERADYNE/UDRI/2								
EC-152	NGK/UDRI/2	3.23							
NT-154	NORTON/UDRI/2								
NT-154	NORTON/ORN/1		310.5						
SN-252	KYOCERA/UDRI/2								
SN-4	HOWMET/UDRI/2	3.23	204.0						
GTE PY6	GTEL/UDRI/2	3.24	293.0	VICKERS	1458kg/mm2	3.400		3.000	
GTE PY6*	UDRI-SA9	3.24	267.0			3.500		4.250	
TS-PSZ*	NILCRA/UDRI/1	5.78		VICKERS	1025 kg/mm2	9.500		6.000	
MS-PSZ*	NILCRA/UDRI/1	5.69		VICKERS	1099 kg/mm2	10.300		7.600	
Z-201*	KYO1985/MTL	5.85	201.0	745.0 KNOOP.3kg	10.5 kg/mm2			8.800	

* These data included, although from a different batch, for guidance purposes only.

SECTION 2. GENERAL TEXT INFORMATION ON MATERIALS IN THIS REPORT

SECTION 2. GENERAL TEST INFORMATION IN FIRST 5 CH.					
MATERIAL	BATCH CODE	REFERENCE CODE	CATEGORY	SEQ	TEXT
SILICON CARBIDES					
CVD SiC	CVD/UDRI/2	UDRI PKG NOV 89	PROCESS	A	SiC prepared by chemical vapor deposition techniques.
HEXOLOYS A	SOHIO/UDRI/2	UDRI PKG NOV 89	PROCESS	A	Cold formed (injection molded or isostatic pressed) and pressurelessly sintered
				B	alpha-silicon carbide with additions of B and Al.
SILICON NITRIDES					
CERALLOY 147-3	CERADYNE/UDRI/2	UDRI PKG NOV 89	PROCESS	A B	Cold formed (isopressing/slip casting/injection molding) sintered Si3N4 with additions of Y2O3 and Al2O3.
EC-152	NGK/UDRI/2	UDRI PKG NOV 89	PROCESS	A	Gas pressure sintered Si3N4 with additions of Al2O3 and Y2O3.
GTE PY6	GTEL/UDRI/2	UDRI PKG NOV 89	PROCESS	A	Injection molded and HIP'ed beta silicon nitride with additions of Y2O3.
NT-154	NORTON/UDRI/2	UDRI PKG NOV 89	PROCESS	A	Sintered and HIP'ed Si3N4.
SN-4	HOWMET/UDRI/2	UDRI PKG NOV 89	PROCESS	A B	Cold formed (die pressing/isostatic pressing) sintered and HIP'ed Si3N4 with 10% oxide sintering aids (Al2O3 and Y2O3).
SN-252	KYOCERA/UDRI/2	UDRI PKG NOV 89	PROCESS	A B C	Cold formed (isopressed/slip cast/etc.) and sintered Si3N4 with additions of Yb2O3, Y2O3, and Al2O3 (Note: the sintering process is controlled to promote the growth of a beta Si3N4 whisker phase in the Si3N4 matrix).

SECTION 3. DENSITIES

MATERIAL	BATCH CODE	REFERENCE CODE	PROCESS	SPECIMEN NUMBER	TEMP °C	DENSITY g/cm ³
SILICON CARBIDES						
HEXOLOY SA	SOHIO/UDRI/2	UDRIPKGN0V89	IMMERSION METHOD	16	21	3.1600
HEXOLOY SA	SOHIO/UDRI/2	UDRIPKGN0V89	IMMERSION METHOD	17	21	3.1500
HEXOLOY SA	SOHIO/UDRI/2	UDRIPKGN0V89	IMMERSION METHOD	18	21	3.1400
HEXOLOY SA	SOHIO/UDRI/2	UDRIPKGN0V89	IMMERSION METHOD	19	21	3.1600
HEXOLOY SA	SOHIO/UDRI/2	UDRIPKGN0V89	IMMERSION METHOD	20	21	3.1500
SILICON NITRIDES						
GTE PY6	GTEL/UDRI/2	UDRIPKGN0V89	IMMERSION METHOD	6	21	3.2600
GTE PY6	GTEL/UDRI/2	UDRIPKGN0V89	IMMERSION METHOD	7	21	3.2700
GTE PY6	GTEL/UDRI/2	UDRIPKGN0V89	IMMERSION METHOD	8	21	3.2700
GTE PY6	GTEL/UDRI/2	UDRIPKGN0V89	IMMERSION METHOD	9	21	3.2700
GTE PY6	GTEL/UDRI/2	UDRIPKGN0V89	IMMERSION METHOD	10	21	3.2700
NT-154	NORTON/UDRI/2	UDRIPKGN0V89	IMMERSION METHOD	96	21	3.2300
NT-154	NORTON/UDRI/2	UDRIPKGN0V89	IMMERSION METHOD	97	21	3.2300
NT-154	NORTON/UDRI/2	UDRIPKGN0V89	IMMERSION METHOD	98	21	3.2300
NT-154	NORTON/UDRI/2	UDRIPKGN0V89	IMMERSION METHOD	99	21	3.2300
NT-154	NORTON/UDRI/2	UDRIPKGN0V89	IMMERSION METHOD	100	21	3.2400
SN-4	HOWMET/UDRI/2	UDRIPKGN0V89	IMMERSION METHOD	8	21	3.2300
SN-4	HOWMET/UDRI/2	UDRIPKGN0V89	IMMERSION METHOD	17	21	3.2300
SN-4	HOWMET/UDRI/2	UDRIPKGN0V89	IMMERSION METHOD	20	21	3.2300

SECTION 4. HARDNESS MEASUREMENTS

MATERIAL	BATCH CODE	REFERENCE CODE	HARDNESS TEST	SPECIMEN NUMBER	LOAD g	INDENT DEPTH μm	UNITS	HARDNESS VALUE
HEXOLOY SA	SOHIO/UDRI/2	UDRIPKGN0V89	VICKERS	21	500.0	22.3	kg/mm	1865.0
HEXOLOY SA	SOHIO/UDRI/2	UDRIPKGN0V89	VICKERS	21	500.0	18.9	kg/mm	2596.0
HEXOLOY SA	SOHIO/UDRI/2	UDRIPKGN0V89	VICKERS	21	500.0	19.0	kg/mm	2568.0
HEXOLOY SA	SOHIO/UDRI/2	UDRIPKGN0V89	VICKERS	21	500.0	18.4	kg/mm	2739.0
HEXOLOY SA	SOHIO/UDRI/2	UDRIPKGN0V89	VICKERS	21	500.0	18.0	kg/mm	2862.0
HEXOLOY SA	SOHIO/UDRI/2	UDRIPKGN0V89	VICKERS	22	500.0	17.9	kg/mm	2894.0
HEXOLOY SA	SOHIO/UDRI/2	UDRIPKGN0V89	VICKERS	22	500.0	18.5	kg/mm	2709.0
HEXOLOY SA	SOHIO/UDRI/2	UDRIPKGN0V89	VICKERS	22	500.0	17.6	kg/mm	2993.0
HEXOLOY SA	SOHIO/UDRI/2	UDRIPKGN0V89	VICKERS	22	500.0	18.3	kg/mm	2769.0
HEXOLOY SA	SOHIO/UDRI/2	UDRIPKGN0V89	VICKERS	22	500.0	20.0	kg/mm	2318.0
HEXOLOY SA	SOHIO/UDRI/2	UDRIPKGN0V89	VICKERS	23	500.0	17.6	kg/mm	2993.0
HEXOLOY SA	SOHIO/UDRI/2	UDRIPKGN0V89	VICKERS	23	500.0	19.3	kg/mm	2489.0
HEXOLOY SA	SOHIO/UDRI/2	UDRIPKGN0V89	VICKERS	23	500.0	17.9	kg/mm	2894.0
HEXOLOY SA	SOHIO/UDRI/2	UDRIPKGN0V89	VICKERS	23	500.0	19.7	kg/mm	2389.0
HEXOLOY SA	SOHIO/UDRI/2	UDRIPKGN0V89	VICKERS	23	500.0	19.3	kg/mm	2489.0
HEXOLOY SA	SOHIO/UDRI/2	UDRIPKGN0V89	VICKERS	24	500.0	17.8	kg/mm	2926.0
HEXOLOY SA	SOHIO/UDRI/2	UDRIPKGN0V89	VICKERS	24	500.0	17.5	kg/mm	3028.0
HEXOLOY SA	SOHIO/UDRI/2	UDRIPKGN0V89	VICKERS	24	500.0	17.9	kg/mm	2894.0
HEXOLOY SA	SOHIO/UDRI/2	UDRIPKGN0V89	VICKERS	24	500.0	19.0	kg/mm	2568.0
HEXOLOY SA	SOHIO/UDRI/2	UDRIPKGN0V89	VICKERS	24	500.0	18.5	kg/mm	2709.0
HEXOLOY SA	SOHIO/UDRI/2	UDRIPKGN0V89	VICKERS	25	500.0	17.2	kg/mm	3134.0
HEXOLOY SA	SOHIO/UDRI/2	UDRIPKGN0V89	VICKERS	25	500.0	18.1	kg/mm	2830.0
HEXOLOY SA	SOHIO/UDRI/2	UDRIPKGN0V89	VICKERS	25	500.0	18.6	kg/mm	2680.0
HEXOLOY SA	SOHIO/UDRI/2	UDRIPKGN0V89	VICKERS	25	500.0	17.5	kg/mm	3028.0
HEXOLOY SA	SOHIO/UDRI/2	UDRIPKGN0V89	VICKERS	25	500.0	18.2	kg/mm	2799.0
GTE PY6	GTEL/UDRI/2	UDRIPKGN0V89	VICKERS	61	300.0	19.7	kg/mm	1433.0
GTE PY6	GTEL/UDRI/2	UDRIPKGN0V89	VICKERS	61	300.0	20.0	kg/mm	1391.0
GTE PY6	GTEL/UDRI/2	UDRIPKGN0V89	VICKERS	61	300.0	19.4	kg/mm	1476.0
GTE PY6	GTEL/UDRI/2	UDRIPKGN0V89	VICKERS	61	300.0	19.1	kg/mm	1525.0
GTE PY6	GTEL/UDRI/2	UDRIPKGN0V89	VICKERS	61	300.0	19.7	kg/mm	1433.0
GTE PY6	GTEL/UDRI/2	UDRIPKGN0V89	VICKERS	62	300.0	18.3	kg/mm	1661.0
GTE PY6	GTEL/UDRI/2	UDRIPKGN0V89	VICKERS	62	300.0	19.2	kg/mm	1509.0
GTE PY6	GTEL/UDRI/2	UDRIPKGN0V89	VICKERS	62	300.0	18.9	kg/mm	1557.0

[illegible]

SECTION 4. HARDNESS MEASUREMENTS, CONTINUED

MATERIAL	BATCH CODE	REFERENCE CODE	HARDNESS TEST	SPECIMEN NUMBER	LOAD g	INDENT DEPTH μm	UNITS	HARDNESS VALUE
NT-154	NORTON/UDRI/2	UDRIPKGNOV89	VICKERS	32	500.0	23.4	kg/mm	1693.0
NT-154	NORTON/UDRI/2	UDRIPKGNOV89	VICKERS	32	500.0	23.6	kg/mm	1665.0
NT-154	NORTON/UDRI/2	UDRIPKGNOV89	VICKERS	32	500.0	24.3	kg/mm	1570.0
NT-154	NORTON/UDRI/2	UDRIPKGNOV89	VICKERS	33	500.0	23.4	kg/mm	1693.0
NT-154	NORTON/UDRI/2	UDRIPKGNOV89	VICKERS	33	500.0	24.5	kg/mm	1545.0
NT-154	NORTON/UDRI/2	UDRIPKGNOV89	VICKERS	33	500.0	24.3	kg/mm	1570.0
NT-154	NORTON/UDRI/2	UDRIPKGNOV89	VICKERS	33	500.0	24.1	kg/mm	1596.0
NT-154	NORTON/UDRI/2	UDRIPKGNOV89	VICKERS	33	500.0	23.3	kg/mm	1708.0
NT-154	NORTON/UDRI/2	UDRIPKGNOV89	VICKERS	34	500.0	23.5	kg/mm	1679.0
NT-154	NORTON/UDRI/2	UDRIPKGNOV89	VICKERS	34	500.0	24.0	kg/mm	1610.0
NT-154	NORTON/UDRI/2	UDRIPKGNOV89	VICKERS	34	500.0	24.5	kg/mm	1579.0
NT-154	NORTON/UDRI/2	UDRIPKGNOV89	VICKERS	34	500.0	23.5	kg/mm	1679.0
NT-154	NORTON/UDRI/2	UDRIPKGNOV89	VICKERS	34	500.0	24.2	kg/mm	1583.0
NT-154	NORTON/UDRI/2	UDRIPKGNOV89	VICKERS	35	500.0	24.2	kg/mm	1583.0
NT-154	NORTON/UDRI/2	UDRIPKGNOV89	VICKERS	35	500.0	24.0	kg/mm	1610.0
NT-154	NORTON/UDRI/2	UDRIPKGNOV89	VICKERS	35	500.0	23.5	kg/mm	1679.0
NT-154	NORTON/UDRI/2	UDRIPKGNOV89	VICKERS	35	500.0	23.5	kg/mm	1679.0
NT-154	NORTON/UDRI/2	UDRIPKGNOV89	VICKERS	35	500.0	24.7	kg/mm	1520.0
SN-252	KYOCERA/UDRI/2	UDRIPKGNOV89	VICKERS	12	300.0	20.8	kg/mm	1286.0
SN-252	KYOCERA/UDRI/2	UDRIPKGNOV89	VICKERS	12	300.0	17.5	kg/mm	1817.0
SN-252	KYOCERA/UDRI/2	UDRIPKGNOV89	VICKERS	12	300.0	19.9	kg/mm	1405.0
SN-252	KYOCERA/UDRI/2	UDRIPKGNOV89	VICKERS	12	300.0	19.0	kg/mm	1541.0
SN-252	KYOCERA/UDRI/2	UDRIPKGNOV89	VICKERS	16	300.0	19.6	kg/mm	1448.0
SN-252	KYOCERA/UDRI/2	UDRIPKGNOV89	VICKERS	16	300.0	19.2	kg/mm	1509.0
SN-252	KYOCERA/UDRI/2	UDRIPKGNOV89	VICKERS	16	300.0	18.7	kg/mm	1591.0
SN-252	KYOCERA/UDRI/2	UDRIPKGNOV89	VICKERS	16	300.0	19.8	kg/mm	1419.0
SN-252	KYOCERA/UDRI/2	UDRIPKGNOV89	VICKERS	16	300.0	19.5	kg/mm	1463.0
SN-252	KYOCERA/UDRI/2	UDRIPKGNOV89	VICKERS	18	300.0	19.5	kg/mm	1463.0
SN-252	KYOCERA/UDRI/2	UDRIPKGNOV89	VICKERS	18	300.0	19.0	kg/mm	1541.0
SN-252	KYOCERA/UDRI/2	UDRIPKGNOV89	VICKERS	18	300.0	18.7	kg/mm	1591.0
SN-252	KYOCERA/UDRI/2	UDRIPKGNOV89	VICKERS	18	300.0	19.3	kg/mm	1494.0
SN-252	KYOCERA/UDRI/2	UDRIPKGNOV89	VICKERS	18	300.0	20.0	kg/mm	1391.0
SN-252	KYOCERA/UDRI/2	UDRIPKGNOV89	VICKERS	19	300.0	18.5	kg/mm	1625.0

SECTION 4. HARDNESS MEASUREMENTS, CONTINUED

MATERIAL	BATCH CODE	REFERENCE CODE	HARDNESS TEST	SPECIMEN NUMBER	LOAD g	INDENT DEPTH μm	UNITS	HARDNESS VALUE
SN-252	KYOCERA/UDRI/2	UDRI PKGNV89	VICKERS	19	300.0	18.5	kg/mm	1625.0
SN-252	KYOCERA/UDRI/2	UDRI PKGNV89	VICKERS	19	300.0	19.5	kg/mm	1463.0
SN-252	KYOCERA/UDRI/2	UDRI PKGNV89	VICKERS	19	300.0	18.5	kg/mm	1625.0
SN-252	KYOCERA/UDRI/2	UDRI PKGNV89	VICKERS	19	300.0	19.0	kg/mm	1541.0
SN-252	KYOCERA/UDRI/2	UDRI PKGNV89	VICKERS	20	300.0	19.0	kg/mm	1541.0
SN-252	KYOCERA/UDRI/2	UDRI PKGNV89	VICKERS	20	300.0	19.0	kg/mm	1541.0
SN-252	KYOCERA/UDRI/2	UDRI PKGNV89	VICKERS	20	300.0	19.0	kg/mm	1541.0
SN-252	KYOCERA/UDRI/2	UDRI PKGNV89	VICKERS	20	300.0	17.5	kg/mm	1817.0
SN-252	KYOCERA/UDRI/2	UDRI PKGNV89	VICKERS	20	300.0	18.6	kg/mm	1608.0
SN-4	HOWMET/UDRI/2	UDRI PKGNV89	VICKERS	1	200.0	14.5	kg/mm	1764.0
SN-4	HOWMET/UDRI/2	UDRI PKGNV89	VICKERS	1	200.0	15.2	kg/mm	1605.0
SN-4	HOWMET/UDRI/2	UDRI PKGNV89	VICKERS	1	200.0	14.2	kg/mm	1839.0
SN-4	HOWMET/UDRI/2	UDRI PKGNV89	VICKERS	1	200.0	16.5	kg/mm	1362.0
SN-4	HOWMET/UDRI/2	UDRI PKGNV89	VICKERS	1	200.0	14.0	kg/mm	1892.0
SN-4	HOWMET/UDRI/2	UDRI PKGNV89	VICKERS	2	200.0	15.1	kg/mm	1627.0
SN-4	HOWMET/UDRI/2	UDRI PKGNV89	VICKERS	2	200.0	14.9	kg/mm	1671.0
SN-4	HOWMET/UDRI/2	UDRI PKGNV89	VICKERS	2	200.0	16.1	kg/mm	1431.0
SN-4	HOWMET/UDRI/2	UDRI PKGNV89	VICKERS	2	200.0	15.3	kg/mm	1584.0
SN-4	HOWMET/UDRI/2	UDRI PKGNV89	VICKERS	2	200.0	15.8	kg/mm	1486.0
SN-4	HOWMET/UDRI/2	UDRI PKGNV89	VICKERS	3	200.0	15.5	kg/mm	1544.0
SN-4	HOWMET/UDRI/2	UDRI PKGNV89	VICKERS	3	200.0	14.4	kg/mm	1789.0
SN-4	HOWMET/UDRI/2	UDRI PKGNV89	VICKERS	3	200.0	15.3	kg/mm	1584.0
SN-4	HOWMET/UDRI/2	UDRI PKGNV89	VICKERS	3	200.0	15.9	kg/mm	1467.0
SN-4	HOWMET/UDRI/2	UDRI PKGNV89	VICKERS	3	200.0	15.0	kg/mm	1648.0
SN-4	HOWMET/UDRI/2	UDRI PKGNV89	VICKERS	4	200.0	15.7	kg/mm	1505.0
SN-4	HOWMET/UDRI/2	UDRI PKGNV89	VICKERS	4	200.0	16.5	kg/mm	1362.0
SN-4	HOWMET/UDRI/2	UDRI PKGNV89	VICKERS	4	200.0	15.0	kg/mm	1648.0
SN-4	HOWMET/UDRI/2	UDRI PKGNV89	VICKERS	4	200.0	15.7	kg/mm	1505.0
SN-4	HOWMET/UDRI/2	UDRI PKGNV89	VICKERS	4	200.0	15.0	kg/mm	1648.0
SN-4	HOWMET/UDRI/2	UDRI PKGNV89	VICKERS	5	200.0	15.1	kg/mm	1627.0
SN-4	HOWMET/UDRI/2	UDRI PKGNV89	VICKERS	5	200.0	14.8	kg/mm	1693.0
SN-4	HOWMET/UDRI/2	UDRI PKGNV89	VICKERS	5	200.0	15.8	kg/mm	1486.0
SN-4	HOWMET/UDRI/2	UDRI PKGNV89	VICKERS	5	200.0	15.0	kg/mm	1648.0

APPENDIX B. TEST RESULTS

Figure 1.1 Average density at room temperature comparison among three silicon nitrides and one silicon carbide, all tested at UDRI.

Figure 1.2 Average hardnesses for three silicon nitrides and one silicon carbide tested at UDRI. Vickers test was used with the loads indicated in grams over the bars.

SECTION 1. TEST BACKGROUND INFORMATION FOR NON-BRAZED SPECIMEN TESTS

REFERENCE		TEST		SEQ		TEST BACKGROUND INFORMATION	
CODE		TYPE					
ORNL-5612	MOR4PTB			A	This report continues the work reported under REF_CODE ORNL-6513. The same 2		
				B	diesel engines were used to expose the specimens to the combustion environment,		
				C	with access through the unused glow plug port, adjacent to the fuel injector.		
				D	The 2-cylinder engine was new prior to these exposures, running at a nominal		
				E	constant speed of 1800-1900 rpm and a load of 41-43Nm torque. Fuel consumption		
				F	was about 213 g/kWh. The 1-cylinder engine was run at similar conditions at		
				G	half the load and fuel consumption. Exposure times for both engines was 100 hrs,		
				H	which was accumulated over several weeks of running several hours each day.		
				I	The single cylinder engine had been used for other purposes prior to these		
				J	experiments and had aged to the point that the fuel injector was wetting the		
				K	surfaces of the specimens, resulting in high thermal stresses, often leading to		
				L	failure within the engine. Two specimens were gripped side-by-side separated by a		
				M	shim and inserted through the glow plug port. Only 40-41mm of each specimen was		
				N	exposed. Two fuel mixtures were used: d-2 is Philips D-2 diesel, the reference		
				O	fuel; d-2b was a mixture of 50% Philips D-2 and 50%aromatic blend (53.5wt%		
				P	Phillips Light Cycle Oil and 46.5wt% Exxon heavy aromatic naptha targeted for		
				Q	lower cetane number/lower hydrogen content. After exposure, the specimens were		
				R	broken in air at room temperature using a conventional 4 point bend fixture. The		
				S	MOR bars were 50 x 4.5 x 3.5mm with chamfered edges, polished longitudinally to		
				T	.25 micrometers.		
SA12ORN1469	MOR4PTB			A	About 40mm of one end of the specimens were exposed for 100h to discontinuous		
				B	combustion conditions of a Deutz F1L511W diesel engine burning 50% D-2 diesel		
				C	fuel and 50% aromatic blend (53.5% Philips light Cycle Oil (LCO), 46.5% Exxon		
				D	heavy aromatic Naptha (HAN)). The engine was 2 cylinder indirect injection and		
				E	air-cooled. Specimen geometry for MOR bars was 50mm x 4.5mm x 3.5mm. All		
				F	specimens were broken in air at room temperature. The test rig outer span was		
				G	40mm, inner span was 20mm. Specimens were polished longitudinal to .25 micro-		
				H	meters, with average grain size of 30 to 50 um. Original product forms were		
				I	rectangular plates, 101.6mm x 101.6mm x 6.35 mm. These conditions apply for both		
				J	TS-PSZ and MS-PSZ materials for the diesel study. Work performed at ORNL by		
				K	C.R. Brinkman and K. C. Liu.		

SECTION 1. TEST BACKGROUND INFORMATION FOR NON-BRAZED SPECIMEN TESTS

TEST BACKGROUND INFORMATION

REFERENCE CODE	TEST TYPE	SEQ
UDRIPKGNV89	MOR4PTB	A
		B
		C
		D
		E
		F
		G
		H
UDRIPKGNV89	FRACTUJFF	A
		B
		C
UDRIPKGNV89	HARDNESS	A
		B
		C
UDRIPKGNV89	MDE	A
		B
UDRIPKGNV89	TENSILE	A
		B
		C
		D
		E
UDRIPKGNV89	THERMEXP	A
		B

Bend tests were made using 2 Instron Universal Testing Machines (Model 1123) following MIL-STD-1942(MR). High temperature measurements were conducted in 2 ATS #3320 high-temperature furnaces. Test specimens were 3mmx4mmx50mm with the tensile surface ground and polished to 16 microinch finish (MIL-STD-1942(MR)), size B). Long edges were rounded and polished to minimize edge failures. The 4-point bend tests had outer spans of 40mm, inner spans of 20mm. Bend fixtures for room temperature tests were made from steel. For higher temps, the fixtures were made of SiC. Data submitted by Norman Hecht, UDRI, November, 1989.

Fracture toughness was measured using both controlled flaw and microindent methods. An indent load of 2000 grams was used in both methods. Data submitted by Norman Hecht, UDRI, November, 1989.

Hardness measured by Vicker's microindent hardness tester. Fracture origins were determined by optical microscopy and SEM (JEOL/SM-80 with EG&G Ortec System 5000 Microanalysis System). Data submitted by Norman Hecht, UDRI, November, 1989.

The elastic modulus was measured by a Grindo-Sonic (Model MR35T) Transient Impulse/Elastic Modulus Apparatus. Data from Norman Hecht, UDRI, November, 1989.

Tensile strength measurements were made using an Instron Electro-Mechanical Test System (Model 1361) equipped with Instron "sure-grip" universal coupling and water-cooled holders for high-temp tensile testing. An Instron high-temperature short furnace was used for high temperature measurements. Data submitted by Norman L. Hecht, The University of Dayton Research Institute in November, 1989.

Thermal expansion was measured from 25°-1400°C using a Theta Industries Dilatronic II-Model 6024. Data submitted by Norman Hecht, UDRI, November, 1989.

SECTION 2. CYCLIC FATIGUE TEST RESULTS

MATERIAL	BATCH CODE	REFERENCE CODE	TEST ENVIRN.	SPECIMEN NUMBER	TEMP °C	STRESS MPa	CYCLES AT STRESS	CYCLES TO FAILURE	COMMENTS
SILICON NITRIDE									
NT-154	NORTONVORN/CIP	BM689ORN/27	AIR	CP-21	1300	338	1024490		STEP 1
						358	233240		STEP 2
						372	191000		STEP 3
						388	44383	1493113	STEP 4, FAIL
NT-154	NORTONVORN/CIP	BM689ORN/27	AIR	CP-24	1370	207	467600		STEP 1
						220	216200		STEP 2
						243	131766	815566	STEP 3, FAIL
NT-154	NORTONVORN/CIP	BM689ORN/27	AIR	CP-19	1200	475	270		270
NT-154	NORTONVORN/CIP	BM689ORN/27	AIR	CP-20	1200	449	8605		8605
NT-154	NORTONVORN/CIP	BM689ORN/27	AIR	CP-22	1300	388	278		278
NT-154	NORTONVORN/CIP	BM689ORN/27	AIR	CP-23	1300	361	762		762
NT-154	NORTONVORN/CIP	BM689ORN/27	AIR	CP-26	1300	234	2349		2349
NT-154	NORTONVORN/CIP	BM689ORN/27	AIR	CP-27	1370	212	51		51
NT-154	NORTONVORN/CIP	BM689ORN/27	AIR	CP-29	1370	212	238		238
ZIRCONIA									
MS-PSZ	NILCRA/ORN/2-KCL	SA11ORN/306	AIR	40	400	238	1103		1103
MS-PSZ	NILCRA/ORN/2-KCL	SA11ORN/306	AIR	34	1000	140	45100		STEP 1
						154	44850		STEP 2
						168	43938		STEP 3
						183	96657	230545	STEP 4, FAIL
MS-PSZ	NILCRA/ORN/2-KCL	SA11ORN/306	AIR	35	1000	161	46600		STEP 1
						175	42400		STEP 2
						188	89735	178735	STEP 3, FAIL

SECTION 3. FRACTURE TOUGHNESS TEST RESULTS

MATERIAL	BATCH CODE	REFERENCE CODE	TEST ENVIRON.	SPECIMEN NUMBER	TEST TYPE	TEMP °C	LOAD N	KIC MPa√m	CRACK LENGTH μm	X-HEAD SPEED mm/sec	SPECIMEN GEOMETRY
SILICON CARBIDES											
HEXOLOYS A	SOHIO/UDRI/2	UDRIPKGNV89	AIR	21	CONTROLLED FLAW	21	97.90	1.500	57.900	0.0200	4.0030x2.9794mm
HEXOLOYS A	SOHIO/UDRI/2	UDRIPKGNV89	AIR	22	CONTROLLED FLAW	21	93.40	1.400	63.300	0.0200	3.9853x2.9972mm
HEXOLOYS A	SOHIO/UDRI/2	UDRIPKGNV89	AIR	23	CONTROLLED FLAW	21	97.00	1.400	53.000	0.0200	3.9980x2.9616mm
HEXOLOYS A	SOHIO/UDRI/2	UDRIPKGNV89	AIR	24	CONTROLLED FLAW	21	93.90	1.500	64.900	0.0200	3.9929x2.9921mm
HEXOLOYS A	SOHIO/UDRI/2	UDRIPKGNV89	AIR	25	CONTROLLED FLAW	21	95.20	1.400	59.900	0.0200	3.9903x2.9896mm
HEXOLOYS A	SOHIO/UDRI/2	UDRIPKGNV89	AIR	26	CONTROLLED FLAW	21	96.10	1.500	63.600	0.0200	4.0030x2.9896mm
HEXOLOYS A	SOHIO/UDRI/2	UDRIPKGNV89	AIR	27	CONTROLLED FLAW	21	103.20	1.500	53.500	0.0200	3.9954x2.9769mm
HEXOLOYS A	SOHIO/UDRI/2	UDRIPKGNV89	AIR	28	CONTROLLED FLAW	21	95.60	1.400	55.500	0.0200	4.0005x2.9642mm
HEXOLOYS A	SOHIO/UDRI/2	UDRIPKGNV89	AIR	29	CONTROLLED FLAW	21	95.60	1.400	59.300	0.0200	3.9980x2.9870mm
HEXOLOYS A	SOHIO/UDRI/2	UDRIPKGNV89	AIR	30	CONTROLLED FLAW	21	105.40	1.600	62.300	0.0200	4.0056x2.9845mm
HEXOLOYS A	SOHIO/UDRI/2	UDRIPKGNV89	AIR	151	CONTROLLED FLAW	1400	200.60	3.300	68.800	0.0200	4.0005x2.9439mm
HEXOLOYS A	SOHIO/UDRI/2	UDRIPKGNV89	AIR	152	CONTROLLED FLAW	1400	215.70	3.100	52.500	0.0200	4.0056x2.9820mm
HEXOLOYS A	SOHIO/UDRI/2	UDRIPKGNV89	AIR	154	CONTROLLED FLAW	1400	159.70	2.600	67.500	0.0200	4.0030x2.9870mm
HEXOLOYS A	SOHIO/UDRI/2	UDRIPKGNV89	AIR	155	CONTROLLED FLAW	1400	204.60	3.500	76.300	0.0200	3.9954x2.9693mm
HEXOLOYS A	SOHIO/UDRI/2	UDRIPKGNV89	AIR	156	CONTROLLED FLAW	1400	177.90	3.000	75.000	0.0200	3.9954x2.9743mm
HEXOLOYS A	SOHIO/UDRI/2	UDRIPKGNV89	AIR	157	CONTROLLED FLAW	1400	166.40	2.900	78.100	0.0200	4.0005x2.9921mm
HEXOLOYS A	SOHIO/UDRI/2	UDRIPKGNV89	AIR	158	CONTROLLED FLAW	1400	185.00	3.000	68.800	0.0200	4.0056x2.9693mm
HEXOLOYS A	SOHIO/UDRI/2	UDRIPKGNV89	AIR	159	CONTROLLED FLAW	1400	169.90	2.800	69.400	0.0200	4.0030x2.9667mm
HEXOLOYS A	SOHIO/UDRI/2	UDRIPKGNV89	AIR	160	CONTROLLED FLAW	1400	215.30	3.600	72.500	0.0200	3.9853x2.9769mm
SILICON NITRIDES											
GTE PY6	GTEL/UDRI/2	UDRIPKGNV89	AIR	61	CONTROLLED FLAW	21	250.90	3.600	52.500	0.0200	3.9954x2.9566mm
GTE PY6	GTEL/UDRI/2	UDRIPKGNV89	AIR	62	CONTROLLED FLAW	21	209.50	2.900	46.300	0.0200	3.9980x2.9489mm
GTE PY6	GTEL/UDRI/2	UDRIPKGNV89	AIR	63	CONTROLLED FLAW	21	254.00	3.700	51.300	0.0200	3.9853x2.9388mm
GTE PY6	GTEL/UDRI/2	UDRIPKGNV89	AIR	64	CONTROLLED FLAW	21	240.20	3.300	48.800	0.0200	3.9903x2.9616mm
GTE PY6	GTEL/UDRI/2	UDRIPKGNV89	AIR	65	CONTROLLED FLAW	21	235.70	3.100	42.500	0.0200	3.9903x2.9591mm
GTE PY6	GTEL/UDRI/2	UDRIPKGNV89	AIR	66	CONTROLLED FLAW	21	250.00	3.400	43.800	0.0200	4.0005x2.9312mm
GTE PY6	GTEL/UDRI/2	UDRIPKGNV89	AIR	67	CONTROLLED FLAW	21	248.20	3.200	43.800	0.0200	4.0030x2.9693mm
GTE PY6	GTEL/UDRI/2	UDRIPKGNV89	AIR	68	CONTROLLED FLAW	21	253.50	3.200	38.800	0.0200	4.0030x2.9439mm
GTE PY6	GTEL/UDRI/2	UDRIPKGNV89	AIR	69	CONTROLLED FLAW	21	258.00	2.900	32.500	0.0200	4.0056x2.9489mm
GTE PY6	GTEL/UDRI/2	UDRIPKGNV89	AIR	70	CONTROLLED FLAW	21	259.80	3.100	35.000	0.0200	3.9980x2.9464mm
NT-154	NORTON/UDRI/2	UDRIPKGNV89	AIR	31	CONTROLLED FLAW	21	201.50	2.700	45.000	0.0200	3.9827x2.9388mm
NT-154	NORTON/UDRI/2	UDRIPKGNV89	AIR	32	CONTROLLED FLAW	21	217.50	3.200	51.300	0.0200	3.9954x2.9210mm
NT-154	NORTON/UDRI/2	UDRIPKGNV89	AIR	33	CONTROLLED FLAW	21	227.30	3.100	46.300	0.0200	3.9903x2.9439mm
NT-154	NORTON/UDRI/2	UDRIPKGNV89	AIR	34	CONTROLLED FLAW	21	208.60	3.200	56.300	0.0200	3.9853x2.9413mm
NT-154	NORTON/UDRI/2	UDRIPKGNV89	AIR	35	CONTROLLED FLAW	21	223.70	3.100	48.800	0.0200	3.9903x2.9489mm
NT-154	NORTON/UDRI/2	UDRIPKGNV89	AIR	36	CONTROLLED FLAW	21	216.20	3.200	52.500	0.0200	3.9878x2.9464mm
NT-154	NORTON/UDRI/2	UDRIPKGNV89	AIR	37	CONTROLLED FLAW	21	229.50	3.400	53.800	0.0200	4.0005x2.9515mm
NT-154	NORTON/UDRI/2	UDRIPKGNV89	AIR	38	CONTROLLED FLAW	21	224.60	3.100	46.300	0.0200	3.9980x2.9489mm

SECTION 3. FRACTURE TOUGHNESS TEST RESULTS, CONTINUED

MATERIAL	BATCH CODE	REFERENCE CODE	TEST ENVIRON.	SPECIMEN NUMBER	TEST TYPE	TEMP °C	LOAD N	KIC MPa√m	CRACK LENGTH μm	X-HEAD SPEED mm/sec	SPECIMEN GEOMETRY
NT-154	NORTON/UDRI/2	UDRIKGNV89	AIR	39	CONTROLLED FLAW	21	227.70	3.400	53.800	0.0200	4.0030x2.9464mm
NT-154	NORTON/UDRI/2	UDRIKGNV89	AIR	40	CONTROLLED FLAW	21	225.50	3.200	51.300	0.0200	3.9980x2.9489mm
NT-154	NORTON/UDRI/2	UDRIKGNV89	AIR	51	CONTROLLED FLAW	1400	287.80	3.500	37.500	0.0200	4.0030x2.9794mm
NT-154	NORTON/UDRI/2	UDRIKGNV89	AIR	52	CONTROLLED FLAW	1400	297.10	3.900	41.300	0.0200	4.0056x2.9159mm
NT-154	NORTON/UDRI/2	UDRIKGNV89	AIR	53	CONTROLLED FLAW	1400	271.80	3.100	32.500	0.0200	4.0056x2.9464mm
NT-154	NORTON/UDRI/2	UDRIKGNV89	AIR	54	CONTROLLED FLAW	1400	298.00	4.200	48.800	0.0200	4.0005x2.9464mm
NT-154	NORTON/UDRI/2	UDRIKGNV89	AIR	56	CONTROLLED FLAW	1400	259.80	3.500	45.000	0.0200	4.0056x2.9489mm
NT-154	NORTON/UDRI/2	UDRIKGNV89	AIR	57	CONTROLLED FLAW	1400	278.00	3.500	37.500	0.0200	4.0081x2.9286mm
NT-154	NORTON/UDRI/2	UDRIKGNV89	AIR	58	CONTROLLED FLAW	1400	279.30	4.000	47.500	0.0200	4.0005x2.9134mm
NT-154	NORTON/UDRI/2	UDRIKGNV89	AIR	60	CONTROLLED FLAW	1400	263.80	3.400	40.000	0.0200	4.0234x2.9261mm
SN-4	HOWMET/UDRI/2	UDRIKGNV89	AIR	1A	CONTROLLED FLAW	21	951.90	3.600	33.100	0.0200	6.1646x3.0810mm
SN-4	HOWMET/UDRI/2	UDRIKGNV89	AIR	2A	CONTROLLED FLAW	21	911.80	3.800	38.900	0.0200	6.1544x3.0734mm
SN-4	HOWMET/UDRI/2	UDRIKGNV89	AIR	2B	CONTROLLED FLAW	21	898.50	3.600	37.000	0.0200	6.1570x3.0709mm
SN-4	HOWMET/UDRI/2	UDRIKGNV89	AIR	3A	CONTROLLED FLAW	21	911.80	3.700	37.400	0.0200	6.1570x3.0607mm
SN-4	HOWMET/UDRI/2	UDRIKGNV89	AIR	3B	CONTROLLED FLAW	21	947.40	3.700	33.900	0.0200	6.1595x3.0658mm
SN-4	HOWMET/UDRI/2	UDRIKGNV89	AIR	4A	CONTROLLED FLAW	21	938.50	3.700	35.500	0.0200	6.1570x3.0683mm
SN-4	HOWMET/UDRI/2	UDRIKGNV89	AIR	4B	CONTROLLED FLAW	21	929.60	3.800	36.800	0.0200	6.1646x3.0709mm
SN-4	HOWMET/UDRI/2	UDRIKGNV89	AIR	5A	CONTROLLED FLAW	21	880.70	3.900	45.000	0.0200	6.1570x3.0709mm
SN-4	HOWMET/UDRI/2	UDRIKGNV89	AIR	5B	CONTROLLED FLAW	21	867.40	3.400	35.000	0.0200	6.1595x3.0734mm

SECTION 4. INTERRUPTED FATIGUE TEST RESULTS ON A YITRIA-PARTIALLY STABILIZED ZIRCONIA

MATERIAL	BATCH CODE	REFERENCE CODE	SPECIMEN NUMBER	WIDTH mm	THICK mm	FIG NO.	TEMP. °C	HOLD TIME hours	APPLIED STRESS MPa	REQUIRED LOADING N	LOADING RATE N/s	FRACTURE LOAD N	FRACTURE STRENGTH MPa
Z-201	KYOCERA/1985	ORNL/FERBER-289	13	2.7915	2.5502	4	800	0.5	0	0	222.4	282.89	296.9
Z-201	KYOCERA/1985	ORNL/FERBER-289	14	2.7915	2.5451	5	800	0.5	0	0	222.4	292.68	308.4
Z-201	KYOCERA/1985	ORNL/FERBER-289	15	2.7889	2.5451	6	800	0.5	0	0	222.4	289.12	304.9
Z-201	KYOCERA/1985	ORNL/FERBER-289	19	2.7889	2.5527	1	800	24	0	0	222.4	305.13	319.9
Z-201	KYOCERA/1985	ORNL/FERBER-289	20	2.7915	2.5527	2	800	24	0	0	222.4	286.45	300
Z-201	KYOCERA/1985	ORNL/FERBER-289	21	2.7864	2.5451	3	800	24	0	0	222.4	286.45	302.4
Z-201	KYOCERA/1985	ORNL/FERBER-289	22	2.7915	2.5527	6	800	168	0	0	222.4	284.67	298.1
Z-201	KYOCERA/1985	ORNL/FERBER-289	23	2.7915	2.5476	5	800	168	0	0	222.4	256.2	269.4
Z-201	KYOCERA/1985	ORNL/FERBER-289	25	2.7915	2.5527	4	800	168	0	0	222.4	258.87	271.1
Z-201	KYOCERA/1985	ORNL/FERBER-289	26	2.7915	2.5425	1	800	336	0	0	222.4	319.37	337.2
Z-201	KYOCERA/1985	ORNL/FERBER-289	27	2.7915	2.5425	2	800	336	0	0	222.4	326.48	344.7
Z-201	KYOCERA/1985	ORNL/FERBER-289	28	2.7915	2.5425	3	800	336	0	0	222.4	339.38	358.3
Z-201	KYOCERA/1985	ORNL/FERBER-289	29	2.7915	2.5425	4	800	24	181.656	172.062	222.4	323.81	341.9
Z-201	KYOCERA/1985	ORNL/FERBER-289	30	2.7915	2.54	5	800	24	181.656	171.718	222.4	284.67	301.1
Z-201	KYOCERA/1985	ORNL/FERBER-289	31	2.7864	2.5425	6	800	24	181.656	171.749	222.4	316.7	335
Z-201	KYOCERA/1985	ORNL/FERBER-289	32	2.7889	2.5451	4	800	168	181.656	172.249	222.4	298.02	314.3
Z-201	KYOCERA/1985	ORNL/FERBER-289	33	2.7991	2.5451	5	800	168	181.656	172.876	222.4	350.95	368.8
Z-201	KYOCERA/1985	ORNL/FERBER-289	34	2.7915	2.5425	6	800	168	181.656	172.062	222.4	277.11	292.5
Z-201	KYOCERA/1985	ORNL/FERBER-289	35	2.7864	2.5425	1	800	214	181.656	171.749	222.4	308.69	326.5
Z-201	KYOCERA/1985	ORNL/FERBER-289	36	2.7889	2.5451	2	800	214	181.656	172.249	222.4	343.83	362.6
Z-201	KYOCERA/1985	ORNL/FERBER-289	37	2.7915	2.5425	3	800	214	181.656	172.062	222.4	326.04	344.2
Z-201	KYOCERA/1985	ORNL/FERBER-289	38	2.7915	2.5425	4	1000	144	0	0	222.4	208.17	219.8
Z-201	KYOCERA/1985	ORNL/FERBER-289	39	2.7889	2.5476	5	1000	144	0	0	222.4	267.77	281.8
Z-201	KYOCERA/1985	ORNL/FERBER-289	40	2.7915	2.5476	6	1000	144	0	0	222.4	279.78	294.2

Figure 2.1. Strength vs. temperature plot for Kyocera Z-201 (1985), a yttria-partially stabilized zirconia.

Figure 2.2. Strength vs. hold time for Kyocera Z-201 (1985) with no load and with 60% load.

SECTION 5. MOR 4-POINT BEND TEST RESULTS

MATERIAL	BATCH CODE	REFERENCE CODE	TEST ENVIRON.	SPECIMEN NUMBER	TEMP °C	LOAD N	WIDTH mm	THICK mm	BEND STRENGTH MPa	X-HEAD SPEED mm/sec	COMMENTS
CVD SIC	CVD/UDRI/2	UDRIPKGNV89	AIR	1	21	645.0	3.9954	3.0175	532.0	0.042330	
CVD SIC	CVD/UDRI/2	UDRIPKGNV89	AIR	2	21	395.9	3.9903	2.9972	331.0	0.042330	
CVD SIC	CVD/UDRI/2	UDRIPKGNV89	AIR	4	21	511.5	3.9929	2.9769	434.0	0.042330	
CVD SIC	CVD/UDRI/2	UDRIPKGNV89	AIR	5	21	702.8	4.0005	2.9566	535.0	0.042330	
CVD SIC	CVD/UDRI/2	UDRIPKGNV89	AIR	6	21	502.6	3.9700	2.9794	428.0	0.042330	
CVD SIC	CVD/UDRI/2	UDRIPKGNV89	AIR	7	21	627.2	3.9954	3.0099	520.0	0.042330	
CVD SIC	CVD/UDRI/2	UDRIPKGNV89	AIR	9	21	484.8	3.9726	2.9794	412.0	0.042330	
CVD SIC	CVD/UDRI/2	UDRIPKGNV89	AIR	10	21	520.4	4.0005	2.9870	437.0	0.042330	
CVD SIC	CVD/UDRI/2	UDRIPKGNV89	AIR	62	1000	814.0	4.0234	2.9845	681.0	0.042330	
CVD SIC	CVD/UDRI/2	UDRIPKGNV89	AIR	63	1000	885.2	4.0310	2.9820	741.0	0.042330	
CVD SIC	CVD/UDRI/2	UDRIPKGNV89	AIR	64	1000	467.0	3.9726	2.9870	395.0	0.042330	
CVD SIC	CVD/UDRI/2	UDRIPKGNV89	AIR	65	1000	538.2	3.9599	2.9820	459.0	0.042330	
CVD SIC	CVD/UDRI/2	UDRIPKGNV89	AIR	66	1000	960.8	4.0284	2.9896	801.0	0.042330	
CVD SIC	CVD/UDRI/2	UDRIPKGNV89	AIR	67	1000	1112.0	4.0259	2.9870	929.0	0.042330	
CVD SIC	CVD/UDRI/2	UDRIPKGNV89	AIR	68	1000	814.0	4.0234	2.9870	680.0	0.042330	
CVD SIC	CVD/UDRI/2	UDRIPKGNV89	AIR	69	1000	765.1	4.0208	2.9870	640.0	0.042330	
CVD SIC	CVD/UDRI/2	UDRIPKGNV89	AIR	70	1000	716.1	4.0259	2.9870	598.0	0.042330	
CVD SIC	CVD/UDRI/2	UDRIPKGNV89	AIR	51	1000	693.9	3.9878	2.9134	615.0	0.000423	
CVD SIC	CVD/UDRI/2	UDRIPKGNV89	AIR	53	1000	218.0	3.9878	2.9642	187.0	0.000423	
CVD SIC	CVD/UDRI/2	UDRIPKGNV89	AIR	54	1000	2086.1	3.9700	2.9515	652.0	0.000423	
CVD SIC	CVD/UDRI/2	UDRIPKGNV89	AIR	55	1000	653.9	3.9980	2.9413	567.0	0.000423	
CVD SIC	CVD/UDRI/2	UDRIPKGNV89	AIR	56	1000	916.3	3.9827	3.0023	766.0	0.000423	
CVD SIC	CVD/UDRI/2	UDRIPKGNV89	AIR	57	1000	751.7	3.9751	2.9362	658.0	0.000423	
CVD SIC	CVD/UDRI/2	UDRIPKGNV89	AIR	58	1000	636.1	3.9827	3.0048	531.0	0.000423	
CVD SIC	CVD/UDRI/2	UDRIPKGNV89	AIR	59	1000	498.2	3.9700	2.9464	434.0	0.000423	
CVD SIC	CVD/UDRI/2	UDRIPKGNV89	AIR	60	1000	484.8	3.9421	2.9439	426.0	0.000423	
CVD SIC	CVD/UDRI/2	UDRIPKGNV89	AIR	21	1200	578.2	3.9878	2.9743	492.0	0.042330	
CVD SIC	CVD/UDRI/2	UDRIPKGNV89	AIR	22	1200	493.7	3.9624	2.9515	429.0	0.042330	
CVD SIC	CVD/UDRI/2	UDRIPKGNV89	AIR	23	1200	627.2	3.9700	2.9972	528.0	0.042330	
CVD SIC	CVD/UDRI/2	UDRIPKGNV89	AIR	24	1200	609.4	3.9878	2.9794	516.0	0.042330	
CVD SIC	CVD/UDRI/2	UDRIPKGNV89	AIR	25	1200	520.4	3.9802	2.9769	443.0	0.042330	
CVD SIC	CVD/UDRI/2	UDRIPKGNV89	AIR	26	1200	569.3	3.9929	2.9718	484.0	0.042330	
CVD SIC	CVD/UDRI/2	UDRIPKGNV89	AIR	27	1200	649.4	3.9751	2.9870	549.0	0.042330	
CVD SIC	CVD/UDRI/2	UDRIPKGNV89	AIR	28	1200	551.6	3.9700	2.9743	471.0	0.042330	
CVD SIC	CVD/UDRI/2	UDRIPKGNV89	AIR	29	1200	569.3	3.9776	2.9718	486.0	0.042330	
CVD SIC	CVD/UDRI/2	UDRIPKGNV89	AIR	30	1200	645.0	3.9675	2.9794	549.0	0.042330	
CVD SIC	CVD/UDRI/2	UDRIPKGNV89	AIR	41	1200	636.1	3.9675	2.9540	551.0	0.000423	
CVD SIC	CVD/UDRI/2	UDRIPKGNV89	AIR	42	1200	707.2	3.9700	2.9769	603.0	0.000423	
CVD SIC	CVD/UDRI/2	UDRIPKGNV89	AIR	43	1200	653.9	3.9903	2.9616	560.0	0.000423	

SECTION 5. MOR 4-POINT BEND TEST RESULTS

MATERIAL	BATCH CODE	REFERENCE CODE	TEST ENVIRON.	SPEC. No.	TEMP °C	LOAD N	WIDTH mm	THICK mm	BEND STRENGTH MPa	X-HEAD SPEED mm/s	COMMENTS
CVD SIC	CVD/UDRI/2	UDRIPKGNV89	AIR	1	21	645.0	3.9954	3.0175	532.0	0.042330	
CVD SIC	CVD/UDRI/2	UDRIPKGNV89	AIR	2	21	395.9	3.9903	2.9972	331.0	0.042330	
CVD SIC	CVD/UDRI/2	UDRIPKGNV89	AIR	4	21	511.5	3.9929	2.9769	434.0	0.042330	
CVD SIC	CVD/UDRI/2	UDRIPKGNV89	AIR	5	21	702.8	4.0005	2.9566	535.0	0.042330	
CVD SIC	CVD/UDRI/2	UDRIPKGNV89	AIR	6	21	502.6	3.9700	2.9794	428.0	0.042330	
CVD SIC	CVD/UDRI/2	UDRIPKGNV89	AIR	7	21	627.2	3.9954	3.0099	520.0	0.042330	
CVD SIC	CVD/UDRI/2	UDRIPKGNV89	AIR	9	21	484.8	3.9726	2.9794	412.0	0.042330	
CVD SIC	CVD/UDRI/2	UDRIPKGNV89	AIR	10	21	520.4	4.0005	2.9870	437.0	0.042330	
CVD SIC	CVD/UDRI/2	UDRIPKGNV89	AIR	62	1000	814.0	4.0234	2.9845	681.0	0.042330	
CVD SIC	CVD/UDRI/2	UDRIPKGNV89	AIR	63	1000	885.2	4.0310	2.9820	741.0	0.042330	
CVD SIC	CVD/UDRI/2	UDRIPKGNV89	AIR	64	1000	467.0	3.9726	2.9870	395.0	0.042330	
CVD SIC	CVD/UDRI/2	UDRIPKGNV89	AIR	65	1000	538.2	3.9599	2.9820	459.0	0.042330	
CVD SIC	CVD/UDRI/2	UDRIPKGNV89	AIR	66	1000	960.8	4.0284	2.9896	801.0	0.042330	
CVD SIC	CVD/UDRI/2	UDRIPKGNV89	AIR	67	1000	1112.0	4.0259	2.9870	929.0	0.042330	
CVD SIC	CVD/UDRI/2	UDRIPKGNV89	AIR	68	1000	814.0	4.0234	2.9870	680.0	0.042330	
CVD SIC	CVD/UDRI/2	UDRIPKGNV89	AIR	69	1000	765.1	4.0208	2.9870	640.0	0.042330	
CVD SIC	CVD/UDRI/2	UDRIPKGNV89	AIR	70	1000	716.1	4.0259	2.9870	598.0	0.042330	
CVD SIC	CVD/UDRI/2	UDRIPKGNV89	AIR	51	1000	693.9	3.9878	2.9134	615.0	0.000423	
CVD SIC	CVD/UDRI/2	UDRIPKGNV89	AIR	53	1000	218.0	3.9878	2.9642	187.0	0.000423	
CVD SIC	CVD/UDRI/2	UDRIPKGNV89	AIR	54	1000	2086.1	3.9700	2.9515	652.0	0.000423	
CVD SIC	CVD/UDRI/2	UDRIPKGNV89	AIR	55	1000	653.9	3.9980	2.9413	567.0	0.000423	
CVD SIC	CVD/UDRI/2	UDRIPKGNV89	AIR	56	1000	916.3	3.9827	3.0023	766.0	0.000423	
CVD SIC	CVD/UDRI/2	UDRIPKGNV89	AIR	57	1000	751.7	3.9751	2.9362	658.0	0.000423	
CVD SIC	CVD/UDRI/2	UDRIPKGNV89	AIR	58	1000	636.1	3.9827	3.0048	531.0	0.000423	
CVD SIC	CVD/UDRI/2	UDRIPKGNV89	AIR	59	1000	498.2	3.9700	2.9464	434.0	0.000423	
CVD SIC	CVD/UDRI/2	UDRIPKGNV89	AIR	60	1000	484.8	3.9421	2.9439	426.0	0.000423	
CVD SIC	CVD/UDRI/2	UDRIPKGNV89	AIR	21	1200	578.2	3.9878	2.9743	492.0	0.042330	
CVD SIC	CVD/UDRI/2	UDRIPKGNV89	AIR	22	1200	493.7	3.9624	2.9515	429.0	0.042330	
CVD SIC	CVD/UDRI/2	UDRIPKGNV89	AIR	23	1200	627.2	3.9700	2.9972	528.0	0.042330	
CVD SIC	CVD/UDRI/2	UDRIPKGNV89	AIR	24	1200	609.4	3.9878	2.9794	516.0	0.042330	
CVD SIC	CVD/UDRI/2	UDRIPKGNV89	AIR	25	1200	520.4	3.9802	2.9769	443.0	0.042330	
CVD SIC	CVD/UDRI/2	UDRIPKGNV89	AIR	26	1200	569.3	3.9929	2.9718	484.0	0.042330	
CVD SIC	CVD/UDRI/2	UDRIPKGNV89	AIR	27	1200	649.4	3.9751	2.9870	549.0	0.042330	
CVD SIC	CVD/UDRI/2	UDRIPKGNV89	AIR	28	1200	551.6	3.9700	2.9743	471.0	0.042330	
CVD SIC	CVD/UDRI/2	UDRIPKGNV89	AIR	29	1200	569.3	3.9776	2.9718	486.0	0.042330	

SECTION 5. MOR 4-POINT BEND TEST RESULTS, continued

MATERIAL	BATCH CODE	REFERENCE CODE	TEST ENVIRON.	SPEC. No.	TEMP °C	LOAD N	WIDTH mm	THICK mm	BEND STRENGTH MPa	X-HEAD SPEED mm/s	COMMENTS
CVD SIC	CVD/UDRI/2	UDRIPKGNOV89	AIR	30	1200	645.0	3.9675	2.9784	549.0	0.042330	
CVD SIC	CVD/UDRI/2	UDRIPKGNOV89	AIR	41	1200	636.1	3.9675	2.9540	551.0	0.000423	
CVD SIC	CVD/UDRI/2	UDRIPKGNOV89	AIR	42	1200	707.2	3.9700	2.9769	603.0	0.000423	
CVD SIC	CVD/UDRI/2	UDRIPKGNOV89	AIR	43	1200	653.9	3.9803	2.9616	560.0	0.000423	
CVD SIC	CVD/UDRI/2	UDRIPKGNOV89	AIR	44	1200	756.2	3.9878	2.9337	661.0	0.000423	
CVD SIC	CVD/UDRI/2	UDRIPKGNOV89	AIR	45	1200	218.0	3.9903	2.9235	192.0	0.000423	
CVD SIC	CVD/UDRI/2	UDRIPKGNOV89	AIR	46	1200	778.4	3.9827	2.9921	655.0	0.000423	
CVD SIC	CVD/UDRI/2	UDRIPKGNOV89	AIR	47	1200	582.7	3.9854	2.9108	516.0	0.000423	
CVD SIC	CVD/UDRI/2	UDRIPKGNOV89	AIR	48	1200	782.9	3.9878	2.9845	661.0	0.000423	
CVD SIC	CVD/UDRI/2	UDRIPKGNOV89	AIR	49	1200	516.0	3.9751	2.9921	435.0	0.000423	
CVD SIC	CVD/UDRI/2	UDRIPKGNOV89	AIR	50*	1200	387.0	3.9649	2.9566	335.0	0.000423	
CVD SIC	CVD/UDRI/2	UDRIPKGNOV89	AIR	11	1400	467.0	3.9624	2.9489	407.0	0.042330	
CVD SIC	CVD/UDRI/2	UDRIPKGNOV89	AIR	12	1400	440.4	4.0640	2.9845	365.0	0.042330	
CVD SIC	CVD/UDRI/2	UDRIPKGNOV89	AIR	13	1400	604.9	3.9827	2.9743	515.0	0.042330	
CVD SIC	CVD/UDRI/2	UDRIPKGNOV89	AIR	14	1400	596.0	3.9903	3.0201	491.0	0.042330	
CVD SIC	CVD/UDRI/2	UDRIPKGNOV89	AIR	15	1400	676.1	3.9649	2.9718	576.0	0.042330	
CVD SIC	CVD/UDRI/2	UDRIPKGNOV89	AIR	17	1400	751.7	3.9829	2.9464	651.0	0.042330	
CVD SIC	CVD/UDRI/2	UDRIPKGNOV89	AIR	18	1400	640.5	3.9878	3.0023	535.0	0.042330	
CVD SIC	CVD/UDRI/2	UDRIPKGNOV89	AIR	19	1400	683.9	3.9726	2.9921	585.0	0.042330	
CVD SIC	CVD/UDRI/2	UDRIPKGNOV89	AIR	20	1400	569.3	3.9700	3.0124	474.0	0.042330	
CVD SIC	CVD/UDRI/2	UDRIPKGNOV89	AIR	31	1400	658.3	3.9675	2.9769	562.0	0.000423	
CVD SIC	CVD/UDRI/2	UDRIPKGNOV89	AIR	32	1400	564.9	3.9700	2.9794	481.0	0.000423	
CVD SIC	CVD/UDRI/2	UDRIPKGNOV89	AIR	33	1400	729.5	3.9878	2.9769	619.0	0.000423	
CVD SIC	CVD/UDRI/2	UDRIPKGNOV89	AIR	34	1400	774.0	3.9824	3.0201	643.0	0.000423	
CVD SIC	CVD/UDRI/2	UDRIPKGNOV89	AIR	35	1400	707.2	3.9954	2.9743	600.0	0.000423	
CVD SIC	CVD/UDRI/2	UDRIPKGNOV89	AIR	36	1400	747.3	3.9776	2.9769	636.0	0.000423	
CVD SIC	CVD/UDRI/2	UDRIPKGNOV89	AIR	37	1400	489.3	3.9776	2.9870	414.0	0.000423	
CVD SIC	CVD/UDRI/2	UDRIPKGNOV89	AIR	38	1400	765.1	3.9751	2.9972	643.0	0.000423	
CVD SIC	CVD/UDRI/2	UDRIPKGNOV89	AIR	39	1400	707.2	3.9802	2.9667	606.0	0.000423	
CVD SIC	CVD/UDRI/2	UDRIPKGNOV89	AIR	40	1400	716.1	3.9548	2.9566	622.0	0.000423	
HEXOLOY SA	SOHO/UDRI/2	UDRIPKGNOV89	AIR	41	21	480.4	4.0005	2.9947	402.0	0.042330	
HEXOLOY SA	SOHO/UDRI/2	UDRIPKGNOV89	AIR	42	21	587.1	3.9954	2.9820	496.0	0.042330	
HEXOLOY SA	SOHO/UDRI/2	UDRIPKGNOV89	AIR	43	21	418.1	3.9903	3.0074	348.0	0.042330	
HEXOLOY SA	SOHO/UDRI/2	UDRIPKGNOV89	AIR	44	21	475.9	3.9878	3.0074	396.0	0.042330	

SPECIMEN DELAMINATED

SECTION 5. MOR 4-POINT BEND TEST RESULTS, continued

MATERIAL	BATCH CODE	REFERENCE CODE	TEST ENVIRON.	SPEC. No.	TEMP °C	LOAD N	WIDTH mm	THICK mm	BEND STRENGTH MPa	X-HEAD SPEED mm/s	COMMENTS
HEXOLOY SA	SOHIO/UDRI/2	UDRIIPKGN0V89	AIR	45	21	493.7	4.0005	2.9921	414.0	0.042330	
HEXOLOY SA	SOHIO/UDRI/2	UDRIIPKGN0V89	AIR	46	21	482.6	3.9929	3.0048	385.0	0.042330	
HEXOLOY SA	SOHIO/UDRI/2	UDRIIPKGN0V89	AIR	47	21	547.1	3.9903	3.0124	453.0	0.042330	
HEXOLOY SA	SOHIO/UDRI/2	UDRIIPKGN0V89	AIR	48	21	480.4	4.0005	3.0023	400.0	0.042330	
HEXOLOY SA	SOHIO/UDRI/2	UDRIIPKGN0V89	AIR	49	21	369.2	3.9980	3.0150	305.0	0.042330	
HEXOLOY SA	SOHIO/UDRI/2	UDRIIPKGN0V89	AIR	50	21	507.1	4.0081	2.9997	422.0	0.042330	
HEXOLOY SA	SOHIO/UDRI/2	UDRIIPKGN0V89	AIR	123	21	449.3	4.0107	3.0099	371.0	0.000423	
HEXOLOY SA	SOHIO/UDRI/2	UDRIIPKGN0V89	AIR	124	21	475.9	3.9903	2.9972	398.0	0.000423	
HEXOLOY SA	SOHIO/UDRI/2	UDRIIPKGN0V89	AIR	125	21	444.8	3.9929	2.9683	379.0	0.000423	
HEXOLOY SA	SOHIO/UDRI/2	UDRIIPKGN0V89	AIR	126	21	502.6	4.0081	3.0175	413.0	0.000423	
HEXOLOY SA	SOHIO/UDRI/2	UDRIIPKGN0V89	AIR	127	21	502.6	4.0234	3.0124	413.0	0.000423	
HEXOLOY SA	SOHIO/UDRI/2	UDRIIPKGN0V89	AIR	6	1000	524.9	3.9878	3.0099	436.0	0.042330	
HEXOLOY SA	SOHIO/UDRI/2	UDRIIPKGN0V89	AIR	7	1000	444.8	4.0030	2.9820	375.0	0.042330	
HEXOLOY SA	SOHIO/UDRI/2	UDRIIPKGN0V89	AIR	8	1000	516.0	4.0005	2.9845	434.0	0.042330	
HEXOLOY SA	SOHIO/UDRI/2	UDRIIPKGN0V89	AIR	9	1000	542.7	3.9878	3.0023	453.0	0.042330	
HEXOLOY SA	SOHIO/UDRI/2	UDRIIPKGN0V89	AIR	10	1000	538.2	4.0005	2.9997	449.0	0.042330	
HEXOLOY SA	SOHIO/UDRI/2	UDRIIPKGN0V89	AIR	11	1000	493.7	4.0030	3.0124	408.0	0.042330	
HEXOLOY SA	SOHIO/UDRI/2	UDRIIPKGN0V89	AIR	12	1000	440.4	4.0005	3.0023	366.0	0.042330	
HEXOLOY SA	SOHIO/UDRI/2	UDRIIPKGN0V89	AIR	13	1000	511.5	3.9903	3.0023	427.0	0.042330	
HEXOLOY SA	SOHIO/UDRI/2	UDRIIPKGN0V89	AIR	14	1000	498.2	3.9903	2.9794	422.0	0.042330	
HEXOLOY SA	SOHIO/UDRI/2	UDRIIPKGN0V89	AIR	15	1000	467.0	3.9878	3.0099	388.0	0.042330	
HEXOLOY SA	SOHIO/UDRI/2	UDRIIPKGN0V89	AIR	103	1000	507.1	3.9954	2.9769	430.0	0.004233	
HEXOLOY SA	SOHIO/UDRI/2	UDRIIPKGN0V89	AIR	104	1000	484.8	4.0030	3.0074	402.0	0.004233	
HEXOLOY SA	SOHIO/UDRI/2	UDRIIPKGN0V89	AIR	105	1000	533.8	4.0005	3.0201	439.0	0.004233	
HEXOLOY SA	SOHIO/UDRI/2	UDRIIPKGN0V89	AIR	106	1000	449.3	4.0056	3.0124	471.0	0.004233	
HEXOLOY SA	SOHIO/UDRI/2	UDRIIPKGN0V89	AIR	107	1000	547.1	4.0005	2.9820	461.0	0.004233	
HEXOLOY SA	SOHIO/UDRI/2	UDRIIPKGN0V89	AIR	108	1000	431.5	4.0030	2.9870	362.0	0.004233	
HEXOLOY SA	SOHIO/UDRI/2	UDRIIPKGN0V89	AIR	109	1000	573.8	3.9903	2.9997	479.0	0.004233	
HEXOLOY SA	SOHIO/UDRI/2	UDRIIPKGN0V89	AIR	110	1000	395.9	3.9853	3.0048	330.0	0.004233	
HEXOLOY SA	SOHIO/UDRI/2	UDRIIPKGN0V89	AIR	111	1000	556.0	3.9980	3.0023	463.0	0.004233	
HEXOLOY SA	SOHIO/UDRI/2	UDRIIPKGN0V89	AIR	112	1000	502.6	4.0030	3.0023	418.0	0.004233	
HEXOLOY SA	SOHIO/UDRI/2	UDRIIPKGN0V89	AIR	83	1000	516.0	3.9903	2.9972	432.0	0.000423	
HEXOLOY SA	SOHIO/UDRI/2	UDRIIPKGN0V89	AIR	84	1000	486.3	3.9954	2.9820	413.0	0.000423	
HEXOLOY SA	SOHIO/UDRI/2	UDRIIPKGN0V89	AIR	85	1000	486.3	3.9954	2.9794	414.0	0.000423	
HEXOLOY SA	SOHIO/UDRI/2	UDRIIPKGN0V89	AIR	86	1000	422.6	3.9802	2.9870	357.0	0.000423	

SECTION 5. MOR 4-POINT BEND TEST RESULTS, continued

MATERIAL	BATCH CODE	REFERENCE CODE	TEST ENVIRON.	SPEC. No.	TEMP °C	LOAD N	WIDTH mm	THICK mm	BEND STRENGTH MPa	X-HEAD SPEED mm/s	COMMENTS
HEXQLOY SA	SOHIO/UDRI/2	UDRIPKGNV89	AIR	87	1000	569.3	4.0056	2.9820	480.0	0.000423	
HEXQLOY SA	SOHIO/UDRI/2	UDRIPKGNV89	AIR	88	1000	520.4	4.0081	2.9870	437.0	0.000423	
HEXQLOY SA	SOHIO/UDRI/2	UDRIPKGNV89	AIR	89	1000	444.8	4.0056	2.9997	370.0	0.000423	
HEXQLOY SA	SOHIO/UDRI/2	UDRIPKGNV89	AIR	90	1000	444.8	4.0030	2.9845	374.0	0.000423	
HEXQLOY SA	SOHIO/UDRI/2	UDRIPKGNV89	AIR	91	1000	502.6	4.0030	3.0175	414.0	0.000423	
HEXQLOY SA	SOHIO/UDRI/2	UDRIPKGNV89	AIR	92	1000	511.5	4.0030	2.9845	430.0	0.000423	
HEXQLOY SA	SOHIO/UDRI/2	UDRIPKGNV89	AIR	51	1200	467.0	3.9954	3.0048	388.0	0.042330	
HEXQLOY SA	SOHIO/UDRI/2	UDRIPKGNV89	AIR	52	1200	649.4	4.0056	2.9896	544.0	0.042330	
HEXQLOY SA	SOHIO/UDRI/2	UDRIPKGNV89	AIR	53	1200	404.8	4.0005	3.0074	336.0	0.042330	
HEXQLOY SA	SOHIO/UDRI/2	UDRIPKGNV89	AIR	54	1200	551.6	3.9803	2.9972	462.0	0.042330	
HEXQLOY SA	SOHIO/UDRI/2	UDRIPKGNV89	AIR	55	1200	533.8	4.0030	2.9997	445.0	0.042330	
HEXQLOY SA	SOHIO/UDRI/2	UDRIPKGNV89	AIR	56	1200	529.3	4.0030	3.0099	438.0	0.042330	
HEXQLOY SA	SOHIO/UDRI/2	UDRIPKGNV89	AIR	57	1200	520.4	4.0030	2.9997	433.0	0.042330	
HEXQLOY SA	SOHIO/UDRI/2	UDRIPKGNV89	AIR	58	1200	511.5	4.0005	3.0048	425.0	0.042330	
HEXQLOY SA	SOHIO/UDRI/2	UDRIPKGNV89	AIR	59	1200	529.3	4.0056	3.0124	437.0	0.042330	
HEXQLOY SA	SOHIO/UDRI/2	UDRIPKGNV89	AIR	60	1200	533.8	4.0056	3.0099	441.0	0.042330	
HEXQLOY SA	SOHIO/UDRI/2	UDRIPKGNV89	AIR	113	1200	529.3	3.9954	2.9870	445.0	0.004233	
HEXQLOY SA	SOHIO/UDRI/2	UDRIPKGNV89	AIR	114	1200	542.7	4.0132	3.0099	448.0	0.004233	
HEXQLOY SA	SOHIO/UDRI/2	UDRIPKGNV89	AIR	115	1200	578.2	4.0081	2.9794	488.0	0.004233	
HEXQLOY SA	SOHIO/UDRI/2	UDRIPKGNV89	AIR	116	1200	329.2	4.0056	2.9947	275.0	0.004233	
HEXQLOY SA	SOHIO/UDRI/2	UDRIPKGNV89	AIR	117	1200	467.0	3.9903	3.0099	388.0	0.004233	
HEXQLOY SA	SOHIO/UDRI/2	UDRIPKGNV89	AIR	118	1200	418.1	4.0056	2.9769	353.0	0.004233	
HEXQLOY SA	SOHIO/UDRI/2	UDRIPKGNV89	AIR	119	1200	440.4	4.0056	2.9972	367.0	0.004233	
HEXQLOY SA	SOHIO/UDRI/2	UDRIPKGNV89	AIR	120	1200	498.2	4.0056	2.9972	415.0	0.004233	
HEXQLOY SA	SOHIO/UDRI/2	UDRIPKGNV89	AIR	121	1200	471.5	3.9980	2.9972	394.0	0.004233	
HEXQLOY SA	SOHIO/UDRI/2	UDRIPKGNV89	AIR	122	1200	516.0	3.9929	2.9972	432.0	0.004233	
HEXQLOY SA	SOHIO/UDRI/2	UDRIPKGNV89	AIR	72	1200	493.7	4.0030	2.9947	413.0	0.000423	
HEXQLOY SA	SOHIO/UDRI/2	UDRIPKGNV89	AIR	73	1200	427.0	3.9929	3.0048	355.0	0.000423	
HEXQLOY SA	SOHIO/UDRI/2	UDRIPKGNV89	AIR	74	1200	582.7	3.9980	2.9997	486.0	0.000423	
HEXQLOY SA	SOHIO/UDRI/2	UDRIPKGNV89	AIR	75	1200	556.0	3.9929	2.9997	464.0	0.000423	
HEXQLOY SA	SOHIO/UDRI/2	UDRIPKGNV89	AIR	76	1200	462.6	4.0030	2.9997	385.0	0.000423	
HEXQLOY SA	SOHIO/UDRI/2	UDRIPKGNV89	AIR	77	1200	458.1	4.0030	3.0201	376.0	0.000423	
HEXQLOY SA	SOHIO/UDRI/2	UDRIPKGNV89	AIR	78	1200	596.0	4.0030	2.9870	501.0	0.000423	
HEXQLOY SA	SOHIO/UDRI/2	UDRIPKGNV89	AIR	79	1200	551.6	3.9878	2.9921	464.0	0.000423	
HEXQLOY SA	SOHIO/UDRI/2	UDRIPKGNV89	AIR	80	1200	538.2	3.9878	3.0099	447.0	0.000423	

SECTION 5. MOR 4-POINT BEND TEST RESULTS, continued

MATERIAL	BATCH	REFERENCE	TEST	SPEC.	TEMP	LOAD	WIDTH	THICK	BEND	X-HEAD	COMMENTS
	CODE	CODE	ENVIRON.	No.	°C	N	mm	mm	STRENGTH	SPEED	
									MPa	mm/s	
SILICON NITRIDES											
CERAMLOY 147-3	CERADYNE/UDRI/2	UDRIKPGNOV89	AIR	26	21	885.2	3.9980	2.9870	744.7	0.042330	
CERAMLOY 147-3	CERADYNE/UDRI/2	UDRIKPGNOV89	AIR	28	21	1005.3	3.9954	3.0124	831.5	0.042330	
CERAMLOY 147-3	CERADYNE/UDRI/2	UDRIKPGNOV89	AIR	29	21	885.2	3.9980	2.9870	744.7	0.042330	
CERAMLOY 147-3	CERADYNE/UDRI/2	UDRIKPGNOV89	AIR	30	21	880.7	3.9929	2.9845	742.6	0.042330	
CERAMLOY 147-3	CERADYNE/UDRI/2	UDRIKPGNOV89	AIR	51	1000	858.5	3.9929	3.0175	708.1	0.042330	
CERAMLOY 147-3	CERADYNE/UDRI/2	UDRIKPGNOV89	AIR	52	1000	636.1	3.9954	2.9997	530.9	0.042330	
CERAMLOY 147-3	CERADYNE/UDRI/2	UDRIKPGNOV89	AIR	53	1000	596.0	3.9929	3.0074	495.1	0.042330	
CERAMLOY 147-3	CERADYNE/UDRI/2	UDRIKPGNOV89	AIR	54	1000	569.3	3.9980	3.0150	470.2	0.042330	
CERAMLOY 147-3	CERADYNE/UDRI/2	UDRIKPGNOV89	AIR	55	1000	578.2	3.9929	2.9896	486.1	0.042330	
CERAMLOY 147-3	CERADYNE/UDRI/2	UDRIKPGNOV89	AIR	56	1000	524.9	3.9980	2.9870	441.3	0.042330	
CERAMLOY 147-3	CERADYNE/UDRI/2	UDRIKPGNOV89	AIR	57	1000	751.7	3.9929	3.0124	622.6	0.042330	
CERAMLOY 147-3	CERADYNE/UDRI/2	UDRIKPGNOV89	AIR	58	1000	604.9	3.9929	3.0150	499.9	0.042330	
CERAMLOY 147-3	CERADYNE/UDRI/2	UDRIKPGNOV89	AIR	59	1000	782.9	3.9903	2.9921	664.7	0.042330	
CERAMLOY 147-3	CERADYNE/UDRI/2	UDRIKPGNOV89	AIR	60	1000	782.9	3.9954	3.0048	650.9	0.042330	
CERAMLOY 147-3	CERADYNE/UDRI/2	UDRIKPGNOV89	AIR	41	1000	600.5	3.9980	3.0175	495.1	0.000423	
CERAMLOY 147-3	CERADYNE/UDRI/2	UDRIKPGNOV89	AIR	42	1000	564.9	3.9980	2.9820	476.4	0.000423	
CERAMLOY 147-3	CERADYNE/UDRI/2	UDRIKPGNOV89	AIR	43	1000	671.7	3.9980	2.9870	564.7	0.000423	
CERAMLOY 147-3	CERADYNE/UDRI/2	UDRIKPGNOV89	AIR	44	1000	707.2	3.9954	2.9896	594.3	0.000423	
CERAMLOY 147-3	CERADYNE/UDRI/2	UDRIKPGNOV89	AIR	45	1000	542.7	3.9608	3.0124	464.7	0.000423	
CERAMLOY 147-3	CERADYNE/UDRI/2	UDRIKPGNOV89	AIR	46	1000	564.9	3.9980	3.0175	465.4	0.000423	
CERAMLOY 147-3	CERADYNE/UDRI/2	UDRIKPGNOV89	AIR	47	1000	511.5	3.9954	3.0201	421.3	0.000423	
CERAMLOY 147-3	CERADYNE/UDRI/2	UDRIKPGNOV89	AIR	48	1000	502.6	3.9980	2.9870	422.7	0.000423	
CERAMLOY 147-3	CERADYNE/UDRI/2	UDRIKPGNOV89	AIR	49	1000	524.9	3.9929	3.0124	434.4	0.000423	
CERAMLOY 147-3	CERADYNE/UDRI/2	UDRIKPGNOV89	AIR	50	1000	649.4	3.9980	3.0124	537.1	0.000423	
CERAMLOY 147-3	CERADYNE/UDRI/2	UDRIKPGNOV89	AIR	11	1200	618.3	3.9929	3.0124	511.6	0.042330	
CERAMLOY 147-3	CERADYNE/UDRI/2	UDRIKPGNOV89	AIR	12	1200	658.3	3.9980	3.0124	544.7	0.042330	
CERAMLOY 147-3	CERADYNE/UDRI/2	UDRIKPGNOV89	AIR	13	1200	640.5	3.9980	2.9845	539.9	0.042330	
CERAMLOY 147-3	CERADYNE/UDRI/2	UDRIKPGNOV89	AIR	14	1200	662.8	3.9954	2.9896	557.1	0.042330	
CERAMLOY 147-3	CERADYNE/UDRI/2	UDRIKPGNOV89	AIR	15	1200	573.8	3.9980	3.0226	471.6	0.042330	
CERAMLOY 147-3	CERADYNE/UDRI/2	UDRIKPGNOV89	AIR	16	1200	613.8	4.0005	2.9947	513.0	0.042330	
CERAMLOY 147-3	CERADYNE/UDRI/2	UDRIKPGNOV89	AIR	17	1200	649.4	3.9980	3.0150	536.4	0.042330	
CERAMLOY 147-3	CERADYNE/UDRI/2	UDRIKPGNOV89	AIR	18	1200	636.1	3.9903	2.9845	537.1	0.042330	

SECTION 5. MOR 4-POINT BEND TEST RESULTS, continued

MATERIAL	BATCH CODE	REFERENCE CODE	TEST ENVIRON.	SPEC. No.	TEMP °C	LOAD N	WIDTH mm	THICK mm	BEND STRENGTH MPa	X-HEAD SPEED mm/s	COMMENTS
HEXOLOY SA	SOHO/UDRI/2	UDRIKGNV89	AIR	82	1200	613.8	3.9980	2.9769	520.0	0.000423	
HEXOLOY SA	SOHO/UDRI/2	UDRIKGNV89	AIR	31	1400	458.1	3.9929	3.0074	381.0	0.042330	
HEXOLOY SA	SOHO/UDRI/2	UDRIKGNV89	AIR	32	1400	609.4	4.0056	3.0074	505.0	0.042330	
HEXOLOY SA	SOHO/UDRI/2	UDRIKGNV89	AIR	33	1400	498.2	3.9980	3.0175	411.0	0.042330	
HEXOLOY SA	SOHO/UDRI/2	UDRIKGNV89	AIR	34	1400	573.8	4.0030	3.0124	474.0	0.042330	
HEXOLOY SA	SOHO/UDRI/2	UDRIKGNV89	AIR	35	1400	587.1	4.0132	2.9997	491.0	0.042330	
HEXOLOY SA	SOHO/UDRI/2	UDRIKGNV89	AIR	36	1400	458.1	3.9827	3.0150	380.0	0.042330	
HEXOLOY SA	SOHO/UDRI/2	UDRIKGNV89	AIR	37	1400	538.2	3.9980	2.9997	449.0	0.042330	
HEXOLOY SA	SOHO/UDRI/2	UDRIKGNV89	AIR	38	1400	580.6	4.0005	2.9997	389.0	0.042330	
HEXOLOY SA	SOHO/UDRI/2	UDRIKGNV89	AIR	39	1400	564.9	3.9827	3.0074	471.0	0.042330	
HEXOLOY SA	SOHO/UDRI/2	UDRIKGNV89	AIR	40	1400	489.3	4.0030	2.9972	408.0	0.042330	
HEXOLOY SA	SOHO/UDRI/2	UDRIKGNV89	AIR	93	1400	578.2	4.0056	3.0099	478.0	0.04233	
HEXOLOY SA	SOHO/UDRI/2	UDRIKGNV89	AIR	94	1400	502.6	3.9980	2.9997	419.0	0.04233	
HEXOLOY SA	SOHO/UDRI/2	UDRIKGNV89	AIR	95	1400	422.6	4.0005	3.0124	349.0	0.04233	
HEXOLOY SA	SOHO/UDRI/2	UDRIKGNV89	AIR	96	1400	484.8	4.0056	3.0150	399.0	0.04233	
HEXOLOY SA	SOHO/UDRI/2	UDRIKGNV89	AIR	97	1400	556.0	3.9929	3.0023	463.0	0.04233	
HEXOLOY SA	SOHO/UDRI/2	UDRIKGNV89	AIR	98	1400	431.5	4.0030	2.9896	362.0	0.04233	
HEXOLOY SA	SOHO/UDRI/2	UDRIKGNV89	AIR	99	1400	520.4	4.0081	2.9866	436.0	0.04233	
HEXOLOY SA	SOHO/UDRI/2	UDRIKGNV89	AIR	100	1400	511.5	3.9980	2.9921	429.0	0.04233	
HEXOLOY SA	SOHO/UDRI/2	UDRIKGNV89	AIR	101	1400	489.3	4.0107	3.0201	401.0	0.04233	
HEXOLOY SA	SOHO/UDRI/2	UDRIKGNV89	AIR	102	1400	498.2	4.0030	3.0201	410.0	0.04233	
HEXOLOY SA	SOHO/UDRI/2	UDRIKGNV89	AIR	61	1400	382.5	3.9954	2.9769	324.0	0.000423	
HEXOLOY SA	SOHO/UDRI/2	UDRIKGNV89	AIR	62	1400	467.0	3.9929	2.9997	390.0	0.000423	
HEXOLOY SA	SOHO/UDRI/2	UDRIKGNV89	AIR	64	1400	493.7	3.9954	3.0023	411.0	0.000423	
HEXOLOY SA	SOHO/UDRI/2	UDRIKGNV89	AIR	65	1400	467.0	3.9954	2.9947	391.0	0.000423	
HEXOLOY SA	SOHO/UDRI/2	UDRIKGNV89	AIR	66	1400	498.2	4.0056	2.9845	419.0	0.000423	
HEXOLOY SA	SOHO/UDRI/2	UDRIKGNV89	AIR	67	1400	516.0	4.0030	2.9820	435.0	0.000423	
HEXOLOY SA	SOHO/UDRI/2	UDRIKGNV89	AIR	68	1400	498.2	3.9802	2.9972	418.0	0.000423	
HEXOLOY SA	SOHO/UDRI/2	UDRIKGNV89	AIR	69	1400	458.1	3.9751	3.0023	384.0	0.000423	
HEXOLOY SA	SOHO/UDRI/2	UDRIKGNV89	AIR	70	1400	400.3	4.0005	2.9997	334.0	0.000423	
HEXOLOY SA	SOHO/UDRI/2	UDRIKGNV89	AIR	71	1400	471.5	3.9954	2.9921	395.0	0.000423	

SECTION 5. MOR 4-POINT BEND TEST RESULTS, continued

MATERIAL	BATCH CODE	REFERENCE CODE	TEST ENVIRON.	SPEC. No.	TEMP °C	LOAD N	WIDTH mm	THICK mm	BEND STRENGTH MPa	X-HEAD SPEED mm/s	COMMENTS
CERALLOY 147-3	CERADYNE/UDRI/2	UDRIPKGN0V89	AIR	19	1200	618.3	3.9980	3.0201	508.9	0.042330	
CERALLOY 147-3	CERADYNE/UDRI/2	UDRIPKGN0V89	AIR	20	1200	689.4	3.9980	3.0099	570.9	0.042330	
CERALLOY 147-3	CERADYNE/UDRI/2	UDRIPKGN0V89	AIR	31	1200	498.2	3.9929	2.9997	415.8	0.000423	
CERALLOY 147-3	CERADYNE/UDRI/2	UDRIPKGN0V89	AIR	32	1200	404.8	3.9954	3.0150	334.4	0.000423	
CERALLOY 147-3	CERADYNE/UDRI/2	UDRIPKGN0V89	AIR	33	1200	453.7	3.9980	2.9896	380.6	0.000423	
CERALLOY 147-3	CERADYNE/UDRI/2	UDRIPKGN0V89	AIR	34	1200	564.9	3.9929	3.0150	466.8	0.000423	
CERALLOY 147-3	CERADYNE/UDRI/2	UDRIPKGN0V89	AIR	35	1200	378.1	3.9980	2.9947	316.5	0.000423	
CERALLOY 147-3	CERADYNE/UDRI/2	UDRIPKGN0V89	AIR	36	1200	538.2	3.9954	3.0175	444.0	0.000423	
CERALLOY 147-3	CERADYNE/UDRI/2	UDRIPKGN0V89	AIR	37	1200	507.1	3.9954	3.0175	417.8	0.000423	
CERALLOY 147-3	CERADYNE/UDRI/2	UDRIPKGN0V89	AIR	38	1200	538.2	3.9954	3.0023	448.2	0.000423	
CERALLOY 147-3	CERADYNE/UDRI/2	UDRIPKGN0V89	AIR	39	1200	444.8	3.9929	3.0201	366.1	0.000423	
CERALLOY 147-3	CERADYNE/UDRI/2	UDRIPKGN0V89	AIR	40	1200	516.0	3.9954	2.9870	434.4	0.000423	
CERALLOY 147-3	CERADYNE/UDRI/2	UDRIPKGN0V89	AIR	1	1400	275.8	3.9980	2.9870	231.7	0.042330	
CERALLOY 147-3	CERADYNE/UDRI/2	UDRIPKGN0V89	AIR	2	1400	222.4	3.9980	3.0150	183.4	0.042330	
CERALLOY 147-3	CERADYNE/UDRI/2	UDRIPKGN0V89	AIR	3	1400	224.6	3.9980	2.9921	188.2	0.042330	
CERALLOY 147-3	CERADYNE/UDRI/2	UDRIPKGN0V89	AIR	4	1400	238.9	4.0005	2.9896	200.6	0.042330	
CERALLOY 147-3	CERADYNE/UDRI/2	UDRIPKGN0V89	AIR	5	1400	286.9	3.9929	3.0124	237.9	0.042330	
CERALLOY 147-3	CERADYNE/UDRI/2	UDRIPKGN0V89	AIR	6	1400	241.5	4.0005	2.9947	202.0	0.042330	
CERALLOY 147-3	CERADYNE/UDRI/2	UDRIPKGN0V89	AIR	7	1400	193.5	3.9954	2.9896	162.7	0.042330	
CERALLOY 147-3	CERADYNE/UDRI/2	UDRIPKGN0V89	AIR	8	1400	206.8	3.9980	2.9921	173.1	0.042330	
CERALLOY 147-3	CERADYNE/UDRI/2	UDRIPKGN0V89	AIR	9	1400	271.8	4.0030	2.9896	228.2	0.042330	
CERALLOY 147-3	CERADYNE/UDRI/2	UDRIPKGN0V89	AIR	10	1400	227.3	3.9980	2.9845	191.7	0.042330	
CERALLOY 147-3	CERADYNE/UDRI/2	UDRIPKGN0V89	AIR	21	1400	177.0	3.9954	2.9896	148.9	0.000423	
CERALLOY 147-3	CERADYNE/UDRI/2	UDRIPKGN0V89	AIR	22	1400	151.2	4.0005	2.9820	127.6	0.000423	
CERALLOY 147-3	CERADYNE/UDRI/2	UDRIPKGN0V89	AIR	23	1400	185.0	3.9980	2.9870	155.8	0.000423	
CERALLOY 147-3	CERADYNE/UDRI/2	UDRIPKGN0V89	AIR	24	1400	183.3	4.0005	2.9870	153.8	0.000423	
CERALLOY 147-3	CERADYNE/UDRI/2	UDRIPKGN0V89	AIR	25	1400	171.7	3.9980	2.9845	144.8	0.000423	
EC-152	NGK/UDRI/2	UDRIPKGN0V89	AIR	1	1000	987.5	4.0200	3.0300	803.0	0.04	
EC-152	NGK/UDRI/2	UDRIPKGN0V89	AIR	2	1000	1178.7	4.0100	3.0200	968.0	0.04	
EC-152	NGK/UDRI/2	UDRIPKGN0V89	AIR	3	1000	956.3	4.0200	3.0300	777.0	0.04	
EC-152	NGK/UDRI/2	UDRIPKGN0V89	AIR	4	1000	969.7	4.0200	3.0300	787.0	0.04	
EC-152	NGK/UDRI/2	UDRIPKGN0V89	AIR	5	1000	831.8	4.0200	3.0300	678.0	0.04	

SECTION 5. MOR 4-POINT BEND TEST RESULTS, continued

MATERIAL	BATCH CODE	REFERENCE CODE	TEST ENVIRON.	SPEC. No.	TEMP °C	LOAD N	WIDTH mm	THICK mm	BEND STRENGTH MPa	X-HEAD SPEED mm/s	COMMENTS
EC-152	NGK/UDRI/2	UDRI PKG NOV89	AIR	6	1000	1169.8	4.0200	3.0200	958.0	0.04	
EC-152	NGK/UDRI/2	UDRI PKG NOV89	AIR	7	1000	1018.6	4.0200	3.0100	836.0	0.04	
EC-152	NGK/UDRI/2	UDRI PKG NOV89	AIR	8	1000	1187.6	4.0200	3.0300	970.0	0.04	
EC-152	NGK/UDRI/2	UDRI PKG NOV89	AIR	9	1000	1120.9	4.0100	3.0300	911.0	0.04	
EC-152	NGK/UDRI/2	UDRI PKG NOV89	AIR	10	1000	898.5	4.0100	3.0200	738.0	0.04	
EC-152	NGK/UDRI/2	UDRI PKG NOV89	AIR	40	1000	987.5	4.0100	3.0100	813.0	0.0004233	
EC-152	NGK/UDRI/2	UDRI PKG NOV89	AIR	41	1000	911.8	4.0200	3.0200	747.0	0.0004233	
EC-152	NGK/UDRI/2	UDRI PKG NOV89	AIR	42	1000	987.5	4.0200	3.0400	798.0	0.0004233	
EC-152	NGK/UDRI/2	UDRI PKG NOV89	AIR	43	1000	1023.0	4.0300	3.0300	829.0	0.0004233	
EC-152	NGK/UDRI/2	UDRI PKG NOV89	AIR	44	1000	943.0	4.0200	3.0400	762.0	0.0004233	
EC-152	NGK/UDRI/2	UDRI PKG NOV89	AIR	45	1000	947.4	4.0300	3.0200	774.0	0.0004233	
EC-152	NGK/UDRI/2	UDRI PKG NOV89	AIR	46	1000	929.6	4.0100	3.0400	751.0	0.0004233	
EC-152	NGK/UDRI/2	UDRI PKG NOV89	AIR	47	1000	1054.2	4.0100	3.0300	861.0	0.0004233	
EC-152	NGK/UDRI/2	UDRI PKG NOV89	AIR	48	1000	733.9	4.0100	3.0200	603.0	0.0004233	
EC-152	NGK/UDRI/2	UDRI PKG NOV89	AIR	49	1000	898.5	4.0200	3.0200	737.0	0.0004233	
EC-152	NGK/UDRI/2	UDRI PKG NOV89	AIR	19	1200	1014.1	4.0100	3.0300	828.0	0.04	
EC-152	NGK/UDRI/2	UDRI PKG NOV89	AIR	20	1200	1005.3	4.0100	3.0200	826.0	0.04	
EC-152	NGK/UDRI/2	UDRI PKG NOV89	AIR	21	1200	1031.9	4.0100	3.0200	847.0	0.04	
EC-152	NGK/UDRI/2	UDRI PKG NOV89	AIR	22	1200	1008.7	4.0200	3.0200	825.0	0.04	
EC-152	NGK/UDRI/2	UDRI PKG NOV89	AIR	23	1200	947.4	4.0100	3.0300	771.0	0.04	
EC-152	NGK/UDRI/2	UDRI PKG NOV89	AIR	24	1200	1089.8	4.0200	3.0200	894.0	0.04	
EC-152	NGK/UDRI/2	UDRI PKG NOV89	AIR	25	1200	1031.9	4.0200	3.0200	845.0	0.04	
EC-152	NGK/UDRI/2	UDRI PKG NOV89	AIR	26	1200	1014.1	4.0100	3.0200	833.0	0.04	
EC-152	NGK/UDRI/2	UDRI PKG NOV89	AIR	27	1200	943.0	4.0100	3.0100	778.0	0.04	
EC-152	NGK/UDRI/2	UDRI PKG NOV89	AIR	28	1200	978.6	4.0100	3.0100	807.0	0.04	
EC-152	NGK/UDRI/2	UDRI PKG NOV89	AIR	29	1200	827.3	4.0100	3.0100	680.0	0.0004233	
EC-152	NGK/UDRI/2	UDRI PKG NOV89	AIR	30	1200	683.9	4.0000	3.0100	572.0	0.0004233	
EC-152	NGK/UDRI/2	UDRI PKG NOV89	AIR	31	1200	800.6	4.0100	3.0200	655.0	0.0004233	
EC-152	NGK/UDRI/2	UDRI PKG NOV89	AIR	32	1200	716.1	4.0100	3.0100	589.0	0.0004233	
EC-152	NGK/UDRI/2	UDRI PKG NOV89	AIR	33	1200	733.9	4.0100	3.0300	600.0	0.0004233	
EC-152	NGK/UDRI/2	UDRI PKG NOV89	AIR	34	1200	725.0	4.0100	3.0500	584.0	0.0004233	
EC-152	NGK/UDRI/2	UDRI PKG NOV89	AIR	35	1200	765.1	4.0100	3.0300	626.0	0.0004233	
EC-152	NGK/UDRI/2	UDRI PKG NOV89	AIR	36	1200	716.1	4.0100	3.0300	586.0	0.0004233	

SECTION 5. MOR 4-POINT BEND TEST RESULTS, continued

MATERIAL	BATCH CODE	REFERENCE CODE	TEST ENVIRON.	SPEC. No.	TEMP °C	LOAD N	WIDTH mm	THICK mm	BEND STRENGTH MPa	X-HEAD SPEED mm/s	COMMENTS
EC-152	NGKJUDRI/2	UDRIPKGN0V89	AIR	37	1200	751.7	4.0200	3.0200	615.0	0.0004233	
EC-152	NGKJUDRI/2	UDRIPKGN0V89	AIR	38	1200	720.6	4.0100	3.0100	594.0	0.0004233	
EC-152	NGKJUDRI/2	UDRIPKGN0V89	AIR	11	1400	431.5	4.0200	3.0200	353.0	0.04	Width and thickness used for the MOR calc. are averages of 10 unoxid. specimens.
EC-152	NGKJUDRI/2	UDRIPKGN0V89	AIR	12	1400	475.9	4.0200	3.0200	389.0	0.04	
EC-152	NGKJUDRI/2	UDRIPKGN0V89	AIR	13	1400	422.6	4.0200	3.0200	346.0	0.04	
EC-152	NGKJUDRI/2	UDRIPKGN0V89	AIR	14	1400	449.3	4.0200	3.0200	367.0	0.04	See note above.
EC-152	NGKJUDRI/2	UDRIPKGN0V89	AIR	15	1400	600.5	4.0200	3.0200	491.0	0.04	See note above.
EC-152	NGKJUDRI/2	UDRIPKGN0V89	AIR	18	1400	400.3	4.0200	3.0200	211.0	0.0004233	See note above.
GTE PY6	GTELJUDRI/2	UDRIPKGN0V89	AIR	71	21	956.3	4.0056	3.0074	792.0	0.042330	
GTE PY6	GTELJUDRI/2	UDRIPKGN0V89	AIR	72	21	1054.2	3.9980	2.9997	879.0	0.042330	
GTE PY6	GTELJUDRI/2	UDRIPKGN0V89	AIR	73	21	978.6	4.0056	3.0069	809.0	0.042330	
GTE PY6	GTELJUDRI/2	UDRIPKGN0V89	AIR	74	21	1128.8	3.9980	2.9997	942.0	0.042330	
GTE PY6	GTELJUDRI/2	UDRIPKGN0V89	AIR	75	21	898.5	3.9929	3.0048	748.0	0.042330	
GTE PY6	GTELJUDRI/2	UDRIPKGN0V89	AIR	76	21	1174.3	3.9929	2.9921	986.0	0.042330	
GTE PY6	GTELJUDRI/2	UDRIPKGN0V89	AIR	77	21	1134.2	3.9927	2.9896	956.0	0.042330	
GTE PY6	GTELJUDRI/2	UDRIPKGN0V89	AIR	78	21	1049.7	3.9929	3.0023	875.0	0.042330	
GTE PY6	GTELJUDRI/2	UDRIPKGN0V89	AIR	79	21	1080.9	4.0056	3.0023	898.0	0.042330	
GTE PY6	GTELJUDRI/2	UDRIPKGN0V89	AIR	80	21	898.5	4.0030	3.0074	745.0	0.042330	
GTE PY6	GTELJUDRI/2	UDRIPKGN0V89	AIR	111	1000	858.5	3.9980	2.9997	716.0	0.042330	
GTE PY6	GTELJUDRI/2	UDRIPKGN0V89	AIR	112	1000	849.6	4.0030	2.9972	709.0	0.042330	
GTE PY6	GTELJUDRI/2	UDRIPKGN0V89	AIR	113	1000	876.3	3.9954	2.9921	735.0	0.042330	
GTE PY6	GTELJUDRI/2	UDRIPKGN0V89	AIR	114	1000	782.9	3.9980	2.9947	655.0	0.042330	
GTE PY6	GTELJUDRI/2	UDRIPKGN0V89	AIR	115	1000	894.1	3.9929	2.9870	753.0	0.042330	
GTE PY6	GTELJUDRI/2	UDRIPKGN0V89	AIR	116	1000	951.9	3.9980	2.9972	795.0	0.042330	
GTE PY6	GTELJUDRI/2	UDRIPKGN0V89	AIR	117	1000	956.3	3.9827	2.9845	809.0	0.042330	
GTE PY6	GTELJUDRI/2	UDRIPKGN0V89	AIR	118	1000	876.3	3.9827	3.0023	732.0	0.042330	1 lower pt failed during test.
GTE PY6	GTELJUDRI/2	UDRIPKGN0V89	AIR	119	1000	862.9	3.9980	2.9921	723.0	0.042330	
GTE PY6	GTELJUDRI/2	UDRIPKGN0V89	AIR	120	1000	876.3	3.9954	2.9972	732.0	0.042330	
GTE PY6	GTELJUDRI/2	UDRIPKGN0V89	AIR	91	1000	769.5	3.9954	2.9972	643.0	0.004233	
GTE PY6	GTELJUDRI/2	UDRIPKGN0V89	AIR	92	1000	676.1	3.9929	3.0023	564.0	0.004233	
GTE PY6	GTELJUDRI/2	UDRIPKGN0V89	AIR	93	1000	756.2	3.9929	2.9972	632.0	0.004233	
GTE PY6	GTELJUDRI/2	UDRIPKGN0V89	AIR	94	1000	1005.3	4.0030	3.0099	832.0	0.004233	

SECTION 5. MOR 4-POINT BEND TEST RESULTS, continued

MATERIAL	BATCH CODE	REFERENCE CODE	TEST ENVIRON.	SPEC. No.	TEMP °C	LOAD N	WIDTH mm	THICK mm	BEND STRENGTH MPa	X-HEAD SPEED mm/s	COMMENTS
GTE PY6	GTEL/JDR/2	UDRIPKGNV89	AIR	95	1000	916.3	3.9954	2.9972	766.0	0.004233	
GTE PY6	GTEL/JDR/2	UDRIPKGNV89	AIR	96	1000	831.8	3.9954	2.9997	694.0	0.004233	
GTE PY6	GTEL/JDR/2	UDRIPKGNV89	AIR	97	1000	786.2	3.9929	2.9997	665.0	0.004233	
GTE PY6	GTEL/JDR/2	UDRIPKGNV89	AIR	98	1000	876.3	3.9929	2.9972	733.0	0.004233	
GTE PY6	GTEL/JDR/2	UDRIPKGNV89	AIR	99	1000	818.4	3.9954	3.0124	677.0	0.004233	
GTE PY6	GTEL/JDR/2	UDRIPKGNV89	AIR	100	1000	925.2	4.0030	2.9997	771.0	0.004233	
GTE PY6	GTEL/JDR/2	UDRIPKGNV89	AIR	101	1000	800.6	3.9878	2.9870	675.0	0.00423	
GTE PY6	GTEL/JDR/2	UDRIPKGNV89	AIR	102	1000	831.8	3.9954	2.9896	699.0	0.00423	
GTE PY6	GTEL/JDR/2	UDRIPKGNV89	AIR	103	1000	782.9	3.9954	2.9972	654.0	0.00423	
GTE PY6	GTEL/JDR/2	UDRIPKGNV89	AIR	104	1000	800.6	4.0005	2.9921	671.0	0.00423	
GTE PY6	GTEL/JDR/2	UDRIPKGNV89	AIR	105	1000	849.6	3.9903	2.9997	710.0	0.00423	
GTE PY6	GTEL/JDR/2	UDRIPKGNV89	AIR	106	1000	836.2	3.9929	2.9947	701.0	0.00423	
GTE PY6	GTEL/JDR/2	UDRIPKGNV89	AIR	107	1000	818.4	3.9878	2.9921	688.0	0.00423	
GTE PY6	GTEL/JDR/2	UDRIPKGNV89	AIR	108	1000	859.5	3.9980	3.0074	712.0	0.00423	
GTE PY6	GTEL/JDR/2	UDRIPKGNV89	AIR	109	1000	849.6	3.9929	2.9972	711.0	0.00423	
GTE PY6	GTEL/JDR/2	UDRIPKGNV89	AIR	110	1000	827.3	3.9980	3.0124	684.0	0.00423	
GTE PY6	GTEL/JDR/2	UDRIPKGNV89	AIR	41	1200	831.8	3.9929	2.9972	696.0	0.042330	
GTE PY6	GTEL/JDR/2	UDRIPKGNV89	AIR	42	1200	840.7	3.9980	3.0023	700.0	0.042330	
GTE PY6	GTEL/JDR/2	UDRIPKGNV89	AIR	43	1200	751.7	3.9853	2.9972	630.0	0.042330	
GTE PY6	GTEL/JDR/2	UDRIPKGNV89	AIR	44	1200	845.1	3.9929	3.0124	700.0	0.042330	
GTE PY6	GTEL/JDR/2	UDRIPKGNV89	AIR	45	1200	840.7	4.0005	3.0048	698.0	0.042330	
GTE PY6	GTEL/JDR/2	UDRIPKGNV89	AIR	46	1200	849.6	4.0107	3.0099	702.0	0.042330	
GTE PY6	GTEL/JDR/2	UDRIPKGNV89	AIR	47	1200	791.7	3.9980	3.0124	655.0	0.042330	
GTE PY6	GTEL/JDR/2	UDRIPKGNV89	AIR	48	1200	840.7	4.0081	3.0201	690.0	0.042330	
GTE PY6	GTEL/JDR/2	UDRIPKGNV89	AIR	49	1200	751.7	4.0056	3.0150	619.0	0.042330	
GTE PY6	GTEL/JDR/2	UDRIPKGNV89	AIR	50	1200	689.4	4.0107	3.0175	566.0	0.042330	
GTE PY6	GTEL/JDR/2	UDRIPKGNV89	AIR	81	1200	791.7	3.9853	2.9921	686.0	0.004233	
GTE PY6	GTEL/JDR/2	UDRIPKGNV89	AIR	82	1200	774.0	3.9903	3.0074	643.0	0.004233	
GTE PY6	GTEL/JDR/2	UDRIPKGNV89	AIR	83	1200	725.0	3.9878	3.0048	604.0	0.004233	
GTE PY6	GTEL/JDR/2	UDRIPKGNV89	AIR	84	1200	733.9	3.9878	3.0074	611.0	0.004233	
GTE PY6	GTEL/JDR/2	UDRIPKGNV89	AIR	85	1200	689.4	3.9903	2.9972	577.0	0.004233	
GTE PY6	GTEL/JDR/2	UDRIPKGNV89	AIR	86	1200	707.2	3.9903	3.0074	598.0	0.004233	
GTE PY6	GTEL/JDR/2	UDRIPKGNV89	AIR	87	1200	738.4	3.9878	2.9921	620.0	0.004233	

SECTION 5. MOR 4-POINT BEND TEST RESULTS, continued

MATERIAL	BATCH CODE	REFERENCE CODE	TEST ENVIRON.	SPEC. No.	TEMP °C	LOAD N	WIDTH mm	THICK mm	BEND STRENGTH MPa	X-HEAD SPEED mm/s	COMMENTS
GTE PY6	GTELAUDRI/2	UDRIKPGNOV88	AIR	88	1200	707.2	4.0056	3.0074	596.0	0.004233	
GTE PY6	GTELAUDRI/2	UDRIKPGNOV88	AIR	89	1200	800.6	3.9878	3.0150	663.0	0.004233	
GTE PY6	GTELAUDRI/2	UDRIKPGNOV88	AIR	90	1200	765.1	3.9929	3.0150	632.0	0.004233	
GTE PY6	GTELAUDRI/2	UDRIKPGNOV88	AIR	51	1200	676.1	4.0081	3.0124	558.0	0.000423	
GTE PY6	GTELAUDRI/2	UDRIKPGNOV88	AIR	52	1200	707.2	4.0030	2.9997	589.0	0.000423	
GTE PY6	GTELAUDRI/2	UDRIKPGNOV88	AIR	53	1200	751.7	4.0132	2.9972	626.0	0.000423	
GTE PY6	GTELAUDRI/2	UDRIKPGNOV88	AIR	54	1200	667.2	4.0081	3.0074	552.0	0.000423	
GTE PY6	GTELAUDRI/2	UDRIKPGNOV88	AIR	55	1200	698.3	4.0081	3.0124	576.0	0.000423	
GTE PY6	GTELAUDRI/2	UDRIKPGNOV88	AIR	56	1200	582.7	4.0030	3.0353	474.0	0.000423	
GTE PY6	GTELAUDRI/2	UDRIKPGNOV88	AIR	57	1200	711.7	3.9954	3.0023	593.0	0.000423	
GTE PY6	GTELAUDRI/2	UDRIKPGNOV88	AIR	58	1200	671.7	3.9980	3.0023	559.0	0.000423	
GTE PY6	GTELAUDRI/2	UDRIKPGNOV88	AIR	59	1200	711.7	4.0056	3.0251	582.0	0.000423	
GTE PY6	GTELAUDRI/2	UDRIKPGNOV88	AIR	60	1200	756.2	4.0005	3.0074	627.0	0.000423	
GTE PY6	GTELAUDRI/2	UDRIKPGNOV88	AIR	11	1400	609.4	3.9980	3.0251	500.0	0.042330	
GTE PY6	GTELAUDRI/2	UDRIKPGNOV88	AIR	12	1400	609.4	3.9980	3.0302	498.0	0.042330	
GTE PY6	GTELAUDRI/2	UDRIKPGNOV88	AIR	13	1400	582.7	3.9954	3.0277	477.0	0.042330	
GTE PY6	GTELAUDRI/2	UDRIKPGNOV88	AIR	14	1400	538.2	3.9980	3.0251	441.0	0.042330	
GTE PY6	GTELAUDRI/2	UDRIKPGNOV88	AIR	15	1400	645.0	4.0030	3.0455	521.0	0.042330	
GTE PY6	GTELAUDRI/2	UDRIKPGNOV88	AIR	16	1400	573.8	3.9980	3.0150	474.0	0.042330	
GTE PY6	GTELAUDRI/2	UDRIKPGNOV88	AIR	17	1400	596.0	4.0056	3.0099	493.0	0.042330	
GTE PY6	GTELAUDRI/2	UDRIKPGNOV88	AIR	18	1400	645.0	3.9980	3.0201	531.0	0.042330	
GTE PY6	GTELAUDRI/2	UDRIKPGNOV88	AIR	19	1400	680.5	4.0081	3.0328	554.0	0.042330	
GTE PY6	GTELAUDRI/2	UDRIKPGNOV88	AIR	20	1400	533.8	3.9954	3.0048	444.0	0.042330	
GTE PY6	GTELAUDRI/2	UDRIKPGNOV88	AIR	31	1400	342.5	4.0132	3.0251	280.0	0.004233	
GTE PY6	GTELAUDRI/2	UDRIKPGNOV88	AIR	32	1400	462.6	4.0208	3.0048	382.0	0.004233	
GTE PY6	GTELAUDRI/2	UDRIKPGNOV88	AIR	33	1400	458.1	4.0005	3.0201	377.0	0.004233	
GTE PY6	GTELAUDRI/2	UDRIKPGNOV88	AIR	34	1400	355.8	4.0030	3.0150	293.0	0.004233	
GTE PY6	GTELAUDRI/2	UDRIKPGNOV88	AIR	35	1400	409.2	3.9903	2.9921	344.0	0.004233	
GTE PY6	GTELAUDRI/2	UDRIKPGNOV88	AIR	36	1400	404.8	3.9980	3.0099	335.0	0.004233	
GTE PY6	GTELAUDRI/2	UDRIKPGNOV88	AIR	37	1400	404.8	3.9954	3.0150	334.0	0.004233	
GTE PY6	GTELAUDRI/2	UDRIKPGNOV88	AIR	38	1400	467.0	4.0081	3.0099	386.0	0.004233	
GTE PY6	GTELAUDRI/2	UDRIKPGNOV88	AIR	39	1400	458.1	3.9980	2.9987	382.0	0.004233	
GTE PY6	GTELAUDRI/2	UDRIKPGNOV88	AIR	40	1400	475.9	4.0081	3.0099	393.0	0.004233	

SECTION 5. MOR 4-POINT BEND TEST RESULTS, continued

MATERIAL	BATCH CODE	REFERENCE CODE	TEST ENVIRON.	SPEC. No.	TEMP °C	LOAD N	WIDTH mm	THICK mm	BEND STRENGTH MPa	X-HEAD SPEED mm/s	COMMENTS
GTE PY6	GTEL/UDRI/2	UDRIPKGN0V89	AIR	21	1400	324.7	3.9980	3.0023	270.0	0.000423	
GTE PY6	GTEL/UDRI/2	UDRIPKGN0V89	AIR	22	1400	407.0	3.9980	3.0023	339.0	0.000423	
GTE PY6	GTEL/UDRI/2	UDRIPKGN0V89	AIR	23	1400	396.3	4.0081	3.0175	326.0	0.000423	
GTE PY6	GTEL/UDRI/2	UDRIPKGN0V89	AIR	24	1400	399.9	3.9954	3.0074	332.0	0.000423	
GTE PY6	GTEL/UDRI/2	UDRIPKGN0V89	AIR	25	1400	329.2	4.0005	2.9872	275.0	0.000423	
GTE PY6	GTEL/UDRI/2	UDRIPKGN0V89	AIR	26	1400	355.8	4.0030	3.0048	295.0	0.000423	
GTE PY6	GTEL/UDRI/2	UDRIPKGN0V89	AIR	27	1400	386.1	4.0030	3.0099	319.0	0.000423	
GTE PY6	GTEL/UDRI/2	UDRIPKGN0V89	AIR	28	1400	397.7	4.0030	3.0048	330.0	0.000423	
GTE PY6	GTEL/UDRI/2	UDRIPKGN0V89	AIR	29	1400	335.4	4.0411	3.0074	275.0	0.000423	
GTE PY6	GTEL/UDRI/2	UDRIPKGN0V89	AIR	30	1400	383.9	3.9980	2.9896	327.0	0.000423	
NT-154	NORTON/UDRI/2	UDRIPKGN0V89	AIR	1	21	898.5	3.9878	2.9870	758.0	0.042330	
NT-154	NORTON/UDRI/2	UDRIPKGN0V89	AIR	2	21	1160.9	3.9853	2.9845	981.0	0.042330	
NT-154	NORTON/UDRI/2	UDRIPKGN0V89	AIR	3	21	1147.6	3.9853	2.9870	968.0	0.042330	
NT-154	NORTON/UDRI/2	UDRIPKGN0V89	AIR	4	21	1009.7	3.9853	2.9870	852.0	0.042330	
NT-154	NORTON/UDRI/2	UDRIPKGN0V89	AIR	5	21	1120.9	3.9853	2.9870	946.0	0.042330	
NT-154	NORTON/UDRI/2	UDRIPKGN0V89	AIR	6	21	1201.0	3.9878	2.9921	1009.0	0.042330	
NT-154	NORTON/UDRI/2	UDRIPKGN0V89	AIR	7	21	1000.8	3.9878	2.9870	844.0	0.042330	
NT-154	NORTON/UDRI/2	UDRIPKGN0V89	AIR	8	21	1103.1	3.9853	2.9845	932.0	0.042330	
NT-154	NORTON/UDRI/2	UDRIPKGN0V89	AIR	9	21	1103.1	3.9853	2.9870	931.0	0.042330	
NT-154	NORTON/UDRI/2	UDRIPKGN0V89	AIR	10	21	1005.3	3.9878	2.9921	845.0	0.042330	
NT-154	NORTON/UDRI/2	UDRIPKGN0V89	AIR	91	21	943.0	4.0005	2.9921	790.0	0.000423	
NT-154	NORTON/UDRI/2	UDRIPKGN0V89	AIR	92	21	907.4	3.9980	2.9947	759.0	0.000423	
NT-154	NORTON/UDRI/2	UDRIPKGN0V89	AIR	93	21	831.8	4.0005	2.9896	698.0	0.000423	
NT-154	NORTON/UDRI/2	UDRIPKGN0V89	AIR	94	21	827.3	4.0035	2.9896	694.0	0.000423	
NT-154	NORTON/UDRI/2	UDRIPKGN0V89	AIR	95	21	965.2	4.0081	2.9947	806.0	0.000423	
NT-154	NORTON/UDRI/2	UDRIPKGN0V89	AIR	61	1000	1000.8	3.9990	2.9870	842.0	0.042330	
NT-154	NORTON/UDRI/2	UDRIPKGN0V89	AIR	62	1000	876.3	4.0005	2.9896	735.0	0.042330	
NT-154	NORTON/UDRI/2	UDRIPKGN0V89	AIR	63	1000	938.5	4.0030	2.9921	786.0	0.042330	
NT-154	NORTON/UDRI/2	UDRIPKGN0V89	AIR	64	1000	911.8	4.0005	2.9896	765.0	0.042330	
NT-154	NORTON/UDRI/2	UDRIPKGN0V89	AIR	65	1000	898.5	4.0030	3.0023	747.0	0.042330	
NT-154	NORTON/UDRI/2	UDRIPKGN0V89	AIR	66	1000	965.2	4.0081	2.9947	806.0	0.042330	
NT-154	NORTON/UDRI/2	UDRIPKGN0V89	AIR	67	1000	636.1	4.0030	2.9997	530.0	0.042330	

SECTION 5. MOR 4-POINT BEND TEST RESULTS, continued

MATERIAL	BATCH CODE	REFERENCE CODE	TEST ENVIRON.	SPEC. No.	TEMP °C	LOAD N	WIDTH mm	THICK mm	BEND STRENGTH MPa	X-HEAD SPEED mm/s	COMMENTS
NT-154	NORTON/UDRI/2	UDRIKGNV89	AIR	68	1000	876.3	4.0005	2.9921	734.0	0.042330	
NT-154	NORTON/UDRI/2	UDRIKGNV89	AIR	69	1000	809.5	4.0005	2.9921	678.0	0.042330	
NT-154	NORTON/UDRI/2	UDRIKGNV89	AIR	70	1000	938.5	4.0030	2.9947	784.0	0.042330	
NT-154	NORTON/UDRI/2	UDRIKGNV89	AIR	41	1000	947.4	3.9878	2.9896	798.0	0.000423	
NT-154	NORTON/UDRI/2	UDRIKGNV89	AIR	42	1000	969.7	3.9853	2.9845	820.0	0.000423	
NT-154	NORTON/UDRI/2	UDRIKGNV89	AIR	43	1000	858.5	3.9853	2.9870	724.0	0.000423	
NT-154	NORTON/UDRI/2	UDRIKGNV89	AIR	44	1000	907.4	3.9929	2.9947	760.0	0.000423	
NT-154	NORTON/UDRI/2	UDRIKGNV89	AIR	45	1000	978.6	3.9878	2.9921	822.0	0.000423	
NT-154	NORTON/UDRI/2	UDRIKGNV89	AIR	46	1000	947.4	3.9827	2.9845	801.0	0.000423	
NT-154	NORTON/UDRI/2	UDRIKGNV89	AIR	47	1000	960.8	4.0030	2.9896	806.0	0.000423	
NT-154	NORTON/UDRI/2	UDRIKGNV89	AIR	48	1000	956.3	3.9827	2.9845	809.0	0.000423	
NT-154	NORTON/UDRI/2	UDRIKGNV89	AIR	49	1000	974.1	3.9827	2.9947	818.0	0.000423	
NT-154	NORTON/UDRI/2	UDRIKGNV89	AIR	50	1000	889.6	4.0005	2.9997	741.0	0.000423	
NT-154	NORTON/UDRI/2	UDRIKGNV89	AIR	81	1200	858.5	4.0030	2.9947	717.0	0.042330	
NT-154	NORTON/UDRI/2	UDRIKGNV89	AIR	82	1200	858.5	4.0005	2.9921	719.0	0.042330	
NT-154	NORTON/UDRI/2	UDRIKGNV89	AIR	83	1200	898.5	4.0107	2.9947	749.0	0.042330	
NT-154	NORTON/UDRI/2	UDRIKGNV89	AIR	84	1200	867.4	4.0030	2.9921	726.0	0.042330	
NT-154	NORTON/UDRI/2	UDRIKGNV89	AIR	85	1200	791.7	4.0030	2.9997	659.0	0.042330	
NT-154	NORTON/UDRI/2	UDRIKGNV89	AIR	86	1200	782.9	4.0005	2.9972	654.0	0.042330	
NT-154	NORTON/UDRI/2	UDRIKGNV89	AIR	87	1200	747.3	4.0107	2.9921	624.0	0.042330	
NT-154	NORTON/UDRI/2	UDRIKGNV89	AIR	88	1200	858.5	3.9980	2.9870	722.0	0.042330	
NT-154	NORTON/UDRI/2	UDRIKGNV89	AIR	89	1200	716.1	4.0005	2.9870	602.0	0.042330	
NT-154	NORTON/UDRI/2	UDRIKGNV89	AIR	90	1200	822.9	4.0005	2.9896	690.0	0.042330	
NT-154	NORTON/UDRI/2	UDRIKGNV89	AIR	71	1200	720.6	4.0030	2.9820	607.0	0.000423	
NT-154	NORTON/UDRI/2	UDRIKGNV89	AIR	72	1200	756.2	4.0005	2.9870	636.0	0.000423	
NT-154	NORTON/UDRI/2	UDRIKGNV89	AIR	73	1200	765.1	4.0005	2.9972	639.0	0.000423	
NT-154	NORTON/UDRI/2	UDRIKGNV89	AIR	74	1200	720.6	4.0056	2.9947	602.0	0.000423	
NT-154	NORTON/UDRI/2	UDRIKGNV89	AIR	75	1200	747.3	4.0081	2.9997	622.0	0.000423	
NT-154	NORTON/UDRI/2	UDRIKGNV89	AIR	76	1200	725.0	4.0081	2.9947	605.0	0.000423	
NT-154	NORTON/UDRI/2	UDRIKGNV89	AIR	77	1200	685.0	4.0056	2.9997	570.0	0.000423	
NT-154	NORTON/UDRI/2	UDRIKGNV89	AIR	78	1200	689.4	4.0081	2.9947	575.0	0.000423	
NT-154	NORTON/UDRI/2	UDRIKGNV89	AIR	79	1200	822.9	4.0030	2.9972	687.0	0.000423	
NT-154	NORTON/UDRI/2	UDRIKGNV89	AIR	80	1200	814.0	4.0030	2.9847	680.0	0.000423	

SECTION 5. MOR 4-POINT BEND TEST RESULTS, continued

MATERIAL	BATCH CODE	REFERENCE CODE	TEST ENVIRON.	SPEC. No.	TEMP °C	LOAD N	WIDTH mm	THICK mm	BEND STRENGTH MPa	X-HEAD SPEED mm/s	COMMENTS
NT-154	NORTON/UDRI/2	UDRIPKGNV89	AIR	11	1400	698.3	3.9929	2.9972	584.0	0.042330	
NT-154	NORTON/UDRI/2	UDRIPKGNV89	AIR	12	1400	756.2	3.9980	2.9987	631.0	0.042330	
NT-154	NORTON/UDRI/2	UDRIPKGNV89	AIR	13	1400	796.2	3.9954	3.0074	661.0	0.042330	
NT-154	NORTON/UDRI/2	UDRIPKGNV89	AIR	14	1400	685.0	3.9954	3.0175	565.0	0.042330	
NT-154	NORTON/UDRI/2	UDRIPKGNV89	AIR	15	1400	768.5	4.0030	3.0074	638.0	0.042330	
NT-154	NORTON/UDRI/2	UDRIPKGNV89	AIR	16	1400	707.2	3.9980	3.0175	583.0	0.042330	
NT-154	NORTON/UDRI/2	UDRIPKGNV89	AIR	17	1400	738.4	3.9929	3.0099	612.0	0.042330	
NT-154	NORTON/UDRI/2	UDRIPKGNV89	AIR	18	1400	716.1	4.0005	3.0023	596.0	0.042330	
NT-154	NORTON/UDRI/2	UDRIPKGNV89	AIR	19	1400	716.1	3.9853	2.9896	603.0	0.042330	
NT-154	NORTON/UDRI/2	UDRIPKGNV89	AIR	20	1400	756.2	3.9929	3.0023	630.0	0.042330	
NT-154	NORTON/UDRI/2	UDRIPKGNV89	AIR	21	1400	422.6	3.9903	2.9896	355.0	0.000423	
NT-154	NORTON/UDRI/2	UDRIPKGNV89	AIR	22	1400	418.1	3.9929	2.9947	350.0	0.000423	
NT-154	NORTON/UDRI/2	UDRIPKGNV89	AIR	23	1400	502.6	4.0005	3.0124	415.0	0.000423	
NT-154	NORTON/UDRI/2	UDRIPKGNV89	AIR	24	1400	502.6	3.9954	2.9997	419.0	0.000423	
NT-154	NORTON/UDRI/2	UDRIPKGNV89	AIR	25	1400	484.8	3.9954	3.0048	403.0	0.000423	
NT-154	NORTON/UDRI/2	UDRIPKGNV89	AIR	26	1400	538.2	3.9954	2.9972	450.0	0.000423	
NT-154	NORTON/UDRI/2	UDRIPKGNV89	AIR	27	1400	507.1	3.9929	2.9847	425.0	0.000423	
NT-154	NORTON/UDRI/2	UDRIPKGNV89	AIR	28	1400	333.6	4.0030	3.0074	276.0	0.000423	
NT-154	NORTON/UDRI/2	UDRIPKGNV89	AIR	29	1400	324.7	4.0005	2.9997	271.0	0.000423	
NT-154	NORTON/UDRI/2	UDRIPKGNV89	AIR	30	1400	329.2	4.0005	3.0023	274.0	0.000423	
SN-252	KYOCERA/UDRI/2	UDRIPKGNV89	AIR	11	1000	667.2	4.0000	3.0000	555.0	0.04	
SN-252	KYOCERA/UDRI/2	UDRIPKGNV89	AIR	12	1000	622.7	4.0100	3.0100	514.0	0.04	
SN-252	KYOCERA/UDRI/2	UDRIPKGNV89	AIR	13	1000	609.4	4.0000	3.0200	501.0	0.04	
SN-252	KYOCERA/UDRI/2	UDRIPKGNV89	AIR	14	1000	608.4	4.0100	3.0100	504.0	0.04	
SN-252	KYOCERA/UDRI/2	UDRIPKGNV89	AIR	15	1000	622.7	3.9900	3.0100	515.0	0.04	
SN-252	KYOCERA/UDRI/2	UDRIPKGNV89	AIR	16	1000	667.2	4.0000	3.0100	553.0	0.04	
SN-252	KYOCERA/UDRI/2	UDRIPKGNV89	AIR	17	1000	683.9	3.9800	3.0100	576.0	0.04	
SN-252	KYOCERA/UDRI/2	UDRIPKGNV89	AIR	18	1000	671.7	4.0100	3.0100	555.0	0.04	
SN-252	KYOCERA/UDRI/2	UDRIPKGNV89	AIR	19	1000	573.8	4.0000	3.0000	479.0	0.04	
SN-252	KYOCERA/UDRI/2	UDRIPKGNV89	AIR	20	1000	618.3	4.0100	3.0200	509.0	0.04	
SN-252	KYOCERA/UDRI/2	UDRIPKGNV89	AIR	1	1000	587.1	4.0000	3.0100	486.0	0.0004233	
SN-252	KYOCERA/UDRI/2	UDRIPKGNV89	AIR	2	1000	551.6	4.0100	3.0100	455.0	0.0004233	

SECTION 5. MOR 4-POINT BEND TEST RESULTS, continued

MATERIAL	BATCH CODE	REFERENCE CODE	TEST ENVIRON.	SPEC. No.	TEMP °C	LOAD N	WIDTH mm	THICK mm	BEND STRENGTH MPa	X-HEAD SPEED mm/s	COMMENTS
SN-252	KYOCERA/UDRI/2	UDRIKPGNOV89	AIR	3	1000	569.3	3.9900	2.9800	484.0	0.0004233	
SN-252	KYOCERA/UDRI/2	UDRIKPGNOV89	AIR	4	1000	609.0	4.0000	2.9900	510.0	0.0004233	
SN-252	KYOCERA/UDRI/2	UDRIKPGNOV89	AIR	5	1000	564.9	4.0000	3.0100	467.0	0.0004233	
SN-252	KYOCERA/UDRI/2	UDRIKPGNOV89	AIR	6	1000	556.0	3.9900	3.0100	461.0	0.0004233	
SN-252	KYOCERA/UDRI/2	UDRIKPGNOV89	AIR	7	1000	516.0	4.0100	3.0100	426.0	0.0004233	
SN-252	KYOCERA/UDRI/2	UDRIKPGNOV89	AIR	8	1000	533.8	4.0100	3.0200	438.0	0.0004233	
SN-252	KYOCERA/UDRI/2	UDRIKPGNOV89	AIR	9	1000	542.7	4.0100	3.0100	448.0	0.0004233	
SN-252	KYOCERA/UDRI/2	UDRIKPGNOV89	AIR	10	1000	587.1	4.0000	3.0000	489.0	0.0004233	
SN-252	KYOCERA/UDRI/2	UDRIKPGNOV89	AIR	41	1200	560.5	4.0100	3.0200	460.0	0.04	
SN-252	KYOCERA/UDRI/2	UDRIKPGNOV89	AIR	42	1200	662.8	3.9800	3.0100	549.0	0.04	
SN-252	KYOCERA/UDRI/2	UDRIKPGNOV89	AIR	43	1200	529.3	4.0000	3.0100	439.0	0.04	
SN-252	KYOCERA/UDRI/2	UDRIKPGNOV89	AIR	44	1200	604.9	3.9900	3.0100	501.0	0.04	
SN-252	KYOCERA/UDRI/2	UDRIKPGNOV89	AIR	45	1200	631.6	3.9900	3.0100	523.0	0.04	
SN-252	KYOCERA/UDRI/2	UDRIKPGNOV89	AIR	46	1200	524.9	3.9900	3.0000	438.0	0.04	
SN-252	KYOCERA/UDRI/2	UDRIKPGNOV89	AIR	47	1200	609.4	4.0000	3.0200	503.0	0.04	
SN-252	KYOCERA/UDRI/2	UDRIKPGNOV89	AIR	48	1200	560.5	4.0100	3.0100	464.0	0.04	
SN-252	KYOCERA/UDRI/2	UDRIKPGNOV89	AIR	49	1200	511.5	4.0000	3.0000	425.0	0.04	
SN-252	KYOCERA/UDRI/2	UDRIKPGNOV89	AIR	50	1200	489.3	4.0000	3.0300	401.0	0.0004233	
SN-252	KYOCERA/UDRI/2	UDRIKPGNOV89	AIR	51	1200	596.0	4.0000	3.0100	494.0	0.0004233	
SN-252	KYOCERA/UDRI/2	UDRIKPGNOV89	AIR	52	1200	627.2	4.0000	3.0100	518.0	0.0004233	
SN-252	KYOCERA/UDRI/2	UDRIKPGNOV89	AIR	53	1200	604.9	4.0000	3.0000	504.0	0.0004233	
SN-252	KYOCERA/UDRI/2	UDRIKPGNOV89	AIR	54	1200	591.6	3.9900	3.0100	491.0	0.0004233	
SN-252	KYOCERA/UDRI/2	UDRIKPGNOV89	AIR	55	1200	600.5	4.0000	3.0200	495.0	0.0004233	
SN-252	KYOCERA/UDRI/2	UDRIKPGNOV89	AIR	56	1200	564.9	4.0100	3.0000	470.0	0.0004233	
SN-252	KYOCERA/UDRI/2	UDRIKPGNOV89	AIR	57	1200	578.2	3.9900	3.0200	476.0	0.0004233	
SN-252	KYOCERA/UDRI/2	UDRIKPGNOV89	AIR	58	1200	573.8	3.9900	3.0200	473.0	0.0004233	
SN-252	KYOCERA/UDRI/2	UDRIKPGNOV89	AIR	59	1200	636.1	3.9900	3.0100	529.0	0.0004233	
SN-252	KYOCERA/UDRI/2	UDRIKPGNOV89	AIR	21	1400	564.9	4.0100	3.0100	467.0	0.04	
SN-252	KYOCERA/UDRI/2	UDRIKPGNOV89	AIR	22	1400	542.7	3.9900	3.0000	452.0	0.04	
SN-252	KYOCERA/UDRI/2	UDRIKPGNOV89	AIR	23	1400	520.4	3.9900	3.0100	431.0	0.04	
SN-252	KYOCERA/UDRI/2	UDRIKPGNOV89	AIR	24	1400	551.6	4.0000	3.0100	457.0	0.04	
SN-252	KYOCERA/UDRI/2	UDRIKPGNOV89	AIR	25	1400	604.9	3.9900	3.0000	506.0	0.04	
SN-252	KYOCERA/UDRI/2	UDRIKPGNOV89	AIR	26	1400	493.7	4.0200	3.0200	404.0	0.04	

SECTION 5. MOR 4-POINT BEND TEST RESULTS, continued

MATERIAL	BATCH CODE	REFERENCE CODE	TEST ENVIRON.	SPEC. No.	TEMP °C	LOAD N	WIDTH mm	THICK mm	BEND STRENGTH MPa	X-HEAD SPEED mm/s	COMMENTS
SN-252	KYOCERA/UDRI/2	UDRIIPKGN0V89	AIR	27	1400	578.2	4.0000	3.0000	491.0	0.04	
SN-252	KYOCERA/UDRI/2	UDRIIPKGN0V89	AIR	28	1400	556.0	4.0200	3.0200	456.0	0.04	
SN-252	KYOCERA/UDRI/2	UDRIIPKGN0V89	AIR	29	1400	591.6	4.0100	3.0100	499.0	0.04	
SN-252	KYOCERA/UDRI/2	UDRIIPKGN0V89	AIR	30	1400	542.7	4.0100	3.0100	449.0	0.04	
SN-252	KYOCERA/UDRI/2	UDRIIPKGN0V89	AIR	0	1400	520.4	3.9900	2.9900	438.0	0.0004233	
SN-252	KYOCERA/UDRI/2	UDRIIPKGN0V89	AIR	0	1400	649.4	4.0100	2.9900	543.0	0.0004233	
SN-252	KYOCERA/UDRI/2	UDRIIPKGN0V89	AIR	33	1400	613.8	4.0100	3.0100	508.0	0.0004233	
SN-252	KYOCERA/UDRI/2	UDRIIPKGN0V89	AIR	34	1400	587.1	3.9900	3.0300	482.0	0.0004233	
SN-252	KYOCERA/UDRI/2	UDRIIPKGN0V89	AIR	35	1400	640.5	4.0200	3.0200	525.0	0.0004233	
SN-252	KYOCERA/UDRI/2	UDRIIPKGN0V89	AIR	36	1400	578.2	4.0000	3.0000	482.0	0.0004233	
SN-252	KYOCERA/UDRI/2	UDRIIPKGN0V89	AIR	37	1400	591.6	4.0000	3.0000	482.0	0.0004233	
SN-252	KYOCERA/UDRI/2	UDRIIPKGN0V89	AIR	38	1400	582.7	4.0200	3.0100	481.0	0.0004233	
SN-252	KYOCERA/UDRI/2	UDRIIPKGN0V89	AIR	39	1400	618.3	4.0000	3.0200	507.0	0.0004233	
SN-252	KYOCERA/UDRI/2	UDRIIPKGN0V89	AIR	40	1400	627.2	3.9800	3.0100	520.0	0.0004233	
SN-4	HOWMET/UDRI/2	UDRIIPKGN0V89	AIR	6	20	2077.2	6.1595	3.0734	1020.0	0.042330	
SN-4	HOWMET/UDRI/2	UDRIIPKGN0V89	AIR	7	20	2010.5	6.1595	3.0759	986.0	0.042330	
SN-4	HOWMET/UDRI/2	UDRIIPKGN0V89	AIR	8	20	2072.8	6.1620	3.0912	1006.0	0.042330	
SN-4	HOWMET/UDRI/2	UDRIIPKGN0V89	AIR	9	20	2224.0	6.1620	3.0785	1088.0	0.042330	
SN-4	HOWMET/UDRI/2	UDRIIPKGN0V89	AIR	10	20	2090.6	6.1620	3.0759	1025.0	0.042330	
SN-4	HOWMET/UDRI/2	UDRIIPKGN0V89	AIR	11	20	2299.6	6.1595	3.0785	1126.0	0.042330	
SN-4	HOWMET/UDRI/2	UDRIIPKGN0V89	AIR	12	20	2224.0	6.1671	3.0759	1089.0	0.042330	
SN-4	HOWMET/UDRI/2	UDRIIPKGN0V89	AIR	13	20	1716.9	6.1620	3.0785	840.0	0.042330	
SN-4	HOWMET/UDRI/2	UDRIIPKGN0V89	AIR	14	20	1749.1	6.1620	3.0759	857.0	0.042330	
SN-4	HOWMET/UDRI/2	UDRIIPKGN0V89	AIR	15	20	1669.0	6.1595	3.0836	814.0	0.042330	
SN-4	HOWMET/UDRI/2	UDRIIPKGN0V89	AIR	16	20	1779.2	6.1620	3.0785	871.0	0.042330	
SN-4	HOWMET/UDRI/2	UDRIIPKGN0V89	AIR	17	20	2023.8	6.1646	3.0937	980.0	0.042330	
SN-4	HOWMET/UDRI/2	UDRIIPKGN0V89	AIR	18	20	2001.6	6.1620	3.0785	979.0	0.042330	
SN-4	HOWMET/UDRI/2	UDRIIPKGN0V89	AIR	19	20	2184.0	6.1620	3.0785	1069.0	0.042330	
SN-4	HOWMET/UDRI/2	UDRIIPKGN0V89	AIR	20	20	2246.2	6.1595	3.0759	1101.0	0.042330	
SN-4	HOWMET/UDRI/2	UDRIIPKGN0V89	AIR	64	20	2055.0	6.1595	3.0861	1001.0	0.042330	
SN-4	HOWMET/UDRI/2	UDRIIPKGN0V89	AIR	65	20	2072.8	6.1620	3.0937	1004.0	0.042330	
SN-4	HOWMET/UDRI/2	UDRIIPKGN0V89	AIR	66	20	2179.5	6.1620	3.0861	1061.0	0.042330	

SECTION 5. MOR 4-POINT BEND TEST RESULTS, continued

MATERIAL	BATCH	REFERENCE	TEST	SPEC.	TEMP	LOAD	WIDTH	THICK	BEND	X-HEAD	COMMENTS
	CODE	CODE	ENVIRON.	No.	°C	N	mm	mm	STRENGTH	SPEED	
									MPa	mm/s	
SN-4	HOWMET/UDRI/2	UDRIPKGNV89	AIR	68	20	1196.5	6.1620	3.0836	584.0	0.042330	
SN-4	HOWMET/UDRI/2	UDRIPKGNV89	AIR	69	20	2135.0	6.1595	3.0861	1040.0	0.042330	
SN-4	HOWMET/UDRI/2	UDRIPKGNV89	AIR	39	20	1450.1	4.1072	3.0937	1054.0	0.042330	
SN-4	HOWMET/UDRI/2	UDRIPKGNV89	AIR	40	20	1192.1	4.0845	3.0937	869.0	0.042330	
SN-4	HOWMET/UDRI/2	UDRIPKGNV89	AIR	41	20	1503.4	4.1072	3.0912	1095.0	0.042330	
SN-4	HOWMET/UDRI/2	UDRIPKGNV89	AIR	42	20	1063.1	4.1021	3.0912	775.0	0.042330	
SN-4	HOWMET/UDRI/2	UDRIPKGNV89	AIR	43	20	1289.9	4.1021	3.0861	944.0	0.042330	
SN-4	HOWMET/UDRI/2	UDRIPKGNV89	AIR	44	20	1370.0	4.1097	3.0912	997.0	0.042330	
SN-4	HOWMET/UDRI/2	UDRIPKGNV89	AIR	45	20	1494.5	4.0894	3.0886	1095.0	0.042330	
SN-4	HOWMET/UDRI/2	UDRIPKGNV89	AIR	46	20	1165.4	4.1046	3.0912	849.0	0.042330	
SN-4	HOWMET/UDRI/2	UDRIPKGNV89	AIR	47	20	1192.1	4.0894	3.0861	875.0	0.042330	
SN-4	HOWMET/UDRI/2	UDRIPKGNV89	AIR	48	20	1156.5	4.1097	3.0709	853.0	0.042330	
SN-4	HOWMET/UDRI/2	UDRIPKGNV89	AIR	49	20	1378.9	4.1046	3.0886	1006.0	0.042330	
SN-4	HOWMET/UDRI/2	UDRIPKGNV89	AIR	50	20	1298.8	4.1072	3.0886	947.0	0.042330	
SN-4	HOWMET/UDRI/2	UDRIPKGNV89	AIR	51	20	1272.1	4.0996	3.0836	933.0	0.042330	
SN-4	HOWMET/UDRI/2	UDRIPKGNV89	AIR	52	20	1152.0	4.1046	3.0886	841.0	0.042330	
SN-4	HOWMET/UDRI/2	UDRIPKGNV89	AIR	53	20	1352.2	4.1072	3.0912	985.0	0.042330	
SN-4	HOWMET/UDRI/2	UDRIPKGNV89	AIR	54	20	1276.6	4.1046	3.0886	932.0	0.042330	
SN-4	HOWMET/UDRI/2	UDRIPKGNV89	AIR	55	20	1098.7	4.0665	3.0861	811.0	0.042330	
SN-4	HOWMET/UDRI/2	UDRIPKGNV89	AIR	56	20	1214.3	4.1072	3.0836	889.0	0.042330	
SN-4	HOWMET/UDRI/2	UDRIPKGNV89	AIR	57	20	1383.3	4.0970	3.0836	1015.0	0.042330	
SN-4	HOWMET/UDRI/2	UDRIPKGNV89	AIR	58	20	1276.6	4.1046	3.0810	936.0	0.042330	
SN-4	HOWMET/UDRI/2	UDRIPKGNV89	AIR	34	1000	1574.6	6.1646	3.0937	763.0	0.042330	
SN-4	HOWMET/UDRI/2	UDRIPKGNV89	AIR	35	1000	1401.1	6.1646	3.0861	682.0	0.042330	
SN-4	HOWMET/UDRI/2	UDRIPKGNV89	AIR	36	1000	1463.4	6.1671	3.1013	705.0	0.042330	
SN-4	HOWMET/UDRI/2	UDRIPKGNV89	AIR	37	1000	1401.1	6.1646	3.0963	678.0	0.042330	
SN-4	HOWMET/UDRI/2	UDRIPKGNV89	AIR	38	1000	1841.5	6.1646	3.0886	895.0	0.042330	
SN-4	HOWMET/UDRI/2	UDRIPKGNV89	AIR	59	1000	1165.4	6.1671	3.0963	563.0	0.000423	
SN-4	HOWMET/UDRI/2	UDRIPKGNV89	AIR	60	1000	996.4	6.1620	3.0886	484.0	0.000423	
SN-4	HOWMET/UDRI/2	UDRIPKGNV89	AIR	61	1000	1112.0	6.1646	3.0912	539.0	0.000423	
SN-4	HOWMET/UDRI/2	UDRIPKGNV89	AIR	62	1000	934.1	6.1620	3.1064	449.0	0.000423	
SN-4	HOWMET/UDRI/2	UDRIPKGNV89	AIR	63	1000	1103.1	6.1646	3.0886	536.0	0.000423	
SN-4	HOWMET/UDRI/2	UDRIPKGNV89	AIR	23	1200	902.9	6.1646	3.0861	440.0	0.042330	

SECTION 5. MOR 4-POINT BEND TEST RESULTS, continued

MATERIAL	BATCH CODE	REFERENCE CODE	TEST ENVIRON.	SPEC. No.	TEMP °C	LOAD N	WIDTH mm	THICK mm	BEND STRENGTH MPa	X-HEAD SPEED mm/s	COMMENTS
SN-4	HOWMET/UDRI/2	UDRIPKGN0V89	AIR	24	1200	867.4	6.1722	3.0886	421.0	0.042330	
SN-4	HOWMET/UDRI/2	UDRIPKGN0V89	AIR	25	1200	800.6	6.1646	3.0937	388.0	0.042330	
SN-4	HOWMET/UDRI/2	UDRIPKGN0V89	AIR	26	1200	862.9	6.1646	3.0963	417.0	0.042330	
SN-4	HOWMET/UDRI/2	UDRIPKGN0V89	AIR	27	1200	680.5	6.1646	3.0886	331.0	0.042330	
SN-4	HOWMET/UDRI/2	UDRIPKGN0V89	AIR	28	1200	894.1	6.1646	3.0937	433.0	0.042330	
SN-4	HOWMET/UDRI/2	UDRIPKGN0V89	AIR	29	1200	591.6	6.1570	2.8575	336.0	0.000423	
SN-4	HOWMET/UDRI/2	UDRIPKGN0V89	AIR	30	1200	622.7	6.1646	3.0963	301.0	0.000423	
SN-4	HOWMET/UDRI/2	UDRIPKGN0V89	AIR	31	1200	618.3	6.1595	3.0912	330.0	0.000423	
SN-4	HOWMET/UDRI/2	UDRIPKGN0V89	AIR	32	1200	636.1	6.1620	3.0937	308.0	0.000423	
SN-4	HOWMET/UDRI/2	UDRIPKGN0V89	AIR	33	1200	640.5	6.1595	3.0734	315.0	0.000423	
SN-4	HOWMET/UDRI/2	UDRIPKGN0V89	AIR	21*	1400	385.9	6.1722	3.0988	191.0	0.042330	SEE DATATXT
SN-4	HOWMET/UDRI/2	UDRIPKGN0V89	AIR	22*	1400	391.4	6.1722	3.0988	189.0	0.042330	SEE DATATXT

SECTION 5. MOR 4-POINT BEND TEST RESULTS, continued

MATERIAL	BATCH	REFERENCE	HEAT	TEST	SPEC.	TEMP	WIDTH	THICK	BEND	COMMENTS
	CODE	CODE	TREATMENT	ENVIRON.	NO.	°C	mm	mm	STRENGTH	
									MPa	
SILICON CARBIDE WHISKER-REINFORCED SILICON NITRIDE										
SNW-1000	GTE/174-MA-1607	ORNL-CRB1289	AS FABRICATED	AIR	26	25	4.50	3.50	465.0	
SNW-1000	GTE/174-MA-1607	ORNL-CRB1289	AS FABRICATED	AIR	27	25	4.50	3.50	512.3	
SNW-1000	GTE/174-MA-1607	ORNL-CRB1289	AS FABRICATED	AIR	28	25	4.50	3.50	493.7	
SNW-1000	GTE/174-MA-1607	ORNL-CRB1289	AS FABRICATED	AIR	29	25	4.50	3.50	470.5	
SNW-1000	GTE/174-MA-1607	ORNL-CRB1289	AS FABRICATED	AIR	30	25	4.50	3.50	468.5	
SNW-1000	GTE/174-MA-1607	ORNL-CRB1289	AS FABRICATED	AIR	36	25	4.50	3.50	522.1	
SNW-1000	GTE/174-MA-1607	ORNL-CRB1289	AS FABRICATED	AIR	37	25	4.50	3.50	522.1	
SNW-1000	GTE/174-MA-1607	ORNL-CRB1289	AS FABRICATED	AIR	38	25	4.50	3.50	523.0	
SNW-1000	GTE/174-MA-1607	ORNL-CRB1289	AS FABRICATED	AIR	39	25	4.50	3.50	540.3	
SNW-1000	GTE/174-MA-1607	ORNL-CRB1289	AS FABRICATED	AIR	40	25	4.50	3.50	525.3	
SNW-1000	GTE/174-MA-1607	ORNL-CRB1289	AS FABRICATED	AIR	41	25	4.50	3.50	575.0	
SNW-1000	GTE/174-MA-1607	ORNL-CRB1289	AS FABRICATED	AIR	42	25	4.50	3.50	495.2	
SNW-1000	GTE/174-MA-1607	ORNL-CRB1289	AS FABRICATED	AIR	43	25	4.50	3.50	508.9	
SNW-1000	GTE/174-MA-1607	ORNL-CRB1289	AS FABRICATED	AIR	44	25	4.50	3.50	531.8	
SNW-1000	GTE/174-MA-1607	ORNL-CRB1289	AS FABRICATED	AIR	45	25	4.50	3.50	576.9	
SNW-1000	GTE/174-MA-1607	ORNL-CRB1289	AS FABRICATED	AIR	46	25	4.50	3.50	584.2	
SNW-1000	GTE/174-MA-1607	ORNL-CRB1289	AS FABRICATED	AIR	47	25	4.50	3.50	416.7	
SNW-1000	GTE/174-MA-1607	ORNL-CRB1289	AS FABRICATED	AIR	48	25	4.50	3.50	403.3	
SNW-1000	GTE/174-MA-1607	ORNL-CRB1289	AS FABRICATED	AIR	49	25	4.50	3.50	440.6	
SNW-1000	GTE/174-MA-1607	ORNL-CRB1289	AS FABRICATED	AIR	50	25	4.50	3.50	595.7	
SNW-1000	GTE/174-MA-1607	ORNL-CRB1289	AS FABRICATED	AIR	51	25	4.50	3.50	369.5	
SNW-1000	GTE/174-MA-1607	ORNL-CRB1289	AS FABRICATED	AIR	52	25	4.50	3.50	459.9	
SNW-1000	GTE/174-MA-1607	ORNL-CRB1289	AS FABRICATED	AIR	53	25	4.50	3.50	568.1	
SNW-1000	GTE/174-MA-1607	ORNL-CRB1289	AS FABRICATED	AIR	54	25	4.50	3.50	424.5	
SNW-1000	GTE/174-MA-1607	ORNL-CRB1289	AS FABRICATED	AIR	55	25	4.50	3.50	570.9	
SNW-1000	GTE/174-MA-1607	ORNL-CRB1289	AS FABRICATED	AIR	56	25	4.50	3.50	533.3	
SNW-1000	GTE/174-MA-1607	ORNL-CRB1289	AS FABRICATED	AIR	57	25	4.50	3.50	482.3	
SNW-1000	GTE/174-MA-1607	ORNL-CRB1289	AS FABRICATED	AIR	58	25	4.50	3.50	542.2	

SECTION 5. MOR 4-POINT BEND TEST RESULTS, continued

MATERIAL	BATCH	REFERENCE	HEAT	TEST	SPEC.	TEMP	WIDTH	THICK	BEND	COMMENTS
	CODE	CODE	TREATMENT	ENVIRON.	NO.	°C	mm	mm	STRENGTH	
									MPa	
SNW-1000	GTE/174-MA-1607	ORNLCRB1289	AS FABRICATED	AIR	59	25	4.50	3.50	411.2	
SNW-1000	GTE/174-MA-1607	ORNLCRB1289	AS FABRICATED	AIR	60	25	4.50	3.50	547.1	
SNW-1000	GTE/174-MA-1607	ORNLCRB1289	AS FABRICATED	AIR	62	25	4.50	3.50	462.0	
SNW-1000	GTE/174-MA-1607	ORNLCRB1289	AS FABRICATED	AIR	63	25	4.50	3.50	489.7	
SNW-1000	GTE/174-MA-1607	ORNLCRB1289	AS FABRICATED	AIR	64	25	4.50	3.50	546.9	
SNW-1000	GTE/174-MA-1607	ORNLCRB1289	AS FABRICATED	AIR	65	25	4.50	3.50	567.3	
SNW-1000	GTE/174-MA-1607	ORNLCRB1289	AS FABRICATED	AIR	66	25	4.50	3.50	535.1	
SNW-1000	GTE/174-MA-1607	ORNLCRB1289	AS FABRICATED	AIR	67	25	4.50	3.50	555.7	
SNW-1000	GTE/174-MA-1607	ORNLCRB1289	AS FABRICATED	AIR	68	25	4.50	3.50	491.9	
SNW-1000	GTE/174-MA-1607	ORNLCRB1289	AS FABRICATED	AIR	69	25	4.50	3.50	563.5	
SNW-1000	GTE/174-MA-1607	ORNLCRB1289	AS FABRICATED	AIR	70	25	4.50	3.50	443.6	
SNW-1000	GTE/174-MA-1607	ORNLCRB1289	AS FABRICATED	AIR	71	25	4.50	3.50	495.6	
SNW-1000	GTE/174-MA-1607	ORNLCRB1289	1000H/D-2/E2**	AIR	1	25	4.50	3.50	533.9	**SEE TESTBKGD FOR DETAILS
SNW-1000	GTE/174-MA-1607	ORNLCRB1289	1000H/D-2/E2**	AIR	2	25	4.50	3.50	515.4	**SEE TESTBKGD FOR DETAILS
SNW-1000	GTE/174-MA-1607	ORNLCRB1289	1000H/D-2/E2**	AIR	3	25	4.50	3.50	508.5	**SEE TESTBKGD FOR DETAILS
SNW-1000	GTE/174-MA-1607	ORNLCRB1289	1000H/D-2/E2**	AIR	4	25	4.50	3.50	566.3	**SEE TESTBKGD FOR DETAILS
SNW-1000	GTE/174-MA-1607	ORNLCRB1289	1000H/D-2/E2**	AIR	5	25	4.50	3.50	517.7	**SEE TESTBKGD FOR DETAILS
SNW-1000	GTE/174-MA-1607	ORNLCRB1289	1000H/D-2/E2**	AIR	6	25	4.50	3.50	527.8	**SEE TESTBKGD FOR DETAILS
SNW-1000	GTE/174-MA-1607	ORNLCRB1289	1000H/D-2/E2**	AIR	7	25	4.50	3.50	535.4	**SEE TESTBKGD FOR DETAILS
SNW-1000	GTE/174-MA-1607	ORNLCRB1289	1000H/D-2/E2**	AIR	8	25	4.50	3.50	577.7	**SEE TESTBKGD FOR DETAILS
SNW-1000	GTE/174-MA-1607	ORNLCRB1289	1000H/D-2/E2**	AIR	9	25	4.50	3.50	561.1	**SEE TESTBKGD FOR DETAILS
SNW-1000	GTE/174-MA-1607	ORNLCRB1289	1000H/D-2/E2**	AIR	10	25	4.50	3.50	542.0	**SEE TESTBKGD FOR DETAILS
SNW-1000	GTE/174-MA-1607	ORNLCRB1289	1000H/D-2/E2**	AIR	11	25	4.50	3.50	557.3	**SEE TESTBKGD FOR DETAILS
SNW-1000	GTE/174-MA-1607	ORNLCRB1289	1000H/D-2/E2**	AIR	12	25	4.50	3.50	576.6	**SEE TESTBKGD FOR DETAILS
SNW-1000	GTE/174-MA-1607	ORNLCRB1289	1000H/D-2/E2**	AIR	13	25	4.50	3.50	531.1	**SEE TESTBKGD FOR DETAILS
SNW-1000	GTE/174-MA-1607	ORNLCRB1289	1000H/D-2/E2**	AIR	14	25	4.50	3.50	528.7	**SEE TESTBKGD FOR DETAILS
SNW-1000	GTE/174-MA-1607	ORNLCRB1289	1000H/D-2/E2**	AIR	15	25	4.50	3.50	529.8	**SEE TESTBKGD FOR DETAILS

SECTION 5. MOR 4-POINT BEND TEST RESULTS, continued

MATERIAL	BATCH CODE	REFERENCE CODE	HEAT TREATMENT	TEST ENVIRON.	SPEC. NO.	TEMP °C	WIDTH mm	THICK mm	BEND STRENGTH MPa	COMMENTS
SNW-1000	GTE/174-MA-1607	ORNL-CRB1289	1000H/D-2/E2**	AIR	16	25	4.50	3.50	533.2	**SEE TESTBKGD FOR DETAILS
SNW-1000	GTE/174-MA-1607	ORNL-CRB1289	1000H/D-2/E2**	AIR	17	25	4.50	3.50	515.6	**SEE TESTBKGD FOR DETAILS
SNW-1000	GTE/174-MA-1607	ORNL-CRB1289	1000H/D-2/E2**	AIR	18	25	4.50	3.50	520.2	**SEE TESTBKGD FOR DETAILS
SNW-1000	GTE/174-MA-1607	ORNL-CRB1289	1000H/D-2/E2**	AIR	19	25	4.50	3.50	487.5	**SEE TESTBKGD FOR DETAILS
SNW-1000	GTE/174-MA-1607	ORNL-CRB1289	1000H/D-2/E2**	AIR	20	25	4.50	3.50	408.2	**SEE TESTBKGD FOR DETAILS
SNW-1000	GTE/174-MA-1607	ORNL-CRB1289	1000H/D-2/E2**	AIR	21	25	4.50	3.50	518.7	**SEE TESTBKGD FOR DETAILS
SNW-1000	GTE/174-MA-1607	ORNL-CRB1289	1000H/D-2/E2**	AIR	22	25	4.50	3.50	505.4	**SEE TESTBKGD FOR DETAILS
SNW-1000	GTE/174-MA-1607	ORNL-CRB1289	1000H/D-2/E2**	AIR	23	25	4.50	3.50	321.2	**SEE TESTBKGD FOR DETAILS
SNW-1000	GTE/174-MA-1607	ORNL-CRB1289	1000H/D-2/E2**	AIR	24	25	4.50	3.50	505.6	**SEE TESTBKGD FOR DETAILS
SNW-1000	GTE/174-MA-1607	ORNL-CRB1289	1000H/D-2/E2**	AIR	25	25	4.50	3.50	488.4	**SEE TESTBKGD FOR DETAILS
SNW-1000	GTE/174-MA-1607	ORNL-CRB1289	1000H/D-2/E2**	AIR	33	25	4.50	3.50	546.7	**SEE TESTBKGD FOR DETAILS
SNW-1000	GTE/174-MA-1607	ORNL-CRB1289	1000H/D-2/E2**	AIR	32	25	4.50	3.50	419.0	**SEE TESTBKGD FOR DETAILS
SNW-1000	GTE/174-MA-1607	ORNL-CRB1289	1000H/D-2/E2**	AIR	31	25	4.50	3.50	420.6	**SEE TESTBKGD FOR DETAILS
SNW-1000	GTE/174-MA-1607	ORNL-CRB1289	1000H/D-2/E2**	AIR	34	25	4.50	3.50	512.6	**SEE TESTBKGD FOR DETAILS
SNW-1000	GTE/174-MA-1607	ORNL-CRB1289	1000H/D-2/E2**	AIR	35	25	4.50	3.50	572.1	**SEE TESTBKGD FOR DETAILS
SNW-1000	GTE/174-MA-1607	ORNL-CRB1289	1000H/D-2/E2**	AIR	71	25	4.50	3.50	474.7	**SEE TESTBKGD FOR DETAILS
SNW-1000	GTE/174-MA-1607	ORNL-CRB1289	1000H/D-2/E2**	AIR	72	25	4.50	3.50	545.6	**SEE TESTBKGD FOR DETAILS

SECTION 5. MOR 4-POINT BEND TEST RESULTS, continued

MATERIAL	BATCH	REFERENCE	HEAT	TEST	SPEC.	TEMP	WIDTH	THICK	BEND	X-HEAD	COMMENTS
	CODE	CODE	TREATMENT	ENVIRON.	No.	°C	mm	mm	MPa	SPEED	
										mm/s	
Zirconias											
MS-PSZ	NILCRAVORNL-CRB	ORNL-5612	100H/D2+B/E2**	AIR	113	25	4.50	3.50	611.6		**SEE TESTBKGD FOR DETAILS
MS-PSZ	NILCRAVORNL-CRB	ORNL-5612	100H/D2+B/E2**	AIR	111	25	4.50	3.50	632.1		**SEE TESTBKGD FOR DETAILS
MS-PSZ	NILCRAVORNL-CRB	ORNL-5612	100H/D2+B/E2**	AIR	112	25	4.50	3.50	619.6		**SEE TESTBKGD FOR DETAILS
MS-PSZ	NILCRAVORNL-CRB	ORNL-5612	100H/D2+B/E2**	AIR	114	25	4.50	3.50	620.7		**SEE TESTBKGD FOR DETAILS
MS-PSZ	NILCRAVORNL-CRB	ORNL-6513	AS FABRICATE	AIR	1	25	4.50	3.50	679.4	0.00847	
MS-PSZ	NILCRAVORNL-CRB	ORNL-6513	AS FABRICATE	AIR	2	25	4.50	3.50	703.5	0.00847	
MS-PSZ	NILCRAVORNL-CRB	ORNL-6513	AS FABRICATE	AIR	3	25	4.50	3.50	688.8	0.00847	
MS-PSZ	NILCRAVORNL-CRB	ORNL-6513	AS FABRICATE	AIR	4	25	4.50	3.50	674.7	0.00847	
MS-PSZ	NILCRAVORNL-CRB	ORNL-6513	AS FABRICATE	AIR	5	25	4.50	3.50	692.9	0.00847	
MS-PSZ	NILCRAVORNL-CRB	ORNL-6513	AS FABRICATE	AIR	6	25	4.50	3.50	695.6	0.00847	
MS-PSZ	NILCRAVORNL-CRB	ORNL-6513	AS FABRICATE	AIR	7	25	4.50	3.50	728.9	0.00847	
MS-PSZ	NILCRAVORNL-CRB	ORNL-6513	AS FABRICATE	AIR	8	25	4.50	3.50	706.9	0.00847	
MS-PSZ	NILCRAVORNL-CRB	ORNL-6513	AS FABRICATE	AIR	9	25	4.50	3.50	697.7	0.00847	
MS-PSZ	NILCRAVORNL-CRB	ORNL-6513	AS FABRICATE	AIR	10	25	4.50	3.50	682.4	0.00847	
MS-PSZ	NILCRAVORNL-CRB	ORNL-6513	AS FABRICATE	AIR	11	25	4.50	3.50	611.1	0.00847	
MS-PSZ	NILCRAVORNL-CRB	ORNL-6513	AS FABRICATE	AIR	12	25	4.50	3.50	708.9	0.00847	
MS-PSZ	NILCRAVORNL-CRB	ORNL-6513	AS FABRICATE	AIR	13	25	4.50	3.50	733.7	0.00847	
MS-PSZ	NILCRAVORNL-CRB	ORNL-6513	AS FABRICATE	AIR	14	25	4.50	3.50	684.4	0.00847	
MS-PSZ	NILCRAVORNL-CRB	ORNL-6513	AS FABRICATE	AIR	15	25	4.50	3.50	698.3	0.00847	
MS-PSZ	NILCRAVORNL-CRB	ORNL-6513	AS FABRICATE	AIR	16	25	4.50	3.50	680.4	0.00847	
MS-PSZ	NILCRAVORNL-CRB	ORNL-6513	AS FABRICATE	AIR	17	25	4.50	3.50	603.5	0.00847	
MS-PSZ	NILCRAVORNL-CRB	ORNL-6513	AS FABRICATE	AIR	18	25	4.50	3.50	681.6	0.00847	
MS-PSZ	NILCRAVORNL-CRB	ORNL-6513	AS FABRICATE	AIR	19	25	4.50	3.50	698.7	0.00847	
MS-PSZ	NILCRAVORNL-CRB	ORNL-6513	AS FABRICATE	AIR	20	25	4.50	3.50	680.5	0.00847	
MS-PSZ	NILCRAVORNL-CRB	ORNL-6513	AS FABRICATE	AIR	21	25	4.50	3.50	674.6	0.00847	
MS-PSZ	NILCRAVORNL-CRB	ORNL-6513	AS FABRICATE	AIR	22	25	4.50	3.50	642.7	0.00847	
MS-PSZ	NILCRAVORNL-CRB	ORNL-6513	AS FABRICATE	AIR	23	25	4.50	3.50	695.5	0.00847	
MS-PSZ	NILCRAVORNL-CRB	ORNL-6513	AS FABRICATE	AIR	24	25	4.50	3.50	708.4	0.00847	
MS-PSZ	NILCRAVORNL-CRB	ORNL-6513	AS FABRICATE	AIR	25	25	4.50	3.50	691.4	0.00847	
MS-PSZ	NILCRAVORNL-CRB	ORNL-6513	AS FABRICATE	AIR	26	25	4.50	3.50	725.8	0.00847	
MS-PSZ	NILCRAVORNL-CRB	ORNL-6513	AS FABRICATE	AIR	27	25	4.50	3.50	685.2	0.00847	

SECTION 5. MOR 4-POINT BEND TEST RESULTS, continued

MATERIAL	BATCH	REFERENCE	HEAT	TEST	SPEC.	TEMP	WIDTH	THICK	BEND	X-HEAD	COMMENTS
	CODE	CODE	TREATMENT	ENVIRON.	No.	°C	mm	mm	STRENGTH	SPEED	
									MPa	mm/s	
MS-PSZ	NILCRA/ORNLCRB	ORNLCRB-6513	AS FABRICATE	AIR	28	25	4.50	3.50	636.5	0.00847	
MS-PSZ	NILCRA/ORNLCRB	ORNLCRB-6513	AS FABRICATE	AIR	29	25	4.50	3.50	684.2	0.00847	
MS-PSZ	NILCRA/ORNLCRB	ORNLCRB-6513	AS FABRICATE	AIR	30	25	4.50	3.50	690.6	0.00847	
MS-PSZ	NILCRA/ORNLCRB	ORNLCRB-6513	AS FABRICATE	AIR	31	25	4.50	3.50	662.3	0.00847	
MS-PSZ	NILCRA/ORNLCRB	ORNLCRB-6513	AS FABRICATE	AIR	32	25	4.50	3.50	685.2	0.00847	
MS-PSZ	NILCRA/ORNLCRB	ORNLCRB-6513	AS FABRICATE	AIR	33	25	4.50	3.50	718.8	0.00847	
MS-PSZ	NILCRA/ORNLCRB	ORNLCRB-6513	AS FABRICATE	AIR	34	25	4.50	3.50	702.1	0.00847	
MS-PSZ	NILCRA/ORNLCRB	ORNLCRB-6513	AS FABRICATE	AIR	35	25	4.50	3.50	666.4	0.00847	
MS-PSZ	NILCRA/ORNLCRB	ORNLCRB-6513	AS FABRICATE	AIR	36	25	4.50	3.50	691.8	0.00847	
MS-PSZ	NILCRA/ORNLCRB	ORNLCRB-6513	AS FABRICATE	AIR	37	25	4.50	3.50	653.5	0.00847	
MS-PSZ	NILCRA/ORNLCRB	ORNLCRB-6513	AS FABRICATE	AIR	38	25	4.50	3.50	632.8	0.00847	
MS-PSZ	NILCRA/ORNLCRB	ORNLCRB-6513	AS FABRICATE	AIR	39	25	4.50	3.50	666.8	0.00847	
MS-PSZ	NILCRA/ORNLCRB	ORNLCRB-6513	AS FABRICATE	AIR	40	25	4.50	3.50	685.6	0.00847	
MS-PSZ	NILCRA/ORNLCRB	ORNLCRB-6513	EXPOSED/100F	AIR	51	25	4.50	3.50	603.2	0.00847	**SEE TEXT FOR DETAILS
MS-PSZ	NILCRA/ORNLCRB	ORNLCRB-6513	EXPOSED/100F	AIR	52	25	4.50	3.50	561.8	0.00847	**SEE TEXT FOR DETAILS
MS-PSZ	NILCRA/ORNLCRB	ORNLCRB-6513	EXPOSED/100F	AIR	53	25	4.50	3.50	648.1	0.00847	**SEE TEXT FOR DETAILS
MS-PSZ	NILCRA/ORNLCRB	ORNLCRB-6513	EXPOSED/100F	AIR	54	25	4.50	3.50	622.1	0.00847	**SEE TEXT FOR DETAILS
MS-PSZ	NILCRA/ORNLCRB	ORNLCRB-6513	EXPOSED/100F	AIR	55	25	4.50	3.50	644.4	0.00847	**SEE TEXT FOR DETAILS
MS-PSZ	NILCRA/ORNLCRB	ORNLCRB-6513	EXPOSED/100F	AIR	56	25	4.50	3.50	536.1	0.00847	**SEE TEXT FOR DETAILS
MS-PSZ	NILCRA/ORNLCRB	ORNLCRB-6513	EXPOSED/100F	AIR	57	25	4.50	3.50	673.8	0.00847	**SEE TEXT FOR DETAILS
MS-PSZ	NILCRA/ORNLCRB	ORNLCRB-6513	EXPOSED/100F	AIR	58	25	4.50	3.50	640.9	0.00847	**SEE TEXT FOR DETAILS
MS-PSZ	NILCRA/ORNLCRB	ORNLCRB-6513	EXPOSED/100F	AIR	41	25	4.50	3.50	659.8	0.00847	**SEE TEXT FOR DETAILS
MS-PSZ	NILCRA/ORNLCRB	ORNLCRB-6513	EXPOSED/100F	AIR	42	25	4.50	3.50	642.0	0.00847	**SEE TEXT FOR DETAILS
MS-PSZ	NILCRA/ORNLCRB	ORNLCRB-6513	EXPOSED/100F	AIR	43	25	4.50	3.50	610.4	0.00847	**SEE TEXT FOR DETAILS
MS-PSZ	NILCRA/ORNLCRB	ORNLCRB-6513	EXPOSED/100F	AIR	44	25	4.50	3.50	567.8	0.00847	**SEE TEXT FOR DETAILS
MS-PSZ	NILCRA/ORNLCRB	ORNLCRB-6513	EXPOSED/100F	AIR	59	25	4.50	3.50	674.5	0.00847	**SEE TEXT FOR DETAILS
MS-PSZ	NILCRA/ORNLCRB	ORNLCRB-6513	EXPOSED/100F	AIR	60	25	4.50	3.50	639.9	0.00847	**SEE TEXT FOR DETAILS
MS-PSZ	NILCRA/ORNLCRB	ORNLCRB-6513	EXPOSED/100F	AIR	45	25	4.50	3.50	635.1	0.00847	**SEE TEXT FOR DETAILS
MS-PSZ	NILCRA/ORNLCRB	ORNLCRB-6513	EXPOSED/100F	AIR	46	25	4.50	3.50	583.4	0.00847	**SEE TEXT FOR DETAILS
MS-PSZ	NILCRA/ORNLCRB	ORNLCRB-6513	EXPOSED/100F	AIR	47	25	4.50	3.50	659.3	0.00847	**SEE TEXT FOR DETAILS
MS-PSZ	NILCRA/ORNLCRB	ORNLCRB-6513	EXPOSED/100F	AIR	48	25	4.50	3.50	601.1	0.00847	**SEE TEXT FOR DETAILS
MS-PSZ	NILCRA/ORNLCRB	ORNLCRB-6513	EXPOSED/100F	AIR	49	25	4.50	3.50	637.9	0.00847	**SEE TEXT FOR DETAILS

SECTION 5. MOR 4-POINT BEND TEST RESULTS, continued

MATERIAL	BATCH	REFERENCE	HEAT	TEST	SPEC.	TEMP	WIDTH	THICK	BEND	X-HEAD	COMMENTS
	CODE	CODE	TREATMENT	ENVIRON.	No.	°C	mm	mm	STRENGTH	SPEED	
									MPa	mm/s	
MS-PSZ	NILCRA/ORNL-CRB	ORNL-6513	EXPOSED/100H	AIR	50	25	4.50	3.50	659.0	0.00847	**SEE TEXT FOR DETAILS
MS-PSZ	NILCRA/ORNL-CRB	ORNL-6513	AGE/100H@700	AIR	61	25	4.50	3.50	689.0	0.00847	
MS-PSZ	NILCRA/ORNL-CRB	ORNL-6513	AGE/100H@700	AIR	62	25	4.50	3.50	671.7	0.00847	
MS-PSZ	NILCRA/ORNL-CRB	ORNL-6513	AGE/100H@700	AIR	63	25	4.50	3.50	669.8	0.00847	
MS-PSZ	NILCRA/ORNL-CRB	ORNL-6513	AGE/100H@700	AIR	64	25	4.50	3.50	664.9	0.00847	
MS-PSZ	NILCRA/ORNL-CRB	ORNL-6513	AGE/100H@700	AIR	65	25	4.50	3.50	659.2	0.00847	
MS-PSZ	NILCRA/ORNL-CRB	ORNL-6513	AGE/100H@700	AIR	66	25	4.50	3.50	658.8	0.00847	
MS-PSZ	NILCRA/ORNL-CRB	ORNL-6513	AGE/100H@700	AIR	67	25	4.50	3.50	657.6	0.00847	
MS-PSZ	NILCRA/ORNL-CRB	ORNL-6513	AGE/100H@700	AIR	68	25	4.50	3.50	656.3	0.00847	
MS-PSZ	NILCRA/ORNL-CRB	ORNL-6513	AGE/100H@700	AIR	69	25	4.50	3.50	655.9	0.00847	
MS-PSZ	NILCRA/ORNL-CRB	ORNL-6513	AGE/100H@700	AIR	70	25	4.50	3.50	655.3	0.00847	
MS-PSZ	NILCRA/ORNL-CRB	ORNL-6513	AGE/100H@700	AIR	71	25	4.50	3.50	653.4	0.00847	
MS-PSZ	NILCRA/ORNL-CRB	ORNL-6513	AGE/100H@700	AIR	72	25	4.50	3.50	647.7	0.00847	
MS-PSZ	NILCRA/ORNL-CRB	ORNL-6513	AGE/100H@700	AIR	73	25	4.50	3.50	644.6	0.00847	
MS-PSZ	NILCRA/ORNL-CRB	ORNL-6513	AGE/100H@700	AIR	74	25	4.50	3.50	641.6	0.00847	
MS-PSZ	NILCRA/ORNL-CRB	ORNL-6513	AGE/100H@700	AIR	75	25	4.50	3.50	639.6	0.00847	
MS-PSZ	NILCRA/ORNL-CRB	ORNL-6513	AGE/100H@700	AIR	76	25	4.50	3.50	638.8	0.00847	
MS-PSZ	NILCRA/ORNL-CRB	ORNL-6513	AGE/100H@700	AIR	77	25	4.50	3.50	636.2	0.00847	
MS-PSZ	NILCRA/ORNL-CRB	ORNL-6513	AGE/100H@700	AIR	78	25	4.50	3.50	627.9	0.00847	
MS-PSZ	NILCRA/ORNL-CRB	ORNL-6513	AGE/100H@700	AIR	79	25	4.50	3.50	536.2	0.00847	
MS-PSZ	NILCRA/ORNL-CRB	ORNL-6513	AGE/100H@700	AIR	80	25	4.50	3.50	527.4	0.00847	
MS-PSZ	NILCRA/ORNL-CRB	ORNL-6513	AGE/100H@750	AIR	81	25	4.50	3.50	676.0	0.00847	
MS-PSZ	NILCRA/ORNL-CRB	ORNL-6513	AGE/100H@750	AIR	82	25	4.50	3.50	672.0	0.00847	
MS-PSZ	NILCRA/ORNL-CRB	ORNL-6513	AGE/100H@750	AIR	83	25	4.50	3.50	667.5	0.00847	
MS-PSZ	NILCRA/ORNL-CRB	ORNL-6513	AGE/100H@750	AIR	84	25	4.50	3.50	663.0	0.00847	
MS-PSZ	NILCRA/ORNL-CRB	ORNL-6513	AGE/100H@750	AIR	85	25	4.50	3.50	646.8	0.00847	
MS-PSZ	NILCRA/ORNL-CRB	ORNL-6513	AGE/100H@750	AIR	86	25	4.50	3.50	644.0	0.00847	
MS-PSZ	NILCRA/ORNL-CRB	ORNL-6513	AGE/100H@750	AIR	87	25	4.50	3.50	641.2	0.00847	
MS-PSZ	NILCRA/ORNL-CRB	ORNL-6513	AGE/100H@750	AIR	88	25	4.50	3.50	641.0	0.00847	
MS-PSZ	NILCRA/ORNL-CRB	ORNL-6513	AGE/100H@750	AIR	90	25	4.50	3.50	639.4	0.00847	
MS-PSZ	NILCRA/ORNL-CRB	ORNL-6513	AGE/100H@750	AIR	91	25	4.50	3.50	635.5	0.00847	
MS-PSZ	NILCRA/ORNL-CRB	ORNL-6513	AGE/100H@750	AIR	92	25	4.50	3.50	630.9	0.00847	

SECTION 5. MOR 4-POINT BEND TEST RESULTS, continued

MATERIAL	BATCH CODE	REFERENCE CODE	HEAT TREATMENT	TEST ENVIRON.	SPEC. No.	TEMP °C	WIDTH mm	THICK mm	BEND STRENGTH MPa	X-HEAD SPEED mm/s	COMMENTS
MS-PSZ	NILCRA/ORNL-CRB	ORNL-6513	AGE/100H@750	AIR	93	25	4.50	3.50	629.2	0.00847	
MS-PSZ	NILCRA/ORNL-CRB	ORNL-6513	AGE/100H@750	AIR	94	25	4.50	3.50	622.5	0.00847	
MS-PSZ	NILCRA/ORNL-CRB	ORNL-6513	AGE/100H@750	AIR	95	25	4.50	3.50	619.4	0.00847	
MS-PSZ	NILCRA/ORNL-CRB	ORNL-6513	AGE/100H@750	AIR	96	25	4.50	3.50	614.8	0.00847	
MS-PSZ	NILCRA/ORNL-CRB	ORNL-6513	AGE/100H@750	AIR	97	25	4.50	3.50	609.5	0.00847	
MS-PSZ	NILCRA/ORNL-CRB	ORNL-6513	AGE/100H@750	AIR	98	25	4.50	3.50	597.0	0.00847	
MS-PSZ	NILCRA/ORNL-CRB	ORNL-6513	AGE/100H@750	AIR	99	25	4.50	3.50	596.6	0.00847	
MS-PSZ	NILCRA/ORNL-CRB	ORNL-6513	AGE/100H@750	AIR	100	25	4.50	3.50	512.7	0.00847	
MS-PSZ	NILCRA/ORNL-CRB	ORNL-6513	AGE/100H@750	AIR	131	25	4.50	3.50	641.3	0.00847	
MS-PSZ	NILCRA/ORNL-CRB	ORNL-6513	AGE/100H@800	AIR	132	25	4.50	3.50	642.0	0.00847	
MS-PSZ	NILCRA/ORNL-CRB	ORNL-6513	AGE/100H@800	AIR	133	25	4.50	3.50	645.3	0.00847	
MS-PSZ	NILCRA/ORNL-CRB	ORNL-6513	AGE/100H@800	AIR	134	25	4.50	3.50	593.6	0.00847	
MS-PSZ	NILCRA/ORNL-CRB	ORNL-6513	AGE/100H@800	AIR	135	25	4.50	3.50	620.0	0.00847	
MS-PSZ	NILCRA/ORNL-CRB	ORNL-6513	AGE/100H@800	AIR	136	25	4.50	3.50	662.6	0.00847	
MS-PSZ	NILCRA/ORNL-CRB	ORNL-6513	AGE/100H@800	AIR	137	25	4.50	3.50	593.9	0.00847	
MS-PSZ	NILCRA/ORNL-CRB	ORNL-6513	AGE/100H@800	AIR	138	25	4.50	3.50	656.8	0.00847	
MS-PSZ	NILCRA/ORNL-CRB	ORNL-6513	AGE/100H@800	AIR	139	25	4.50	3.50	644.0	0.00847	
MS-PSZ	NILCRA/ORNL-CRB	ORNL-6513	AGE/100H@800	AIR	140	25	4.50	3.50	634.6	0.00847	
MS-PSZ	NILCRA/ORNL-CRB	ORNL-6513	AGE/100H@800	AIR	141	25	4.50	3.50	651.6	0.00847	
MS-PSZ	NILCRA/ORNL-CRB	ORNL-6513	AGE/100H@800	AIR	142	25	4.50	3.50	653.4	0.00847	
MS-PSZ	NILCRA/ORNL-CRB	ORNL-6513	AGE/100H@800	AIR	143	25	4.50	3.50	599.1	0.00847	
MS-PSZ	NILCRA/ORNL-CRB	ORNL-6513	AGE/100H@800	AIR	144	25	4.50	3.50	658.8	0.00847	
MS-PSZ	NILCRA/ORNL-CRB	ORNL-6513	AGE/100H@800	AIR	145	25	4.50	3.50	591.5	0.00847	
MS-PSZ	NILCRA/ORNL-CRB	ORNL-6513	AGE/100H@800	AIR	146	25	4.50	3.50	649.5	0.00847	
MS-PSZ	NILCRA/ORNL-CRB	ORNL-6513	AGE/100H@800	AIR	147	25	4.50	3.50	651.6	0.00847	
MS-PSZ	NILCRA/ORNL-CRB	ORNL-6513	AGE/100H@800	AIR	148	25	4.50	3.50	627.2	0.00847	
MS-PSZ	NILCRA/ORNL-CRB	ORNL-6513	AGE/100H@800	AIR	149	25	4.50	3.50	649.9	0.00847	
MS-PSZ	NILCRA/ORNL-CRB	ORNL-6513	AGE/100H@800	AIR	159	25	4.50	3.50	646.8	0.00847	
TS-PSZ	NILCRA/85-218	ORNL-5612	AS FABRICATE	AIR	221	25	4.50	3.50	664.1		
TS-PSZ	NILCRA/85-218	ORNL-5612	AS FABRICATE	AIR	222	25	4.50	3.50	623.7		
TS-PSZ	NILCRA/85-218	ORNL-5612	AS FABRICATE	AIR	223	25	4.50	3.50	591.4		
TS-PSZ	NILCRA/85-218	ORNL-5612	AS FABRICATE	AIR	224	25	4.50	3.50	597.7		

SECTION 5. MOR 4-POINT BEND TEST RESULTS, continued

MATERIAL	BATCH CODE	REFERENCE CODE	HEAT TREATMENT	TEST ENVIRON.	SPEC. No.	TEMP °C	WIDTH mm	THICK mm	BEND STRENGTH MPa	X-HEAD SPEED mm/s	COMMENTS
TS-PSZ	NILCRA/85-218	ORNL-5612	AS FABRICATE	AIR	225	25	4.50	3.50	651.5		
TS-PSZ	NILCRA/85-218	ORNL-5612	AS FABRICATE	AIR	226	25	4.50	3.50	671.4		
TS-PSZ	NILCRA/85-218	ORNL-5612	AS FABRICATE	AIR	227	25	4.50	3.50	639.7		
TS-PSZ	NILCRA/85-218	ORNL-5612	AS FABRICATE	AIR	228	25	4.50	3.50	636.7		
TS-PSZ	NILCRA/85-218	ORNL-5612	AS FABRICATE	AIR	229	25	4.50	3.50	648.7		
TS-PSZ	NILCRA/85-218	ORNL-5612	AS FABRICATE	AIR	230	25	4.50	3.50	626.8		
TS-PSZ	NILCRA/85-218	ORNL-5612	AS FABRICATE	AIR	231	25	4.50	3.50	656.5		
TS-PSZ	NILCRA/85-218	ORNL-5612	AS FABRICATE	AIR	232	25	4.50	3.50	664.9		
TS-PSZ	NILCRA/85-218	ORNL-5612	AS FABRICATE	AIR	233	25	4.50	3.50	568.2		
TS-PSZ	NILCRA/85-218	ORNL-5612	AS FABRICATE	AIR	234	25	4.50	3.50	638.4		
TS-PSZ	NILCRA/85-218	ORNL-5612	AS FABRICATE	AIR	235	25	4.50	3.50	609.0		
TS-PSZ	NILCRA/85-218	ORNL-5612	AS FABRICATE	AIR	236	25	4.50	3.50	603.7		
TS-PSZ	NILCRA/85-218	ORNL-5612	AS FABRICATE	AIR	237	25	4.50	3.50	670.8		
TS-PSZ	NILCRA/85-218	ORNL-5612	AS FABRICATE	AIR	238	25	4.50	3.50	574.4		
TS-PSZ	NILCRA/85-218	ORNL-5612	AS FABRICATE	AIR	239	25	4.50	3.50	630.6		
TS-PSZ	NILCRA/85-218	ORNL-5612	AS FABRICATE	AIR	240	25	4.50	3.50	624.7		
TS-PSZ	NILCRA/ORNL-CRB	ORNL-5612	100H/D2+B/E2**	AIR	70	25	4.50	3.50	550.0		**SEE TESTBKGD FOR DETAILS
TS-PSZ	NILCRA/ORNL-CRB	ORNL-5612	100H/D2+B/E2**	AIR	145	25	4.50	3.50	546.5		**SEE TESTBKGD FOR DETAILS
TS-PSZ	NILCRA/ORNL-CRB	ORNL-5612	100H/D2+B/E2**	AIR	142	25	4.50	3.50	499.1		**SEE TESTBKGD FOR DETAILS
TS-PSZ	NILCRA/ORNL-CRB	ORNL-5612	100H/D2+B/E2**	AIR	143	25	4.50	3.50	427.7		**SEE TESTBKGD FOR DETAILS
TS-PSZ	NILCRA/ORNL-CRB	ORNL-5612	100H/D2+B/E2**	AIR	148	25	4.50	3.50	525.9		**SEE TESTBKGD FOR DETAILS
TS-PSZ	NILCRA/ORNL-CRB	ORNL-6513	AS FABRICATE	AIR	72	25	4.50	3.50	598.6	0.00847	
TS-PSZ	NILCRA/ORNL-CRB	ORNL-6513	AS FABRICATE	AIR	73	25	4.50	3.50	604.5	0.00847	
TS-PSZ	NILCRA/ORNL-CRB	ORNL-6513	AS FABRICATE	AIR	74	25	4.50	3.50	613.7	0.00847	
TS-PSZ	NILCRA/ORNL-CRB	ORNL-6513	AS FABRICATE	AIR	75	25	4.50	3.50	590.5	0.00847	
TS-PSZ	NILCRA/ORNL-CRB	ORNL-6513	AS FABRICATE	AIR	76	25	4.50	3.50	595.3	0.00847	
TS-PSZ	NILCRA/ORNL-CRB	ORNL-6513	AS FABRICATE	AIR	77	25	4.50	3.50	612.5	0.00847	
TS-PSZ	NILCRA/ORNL-CRB	ORNL-6513	AS FABRICATE	AIR	78	25	4.50	3.50	559.4	0.00847	
TS-PSZ	NILCRA/ORNL-CRB	ORNL-6513	AS FABRICATE	AIR	79	25	4.50	3.50	593.8	0.00847	
TS-PSZ	NILCRA/ORNL-CRB	ORNL-6513	AS FABRICATE	AIR	80	25	4.50	3.50	609.2	0.00847	
TS-PSZ	NILCRA/ORNL-CRB	ORNL-6513	AS FABRICATE	AIR	82	25	4.50	3.50	556.9	0.00847	
TS-PSZ	NILCRA/ORNL-CRB	ORNL-6513	AS FABRICATE	AIR	83	25	4.50	3.50	588.2	0.00847	

SECTION 5. MOR 4-POINT BEND TEST RESULTS, continued

MATERIAL	BATCH CODE	REFERENCE CODE	HEAT TREATMENT	TEST ENVIRON.	SPEC. No.	TEMP °C	WIDTH mm	THICK mm	BEND STRENGTH MPa	X-HEAD SPEED mm/s	COMMENTS
TS-PSZ	NILCRA/ORNLCRB	ORNLCRB-6513	AS FABRICATE	AIR	84	25	4.50	3.50	591.2	0.00847	
TS-PSZ	NILCRA/ORNLCRB	ORNLCRB-6513	AS FABRICATE	AIR	85	25	4.50	3.50	590.4	0.00847	
TS-PSZ	NILCRA/ORNLCRB	ORNLCRB-6513	AS FABRICATE	AIR	86	25	4.50	3.50	584.9	0.00847	
TS-PSZ	NILCRA/ORNLCRB	ORNLCRB-6513	AS FABRICATE	AIR	87	25	4.50	3.50	595.7	0.00847	
TS-PSZ	NILCRA/ORNLCRB	ORNLCRB-6513	AS FABRICATE	AIR	88	25	4.50	3.50	596.3	0.00847	
TS-PSZ	NILCRA/ORNLCRB	ORNLCRB-6513	AS FABRICATE	AIR	90	25	4.50	3.50	576.5	0.00847	
TS-PSZ	NILCRA/ORNLCRB	ORNLCRB-6513	AS FABRICATE	AIR	91	25	4.50	3.50	591.5	0.00847	
TS-PSZ	NILCRA/ORNLCRB	ORNLCRB-6513	AS FABRICATE	AIR	92	25	4.50	3.50	596.5	0.00847	
TS-PSZ	NILCRA/ORNLCRB	ORNLCRB-6513	AS FABRICATE	AIR	93	25	4.50	3.50	600.0	0.00847	
TS-PSZ	NILCRA/ORNLCRB	ORNLCRB-6513	AS FABRICATE	AIR	94	25	4.50	3.50	597.9	0.00847	
TS-PSZ	NILCRA/ORNLCRB	ORNLCRB-6513	AS FABRICATE	AIR	96	25	4.50	3.50	572.6	0.00847	
TS-PSZ	NILCRA/ORNLCRB	ORNLCRB-6513	AS FABRICATE	AIR	97	25	4.50	3.50	590.9	0.00847	
TS-PSZ	NILCRA/ORNLCRB	ORNLCRB-6513	AS FABRICATE	AIR	98	25	4.50	3.50	601.3	0.00847	
TS-PSZ	NILCRA/ORNLCRB	ORNLCRB-6513	AS FABRICATE	AIR	99	25	4.50	3.50	585.9	0.00847	
TS-PSZ	NILCRA/ORNLCRB	ORNLCRB-6513	AS FABRICATE	AIR	100	25	4.50	3.50	596.2	0.00847	
TS-PSZ	NILCRA/ORNLCRB	ORNLCRB-6513	AS FABRICATE	AIR	101	25	4.50	3.50	579.7	0.00847	
TS-PSZ	NILCRA/ORNLCRB	ORNLCRB-6513	AS FABRICATE	AIR	102	25	4.50	3.50	562.6	0.00847	
TS-PSZ	NILCRA/ORNLCRB	ORNLCRB-6513	AS FABRICATE	AIR	103	25	4.50	3.50	589.1	0.00847	
TS-PSZ	NILCRA/ORNLCRB	ORNLCRB-6513	AS FABRICATE	AIR	104	25	4.50	3.50	602.2	0.00847	
TS-FSZ	NILCRA/ORNLCRB	ORNLCRB-6513	AS FABRICATE	AIR	105	25	4.50	3.50	589.0	0.00847	
TS-PSZ	NILCRA/ORNLCRB	ORNLCRB-6513	AS FABRICATE	AIR	106	25	4.50	3.50	581.9	0.00847	
TS-PSZ	NILCRA/ORNLCRB	ORNLCRB-6513	AS FABRICATE	AIR	107	25	4.50	3.50	602.2	0.00847	
TS-PSZ	NILCRA/ORNLCRB	ORNLCRB-6513	AS FABRICATE	AIR	109	25	4.50	3.50	595.2	0.00847	
TS-PSZ	NILCRA/ORNLCRB	ORNLCRB-6513	AS FABRICATE	AIR	110	25	4.50	3.50	607.7	0.00847	
TS-PSZ	NILCRA/ORNLCRB	ORNLCRB-6513	AS FABRICATE	AIR	111	25	4.50	3.50	591.2	0.00847	
TS-PSZ	NILCRA/ORNLCRB	ORNLCRB-6513	AS FABRICATE	AIR	112	25	4.50	3.50	588.3	0.00847	
TS-PSZ	NILCRA/ORNLCRB	ORNLCRB-6513	AS FABRICATE	AIR	113	25	4.50	3.50	594.1	0.00847	
TS-PSZ	NILCRA/ORNLCRB	ORNLCRB-6513	AS FABRICATE	AIR	114	25	4.50	3.50	600.5	0.00847	
TS-PSZ	NILCRA/ORNLCRB	ORNLCRB-6513	AS FABRICATE	AIR	115	25	4.50	3.50	588.8	0.00847	
TS-PSZ	NILCRA/ORNLCRB	ORNLCRB-6513	AS FABRICATE	AIR	117	25	4.50	3.50	522.7	0.00847	
TS-PSZ	NILCRA/ORNLCRB	ORNLCRB-6513	AS FABRICATE	AIR	118	25	4.50	3.50	587.4	0.00847	
TS-PSZ	NILCRA/ORNLCRB	ORNLCRB-6513	AS FABRICATE	AIR	119	25	4.50	3.50	598.9	0.00847	

SECTION 5. MOR 4-POINT BEND TEST RESULTS, continued

MATERIAL	BATCH CODE	REFERENCE CODE	HEAT TREATMENT	TEST ENVIRON.	SPEC. No.	TEMP °C	WIDTH mm	THICK mm	BEND STRENGTH MPa	X-HEAD SPEED mm/s	COMMENTS
TS-PSZ	NILCRA/ORNL-CRB	ORNL-6513	AS FABRICATE	AIR	120	25	4.50	3.50	599.5	0.00847	
TS-PSZ	NILCRA/ORNL-CRB	ORNL-6513	AS FABRICATE	AIR	121	25	4.50	3.50	578.7	0.00847	
TS-PSZ	NILCRA/ORNL-CRB	ORNL-6513	AS FABRICATE	AIR	122	25	4.50	3.50	590.1	0.00847	
TS-PSZ	NILCRA/ORNL-CRB	ORNL-6513	AS FABRICATE	AIR	124	25	4.50	3.50	577.8	0.00847	
TS-PSZ	NILCRA/ORNL-CRB	ORNL-6513	AS FABRICATE	AIR	125	25	4.50	3.50	593.2	0.00847	
TS-PSZ	NILCRA/ORNL-CRB	ORNL-6513	AS FABRICATE	AIR	126	25	4.50	3.50	605.8	0.00847	
TS-PSZ	NILCRA/ORNL-CRB	ORNL-6513	AS FABRICATE	AIR	127	25	4.50	3.50	600.9	0.00847	
TS-PSZ	NILCRA/ORNL-CRB	ORNL-6513	AS FABRICATE	AIR	128	25	4.50	3.50	587.4	0.00847	
TS-PSZ	NILCRA/ORNL-CRB	ORNL-6513	AS FABRICATE	AIR	129	25	4.50	3.50	490.2	0.00847	
TS-PSZ	NILCRA/ORNL-CRB	ORNL-6513	AS FABRICATE	AIR	130	25	4.50	3.50	586.4	0.00847	
TS-PSZ	NILCRA/ORNL-CRB	ORNL-6513	AS FABRICATE	AIR	71	25	4.50	3.50	204.0	0.00847	**SEE TEXT FOR DETAILS
TS-PSZ	NILCRA/ORNL-CRB	ORNL-6513	EXPOSED/100F	AIR	65	25	4.50	3.50	228.0	0.00847	**SEE TEXT FOR DETAILS
TS-PSZ	NILCRA/ORNL-CRB	ORNL-6513	EXPOSED/100F	AIR	133	25	4.50	3.50	285.0	0.00847	**SEE TEXT FOR DETAILS
TS-PSZ	NILCRA/ORNL-CRB	ORNL-6513	EXPOSED/100F	AIR	66	25	4.50	3.50	307.0	0.00847	**SEE TEXT FOR DETAILS
TS-PSZ	NILCRA/ORNL-CRB	ORNL-6513	EXPOSED/100F	AIR	81	25	4.50	3.50	309.0	0.00847	**SEE TEXT FOR DETAILS
TS-PSZ	NILCRA/ORNL-CRB	ORNL-6513	EXPOSED/100F	AIR	95	25	4.50	3.50	334.0	0.00847	**SEE TEXT FOR DETAILS
TS-PSZ	NILCRA/ORNL-CRB	ORNL-6513	EXPOSED/100F	AIR	123	25	4.50	3.50	453.0	0.00847	**SEE TEXT FOR DETAILS
TS-PSZ	NILCRA/ORNL-CRB	ORNL-6513	EXPOSED/100F	AIR	144	25	4.50	3.50	453.0	0.00847	**SEE TEXT FOR DETAILS
TS-PSZ	NILCRA/ORNL-CRB	ORNL-6513	EXPOSED/100F	AIR	63	25	4.50	3.50	474.0	0.00847	**SEE TEXT FOR DETAILS
TS-PSZ	NILCRA/ORNL-CRB	ORNL-6513	EXPOSED/100F	AIR	58	25	4.50	3.50	475.0	0.00847	**SEE TEXT FOR DETAILS
TS-PSZ	NILCRA/ORNL-CRB	ORNL-6513	EXPOSED/100F	AIR	89	25	4.50	3.50	501.0	0.00847	**SEE TEXT FOR DETAILS
TS-PSZ	NILCRA/ORNL-CRB	ORNL-6513	EXPOSED/100F	AIR	150	25	4.50	3.50	515.0	0.00847	**SEE TEXT FOR DETAILS
TS-PSZ	NILCRA/ORNL-CRB	ORNL-6513	EXPOSED/100F	AIR	151	25	4.50	3.50	546.0	0.00847	**SEE TEXT FOR DETAILS
TS-PSZ	NILCRA/ORNL-CRB	ORNL-6513	EXPOSED/100F	AIR	152	25	4.50	3.50	540.0	0.00847	**SEE TEXT FOR DETAILS
TS-PSZ	NILCRA/ORNL-CRB	ORNL-6513	EXPOSED/100F	AIR	11	25	4.50	3.50	541.9	0.00847	**SEE TEXT FOR DETAILS
TS-PSZ	NILCRA/ORNL-CRB	ORNL-6513	AGE/100H@700	AIR	12	25	4.50	3.50	532.1	0.00847	**SEE TEXT FOR DETAILS
TS-PSZ	NILCRA/ORNL-CRB	ORNL-6513	AGE/100H@700	AIR	13	25	4.50	3.50	551.9	0.00847	**SEE TEXT FOR DETAILS
TS-PSZ	NILCRA/ORNL-CRB	ORNL-6513	AGE/100H@700	AIR	14	25	4.50	3.50	536.3	0.00847	**SEE TEXT FOR DETAILS
TS-PSZ	NILCRA/ORNL-CRB	ORNL-6513	AGE/100H@700	AIR	15	25	4.50	3.50	525.2	0.00847	**SEE TEXT FOR DETAILS
TS-PSZ	NILCRA/ORNL-CRB	ORNL-6513	AGE/100H@700	AIR	46	25	4.50	3.50	555.2	0.00847	**SEE TEXT FOR DETAILS
TS-PSZ	NILCRA/ORNL-CRB	ORNL-6513	AGE/100H@700	AIR	47	25	4.50	3.50	553.0	0.00847	**SEE TEXT FOR DETAILS
TS-PSZ	NILCRA/ORNL-CRB	ORNL-6513	AGE/100H@700	AIR	48	25	4.50	3.50	553.1	0.00847	**SEE TEXT FOR DETAILS

SECTION 5. MOR 4-POINT BEND TEST RESULTS, continued

MATERIAL	BATCH CODE	REFERENCE CODE	HEAT TREATMENT	TEST ENVIRON.	SPEC. No.	TEMP °C	WIDTH mm	THICK mm	BEND STRENGTH MPa	X-HEAD SPEED mm/s	COMMENTS
TS-PSZ	NILCRAVORNLCRB	ORNLCRB	AGE/100H@700	AIR	49	25	4.50	3.50	576.1	0.00847	
TS-PSZ	NILCRAVORNLCRB	ORNLCRB	AGE/100H@700	AIR	50	25	4.50	3.50	556.4	0.00847	
TS-PSZ	NILCRAVORNLCRB	ORNLCRB	AGE/100H@700	AIR	51	25	4.50	3.50	537.3	0.00847	
TS-PSZ	NILCRAVORNLCRB	ORNLCRB	AGE/100H@700	AIR	52	25	4.50	3.50	569.0	0.00847	
TS-PSZ	NILCRAVORNLCRB	ORNLCRB	AGE/100H@700	AIR	53	25	4.50	3.50	544.6	0.00847	
TS-PSZ	NILCRAVORNLCRB	ORNLCRB	AGE/100H@700	AIR	54	25	4.50	3.50	549.9	0.00847	
TS-PSZ	NILCRAVORNLCRB	ORNLCRB	AGE/100H@700	AIR	55	25	4.50	3.50	559.4	0.00847	
TS-PSZ	NILCRAVORNLCRB	ORNLCRB	AGE/100H@700	AIR	56	25	4.50	3.50	566.2	0.00847	
TS-PSZ	NILCRAVORNLCRB	ORNLCRB	AGE/100H@700	AIR	57	25	4.50	3.50	562.0	0.00847	
TS-PSZ	NILCRAVORNLCRB	ORNLCRB	AGE/100H@700	AIR	59	25	4.50	3.50	550.3	0.00847	
TS-PSZ	NILCRAVORNLCRB	ORNLCRB	AGE/100H@700	AIR	60	25	4.50	3.50	506.1	0.00847	
TS-PSZ	NILCRAVORNLCRB	ORNLCRB	AGE/100H@700	AIR	136	25	4.50	3.50	553.0	0.00847	
TS-PSZ	NILCRAVORNLCRB	ORNLCRB	AGE/100H@700	AIR	137	25	4.50	3.50	560.2	0.00847	
TS-PSZ	NILCRAVORNLCRB	ORNLCRB	AGE/100H@700	AIR	138	25	4.50	3.50	553.9	0.00847	
TS-PSZ	NILCRAVORNLCRB	ORNLCRB	AGE/100H@700	AIR	140	25	4.50	3.50	505.1	0.00847	
TS-PSZ	NILCRAVORNLCRB	ORNLCRB	AGE/100H@700	AIR	1	25	4.50	3.50	569.4	0.00847	
TS-PSZ	NILCRAVORNLCRB	ORNLCRB	AGE/100H@750	AIR	2	25	4.50	3.50	568.2	0.00847	
TS-PSZ	NILCRAVORNLCRB	ORNLCRB	AGE/100H@750	AIR	3	25	4.50	3.50	624.0	0.00847	
TS-PSZ	NILCRAVORNLCRB	ORNLCRB	AGE/100H@750	AIR	4	25	4.50	3.50	583.6	0.00847	
TS-PSZ	NILCRAVORNLCRB	ORNLCRB	AGE/100H@750	AIR	5	25	4.50	3.50	597.4	0.00847	
TS-PSZ	NILCRAVORNLCRB	ORNLCRB	AGE/100H@750	AIR	6	25	4.50	3.50	529.3	0.00847	
TS-PSZ	NILCRAVORNLCRB	ORNLCRB	AGE/100H@750	AIR	7	25	4.50	3.50	558.0	0.00847	
TS-PSZ	NILCRAVORNLCRB	ORNLCRB	AGE/100H@750	AIR	8	25	4.50	3.50	543.2	0.00847	
TS-PSZ	NILCRAVORNLCRB	ORNLCRB	AGE/100H@750	AIR	9	25	4.50	3.50	519.0	0.00847	
TS-PSZ	NILCRAVORNLCRB	ORNLCRB	AGE/100H@750	AIR	10	25	4.50	3.50	558.3	0.00847	
TS-PSZ	NILCRAVORNLCRB	ORNLCRB	AGE/100H@750	AIR	11	25	4.50	3.50	536.1	0.00847	
TS-PSZ	NILCRAVORNLCRB	ORNLCRB	AGE/100H@750	AIR	12	25	4.50	3.50	539.4	0.00847	
TS-PSZ	NILCRAVORNLCRB	ORNLCRB	AGE/100H@750	AIR	13	25	4.50	3.50	535.9	0.00847	
TS-PSZ	NILCRAVORNLCRB	ORNLCRB	AGE/100H@750	AIR	14	25	4.50	3.50	527.9	0.00847	
TS-PSZ	NILCRAVORNLCRB	ORNLCRB	AGE/100H@750	AIR	15	25	4.50	3.50	555.6	0.00847	
TS-PSZ	NILCRAVORNLCRB	ORNLCRB	AGE/100H@750	AIR	16	25	4.50	3.50	525.7	0.00847	
TS-PSZ	NILCRAVORNLCRB	ORNLCRB	AGE/100H@750	AIR	17	25	4.50	3.50	481.3	0.00847	

SECTION 5. MOR 4-POINT BEND TEST RESULTS, continued

MATERIAL	BATCH CODE	REFERENCE CODE	HEAT TREATMENT	TEST ENVIRON.	SPEC. No.	TEMP °C	WIDTH mm	THICK mm	BEND STRENGTH MPa	X-HEAD SPEED mm/s	COMMENTS
TS-PSZ	NILCRAVORNLCRB	ORNL-6513	AGE/100H@750	AIR	18	25	4.50	3.50	427.7	0.00847	
TS-PSZ	NILCRAVORNLCRB	ORNL-6513	AGE/100H@750	AIR	19	25	4.50	3.50	501.6	0.00847	
TS-PSZ	NILCRAVORNLCRB	ORNL-6513	AGE/100H@750	AIR	20	25	4.50	3.50	520.2	0.00847	
TS-PSZ	NILCRAVORNLCRB	ORNL-6513	AGE/100H@800	AIR	6	25	4.50	3.50	548.4	0.00847	
TS-PSZ	NILCRAVORNLCRB	ORNL-6513	AGE/100H@800	AIR	7	25	4.50	3.50	528.7	0.00847	
TS-PSZ	NILCRAVORNLCRB	ORNL-6513	AGE/100H@800	AIR	8	25	4.50	3.50	505.8	0.00847	
TS-PSZ	NILCRAVORNLCRB	ORNL-6513	AGE/100H@800	AIR	9	25	4.50	3.50	514.7	0.00847	
TS-PSZ	NILCRAVORNLCRB	ORNL-6513	AGE/100H@800	AIR	10	25	4.50	3.50	517.0	0.00847	
TS-PSZ	NILCRAVORNLCRB	ORNL-6513	AGE/100H@800	AIR	31	25	4.50	3.50	533.4	0.00847	
TS-PSZ	NILCRAVORNLCRB	ORNL-6513	AGE/100H@800	AIR	32	25	4.50	3.50	512.4	0.00847	
TS-PSZ	NILCRAVORNLCRB	ORNL-6513	AGE/100H@800	AIR	33	25	4.50	3.50	540.9	0.00847	
TS-PSZ	NILCRAVORNLCRB	ORNL-6513	AGE/100H@800	AIR	34	25	4.50	3.50	525.9	0.00847	
TS-PSZ	NILCRAVORNLCRB	ORNL-6513	AGE/100H@800	AIR	35	25	4.50	3.50	520.0	0.00847	
TS-PSZ	NILCRAVORNLCRB	ORNL-6513	AGE/100H@800	AIR	36	25	4.50	3.50	522.5	0.00847	
TS-PSZ	NILCRAVORNLCRB	ORNL-6513	AGE/100H@800	AIR	37	25	4.50	3.50	529.5	0.00847	
TS-PSZ	NILCRAVORNLCRB	ORNL-6513	AGE/100H@800	AIR	38	25	4.50	3.50	537.8	0.00847	
TS-PSZ	NILCRAVORNLCRB	ORNL-6513	AGE/100H@800	AIR	39	25	4.50	3.50	520.1	0.00847	
TS-PSZ	NILCRAVORNLCRB	ORNL-6513	AGE/100H@800	AIR	40	25	4.50	3.50	536.7	0.00847	
TS-PSZ	NILCRAVORNLCRB	ORNL-6513	AGE/100H@800	AIR	41	25	4.50	3.50	536.0	0.00847	
TS-PSZ	NILCRAVORNLCRB	ORNL-6513	AGE/100H@800	AIR	42	25	4.50	3.50	538.7	0.00847	
TS-PSZ	NILCRAVORNLCRB	ORNL-6513	AGE/100H@800	AIR	43	25	4.50	3.50	529.7	0.00847	
TS-PSZ	NILCRAVORNLCRB	ORNL-6513	AGE/100H@800	AIR	44	25	4.50	3.50	526.3	0.00847	
TS-PSZ	NILCRAVORNLCRB	ORNL-6513	AGE/100H@800	AIR	45	25	4.50	3.50	544.1	0.00847

Figure 2.3. A comparison of bend strengths of the UDR/silicon nitrides tested at .000423 mm/sec.

Figure 2.4. A comparison of the bend strengths of the UDRI silicon nitrides tested at 0.0423 mm/sec.

Figure 2.5. Weibull plot of CVD SiC at room temperature. Crosshead speed was 0.04 millimeters per second.

Figure 2.6. Weibull plot of CVD-SiC tests run at 1000°C using 2 different crosshead speeds.

Figure 2.7. Weibull plot of CVD-SiC tests run at 1200°C at 2 crosshead speeds.

Figure 2.8. Weibull plot of CVD-SiC tests run at 1400°C using 2 crosshead speeds.

Figure 2.9. Weibull plot of Hexoloy SA MOR 4-point bend tests run at 21°C at 2 crosshead speeds.

Figure 2.10. Weibull plot of Hexoloy SA MOR 4-point bend tests run at 1000°C at 3 crosshead speeds.

Figure 2.11. Weibull plot of Hexoloy SA MOR 4-point bend tests run at 1200°C at 3 crosshead speeds.

Figure 2.12. Weibull plot of Hexoloy SA MOR 4-point bend tests run at 1400°C at 3 crosshead speeds.

Figure 2.13. Weibull plot of Ceralloy 147-3 MOR 4-point bend tests run at 21°C at a crosshead speed of .04233 millimeters per second.

Figure 2.14. Weibull plot of Ceralloy 147-3 MOR 4-point bend tests run at 1000°C at 2 crosshead speeds.

Figure 2.15. Weibull plot of Ceralloy 147-3 MOR 4-point bend tests run at 1200°C at 2 crosshead speeds.

Figure 2.16. Weibull plot of Ceralloy 147-3 MOR 4-point bend tests run at 1400°C at 2 crosshead speeds.

Figure 2.17. Weibull plot of EC-152 MOR 4-point bend tests run at 1000°C at 2 crosshead speeds.

Figure 2.18. Weibull plot of EC-152 MOR 4-point bend tests run at 1200°C at 2 crosshead speeds.

Figure 2.19. Weibull plot of EC-152 MOR 4-point bend tests run at 1400°C at 0.0423 millimeters per second.

Figure 2.20. Weibull plot of GTE PY6 MOR 4-point bend tests run at 21°C at 0.04233 millimeters per second.

Figure 2.21. Weibull plot of GTE PY6 MOR 4-point bend tests run at 1000°C at 3 crosshead speeds.

Figure 2.22. Weibull plot of GTE PY6 MOR 4-point bend tests run at 1200°C at 3 crosshead speeds.

Figure 2.23. Weibull plot of GTE PY6 MOR 4-point bend tests run at 1400°C at 3 crosshead speeds.

Figure 2.24. Weibull plot of NT-154 MOR 4-point bend tests run at 21°C at 2 crosshead speeds.

Figure 2.25. Weibull plot of NT-154 MOR 4-point bend tests run at 1000°C at 2 crosshead speeds.

Figure 2.26. Weibull plot of NT-154 MOR 4-point bend tests run at 1200°C at 2 crosshead speeds.

Figure 2.27. Weibull plot of NT-154 MOR 4-point bend tests run at 1400°C at 2 crosshead speeds.

Figure 2.28. Weibull plot for SN-4 MOR 4-point bend tests run at 20°C at .0423 millimeters per second.

Figure 2.29. Weibull plot OF SN-4 MOR 4-point bend tests run at 1000°C at 2 crosshead speeds.

Figure 2.30. Weibull plot of SN-4 MOR 4-point bend tests run at 1200°C at 2 crosshead speeds.

Figure 2.31. Weibull plot of SN-252 MOR 4-point bend tests run at 1000°C at 2 crosshead speeds.

Figure 2.32. Weibull plot of SN-252 MOR 4-point bend tests run at 1200°C at 2 crosshead speeds.

Figure 2.33. Weibull plot of SN-252 MOR 4-point bend tests run at 1400°C at 2 crosshead speeds.

Figure 2.34. Weibull plot comparing 2 batches of Nilcra TS-PSZ with 1 batch of Nilcra MS-PSZ in the as-fabricated condition at 25°C.

Figure 2.35. Weibull plot comparing MS-PSZ and TS-PSZ tested at 25°C after 100 hours diesel engine exposure.

Figure 2.36. Weibull plot comparing TS-PSZ to MS-PSZ after aging 100 hours at 700°C. Test temperature was 25°C.

Figure 2.37. Weibull plot comparing MS-PSZ to TS-PSZ after aging 100 hours at 750°C. Test temperature was 25°C.

Figure 2.38. Weibull plot comparing MS-PSZ and TS-PSZ after aging 100 hours at 800°C. Test temperature was 25°C.

SECTION 6. MODULUS OF ELASTICITY

MATERIAL	BATCH CODE	REFERENCE CODE	TEST ENVIRON	SPECIMEN NUMBER	TEST TYPE	TEST TEMP °C	MODULUS ELASTICITY GPa
SILICON CARBIDE							
HEXOLOY SA	SOHIO/UDRI/2	UDRIPKGNV89	AIR	16	SONIC	20	420.60
HEXOLOY SA	SOHIO/UDRI/2	UDRIPKGNV89	AIR	17	SONIC	20	411.63
HEXOLOY SA	SOHIO/UDRI/2	UDRIPKGNV89	AIR	18	SONIC	20	411.63
HEXOLOY SA	SOHIO/UDRI/2	UDRIPKGNV89	AIR	19	SONIC	20	417.84
HEXOLOY SA	SOHIO/UDRI/2	UDRIPKGNV89	AIR	20	SONIC	20	436.45
HEXOLOY SA	SOHIO/UDRI/2	UDRIPKGNV89	AIR	20	SONIC	1000	417.84
HEXOLOY SA	SOHIO/UDRI/2	UDRIPKGNV89	AIR	19	SONIC	1000	399.22
HEXOLOY SA	SOHIO/UDRI/2	UDRIPKGNV89	AIR	18	SONIC	1000	397.84
HEXOLOY SA	SOHIO/UDRI/2	UDRIPKGNV89	AIR	17	SONIC	1000	396.46
HEXOLOY SA	SOHIO/UDRI/2	UDRIPKGNV89	AIR	16	SONIC	1000	395.08
HEXOLOY SA	SOHIO/UDRI/2	UDRIPKGNV89	AIR	16	SONIC	1400	393.02
HEXOLOY SA	SOHIO/UDRI/2	UDRIPKGNV89	AIR	17	SONIC	1400	385.43
HEXOLOY SA	SOHIO/UDRI/2	UDRIPKGNV89	AIR	18	SONIC	1400	388.88
HEXOLOY SA	SOHIO/UDRI/2	UDRIPKGNV89	AIR	19	SONIC	1400	395.08
HEXOLOY SA	SOHIO/UDRI/2	UDRIPKGNV89	AIR	20	SONIC	1400	408.18
SILICON NITRIDES							
GTE PY6	GTEL/UDRI/2	UDRIPKGNV89	AIR	6	SONIC	21	301.31
GTE PY6	GTEL/UDRI/2	UDRIPKGNV89	AIR	7	SONIC	21	301.31
GTE PY6	GTEL/UDRI/2	UDRIPKGNV89	AIR	8	SONIC	21	301.31
GTE PY6	GTEL/UDRI/2	UDRIPKGNV89	AIR	9	SONIC	21	304.07
GTE PY6	GTEL/UDRI/2	UDRIPKGNV89	AIR	10	SONIC	21	299.93
NT-154	NORTON/UDRI/2	UDRIPKGNV89	AIR	96	SONIC	20	310.96
NT-154	NORTON/UDRI/2	UDRIPKGNV89	AIR	97	SONIC	20	309.58
NT-154	NORTON/UDRI/2	UDRIPKGNV89	AIR	98	SONIC	20	309.58
NT-154	NORTON/UDRI/2	UDRIPKGNV89	AIR	99	SONIC	20	310.28
NT-154	NORTON/UDRI/2	UDRIPKGNV89	AIR	100	SONIC	20	310.28
NT-154	NORTON/UDRI/2	UDRIPKGNV89	AIR	100	SONIC	1000	302.69
NT-154	NORTON/UDRI/2	UDRIPKGNV89	AIR	99	SONIC	1000	297.86
NT-154	NORTON/UDRI/2	UDRIPKGNV89	AIR	98	SONIC	1000	296.49
NT-154	NORTON/UDRI/2	UDRIPKGNV89	AIR	97	SONIC	1000	296.49
NT-154	NORTON/UDRI/2	UDRIPKGNV89	AIR	96	SONIC	1000	299.93

SECTION 6. MODULUS OF ELASTICITY							
MATERIAL	BATCH CODE	REFERENCE CODE	TEST ENVIRON	SPECIMEN NUMBER	TEST TYPE	TEST TEMP °C	TEST MODULUS ELASTICITY GPa
NT-154	NORTON/UDRI/2	UDRIPKGNV89	AIR	96	SONIC	1400	297.17
NT-154	NORTON/UDRI/2	UDRIPKGNV89	AIR	97	SONIC	1400	293.73
NT-154	NORTON/UDRI/2	UDRIPKGNV89	AIR	98	SONIC	1400	290.97
NT-154	NORTON/UDRI/2	UDRIPKGNV89	AIR	99	SONIC	1400	294.42
NT-154	NORTON/UDRI/2	UDRIPKGNV89	AIR	99	SONIC	1400	294.42
NT-154	NORTON/UDRI/2	UDRIPKGNV89	AIR	100	SONIC	1400	294.42
SN-4	HOWMET/UDRI/2	UDRIPKGNV89	AIR	8	SONIC	21	174.00

Figure 2.39. A comparison of moduli of elasticity for two silicon nitrides and one silicon carbide.

SECTION 7. TENSILE TEST RESULTS

SECTION 7. TENSILE TEST RESULTS										COMMENTS
MATERIAL	BATCH CODE	REFERENCE CODE	TEST ENVIRON.	SPECIMEN NUMBER	TEMP °C	TENSILE		SPECIMEN DIAMETER mm	LOAD N	
						STRENGTH MPa				
SILICON CARBIDES										
HEXOLOY SA	SOHIO/UDRI/2	UDRIPKGNV89	AIR	3	21	251.0	6.36	7962.0		
HEXOLOY SA	SOHIO/UDRI/2	UDRIPKGNV89	AIR	4	21	247.0	6.36	7828.5		
HEXOLOY SA	SOHIO/UDRI/2	UDRIPKGNV89	AIR	5	21	294.0	6.51	9785.6		
HEXOLOY SA	SOHIO/UDRI/2	UDRIPKGNV89	AIR	6	21	307.0	6.33	9652.2		
HEXOLOY SA	SOHIO/UDRI/2	UDRIPKGNV89	AIR	7*	21	161.0	6.62	5560.0		Specimen failed at grind mark on the surface.
HEXOLOY SA	SOHIO/UDRI/2	UDRIPKGNV89	AIR	8	21	253.0	6.42	8184.3		
HEXOLOY SA	SOHIO/UDRI/2	UDRIPKGNV89	AIR	10	21	277.0	6.36	8807.0		
HEXOLOY SA	SOHIO/UDRI/2	UDRIPKGNV89	AIR	12	21	219.0	6.37	6983.4		
HEXOLOY SA	SOHIO/UDRI/2	UDRIPKGNV89	AIR	14	21	286.0	6.36	9073.9		
HEXOLOY SA	SOHIO/UDRI/2	UDRIPKGNV89	AIR	15	21	220.0	6.39	7072.3		
HEXOLOY SA	SOHIO/UDRI/2	UDRIPKGNV89	AIR	16	21	250.0	6.37	7961.9		
HEXOLOY SA	SOHIO/UDRI/2	UDRIPKGNV89	AIR	17	21	352.0	6.34	11120.0		
HEXOLOY SA	SOHIO/UDRI/2	UDRIPKGNV89	AIR	18	21	290.0	6.36	9207.4		
HEXOLOY SA	SOHIO/UDRI/2	UDRIPKGNV89	AIR	19*	21	246.0	6.37	7828.5		Specimen failed at grind mark on the surface.
HEXOLOY SA	SOHIO/UDRI/2	UDRIPKGNV89	AIR	20*	21	225.0	6.37	7161.3		Specimen failed at grind mark on the surface.
HEXOLOY SA	SOHIO/UDRI/2	UDRIPKGNV89	AIR	22*	21	128.0	6.35	4047.7		Specimen failed at grind mark on the surface.
HEXOLOY SA	SOHIO/UDRI/2	UDRIPKGNV89	AIR	23*	21	194.0	6.35	6138.2		Specimen failed at grind mark on the surface.
HEXOLOY SA	SOHIO/UDRI/2	UDRIPKGNV89	AIR	25*	21	208.0	6.35	6583.0		Specimen failed at grind mark on the surface.
HEXOLOY SA	SOHIO/UDRI/2	UDRIPKGNV89	AIR	26	21	228.0	6.36	7250.2		
HEXOLOY SA	SOHIO/UDRI/2	UDRIPKGNV89	AIR	27*	21	170.0	6.32	5337.6		Specimen failed at grind mark on the surface.
HEXOLOY SA	SOHIO/UDRI/2	UDRIPKGNV89	AIR	28*	21	157.0	6.35	4981.8		Specimen failed at grind mark on the surface.
HEXOLOY SA	SOHIO/UDRI/2	UDRIPKGNV89	AIR	30	21	257.0	6.36	8139.8		
HEXOLOY SA	SOHIO/UDRI/2	UDRIPKGNV89	AIR	38*	21	224.0	6.36	7116.8		Specimen failed at grind mark on the surface.
HEXOLOY SA	SOHIO/UDRI/2	UDRIPKGNV89	AIR	122*	21	220.0	6.36	6983.4		Specimen failed at grind mark on the surface.
HEXOLOY SA	SOHIO/UDRI/2	UDRIPKGNV89	AIR	123	21	191.0	6.35	6049.3		
HEXOLOY SA	SOHIO/UDRI/2	UDRIPKGNV89	AIR	36	1000	258.0	6.35	8184.3		
HEXOLOY SA	SOHIO/UDRI/2	UDRIPKGNV89	AIR	42	1000	237.0	6.35	7517.1		
HEXOLOY SA	SOHIO/UDRI/2	UDRIPKGNV89	AIR	46	1000	261.0	6.33	8228.8		
HEXOLOY SA	SOHIO/UDRI/2	UDRIPKGNV89	AIR	51	1000	204.0	6.32	6405.1		
HEXOLOY SA	SOHIO/UDRI/2	UDRIPKGNV89	AIR	52	1000	238.0	6.34	7517.1		
HEXOLOY SA	SOHIO/UDRI/2	UDRIPKGNV89	AIR	53	1000	245.0	6.36	7784.0		
HEXOLOY SA	SOHIO/UDRI/2	UDRIPKGNV89	AIR	54	1000	261.0	6.35	8273.3		
HEXOLOY SA	SOHIO/UDRI/2	UDRIPKGNV89	AIR	55	1000	195.0	6.35	6182.7		
HEXOLOY SA	SOHIO/UDRI/2	UDRIPKGNV89	AIR	56	1000	241.0	6.35	7650.6		
HEXOLOY SA	SOHIO/UDRI/2	UDRIPKGNV89	AIR	57	1000	219.0	6.36	6938.9		
HEXOLOY SA	SOHIO/UDRI/2	UDRIPKGNV89	AIR	60	1000	247.0	6.36	7828.5		
HEXOLOY SA	SOHIO/UDRI/2	UDRIPKGNV89	AIR	61	1000	219.0	6.36	6938.9		
HEXOLOY SA	SOHIO/UDRI/2	UDRIPKGNV89	AIR	62	1000	232.0	6.35	7339.2		
HEXOLOY SA	SOHIO/UDRI/2	UDRIPKGNV89	AIR	63	1000	269.0	6.34	8495.7		

SECTION 7. TENSILE TEST RESULTS. CONTINUED

MATERIAL	BATCH CODE	REFERENCE CODE	TEST ENVIRON.	SPECIMEN NUMBER	TEMP °C	TENSILE STRENGTH MPa	SPECIMEN DIAMETER mm	LOAD N	COMMENTS
HEXOLOYS A	SOHIO/UDRI/2	UDRI PKG NOV89	AIR	64	1000	271.0	6.35	8584.6	
HEXOLOYS A	SOHIO/UDRI/2	UDRI PKG NOV89	AIR	107	1200	182.0	6.34	5737.9	
HEXOLOYS A	SOHIO/UDRI/2	UDRI PKG NOV89	AIR	111	1200	208.0	6.31	6494.1	
HEXOLOYS A	SOHIO/UDRI/2	UDRI PKG NOV89	AIR	113	1200	214.0	6.35	6761.0	
HEXOLOYS A	SOHIO/UDRI/2	UDRI PKG NOV89	AIR	100	1200	267.0	6.33	8406.7	
HEXOLOYS A	SOHIO/UDRI/2	UDRI PKG NOV89	AIR	116	1200	268.0	6.34	8451.2	
HEXOLOYS A	SOHIO/UDRI/2	UDRI PKG NOV89	AIR	103	1200	268.0	6.37	8540.2	
HEXOLOYS A	SOHIO/UDRI/2	UDRI PKG NOV89	AIR	93	1200	269.0	6.34	8495.7	
HEXOLOYS A	SOHIO/UDRI/2	UDRI PKG NOV89	AIR	102	1200	274.0	6.33	8629.1	
HEXOLOYS A	SOHIO/UDRI/2	UDRI PKG NOV89	AIR	104	1200	278.0	6.33	8762.6	
HEXOLOYS A	SOHIO/UDRI/2	UDRI PKG NOV89	AIR	89	1200	279.0	6.34	8807.0	
HEXOLOYS A	SOHIO/UDRI/2	UDRI PKG NOV89	AIR	92	1200	289.0	6.35	9162.9	
HEXOLOYS A	SOHIO/UDRI/2	UDRI PKG NOV89	AIR	105	1200	292.0	6.35	9251.8	
HEXOLOYS A	SOHIO/UDRI/2	UDRI PKG NOV89	AIR	118	1200	295.0	6.34	9340.8	
HEXOLOYS A	SOHIO/UDRI/2	UDRI PKG NOV89	AIR	119	1200	301.0	6.37	9607.7	
HEXOLOYS A	SOHIO/UDRI/2	UDRI PKG NOV89	AIR	109	1200	314.0	6.34	9919.0	
HEXOLOYS A	SOHIO/UDRI/2	UDRI PKG NOV89	AIR	66	1400	258.0	6.35	8184.3	
HEXOLOYS A	SOHIO/UDRI/2	UDRI PKG NOV89	AIR	67	1400	222.0	6.36	7027.8	
HEXOLOYS A	SOHIO/UDRI/2	UDRI PKG NOV89	AIR	68	1400	237.0	6.35	7517.1	
HEXOLOYS A	SOHIO/UDRI/2	UDRI PKG NOV89	AIR	69	1400	233.0	6.33	7339.2	
HEXOLOYS A	SOHIO/UDRI/2	UDRI PKG NOV89	AIR	70	1400	182.0	6.36	5782.4	
HEXOLOYS A	SOHIO/UDRI/2	UDRI PKG NOV89	AIR	71	1400	258.0	6.36	8184.3	
HEXOLOYS A	SOHIO/UDRI/2	UDRI PKG NOV89	AIR	73	1400	270.0	6.34	8540.2	
HEXOLOYS A	SOHIO/UDRI/2	UDRI PKG NOV89	AIR	74	1400	270.0	6.35	8540.2	
HEXOLOYS A	SOHIO/UDRI/2	UDRI PKG NOV89	AIR	75	1400	286.0	6.35	9073.9	
HEXOLOYS A	SOHIO/UDRI/2	UDRI PKG NOV89	AIR	77	1400	281.0	6.35	8896.0	
HEXOLOYS A	SOHIO/UDRI/2	UDRI PKG NOV89	AIR	78	1400	237.0	6.34	7472.6	
HEXOLOYS A	SOHIO/UDRI/2	UDRI PKG NOV89	AIR	79	1400	229.0	6.34	7250.2	
HEXOLOYS A	SOHIO/UDRI/2	UDRI PKG NOV89	AIR	80	1400	251.0	6.35	7961.9	
HEXOLOYS A	SOHIO/UDRI/2	UDRI PKG NOV89	AIR	82	1400	223.0	6.34	7027.8	
HEXOLOYS A	SOHIO/UDRI/2	UDRI PKG NOV89	AIR	83	1400	233.0	6.37	7428.2	
HEXOLOYS A	SOHIO/UDRI/2	UDRI PKG NOV89	AIR	84	1400	288.0	6.35	9118.4	
HEXOLOYS A	SOHIO/UDRI/2	UDRI PKG NOV89	AIR	85	1400	269.0	6.34	8495.7	
HEXOLOYS A	SOHIO/UDRI/2	UDRI PKG NOV89	AIR	86	1400	264.0	6.35	8362.2	

SECTION 7. TENSILE TEST RESULTS. CONTINUED

MATERIAL	BATCH CODE	REFERENCE CODE	TEST ENVIRON.	SPECIMEN NUMBER	TEMP °C	TENSILE STRENGTH MPa	SPECIMEN DIAMETER mm	LOAD N	STRAIN %	LOADING RATE N/sec	YOUNG'S MODULUS GPa	COMMENTS
SILICON NITRIDES												
NT-154	NORTON/ORN/CIP	BM889ORN27	AIR	CP-3	1100	534.0			0.2240	0.125	236.9	LOADRATE=MPA/SEC
NT-154	NORTON/ORN/CIP	BM889ORN27	AIR	CP-11	1100	443.0			0.1820	0.125	242.3	LOADRATE=MPA/SEC
NT-154	NORTON/ORN/CAS	BM889ORN28	AIR	PC-5	1100	721.0			0.2470	35.000	290.4	LOADRATE=MPA/SEC
NT-154	NORTON/ORN/CAS	BM889ORN28	AIR	PC-6	1100	560.0			0.2260	0.125	247.4	LOADRATE=MPA/SEC
NT-154	NORTON/ORN/CAS	BM889ORN28	AIR	PC-10	1200	638.0				35.000		LOADRATE=MPA/SEC
NT-154	NORTON/ORN/CAS	BM889ORN28	AIR	PC-9	1200	524.0			0.2310	0.125	224.5	LOADRATE=MPA/SEC
NT-154	NORTON/ORN/CAS	BM889ORN28	AIR	PC-1*	1200	419.0				35.000		*FAILED IN BUTTONHEAD
NT-154	NORTON/ORN/CAS	BM889ORN28	AIR	PC-4*	1200	525.0				35.000		*FAILED IN BUTTONHEAD
NT-154	NORTON/ORN/CAS	BM889ORN28	AIR	PC-2	1300	382.0				35.000		LOADRATE=MPA/SEC
NT-154	NORTON/ORN/CAS	BM889ORN28	AIR	PC-3	1300	295.0			0.2420	0.125	211.9	LOADRATE=MPA/SEC
NT-154	NORTON/UDRI/2	UDRIPKGNV89	AIR	89	21	490.0	6.36	15568.0				
NT-154	NORTON/UDRI/2	UDRIPKGNV89	AIR	80	21	614.0	6.35	19437.8				
NT-154	NORTON/UDRI/2	UDRIPKGNV89	AIR	36	21	637.0	6.37	20282.9				
NT-154	NORTON/UDRI/2	UDRIPKGNV89	AIR	48	21	638.0	6.36	20238.4				
NT-154	NORTON/UDRI/2	UDRIPKGNV89	AIR	9	21	654.0	6.35	20727.7				
NT-154	NORTON/UDRI/2	UDRIPKGNV89	AIR	16	21	684.0	6.34	21617.3				
NT-154	NORTON/UDRI/2	UDRIPKGNV89	AIR	39	21	684.0	6.35	21661.8				
NT-154	NORTON/UDRI/2	UDRIPKGNV89	AIR	21	21	702.0	6.35	22240.0				
NT-154	NORTON/UDRI/2	UDRIPKGNV89	AIR	75	21	718.0	6.36	22773.8				
NT-154	NORTON/UDRI/2	UDRIPKGNV89	AIR	56	21	767.0	6.34	24197.1				
NT-154	NORTON/UDRI/2	UDRIPKGNV89	AIR	7	21	782.0	6.35	24775.4				
NT-154	NORTON/UDRI/2	UDRIPKGNV89	AIR	43	21	855.0	6.35	27088.3				
NT-154	NORTON/UDRI/2	UDRIPKGNV89	AIR	35	21	857.0	6.35	27132.8				
NT-154	NORTON/UDRI/2	UDRIPKGNV89	AIR	54	21	895.0	6.35	28378.2				
NT-154	NORTON/UDRI/2	UDRIPKGNV89	AIR	34	21	906.0	6.35	28689.6				
NT-154	NORTON/UDRI/2	UDRIPKGNV89	AIR	59	1000	424.0	6.34	13388.5				
NT-154	NORTON/UDRI/2	UDRIPKGNV89	AIR	111	1000	434.0	6.34	13699.8				
NT-154	NORTON/UDRI/2	UDRIPKGNV89	AIR	107	1000	449.0	6.35	14233.6				
NT-154	NORTON/UDRI/2	UDRIPKGNV89	AIR	58	1000	525.0	6.36	16680.0				
NT-154	NORTON/UDRI/2	UDRIPKGNV89	AIR	108	1000	531.0	6.35	16813.4				
NT-154	NORTON/UDRI/2	UDRIPKGNV89	AIR	104	1000	546.0	6.49	18058.9				
NT-154	NORTON/UDRI/2	UDRIPKGNV89	AIR	78	1000	550.0	6.34	17391.7				
NT-154	NORTON/UDRI/2	UDRIPKGNV89	AIR	106	1000	550.0	6.38	17569.6				
NT-154	NORTON/UDRI/2	UDRIPKGNV89	AIR	88	1000	565.0	6.41	18236.8				
NT-154	NORTON/UDRI/2	UDRIPKGNV89	AIR	91	1000	576.0	6.36	18281.3				
NT-154	NORTON/UDRI/2	UDRIPKGNV89	AIR	87	1000	591.0	6.34	18681.6				
NT-154	NORTON/UDRI/2	UDRIPKGNV89	AIR	79	1000	598.0	6.38	19081.9				
NT-154	NORTON/UDRI/2	UDRIPKGNV89	AIR	109	1000	626.0	6.35	19838.1				
NT-154	NORTON/UDRI/2	UDRIPKGNV89	AIR	110	1000	654.0	6.35	20683.2				
NT-154	NORTON/UDRI/2	UDRIPKGNV89	AIR	72	1000	661.0	6.35	20905.6				

SECTION 7. TENSILE TEST RESULTS, CONTINUED

MATERIAL	BATCH CODE	REFERENCE CODE	TEST ENVIRON.	SPECIMEN NUMBER	TEMP °C	TENSILE STRENGTH MPa	SPECIMEN DIAMETER mm	LOAD N	COMMENTS
NT-154	NORTON/UDRI/2	UDRI PKGNV89	AIR	60	1200	342.0	6.56	11564.8	
NT-154	NORTON/UDRI/2	UDRI PKGNV89	AIR	8	1200	438.0	6.35	13877.8	
NT-154	NORTON/UDRI/2	UDRI PKGNV89	AIR	92	1200	444.0	6.35	14055.7	
NT-154	NORTON/UDRI/2	UDRI PKGNV89	AIR	53	1200	485.0	6.35	15345.6	
NT-154	NORTON/UDRI/2	UDRI PKGNV89	AIR	6	1200	496.0	6.35	15701.4	
NT-154	NORTON/UDRI/2	UDRI PKGNV89	AIR	4	1200	508.0	6.35	16101.8	
NT-154	NORTON/UDRI/2	UDRI PKGNV89	AIR	5	1200	512.0	6.34	16190.7	
NT-154	NORTON/UDRI/2	UDRI PKGNV89	AIR	18	1200	523.0	6.35	16546.6	
NT-154	NORTON/UDRI/2	UDRI PKGNV89	AIR	90	1200	533.0	6.35	16902.4	
NT-154	NORTON/UDRI/2	UDRI PKGNV89	AIR	69	1200	537.0	6.33	16902.4	
NT-154	NORTON/UDRI/2	UDRI PKGNV89	AIR	17	1200	542.0	6.35	17169.3	
NT-154	NORTON/UDRI/2	UDRI PKGNV89	AIR	83	1200	581.0	6.35	18414.7	
NT-154	NORTON/UDRI/2	UDRI PKGNV89	AIR	15	1200	610.0	6.35	19304.3	
NT-154	NORTON/UDRI/2	UDRI PKGNV89	AIR	66	1200	623.0	6.35	19749.1	
NT-154	NORTON/UDRI/2	UDRI PKGNV89	AIR	73	1200	624.0	6.36	19793.6	
NT-154	NORTON/UDRI/2	UDRI PKGNV89	AIR	55	1400	225.0	6.35	7116.8	
NT-154	NORTON/UDRI/2	UDRI PKGNV89	AIR	47	1400	264.0	6.35	8362.2	
NT-154	NORTON/UDRI/2	UDRI PKGNV89	AIR	46	1400	287.0	6.36	9118.4	
NT-154	NORTON/UDRI/2	UDRI PKGNV89	AIR	41	1400	236.0	6.35	10319.4	
NT-154	NORTON/UDRI/2	UDRI PKGNV89	AIR	44	1400	339.0	6.34	10719.7	
NT-154	NORTON/UDRI/2	UDRI PKGNV89	AIR	38	1400	345.0	6.35	10942.1	
NT-154	NORTON/UDRI/2	UDRI PKGNV89	AIR	50	1400	349.0	6.35	11075.5	
NT-154	NORTON/UDRI/2	UDRI PKGNV89	AIR	10	1400	353.0	6.34	11164.5	
NT-154	NORTON/UDRI/2	UDRI PKGNV89	AIR	19	1400	357.0	6.35	11297.9	
NT-154	NORTON/UDRI/2	UDRI PKGNV89	AIR	14	1400	365.0	6.35	11564.8	
NT-154	NORTON/UDRI/2	UDRI PKGNV89	AIR	45	1400	366.0	6.34	11564.8	
NT-154	NORTON/UDRI/2	UDRI PKGNV89	AIR	40	1400	377.0	6.36	11965.1	
NT-154	NORTON/UDRI/2	UDRI PKGNV89	AIR	51	1400	388.0	6.36	12321.0	
NT-154	NORTON/UDRI/2	UDRI PKGNV89	AIR	52	1400	399.0	6.35	12632.3	
NT-154	NORTON/UDRI/2	UDRI PKGNV89	AIR	49	1400	406.0	6.36	12899.2	
ZIRCONIAS									
MS-PSZ	NILCRA/ORN/L1	SA11ORN/L306	AIR	26	25	468.0			
MS-PSZ	NILCRA/ORN/L1	SA11ORN/L306	AIR	28	400	341.0			
MS-PSZ	NILCRA/ORN/L1	SA11ORN/L306	AIR	29	400	440.0			
MS-PSZ	NILCRA/ORN/L1	SA11ORN/L306	AIR	30	800	265.0			
MS-PSZ	NILCRA/ORN/L1	SA11ORN/L306	AIR	31	800	258.0			
MS-PSZ	NILCRA/ORN/L1	SA11ORN/L306	AIR	38	800	190.0			
MS-PSZ	NILCRA/ORN/L1	SA11ORN/L306	AIR	32	1000	222.0			
MS-PSZ	NILCRA/ORN/L1	SA11ORN/L306	AIR	33	1000	194.0

Figure 2.40. A comparison of tensile strengths for three batches of NT-154.

Figure 2.41 A comparison of tensile strengths for two classes of ceramic materials.

SECTION 8. THERMAL EXPANSION TEST RESULTS

MATERIAL	BATCH CODE	REFERENCE CODE	SPECIMEN NUMBER	TEMP °C	TEMPERATURE RANGE °C	COEFFICIENT OF THERMAL EXPANSION 1.E-06/°C
SILICON CARBIDE						
HEXOLOYS A	SOHIO/UDRI/2	UDRIPKGNV89	1	1400	25-1400	4.80
HEXOLOYS A	SOHIO/UDRI/2	UDRIPKGNV89	2	1400	25-1400	5.00
HEXOLOYS A	SOHIO/UDRI/2	UDRIPKGNV89	3	1400	25-1400	4.80
HEXOLOYS A	SOHIO/UDRI/2	UDRIPKGNV89	4	1400	25-1400	4.90
HEXOLOYS A	SOHIO/UDRI/2	UDRIPKGNV89	5	1400	25-1400	4.90
SILICON NITRIDE						
GTE PY6	GTEL/UDRI/2	UDRIPKGNV89	1	850	25-850	3.10
GTE PY6	GTEL/UDRI/2	UDRIPKGNV89	2	850	25-850	3.20
GTE PY6	GTEL/UDRI/2	UDRIPKGNV89	3	850	25-850	3.10
GTE PY6	GTEL/UDRI/2	UDRIPKGNV89	4	850	25-850	3.20
GTE PY6	GTEL/UDRI/2	UDRIPKGNV89	5	850	25-850	3.20
GTE PY6	GTEL/UDRI/2	UDRIPKGNV89	1	1400	25-1400	3.40
GTE PY6	GTEL/UDRI/2	UDRIPKGNV89	2	1400	25-1400	3.50
GTE PY6	GTEL/UDRI/2	UDRIPKGNV89	3	1400	25-1400	3.50
GTE PY6	GTEL/UDRI/2	UDRIPKGNV89	4	1400	25-1400	3.40
GTE PY6	GTEL/UDRI/2	UDRIPKGNV89	5	1400	25-1400	3.40

Figure 2.42. A comparison of thermal expansion coefficients between a silicon carbide and a silicon nitride.

SECTION 9. MOR 4-POINT BEND STRENGTH TEST RESULTS FOR BRAZED SPECIMENS

BASE MATERIAL = MG-PSZ
 BATCH CODE FOR BASE MATERIAL = CORNING ZYCRON L
 REFERENCE CODE = BM1288BCL65
 OTHER MATERIAL = MG-PSZ
 BATCH CODE FOR OTHER MATERIAL = CORNING ZYCRON L

FILLER MATERIAL = CaO-TiO₂-SiO₂+30wt% ZrO₂
 JOINT METHOD = HOT PRESSED
 JOINT PROCESS = HP/1420C/13.79MPa
 NO ADDITIONAL HEAT TREATMENT AFTER BRAZE
 TESTS WERE PERFORMED IN AIR

2 MG-PSZ (Corning Zycron L) billets (D-shaped) were joined together by hotpressing the MG-PSZ+CTS(CaO-TiO₂-SiO₂)+MG-PSZ sandwich in a creep testing unit at 1420C and 13.79MPa. Bend bars, 2.54x5.08x63.5mm, were machined from the 50.8mm diameter x 38.1mm long cylinder and tested in a 4-point fixture with outer span of 31.75mm and 19.05mm inner span. A thermal expansion mismatch between the materials caused a poor quality joint.

These specimens were joined in the same manner as mentioned before except that 30wt% ZrO₂ was added to the CTS layer to overcome thermal expansion problems which caused extensive cracking. Like before, 2 D-shaped Mg-PSZ billets were pressed together with the CTS-ZrO layer in between. Specimens were cut so that the joint was in the middle. Work was performed by R.A.Schmidt, A.T.Hopper, J. Ahmad and R.A.Rosenfield at Battelle Columbus Laboratories.

TEMP °C	SPECIMEN NUMBER	BEND STRENGTH MPa	WIDTH mm	THICK mm
25	HP5-ZZB3	81.9	5.08	2.54
25	HP5-ZZB4	63.7	5.08	2.54
25	HP5-ZZB5	71.5	5.08	2.54
25	HP5-ZZB6	79.5	5.08	2.54
25	HP5-ZZB8	60.9	5.08	2.54
25	HP5-ZZB9	53.6	5.08	2.54
25	HP5ZZB10	54.4	5.08	2.54
25	HP5ZZB11	49.3	5.08	2.54
25	HP5ZZB12	72.9	5.08	2.54
25	HP5ZZB13	68.9	5.08	2.54

BASE MATERIAL = MG-PSZ/TI COATING
 BASE MATERIAL BATCH CODE = CORNING-ZYCRON L
 REFERENCE CODE = SA12BCL279
 OTHER MATERIAL = CAST IRON
 OTHER MATERIAL BATCH CODE = 60% PEARLITE

FILLER MATERIAL = L&M 604
 JOINT METHOD = HOT PRESSING
 NO ADDITIONAL HEAT TREATMENT AFTER BRAZE
 TESTS WERE PERFORMED IN AIR

A 50.8mm square x 19.05mm thick piece of nodular cast iron (ground with 240-grit SiC paper) was brazed to a 50.8mm diameter x 19.05mm thick disk of MG-PSZ (Corning Zycron L) which had been coated with .3um thick layer of Ti at NASA-Lewis using RF-sputter. The cast iron was NOT coated with copper! Each specimen was ultrasonically cleaned w/acetone, then alcohol. The iron was placed on top the MG-PSZ to provide a load during brazing. Details of the braze: temperature increased 30C/minute to 650C, then 7C/minute to 720C. Power was then shut off and the joint allowed to cool to room temperature. All work was performed in a vacuum at about 1.E-05 torr.

TEMP °C	SPECIMEN NUMBER	BEND STRENGTH MPa	WIDTH mm	THICK mm
25	MCB-4	164.0	5.08	2.54
25	MCB-5	76.0	5.08	2.54
25	MCB-6	161.0	5.08	2.54

SECTION 9. MOR 4-POINT BEND STRENGTH TEST RESULTS FOR BRAZED SPECIMENS, CONTINUED

BASE MATERIAL = MG-PSZ

BATCH CODE FOR BASE MATERIAL = CORNING ZYCRON L

REFERENCE CODE = SA11BCL209

OTHER MATERIAL = MG-PSZ

BATCH CODE FOR OTHER MATERIAL = CORNING ZYCRON L

FILLER MATERIAL = CaO-TiO₂-SiO₂

JOINT METHOD = HOT PRESSED

JOINT PROCESS = HP/1420C/13.79MPa

NO ADDITIONAL HEAT TREATMENT AFTER BRAZE

TESTS WERE PERFORMED IN AIR

2 MG-PSZ (Corning Zycron L) billets were joined together by hotpressing the MG-PSZ+CTS(CaO-TiO₂-SiO₂)+MG-PSZ sandwich in a creep testing unit at 1420C and 13.79MPa. Bend bars, 2.54x5.08x63.5mm, were machined from the 50.8mm diameter x 38.1mm long cylinder and tested in a 4-point fixture with outer span of 31.75mm and 19.05mm inner span. A thermal expansion mismatch between the materials caused a poor quality joint. Work was performed by R.A.Schmidt, A.T.Hopper, J. Ahmad and R.A.Rosenfield at Battelle Columbus Laboratories.

TEMP °C	SPECIMEN NUMBER	LOAD N	BEND STRENGTH MPa	WIDTH mm	THICK mm	COMMENTS
25	ZZB-3	135.7	81.9	5.08	2.54	CTS-BONDED ZrO ₂
25	ZZB-4	105.0	63.7	5.08	2.54	CTS-BONDED ZrO ₂
25	ZZB-5	117.9	71.5	5.08	2.54	CTS-BONDED ZrO ₂
25	ZZB-6	130.8	79.5	5.08	2.54	CTS-BONDED ZrO ₂

BASE MATERIAL = MG-PSZ/Ti

BASE MATERIAL BATCH CODE = CORNING-ZYCRONL

REFERENCE CODE = SA11BCL212

OTHER MATERIAL = CAST IRON/CU

OTHER MATERIAL BATCH CODE = 60% PEARLITE

FILLER MATERIAL = L&M 604

JOINT METHOD = ACTIVE SUBSTRATE

JOINT PROCESS = HP/750C/10min./vac.

NO ADDITIONAL HEAT TREATMENT AFTER BRAZE

TESTS WERE PERFORMED IN AIR

Specimens (2.5x5.08x63.5mm) were cut from MG-PSZ with Ti coating (plasma ion etched for 1 minute, then RF-sputtered 15 minutes at 6.67e-12MPa, 1.4um thick), joined by active substrate brazing (Lucas-Milhaupt No. 604, Ag-30Cu-10Sn) to nodular cast iron (60% pearlite) that had been vapor-deposit plated with copper. Both materials had been ground to 0.3um finish. The bend strength was calculated using the monolithic materials equation. Work performed at Battelle Columbus Laboratories by A.T.Hopper, J.Ahmad and A. Rosenfield.

TEMP °C	SPECIMEN NUMBER	LOAD N	BEND STRENGTH MPa	WIDTH mm	THICK mm
25	MCB-1	151.0	88.9	5.08	2.54
25	MCB-2	138.0	81.4	5.08	2.54
25	MCB-3	138.0	80.9	5.08	2.54

SECTION 9. MOR 4-POINT BEND STRENGTH TEST RESULTS FOR BRAZED SPECIMENS, CONTINUED

BASE MATERIAL = MS-PSZ/TI COATING

BASE MATERIAL BATCH CODE = NILSEN/ORNLIJ1

REFERENCE CODE = SA10ORNLI75

OTHER MATERIAL = TITANIUM

OTHER MATERIAL BATCH CODE = ASTM/B265 GR1

FILLER MATERIAL = BR604

JOINT METHOD = ACTIVE SUBSTRATE

JOINT PROCESS = BRAZED IN VAC@735C

NO ADDITIONAL HEAT TREATMENT AFTER BRAZE

TESTS WERE PERFORMED IN AIR

See SA10ORNLI74 for main details. These specimens were Nilsen MS-PSZ brazed to nodular cast iron, grade 8003, using active substrate process(AS), where the zirconia plate was vapor coated with commercially pure titanium and the iron was plated with copper to improve wetting. Brazing was done in a vacuum with Handy & Harmon Braze 604 (BVAg-18). Load rate was 22.7 kg/sec. Outer span was 19.05mm, inner span was 6.35mm. Work performed at ORNL by Mike Santella.

TEMP °C	SPECIMEN NUMBER	BEND STRENGTH MPa	WIDTH mm	THICK mm
25	MCB-343A	435.0	2.50	2.00
25	MCB-344A	309.0	2.50	2.00
25	MCB-345A	351.0	2.50	2.00
25	MCB-364A	345.0	2.50	2.00
25	MCB-365A	307.0	2.50	2.00
25	MCB-366A	399.0	2.50	2.00
200	MCB-298D	353.0	2.50	2.00
200	MCB-344B	287.0	2.50	2.00
200	MCB-345B	319.0	2.50	2.00
200	MCB-364B	280.0	2.50	2.00
200	MCB-365B	106.0	2.50	2.00
200	MCB-365C	142.0	2.50	2.00
200	MCB-366B	332.0	2.50	2.00
200	MCB-366C	309.0	2.50	2.00
400	MCB-298E	182.0	2.50	2.00
400	MCB-344C	180.0	2.50	2.00
400	MCB-344D	168.0	2.50	2.00
400	MCB-345C	212.0	2.50	2.00
400	MCB-364C	173.0	2.50	2.00
400	MCB-364D	166.0	2.50	2.00
400	MCB-365D	197.0	2.50	2.00
400	MCB-366C	189.0	2.50	2.00
400	MCB-366D	137.0	2.50	2.00
575	MCB-298F	118.0	2.50	2.00
575	MCB-344E	100.0	2.50	2.00
575	MCB-345D	128.0	2.50	2.00
575	MCB-345E	107.0	2.50	2.00
575	MCB-364E	109.0	2.50	2.00
575	MCB-364F	103.0	2.50	2.00
575	MCB-365E	49.0	2.50	2.00

SECTION 9. MOR 4-POINT BEND STRENGTH TEST RESULTS FOR BRAZED SPECIMENS, CONTINUED

BASE MATERIAL = MS-PSZ/TI COATING
 BASE MATERIAL BATCH CODE = NILSEN/ORNL/J1
 REFERENCE CODE = SA10ORN175
 OTHER MATERIAL = CAST IRON/COPPER COATING
 OTHER MATERIAL BATCH CODE = CUMMINS/GR.8003

FILLER MATERIAL = BR604
 JOINT METHOD = ACTIVE SUBSTRATE
 JOINT PROCESS = BRAZED IN VAC@735C
 NO ADDITIONAL HEAT TREATMENT AFTER BRAZE
 TESTS WERE PERFORMED IN AIR

See SA10ORN174 for main details. These specimens were Nilsen MS-PSZ brazed to nodular cast iron, grade 8003, using active substrate process(AS), where the zirconia plate was vapor coated with commercially pure titanium and the iron was plated with copper to improve wetting. Brazing was done in a vacuum with Handy & Harmon Braze 604 (BVAg-18). Load rate was 22.7 kg/sec. Outer span was 19.05mm, inner span was 6.35mm. Work performed at ORNL by Mike Santella.

TEMP °C	SPECIMEN NUMBER	BEND STRENGTH MPa	WIDTH mm	THICK mm
25	MCB-351A	25.0	2.50	2.00
25	MCB-367A	36.0	2.50	2.00
25	MCB-369A	102.0	2.50	2.00
200	MCB-300F	363.0	2.50	2.00
200	MCB-349A	58.0	2.50	2.00
200	MCB-350B	237.0	2.50	2.00
200	MCB-367B	326.0	2.50	2.00
400	MCB-300G	364.0	2.50	2.00
400	MCB-349B	80.0	2.50	2.00
400	MCB-350C	249.0	2.50	2.00
400	MCB-367C	358.0	2.50	2.00
400	MCB-369B	111.0	2.50	2.00
400	MCB-369C	53.0	2.50	2.00
575	MCB-300H	39.0	2.50	2.00
575	MCB-349C	28.0	2.50	2.00
575	MCB-350D	101.0	2.50	2.00
575	MCB-367D	70.0	2.50	2.00
575	MCB-367E	28.0	2.50	2.00
575	MCB-369C	27.0	2.50	2.00
575	MCB-369D	16.0	2.50	2.00

SECTION 9. MOR 4-POINT BEND STRENGTH TEST RESULTS FOR BRAZED SPECIMENS, CONTINUED

BASE MATERIAL = MS-PSZ/TI COATING	FILLER MATERIAL = BR604
BASE MATERIAL BATCH CODE = NILSEN/ORN/LJ1	JOINT METHOD = ACTIVE SUBSTRATE
REFERENCE CODE = SA10ORN/L175	JOINT PROCESS = BRAZED IN VAC@735C
OTHER MATERIAL = MS-PSZ/TI COATING	NO ADDITIONAL HEAT TREATMENT AFTER BRAZE
OTHER MATERIAL BATCH CODE = NILSEN/ORN/LJ1	TESTS WERE PERFORMED IN AIR

Individual plates (25x14x3mm) were joined along the 25x3mm edge, surface ground on both faces, polished to 1 micrometer diamond finish on the tensile face, then cut into MOR bars 28x2.5x2mm with the brazed joint in the middle of each bar. Outer span 19.05mm, inner span 6.35mm. Work done by Mike Santella at ORNL.

These specimens were Nilsen MS-PSZ brazed to nodular cast iron grade 8003 (from Cummins Engine Co.), using active substrate process(AS), where the zirconia plate was vapor coated with commercially pure titanium and the iron was plated with copper to improve wetting. Brazing was done in a vacuum with Handy & Harmon Braze 604 (BVAg-18). Load rate was 22.7 kg/sec. Outer span was 19.05mm, inner span was 6.35mm. Work performed at ORNL by Mike Santella.

TEMP °C	SPECIMEN NUMBER	BEND STRENGTH MPa	WIDTH mm	THICK mm
25	MCB-299A	571.0	2.50	2.00
25	MCB-299B	532.0	2.50	2.00
25	MCB-299C	493.0	2.50	2.00
25	MCB-346A	327.0	2.50	2.00
25	MCB-347A	269.0	2.50	2.00
25	MCB-348A	314.0	2.50	2.00
25	MCB-361A	332.0	2.50	2.00
25	MCB-362A	432.0	2.50	2.00
25	MCB-363A	312.0	2.50	2.00
200	MCB-299D	459.0	2.50	2.00
200	MCB-346B	444.0	2.50	2.00
200	MCB-347B	323.0	2.50	2.00
200	MCB-347C	293.0	2.50	2.00
200	MCB-348B	383.0	2.50	2.00
200	MCB-362B	239.0	2.50	2.00
200	MCB-363B	342.0	2.50	2.00
400	MCB-299E	356.0	2.50	2.00
400	MCB-346C	370.0	2.50	2.00
400	MCB-347D	228.0	2.50	2.00
400	MCB-348C	325.0	2.50	2.00
400	MCB-361B	242.0	2.50	2.00
400	MCB-362C	319.0	2.50	2.00
400	MCB-362D	299.0	2.50	2.00
400	MCB-363C	199.0	2.50	2.00
400	MCB-363D	296.0	2.50	2.00
575	MCB-299F	61.0	2.50	2.00
575	MCB-346D	149.0	2.50	2.00
575	MCB-347E	124.0	2.50	2.00
575	MCB-348D	127.0	2.50	2.00
575	MCB-348E	94.0	2.50	2.00
575	MCB-362E	125.0	2.50	2.00
575	MCB-362E	71.0	2.50	2.00
575	MCB-363D	109.0	2.50	2.00
575	MCB-363E	48.0	2.50	2.00

Figure 2.43. A comparison of strengths of three different PSZ-to-cast iron brazed joints.

Figure 2.44. MOR 4-point bend strength test results for three brazed Ti-coated MS-PSZ joints.

SECTION 10. SHEAR STRENGTH OF BRAZED SPECIMENS

BASE MATERIAL = MS-PSZ
 BASE MATERIAL BATCH CODE = NILSEN/ORN/LJ1
 REFERENCE CODE = SA10ORN/L171
 OTHER MATERIAL = CAST IRON/COPPER COATING
 OTHER MATERIAL BATCH CODE = CUMMINS/GR.8003

FILLER MATERIAL = INCUSIL-15ABA
 JOINT METHOD = ACTIVE FILLER METAL
 JOINT PROCESS = BRAZED IN VAC@770C
 NO POST BRAZE HEAT TREATMENT
 TESTS WERE PERFORMED IN AIR

A pad/bar type specimen was used, with the pad 12.7x12.7x5.1mm and the bar 12.7x5.1x3.4mm. The pad is OTHER MATERIAL, the bar is BASE MATERIAL.

The AFM (active filler metal) method used Incusil-15 ABA, composed of Ag-23.5Cu-14.5In-1.3Ti (wt%). Testing was done in a pad/bar tester on a 44.5kN Instron tensile machine equipped with a clam-shell furnace and a quartz line for elevated temperature testing. Work was performed at Oak Ridge National Laboratory by Mike Santella.

SPECIMEN CODE	TEMP °C	SHEAR STRENGTH MPa	COMMENTS
MCB-60	25	127.0	UNPOLISHD ZrO2, UNCOAT Fe
MCB-61	25	165.0	UNPOLISHD ZrO2,Cu-COAT Fe
MCB-62	25	77.0	POLISHD ZrO2, UNCOAT Fe
MCB-63	25	11.0	POLISHD ZrO2,Cu-COAT Fe
MCB-79	400	140.0	UNPOLISHD ZrO2,Cu-COAT Fe
MCB-96	400	28.0	UNPOLISHD ZrO2,Cu-COAT Fe

BASE MATERIAL = MS-PSZ
 BASE MATERIAL BATCH CODE = NILSEN/ORN/LJ1
 REFERENCE CODE = SA10ORN/L172
 OTHER MATERIAL = TITANIUM
 OTHER MATERIAL BATCH CODE = ASTM/B265 GR1

FILLER MATERIAL = INCUSIL-15ABA
 JOINT METHOD = ACTIVE FILLER METAL
 JOINT PROCESS = BRAZED IN VAC@770C
 TESTS WERE PERFORMED IN AIR

A pad/bar type specimen was used, with the pad 12.7x12.7x5.1mm and the bar 12.7x5.1x3.4mm. The pad is OTHER MATERIAL, the bar is BASE MATERIAL.

The AFM (active filler metal) method used Incusil-15 ABA, composed of Ag-23.5Cu-14.5In-1.3Ti (wt%). Testing was done in a pad/bar tester on a 44.5kN Instron tensile machine equipped with a clam-shell furnace and a quartz line for elevated temperature testing. Work was performed at Oak Ridge National Laboratory by Mike Santella.

SPECIMEN CODE	TEMP °C	POST-BRAZE HEAT TREATMENT	SHEAR STRENGTH MPa	COMMENTS
MCB-111	400	400C/100h	67.0	UNPOLISHD ZrO2
MCB-187	25	400C/500h	39.0	UNPOLISHD ZrO2
MCB-188	25	400C/500h	111.0	UNPOLISHD ZrO2
MCB-108	25	AS BRAZED	289.0	UNPOLISHD ZrO2
MCB-109	400	AS BRAZED	123.0	UNPOLISHD ZrO2

SECTION 10. SHEAR STRENGTH OF BRAZED SPECIMENS, CONTINUED

BASE MATERIAL = MS-PSZ/ TITANIUM COATING
 BASE MATERIAL BATCH CODE = NILSEN/ORN/LJ1
 REFERENCE CODE = SA10ORN/L170
 OTHER MATERIAL = CAST IRON/COPPER COATING
 OTHER MATERIAL BATCH CODE = CUMMINS/GR.8003

FILLER MATERIAL = BR 604
 JOINT METHOD = ACTIVE SUBSTRATE
 JOINT PROCESS = BRAZED IN VAC@735C
 TESTS WERE PERFORMED IN AIR

A pad/bar type specimen was used, with the pad 12.7x12.7x5.1mm and the bar 12.7x5.1x3.4mm. The pad is OTHER MATERIAL, the bar is BASE MATERIAL. The joint was produced by active substrate: the zirconia specimens were vapor coated with pure titanium to .6 micrometers thick. Specimens were not preheated before coating. The nodular cast iron specimens were cleaned, then electroplated with pure copper to improve wetting and bonding capabilities. All brazing was done in a vacuum. Handy & Harmon Braze 604 (BVAg-18) composed of Ag-30Cu-10Sn (wt%) was the filler material.

SPECIMEN CODE	TEMP °C	POST-BRAZE HEAT TREATMENT	SHEAR STRENGTH MPa	COMMENTS
MCB-65	25	AS BRAZED	194.0	
MCB-66	25	AS BRAZED	191.0	
MCB-70	400	AS BRAZED	85.0	
MCB-71	400	AS BRAZED	96.0	
MCB-73	400	400C/100h	30.0	

BASE MATERIAL = MS-PSZ/ TITANIUM COATING
 BASE MATERIAL BATCH CODE = NILSEN/ORN/LJ1
 REFERENCE CODE = SA10ORN/L170
 OTHER MATERIAL = TITANIUM
 OTHER MATERIAL BATCH CODE = ASTM/B265 GR1

FILLER MATERIAL = BR 604
 JOINT METHOD = ACTIVE SUBSTRATE
 JOINT PROCESS = BRAZED IN VAC@735C
 TESTS WERE PERFORMED IN AIR

A pad/bar type specimen was used, with the pad 12.7x12.7x5.1mm and the bar 12.7x5.1x3.4mm. The pad is OTHER MATERIAL, the bar is BASE MATERIAL. The joint was produced by active substrate: the zirconia specimens were vapor coated with pure titanium to .6 micrometers thick. Specimens were not preheated before coating. All brazing was done in a vacuum. Handy & Harmon Braze 604 (BVAg-18), composed of Ag-30Cu-10Sn (wt%), was the filler material.

SPECIMEN CODE	TEMP °C	POST-BRAZE HEAT TREATMENT	SHEAR STRENGTH MPa	COMMENTS
MCB-97	25	AS BRAZED	262.0	
MCB-98	400	AS BRAZED	133.0	
MCB-171	25	400C/500h	291.0	
MCB-172	25	400C/500h	259.0	
MCB-100	400	400C/100h	123.0

Figure 2.45. Shear strengths of four MS-PSZ-titanium joints made with different processes and heat treatments.

Figure 2.46. Shear strengths of three MS-PSZ-to-Cast Iron joints, all in the as-brazed condition.

INTERNAL DISTRIBUTION

1-2.	Central Research Library	42.	M. G. Jenkins
3.	Document Reference Section	43.	D. R. Johnson
4-5.	Laboratory Records Department	44.	W. F. Jones
6.	Laboratory Records, ORNL RC	45.	D. Joslin
7.	ORNL Patent Section	46.	R. R. Judkins
8-10.	M&C Records Office	47.	M. A. Karnitz
11.	L. F. Allard, Jr.	48.	M. R. Kass
12.	L. D. Armstrong	49-53.	B. L. P. Keyes
13.	P. F. Becher	54.	H. D. Kimrey, Jr.
14.	R. F. Bernal	55.	T. G. Kollie
15.	T. M. Besmann	56.	K. C. Liu
16.	P. J. Blau	57.	E. L. Long, Jr.
17.	A. Bleier	58.	W. D. Manly
18.	E. E. Bloom	59.	R. W. McClung
19.	K. W. Boling	60.	D. J. McGuire
20.	R. A. Bradley	61.	J. R. Merziman
21.	C. R. Brinkman	62.	D. L. Moses
22.	V. R. Bullington	63.	T. A. Nolan
23.	R. S. Carlsmith	64.	A. E. Pasto
24.	P. T. Carlson	65.	J. L. Rich
25.	G. M. Caton	66.	C. R. Richmond
26.	S. J. Chang	67.	J. M. Robbins
27.	R. H. Cooper, Jr.	68.	M. L. Santella
28.	B. L. Cox	69.	A. C. Schaffhauser
29.	D. F. Craig	70.	S. Scott
30.	S. A. David	71.	G. M. Slaughter
31.	J. H. DeVan	72.	E. J. Soderstrom
32.	J. L. Ding	73.	D. P. Stinton
33.	M. K. Ferber	74.	R. W. Swindeman
34.	F. M. Foust	75.	V. J. Tennery
35.	W. Fulkerson	76.	T. N. Tiegs
36.	R. L. Graves	77.	J. R. Weir, Jr.
37.	D. L. Greene	78.	B. H. West
38.	M. H. Harris	79.	F. W. Wiffen
39.	E. E. Hoffman	80.	S. G. Winslow
40.	C. R. Hubbard	81.	J. M. Wyrick
41.	M. A. Janney	82.	C. S. Yust

EXTERNAL DISTRIBUTION

<p>83. James H. Adair
University of Florida
Materials Science and
Engineering
317 MAE Bldg.
Gainesville, FL 32611-2066</p>	<p>91. Richard T. Alpaugh
U.S. Department of Energy
Advanced Propulsion Division
CE-322, Forrestal Building
Washington, DC 20585</p>
<p>84. Donald F. Adams
University of Wyoming
Mechanical Engineering
Department
P. O. Box 3295
Laramie, WY 82071</p>	<p>92. Joseph E. Amaral
Instron Corporation
Corporate Engineering Office
100 Royale Street
Canton, MA 02021</p>
<p>85. Jalees Ahmad
AdTech Systems Research, Inc.
1342 North Fairfield Road
Dayton, OH 45432-2698</p>	<p>93. Edward M. Anderson
Aluminum Company of America
North American Industrial
Chemicals Division
P.O. Box 300
Bauxite, AR 72011</p>
<p>86. Yoshio Akimune
NISSAN Motor Co., Ltd.
Materials Research Laboratory
1 Natsushima-Cho
Yokosuka 237
JAPAN AIR MAIL</p>	<p>94. Norman C. Anderson
Ceradyne, Inc.
Ceramic-to-Metal Division
3169 Redhill Avenue
Costa Mesa, CA 92626</p>
<p>87. Mufit Akinc
Iowa State University
322 Spedding Hall
Ames, IA 50011</p>	<p>95. Don Anson
Battelle Columbus Laboratories
Thermal Power Systems
505 King Avenue
Columbus, OH 43201-2693</p>
<p>88. Ilhan A. Aksay
University of Washington
Materials Science and Engineering
Department, FB-10
Seattle, WA 98195</p>	<p>96. Thomas Arbanas
G.B.C. Materials Corporation
580 Monastery Drive
Latrobe, PA 15650-2698</p>
<p>89. R. G. Alexander
BASE
26 Malvern Close
Kettering Northants NN16 8JP
UNITED KINGDOM AIR MAIL</p>	<p>97. Frank Armatis
3M Company
3M Center
Building 60-1N-01
St. Paul, MN 55144-1000</p>
<p>90. Richard L. Allor
Ford Motor Company
Material Systems
Reliability Department
20000 Rotunda Drive
P.O. Box 2053, Room S-2031
Dearborn, MI 48121-2053</p>	<p>98. Everett B. Arnold
Detroit Diesel Corporation
Mechanical Systems Technology
13400 Outer Drive, West
Detroit, MI 48239-4001</p>
	<p>99. Richard M. Arons
PA Consulting Group
279 Princeton Road
Hightstown, NJ 08550</p>

100. Bertil Aronsson
Sandvik AB
S-12680
Stockholm Lerkrogsvagen 19
SWEDEN AIR MAIL
101. Dennis Assanis
University of Illinois
Department of Mechanical
Engineering
1206 W. Green Street
Urbana, IL 61801
102. William H. Atwell
Dow Corning Corporation
3901 South Saginaw Road
MS:540
Midland, MI 48686-0995
103. V. S. Avva
North Carolina A&T State
University
Department of Mechanical
Engineering
Greensboro, NC 27411
104. Patrick Badgley
Adiabatics, Inc.
3385 Commerce Drive
Columbus, IN 47201
105. Sunggi Baik
Pohang Institute of Science
& Technology
Department of Materials
Science and Engineering
P.O. Box 125
Pohang 790-600
KOREA AIR MAIL
106. John M. Bailey
Caterpillar, Inc.
Technical Center
Building L
P.O. Box 1875
Peoria, IL 61656-1875
107. Bob Baker
Ceradyne, Inc.
3169 Redhill Avenue
Costa Mesa, CA 92626
108. Frank Baker
Aluminum Company of America
Alcoa Technical Center
Alcoa Center, PA 15069
109. J. G. Baldoni
GTE Laboratories Inc.
40 Sylvan Road
Waltham, MA 02254
110. Clifford P. Ballard
Allied-Signal, Inc.
Ceramics Program
P.O. Box 1021
Morristown, NJ 07962-1021
111. M. Balu
Amoco Performance Products Inc.
4500 McGinnis Ferry Road
Alpharetta, GA 30202
112. B. P. Bandyopadhyay
Toyohashi University of Technology
School of Production Systems
Engineering
Tempaku-Cho Toyohashi 440
JAPAN AIR MAIL
113. P. M. Barnard
Ruston Gas Turbines Limited
Metallurgical Laboratory
P. O. Box 1
Lincoln LN2 5DJ
ENGLAND AIR MAIL
114. Harold N. Barr
Hittman Corporation
9190 Red Branch Road
Columbia, MD 21045
115. Renald D. Bartoe
Vesuvius McDanel
510 Ninth Avenue
Box 560
Beaver Falls, PA 15010-0560
116. Donald M. Bartos
Dow Corning Corporation
Advanced Ceramics Program
Midland, MI 48686-0995

117. David L. Baty
Babcock & Wilcox-LRC
P.O. Box 11165
Lynchburg, VA 24506-1165
118. Donald F. Baxter, Jr.
ASM International
Advanced Materials and
Processes
Materials Park, OH 44073-0002
119. M. Brad Beardsley
Caterpillar, Inc.
Advanced Materials Technology
Technical Center Bldg. E
P.O. Box 1875
Peoria, IL 61656-1875
120. Robert Beck
Teledyne CAE
Materials Engineering/Programs
1330 Laskey Road
P.O. Box 6971
Toledo, OH 43612
121. John C. Bell
Shell Research Limited
Thornton Research Centre
P.O. Box 1
Chester, Ch1 3SH
ENGLAND AIR MAIL
122. Albert H. Bell, III
General Motors Technical Center
30200 Mound Road
Engineering Building/W3 Turbine
Warren, MI 48090-9010
123. M. Bentele
Xamag, Inc.
259 Melville Avenue
Fairfield, CT 06430
124. Larry D. Bentsen
BF Goodrich Company
R&D Center
9921 Brecksville Road
Brecksville, OH 44141
125. Joseph C. Bentz
ENCERATEC
2525 Sandcrest Drive
Columbus, IN 47203
126. Louis Beregszazi
Defiance Precision Products
P.O. Drawer 428
Defiance, OH 43512
127. Tom Bernecki
Northwestern University
BIRL
1801 Maple Avenue
Evanston, IL 60201-3135
128. Charles F. Bersch
Institute for Defense Analyses
1801 North Beauregard Street
Alexandria, VA 22311
129. Ram Bhatt
NASA Lewis Research Center
21000 Brookpark Road
Cleveland, OH 44135
130. Deane I. Biehler
Caterpillar, Inc.
Engineering and Research
Materials
Technical Center, Building E
P.O. Box 1875
Peoria, IL 61656-1875
131. John. W. Bjerklie
Consolidated Natural Gas
Service Co., Inc.
Research Department
CNG Tower
Pittsburgh, PA 15222-3199
132. William D. Bjorndahl
TRW, Inc.
One Space Park
Building 01, Room 2040
Redondo Beach, CA 90278
133. Keith A. Blakely
Advanced Refractory
Technologies, Inc.
699 Hertel Avenue
Buffalo, NY 14207
134. Edward G. Blanchard
Netzsch Inc.
119 Pickering Way
Exton, PA 19341

135. Keith Blandford
Boride Products, Inc.
2879 Aero Park Drive
Traverse City, MI 49684
136. Bruce Boardman
Deere and Company Technical
Center
3300 River Drive
Moline, IL 61265
137. Russell Bockstedt
Hoechst Celanese Corporation
150 JFK Parkway
Short Hills, NJ 07078
138. M. Boehmer
DLR German Aerospace Research
Establishment
Postfach 90 60 58
D-5000 Koln 90
GERMANY AIR MAIL
139. Lawrence P. Boesch
EER Systems Corp.
1593 Spring Hill Road
Vienna, VA 22182-2239
140. Donald H. Boone
Boone & Associates
2412 Cascade Drive
Walnut Creek, CA 94598-4313
141. Tom Booth
Allied-Signal Aerospace
Company
AiResearch Los Angeles
Division
2525 West 190th Street
Torrance, CA 90509-2960
142. Tibor Bornemisza
Sundstrand Power Systems
4400 Ruffin Road
San Diego, CA 92186-5757
143. J.A.M. Boulet
University of Tennessee
Department of Engineering
Science and Mechanics
310 Perkins Hall
Knoxville, TN 37996-2030
144. H. Kent Bowen
Massachusetts Institute of
Technology
77 Massachusetts Avenue
Room E40-434
Cambridge, MA 02139
145. Leslie J. Bowen
Materials Systems
53 Hillcrest Road
Concord, MA 01742
146. Steven C. Boyce
Air Force Office of
Scientific Research
AFOSR/NA Bldg. 410
Bolling AFB DC 20332-6448
147. Gary L. Boyd
CEC
400 Howell Avenue, No. 4
Warland, WY 82401
148. Steve Bradley
UOP Research Center
50 East Algonquin Road
Des Plaines, IL 60017-6187
149. Michael C. Brands
Cummins Engine Company, Inc.
P.O. Box 3005
Mail Code 50179
Columbus, IN 47201
150. Raymond J. Bratton
Westinghouse Science and
Technology Center
1310 Beulah Road
Pittsburgh, PA 15235
151. John J. Brennan
United Technologies Corporation
Research Center
Silver Lane, MS:24
East Hartford, CT 06108
152. Jeff D. Bright
Ceramatec, Inc.
2425 South 900 West
Salt Lake City, UT 84108

153. Terrence K. Brog
Coors Ceramics Company
Corporate Development and
Technology
4545 McIntyre Street
Golden, CO 80403
154. Gunnar Broman
317 Fairlane Drive
Spartanburg, SC 29302
155. Al Brown
High-Tech Materials Alert
P.O. Box 882
Dayton, NJ 08810
156. Jesse Brown
Virginia Polytechnic Institute
and State University
Center for Advanced Ceramic
Materials
Blacksburg, VA 24061-0256
157. Sherman D. Brown
University of Illinois
Materials Science and
Engineering Department
105 South Goodwin Avenue
204 Ceramics Building
Urbana, IL 61801
158. S. L. Bruner
Ceramatec, Inc.
2425 South 900 West
Salt Lake City, UT 84119
159. Adolfo Brusaferro
Keramont Corporation
4231 South Fremont Avenue
Tucson, AZ 85714
160. W. Bryzik
U.S. Army Tank Automotive
Command
R&D Center
Propulsion Systems Division
Warren, MI 48397-5000
161. S. T. Buljan
GTE Laboratories, Inc.
40 Sylvan Road
Waltham, MA 02254
162. S. J. Burden
GTE Valenite
1711 Thunderbird
Troy, MI 48084
163. Curt V. Burkland
AMERCOM, Inc.
8928 Fullbright Avenue
Chatsworth, CA 91311
164. Bill Bustamante
AMERCOM, Inc.
8928 Fullbright Street
Chatsworth, CA 91311
165. Oral Buyukozturk
Massachusetts Institute of
Technology
77 Massachusetts Avenue
Room 1-280
Cambridge, MA 02139
166. David A. Caillet
Ethyl Corporation
451 Florida Street
Baton Rouge, LA 70801
167. Frederick J. Calnan
Heany Industries, Inc.
249 Briarwood Lane
P.O. Box 38
Scottsville, NY 14546
168. Roger Cannon
Rutgers University
Ceramics Department
P.O. Box 909
Piscataway, NJ 08855-0909
169. Scott Cannon
P.O. Box 567254
Atlanta, GA 30356
170. Harry W. Carpenter
19945 Acre Street
Northridge, CA 91324
171. David Carruthers
Kyocera Industrial Ceramics
Company
P.O. Box 2279
Vancouver, WA 98668-2279

172. Calvin H. Carter, Jr.
Cree Research, Inc.
2810 Meridian Parkway
Durham, NC 27713
173. J. David Casey
35 Atlantis Street
West Roxbury, MA 02132
174. Jere G. Castor
J. C. Enterprise
5078 North 83rd Street
Scottsdale, AZ 85250
175. James D. Cawley
Case Western Reserve University
Materials Science and
Engineering Department
Cleveland, OH 44106
176. Thomas C. Chadwick
Den-Mat Corporation
P.O. Box 1729
Santa Maria, CA 93456
177. Ronald H. Chand
Chand Kare Technical Ceramics
2 Coppage Drive
Worcester, MA 01603
178. Robert E. Chaney
EG&G Idaho, Inc.
Idaho National Engineering
Laboratory
P.O. Box 1625
Idaho Falls, ID 83415-3525
179. Frank C. Chang
U.S. Army Materials
Technology Laboratory
AMTL-EMM
405 Arsenal Street
Watertown, MA 02172
180. Robert M. Chapman
Allied-Signal Aerospace
Company
1530 Wilson Boulevard,
10th Floor
Arlington, VA 22209
181. William Chapman
Williams International
Corporation
2280 West Maple Road
Walled Lake, MI 48390-0200
182. Charlie Chen
LECO Corporation
P.O. Box 211688
Augusta, GA 30917
183. Albert A. Chesnes
U.S. Department of Energy
Transportation Technologies
CE-30, Forrestal Building,
6B-094
Washington, DC 20585
184. Kaiyin Chia
Carborundum Company
P.O. Box 832
Niagara Falls, NY 14302
185. Frank Childs
EG&G Idaho, Inc.
Idaho National Engineering
Laboratory
P.O. Box 1625
Idaho Falls, ID 83415-3527
186. William J. Chmura
Torrington Company
59 Field Street
Torrington, CT 06790-4942
187. Tsu-Wei Chou
University of Delaware
Center for Composite
Materials
201 Spencer Laboratory
Newark, DE 19716
188. R. J. Christopher
Ricardo Consulting Engineers
Bridge Works
Shoreham-By-Sea West Sussex
BN43 5FG
ENGLAND AIR MAIL
189. Joel P. Clark
Massachusetts Institute of
Technology
Room 8-409
Cambridge, MA 02139

190. Giorgio Clarotti
Commission of the European
Communities
DGXII-C3, M075, 1-53;
200 Rue de la Loi
B-1049 Brussels
BELGIUM AIR MAIL
191. W. J. Clegg
ICI Advanced Materials
P.O. Box 11
The Heath, Runcorn Cheshire
WA7 4QE
ENGLAND AIR MAIL
192. Joseph Cleveland
GTE Products Corporation
Hawes Street
Towanda, PA 18848-0504
193. Gloria M. Collins
ASTM
1916 Race Street
Philadelphia, PA 19103
194. William C. Connors
Sundstrand Aviation Operations
Materials Science and
Engineering Department
4747 Harrison Avenue
P.O. Box 7002
Rockford, IL 61125-7002
195. John A. Coppola
Carborundum Company
P.O. Box 156
Niagara Falls, NY 14302
196. Normand D. Corbin
Norton Company
Advanced Ceramics
Goddard Road
Northboro, MA 01532-1545
197. Douglas Corey
Allied-Signal Aerospace
Company
2525 West 190th Street
MS:T52
Torrance, CA 90504-6099
198. Keith P. Costello
Chand/Kare Technical Ceramics
2 Coppage Drive
Worcester, MA 01603-1252
199. Ed L. Courtright
Pacific Northwest
Laboratory
MS:K3-59
Richland, WA 99352
200. Anna Cox
Mitchell Market Reports
P.O. Box 23
Monmouth Gwent NP5 4YG
UNITED KINGDOM AIR MAIL
201. Thomas Coyle
Unocal Corporation
Unocal Science & Technology
Division
376 South Valencia Avenue
Brea, CA 92621
202. Art Cozens
Instron Corporation
3414 Snowden Avenue
Long Beach, CA 90808
203. Robert C. Craft
American Ceramic
Society, Inc.
757 Brooksedge Plaza Drive
Westerville, OH 43081
204. Mark Crawford
New Technology Week
4604 Monterey Drive
Annandale, VA 22003
205. Richard A. Cree
Markets & Products, Inc.
P.O. Box 14328
Columbus, OH 43214-0328
206. Les Crittenden
Vesuvius McDanel
Box 560
Beaver Falls, PA 15010

207. William J. Croft
U.S. Army Materials
Technology Laboratory
405 Arsenal Street
Watertown, MA 02172
208. M. J. Cronin
Mechanical Technology, Inc.
968 Albany-Shaker Road
Latham, NY 12110
209. Gary M. Crosbie
Ford Motor Company
1430 Culver Avenue
S-2079, SRL Building
Dearborn, MI 48121-4036
210. Floyd W. Crouse, Jr.
U.S. Department of Energy
Morgantown Energy
Technology Center
Collins Ferry Road
P.O. Box 880
Morgantown, WV 26505
211. John Cuccio
Allied-Signal Aerospace
Company
Garrett Auxiliary Power
Division
P.O. Box 5227, MS:1302-2Q
Phoenix, AZ 85010
212. Raymond Cutler
Ceramatec, Inc.
2425 South 900 West
Salt Lake City, UT 84119
213. Charles D'Angelo
GTE Laboratories, Inc.
40 Sylvan Road
Waltham, MA 02154
214. Stephen C. Danforth
Rutgers University
Ceramic Engineering Department
P.O. Box 909
Piscataway, NJ 08855-0909
215. Sankar Das Gupta
Electrofuel Manufacturing
Co., Ltd.
9 Hanna Avenue
Toronto Ontario MGK-1W8
CANADA AIR MAIL
216. Charles Davis
Sverdrup Technology,
Inc., MSFC
620 Discovery Drive
Huntsville, AL 35806
217. Frank Davis
Allied Signal Aerospace Co.
7550 Lucerne Dr., # 203
Middleburg Heights, OH 44130
218. Robert F. Davis
North Carolina State
University
Materials Engineering
Department
229 Riddick Laboratory
P.O. Box 7907
Raleigh, NC 27695
219. Thomas DeAngelis
Carborundum Company
Niagara Falls R&D Center
P.O. Box 832
Niagara Falls, NY 14302
220. George DeBell
Ford Motor Company
Material Systems Reliability
Department
20000 Rotunda Drive
P.O. Box 2053, Room S-2023
Dearborn, MI 48121-2053
221. Michael DeLuca
AMP-AKZO
West Lane
Aquebogue, NY 11931
222. Gerald L. DePoorter
Colorado School of Mines
Metallurgical and Materials
Engineering Department
Golden, CO 80401

223. J. F. DeRidder
Omni Electro Motive, Inc.,
12 Seely Hill Road
Newfield, NY 14867
224. Nick C. Dellow
Materials Technology
Publications
40 Sotherton Road
Watford Herts WD1 2QA
UNITED KINGDOM AIR MAIL
225. L. R. Dharani
University of Missouri-Rolla
224 M.E.
Rolla, MO 65401
226. Douglas A. Dickerson
Union Carbide Specialty
Powders
1555 Main Street
Indianapolis, IN 46224
227. John Dodsworth
Vesuvius Research &
Development
Technical Ceramics Group
Box 560
Beaver Falls, PA 15010
228. E. Dogan
Institut fur Werkstofforschung
GKSS-Forschungszentrum
Geesthacht GmbH
Max-Planck-Strasse
D-2054 Geesthacht
GERMANY AIR MAIL
229. Jean-Marie Drapier
FN Moteurs S.A.
Material and Processing
B-4041 Milmort (Herstal)
BELGIUM AIR MAIL
230. Kenneth C. Dreitlein
United Technologies
Research Center
Silver Lane
East Hartford, CT 06108
231. Robin A.L. Drew
McGill University
Department of Mining and
Metallurgical Engineering
3450 University Street
Montreal Quebec H3A 2A7
CANADA AIR MAIL
232. Winston H. Duckworth
BCL
Columbus Division
505 King Avenue
Columbus, OH 43201-2693
233. Edmund M. Dunn
Texel Company
6 Third Street
Lexington, MA 02173
234. Bill Durako
Sundstrand Aviation Operations
Department 789-6
4747 Harrison Avenue
P.O. Box 7002
Rockford, IL 61125-7002
235. Ernest J. Duwell
212 Elm Street
Hudson, WI 54016
236. Chuck J. Dziedzic
Coors Ceramics Company
Structural Products Group
17750 West 32nd Avenue
Golden, CO 80401
237. Robert J. Eagan
Sandia National Laboratories
Engineered Materials &
Processes Center
Org 1700
P.O. Box 5800
Albuquerque, NM 87185-5800
238. Jeffrey Eagleson
Lanxide Corporation
1001 Connecticut Avenue, N.W.
Washington, DC 20036

239. Harry E. Eaton
United Technologies Corporation
Research Center
Silver Lane
East Hartford, CT 06108
240. Harvill C. Eaton
Louisiana State
University
Office of Research
and Economic Development
240 Thomas Boyd Hall
Baton Rouge, LA 70803
241. Christopher A. Ebel
Carborundum Company
Technology Division
P.O. Box 337
Niagara Falls, NY 14302
242. J. J. Eberhardt
U.S. Department of Energy
Office of Transportation
Materials
CE-34, Forrestal Building
Washington, DC 20585
243. Jim Edler
Eaton Corporation
26201 Northwestern
Highway
P.O. Box 766
Southfield, MI 48037
244. William A. Ellingson
Argonne National Laboratory
Materials Science & Technology
Division
9700 South Cass Avenue
Argonne, IL 60439
245. William S. Ellis
Machined Ceramics
629 N. Graham St.
N. Industrial Park
Bowling Green, KY 42101
246. Glen B. Engle
Nuclear & Aerospace Materials
Corporation
16716 Martincoit Road
Poway, CA 92064
247. Jeff Epstein
Ceramic Technologies, Inc.
2107 Jamara Lane
Houston, TX 77077
248. Kenneth A. Epstein
Dow Chemical U.S.A.
Ceramics and Advanced
Materials
800 Building
Midland, MI 48667
249. Art Erdemir
Argonne National Laboratory
Materials and Components
Technology Division
9700 South Cass Avenue
Argonne, IL 60439
250. E. M. Erwin
Lubrizol Corporation
1819 East 225th Street
Euclid, OH 44117
251. Kenji Esaki
Toyota Technical Center
U.S.A., Inc.
2000 Town Center, Suite 500
Southfield, MI 48075
252. Jose L. Escalante
Anglo-Mex-Tech. Inc.
3923 N.W. 24th Street
Miami, FL 33142
253. John N. Eustis
U.S. Department of Energy
Industrial Energy Efficiency
Division
CE-221, Forrestal Building
Washington, DC 20585
254. Robert C. Evans
NASA Lewis Research Center
Terrestrial Propulsion Office
21000 Brookpark Road, MS:86-6
Cleveland, OH 44135
255. W. L. Everitt
Kyocera International, Inc.
8611 Balboa Avenue
San Diego, CA 92123

256. Gordon Q. Evison
332 South Michigan Avenue
Suite 1730
Chicago, IL 60604
257. John W. Fairbanks
U.S. Department of Energy
Advanced Propulsion Division
CE-322, Forrestal Building
Washington, DC 20585
258. Tim Fawcett
Dow Chemical Company
Central Research, Advanced
Ceramics Laboratory
1776 Building
Midland, MI 48674
259. Robert W. Fawley
Sundstrand Power Systems
Division of Sundstrand
Corporation
4400 Ruffin Road
P.O. Box 85757
San Diego, CA 92186-5757
260. John J. Fedorchak
GTE Products Corporation
Hawes Street
Towanda, PA 18848-0504
261. Jeff T. Fenton
Vista Chemical Company
900 Threadneedle
Houston, TX 77079
262. Larry Ferrell
Babcock & Wilcox
Old Forest Road
Lynchburg, VA 24505
263. Raymond R. Fessler
BIRL
Industrial Research Lab
1801 Maple Avenue
Evanston, IL 60201
264. Michelle Finch
E. I. DuPont de Nemours &
Company, Inc.
Experimental Station
Information Center E302/301
Wilmington, DE 19898
265. Arthur D. Fine
United Technologies Corporation
Pratt & Whitney Aircraft
400 Main Street
MS:163-10
East Hartford, CT 06108
266. Ross F. Firestone
Ross Firestone Company
188 Mary Street
Winnetka, IL 60093-1520
267. Sharon L. Fletcher
Arthur D. Little, Inc.
15 Acorn Park
Cambridge, MA 02140-2390
268. Thomas F. Foltz
Textron Specialty Materials
2 Industrial Avenue
Lowell, MA 01851
269. Renee G. Ford
Materials and Processing Report
P.O. Box 72
Harrison, NY 10528
270. John Formica
Supermaterials
2020 Lakeside Avenue
Cleveland, OH 44114
271. Jennifer M. Fox
Dyson Refractories Limited
R&D Laboratory
Owler Bar
Sheffield S17 3BJ
UNITED KINGDOM AIR MAIL
272. Edwin Frame
Southwest Research Institute
Division 2
P.O. Drawer 28510
San Antonio, TX 78284
273. Armanet Francois
French Scientific Mission
4101 Reservoir Road, N.W.
Washington DC 20007-2176
274. R. G. Frank
Technology Assessment Group
10793 Bentley Pass Lane
Loveland, OH 45140

275. David J. Franus
Forecast International
22 Commerce Road
Newtown, CT 06470
276. Marc R. Freedman
NASA Lewis Research Center
21000 Brookpark Road
MS:49-3
Cleveland, OH 44135
277. Douglas Freitag
LTV Missiles Division
P.O. Box 650003
MS:WT-21
Dallas, TX 75265
278. Brian R.T. Frost
Argonne National Laboratory
9700 South Cass Avenue
Building 900
Argonne, IL 60439
279. Lawrence R. Frost
Instron Corporation
100 Royall Street
Canton, MA 02021
280. George A. Fryburg
Norton/TRW Ceramics
7A-4 Raymond Avenue
Salem, NH 03079
281. Xiren Fu
Shanghai Institute of Ceramics
Chinese Academy of Sciences
1295 Ding-xi Road
Shanghai 200050
CHINA AIR MAIL
282. John Gahimer
P.O. Box 1302
Dublin, OH 43017
283. J. P. Gallagher
University of Dayton Research
Institute
300 College Park, JPC-250
Dayton, OH 45469-0120
284. Tom Garritano
University of Tennessee
Science Alliance
101 South College
Knoxville, TN 37996-1328
285. Joy A. Garwood
Norton Company
Advanced Ceramics
Goddard Road
Northboro, MA 01532-1545
286. H. Maury Gatewood
Reynolds Metals Company
Corporate R&D
Fourth and Canal Streets
P.O. Box 27003
Richmond, VA 23261
287. L. J. Gauckler
ETH-Zurich
Sonneggstrasse 5
CH-8092 Zurich 8092
SWITZERLAND AIR MAIL
288. Peter A. Gaydos
Battelle Columbus Laboratories
505 King Avenue
Columbus, OH 43201
289. George E. Gazza
U.S. Army Materials
Technology Laboratory
Ceramics Research Division
405 Arsenal Street
Watertown, MA 02172-0001
290. D. Gerster
CEA-DCOM
33 Rue De La Federation
Paris 75015
FRANCE AIR MAIL
291. John Ghinazzi
Coors Technical Ceramics
Company
1100 Commerce Park Drive
Oak Ridge, TN 37830

292. Robert Giddings
General Electric Company
Research Laboratory
P.O. Box 8
Schenectady, NY 12301
293. A. M. Glaeser
University of California
Materials Science and Mineral
Engineering
Lawrence Berkeley Laboratory
Hearst Mining Building
Berkeley, CA 94720
294. Paul Glance
Concept Analysis
R&D
950 Stephenson Highway
Dupont Automotive Development
Building
Troy, MI 48007-7013
295. Joseph W. Glatz
Naval Air Propulsion Center
Systems Engineering Division
P.O. Box 7176, PE24
Trenton, NJ 08628
296. W. M. Goldberger
Superior Graphite Company
R&D
2175 East Broad Street
Columbus, OH 43209
297. Allan E. Goldman
U.S. Graphite, Inc.
907 West Outer Drive
Oak Ridge, TN 37830
298. Stephen T. Gonczy
Allied Signal Research
P.O. Box 5016
Des Plaines, IL 60017
299. Jeffrey M. Gonzales
GTE Products Corporation
Hawes Street
Towanda, PA 18848-0504
300. Robert J. Gottschall
U.S. Department of Energy
ER-131, MS:G-236
Washington, DC 20545
301. Earl Graham
Cleveland State University
Department of Chemical
Engineering
Euclid Avenue at
East 24th Street
Cleveland, OH 44115
302. William A. Graham
Lanxide Corporation
P.O. Box 6077
Newark, DE 19714-6077
303. Robert E. Green, Jr.
Johns Hopkins University
Materials Science and
Engineering Department
Baltimore, MD 21218
304. Lance Groseclose
General Motors Corporation
Allison Gas Turbine Division
P.O. Box 420, MS:W-5
Indianapolis, IN 46206
305. Mark F. Gruninger
Union Carbide Corporation
Specialty Powder Business
1555 Main Street
Indianapolis, IN 46224
306. Ernst Gugel
Cremer Forschungsinstitut
GmbH&Co.KG
Oeslauer Strasse 35
D-8633 Roedental 8633
GERMANY AIR MAIL
307. Donald L. Guile
Corning Glass Works
SP-DV-1-9
Corning, NY 14831
308. Bimleshwar P. Gupta
Solar Energy Research
Institute
Mechanical and Industrial
Technology Division
1617 Cole Boulevard
Golden, CO 80401

309. John P. Gyekenyesi
NASA Lewis Research Center
21000 Brookpark Road, MS:6-1
Cleveland, OH 44135
310. Nabil S. Hakim
Detroit Diesel Corporation
13400 West Outer Drive
Detroit, MI 48239
311. Philip J. Haley
General Motors Corporation
Vehicular Engineering
P.O. Box 420, MS:T12A
Indianapolis, IN 46236
312. Judith Hall
Fiber Materials, Inc.
Biddeford Industrial Park
5 Morin Street
Biddeford, ME 04005
313. Y. Harada
IIT Research Institute
Nometallic Materials and
Composites
10 West 35th Street
Chicago, IL 60616
314. R. A. Harmon
25 Schalren Drive
Latham, NY 12110
315. Amy Harmon-Barrett
Martin Marietta Laboratories
1450 South Rolling Road
Baltimore, MD 21227
316. Norman H. Harris
Hughes Aircraft Company
P.O. Box 800520
Saugus, CA 91380-0520
317. Alan Hart
Dow Chemical Company
Advanced Ceramics Laboratory
1776 Building
Midland, MI 48674
318. Pat E. Hart
Battelle Pacific Northwest
Laboratories
Ceramics and Polymers
Development Section
P.O. Box 999
Richland, WA 99352
319. Stephen D. Hartline
Norton Company
Advanced Ceramics
Goddard Road
Northboro, MA 01532-1545
320. Michael H. Haselkorn
Caterpillar, Inc.
Engineering Research Materials
Technical Center, Building E
P.O. Box 1875
Peoria, IL 61656-1875
321. N. B. Havewala
Corning, Inc.
SP-PR-11
Corning, NY 14831
322. John Haygarth
Teledyne WAA Chang Albany
P.O. Box 460
Albany, OR 97321
323. Norman L. Hecht
University of Dayton Research
Institute
300 College Park
Dayton, OH 45469-0172
324. Peter W. Heitman
General Motors Corporation
Allison Gas Turbine Division
P.O. Box 420, MS:W-5
Indianapolis, IN 46206-0420
325. Robert W. Hendricks
Virginia Polytechnic Institute
and State University
Materials Engineering
Department
210 Holden Hall
Blacksburg, VA 24061-0237

326. Wynne Henley
Hertel Cutting Technologies, Inc.
1000 Clearview Court
Oak Ridge, TN 37830
327. Thomas L. Henson
GTE Products Corporation
Chemical & Metallurgical
Division
Hawes Street
Towanda, PA 18848
328. Thomas P. Herbell
NASA Lewis Research Center
21000 Brookpark Road
MS:49-3
Cleveland, OH 44135
329. Marlene Heroux
Rolls-Royce, Inc.
2849 Paces Ferry Road
Suite 450
Atlanta, GA 30339-3769
330. Robert L. Hershey
Science Management Corporation
1255 New Hampshire Ave., N.W.
Suite 1033
Washington, DC 20036
331. Hendrik Heystek
Bureau of Mines
Tuscaloosa Research Center
P.O. Box L
University, AL 35486
332. Wallace C. Higgins
Norwal Unlimited
P.O. Box 1258
Alfred, NY 14802
333. Robert V. Hillery
GE Aircraft Engines
One Neumann Way, M.D. H85
Cincinnati, OH 45215
334. Arthur Hindman
Instron Corporation
100 Royall Street
Canton, MA 02021
335. Jon Hines
American Ceramic Society, Inc.
757 Brooksedge Plaza Drive
Westerville, OH 43081-6136
336. Hans Erich Hintermann
CSEM
Materials and Micromechanics
Division
Rue Breguet 2
Neuchatel 2000
SWITZERLAND AIR MAIL
337. Shinichi Hirano
Mazda R&D of North
America, Inc.
1203 Woodridge Avenue
Ann Arbor, MI 48105
338. Tommy Hiraoka
NGK Locke, Inc.
1000 Town Center
Southfield, MI 48075
339. John M. Hobday
U.S. Department of Energy
Morgantown Energy Technology
Center
Collins Ferry Road
P.O. Box 880
Morgantown, WV 26507
340. Greg Hoenes
Vista Chemical Company
900 Threadneedle
P.O. Box 19029
Houston, TX 77079-2990
341. Clarence Hoenig
Lawrence Livermore National
Laboratory
P.O. Box 808, Mail Code L-369
Livermore, CA 94550
342. Thomas Hollstein
Fraunhofer-Institut fur
Werkstoffmechanik IWM
Wohlerstrabe 11
D-7800 Freiburg
GERMANY AIR MAIL

343. Richard Holt
National Research Council
of Canada
Structures and Materials
Laboratory
Ottawa Ontario K1A 0R6
CANADA AIR MAIL
344. Joseph Homeny
University of Illinois
Department of Materials Science
and Engineering
105 South Goodwin Avenue
Ceramics Building
Urbana, IL 61801
345. A. T. Hopper
Battelle Columbus
Laboratories
Metals and Ceramics Department
505 King Avenue
Columbus, OH 43201-2693
346. Michael Horgan
Materials Engineering Magazine
1100 Superior Avenue
Cleveland, OH 44114
347. Woodie Howe
Coors Technical Ceramics
Company
1100 Commerce Park Drive
Oak Ridge, TN 37830
348. Stephen M. Hsu
National Institute of
Standards and Technology
Gaithersburg, MD 20899
349. Hann S. Huang
Argonne National Laboratory
9700 South Cass Avenue
Argonne, IL 60439-4815
350. Gene Huber
Precision Ferrites & Ceramics
5576 Corporate Drive
Cypress, CA 90630
351. M. L. Huckabee
GTE Laboratories, Inc.
40 Sylvan Road
Waltham, MA 02254
352. Harold A. Huckins
Princeton Advanced
Technology, Inc.
56 Finley Road
Princeton, NJ 08540
353. Fred R. Huettig
Advanced Magnetics, Inc.
45 Corey Lane
Mendham, NJ 07945
354. Bill Huffman
Zircar
110 North Main Street
Florida, NY 10921
355. Brian K. Humphrey
Lubrizol Petroleum
Chemicals Co.
3000 Town Center, Suite 1340
Southfield, MI 48075-1201
356. Robert M. Humrick
Dylon Ceramic Technologies
3100 Edgehill Road
Cleveland Heights, OH 44118
357. Lorretta Inglehart
National Science Foundation
Division of Materials Research
1800 "G" Street, N.W.,
Room 408
Washington, DC 20550
358. Michael S. Inoue
Kyocera International, Inc.
KII Library
8611 Balboa Avenue
San Diego, CA 92123-1580
359. Osama Jadaan
University of Wisconsin-
Platteville
General Engineering Division
1 University Plaza
Platteville, WI 53818
360. Curtis A. Johnson
General Electric Company
Corporate R&D
Room MB-187
P.O. Box 8
Schenectady, NY 12301

361. Sylvia Johnson
SRI International
333 Ravenswood Avenue
Menlo Park, CA 94025
362. Thomas A. Johnson
Lanxide Corporation
1300 Marrows Road
P.O. Box 6077
Newark, DE 19714-6077
363. W. S. Johnson
Indiana University
One City Centre, Suite 200
Bloomington, IN 47405
364. Jill E. Jonkouski
U.S. Department of Energy
9800 South Cass Avenue
Argonne, IL 60439-4899
365. L. A. Joo
Great Lakes Research
Corporation
P.O. Box 1031
Elizabethton, TN 37643
366. A. D. Joseph
SPX Corporation
700 Terrace Point
Muskegon, MI 49443
367. Adam Jostsons
Australian Nuclear Science &
Technology Organization
Lucas Heights Research
Laboratories
New Illawarra Road
Lucas Heights New South Wales
AUSTRALIA AIR MAIL
368. Matthew K. Juneau
Ethyl Corporation
451 Florida Street
Baton Rouge, LA 70801
369. Hartmut Kainer
Didier-Werke AG
Anlagentechnik Wiesbaden
Abraham-Lincoln-Str. 16
D-62 Wiesbaden
GERMANY AIR MAIL
370. Tom Kalamasz
Norton/TRW Ceramics
7A-4 Raymond Avenue
Salem, NH 03079
371. Lyle R. Kallenbach
Phillips Petroleum Company
R&D
Mail Drop:123AL
Bartlesville, OK 74004
372. Nick Kamiya
Kyocera Industrial Ceramics
Corporation
2700 River Road
Des Plaines, IL 60018
373. Roy Kamo
Adiabatics, Inc.
3385 Commerce Park Drive
Columbus, IN 47201
374. S. Kang
GTE Laboratories, Inc.
40 Sylvan Road
Waltham, MA 02254
375. Chih-Chun Kao
Industrial Technology Research
Institute
Materials Research
Laboratories
195 Chung-Hsing Road, Sec. 4
Chutung Hsinchu 31015 R.O.C.
TAIWAN AIR MAIL
376. Keith R. Karasek
Allied-Signal, Inc.
Engineered Materials Research
Center
50 East Algonquin Road
P.O. Box 5016
Des Plaines, IL 60017-5016
377. Robert E. Kassel
Ceradyne, Inc.
3169 Redhill Avenue
Costa Mesa, CA 92626
378. Allan Katz
Wright Laboratory
Metals and Ceramics Division
WL/MLLM
Wright-Patterson AFB, OH 45433

379. R. Nathan Katz
Worcester Polytechnic
Institute
Dept. of Mechanical
Engineering
100 Institute Road
Worcester, MA 01609
380. Ted Kawaguchi
Tokai Carbon America, Inc.
375 Park Avenue, Suite 3802
New York, NY 10152
381. Noritsugu Kawashima
TOSHIBA Corporation
Mechanical Engineering
Laboratory
4-1 Ukishima-Cho
Kawasaki-Ku Kawasaki 210
JAPAN AIR MAIL
382. Lisa Kempfer
Penton Publishing
Materials Engineering
1100 Superior Avenue
Cleveland, OH 44114-2543
383. Frederick L. Kennard, III
General Motors Corporation
AC Rochester
Department 32-24, EB
1300 North Dort Highway
Flint, MI 48556
384. David O. Kennedy
Lester B. Knight Cast
Metals Inc.
549 West Randolph Street
Chicago, IL 60661
385. George Keros
Photon Physics
3175 Penobscot Building
Detroit, MI 48226
386. Pramod K. Khandelwal
General Motors Corporation
Allison Gas Turbine
Division
P.O. Box 420, MS:W05
Indianapolis, IN 46206
387. Jim R. Kidwell
Allied-Signal Aerospace
Company
Garrett Auxiliary Power
Division
P.O. Box 5227
Phoenix, AZ 85010
388. Han J. Kim
GTE Laboratories, Inc.
40 Sylvan Road
Waltham, MA 02254
389. Shin Kim
Korea Institute of Machinery
& Metals
66 Sangnam-dong, Changwon
Kyungnam 641-010
KOREA AIR MAIL
390. W. C. King
Mack Truck, Z-41
1999 Pennsylvania Avenue
Hagerstown, MD 21740
391. Carol Kirkpatrick
MSE, Inc.
CDIF Technical Library
P.O. Box 3767
Butte, MT 59702
392. Tony Kirn
Caterpillar, Inc.
Defense Products Department, JB7
Peoria, IL 61629
393. James D. Kiser
NASA Lewis Research Center
21000 Brookpark Road, MS:49-3
Cleveland, OH 44135
394. Max Klein
Gas Research Institute
Thermodynamics
8600 West Bryn Mawr Avenue
Chicago, IL 60631
395. Richard N. Kleiner
Coors Ceramics Company
4545 McIntyre Street
Golden, CO 80403

396. Stanley J. Klima
NASA Lewis Research Center
21000 Brookpark Road
MS:6-1
Cleveland, OH 44135
397. Chris E. Knapp
Norton Advanced Ceramics
of Canada Ltd.
8001 Daly Street
Niagara Falls, Ontario L2G 6S2
CANADA AIR MAIL
398. Albert S. Kobayashi
University of Washington
Mechanical Engineering
Department
MS:FU10
Seattle, WA 98195
399. Shigeki Kobayashi
Toyota Central Research
Labs, Inc.
Nagakute Aichi 480-11
JAPAN AIR MAIL
400. Richard A. Kole
Z-Tech Corporation
8 Dow Road
Bow, NH 03304
401. E. Kostiner
University of Connecticut
Chemistry Department, U-60
Storrs, CT 06269-3060
402. Kenneth A. Kovaly
Technical Insights, Inc.
P.O. Box 1304
Fort Lee, NJ 07024-9967
403. Ralph G. Kraft
Spraying Systems Company
North Avenue at Schmale Road
Wheaton, IL 60189-7900
404. Saunders B. Kramer
U.S. Department of Energy
Advanced Propulsion Division
CE-322, Forrestal Building
Washington, DC 20585
405. Arthur Kranish
Trends Publishing, Inc.
1079 National Press Building
Washington, DC 20045
406. A. S. Krieger
Radiation Science, Inc.
P.O. Box 293
Belmont, MA 02178
407. Pieter Krijgsman
Ceramic Design International
Holding B.V.
P.O. Box 68
Hattem 8050-AB
THE NETHERLANDS AIR MAIL
408. Waltraud M. Kriven
University of Illinois
Materials Science and
Engineering Department
105 South Goodwin Avenue
Urbana, IL 61801
409. Edward J. Kubel, Jr.
ASM International Advanced
Materials & Processes
Materials Park, OH 44073
410. Dave Kupperman
Argonne National Laboratory
9700 South Cass Avenue
Argonne, IL 60439
411. Oh-Hun Kwon
Norton Company
Advanced Ceramics
Goddard Road
Northboro, MA 01532-1545
412. W. J. Lackey
Georgia Institute of Technology
Materials Science and
Technology
Atlanta, GA 30332
413. Jai Lala
Tenmat Ltd.
40 Somers Road
Rugby Warwickshire CV22 7DH
ENGLAND AIR MAIL

414. Hari S. Lamba
General Motors Corporation
Electro-Motive Division
9301 West 55th Street
LaGrange, IL 60525
415. Richard L. Landingham
Lawrence Livermore National
Laboratory
Ceramics, Corrosion, and
Thermochemistry
P.O. Box 808, L-369
Livermore, CA 94550
416. Charles J. Landry
Chand Kare Technical Ceramics
712 Flat Hill Road
Lumeburg, MA 01462
417. Manfred W. Langer
Volkswagen AG
Material Technology
3180 Wolfsburg 1
GERMANY AIR MAIL
418. James Lankford
Southwest Research Institute
Department of Materials
Sciences
6220 Culebra Road
San Antonio, TX 78228-0510
419. Stanley B. Lasday
Business News Publishing Co.
Manor Oak One
1910 Cochran Road, Suite 630
Pittsburgh, PA 15220
420. Mark S. Laser
Solar Turbines, Inc.
2211 Erie Street
San Diego, CA 92110
421. S. K. Lau
Carborundum Company
Technology Division
P.O. Box 832, B-100
Niagara Falls, NY 14302
422. Edward A. Lauder
Advanced Composite Materials
Corporation
1525 South Buncombe Road
Greer, SC 29651-9208
423. J. Lawrence Lauderdale
Babcock & Wilcox
Contract Research Division
1850 "K" Street, Suite 950
Washington, DC 20006
424. Harry A. Lawler
Carborundum Company
Technology Division
P.O. Box 832
Niagara Falls, NY 14302
425. Jean F. LeCostaouec
Textron Speciality Materials
2 Industrial Avenue
Lowell, MA 01851
426. Benson P. Lee
Interscience, Inc.
9718 Lake Shore Boulevard
Cleveland, OH 44108
427. Burtrand I. Lee
Clemson University
Department of Ceramic
Engineering
Olin Hall
Clemson, SC 29634-0907
428. June-Gunn Lee
KIST
Structural Ceramic Lab
P.O. Box 131, Cheong-Ryang
Seoul 130-650
KOREA AIR MAIL
429. Ran-Rong Lee
Ceramics Process Systems
Corporation
155 Fortune Boulevard
Milford, MA 01757
430. Stan Levine
NASA Lewis Research Center
21000 Brookpark Road
MS:49-3
Cleveland, OH 44135
431. Alan V. Levy
Lawrence Berkeley Laboratory
One Cyclotron Road, MS:62-203
Berkeley, CA 94720

432. Ai-Kang Li
Materials Research
Laboratories, ITRI
195-5 Chung-Hsing Road, Sec. 4
Chutung Hsinchu 31015 R.O.C.
TAIWAN AIR MAIL
433. Winston W. Liang
Hong Kong Industrial
Technology Centre Co. Ltd.
78 Tat Chee Avenue
4/F, HKPC Building
Howloon
HONG KONG AIR MAIL
434. Robert Licht
Norton Company
Advanced Ceramics
Goddard Road
Northboro, MA 01532-1545
435. E. Lilley
Norton Company
Advanced Ceramics
Goddard Road
Northboro, MA 01532-1545
436. Laura J. Lindberg
Allied-Signal Aerospace
Company
Garrett Fluid Systems Division
1300 West Warner
MS: 93-901-1207-4TT
P.O. Box 22200
Tempe, AZ 85284-2200
437. Leonard C. Lindgren
General Motors Corporation
Allison Gas Turbine Division
P.O. Box 420, Speed Code:T-20A
Indianapolis, IN 46206-0420
438. Hans A. Lindner
Cremer Forschungsinstitut
GmbH&Co.KG
Oeslauer Strasse 35
D-8633 Rodental 8866
GERMANY AIR MAIL
439. Ronald E. Loehman
Sandia National Laboratories
Chemistry & Ceramics
Department 1840
P.O. Box 5800
Albuquerque, NM 87185
440. Jeffrey C. Logas
Winona State University
Composite Materials
Engineering
115 Pasteur Hall
Winona, MN 55987
441. Bill Long
Babcock & Wilcox
P.O. Box 11165
Lynchburg, VA 24506
442. William D. Long
Wacker Chemicals (USA), Inc.
ESK Engineered Ceramics
50 Locust Avenue
New Canaan, CT 06840
443. L. A. Lott
EG&G Idaho, Inc.
Idaho National Engineering
Laboratory
P.O. Box 1625
Idaho Falls, ID 83415-2209
444. Raouf O. Loutfy
MER Corporation
7960 South Kolb Road
Tucson, AZ 85706
445. Gordon R. Love
Aluminum Company of America
Alcoa Technical Center
Alcoa Center, PA 15069
446. Lydia Luckevich
Ortech International
2395 Speakman Drive
Mississauga Ontario L5K 1B3
CANADA AIR MAIL

447. James W. MacBath
Carborundum Company
Structural Ceramics Division
P.O. Box 1054
Niagara Falls, NY 14302
448. H. MacLaren
General Electric Company
Thomson Laboratory, Materials
Engineering 36807
1000 Western Avenue
Lynn, MA 01910
449. George Maczura
Aluminum Company of America
Industrial Chemicals Division
670 One Allegheny Square
Pittsburgh, PA 15212
450. David Maginnis
Tinker AFB
OC-ALC/LIIRE
Tinker AFB OK 73145-5989
451. Frank Maginnis
Aspen Research, Inc.
220 Industrial Boulevard
Moore, OK 73160
452. Tai-il Mah
Universal Energy Systems, Inc.
Ceramics and Composites
Research
4401 Dayton-Xenia Road
Dayton, OH 45432
453. Kenneth M. Maillar
Barbour Stockwell Company
83 Linskey Way
Cambridge, MA 02142
454. Lorenzo Majno
Instron Corporation
100 Royall Street
Canton, MA 02021
455. S. G. Malghan
National Institute of Standards
and Technology
1-270 & Clopper Road
Gaithersburg, MD 20899
456. Lars Malmrup
United Turbine AB
Box 13027
Malmo S-200 44
SWEDEN AIR MAIL
457. John Mangels
Ceradyne, Inc.
3169 Redhill Avenue
Costa Mesa, CA 92626
458. Russell V. Mann
Matec Applied Sciences, Inc.
75 South Street
Hopkinton, MA 01748
459. William R. Manning
Champion Aviation Products
Division
Old Norris Road
P.O. Box 686
Liberty, SC 29657
460. Ken Marnoch
Amercom, Inc.
8928 Fullbright Avenue
Chatsworth, CA 91311
461. Robert A. Marra
Aluminum Company of America
Alcoa Technical Center
Advanced Ceramics Center - E
Alcoa Center, PA 15069
462. Chauncey L. Martin
3M Company
3M Center, Building 60-1N-01
St. Paul, MN 55144
463. Steven C. Martin
Advanced Refractory
Technologies, Inc.
699 Hertel Avenue
Buffalo, NY 14207
464. Kelly J. Mather
Williams International
Corporation
2280 West Maple Road
P.O. Box 200
Walled Lake, MI 48088

465. James P. Mathers
3M Company
3M Center
Building 201-3N-06
St. Paul, MN 55144
466. Marshall Mayer
Instron Corporation
3815 Presidential Parkway,
Suite 100
Atlanta, GA 30340
467. Ron Mayville
Arthur D. Little, Inc.
15-163 Acorn Park
Cambridge, MA 02140
468. F. N. Mazadarany
General Electric Company
Research Laboratory
Building K-1, Room MB-159
P.O. Box 8
Schenectady, NY 12301
469. James W. McCauley
Alfred University
NYS College of Ceramics
Binns-Merrill Hall
Alfred, NY 14802
470. Carolyn McCormick
Allied-Signal Aerospace
Company
Garrett Auxiliary Power
Division
Bldg. 1303-206
P.O. Box 5227, MS:9317-2
Phoenix, AZ 85010
471. Louis R. McCreight
2763 San Ramon Drive
Rancho Palos Verdes, CA 90274
472. Colin F. McDonald
McDonald Thermal Engineering
1730 Castellana Road
La Jolla, CA 92037
473. B. J. McEntire
Norton Company, TRW Ceramics
Goddard Road
Northboro, MA 01532-1545
474. Chuck McFadden
Coors Ceramics Company
600 9th Street
Golden, CO 80401
475. Henry McFadden
Magnetic Bearings, Inc.
Engineering Library
609 Rock Road
Radford, VA 24141
476. Thomas D. McGee
Iowa State University
Materials Science and
Engineering Department
110 Engineering Annex
Ames, IA 50011
477. Carol McGill
Corning Inc.
Sullivan Park, FR-02-08
Corning, NY 14831
478. T. C. McLaren
Cameron Forged Products
Company
P.O. Box 1212
Houston, TX 77251-1212
479. James McLaughlin
Sundstrand Power Systems
4400 Ruffin Road
P.O. Box 85757
San Diego, CA 92186-5757
480. Arthur F. McLean
6225 North Camino Almonte
Tucson, AZ 85718
481. Matt McMonigle
U.S. Department of Energy
Improved Energy Productivity
Division
Forrestal Building,
CE-231
Washington, DC 20585
482. Dennis McMurtry
EG&G Idaho, Inc.
Idaho National Engineering
Laboratory
P.O. Box 1625
Idaho Falls, ID 83415

483. D. B. Meadowcroft
National Power Technology
and Environmental Centre
Kelvin Avenue
Leatherhead Surrey
KT22 7SE
ENGLAND AIR MAIL
484. Jo Meglen
11004 Birdfoot Court
Reston, VA 22091
485. Pankaj K. Mehrotra
Kennametal, Inc.
P.O. Box 639
Greensburg, PA 15601
486. Joseph J. Meindl
Reynolds International, Inc.
6603 West Broad Street
P.O. Box 27002
Richmond, VA 23261-7003
487. Michael D. Meiser
Allied-Signal Aerospace Company
Garrett Ceramic Components
Division
19800 South Van Ness Avenue
Torrance, CA 90509
488. George Messenger
National Research Council of
Canada
Engine Laboratory
Building M-7
Ottawa Ontario K1A 0R6
CANADA AIR MAIL
489. D. Messier
U.S. Army Materials Technology
Laboratory
SLCMT-EMC
405 Arsenal Street
Watertown, MA 02172-0001
490. Gary L. Messing
Pennsylvania State University
Ceramic Science and Engineering
Department
119 Steidle Building
University Park, PA 16802
491. Arthur G. Metcalfe
Arthur G. Metcalfe and
Associates, Inc.
2108 East 24th Street
National City, CA 91950
492. R. Metselaar
Eindhoven University
Centre for Technical Ceramics
P.O. Box 513
Eindhoven 5600 MB
THE NETHERLANDS AIR MAIL
493. Nancy S. Meyers
U.S. Department of Energy
Transportation Technologies
CE-30, Forrestal Building
6B-094
Washington, DC 20585
494. David J. Michael
Harbison-Walker Refractories
Company
P.O. Box 98037
Pittsburgh, PA 15227
495. Ken Michaels
Chrysler Motors Corporation
Ceramics Development
Metallurgical Processes
P.O. Box 1118, CIMS:418-17-09
Detroit, MI 48288
496. Bernd Michel
Institute of Mechanics
Fracture and Micromechanics
Department
P.O. Box 408
D-9010 Chemnitz
GERMANY AIR MAIL
497. David E. Miles
Commission of the European
Communities
rue de la Loi, 200
B-1049 Brussels
BELGIUM AIR MAIL
498. John V. Milewski
Superkinetics, Inc.
P.O. Box 8029
Santa Fe, NM 87504

499. Carl E. Miller
AC Rochester
1300 North Dort Highway,
MS:32-31
Engineering Building B
Flint, MI 48556
500. Mike Miller
McGraw-Hill Aviation Week
Performance Materials
1156 15th Street, N.W.
Washington, DC 20005
501. Charles W. Miller, Jr.
Centorr Furnaces/Vacuum
Industries
542 Amherst Street
Nashua, NH 03063
502. R. Mininni
Enichem America
2000 Cornwall Road
Monmouth Junction, NJ 08852
503. Michele V. Mitchell
Allied-Signal Aerospace
Company
Garrett Ceramic Components
Division
19800 South Van Ness Avenue
Torrance, CA 90501-1149
504. Howard Mizuhara
GTE - WESGO
477 Harbor Boulevard
Belmont, CA 94002
505. Helen Moeller
Babcock & Wilcox
P.O. Box 11165
Lynchburg, VA 24506-1165
506. Francois R. Mollard
Metalworking Technology, Inc.
1450 Scalp Avenue
Johnstown, PA 15904
507. Phil Mooney
Panametrics
NDE Division
221 Crescent Street
Waltham, MA 02254
508. Thomas Morel
Ricardo North America
645 Blackhawk Drive
Westmont, IL 60559
509. Geoffrey P. Morris
3M Company
3M Traffic Control Materials
Division
Bldg. 209-BW-10, 3M Center
St. Paul, MN 55144-1000
510. Jay A. Morrison
Rolls-Royce, Inc.
Engineering and Information
Center, Overlook 1
2849 Paces Ferry Road,
Suite 450
Atlanta, GA 30339-3769
511. Joel P. Moskowitz
Ceradyne, Inc.
3169 Redhill Avenue
Costa Mesa, CA 92626
512. Brij Moudgil
University of Florida
Material Science and
Engineering
Gainesville, FL 32611
513. Christoph J. Mueller
Sprechsaal Publishing
Group
P.O. Box 2962, Mauer 2
D-8630 Coburg
GERMANY AIR MAIL
514. Thomas W. Mullan
Vapor Technologies Inc.
345 Route 17 South
Upper Saddle River, NJ 07158
515. M. K. Murthy
MKM Consultants International
10 Avoca Avenue, Unit 1906
Toronto Ontario M4T 2B7
CANADA AIR MAIL
516. Solomon Musikant
TransCon Technologies, Inc.
Materials Science & Engineering
1508 Waynesboro Road
Paoli, PA 19301

517. David L. Mustoe
Custom Technical Ceramics
8041 West I-70 Service Road,
Unit 6
Arvada, CO 80002
518. Curtis V. Nakaishi
U.S. Department of Energy
Morgantown Energy Technology
Center
Collins Ferry Road
P.O. Box 880
Morgantown, WV 26507-0880
519. Yoshio Nakamura
Faicera Research Institute
2-5-8 Hiyakunin-cho Shinjuku-Ko
Tokyo
JAPAN AIR MAIL
520. K. S. Narasimhan
Hoeganaes Corporation
River Road
Riverton, NJ 08077
521. Samuel Natansohn
GTE Laboratories, Inc.
40 Sylvan Road
Waltham, MA 02254
522. Robert Naum
Applied Resources, Inc.
P.O. Box 241
Pittsford, NY 14534
523. Malcolm Naylor
Cummins Engine Company, Inc.
P.O. Box 3005, Mail Code 50183
Columbus, IN 47202-3005
524. Jeffrey Neil
GTE Laboratories, Inc.
40 Sylvan Road
Waltham, MA 02254
525. Fred A. Nichols
Argonne National Laboratory
9700 South Cass Avenue
MCT - Building 212
Argonne, IL 60439
526. H. Nickel
Forschungszentrum Jülich (KFA)
P.O. Box 1913
Jülich 1-5170 BRD NRW
GERMANY AIR MAIL
527. Dale E. Niesz
Rutgers University
Center for Ceramic Research
P.O. Box 909
Piscataway, NJ 08855-0909
528. David M. Nissley
United Technologies Corporation
Pratt & Whitney Aircraft
400 Main Street, MS:163-10
East Hartford, CT 06108
529. Richard D. Nixdorf
ReMaxCo Technologies, Inc.
11317 Snyder Road
Knoxville, TN 37932
530. Bernard North
Kennametal, Inc.
P.O. Box 639
Greensburg, PA 15601
531. Bruce E. Novich
Ceramics Process Systems
Corporation
155 Fortune Boulevard
Milford, MA 01757
532. Daniel Oblas
GTE Laboratories, Inc.
40 Sylvan Road
Waltham, MA 02254
533. Don Ohanehi
Magnetic Bearings, Inc.
1908 Sussex Road
Blacksburg, VA 24060
534. Robert Orenstein
General Electric Company
55-112, River Road
Schenectady, NY 12345

535. Norb Osborn
Aerodyne Dallas
151 Regal Row,
Suite 120
Dallas, TX 75247
536. A. M. Paddick
BP International Limited
BP Research Centre, Main
Library
Chertsey Road
Sunbury-on-Thames
Middlesex TW16 7LN
UNITED KINGDOM AIR MAIL
537. Russell J. Page
Kanthal-Artcor
3001 Redhill Avenue, II-109
Costa Mesa, CA 92705
538. Richard Palicka
Cercom, Inc.
1960 Watson Way
Vista, CA 92083
539. Muktesh Paliwal
GTE Products Corporation
Hawes Street
Towanda, PA 18848
540. Joseph E. Palko
General Electric Company
55-113, River Road
Schenectady, NY 12345
541. Hayne Palmour, III
North Carolina State
University
Materials Science and
Engineering Dept.
Raleigh, NC 27605-7905
542. Joseph N. Panzarino
Norton Company
Advanced Ceramics
Goddard Road
Northboro, MA 01532-1545
543. Pellegrino Papa
Corning Inc.
MP-WX-02-1
Corning, NY 14831
544. E. Beth Pardue
Technology for Energy
Corporation
One Energy Center
P.O. Box 22996
Knoxville, TN 37933-0996
545. Soon C. Park
3M Company
3M Center
Building 142-4N-02
P.O. Box 2963
St. Paul, MN 55144
546. Hartmut Paschke
Schott Glaswerke
Christoph-Dorner-Strasse 29
D-8300 Landshut
GERMANY AIR MAIL
547. Marina R. Pascucci
GTE Laboratories, Inc.
40 Sylvan Road
Waltham, MA 02254
548. James W. Patten
Cummins Engine
Company, Inc.
Materials Engineering
P.O. Box 3005, Mail
Code 50183
Columbus, IN 47202-3005
549. Robert A. Penty
Eastman Kodak Company
KAD/D73 - 35612
901 Elmgrove Road
Rochester, NY 14653
550. Robert W. Pepper
Textron Specialty Materials
2 Industrial Avenue
Lowell, MA 01851
551. Peter Perdue
Detroit Diesel Corporation
Research Advanced Development
Group
13400 West Outer Drive,
Speed Code A-07
Detroit, MI 48239-4001

552. Bruce Peters
Dow Chemical Company
Building 52
Midland, MI 48667
553. John J. Petrovic
Los Alamos National Laboratory
Group MST-4, MS:6771
Los Alamos, NM 87545
554. Frederick S. Pettit
University of Pittsburgh
Pittsburgh, PA 15261
555. Ben A. Phillips
Phillips Engineering Company
721 Pleasant Street
St. Joseph, MI 49085
556. Richard C. Phoenix
Ohmtek, Inc.
2160 Liberty Drive
Niagara Falls, NY 14302
557. Bruce J. Pletka
Michigan Technological
University
Metallurgical and Materials
Engineering Department
Houghton, MI 49931
558. John P. Pollinger
Garrett Ceramic Components
19800 Van Ness Avenue
Torrance, CA 90501
559. P. Popper
High Technology Ceramics
International Journal
22 Pembroke Drive
Westlands Newcastle-under-Lyme
Staffs ST5 2JN
ENGLAND AIR MAIL
560. F. Porz
Universitat Karlsruhe
Institut fur Keramik Im
Maschinendau
Postfach 6980
D-7500 Karlsruhe
GERMANY AIR MAIL
561. Harry L. Potma
Royal Netherlands Embassy
Science and Technology
4200 Linnean Avenue, N.W.
Washington, DC 20008
562. Bob R. Powell
General Motors Research
Laboratories
Metallurgy Department
30500 Mound Road
Box 9055
Warren, MI 48090-9055
563. Stephen C. Pred
ICD Group, Inc.
1100 Valley Brook Avenue
Lyndhurst, NJ 07071
564. Karl M. Prewo
United Technologies Research
Center
411 Silver Lane
MS:24
East Hartford, CT 06108
565. Peter E. Price
Industrial Materials
Technology, Inc.
P.O. Box 9565
Andover, MA 01810
566. Joseph M. Proud
GTE Laboratories, Inc.
Materials Science Laboratory
40 Sylvan Road
Waltham, MA 02254
567. Vimal K. Pujari
Norton Company
Advanced Ceramics
Goddard Road
Northboro, MA 01532-1545
568. George Quinn
National Institute of
Standards and Technology
Ceramics Division, Bldg. 223
Gaithersburg, MD 20899

569. Ramas V. Raman
Ceracon, Inc.
1101 North Market Boulevard,
Suite 9
Sacramento, CA 95834
570. Charles F. Rapp
Owens Corning Fiberglass
2790 Columbus Road
Granville, OH 43023-1200
571. Dennis W. Readey
Colorado School of Mines
Department of Metallurgy
and Materials Engineering
Golden, CO 80401
572. Wilfred J. Rebello
PAR Enterprises, Inc.
12601 Clifton Hunt Lane
Clifton, VA 22024
573. Harold Rechter
Chicago Fire Brick Company
R&D
7531 South Ashland Avenue
Chicago, IL 60620
574. Robert R. Reeber
U.S. Army Research Office
P.O. Box 12211
Research Triangle Park, NC 27709
575. K. L. Reifsnider
Virginia Polytechnic Institute
and State University
Department of Engineering
Science and Mechanics
Blacksburg, VA 24061
576. Paul E. Rempes
McDonnell Douglass Missile
Systems Company
P.O. Box 516,
Mail Code:1066086
St. Louis, MO 63166-0516
577. Gopal S. Revankar
John Deere Company
Metals Research
3300 River Drive
Moline, IL 61265
578. K. T. Rhee
Rutgers University
Mechanical Engineering
P.O. Box 909
Piscataway, NJ 08854
579. James Rhodes
Advanced Composite Materials
Corporation
1525 South Buncombe Road
Greer, SC 29651
580. Roy W. Rice
W. R. Grace and Company
7379 Route 32
Columbia, MD 21044
581. David W. Richerson
2093 East Delmont Drive
Salt Lake City, UT 84117
582. Tomas Richter
J. H. France Refractories
1944 Clarence Road
Snow Shoe, PA 16874
583. Michel Rigaud
Ecole Polytechnique
Campus Universite De Montreal
P.O. Box 6079, Station A
Montreal, P.Q Quebec H3C 3A7
CANADA AIR MAIL
584. R. E. Riman
Rutgers University
Ceramics Engineering
Department
P.O. Box 909
Piscataway, NJ 08855-0909
585. Barry Ringstrom
Superior Graphite Company
P.O. Box 2373
Smyrna, GA 30081
586. John E. Ritter
University of Massachusetts
Mechanical Engineering
Department
Amherst, MA 01003

587. Frank L. Roberge
Allied-Signal Aerospace
Company
Garrett Auxiliary Power
Division
P.O. Box 5227
Phoenix, AZ 85010
588. W. Eric Roberts
Advanced Ceramic
Technology, Inc.
990 "F" Enterprise Street
Orange, CA 92667
589. Martha Rohr
U.S. Department of Energy
DOE Oak Ridge Field Office
Building 4500N
P.O. Box 2008, MS:6269
Oak Ridge, TN 37831-6269
590. Y. G. Roman
TNO TPD Keramick
P.O. Box 595
Eindhoven 5600 AN
HOLLAND AIR MAIL
591. Mark D. Roos
Carborundum Company
P.O. Box 156
Niagara Falls, NY 14302
592. Michael Rossetti
Arthur D. Little, Inc.
15 Acorn Park
Cambridge, MA 01240
593. Barry R. Rossing
Lanxide Corporation
1300 Marrows Road
Newark, DE 19714-6077
594. Steven L. Rotz
Lubrizol Corporation
29400 Lakeland Boulevard
Wickliffe, OH 44092
595. Bruce Rubinger
Global Competitiveness, Inc.
One Devonshire Place,
Suite 1011
Boston, MA 02109
596. Robert Ruh
Wright Laboratory
WL/MLLM
Wright-Patterson AFB, OH 45433
597. Robert J. Russell
17 Highgate Road
Framingham, MA 01701
598. L. William Sahley
Supermaterials Company
24400 Highland Road
Richmond Heights, OH 44143
599. Jon Salem
NASA Lewis Research Center
21000 Brookpark Center
Cleveland, OH 44135
600. W. A. Sanders
NASA Lewis Research Center
21000 Brookpark Road,
MS:49-3
Cleveland, OH 44135
601. J. Sankar
North Carolina A&T State
University
Department of Mechanical
Engineering
Greensboro, NC 27411
602. Yasushi Sato
NGK Spark Plugs (U.S.A.), Inc.
1200 Business Center Drive,
Suite 300
Mt. Prospect, IL 60056
603. Maxine L. Savitz
Allied-Signal Aerospace
Company
Garrett Ceramic Components
Division
19800 South Van Ness Avenue
Torrance, CA 90501
604. Ashok Saxena
Georgia Institute of
Technology
Materials Engineering
Atlanta, GA 30332-0245

605. David W. Scanlon
Instron Corporation
100 Royall Street
Canton, MA 02021
606. Charles A. Schacht
Schacht Consulting Services
12 Holland Road
Pittsburgh, PA 15235
607. James Schienle
Allied-Signal Aerospace
Company
Garrett Auxiliary Power
Division
2739 East Washington Street
P.O. Box 5227, MS:1302-2P
Phoenix, AZ 85010
608. John C. Schneider
San Juan Technologies
P.O. Box 49326
Colorado Springs, CO 80949-9326
609. Gary Schnittgrund
Rocketdyne, BA05
6633 Canoga Avenue
Canoga Park, CA 91303
610. Mark Schomp
Lonza, Inc.
Corporate Headquarters
17-17 Route 208
Fair Lann, NJ 07410
611. Joop Schoonman
Delft University of Technology
Laboratory for Inorganic
Chemistry
P.O. Box 5045
2600 GA Delft
THE NETHERLANDS AIR MAIL
612. John Schuldies
Industrial Ceramic
Technology, Inc.
37 Enterprise Drive
Ann Arbor, MI 48103
613. Robert B. Schulz
U.S. Department of Energy
Office of Transportation
Materials
CE-34, Forrestal Building
Washington, DC 20585
614. Murray A. Schwartz
Materials Technology
Consulting, Inc.
30 Orchard Way, North
Potomac, MD 20854
615. Peter Schwarzkopf
SRI International
333 Ravenswood Avenue
Menlo Park, CA 94025
616. Thomas C. Schweizer
Princeton Economic
Research, Inc.
12300 Twinbrook Pkwy.,
Suite 650
Rockville, MD 20852
617. William T. Schwessinger
Multi-Arc Scientific
Coatings
1064 Chicago Road
Troy, MI 48083-4297
618. W. D. Scott
University of Washington
Materials Science Department
Mail Stop:FB10
Seattle, WA 98195
619. Nancy Scoville
Thermo Electron Technologies
74 West Street
P.O. Box 9046
Waltham, MA 02254-9046
620. Brian Seegmiller
Coors Ceramics Company
600 9th Street
Golden, CO 80401

621. T. B. Selover
AICRE/DIPPR
3575 Traver Road
Shaker Heights, OH 44122
622. J. H. Selverian
GTE Laboratories, Inc.
40 Sylvan Road
Waltham, MA 02254
623. Charles E. Semler
Semler Materials Services
4160 Mumford Court
Columbus, OH 43220
624. Thomas Service
Service Engineering Laboratory
324 Wells Street
Greenfield, MA 01301
625. Kish Seth
Ethyl Corporation
R&D Laboratories
P.O. Box 341
Baton Rouge, LA 70821
626. Karleen Seybold
Allied-Signal Aerospace
Company
Garrett Auxiliary Power
Division
P.O. Box 5227
Phoenix, AZ 85010
627. William J. Shack
Argonne National Laboratory
9700 South Cass Avenue
Building 212
Argonne, IL 60439
628. Peter T. B. Shaffer
Technical Ceramics
Laboratories, Inc.
4045 Nine/McFarland Drive
Alpharetta, GA 30201
629. Richard K. Shaltens
NASA Lewis Research Center
21000 Brookpark Road,
MS:301-2
Cleveland, OH 44135
630. Robert S. Shane
238 Hemlock Road
Wynnewood, PA 19096
631. Daniel Shanefield
Rutgers University
Ceramics Engineering
Department
P.O. Box 909
Piscataway, NJ 08855-0909
632. Ravi Shankar
Chromalloy
Research and Technology
Division
Blaisdell Road
Orangeburg, NY 10962
633. Terence Sheehan
Alpex Wheel Company
727 Berkley Street
New Milford, NJ 07646
634. Dinesh K. Shetty
University of Utah
304 EMRO, Dept. of Materials
Science and Engineering
Salt Lake City, UT 84112
635. Masahide Shimizu
Ceramic Society of Japan
2-2-503 Takiyama 6-chome
Higashikurume-Shi Tokyo 203
JAPAN AIR MAIL
636. John Shipinski
Toyota Technical Center
U.S.A., Inc.
Technical Research Department
2000 Town Center, Suite 500
Southfield, MI 48075
637. Thomas Shreves
American Ceramic Society, Inc.
Library
757 Brooksedge Plaza Drive
Westerville, OH 43081-2821
638. Jack D. Sibold
Coors Ceramics Company
Contracts for Corporate
Technology
4545 McIntyre Street
Golden, CO 80403

639. George H. Siegel
Point North Associates, Inc.
P.O. Box 907
Madison, NJ 07940
640. Richard Silberglitt
Technology Assessment and
Transfer, Inc.
133 Defense Highway, #212
Annapolis, MD 21401
641. Mary Silverberg
Norton Company
Advanced Ceramics Library
Goddard Road
Northboro, MA 01532-1545
642. Gurpreet Singh
Department of the Navy
Internal Combustion & Gas
Turbine Engine Division
Code 56X31
Washington, DC 20362-5101
643. Maurice J. Sinnott
University of Michigan
Chemical and Metallurgical
Engineering
5106 IST Building
Ann Arbor, MI 48109-2099
644. John Skildum
3M Company
3M Center
Building 224-2S-25
St. Paul, MN 55144
645. David P. Smith
Hoskins, Rees & Smith
1910 Cochran Road
Manor Oak II, Suite 658
Pittsburgh, PA 15220
646. Richard H. Smoak
Smoak & Associates
3554 Hollyslope Road
Altadena, CA 91001-3923
647. Jay R. Smyth
Allied-Signal Aerospace
Company
Garrett Auxiliary Power
Division
2739 East Washington Street
P.O. Box 5227
MS:93-173/1303-207
Phoenix, AZ 85010
648. Edward A. Snajdr
Premier Refractories
and Chemicals, Inc.
P.O. Box 392
Findlay, OH 44815
649. Rafal A. Sobotowski
British Petroleum Company
Technical Center, Broadway
3092 Broadway Avenue
Cleveland, OH 44115
650. A. G. Solomah
SAC International Ltd.
1445 Bonhill Road, # 13
Mississauga Ontario L5T 1V3
CANADA AIR MAIL
651. S. Somiya
Nishi Tokyo University
3-7-19 Seijo, Setagaya
Tokyo 157
JAPAN AIR MAIL
652. Boyd W. Sorenson
DuPont Lanxide Composites
1300 Marrows Road
P.O. Box 6077
Neward, DE 19707
653. Charles A. Sorrell
U.S. Department of Energy
Advanced Industrial
Concepts Division
CE-232, Forrestal
Building
Washington, DC 20585

654. C. Spencer
EA Technology
Capenhurst Chester
CH1 6ES
UNITED KINGDOM AIR MAIL
655. Allen Spizzo
Hercules, Inc.
Hercules Plaza
Wilmington, DE 19894
656. Richard M. Spriggs
Alfred University
Center for Advanced Ceramic
Technology
Alfred, NY 14802
657. Charles Spuckler
NASA Lewis Research Center
21000 Brookpark Road
MS: 5-11
Cleveland, OH 44135-3191
658. M. Srinivasan
Material Solutions
P.O. Box 663
Grand Island, NY 14702-0663
659. Gordon L. Starr
Cummins Engine Company, Inc.
Design & Technology
P.O. Box 3005
Mail Code 50182
Columbus, IN 47202-3005
660. Jim Stevenson
Windrock, Incorporated
154 Fairbanks Plaza
Oak Ridge, TN 37830
661. Tom Stillwagon
Allied-Signal Aerospace
Company
Garrett Ceramic Components
Division
19800 South Van Ness Avenue
Torrance, CA 90501
662. Harold L. Stocker
General Motors Corporation
Allison Gas Turbine Division
P.O. Box 420
Indianapolis, IN 46206
663. Paul D. Stone
Dow Chemical USA
1776 "Eye" Street, N.W.,
Suite 575
Washington, DC 20006
664. Roger S. Storm
Carborundum Company
Technology Division
P.O. Box 337
Niagara Falls, NY 14302-0337
665. Peter A. Stranges
4 Chittenden Lane
Owings Mills, MD 21117
666. F. W. Stringer
Aero & Industrial
Technology Ltd.
P.O. Box 46, Wood Top
Burnley Lancashire BB11 4BX
UNITED KINGDOM AIR MAIL
667. Thomas N. Strom
NASA Lewis Research Center
21000 Brookpark Road
MS:86-6
Cleveland, OH 44135
668. M. F. Stroosnijder
Institute for Advanced
Materials
Joint Research Centre
21020 Ispra (VA)
ITALY AIR MAIL
669. Karsten Styhr
30604 Ganado Drive
Rancho Palos Verdes, CA 90274
670. T. S. Sudarshan
Materials Modification, Inc.
2929-P1 Eskridge Center
Fairfax, VA 22031
671. M. J. Sundaresan
University of Miami
Mechanical Engineering
Department
P.O. Box 248294
Coral Gables, FL 33124

672. Patrick L. Sutton
U.S. Department of Energy
Advanced Propulsion Division
CE-322, Forrestal Building
Washington, DC 20585
673. Willard H. Sutton
United Technologies
Corporation
Research Center, MS:24
Silver Lane
East Hartford, CT 06108
674. Ron Sviben
100 Indel Avenue
Rancocas, NJ 08073
675. J. J. Swab
U.S. Army Materials Technology
Laboratory
Ceramics Research Division
SLCMT-EMC
405 Arsenal Street
Watertown, MA 02172
676. Robert E. Swanson
Metalworking Technology, Inc.
1450 Scalp Avenue
Johnstown, PA 15904
677. Scott L. Swartz
Battelle Columbus
Laboratories
Metals and Ceramics
505 King Avenue
Columbus, OH 43201
678. Steve Szaruga
Air Force Wright Aeronautical
Laboratory
Materials Directorate
WL/MLBC
Wright-Patterson
AFB, OH 45433-6533
679. Yo Tajima
NGK Spark Plug Company, Ltd.
NTK Technical Ceramic Division
2808 Iwasaki
Komaki-shi Aichi-ken 485
JAPAN AIR MAIL
680. Fred Teeter
5 Tralee Terrace
East Amherst, NY 14051
681. Monika O. Ten Eyck
Carborundum Company
Technology Division
P.O. Box 832
Niagara Falls, NY 14302
682. David F. Thompson
Corning Glass Works
SP-DV-02-1
Corning, NY 14831
683. Merle L. Thorpe
Hobart Tafa Technologies, Inc.
146 Pembroke Road
Concord, NH 03301
684. Eberhard Tiefenbacher
Daimler-Benz AG Abt. F1S
Mercedes-Strabe 136
Stuttgart 60
GERMANY AIR MAIL
685. T. Y. Tien
University of Michigan
Materials Science and
Engineering Department
Dow Building
Ann Arbor, MI 48103
686. Julian M. Tishkoff
Air Force Office of Scientific
Research
AFOSR/NA
Bolling AFB, DC 20332-6448
687. D. M. Tracey
Norton Company
Advanced Ceramics
Goddard Road
Northboro, MA 01532-1545
688. Dick Trippett
General Motors Corporation
Allison Gas Turbine Division
P.O. Box 420, MS:W-16
Indianapolis, IN 46206-0420

689. L. J. Trostel, Jr.
Box 199
Princeton, MA 01541
690. W. T. Tucker
General Electric Company
Corporate R&D
Building K1-4C35
P.O. Box 8
Schenectady, NY 12301
691. Masanori Ueki
Nippon Steel Corporation
Central R&D Bureau
1618 Ida
Nakahara-Ku Kawasaki 211
JAPAN AIR MAIL
692. Filippo M. Ugolini
ATA Studio
Via Degli Scipioni, 268A
ROMA 00192
ITALY AIR MAIL
693. Donald L. Vaccari
Allison Gas Turbines
P.O. Box 420
Speed Code S49
Indianapolis, IN 46206-0420
694. Carl F. Van Conant
Boride Products, Inc.
2879 Aero Park Drive
Traverse City, MI 49684
695. Marcel H. Van De Voorde
Commission of the European
Communities
Institute for Advanced
Materials
Joint Research Centre
P.O. Box 2
1755 ZG Petten
THE NETHERLANDS AIR MAIL
696. O. Van Der Biest
Katholieke Universiteit Leuven
Departement Metaalkunde en
Toegepaste
de Croylaan 2
B-3030 Leuven
BELGIUM AIR MAIL
697. Michael Vannier
Washington University,
St. Louis
Mallinckrodt Institute of
Radiology
510 South Kings Highway
St. Louis, MO 63110
698. Stan Venkatesan
Southern Coke & Coal
Corporation
P.O. Box 52383
Knoxville, TN 37950
699. V. Venkateswaran
Carborundum Company
Niagara Falls R&D Center
P.O. Box 832
Niagara Falls, NY 14302
700. Dennis Viechnicki
U.S. Army Materials Technology
Laboratory
405 Arsenal Street
Watertown, MA 02172-0001
701. Ted Vojnovich
U.S. Department of Energy
Office of Energy Research,
ER-42
Washington, DC 20585
702. John D. Volt
E. I. Dupont de Nemours &
Company, Inc.
P.O. Box 80262
Wilmington, DE 19880
703. John B. Wachtman
Rutgers University
Ceramics Department
P.O. Box 909
Piscataway, NJ 08855
704. Shigetaka Wada
Toyota Central Research
Labs, Inc.
Nagakute Aichi 480-11
JAPAN AIR MAIL

705. Janet Wade
Allied-Signal Aerospace
Company
Garrett Auxiliary Power
Division, Department 93-772
P.O. Box 5227, MS:1303-2
Phoenix, AZ 85010
706. Richard L. Wagner
Ceramic Technologies, Inc.
537 Turtle Creek South Drive,
Suite 24D
Indianapolis, IN 46227
707. J. Bruce Wagner, Jr.
Arizona State University
Center for Solid State
Science
Tempe, AZ 85287-1704
708. Daniel J. Wahlen
Kohler, Co.
444 Highland Drive
Kohler, WI 53044
709. Ingrid Wahlgren
Royal Institute of Technology
Studsvik Library
S-611 82 Nykoping
SWEDEN AIR MAIL
710. Ron H. Walecki
Allied-Signal Aerospace
Company
Garrett Ceramic Components
Division
19800 South Van Ness Avenue
Torrance, CA 90501
711. Michael S. Walsh
Vapor Technologies Inc.
2100 Central Avenue
Boulder, CO 80301
712. Chien-Min Wang
Industrial Technology Research
Institute
Materials Research Laboratories
195 Chung-Hsing Road, Sec. 4
Chutung Hsinchu 31015 R.O.C.
TAIWAN AIR MAIL
713. Robert M. Washburn
ASMT
11203 Colima Road
Whittier, CA 90604
714. Gerald Q. Weaver
Carborundum Specialty Products
42 Linus Allain Avenue
Gardner, MA 01440-2478
715. Karen E. Weher
Detroit Diesel Corporation
Technology and Planning
13400 West Outer Drive
Detroit, MI 48239-4001
716. R. W. Weeks
Argonne National Laboratory
MCT-212
9700 South Cass Avenue
Argonne, IL 60439
717. Ludwig Weiler
ASEA Brown Boveri AG
Corporate Research
Eppelheimer Str. 82
D-6900 Heidelberg
GERMANY AIR MAIL
718. James Wessel
Dow Corning Corporation
1800 "M" Street, N.W.,
Suite 325 South
Washington, DC 20036
719. Robert D. West
Therm Advanced Ceramics
P.O. Box 220
Ithaca, NY 14851
720. Thomas J. Whalen
Ford Motor Company
26362 Harriet
Dearborn Heights, MI 48127
721. Ian A. White
Hoeganaes Corporation
River Road
Riverton, NJ 08077

722. Alan Whitehead
General Electric Company
1 River Road, 55-111
Schenectady, NY 12345
723. Sheldon M. Wiederhorn
National Institute of
Standards and Technology
Building 223, Room A329
Gaithersburg, MD 20899
724. John F. Wight
Alfred University
McMahon Building
Alfred, NY 14802
725. D. S. Wilkinson
McMaster University
Materials Science and
Engineering Department
1280 Main Street, West
Hamilton Ontario L8S 4L7
CANADA AIR MAIL
726. James C. Williams
General Electric Company
Engineering Materials
Technology Labs
One Neumann Way
Mail Drop: H85
Cincinnati, OH 45215-6301
727. Janette R. Williams
Kollmorgen Corporation
PCK Technology Division
150 Motor Parkway, # 262
Hauppauge, NY 11788-5108
728. Steve J. Williams
RCG Hagler Bailly, Inc.
1530 Wilson Boulevard,
Suite 900
Arlington, VA 22209-2406
729. Craig A. Willkens
Norton Company
Advanced Ceramics
Goddard Road
Northboro, MA 01532-1545
730. Roger R. Wills
TRW, Inc.
Valve Division
1455 East 185th Street
Cleveland, OH 44110
731. David Gordon Wilson
Massachusetts Institute of
Technology
Mechanical Engineering
Department
77 Massachusetts Avenue,
Room 3-455
Cambridge, MA 02139
732. Matthew F. Winkler
Seaworthy Systems, Inc.
P.O. Box 965
Essex, CT 06426
733. Gerhard Winter
Hermann C. Starck Berlin GmbH,
Werk Goslar
P.O. Box 25 40
D-3380 Goslar 3380
GERMANY AIR MAIL
734. W. L. Winterbottom
Ford Motor Company
Material Systems Reliability
Department
20000 Rotunda Drive
SRL, Room E-3182
P.O. Box 2053
Dearborn, MI 48121
735. David G. Wirth
Coors Ceramics Company
600 9th Street
Golden, CO 80401
736. Thomas J. Wissing
Eaton Corporation
Engineering & Research Center
P.O. Box 766
Southfield, MI 48037
737. James C. Withers
MER Corporation
7960 South Kolb Road
Building F
Tucson, AZ 85706

738. Dale E. Wittmer
Southern Illinois University
Mechanical Engineering
Department
Carbondale, IL 62901
739. Warren W. Wolf
Owens Corning Fiberglass
2790 Columbus Road, Route 16
Granville, OH 43023
740. George W. Wolter
Howmet Turbine Components
Corporation
Technical Center
699 Benston Road
Whitehall, MI 49461
741. James C. Wood
NASA Lewis Research Center
21000 Brookpark Road
MS:86-6
Cleveland, OH 44135
742. Marrill Wood
LECO Corporation
Augusta Division
P.O. Box 211688
Augusta, GA 30917-1688
743. Wayne L. Worrell
University of Pennsylvania
Department of Materials
Science and Engineering
3231 Walnut Street
Philadelphia, PA 19104
744. John F. Wosinski
Corning Inc.
ME-2 E-5 H8
Corning, NY 14830
745. Ian G. Wright
Battelle Columbus Laboratories
505 King Avenue
Columbus, OH 43201
746. Ruth Wroe
ERDC
Metals & Materials Industries
Division
Capenhurst Chester CH1 6ES
ENGLAND AIR MAIL
747. Bernard J. Wrona
Advanced Composite Materials
Corporation
1525 South Buncombe Road
Greer, SC 29651
748. Carl C. M. Wu
Naval Research Laboratory
Ceramic Branch, Code 6373
Washington, DC 20375
749. John C. Wurst
University of Dayton Research
Institute
300 College Park
Dayton, OH 45469-0101
750. Neil Wyant
ARCH Development Corp.
9700 South Cass Avenue
Building 202
Argonne, IL 60439
751. Roy Yamamoto
Texaco Inc.
P.O. Box 509
Beacon, NY 12508-0509
752. John Yamanis
Allied-Signal, Inc.
Ceramics Program
P.O. Box 1021
Morristown, NJ 07962-1021
753. Harry C. Yeh
Allied-Signal Aerospace
Company
Garrett Ceramic Components
Division
19800 South Van Ness Avenue
Torrance, CA 90509
754. Hiroshi Yokoyama
Hitachi Research Lab
4026 Kuji-Cho
Hitachi-shi Ibaraki 319-12
JAPAN AIR MAIL
755. Thomas M. Yonushonis
Cummins Engine Company, Inc.
P.O. Box 3005
Mail Code 50183
Columbus, IN 47202-3005

756. Thomas J. Yost
Corning, Inc.
Technical Products Division,
Main Plant 21-1-2
Corning, NY 14831
757. Jong Yung
Sundstrand Aviation
Operations
Department 789-6
4747 Harrison Avenue
Rockford, IL 61125
758. A. L. Zadoks
Caterpillar Inc.
Technical Center, Building L
P.O. Box 1875
Peoria, IL 61656-1875
759. Avi Zangvil
University of Illinois
Materials Research Laboratory
104 South Goodwin Avenue
Urbana, IL 61801
760. Charles H. Zenuk
Transtech
6529 East Calle Cavalier
Tucson, AZ 85715
761. Anne Marie Zerega
U.S. Department of Energy
Office of Energy Research,
ER-42
Washington, DC 20585
762. Ken Zillmer
Applied Test Systems, Inc.
2571 Mt. Gallant Road
Rock Hill, SC 29730
763. Carl Zweben
General Electric Company
P.O. Box 8555, VFSC/V4019
Philadelphia, PA 19101
764. Klaus M. Zwilsky
National Research Council
National Materials
Advisory Board
2101 Constitution Avenue
Washington, DC 20418
765. Department of Energy
DOE Field Office, Oak Ridge
Assistant Manager for Energy
Research and Development
P.O. Box 2001
Oak Ridge, TN 37831-8501
- 766-775. Department of Energy
Office of Scientific and
Technical Information
Office of Information
Services
P.O. Box 62
Oak Ridge, TN 37831
- For distribution by microfiche
as shown in DOE/OSTI-4500,
Distribution Category UC-332
(Ceramics/Advanced Materials).

END

DATE
FILMED

6 / 11 / 93