DOE/PC/91311--T5

DOE/PC/91311--T5

DE93 008191

QUARTERLY PROGRESS REPORT

ON

CONFIGURATIONAL DIFFUSION OF ASPHALTENES IN FRESH AND AGED CATALYSTS EXTRUDATES

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

Grant No. DE-FG22-91PC91311

9-20-92 to 12-20-92

James A. Guin
A Ray Tarrer

Chemical Engineering Department
Auburn University
Auburn, AL 36849

MASTER

REPRODUCTION OF THIS DOCUMENT IS UNLIMITED

EP

Table of Contents

Objective and Work Statement.....	1
Summary of Progress.....	3
Planned Work.....	3
Detailed Progress—Restrictive Diffusion in Fresh Shell 324 Catalyst	
Theory.....	4
Experimental.....	5
Results and Discussion.....	6
Adsorption Isotherm.....	6
Diffusional Runs and Data Treatment with Numerical Solution.....	6
Conclusion.....	9

Statement of Work

Configurational Diffusion of Asphaltenes in Fresh and Aged Porous Catalyst Extrudates

Objective: The objective of this research is to determine the relationship between the size and shape of coal and petroleum macromolecules and their diffusion rates i.e., effective diffusivities, in catalyst pore structures. That is, how do the effective intrapore diffusivities depend on molecule configuration and pore geometry.

Task 1. Relationship Between Effective Intrapore Diffusion Coefficients, Molecular Size and Pore Geometry.

Finite bath-type diffusion experiments will be performed using both coal and petroleum-derived macromolecular species, e.g. asphaltenes, as well as model compounds, e.g. porphyrins, polymers, of known molecular size. By monitoring the concentration of solute macromolecules in the bath, the effective intrapore diffusion coefficients will be determined through application of the appropriate diffusion equations. Macromolecular species concentrations will be monitored by size exclusion chromatography (SEC). Relationships will be sought between the size, and shape, e.g. planar, coil, of the diffusing solutes and the pore geometry (pore size distribution) of the catalyst support. The effects of molecule configuration and catalyst pore size distribution on the effective intrapore diffusivity will be examined. Specially prepared laboratory catalysts with very narrow pore size distributions and other model porous media, e.g. porous Vycor glass, will be utilized in the experiments. Pore structures of all catalysts and other porous media will be characterized by mercury porosimetry and surface area (BET) analysis.

Task 2. Effects of Solvent Composition, Solute Concentration, and Temperature on the Molecular Configuration and Diffusion Rate of Coal and Petroleum Asphaltenes in Catalyst Pores.

Diffusion experiments such as in Task 1 will be performed with varying solvent compositions, i.e., paraffinic-aromatic mixtures, to examine the effects of the state of molecular aggregation (self-assemblies) on the rates of diffusion of coal and petroleum asphaltenes in the catalyst pores. Similar experiments will be performed to study the effect of *temperature* and solute (macromolecule) *concentration* on the state of molecular configuration and aggregation on the resulting pore diffusivity.

Task 3. Assessment of Diffusional Limitations in Aged Catalysts

Diffusivity measurements such as conducted in Task 1 will be performed with both model compound and coal-derived macromolecular species using extrudate-type aged catalysts from laboratory experiments as well as aged catalysts obtained from actual coal liquefaction pilot plants such as the Wilsonville, AL Advanced Coal Liquefaction R & D Facility. From the experimental diffusivities so obtained, an evaluation of effects of changes in catalyst pore structure, e.g. tortuosity, pore plugging, shall be made. The changes in pore diffusivities associated with the pore structural changes caused by coke and metals deposition will be investigated, as compared with the fresh catalysts. An assessment of the relationship of increased diffusional limitations to coke and metals deposition in the catalyst pores will be made based on the results of the diffusivity measurements. The degree to which pore diffusivities can be restored to their original values by carefully controlled oxidation and/or extractive catalyst regeneration techniques also will be explored. The practical importance of these findings to coal liquefaction technology will be evaluated.

Summary

During this quarter, equilibrium adsorption experiments were carried out to determine the type of adsorption isotherm which was needed in the mathematical treatment of the kinetic data. The equilibrium isotherm for quinoline in cyclohexane with fresh Shell 324 catalyst was found to be nonlinear and was well represented by the Freundlich adsorption isotherm.

The effective diffusivity was determined by applying a pore diffusional model with a Freundlich adsorption isotherm to diffusional run data. The effective diffusivity was found to be less than the estimated pore diffusivity for non-restrictive diffusion, which indicated the pore restriction for the diffusion of quinoline in cyclohexane with Shell 324 catalyst.

Planned Work

Next quarter additional diffusional systems will be employed, possibly using TPP as a diffusional solute, and as well as fresh catalysts. Experimental work will include both diffusional uptake and equilibrium adsorption experiments.

RESTRICTIVE DIFFUSION IN SHELL 324 CATALYST

THEORY

As discussed in the Quarterly Report, Summer, 1992⁽¹⁾, for a well stirred bath diffusional cell where the external mass transfer is relatively fast, the dimensionless diffusional model with Freundlich adsorption isotherm can be described as

$$\frac{\partial \theta_a}{\partial t^*} + E \frac{\partial \theta_a^{\frac{1}{n}}}{\partial t^*} = \frac{1}{\xi^2} \frac{\partial}{\partial \xi} \left(\xi^2 \frac{\partial \theta_a}{\partial \xi} \right) \quad (1)$$

$$\xi=0, \frac{\partial \theta_a}{\partial t^*} = 0 \quad (2)$$

$$\xi=1, \frac{\partial \theta_a}{\partial t^*} = -\frac{3}{F} \frac{\partial \theta_a}{\partial \xi} \quad (3)$$

$$\xi=1, \theta_a = \theta_b = \frac{C_b}{C_{b0}} \quad (4)$$

$$t^*=0, \theta_a|_{\xi=1} = 0 \quad (5)$$

$$t^*=0, \theta_a|_{\xi=1} = 1 \quad (6)$$

where

$$E = \frac{\rho_p m C_{b0}^{\frac{1}{n}}}{K_p e C_{b0}} \quad (7)$$

$$F = \frac{V_b}{K_p e V_p} = \frac{\rho_p V_b}{K_p e W} \quad (8)$$

The above PDEs can be solved numerically given values for

constants of E, F and n, and plots of dimensionless bath concentration C_v/C_{v0} vs. dimensionless time t^* can be drawn.

EXPERIMENTAL

Materials

Quinoline and cyclohexane were chosen as diffusional solute and solvent, respectively. The solvent was pretreated with 4A molecular sieve to remove water.

The extrudate catalyst employed in this work was fresh Shell 324 Ni-Mo/Al₂O₃ catalyst. The catalyst pellets were crushed and sieved to 10-12 Tyler mesh sizes. The sized catalysts were calcined in a muffle furnace at 473K for 4 hours and at 673K for 12 hours. The calcined catalyst was then preserved in desiccator for later use.

Procedures

Two types of experiments were carried out: equilibrium adsorption and diffusional runs at room temperature (298±2 K). The equilibrium solute uptakes for the Shell 324 catalyst were measured at different concentrations of quinoline in cyclohexane to obtain the adsorption isotherm. The equilibrium concentrations were determined by using an ultraviolet spectrophotometer at two wavelengths of 270 and 274 nm, respectively. The amount of solute quinoline taken up by the catalysts at equilibrium was calculated by the difference between the initial and the equilibrium adsorption solution concentrations.

The diffusion experiments were performed in the mechanically stirred metal as well as glass vessels containing wire screen baskets for catalyst holding. The basket containing the catalyst presaturated by solvent was then placed in the vessel filled with quinoline/cyclohexane solution. During the diffusional run, the concentration of the solution was analyzed periodically by UV spectrometer.

RESULTS AND DISCUSSION

Adsorption Isotherm

Results from equilibrium adsorption experiments of quinoline in cyclohexane with Shell 324 catalyst(10-12 mesh) at 298K are presented in Figure 1, which indicates a strongly nonlinear dependence of equilibrium solute uptake on equilibrium concentration. A Freundlich Isotherm of $q_e = mC_e^{1/n}$ was used to fit the equilibrium adsorption data. Values of Freundlich constants were determined by a least-square analysis of $\ln(q_e)$ vs. $\ln(C_e)$, as shown in Figure 2. The Freundlich constants of m and n were found to be 50 and 10.6, respectively, or:

$$q = 50 * C^{\frac{1}{10.6}} \quad (9)$$

Figure 1 also shows the adsorption data plotted using equation (9). The agreement with the experimental data showed that the Freundlich isotherm is followed quite well.

Diffusional Runs and Data Treatment with Numerical Solution

Results from diffusional runs to check the external mass

transfer resistance by varying the stirring speed are shown in Figure 3. From this Figure it can be seen that the external mass transfer resistance at stirring speed higher than 800 rpm was negligible. Thus we choose the stirring speed at 800 rpm for the diffusional run.

Diffusional runs with three different amount of catalysts, or different values of F , are presented in Figures 4, 5, 6, respectively. It can be seen that larger amounts of catalyst enhanced the diffusional rate resulting in the lower values of C_p/C_{b0} at the same diffusional time. This was reasonable, because a larger amount of catalyst would adsorb more solute.

In obtaining the effective diffusivity by treating the kinetic data of diffusional runs using the pore diffusional model, the values for parameters of E and F should be known. E and F can be calculated from the adsorption isotherm constants and the properties of catalyst and diffusional solution, as shown in Table 1. The calculated values of F for the three diffusional runs were

Table 1. Properties of catalyst and diffusional solution and calculated values of E and F

			Ref.
solution	volume, cc	195	
	solute diameter, °A	7.4	(2)
	molecular diffusivity, cm ² /s	11.35*10 ⁻⁶	(3)
	initial concentration, mg/cc	0.0312	
catalyst	particle density, g/cc	1.4	(4)
	porosity	0.57	(4)
	average particle radius, cm	0.08	
	average pore diameter, °A	98	(4)
calculated	weight, g	0.2, 0.4, 1.0	
	F	2809, 1378, 550	
	E	3279	

2809, 1378, and 550, respectively. The values for E were all the same, 3279. Figures 4, 5 and 6 plotted the numerical solution for dimensionless bath concentration with respect to time for specific values of dimensionless constants of E and F. As shown in Figures 4, 5 and 6, the best fits of effective diffusivities were 3.2, 2.7 and 2.1×10^{-6} cm²/s for the F values of 2809, 1378 and 550, respectively. The average of these three values is 2.7×10^{-6} cm²/s.

To check the sensitivity of the value for effective diffusivity to the numerical solution, Figure 7 plotted the effect of effective diffusivity on the computed data curve. From Figure 7 it can be seen that for the D_e range of $3.2 \pm 0.5 \times 10^{-6}$ cm²/s, the computed data points did not change very much compared with the experimental error, which was about 10% for C_v/C_{v0} .

Theoretically, the effective diffusivity should be the same at each catalyst loading. To get an average value of effective diffusivity, Figure 8 plotted the dimensionless time t^* with respect to realtime t for different values of F, which should give a straight line according the equation:

$$t^* = \frac{D_e}{R^2 K_p \epsilon} t \quad (10)$$

From the slope of this straight line, the average effective diffusivity can be calculated, which was about 2.8×10^{-6} cm²/s.

Table 2 lists the values for several parameters obtained from data fitting. The ratio of effective diffusivity to free-pore diffusivity D_e/D_{pe} was substantially less than 1, which means a strong pore restriction or tortuosity effect existed in the

diffusion of quinoline with fresh Shell 324 catalyst. The calculated tortuosity τ was about 1.7, which is also reasonable for supported alumina catalyst.

Table 2. Calculated Values for Quinoline/
Cyclohexane/Shell 324 System

K_p	K_r	D_e $\times 10^6 \text{ cm}^2/\text{s}$	$D_m \epsilon$ $\times 10^6 \text{ cm}^2/\text{s}$	$D_e/D_m \epsilon$	τ^a
0.85	0.85	2.8 ± 0.7	6.5	0.43	1.7

a. τ can be calculated from the equation $D_e = D_m K_r K_p \epsilon / \tau$

CONCLUSION

Based on the above work, the following conclusions can be drawn:

1. The equilibrium adsorption isotherm of quinoline in cyclohexane with fresh Shell 324 catalyst was nonlinear and can be well fitted by Freundlich isotherm in the experiment range as $q = 50 \cdot C^{1/10.6}$.
2. The average effective diffusivity for above system was obtained by applying a pore diffusional model with Freundlich adsorption to the diffusional run data. The fitted effective diffusivity was $2.8 \pm 0.7 \times 10^{-6} \text{ cm}^2/\text{s}$.
3. The value for the ratio of effective diffusivity to the pore diffusivity $D_e/D_m \epsilon$, which is substantially less than 1, indicated a pore restriction or tortuosity effect existed in the diffusion of quinoline in cyclohexane with fresh Shell 324 catalyst.

REFERENCES

1. Guin, J. A. and A. R. Tarrer, Summer Quarterly Report to DOE, 1992.
2. Tsai, C. H., et al., Ind. Eng. Chem. Res., 30 22(1991).
3. Chantong, A., Ph. D. Dissertation, University of Utah. 1982.
4. Guin, J. A., et al., Ind. Eng. Chem. Process Des. Dev., 25, 515(1986).

$$q = 50 * C^{(1/10.6)}$$

Fig. 1 Equilibrium Adsorption Isotherm
for Quinoline in cyclohexane
with Shell 324 catalyst

Fig. 2 Relationship between $\ln q_e$ and $\ln C_e$ for Quinoline in Cyclohexane with Fresh Shell 324 Catalyst

Fig. 3 Effect of Stirring Speed
on the Diffusion Rates

Fig. 4 Concentration Decay Curve for
 Quinoline in Cyclohexane with
 Shell 324. F=2809, W=0.2 g

Fig. 5 Concentration Decay Curve for Quinoline in Cyclohexane with Shell 324. $F=1378$, $W=0.4$ g

Fig. 6 Concentration Decay Curve for Quinoline in Cyclohexane with Shell 324. $F=550$, $W=1.0$ g

Fig. 7 Effect of Effective Diffusivity on the Computed Results for $E=3279$, $F=2809$, $n=10.6$

Fig. 8 Fit of adsorptive Diffusion Rate Data to Pore Diffusion Model for Quinoline in Cyclohexane with Shell 324

END

DATE
FILMED
3/19/93