HEDL-7624

SWELLING OF SOLUTE-MODIFIED Fe-Cr-Mn ALLOYS IN FFTF-MOTA

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

HANFORD ENGINEERING DEVELOPMENT LABORATORY — Operated by Westinghouse Hanford Company, P.O. Box 1970, Richland, WA, a Subsidiary of Westinghouse Electric Corporation. Prepared for the USDOE, Office of Energy Research, Office of Fusion Energy, under Contract No. DE-AC06-76FF02170, B&R No. AT-15-02-03-04.

DISCLAIMER

Portions of this document may be illegible in electronic image products. Images are produced from the best available original document.

HEDL-7624

SWELLING OF SOLUTE-MODIFIED Fe-Cr-Mn ALLOYS IN FFTF-MOTA

HEDL--7624

DE87 005454

F.A. Garner

Date Published: October 1986

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

jsu
MASTER

HANFORD ENGINEERING DEVELOPMENT LABORATORY — Operated by Westinghouse Hanford Company, P.O. Box 1970, Richland, WA, a Subsidiary of Westinghouse Electric Corporation. Prepared for the USDOE, Office of Energy Research, Office of Fusion Energy, under Contract No. DE-AC06-76FF02170, B&R No. AT-15-02-03-04.

OBJECTIVE

The object of this effort is to assess the suitability of austenitic Fe-Cr-Mn alloys as low activation candidates for fusion reactor structural materials.

SUMMARY

Density change data continue to be accumulated on solute-modified and commercial Fe-Cr-Mn alloys irradiated at 520°C and 50 dpa. The tendency toward saturation of density change observed in the simple ternary alloys in the annealed condition is accentuated by cold-working and solute addition. Irradiation at 420°C appears to further accelerate the tendency toward saturation.

PROGRESS AND STATUS

Introduction

The neutron-induced swelling of the annealed condition of simple Fe-Cr-Mn austenitic alloys at 9-14 dpa and 420-600°C has been described in previous reports.¹⁻⁴ Data on these same annealed alloys at 49.8 dpa and 520°C has also been presented.⁵ As shown in Fig. 1, it appeared from these data that simple Fe-Cr-Mn austenitic alloys in the range 420-520°C initially swell at a rate of ~1%/dpa after an incubation period of ~10 dpa, consistent with the behavior observed in annealed Fe-Cr-Ni austenitic alloys.⁶ At 520°C and 50 dpa, however, saturation of swelling appeared to be developing,⁽⁵⁾ as shown in Fig. 2.

Swelling data continue to be accumulated, with the major emphasis directed toward the solute-modified ternary alloys (See Table 1) and the commercial alloys (See Table 2) irradiated at 520°C. A limited amount of data on simple ternary alloys at 420°C and 46 dpa is also available.

Fig. 1. Swelling at 9-14 dpa of simple Fe-Mn and Fe-Cr-Mn alloys at (420°C, 9 dpa) and (520°C, 14 dpa) in FFTF-MOTA.³

Fig. 2. Swelling of simple Fe-Mn and Fe-Cr-Mn alloys at 520°C.⁵ The swelling of commercial alloy AMCR 003 is also shown for comparison.

Table 1. Composition of phase IV solute-modified Fe-Cr-Mn alloys (wt.%)

	Mn	Cr	C	N	V	P	B	Al	W	Ni	Si
X-75	30	2.0	0.10	0.15	-	-	-	-	-	0.5	0.4
R76	30	2.0	0.60	0.05	-	0.05	0.005	-	-	0.5	0.4
R77	30	2.0	0.40	0.15	1.0	0.05	0.005	-	1.0	0.5	0.4
R78	30	5.0	0.05	0.15	-	-	-	-	-	0.5	0.4
R79	30	10	0.05	0.10	-	-	-	-	-	0.5	0.4
R80	30	10	0.50	0.10	2.0	-	0.005	1.0	2.0	0.5	0.4
R81	20	15	0.05	0.10	-	-	-	-	-	0.5	0.4
R82	15	5	0.40	0.10	-	-	-	-	-	0.5	0.4
R83	15	5	0.60	0.05	-	0.05	0.005	-	-	0.5	1.0
R84	15	5	0.70	0.10	2.0	-	-	1.0	-	0.5	0.4
R85	15	15	0.05	0.15	-	-	-	-	-	0.5	0.4
R86	15	15	0.10	0.35	-	-	-	-	-	0.5	0.4
R87	15	15	0.10	0.10	-	0.05	0.005	-	-	0.5	1.0
R88	15	15	0.30	0.30	2.0	0.05	0.005	-	2.0	0.5	0.4
R89	15	15	0.50	0.10	2.0	-	-	1.0	2.0	0.5	0.4

Table 2. Composition of commercial Fe-Cr-Mn austenitic alloys

Designation	Vendor	Composition (wt.%)
NITRONIC ALLOY 32	ARMCO	18Cr-12Mn-1.5Ni-0.6Si-0.2Cu-0.2Mo-0.4N-0.1C-0.02P
18/18 PLUS	CARTECH	18Cr-18Mn-0.5Ni-0.6Si-1.0Cu-1.1Mo-0.4N-0.1C-0.02P
AMCR 0033	CREUSOT-MARREL	10Cr-18Mn-0.7Ni-0.6Si-0.06N-0.2C
NMF3	CREUSOT-MARREL	4Cr-19Mn-0.2Ni-0.7Si-0.09N-0.02P-0.6C
NONMAG 30	KOBE	2Cr-14Mn-2.0Ni-0.3Si-0.02N-0.02P-0.6C

Results

Fig. 3 shows that the tendency toward saturation in simple ternary Fe-Cr-Mn alloys occurs even faster at 420°C than it does at 520°C. Fig. 4 shows the swelling of solute-modified alloys in the 15% manganese range compared to that of the simple ternary alloys on which they are based. At this point it is not possible to separate the various factors which control the swelling, but one can see that aging after cold-working appears to increase the swelling and that varying the levels of various solutes also influences the swelling.

Fig. 5 shows that at 30% manganese the addition of solute can also have a pronounced effect on swelling. Note in Fig. 5b that cold-working of Fe-10Cr-30Mn after addition of 0.05C, 0.1N, 0.5Ni and 0.45Si causes a substantial reduction of swelling in alloy R79. An even greater reduction is realized in Alloy R80 by increasing the carbon level to 0.5% and by adding precipitate-forming elements such as tungsten, vanadium and aluminum.

In both Figs. 4 and 5 the tendency toward saturation is seen to be enhanced relative to that of the base ternary alloys. A similar behavior is observed in the commercial alloys as shown in Table 3. In general, the commercial alloys tend not to swell at 9-14 dpa, and most of them actually densify, as shown in Table 3. At ~50 dpa and 520°C, most of these alloys have begun to swell, however. It appears that the annealed and aged condition of commercial alloys is the most vulnerable to the earliest onset of swelling.

Discussion

The discussion of these results will be deferred until more density change data are available and microscopy has been performed to provide insight on the relative contribution of voidage and phase-related strains.

FUTURE WORK

The accumulation of density change and microscopy data will continue.

Table 3 Swelling of commercial alloys

Alloy	Condition	Swelling, %			
		9dpa, 420°C	14dpa, 520°C	14dpa, 600°C	49.8dpa, 520°C
Nitronic 32	CW*	-0.11	-0.02	-0.19	3.5
18/18 Plus	CW	-0.10	-0.28	-0.56	2.2
18/8 Plus	CWA+	-0.05	---	-0.07	---
AMCR 0033	CW	0.42	0.62	---	1.9
AMCR 0033	CWA	-0.24	-0.02	-0.02	2.5
AMCR 0033	SAA ^x	0.03	0.61	0.22	4.4
NMF3	CW	-0.24	-0.23	---	0.1
NONMAG 30	SAA	0.07	0.17	-0.42	2.87
NONMAG 30	CW	0.42	0.62	---	1.0
NONMAG 30	CWA	-0.24	-0.02	0.20	0.42

*CW = 1030°C/0.5 hr/air cool + 20% cold-work

+CWA = cold-worked condition + 650°C/1 hr/air cool

^xSAA = 1030°C/1 hr/air cool + 760°C/2 hr/air cool

Fig. 3. Comparison of swelling of two simple Fe-Cr-Mn alloys at 420°C and 520°C.

HEDL 8606-097.5

Fig. 4. Swelling of both simple and solute-modified alloys with 15% manganese at ~50 dpa and 520°C. See Table 1 for definition of alloys codes and conditions.

Fig. 5. Swelling of both simple and solute-modified alloys with 30% manganese at ~50 dpa and 520°C. With the exception of R78 all solute-modified alloys in Fig. 5b have 2% chromium; R78 has 5% chromium.

REFERENCES

1. H. R. Brager and F. A. Garner, "Swelling of Fe-Cr-Mn Ternary Alloys in FFTF," pp. 41-43 in Damage Analysis and Fundamental Studies Quarterly Progress Report, DOE/ER-0046/19, U.S. Department of Energy, Office of Fusion Energy, November 1984.
2. F. A. Garner and H. R. Brager, "Neutron-Induced Swelling of Fe-Cr-Mn Ternary Alloys," pp. 41-45 in Damage Analysis and Fundamental Studies Quarterly Progress Report, DOE/ER-0046/21, U.S. Department of Energy, Office of Fusion Energy, May 1985.
3. F. A. Garner and H. R. Brager, "Neutron-Induced Swelling and Microstructural Development of Simple Fe-Mn and Fe-Cr-Mn Alloys in FFTF," pp. 18-23 in Damage Analysis and Fundamental Studies Quarterly Progress Report, DOE/ER-0046/23, U.S. Department of Energy, Office of Fusion Energy, November 1985.
4. F. A. Garner, D. S. Gelles, H. R. Brager and J. M. McCarthy, "Phase Development and Swelling in Fe-Mn and Fe-Cr-Mn alloys During Neutron Irradiation," pp. 22-29 in Damage Analysis and Fundamental Studies Quarterly Progress Report, DOE/ER-0046/24, U.S. Department of Energy, Office of Fusion Energy, February 1986.
5. F. A. Garner and H. R. Brager, "Swelling of Fe-Mn and Fe-Cr-Mn Alloys at High Neutron Fluences," pp. 28-30 in Damage Analysis and Fundamental Studies Quarterly Progress Report DOE/ER-0046/25, U.S. Department of Energy, Office of Fusion Energy, May 1986.
6. F. A. Garner, J. Nucl. Mater., 122/123, 459-471 (1984).