2

Characterization of Multiphase Fluid Flow During Air-Sparged Hydrocyclone Flotation by X-Ray CT

DOE/PC/90311--8

DE93 000920

Eighth Quarterly Report
14 May 1992 - 13 August 1992

DOE Contract No. DE-FG22-90PC90311

Submitted By : J.D. Miller
Professor of Metallurgical Engineering
216 WBB
University of Utah
Salt Lake City, Utah 84112
(801)-581-5160

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

OCT 07 1992

August 17, 1992

MASTER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

REPORT FOR EIGHTH QUARTER

14 May -- 13 August

During this quarter of the DOE project, "Characterization of Multiphase Fluid Flow During Air-sparged Hydrocyclone Flotation" the effect of A^* (the dimensionless ratio of overflow opening area to underflow opening area) on the fluid flow behavior of the 2" ASH-2C unit was studied for different percentage of solids in the suspension. Limestone, a hydrophilic solid was chosen for study. The particle size of the solids was taken as -100 +200 mesh. Three different concentrations of solids in the suspension were considered, 5, 10 and 20 % by weight. The corresponding pulp densities of the feed suspension for these three cases are 1.09, 1.18 and 1.36 g/cc respectively. Since no collector was added to the suspension, all the solids are expected to report to the underflow. For all these studies the Q^* value was maintained at the same level ($Q^* = 2.28$).

Reconstructed images from the CT scanner were analyzed using the graphics software developed at the University of Utah. Assuming the air core to be cylindrical in shape and using the previously generated calibration curve, the average density of the swirl layer and its average thickness were estimated for each slice. These results are presented graphically in the accompanying figures along the axis of the ASH unit from bottom to top.

Figure 1 shows that for 5 and 10 % solids, the average density of the swirl layer increases slightly for all three A^* values considered (1.00, 0.85 and 0.74), as one goes from bottom to top of the ASH unit. This behavior is due to the fact that a higher

centrifugal force at the top keeps the suspension at a relatively more compressed state than at the bottom. However, at 20 % solids in the suspension there appears to be a choking effect near the underflow for higher values of A^* (1.00 and 0.85) and the previously observed trend for low percent solids is reversed. Solids discharge from the underflow is impeded and a high suspension density is observed. For a low A^* value ($A^* = 0.74$) the average density remains more or less constant along the axis.

Examination of Figure 2 reveals that for higher A^* values (1.00 and 0.85) with 20 % solids the swirl layer thickness is much thicker at the bottom. This corroborates the fact that choking of the underflow opening area occurred. For a low A^* value ($A^* = 0.74$), the swirl layer thicknesses are comparable for all solids percentages. Also the swirl layer thickness is quite uniform from top to bottom. It increases slightly near the bottom because of the weaker centrifugal force field. Figure 2 suggests an upper limit of percentage solids that can be used without choking for a particular value of A^* .

During the next quarter, the effect of Q^* on the density profile and the flow pattern of the ASH will be reported for the same percent of solids in the suspension. Further, it is intended to modify the software such that it would not be necessary to assume the air core to be cylindrical in shape. Any offset of the center of the air core from the axis of the ASH will be taken into account. Efforts will be made to improve upon the software such that the radial density profile at any particular elevation in the ASH can be determined.

Figure 1 : Variation of the average density at a given position along the axis of the ASH with percent solids for different A^* values.

Figure 2 : Variation of swirl layer thickness along the axis of the ASH with percent solids for different A^* values.

**DATE
FILMED**
12/21/92