SEP 25 1992

**EFFECT OF HEAVY METALS ON THE IRON OXIDIZING ABILITY OF
Thiobacillus ferrooxidans. PART 1. EFFECT OF SILVER.**

Gopal C. De and Batric Pesic

Department of Mining and Metallurgical Engineering
College of Mines and Earth Resources
University of Idaho
Moscow, Idaho 83843

DOE/PC/88920--T24

Abstract

DE93 004939

The effect of silver ions on the iron oxidizing ability of Thiobacillus ferrooxidans was studied using electrochemical and other physico-chemical techniques. Electrochemical investigation was conducted using a method based on redox potential change. Experiments were performed by adding an aliquot of separately prepared concentrate of the bacteria into the solution of ferrous ion and monitoring the redox potential for at least one hour. Pyrite was used as the indicator electrode. Parameters examined were pH, microbial cell density, ferrous, ferric and silver ion concentration, temperature and pre-conditioning period of the bacteria with silver ions, etc.

Results obtained demonstrate that the rate of ferrous ion oxidation is dependent on pH (optimum pH range is 1.5-2.0) and the substrate (i.e. Fe(II)) to microbial cell concentration ratio. The mechanism of the bacteria mediated oxidation of ferrous iron is remarkably sensitive to temperature changes. At the vicinity of the optimum temperature (i.e. 25°C), the reaction is likely to be controlled by the diffusion of Fe(II) ions through the cell wall of the bacteria, whereas below the range 18-25°C, reaction kinetics may be the rate controlling factor. In the presence of 10 mg/L silver, the reaction may be kinetically controlled over the temperature range 5.5-25°C. Inhibition of microbial Fe(II) oxidation in the presence of silver may take place via a mixed mechanism in which silver may bind with both the enzyme and the enzyme-substrate complex.

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

INTRODUCTION

Because of its great technological potential, bio-leaching involving Thiobacillus ferrooxidans and other autotrophic bacteria has received much attention (1, 2) over the past few decades. For example, microbial oxidation has already been observed to be useful for liberating precious metals, especially gold, locked in the refractory sulfide matrix, and thereby rendering the cyanidation in heap leaching possible (3). Reportedly (3, 4), bio-leaching is also applicable for dump leaching of low grade refractory copper ores such as CuFeS_2 . Recently (5-8), active consideration is given to use bio-leaching for the removal of pyritic sulfur from coal and

help control environmental pollution (i.e. acid rain caused by SO_2 emission from coal power plants).

An evaluation of the literature reports reveals that the role of T. ferrooxidans in bio-leaching of mixed metal sulfides is to catalyze the oxidation of iron sulfide(s) to Fe(III) sulfate. However, previous work do not specify which component of the microbial cell plays key role in bio-leaching. Earlier reports (9, 10) have cited that a type c cytochrome may be responsible for the transport of electrons from Fe(II) to oxygen, while a more recent communication (11) has mentioned that a 92K glycoprotein may be the most important component of the Fe(II) oxidizing system of the T. ferrooxidans. While there is a lack of agreement regarding the identity of the microbial enzyme effective for Fe(II) (or sulfur) oxidation, two alternative mechanisms are suggested for the microbial leaching of metal sulfides. According to the direct mechanism, a physical contact between the bacteria and the sulfide mineral surface is required (12). In the indirect mechanism, the bacteria generated Fe(III) acts as a lixiviant for the solubilization of metals from the mineral (3, 4). In actual fact, however, both of the mechanisms may operate simultaneously in a complementary manner.

An important side effect of bio-leaching may be co-dissolution of other heavy metal ions, which, if accumulated to a certain

level, may influence the activity of the T. ferrooxidans cells. In a more drastic case, the heavy metals may kill the bacteria and thus stop bio-leaching. On the other hand, some heavy metal may exert an inhibitory effect on bio-leaching by deactivating bacteria, the living catalysts. The deactivation process may involve blocking or damaging of a significant fraction of the active sites on the microbial enzyme(s) by heavy metal ions. In another possible deactivation process, the presence of a particular heavy metal may enhance the formation of toxic species from dissolved oxygen e.g. $O_2^{\cdot -}$. Oxygen toxicity through the superoxide (i.e. $O_2^{\cdot -}$) formed in the biological systems is already known in the literature (13).

Tuovinen and Kelly (14), have studied the effect of UO_2^{2+} on the iron oxidation by Thiobacillus ferrooxidans. It was found that the presence of UO_2^{2+} species partially inhibited the oxidizing activity of the bacteria by blocking the cell active sites. Addition of a complexing agent like EDTA, or a non-toxic cation (e.g. Mg^{2+}), reduces the inhibitory action due to uranyl cation. Imai et al (9) found that mercuric and mercurous ions are even more toxic than uranyl or any other heavy metal ions studied, e.g. lead, arsenic, zinc, molybdenum, copper, cadmium etc. The observed variation in toxicity of heavy metals might have resulted from differences in the modes of interactions between the cell enzyme(s) and various heavy metals ions. On the basis of the above information it is likely that UO_2^{2+} may be physically sorbed onto the cell so that it can be exchanged with a divalent cation such as Mg^{2+} . On the other hand, $Hg(II)$ may directly interact with the iron oxidizing system of T. ferrooxidans cells (9). Thus, formation of a chemical bond with the iron oxidase or combination with the enzyme-substrate complex may take place when mercury is present in the system.

Silver, another heavy metal, is often cited as toxic to the T. ferrooxidans (9, 15-18). For example, previous workers (16, 17) have reported that in an aqueous $FeSO_4$ solution of low pH, growth of the T. ferrooxidans is decreased and their ferrous iron

oxidizing ability lost to a significant extent by the presence of approximately 0.10 mg/L Ag^+ . However, if a metal sulfide e.g. CuFeS_2 , is used in the solid form as the bacteria's sole nutrient, then the presence of a significant quantity of silver may not cause any harm to the metal sulfide bio-leaching activity of the bacteria (19-21). In deed, bio-leaching of CuFeS_2 is observed to be enhanced at pH 1.25 in the presence of 30 mg/L Ag^+ (21). The positive catalytic effect of silver ions is explainable (19, 21, 22) in terms of the formation of Ag_2S which is thermodynamically more stable than CuFeS_2 . Ag^+ being a small cation is able to diffuse into CuFeS_2 crystal to take part in the following surface reaction:

Fe(III) may regenerate Ag^+ in accordance with the following surface reaction (22):

In the light of the literature reports mentioned above, it is conceivable that the apparent dual role of silver in the ferrous iron oxidizing ability of T. ferrooxidans is due to differing experimental conditions. Consequently, it was decided to study the effect of silver ions on the iron oxidizing activity of the T. ferrooxidans by extending the experimental parameters beyond those considered in the earlier investigations. The effect of some other heavy metal ions including Hg^{2+} on the iron oxidizing ability of the T. ferrooxidans will be reported in a subsequent publication.

EXPERIMENTAL

Materials and equipment

The equipment and the method of growing T. ferrooxidans (strain ATCC 13598) are reported in reference 23. Only reagent grade chemicals were used.

Procedure

(a) Experiments without heavy metals

Deionized water, 250 mL, of a desired pH was transferred into the bio-reactor to which 25 μL of 1M $\text{Fe}_2(\text{SO}_4)_3$ and 250 μL of 1M FeSO_4 were added. The biooxidation of Fe(II) was initiated by the addition of 2 mL of concentrated T. ferrooxidans cells. The chemical activity of the bacteria was monitored by measuring the redox potential (vs SCE) of the solution. A specially built pyrite electrode served as the indicator electrode.

(b) Experiments with heavy metals

The experimental procedure was similar to the preceding section except that a desired concentration of a heavy metal (e.g. silver) was added before the addition of bacteria to the system.

To study the effect of conditioning the bacteria with silver, 2 mL of concentrated bacteria was added to a solution (250 mL) silver (1-10 mg/L). When the conditioning period, 5-120 minutes, was completed, requisite amounts of ferrous and ferric iron (to make 0.001M and 0.0001M respectively in a 250 mL reactor) were added and redox potential monitoring started.

Standard experimental conditions

The iron oxidizing activity of the Thiobacillus ferrooxidans has been studied under a variety of experimental conditions. The standard conditions are:

pH	1.7
temperature	25°C
concentration of Fe(II)	0.001M
concentration of Fe(III)	0.0001M
<u>T. ferrooxidans</u> cells	2mL
microbial cell density	2.80
(c.f. OD_{590} measurements)	
no heavy metal ions present	

Two parallel sets of experiments were conducted, one with and the other without a heavy metal, to demonstrate the effect of a heavy metal (e.g. silver) on the activity of the T. ferrooxidans.

RESULTS AND DISCUSSION

Results of experiments without heavy metals

Effect of pH

The effect of pH on the redox potential change as a function of time is shown in Fig. 1. The family of potential versus time curves represented by Fig. 1 satisfy the Nernst equation with the standard potential of 0.4324V and slope of 0.055V (equation 1). According to the Nernst equation (23),

$$E = 0.4324 + 0.055 \log\{[\text{Fe(III)}]/[\text{Fe(II)}]\} \quad (1)$$

an increase in electrode potential results from an increase in the ferric iron activity, which is caused by the oxidation of Fe(II) by T. ferrooxidans. The Nernst equation can be used to calculate the rate constant of reaction (23). The results presented in Table 1 suggest that Fe(II) oxidizing activity of the bacteria is significantly influenced by the solution pH. The T. ferrooxidans cells are most active in the pH range 1.5-2.0.

Table 1

Effect of pH on the observed rate constant
of the microbial oxidation of ferrous iron.

pH	Rate constant (min ⁻¹)
1.2	0.0270
1.4	0.0520
1.5	0.0570
1.7	0.0600
1.9	0.0610
2.0	0.0590
2.1	0.0500
2.5	0.0350
3.0	0.0150
3.5	0.0050

Effect of cell concentration

T. ferrooxidans absorb visible light at 590nm (12). This property was utilized to establish a correlation between the reaction rate constant and the cell concentration of T. ferrooxidans. At first, optical densities of the bacterial cells of various concentrations at 590 nm (i.e. OD_{590} s) were measured. Subsequently, the corresponding concentrations of the bacteria were used in ferrous iron oxidation experiments (under standard conditions mentioned above) to determine the rate constants from the measured change of redox potential with time (23). According to the results represented by Fig. 2, the Fe(II) oxidation with T. ferrooxidans is first order with respect to the concentration of the bacteria upto $OD_{590}=2.82$.

Effect of Fe(II) concentration

Three series of experiments were performed with T. ferrooxidans cell concentrations given by $OD_{590}=1.41$, 2.8 and 5.85. In each series of experiments, parameters other than Fe(II) concentration were maintained constant. The results are represented by the curves with closed symbols in Fig. 3. In general, it is observed (Fig. 3) that the rate constant versus concentration of Fe(II) curves shift towards right as the microbial cell density is increased from $OD_{590}=1.41$ to $OD_{590}=5.85$. This happens because the reaction under study requires an optimum substrate i.e. Fe(II) to bacterial cell ratio. If the substrate concentration is lower than optimum, then the substrate concentration will be a limiting factor for the reaction rate. As a result, the rate constant will be lower than what it would be if optimum substrate to cell ratio is used. However, if more substrate is present in the system than optimum, then the reaction will be cell limited. Under this condition, more Fe(II) species will be available to compete for the active sites on the microbial enzyme. Competition among the Fe(II) ions for the active sites on the enzyme will intensify with increasing Fe(II) concentration in the system. This, in turn, may lead to a reduction in the average duration of attachment of a particular Fe(II) ion to

the bacterial enzyme. Consequently, a situation may arise in which only a fraction of the Fe(II) species present in the system will be in direct contact with the microbial enzyme for the time span required to generate enzyme-substrate complex. As an immediate effect, the concentration of enzyme-substrate complex will decrease resulting in a decline in the reaction rate. Reduction of reaction rate in this manner is termed as competitive inhibition by Fe(II) and is well known in the literature (24).

Our results discussed above suggest that for maximum ferrous iron oxidizing activity of the bacteria, the ratio of concentrations of the microbial cell and ferrous ions must be optimized. According to our findings, if 2 mL of T. ferrooxidans cells of $OD_{590}=1.41$ are used in a reactor volume of 250 mL, then the optimum concentration of Fe(II) may be 0.0005M approximately. On counting the bacteria by fluorescence microscopy (25) we have found that 2 mL bacteria of $OD_{590}=1.41$ corresponds to approximately 7.72×10^{10} cells of the T. ferrooxidans in our reactor. If the number of cells in the reactor is increased to 15.44×10^{10} and 32.26×10^{10} (corresponding to $OD_{590}=2.8$ and 5.85), the optimum Fe(II) concentration will be 0.001M and 0.002M respectively. The rate constant under optimum conditions is observed to be 0.06 min^{-1} and corresponds to the maximum point on the curves represented by closed squares or circles in Fig. 3. The portion of each curve right to the maximum point represents the inhibitory range and is attributable to competitive inhibition by Fe(II) species (24). According to previous workers (24), another simultaneous effect i.e. product inhibition due to Fe(III) may also occur. In our study, product inhibition by Fe(III) was confirmed by performing additional experiments using Fe(III) concentration in the range 0.000-0.0005M, while keeping other parameters unchanged, and observing a decrease in the rate constant with an increase in Fe(III) concentration (Fig. 4).

The left side of the curves in Fig. 3 (closed symbols) corresponds to substrate i.e. Fe(II) limitations and is called the stimulation region. The stimulation region of the curve represented

by the closed squares was used for the Lineweaver-Burk analysis (Fig. 5) and direct plot analysis (Fig. 6). Both analyses show that the maximum possible value of the 1st order rate constant should be 0.069 min^{-1} under the conditions used in our work. These analyses also suggest that the Fe(II) concentration corresponding to the half-maximal rate constant (i.e. K_m) is 0.000154M approximately. These results could not be compared with those of the other researchers because no other study was conducted in a similar way.

In order to annul the effect of Fe(III) in our work, an initial kinetic study was performed using Fe(II) concentration in the range 0.0005M - 0.00125M and the microbial cell density given by $\text{OD}_{590} = 2.80$, with other conditions unchanged. The initial rate of Fe(II) oxidation vs Fe(II) concentration plot is shown in Fig. 7. Based on the data represented by Fig. 7, a Lineweaver-Burk plot was obtained as shown in Fig. 8. This plot corresponds to an average K_m value of 0.0018M . According to previous reports (26-28), K_m is in the range 0.001 - 0.01M . Thus our result is consistent with previous findings. Fig. 8 also suggests that the maximum possible reaction rate, V_m , is 0.00007 - $0.00011 \text{ mol/L/min}$ (corresponding to the line with closed triangles and closed squares respectively).

Effect of temperature

Two series experiments were conducted to demonstrate the variation of the 1st order rate constant of microbial oxidation of Fe(II) with temperature. The results of one series is shown in Table 2. It is observed from Table 2 that the 1st order rate constant of the oxidation of Fe(II) in presence of T. ferrooxidans increases as the temperature is increased from 5.5 to 25°C , beyond which it decreases to some extent. Thus, 25°C is the optimum temperature for the reaction being investigated.

Table 2

Effect of temperature on the rate constant of the bacterial oxidation of ferrous iron.

Temperature (°C)	Rate constant (min ⁻¹)	
	No silver	10 ppm silver
5.5	0.0120	0.0060
10	0.0220	0.0100
15	0.0450	0.0140
21	0.0500	0.0180
25	0.0600	0.0285
30	0.0510	0.0100
35	0.0500	0.0090

Arrhenius plots, generated using the data points from Table 2 are shown in Fig. 9. From the plot, activation energy of microbial oxidation of Fe(II) in the absence of any heavy metal is observed to be 11.51 Kcal mole⁻¹ in the temperature range 5.5-25°C. It may be noted that this value of activation energy is much lower (e.g. <5 Kcal/mol) in the range 18-25°C. The dependance of activation energy on temperature range has been reported earlier (29) for biotic systems involving T. ferrooxidans.

Results of experiments involving heavy metal ions

Effect of silver ion concentration

Effect of concentration of silver ion on the oxidation of Fe(II) at pH 1.7 has been demonstrated in Fig. 10. It is observed that the electrode potential versus time plots representing various concentrations of silver (1 mg/L and above) are all below that corresponding to no silver (or <1 mg/L silver). This indicates that silver ions in the range 1-10 mg/L adversely affect the bacteria's iron oxidizing activity. The results also suggest that a silver concentration of around 0.5 mg/L is not adverse to the bacteria's Fe(II) oxidizing activity at pH 1.7. This may indicate that the bacteria are able to tolerate certain concentration of silver. This view is supported by the results of additional experiments

conducted at pH=1.4 and 3.0 described below.

Computation of the rate constant and subsequent plot against silver ion concentration (Fig. 11) shows more clearly that the rate of Fe(II) oxidation catalyzed by T. ferrooxidans is maintainable upto a threshold value of silver concentration, beyond which the rate decays. According to Fig. 11, the threshold value of silver concentration is pH dependent. For instance, at pH 1.7, the maximum concentration of silver that causes no harm to the microbial Fe(II) oxidation is approximately 0.7 mg/L. On the other hand, at pH 1.4, the maximum value of silver concentration tolerable in the bacterial oxidation of Fe(II) approaches towards 0.25 mg/L. At pH 3.0, the effect of silver is not so pronounced, because, at this pH the bacteria's activity is very low even without silver. Thus, our results suggests that the effect of silver on the microbial oxidation of Fe(II) is concentration dependent. While a small concentration of silver in the system may be tolerable, an appreciable concentration of silver (0.25 mg/L or above depending on pH) is detrimental to the bacterial oxidation of ferrous iron in solution.

Effect of Fe(II) concentration in the presence of silver

It is observable from the rate constant versus Fe(II) concentration plots corresponding to the open symbols in Fig. 3 that the curves representing microbial Fe(II) oxidation in the presence of silver shift towards left as the cell density of the bacteria is decreased from $OD_{590}=5.85$ to 1.41. It is explainable in terms of the fact that silver ions may deactivate a portion of the microbial enzymes. As a result, the proportion of the cells effective for Fe(II) oxidation is reduced when 10 mg/L Ag^+ is present in the system. However, since the silver concentration is fixed, it may deactivate a fixed number of cells from each of the three microbial cell concentrations studied. Consequently, the effective number of cells in our work should follow the sequence

$$OD_{590}=1.41 < OD_{590}=2.80 < OD_{590}=5.85.$$

A reduction in the effective number of cells would mean that a lower concentration of Fe(II) would be necessary to optimize the Fe(II) to cell ratio. It is for this reason that the rate constant versus Fe(II) concentration curves symbolized by open symbols in Fig. 3 should shift towards left as in cell density of the bacteria is decreased.

Fig. 7 suggests that the initial rate of oxidation of ferrous iron is reduced in the presence of 10 mg/L silver. Lineweaver-Burk analysis of the data represented by Fig. 7 (correspond to the lines with open symbols in Fig. 8) shows that the average value of K_m increases to 0.0024M approximately whereas the V_m value is reduced to 0.000059-0.000096 mol/L/min due to the presence of 10 mg/L Ag^+ in our system.

Effect of temperature in the presence of silver

If the T. ferrooxidans cells are exposed to 10 mg/L silver and concurrently, the reaction temperature is varied from the optimum value of 25°C, then the rate of microbial oxidation of ferrous iron may decrease remarkably. This is depicted by the data shown in Table 2. For instance, at 25°C and in the presence of 10 mg/L silver, the observed rate constant of reaction is 0.0285 min⁻¹. In presence of 10 ppm silver, if the reaction temperature is varied from 25 to 5.5 and 35°C, the rate constant is observed to be lowered to 0.006 and 0.009 min⁻¹ respectively.

Arrheniuss plots (Fig. 9) obtained on the basis of the data from Table 2 yields an activation energy of 12.33 Kcal mole⁻¹ for experiments involving 10 ppm silver.

Oxidation of Fe(II) with bacteria conditioned with silver

Effect of time

These experiments were performed to examine the effect of conditioning the bacteria with silver for different amount of time. The effect of conditioning period of the T. ferrooxidans with 10 mg/L silver on the observed electrode potential is shown in Fig.

12. It is noticeable that the curves corresponding to different periods of initial contact of the T. ferrooxidans with silver are well below that representing no conditioning of the bacteria. This observation suggests that a pre-contact with soluble silver remarkably reduces the bacteria's iron oxidizing activity. This effect becomes more pronounced as the duration of conditioning is increased from 0 to 2 hours (Fig. 12). This observation may be explained in terms of the fact that as the duration of pre-conditioning increases, an increasing number of Ag^+ ions may diffuse into the periplasmic space to preoccupy the active sites on the microbial enzyme leading to deactivation of the enzyme(s).

The effect of conditioning period of the bacteria with silver on the rate constant of Fe(II) oxidation is represented by Fig. 13, which shows that the rate constant decreases as the duration of conditioning the bacteria with 10 mg/L silver is increased. The effect of conditioning time also depends on the concentration of silver. For example, after 30 minutes' conditioning with 1, 2.5 and 10 mg/L silver, the activity of the bacteria expressed as the rate constant of Fe(II) oxidation was 0.0485, 0.0415 and 0.017 min^{-1} , respectively (Fig. 13).

Effect of pH

Fig. 14 compares the effect of pH on the rate constant of the microbial oxidation of ferrous iron in the absence and in the presence of silver. The top curve of this figure represents the ferrous iron oxidizing activity of the bacteria in the test solutions of differing pH in the absence of silver. The middle curve corresponds to the iron oxidizing activity of the bacteria in the presence of 10 ppm silver in solutions of various pH, while the bottom one demonstrates the activity of the bacteria conditioned for 1 hour with 10 mg/L silver in solutions of different pH. A comparison of the top curve with the other two curves suggests that the presence of 10mg/L silver in the system and conditioning the bacteria with 10mg/L silver for 1 hour are detrimental to microbial oxidation of Fe(II). For example, at pH 1.7 and in absence of

silver, the rate constant of bacterial oxidation of ferrous iron is 0.06 min^{-1} . In presence of 10 mg/L silver (without conditioning), this value is reduced to 0.0285 min^{-1} . When the bacteria are conditioned with 10 mg/L silver for a period of 1 hour, the rate of bacterial oxidation of Fe(II) is further lowered to 0.012 min^{-1} .

Fig. 14 also shows that change of pH beyond 1.5-2.0 has a negative effect on the activity of the bacteria the absence of silver. However, because of severe loss in microbial activity, due to the presence of silver, and conditioning with silver, the pH effect becomes less pronounced in experiments with silver. Consequently, the portion of the rate constant versus pH curve at the vicinity of peak (refers to the top curve in Fig. 14) spreads over a wider pH range with an attendant decrease in activity of the bacteria, if 10 mg/L silver is present in the system. It becomes even wider and shows further loss of bacterial activity when the bacteria are conditioned with 10 mg/L silver for 1 hour. Thus, according to Fig. 14, factors adversely affecting the activity of the T. ferrooxidans may be arranged in the following sequence:

Conditioning with Ag^+ > presence of Ag^+ > pH changes.

Mechanism of inhibition by silver ions

Lineweaver-Burk analysis has been used in our work to uncover the mechanism of inhibition of microbial Fe(II) oxidation in the presence of silver ions. This method has a general applicability for elucidating the inhibition mechanism of the enzyme catalyzed reactions (30). following this method (30), two parallel series of experiments were performed using different concentrations of the substrate (i.e. Fe(II)) and keeping other experimental parameters (e.g. pH, temperature, microbial cell density) constant. In one of the two series of experiments, a constant concentration of the inhibitor (i.e. 10 mg/L Ag^+) was used. Then, the reciprocal of the observed initial rate of reaction was plotted as a function of the reciprocal of initial Fe(II) concentration to obtain two straight lines. Finally, comparing the intercepts of the straight lines on X and Y axes in uninhibited and inhibited case, the mechanism of

inhibition was ascertained. For a typical mixed inhibitor, the Y-intercept increases whereas the X-intercept decreases relative to uninhibited case (30). Reportedly (30) a mixed inhibitor (I) in enzyme kinetics is to combine with both the enzyme (E) and the enzyme-substrate complex (ES) according to the following scheme:

A comparison of the straight lines symbolized by closed squares and closed triangles in Fig. 8, it is observable that due to inhibition by silver ions, the X-intercept has decreased from 579.61 (uninhibited value) to 473.98, while the Y-intercept has increased from 8991.86 (uninhibited value) to 10368.80. Similar trend is observed for the other pair of straight lines symbolized by open symbols. On the basis of the lessons from enzyme kinetics, it may be suggested that inhibition of microbial oxidation of Fe(II) by Ag^+ takes place via a mixed mechanism mentioned above. Since, according to the above scheme, silver ions may block the active site on the enzyme as well as combine with the enzyme-substrate complex, it is likely that in the presence of silver ions, Fe(II) oxidation may not be dependent on the diffusion of Fe(II) ions through cell wall. On the contrary, it may depend on the concentration of enzyme-Fe(II) complex which, avoiding combination with silver ions, can produce Fe(III). The observed activation energy value of $12.33 \text{ Kcalmol}^{-1}$ in the presence of 10 mg/L Ag^+ suggests that the rate of Fe(III) formation is slower (i.e. rate determining) than the rate of Fe(II) diffusion into the periplasmic space of the bacteria.

It may be noted that the proposed mechanism requires a direct contact between the microbial cells and silver ions. Evidences in support of direct interaction between the microbes and Ag^+ are

obtainable from experiments designed to follow the bulk concentration of silver (e.g. using atomic absorption (AA) spectroscopy) and by microscopic examination of cells treated with silver. In our AA work, an experiment was performed with T. ferrooxidans cells, 2.5 mg/L Ag⁺ and other standard conditions. Two samples were withdrawn, one at the beginning (i.e. head) and the other at the end of experiment (i.e. tail). The bacteria were separated from the samples by filtration through Millipore filters (pore size 0.25 micron) and the filtrate analyzed for silver using flame AA at 328.1 nm. Typical results (Table 3) showed a slight decline in the bulk concentration of silver attributable to accumulation of Ag⁺ by

Table 3

Results of AA analysis of samples taken from experiments to diagnose the fate of silver

Sample	Time (min)	Absorbance due to Ag	Ag concentration (mg/L)
Head	0	0.257	2.7
Tail	90	0.237	2.4

T.ferrooxidans cells. In deed, silver accumulation onto bacteria has been confirmed by electron microscopic examination (using SEM and TEM) of cells treated with silver, as mentioned below.

For electron microscopic studies, experiments were performed in a similar way and samples were taken from ongoing experiments with 2.5 mg/L silver and without silver (i.e. control). The bacteria were filtered onto Millipore filters specified above, washed with pH 1.7 deionized water for three times and then examined by SEM. The SEM micrographs are shown in Fig. 15. It is observable that both of the micrographs are similar to look at. However, EDAX analysis reveal the presence of little silver on T. ferrooxidans cells withdrawn from the experiment with 2.5 mg/L

silver (refers to Fig. 15a). As expected, no silver was detected on the bacteria taken from the control experiment (refers to Fig. 15b). This observation suggests that silver ions bind to the bacterial cells.

Further studies using TEM on samples prepared in a similar manner, have identified spots on the cells which correspond to accumulation of both metallic and nonmetallic species. For example, micrographs of bacteria taken from control experiments, as shown in Fig. 16a, contain lighter spots corresponding to the presence of Fe, Ca, K, Si, P and S (Fig. 17a). It may be mentioned that Cu and Si observed in this figure have come from the support grid made of Cu and si- grease used in the TEM work. The other cations and P might have come from the nutrient medium salt solution used during fermentation of the bacteria. S is likely to be from SO_4^{2-} . Photomicrograph of the bacteria taken from an experiment involving 2.5 mg/L silver ions are observed to contain both lighter as well as darker spots as shown in Figs. 16b and c. EDAX analysis reveal that the darker spots are due to accumulation of Ag onto the cell (Fig. 17b). Thus, our SEM and TEM work confirm that there is a direct interaction between silver ions and T. ferrooxidans cells, as required by the proposed mechanism of inhibition of bacterial activity by Ag^+ ions. Although our observation of silver deposition onto the cells agrees well with the previous reports of accumulation of silver onto T. ferrooxidans cells during leaching of sulfide minerals (31, 32), the current study is not able to specify the actual site on the microbial cell at which silver accumulates. However, based on our results and earlier observations, we may make an educated guess as to the identity of the silver-binding sites on the bacterial cell. Previously (32, 33), silver was observed to be complexed by the -SH group of aminoacids like cystein. In accordance with a recent report (34), Ag^+ is often separated from the waste water with ion-exchangers containing -SH as the terminal group. These observations (32-34) and other reports (19, 21, 22) may be taken as to indicate that silver has a great affinity for sulfur. Since T. ferrooxidans

cells are known (35) to possess sulfur containing proteins (e.g. cystein), it may be suggested that the thiol (i.e. -SH) terminal groups of those proteins may act as potential sites for binding Ag^+ ions.

CONCLUSIONS

Microbial oxidation of ferrous iron by T. ferrooxidans was studied using a variety of experimental conditions, e. g. solution pH, temperature, concentrations of bacteria, ferrous and ferric iron, and silver ions, and period of conditioning the bacteria with silver. All of our experiments were conducted without addition of a nutrient in the system other than Fe(II). In addition, the duration of experiments was only one hour which was too short a time for the bacteria to grow. Consequently, our results are not growth biased and may approximate to the true chemical activity of the bacteria. For this reason, care should be taken while comparing our results with other results which are generally growth biased. The important conclusions drawn on the basis of our work follow:

- 1) Our results suggest that the ratio of concentrations of Fe(II) and the microbial cells in the system is an important parameter for the microbial oxidation of Fe(II). If this ratio is varied from the optimum value, then the rate of reaction will decrease (Fig. 3).

- 2) Silver ions exert a detrimental effect on the Fe(II) oxidizing activity of the bacteria. However, the bacteria can maintain its normal activity in the presence of a small concentration of silver (generally <1 mg/L). Silver is likely to inhibit Fe(II) oxidizing ability of the bacteria by a mixed mechanism in which silver may compete with ferrous iron for the active site on the enzyme and also bind to the enzyme-substrate complex.

As a result of conditioning with silver (1 mg/L or over), the active sites on the enzyme may be pre-occupied with silver ions resulting in severe loss of the Fe(II) oxidizing activity of the T. ferrooxidans.

3) The mechanism of T. ferrooxidans mediated oxidation of Fe(II) is remarkably sensitive to temperature changes. In the vicinity of room temperature (18-25°C), the reaction is controlled by the diffusion of Fe(II) whereas below 18°C, the rate of Fe(II) oxidation is controlled by the kinetics of the reaction being studied. In experiments involving 10 mg/L silver, reaction kinetics is likely to be the rate limiting factor for the range of temperature, 5.5-25°C (Fig. 9).

4) On the basis of our results we are not sure about the site on the T. ferrooxidans cells at which silver may accumulate. However, based on the literature reports describing a great affinity of silver for sulfur, it is likely that sulfur atoms of thiol (i.e. -SH) groups on the microbial proteins may be the potential sites for silver binding.

ACKNOWLEDGEMENTS

We thank the U.S. Department of Energy (University Coal Research Program) for extending financial support for this work under the grant number: DE-FG22-88PC88920.

REFERENCES

1. P. R. Norris and D. P. Kelly ed., (1988), Biohydrometallurgy: Proc. Int. Symp. (Warwick, 1987, Science and Technology Letters), p. 177-325.
2. B. J. Scheiner, F. M. Doyle and S. K. Kawatra ed. (1989), Biotech. Miner. Met. Process., (Littleton, CO: Society of Mining Engineers Inc), p. 9-31.
3. R. W. Bartlett, (Feb., 1990), "Aeration Pretreatment of Low Grade Refractory Gold Ores", Miner. Met. Process., p. 22.
4. R. W. Bartlett, (1992), Solution mining, Gordon and Breach Science Publishers, Philadelphia, p. 113.
5. F. Kargi and J. G. Weissman, (1984), Biotech. Bioeng., vol 26, p. 604.
6. A. E. Torma and T. M. Olsen, (1988), "Kinetics of bio-desulfurization of high sulfur coal", Appl. Biochem. Biotech., vol 18, p. 341.
7. P. Dugan, (1986), "Microbiological desulfurization of coal and its increased monetary value", Biotech. Bioeng. Sump., vol 16, p. 185.
8. F. Kargi, (1992), "Microbiological coal desulfurization", Enzym. Microb. Technol., vol 4(1), 13.
9. K. Imai, T. sugio, T. Tsuchida and T. Tano, (1975), "Effect of Heavy Metal Ions on the Growth and Iron-oxidizing Activity of Thiobacillus ferrooxidans", Agri. Biol. Chem., vol. 39(7), p. 1349.
10. P. R. Norris and D. P. Kelly ed. (1988), Biohydrometallurgy: Proc. Int. Symp., (Warwick, 1987, Science and Technology Letters), p. 103.
11. *ibid*, p. 89.
12. T. K. Datta, N. Ghosh, R. Sen and A. K. Dasgupta, (1990), "Pretreatment of Chalcopyrite Ore with Alkali: A Simple Technique to Improve the Leaching Mediated by Thiobacillus ferrooxidans", Miner. Eng., vol. 3(6), p. 641 and references cited therein.
13. T. G. Spiro ed., (1980), Metal Ion Activation of Dioxygen, (J. Wiley and Sons), p. 209.
14. O. H. Tuovinen and D. P. Kelly, (1974), "Studies on the Growth of Thiobacillus ferrooxidans II", Archiev. Microbiol., vol 95, p. 153.
15. B. J. Scheiner, F. M. Doyle and S. K. Kawatra ed., (1989),

Biotech. Miner. Met. Process., (Littleton CO: Society of Mining Engineers Inc.), p. 95.

16. P. Roy and A. K. Mishra, (1981), "Iron Oxidation not Coupled to Growth in Thiobacillus ferrooxidans in Presence of Toxic Metals", J. Appl. Bact., vol. 51, p. 387.

17. O. H. Tuovinen, J. Puhakka, P. Hiltunen and K. M. Dolan, (1985), "Silver Toxicity to Ferrous Iron and Pyrite Oxidation and its Alleviation by Yeast Extracts in Cultures of Thiobacillus ferrooxidans", Biotech. Lett., vol. 7(6), p. 389.

18. B. Volesky ed., (1990), Biosorptions of Heavy Metals, CRC Press, Boston, p.104.

19. P. R. Norris and D. P. Kelly ed., (1988), Biohydrometallurgy: Proc. Int. Symp., (Warwick, 1987, Science and Technology Letters, p. 287.

20. A. Bruynesteyn, R. H. Hackl, R. W. Lawrence and A. I. Vizsolyl, (Feb. 1986), United States Patent 4,571,387, p. 59.

21. L. Ahonen and O. H. Tuovinen, (1990), "Catalytic Effects of Silver in the Microbiological Leaching of Finely Ground Chalcopyrite-containing Ore Materials in Shake Flasks", Hydromet., vol. 24, p. 219.

22. G. Rossi, (1990), Biohydrometallurgy, McGraw Hill, Hamburg, p. 188.

23. B. Pesic, D. J. Oliver and P. Wichlacz, (1989), "An Electrochemical Method of Measuring the Oxidation Rate of Ferrous Iron with Oxygen in the Presence of Thiobacillus ferrooxidans", Biotech. Bioeng., vol 33(4), p. 424.

24. C. A. Jones and D. P. Kelly, (1983), "Growth of T. ferrooxidans on ferrous iron in chemostat culture: influence of product and substrate inhibition", J. Chem. Tech. Biotech., vol. 33B, p. 241.

25. J. E. Hobbie, R. J. Daley and S. Jasper, (1977), "Use of nucleopore filters for counting bacteria by fluorescence microscopy", Appl. Environ. Microbiol., vol 33, p. 1225.

26. P. Kelly, M. Eccleston and C. A. Jones, (1977), Geburtsh. Frauenheilkd., vol 4, p. 2.

27. D. P. Kelly and C. A. Jones, (1978) "Metallurgical applications of bacterial leaching and related microbiological phenomena", L. E. Murr, A. E. Torma and J. A. Brierley, eds., Academic press, N. Y.

28. J. F. Braddock, H. V. Luong and E. J. Brawn, (1984), Appl. Environ. Microbiol., Vol 48, p. 48.

29. G. Rossi, (1990), Biohydrometallurgy, McGraw Hill Co., Hamburg., p. 194 and references cited therein.
30. D. Voet and J. G. Voet, (1990), Biochemistry, J. Wiley and Sons Co., N. Y., p. 343.
31. F. D. Pooley, (April 1982), "Bacteria accumulate silver during leaching of sulfide ore minerals", Nature, vol 296, p. 642.
32. J. T. Trevors, (1987), "Silver resistance and accumulation in bacteria", Enzyme Microb. Technol., vol 9, p. 331.
33. R. C. Tilton and B. Rosenberg, (1978), Appl. Environ. Microbiol., vol 35, p. 1116.
34. B. Volesky (ed), (1990), Biosorption of heavy metals, CRC press, Boston, p. 577.
35. D. J. Oliver, University of Idaho, Moscow, Idaho 83843, private communication.

Fig.1 Plot of potential of the pyrite indicator electrode as a function of time corresponding to different pH (without silver).

Fig. 2 Rate constant of the microbial oxidation of Fe(II) as a function of cell density (in terms of OD590) under standard conditions.

Fig. 3 Rate constant of the microbial oxidation of ferrous iron as a function of ferrous iron concentration (pH 1.7 and temperature 25C. Squares refer to OD590=2.8 while triangles OD590=1.41 and circles OD590=5.85. Closed symbols correspond to experiments without silver whereas open symbols 10 mg/L silver).

Fig. 4 Effect of initial ferric ion concentration on the rate of microbial oxidation of ferrous iron under standard conditions.

Fig. 5 Lineweaver-Burk plot of the rate constant of bacterial oxidation of Fe(II) as a function of Fe(II) concentration. (Refers to the curve with closed squares in Fig. 3 upto an Fe(II) concentration of 0.001M).

Fig. 6 Direct linear plot of rate constant of microbial oxidation of Fe(II) as a function of Fe(II) concentration (Refers to standard conditions except Fe(II) concentration).

Fig. 7 Initial rate of microbial oxidation of ferrous iron as a function of initial concentration of Fe(II) in the absence (refers to the squares) and in the presence of 10 mg/L silver (refers to the triangles). Closed symbols represent experiments using *T. ferrooxidans* cells from a regular 5 day batch, while open symbols refer to experiments with the bacteria from a 4 day batch.

Fig. 8 Lineweaver-Burk analysis of the data representing microbial oxidation of Fe(II) in the absence (refers to the squares) and in the presence of 10 mg/L silver (corresponds to the triangles). Closed symbols represent experiments involving *T. ferrooxidans* cells from a regular 5 day batch, while open symbols refer to experiments using microbial cells from a 4 day batch.

Fig. 9 Arrhenius plot of the oxidation of ferrous iron with *T. ferro-oxidans* in the absence and the presence of 10 mg/L silver (pH 1.70, OD₅₉₀=2.80, Fe(II) concentration=0.001M).

Fig. 10 Potential of the pyrite indicator electrode versus time as a function silver concentration. There was no conditioning of the bacteria with silver.

Fig. 11 Variation of the rate constant of microbial oxidation of Fe(II) with concentration of silver at three different pH values. There was no conditioning of the bacteria with silver.

Fig. 12 Potential of the pyrite indicator electrode versus time during oxidation of ferrous iron with bacteria, conditioned in solutions containing silver (10 mg/lit).

Fig. 13 Rate constant of the microbial oxidation of Fe(II) as a function of conditioning time of the bacteria with silver (other parameters unchanged).

Fig. 14 Plot of rate constant of the bacterial oxidation of Fe(II) as a function of pH (with and without silver).

Fig. 15(a) SEM micrograph of *T. ferrooxidans* taken from an experiment with 2.5 mg/L silver.

Fig. 15(b) SEM micrograph of *T. ferrooxidans* taken from the control experiment.

Fig. 16(a) TEM micrograph of *T. ferrooxidans* taken from control experiment.

Fig. 16(b) TEM micrograph of *T. ferrooxidans* taken from an experiment involving 2.5 mg/L silver.

Fig. 16(c) Magnified TEM micrograph of T. ferrooxidans taken from an experiment with 2.5 mg/L silver.

Fig. 17(a) X-ray emission spectrum (EDAX) of the lighter spot on the bacteria (refers to Fig. 16a).

Fig. 17(b) X-ray emission spectrum (EDAX) of the darker spot on the bacteria (refers to Fig. 16b and c).

END

**DATE
FILMED**

1 / 15 / 93