DOE/PC/90049--T8

DOE/PC/90049--T8

DE93 011514

3572 Iron Works Pike
Lexington, KY 40511-8433
FAX: 606-257-0302

QUARTERLY REPORT FOR THE PERIOD OF JULY - SEPTEMBER, 1991

CLEAN GASOLINE REFORMING WITH SUPERACID CATALYSTS

#DE-AC22-90PC90049

P.I.: B. H. Davis

Begin Date: 9/25/90

End Date: 9/24/92

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

MASTER

An Equal Opportunity/
Affirmative Action University

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

CLEAN GASOLINE REFORMING WITH SUPERACID CATALYSTS

#DE-AC22-90PC90049

July - September 1991

Task 1. Project Work Plan

A detailed work plan covering the entire contract period has been prepared and submitted to DOE.

Task 2.1. Heteroatom Removal

Naphtha Feedstock

Three, 55-gallon drums of a bituminous and a subbituminous coal-derived naphtha were obtained from the Wilsonville, Alabama Advanced Integrated Two Stage Liquefaction pilot plant. The first naphtha hydrotreated was obtained from processing a Black Thunder coal (subbituminous). The second hydrotreated naphtha was obtained while processing an Illinois #6 coal (bituminous). Elemental analyses of the feed naphtha samples are given in Table 1.

Pilot Plant Operations

The naphtha was hydrotreated in the reconfigured CAER 1/8 tpd liquefaction pilot plant. The process diagram is shown in Figure 1. The plant consists of the following sections: (a) feed delivery (naphtha, H₂), (b) reactor, and (c) high and low temperature separators. The reactor was charged with 2 kg of catalyst and operated in a fixed bed down-flow configuration for the hydrotreating operations.

The first catalyst employed was a commercial Co/Mo on alumina catalyst (American Cyanamid HDS-1442A, 1/16" x 1/4" pellets). The second catalyst studied was a commercial Ni/Mo on alumina catalyst (Akzo KF-840 1.3Q).

Both catalysts were presulfided using a mixture of 3% H₂S in hydrogen prior to the beginning of hydrotreating operations. During the presulfiding operation, a flowrate 30 ft.³/h of the H₂S/H₂ mixture was used. The reactor temperature was rapidly increased to 175°C followed by a 25°C/h ramp. During these operations, the composition of the gas stream exiting the plant was monitored at intervals by an on-line gas chromatograph to determine when H₂S breakthrough occurred. At some point, during the ramping of the reactor temperature, the data obtained from the GC indicated that H₂S was not being absorbed by the catalyst. At this point, the temperature was increased to 375°C and held at this temperature for 90 minutes. The reactor temperature was then lowered to 300°C and then the inlet gas stream was switched to hydrogen using a flowrate 5 ft.³/h prior for the start of naphtha processing. The same presulfiding procedure was used for operations with the Ni/Mo catalyst.

The processing conditions for the three pilot runs are given in Table 2. During naphtha processing, daily samples from the low pressure separator (V-451) were obtained for analysis. The pilot plant was placed under nitrogen at a system pressure of 360 psig prior to the beginning of a second hydrotreating run. Prior to the third pilot plant run, the Co/Mo catalyst was replaced by the Ni/Mo catalyst.

During the hydrotreating operations, two barrels of the Black Thunder naphtha was processed. Collection of the hydrotreated naphtha from each pass into the product barrel was initiated upon the attainment of steady state conditions as

indicated by the process variables and the nitrogen content of the daily samples. The feedstock for the second pass using the Black Thunder naphtha was the product barrels obtained during the first pass. The feedstock for the third pass using the Ni/Mo catalyst was the hydrotreated product from the second pass.

An Illinois #6 coal derived naphtha was hydrotreated following completion of the third pass of the Black Thunder naphtha. During the Illinois #6 naphtha processing, several process variable changes were made and are documented in Table 2. Prior to sampling and product collection, a sufficient number of plant turnovers, as indicated by the analyses, were employed to insure the samples were representative of the hydrotreated Illinois #6 naphtha feedstock.

Carbon and hydrogen analyses were performed using a Leco CHN analyzer. Oxygen analyses were performed using the FNAA method and were provided by the University of Kentucky Radioanalytical Services. Trace level nitrogen was determined using a Xertex DN-10 total nitrogen analyzer equipped with a chemiluminescence detector. A Seivers chemiluminescence detector was utilized for sulfur determinations.

Black Thunder Hydrotreatment

The nitrogen content of the hydrotreated naphtha (daily samples) obtained during the three passes are shown in Figure 2. The data clearly show the difficulty in removing nitrogen from the naphtha using either the Co/Mo or Ni/Mo catalysts at these process conditions. During the initial pass, only 43% of the nitrogen was removed from the naphtha. The amount of nitrogen removed during the second pass was only marginally better (51%). Switching to a Ni/Mo catalyst and using the same process conditions increased nitrogen removal to 61%. However, after three passes,

the nitrogen content of the hydrotreated naphtha remained at an average level of 383 ppm. Thus only 52% of the total nitrogen was removed during all three passes. Based on the data for the three passes, it was projected that the naphtha would have to be processed 10 times to obtain a hydrotreated product containing 2 ppm nitrogen (Figure 3). Clearly, hydrotreatment of the Black Thunder naphtha will require more severe conditions than are normally employed in petroleum refining to obtain a final product in which the nitrogen content is sufficiently low for further upgrading by conventional reforming processes.

Nitrogen in coal-derived liquids consists of both basic compounds (e.g., anilines) and neutral compounds (e.g., pyroles). To determine if the nitrogen compounds remaining after hydrotreatment during the Co/Mo runs represented a single class of compound, the naphtha was extracted with 10% H_3PO_4 to remove the basic nitrogen compounds. The resulting raffinates were analyzed for total nitrogen. The nitrogen content of the raffinate of the final products from the first two passes indicated a substantial amount of basic nitrogen compounds are still present. These data suggest that the difficulty in removing the nitrogen during hydrotreatment was not entirely due to a high concentration of neutral nitrogen compounds in the Black Thunder naphtha.

It has been reported that oxygenated compounds and the water produced during the HDO process can inhibit HDN. The amount of oxygen in the hydrotreated Black Thunder naphtha is shown in Figure 4. Although the oxygen content of the original naphtha is high (2.01%), 94% of the oxygen was removed during the first pass to yield a product containing .11% oxygen. The second and third pass (Ni/Mo)

removed an additional 54% and 40% of the oxygen to produce a final hydrotreated naphtha containing .03% oxygen the detection limit of the direct oxygen determination is about 0.05%; thus, the oxygen level may be much lower than 0.03%. The results indicate that the majority of the oxygen was easily removed during the first pass using the Co/Mo catalyst and low oxygen content of naphtha feedstock not substantially improve the amount of nitrogen removed during the second pass.

It is apparent from these data that oxygen is easily removed from the Black Thunder (subbituminous coal) naphtha. The nitrogen compounds found in this naphtha are more difficult to remove than oxygen even during hydrotreating using a WHSV of 1 and a reaction temperature of 403°C. The data suggests that the HDO process did not substantially inhibit the HDN process using either the Co/Mo or Ni/Mo catalysts under these conditions.

Illinois #6 Hydrotreatment

The data obtained from the hydrotreatment of the Black Thunder naphtha suggested a change in operational variables would be required to obtain acceptable levels of nitrogen in the final product. These changes are documented in Table 2 for the Illinois #6 hydrotreatment operational period. The effect of the reactor temperature and space velocity on nitrogen removal is shown in Figure 5.

The Illinois #6 processing period which used the same space velocity and a lower reactor temperature (352°C) than was used for processing the Black Thunder naphtha reduced the nitrogen content by 34% to a level of 521 ppm. A lower (0.2 vs 0.8) space velocity using this reactor temperature improved the HDN of the naphtha. Using these conditions, 80% of the nitrogen was removed; however, a nitrogen level of

159 ppm hydrotreated product did not meet the requirements for a reforming feedstock. Increasing the reactor temperature to 403°C with approximately the same space velocity (0.2) removed 99% of the nitrogen in the hydrotreated product. The final level of nitrogen (3.1 ppm) in the hydrotreated product was sufficiently low for a reformer feedstock.

The oxygen content of the hydrotreated Illinois #6 naphtha for two of the processing periods are shown in Figure 6. As can be seen in the figure, 86% of the oxygen was removed at a lower reaction temperature (351°C). Increasing the reaction temperature (403°C) and decreasing the space velocity marginally increased the level of HDO obtained.

The resulting data from the hydrotreatment of an Illinois #6 and Black Thunder naphtha indicate that the removal of nitrogen is difficult. To obtain a nitrogen content of less than 10 ppm require process conditions which are more severe than normally associated with petroleum hydrotreating. In contrast to the difficulty in obtaining a low nitrogen product, oxygen is relatively easy to remove from both the Illinois #6 and Black Thunder naphtha. The relationship between HDN and HDO obtained for both naphtha samples is shown in Figure 7. It is apparent from these data that new catalysts will have to be developed for the processing of coal-derived naphtha to obtain a sufficiently heteroatom free product using common industrial process conditions.

Task 2.2. Identification of Naphtha Components by GC/MS

The identification of the compounds in the Black Thunder and Illinois #6 naphthas by GC/MS has been initiated. The results obtained to date are shown in

Table 3. The identification of the compounds was based on manual interpretation and computer library searches of the mass spectra obtained. In addition, standard compounds were used to verify a number of the identifications.

Although a 60 meter DB-5 capillary column was used for this work, the chromatograms indicated a considerable amount of overlap, both in the front and tail end of the chromatograms. The use of sub-ambient temperature programming helped alleviate the coelution of compounds in the front end of the chromatogram, but did not improve the resolution in the back end of the chromatogram. To improve the resolution of the chromatography, a 150 meter Petrocol column was purchased and the modifications to the capillary GC to accommodate the higher head pressures have been started.

In addition, an HP GC/MSD system has been purchased (at no cost to the project) and is currently being installed. The instrumentation will facilitate a rapid turn-around for the analysis of model compound and naphtha products from the plug-flow reactor runs.

Task 3. Optimization of Chlorided Pt-Alumina Catalysts

Two additional down-flow, fixed bed reactor systems were constructed and successfully tested. A total of three reactors are available for the catalyst testing experiments.

A commercially prepared Pt (.4 wt.%) on alumina catalyst (1/8" diameter, 1/8" long pellets) was used in the initial set of experiments using cyclohexane and the hydrotreated Illinois #6 naphtha as feedstocks. In addition, a catalyst was prepared

by impregnating a commercially available alumina (1/8" diameter, 1/8" long pellets) with chloroplatinic acid to obtain a catalyst with a 1 wt.% Pt concentration.

Carbon tetrachloride was utilized for adding chloride to the catalyst; a vessel containing carbon tetrachloride was installed in the hydrogen supply line between the flow controller and the reactor. The reactor was heated to 450°C and pressurized to 300 psig with flowing hydrogen before valving the carbon tetrachloride containing vessel into the hydrogen stream. The flowrate of the hydrogen bubbling through the CCl₄ was adjusted to provide a flow of approximately 0.025g chlorine per gram of catalyst per hour. The catalyst was chlorided for 35 to 48 hours. After this period, the bomb was valved out of the hydrogen stream and the reactor temperature was reduced from 450°C to 300°C: H₂ pressure was maintained at 300 psig prior to initiating liquid feed. A hydrogen to hydrocarbon ratio of 2 was maintained during liquid feed to the reactor. The methyl cyclohexane feedstock was doped with CCl₄. The methyl cyclohexane contained CCl₄ concentrations ranging from 0.01 to 0.5 wt.%. The naphtha feedstock was processed both with (0.5 wt.%) and without CCl₄ added.

The methylcyclohexane conversions obtained using the .4 wt.% Pt on alumina catalyst are given in Figure 8. During the initial processing period, the concentration of CCl₄ in the feedstock was 0.01 wt.%. While processing this feedstock, the methylcyclohexane conversions decreased from 71.2 wt.% to 20.5 wt.% during the initial 26 hours on stream.

The feedstock was switched to methylcyclohexane containing 0.5 wt.% CCl₄. The conversion of this feedstock showed a rapid increase; however, the conversion of the methylcyclohexane did not reach the initial level of conversion observed using the

feedstock containing 0.01 wt.% of CCl_4 (Figure 8). After the conversions appeared to be leveling at a value of 43%, the feedstock was switched to a methylcyclohexane containing 0.1 wt.% CCl_4 . As can be seen in Figure 8, the conversion declines rapidly to a value lower than was obtained during the initial processing periods using the methylcyclohexane containing 0.01 wt.% CCl_4 . Switching the feedstock back to the methylcyclohexane containing 0.5 wt.% CCl_4 , the conversion began to increase to a level which was significantly lower than obtained during the previous processing period using the same feedstock.

The results for the conversion of methylcyclohexane using the 1% Pt on alumina catalyst and the same process conditions are shown in Figure 9. As can be seen, in the initial processing period using the 0.1 wt.% CCl_4 in the feed, there is a rapid decrease in the conversion with time on stream. Switching to a feed with a higher concentration of CCl_4 (0.4 wt.%) slightly increases the conversion of the methylcyclohexane. Changing the feed to a methylcyclohexane with 0.01 wt.% CCl_4 causes the conversions to decrease. The trend in the conversions obtained were similar using both the 1.0 wt.% and 0.4 wt.% Pt on alumina catalysts. The data suggests that the loss of activities of these catalysts is due to a loss in the acid sites of the catalyst either by coking and/or loss of chlorine during the reaction.

The hydrotreated Illinois #6 naphtha was processed using the chlorided commercial $\text{Pt}/\text{Al}_2\text{O}_3$ catalyst. The catalyst was chlorided using the same conditions as the previous runs described. During the initial processing period, no CCl_4 was added to the feedstock. The catalyst deactivated very rapidly as can be seen for the data in Figure 10. The initial feed (at time = 0) and product composition by carbon

number show in Figure 10 indicate that the catalyst was active in the first few hours of processing. The product composition after 1 hour of processing indicated that the major compositional changes which occurred were an increase in the concentrations of iso-alkanes and methyl and dimethylcyclopentanes (Table 4). The increase of these compound classes result from the conversion of n-alkanes and the cyclohexanes (Table 5) in the feed. This is the result that is desired since these products are the higher octaine paraffins. After approximately 5 hours of processing the naphtha over this catalyst, the product composition changed very little when compared to the initial composition of the naphtha.

The feed was switched to a naphtha containing .5 wt.% CCl_4 . The catalyst showed no increase in activity as was observed for the model compound runs when the concentration of CCl_4 in the feed was increased. This is illustrated in Figure 11 which shows the cyclohexane/methylcyclopentane ratio for both periods of operation.

Additional runs were made with this commercial catalyst and model compounds. All of the runs showed the rapid deactivation previously discussed. The catalyst pellets showed variation in color which indicates that the platinum was not dispersed evenly among the pellets. Samples of the light colored and dark pellets were analyzed. In addition, the surface of the pellets were removed by scraping and this sample and the pellet centers were analyzed. As can be seen, from the results of the Pt analyses (Table 6) the Pt was not distributed evenly among the pellets of the catalyst. In addition, the Pt is concentrated only on the surface of the pellets. These results indicate that this catalyst was not suitable for further testing in this task.

An aluminum oxide was prepared in-house by precipitation of $\text{AlCl}_3 \cdot 6\text{H}_2\text{O}$ with NH_4OH . The catalyst was impregnated with H_2PtCl_6 to produce a Pt concentration of 1 wt.%. The catalyst was chlorided at a lower temperature (300°C) using nitrogen as a carrier gas for the CCl_4 . During the chloriding of the catalyst, the product gas stream was monitored for CO_2 and CCl_4 . The chloriding of the catalyst was terminated when the CO_2 concentration reached a maximum. For this catalyst, the maximum CO_2 concentration occurred after approximately 2 hours. After chlorination, the reactor temperature was reduced and the hydrogen flow was started. After a sufficient number of reactor turnovers to purge the nitrogen from the system, the reactor temperature was increased to 300°C and liquid feed was started. During the first 7 hours of n-octane processing, the conversion remained near 100%. However, the products of the conversion were primarily iso-butane and iso-pentane indicating that hydrocracking was the major reactions occurring. Very little hydrogenolysis to produce methane (0.14 mole% of the product gas stream) was observed during this time period. The catalyst remained active for hydrocracking for approximately 12 hours. After this, the conversion of n-octane decreased rapidly to less than 10%. The high hydrocracking activity of the catalyst suggested that the reaction temperature was too high.

Another run with this catalyst was performed using a reaction temperature of 150°C for processing the liquid feed. The same procedure for chloriding the catalyst were used as previously described. The conversion of n-octane (spiked with 0.5 wt.% CCl_4) and selectivity to iso-alkanes are shown in Figure 12. The data shown in this figure indicate that, at this reaction temperature, the conversion of n-octane remained

fairly constant at approximately 45% for 27 hours of processing. The majority of the product slate is iso-C₈ compounds indicating that the catalyst has a high isomerization selectivity. No methane was observed in the product gases indicating that hydrogenolysis was not taking place.

After 44 hours of processing the n-octane with .5 wt.% CCl₄ the conversion had dropped to 10%. The feed was then switched to n-octane with 1.0 wt.% CCl₄. The results show that the activity was not restored as previously observed with the commercial Pt/Al₂O₃ catalyst. The feed was switched to 1-octene to evaluate the activity of the metal function of the catalyst. The 1-octene was completely converted to n-octane during this processing period. This indicated that the platinum was still active for hydrogenation, and that the isooctanes were being formed by the acid function, not the pt. From this data, the deactivation of the catalyst was likely due to the loss of active acidic sites on the catalyst due to either coking and/or loss of chlorine. Additional analysis of the catalyst and products are in progress.

Task 5. Preparation of Zirconia Superacid Catalyst

ZrO₂ A was prepared by rapid precipitation from a 0.3M solution of zirconium tetrachloride with a large excess of NH₄OH to produce a pH of 10.5. ZrO₂-B, except for slowly adding the base during 8 hours, was prepared by the same procedure. On calcination of 500°C for 5 hours, ZrO₂-A showed predominantly monoclinic phase, while ZrO₂-B exhibited a major fraction of tetragonal phase. These two precursors were sulfated by immersing back in 1N H₂SO₄, and are designated as ZrO₂-A/S and ZrO₂-B/S respectively. ZrO₂-N/S was also prepared by precipitation from a zirconium

nitrate solution at a pH of 10.5 with excess of NH_4OH , and impregnated to give 1%, 2%, 4%, 6%, or 9% SO_4^{2-} .

Thermal analysis were carried out using a Seiko model TG/DAT 320. Both TG/DTA data were obtained simultaneously from the dried zirconia samples at a heating rate of $20^\circ\text{C}/\text{min}$. in helium flow. These catalysts were tested for catalytic activity and selectivity for 2-octanol conversion.

A typical TG/DTA curve is shown in Figure 13 for $\text{ZrO}_2\text{-A}$. A total weight loss of about 12% has been observed. The DTA curve exhibits a crystallization exotherm at about 470°C , and the heat evolved was the same for both $\text{ZrO}_2\text{-A}$ and $\text{ZrO}_2\text{-B}$, which exhibited different crystal structures after calcination. However, the exotherm peak was shifted to 607°C for $\text{ZrO}_2\text{-A/S}$ (Figure 14). Also, the exotherm peak amplitude has been significantly decreased for the sulfated sample. Similar TGA/DTA data were obtained for the sample $\text{ZrO}_2\text{-B}$ and $\text{ZrO}_2\text{-B/S}$. The mechanism by which the sulfate ions can cause a greater surface area and, at the same time, disturb the phase transition is not clear.

The TGA curves obtained from the sulfated samples prepared from zirconium nitrate precursors are shown in Figure 15. All the samples lose about 12 wt.% up to about 600°C . Above 600°C , additional weight loss occurs. The ultimate weight loss at 900°C , as a function of percent sulfate, is shown in the inset of Figure 15, increases with increase in sulfate content. The additional weight loss of up to 8% after 600°C is due to the evolution of SO_2 species, which is confirmed by mass spec data. The DTA curves for all these sulfated samples are shown in Figure 16, which clearly indicate that the exotherm peak amplitude is gradually affected as the SO_4^{2-} concentration is

increased. For the 9% sulfated sample, the exotherm is very broad, which indicates that the endothermic evolution of SO_2 species compensates for the exothermic crystallization of zirconia, or spreads the crystallization process over a wide temperature range.

Task 6. Testing of Zirconia Superacid Catalysts

The data showing the selectivity for production of 1-octene during dehydration of 2-octanol for $\text{ZrO}_2\text{-A}$ and for $\text{ZrO}_2\text{-A/S}$ are shown in Figure 17. The unsulfated sample exhibits high selectivity for 1-octene initially, but this declines to stabilize at about 40% at a reaction temperature of 320°C . However, the selectivity of the sulfated sample for 1-octene is consistently high at a reaction temperature of 220°C . The addition of sulfate ions has therefore increased the catalytic activity over that of the unsulfated zirconia, and at the same time produced a catalyst that is very selective for 1-octene only. Thus, this $\text{ZrO}_2\text{-A/S}$ sample clearly does not exhibit superacid character since the dehydration product is the least stable one. Under similar conditions, dehydration using amorphous silica-alumina produces an equilibrium distribution of *m*-alkenes. Samples of $\text{ZrO}_2\text{-N}$ were sulfated and these catalysts were even more active for 2-octanol dehydration than $\text{ZrO}_2\text{-A/S}$. However, the sulfated samples based upon $\text{ZrO}_2\text{-N}$ produced nearly 100% conversion at the highest flow rate possible with the equipment [LHSV=12] and showed an equilibrium distribution of normal octenes rather than a selectivity for 1-octene. The samples of sulfated zirconias that are described here show a wide range of activity compared to unsulfated zirconias, but none of them exhibits the chain isomerization character expected of a superacid.

PUBLICATIONS AND PRESENTATIONS

1. R. Srinivasan and B. H. Davis, "Sulfated Zirconia Superacid Catalysts: Thermal Analysis and Characterization Studies", *Am. Chem. Soc., Div. Petro. Prep.*, **36 (4)**, 635 (1991).
2. L. Xu, R. A. Keogh, C. S. Huang, R. Spicer, D. Sparks, S. Lambert, G. Thomas, and B. Davis, "Catalytic Hydrotreatment of Coal-Derived Naphtha", *Am. Chem. Soc., Div. Fuel Prep.*, **36 (4)**, 1909 (1991).
3. L. Xu, R. A. Keogh, C. S. Huang, R. Spicer, D. Sparks, S. Lambert, G. Thomas, and B. Davis, "Catalytic Hydrotreatment of Coal-Derived Naphtha", first draft of manuscript completed.

TABLE 1
Analysis of Feedstocks

	<u>Black Thunder</u> <u>Naphtha</u>	<u>Illinois #6</u> <u>Naphtha</u>
C	85.23%	85.57%
H	12.23%	13.24%
N	3510 ppm	795 ppm
S	363 ppm	353 ppm
O	2.01%	.35%

TABLE 2
Process Summary

Black Thunder
Hydrotreatment

<u>Pass # (Run Hours)</u>	<u>Catalyst</u>	<u>Feed Rate (#/hr)</u>	<u>WHSV # feed/# catalyst/hr</u>	<u>Temp (°C)</u>	<u>Pressure (psig)</u>
1 (0-165)	CoMo	4.0, 4.5	.9, 1.0	418	2010
2 (0-143)	CoMo	4.0, 4.5	.9, 1.0	418	2010
3 (0-127)	NiMo	4.5	.8	403	2000

Illinois #6
Hydrotreatment

1 (127-148)	NiMo	4.5	.8	352	2000
2 (149-284)	NiMo	1.1	.2	352	2000
3 (185-408)	NiMo	1.8	.3	403	2000

TABLE 3
NAPHTHA COMPOSITIONS

<u>Compound</u>	<u>III. #6 Hydrotreated Naphtha (Wt. %)</u>	<u>Black Thunder Hydrotreated Naphtha (Wt. %)</u>
propane	.04	.07
iso-butane	.06	.05
n-butane	.86	.33
iso-pentane	.59	.30
n-pentane	1.31	.63
2,2-dimethylbutane	.004	.01
2,3-dimethylbutane	.04	.03
cyclopentane	1.11	.69
3-methylpentane	.41	.29
n-hexane	1.53	.78
methylcyclopentane	1.74	1.11
3,3-dimethylpentane	.01	.01
cyclohexane	8.12	4.91
2-methylhexane	.16	.43
2,3-dimethylpentane	1.05	.28
1,1-dimethylcyclopentane	.10	.06
3-methylhexane	.79	.42
1,cis-3-dimethylcyclopentane	.30	.20
1,trans-3-dimethylcyclopentane	.36	.24
1,trans-2-dimethylcyclopentane	.49	.43
n-heptane	4.63	.66
methylcyclohexane	10.87	5.03
ethylcyclopentane	.97	.54
toluene (coelution)	1.95	3.59
3-methylheptane	.65	.44
1,trans-4-dimethylcyclohexane	1.52	.72
1,cis-3-dimethylcyclohexane	.73	.31
1-methyl-3-ethylcyclopentane	.25	.16
1-methyl-2-ethylcyclopentane	.18	.13

Table 3 Continued

1-methyl-1-ethylcyclopentane	.39	.31
2-C cyclohexane	.71	.21
n-octane (coelution)	1.51	.65
1,cis-2-dimethylcyclohexane	.31	.16
ethylcyclohexane	4.75	2.94
3-C cyclohexane	.06	.21
ethylbenzene	.82	2.15
m & p-xylene	1.20	.98
3-methyloctane	.36	.39
1-methyl, trans-2-cis- 3-trimethylcyclohexane	.99	.62
1-methyl, trans-2, cis- 4-trimethylcyclohexane	.31	.20
o-xylene (coelution)	.55	.73
4-C cyclopentane	.40	.23
1-methyl-4-ethylcyclohexane	.68	.39
1-methyl-3-ethylcyclohexane	.15	.12
1-methyl-2-ethylcyclohexane	.33	.29
1-methylethylbenzene	.03	.04
i-propylcyclohexane	2.58	1.56
butyl cyclohexane	.36	.20
n-propylbenzene	.59	.26
1-methyl, 2-ethylbenzene	.57	.78
3-C benzene	.15	.27
3-C benzene	.17	.15
1-methyl-4-(1-methylethyl) cyclohexane	.51	.44
C ₁₀ H ₂₀ /C ₉ H ₁₆ (hexahydroindan)	1.28	.71
3-C benzene	.64	.13
Indol/4-C cyclohexane	1.17	.26
Indan	.68	.70
4-C-cyclohexene	.52	.64
1-methyl-3-propylbenzene	.25	---
5-methylindan	.37	.30
1-C indan/biphenyl	1.06	2.33

Table 3 Continued

undecane	.23	.16
acenaphthene/biphenyl	.36	.21
2-C indan or 1-C tetralin	1.06	1.49
1-C indan	1.18	1.61
5-C benzene	.38	.10
5-C benzene	.09	.15
1-C indan	1.56	1.87
2-C indan/1-C tetralin	.70	1.25
2-C indan/1-C tetralin	.23	.56
2-C indan/1-C tetralin	.34	.80
2-C indan/1-C tetralin	.51	.89
dodecane	.35	.89
2-C indan/1-C tetralin	.47	.03
2-C indan/1-C tetralin	.27	.18
2-C indan/1-C tetralin	.21	.04
2-C indan/1-C tetralin	.31	.13
2-C indan/1-C tetralin	.31	.30
6-methyltetralin	1.60	1.30

TABLE 6

Pt Analysis of a Commercial
(.4%) Pt/Al₂O₃ Catalyst

<u>Sample</u>	<u>Wt.% Pt</u>
Light colored pellets	.19, .14, .14
Dark colored pellets	.66, .71, .77
All pellets	.41
Pellet surface scrapings	1.06
Pellet centers	.12

Figure 1. CAER Pilot Plant configuration for naphtha hydrotreating.

Figure 2. Nitrogen content of the daily product samples of the hydrotreated Black Thunder naphtha.

Figure 3. Projected number of hydrotreating passes required to obtain a 2 ppm product.

Figure 4. Summary of the oxygen content of the hydrotreated Black Thunder naphtha.

Illinois #6 Naphtha Feed and Product

Figure 5. The effect of temperature and WHSV on HDN.

Figure 6. Effect of space velocity and temperature on HDO of the Ill.#6 naphtha.

Figure 7. Comparison of HDO and HDN for coal-derived naphtha.

Figure 8. Conversion of methylcyclohexane with a commercial $\text{Pt}/\text{Al}_2\text{O}_3\text{-Cl}$ catalyst.

Figure 9. Conversion of methylcyclohexane with a Pt/Al₂O₃-Cl catalyst.

Figure 10. Distribution of naphtha products by carbon number.

Figure 11. Cyclohexane/methylcyclopentane ratio in naphtha products.

Figure 12. Conversion of n-octane and product distribution.

Figure 13. TGA/DTA traces from the sample ZrO₂-A, which was prepared by rapid precipitation. (Heating rate $\approx 20^{\circ}\text{C}/\text{min}$. in helium).

Figure 14. **TGA/DTA traces from the sample ZrO₂-A /S (Sulfated). (Heating rate $\approx$ 20°C/min. in helium).**

Figure 15. TGA weight loss curves for the sulfated $\text{ZrO}_2\text{-N}$ samples, which were prepared from a zirconium nitrate solution. (a) 1%, (b) 2%, (c) 4%, (d) 6%, and (e) 9% SO_4^{2-} . The final weight loss at 900°C as a function of sulfate content is shown in the inset.

Figure 16. The DTA data for the sulfated $\text{ZrO}_2\text{-N}$ samples. (a) 1%, (b) 2%, (c) 4%, (d) 6%, and (e) 9% SO_4^{2-} . Note that the exotherm peak amplitude is broadened as the sulfate content increases. Above 4% sulfate, the peak is hardly seen.

Figure 17. The selectivity data for 1-octene. (■) Unsulfated ZrO₂-A; the reaction temperature is 320°C, and (●) sulfated ZrO₂-A/S; the reaction temperature is 220°C.

END

DATE
FILMED
5/13/93