Quarterly Progress Report:
High Temperature Membranes for
H₂S and SO₂ Separations
Grant DE-FG22-90PC90293
July 1, 1992 - September 30, 1992

by

Professor Jack Winnick
Georgia Institute of Technology
School of Chemical Engineering
Atlanta, Georgia 30332-0100

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

MASTER

Purpose and Goals of Research

High temperature membrane separation techniques have been applied to gas mixtures involved in coal utilization. For coal gasification, H_2S has been removed from the syn-gas stream, split into hydrogen which enriches the syn-gas, and sulfur which can be condensed from an inert gas sweep stream. For coal combustion, SO_2 has been separated from the flue gas, with concentrated SO_3 produced as a by-product.

Both processes appear economically viable but each requires fundamental improvements: both the H_2S cell and the SO_2 cell require more efficient membranes and the H_2S cell needs a more efficient anode. Membranes will be fabricated by either hot-pressing, impregnation of sintered bodies, or tape casting. Research conducted during the present quarter is highlighted, with an emphasis on progress towards these goals.

I. SO_x/NO_x Removal Cell

Introduction

Successful removal of NO_x and SO_x from flue gas depends on the development of a membrane able to achieve a current density of 50 mA/cm² at a total voltage of approximately 1V. Flooding of electrode has been identified as a problem, leading to increasing polarization over time. The resulting reduction of surface area also tends to limit the mass transfer flux, reducing the efficiency of the cell. To reduce flooding, new materials and techniques of manufacture will be investigated, in the attempt to produce a ceramic membrane of approximately 50% theoretical density. This membrane must have proper pore size distribution to ensure sufficient capillary force to prevent impregnated electrolyte from flooding electrodes, and subsequently drying the ceramic membrane.

Electrolyte introduction to the cell is a continuing problem. The development of a method is still being investigated. Ideally, the electrolyte would be introduced as powder with binder in a green body. This binder would ideally burn away at temperatures of approximately, leaving pure electrolyte to melt and complete the salt bridge necessary for the electrochemical cell. The electrolyte used this quarter was, exclusively, a 90wt%K₂S₂O₇/10wt%V₂O₅ mixture.

Electrodes used this quarter were lithiated nickel oxide. These were obtained from National Standard and the Energy Research Corporation (E.R.C.) as Ni sheets.

These sheets were cut, with a resulting superficial area of approximately 20.0cm². The cut Ni was placed in a 1.2M solution of LiOH, dried, and oxidized at 600° C prior to placement in the cell. This process creates a p-type semiconductor, exhibiting room resistivities on the order of 0.2Ω at room temperatures. Pore size of the National Standard Fibrex electrodes is approximately 1.0 μm. The pore size of the ERC electrode is proprietary.

Current is conducted through the cell from stainless steel 316L housings, to the electrolyte-wetted electrode, where the removal takes place. The current is then carried through the cell by the transporting species in the electrolyte. Oxidation of the transporting species occurs at the anode, and the current passes through the anode electrode to the anodic SS316L housing, and out of the cell.

SO_x REMOVAL:

Summary

Attempts to use polyethylene oxide as an electrolyte binder last quarter were evaluated for material properties and reactions. In addition, the effects of the solvents used in tape casting techniques were evaluated with electrolyte for any reaction that might occur. These evaluations utilized the technique of x-ray diffraction. For this technique, materials to be analyzed must be in solid phase at room temperature, and

have low vapor pressures. Furthermore, organic material such as waxes or greases will not be "seen" by this technique.

A ZrO_2 mat, obtained from Zircar Fibrous Products, was tested and evaluated for its use as a ceramic membrane. Testing involved the evaluation of the mat after 24 hours exposure to the electrolyte at 400°C . Also involved was a full-scale test of the mat in removal cell. Post mortem x-ray diffraction results are discussed.

NO_x removal capabilities were also studied in some depth this quarter. A possible mechanism for the anodic removal is proposed, based on a one electron transfer mechanism. The results of full scale testing and the theoretical diffusion limited current will be compared. Results at this point show excellent fluxes, but poor current utilization based on the present scheme.

Results

A tape cast membrane of 11.1 volume percent "B" (Si_3N_4 of $0.2\mu\text{m}$ particle diameter) was used in a full scale test run. The electrodes used in this run were obtained courtesy E.R.C. Corporation. The interstitial pore size of the resulting "B" membrane would be small enough to prevent flooding of the E.R.C. electrodes. The performance of the E.R.C. electrode in past experiments has suggested that their use in full scale removal systems would be beneficial. The anode side was covered with Pt paint and gold wire was laid length-wise across the electrode in an attempt to ensure non-corroded contact with the housing, and no resistance to current passage from the

housings. The cathode side was well cleaned. Burnout of the polymer binder took place under an oxygen atmosphere, and electrolyte was added to the system after burnout at a temperature of 350° C.

Polarization Performance Run 6 85.3% Removal

ERC electrodes; 90%K₂S₂O₇/10%V₂O₅
 $I = \pm 73\text{mA}$ or 85.3 stoich% removal
 7/12/92

Figure 1: Polarization performance with a 25vol% "B" membrane.

Gas crossover was checked as the temperature reached 400° C, and was found to be substantial, at 5-10 1 cm diameter bubbles per sec in 1 mmH₂O, with a gas flow rate of 220 cc/min. The cell exhibited good polarization characteristics (see Figure 1). Potentials across the cell were also found to be substantial, with an overall cell potential of 2.5 V with an applied current of 73 mA. Removal was found to be poor, around 60% with 100% stoichiometric current applied (see Figure 2), and removal mass balances did not balance. In light of these conditions, the cell was shut down.

SO₂ Removal for Run 6

7/12/92

Figure 2: SO_x removal using a 25vol% "B" membrane.

Post mortem analysis showed the problem to be the non-existent membrane. Evidence suggests that upon burnout, the volume percentage of ceramic in the tape was not high enough to support itself, and dissolved in the electrolyte, allowing the free passage of gas from one side to another. The absence of membrane would explain the effect noticed, and thus, the failure of the cell was attributed to it. The search for a more densely packed membrane, exhibiting, ideally, a small interstitial pore size with a void volume of 50%, continues.

A 25 volume% "B" membrane was constructed. This time, two membranes were placed together, forming a thick green membrane of 0.91 mm thickness. Electrolyte introduction was attempted in a pressed disk of hydroxyethyl cellulose/electrolyte, 80% electrolyte by weight. Fibrex electrodes were used, in an attempt to conserve E.R.C.

electrode material. Gold wire was again used across the electrodes on each side to aid in housing to electrode conduction, with a measured resistance of $0.2\text{--}0.9\Omega$ (25°C) on each side prior to cell start-up.

This run again exhibited a large crossover, rendering the run useless. Additional electrolyte was added in an attempt to alleviate the crossover, to no effect. Power failure to the building necessitated the shutdown of the run. Upon breakdown, it was noted that the electrolyte had not wet the ceramic membrane fully, probably leading to the detected crossover. Resistance measurements showed a housing to electrode resistance of $0.2\text{--}0.8\Omega$ on the cathodic side, and $4\text{--}9\Omega$ on the anodic side. This increase in resistance was startling.

In response to the failure, a run was again attempted with a two 25.9vol% "B" membranes pressed together, with a total thickness of 0.29 mm. Again Fibrex electrodes were utilized, along with gold wire for conduction. The housings were thoroughly cleaned prior to use.

The cell exhibited crossover, with possible leakage out the side. Additional electrolyte was added, and the crossover and leakage problems were eliminated for a very short time. The cell suddenly seemed to "pop," however, as the crossover again started, although cell leakage decreased dramatically. Cell testing continued.

Polarization of the cell showed an excellent response to current (Figure 3), with iR drop showing a linear current response (Figure 4). The limiting polarization is believed to occur due to the formation of sulfate on the surface of the electrolyte/electrode interface, reducing the area available for mass transfer, and thus

Polarization 95cc/min Flue Gas Run 8

$\pm 35\text{mA} \approx 95\text{ stoich\%}$ $T=400\text{C}$
8/12/92 DS

Figure 3: Potential response to current applied to the cell.

increasing the resistance to transport.

This polarization response, corrected for iR , was then graphed as seen in Figure 5. The limiting current occurred at the approximate point of stoichiometric current. This suggested that the system response to current was stoichiometric, but removal remained poor at approximately 45%. Crossover is the probable reason for such poor removal. The limiting potential may have also been caused by diffusion limitations in the gas stream.

Breakdown of the cell showed that only 90% of the membrane was wetted, and gas leakage was suspected to occur in the dry region. Once again, the anodic housing to electrode resistance ($3.5\text{--}5\Omega$) after breakdown was higher than that of the cathode ($<1\Omega$). The gold wire seems to have some effect, as large resistances are not seen, but

Polarization Series Run 8

Flow=89 cc/min, $i(\text{limiting})=35.7\text{mA}$
8/13/92

Figure 4: iR and potential response to applied current.

the problem with increases in resistance on the anodic side still persists. The gold wire fused to the housing to an extent, and was also frozen in electrolyte. electrolyte may have wicked between the gold wire and the electrode. Sulfate formation from the pyrosulfate equilibrium may impede the current path, resulting in a high resistance.

Increasingly, the formation of a lavender color on the anode electrode has been noticed post-mortem. This color is predominate on the electrode in the region where it came into contact with the housing, and was observed to extend onto the housing in areas where the electrode came into contact. This color change may indicate the formation of a chromium (III) sulfate, which is known to exhibit a lavender color¹. Other possibilities include, but are not limited to $\text{CrO}_3 \cdot x\text{H}_2\text{O}$ or Mo_2O_5 . Various other complexes are being researched, including pyrosulfate complexing, vanadium complexes,

Polarization Run 8

$i(\text{limiting}) = 1.819 \text{ mA/cm}^2$
 8/13/92 Flowrate=88 cc/min
 (IR corrected)

Figure 5: iR corrected polarization response of the cell to current applied.

and other metal complexes.

X-ray diffraction performed on an 80wt% electrolyte 20wt% hydroxyethyl cellulose disk after exposure to the atmosphere at 400° C showed the formation of multiple phases, with little to no potassium pyrosulfate detected. Reaction depletion of the pyrosulfate occurred. In addition, electrolyte was dissolved in an 80%/20% ethanol/toluene solution at 25° C. This solution is the solvent used in the polyvinyl binder system discussed in earlier reports. The solution was dried with low heat, and filtered. X-ray diffraction, performed on the resulting solid, showed, again, a reaction had taken place. This result was expected as pervious attempts to use the polyvinyl binder system had resulted in unusable material and membranes.

Future Work

The inability to tape cast a 50% dense membrane with the smaller "B" particles has led to the attempt to sinter such a membrane. Literature suggests that pure Si_3N_4 cannot, in fact, sinter to more than a 50% theoretical density. Usually, additives such as ceria and yttria are used to obtain a 100% dense membrane. Yttria and ceria have been shown by McHenry² to react with the removal system, and thus are not desired. A 50% theoretically dense membrane is desirable in this case. A sintering temperature and rate must be theoretically determined. Theoretically, a thick 2mm membrane will be cast, under a pure N_2 atmosphere, and will then be sanded down to the desired thickness.

Mechanical stability is a major concern, and mechanical and thermal shock to the membrane must be minimized. Preliminary results indicate that a hard, mechanically strong structure can be obtained. It has also been found that Si_3N_4 will react with alumina. At the present time, BN (boron nitride) and Si_3N_4 are being researched as non-reacting systems on which to fire the disk. Further findings will be presented in future reports.

NO_x STUDIES:

Theoretical as well as experimental studies on the removal of NO_x from flue gas have been performed this quarter. The results are promising, although, again, the need for a suitable membrane is crucial to the success of the removal system.

Introduction

Large coal and natural gas reserves in the United States have led to the development of a large coal-based power industry. Various coal and natural gas combustion products, however, have been found to be harmful to both the environment and to humankind. Particularly, the oxides of nitrogen, which can react to form acid rain, are of great concern, and their emission is regulated. Conventional technology for the control of NO_x emissions uses low NO_x burners, which require precise control of air and recycle streams, and has proven to be expensive in the low ppm range. The electrochemical membrane process suggested here is a polishing application, although it has been shown to exhibit excellent removal at higher concentrations.

The control of NO_x emissions has been discussed throughout the industry. There have been two distinct fields of thought developed: one field condones removal after the burning process, and one wants the control of emissions taking place at the burning process. The control of the percentage of air to the burner has been shown to have marked effects upon the level of nitrogen oxides in the flue stream³ The retro-fitting of many burners with low NO_x burners has reduced the emissions through the use of a less turbulent air-fuel mixing zone, reducing the availability of oxygen and reducing NO_x formation. However, as the technology for control of these operations has pushed forward, the cost has increased⁴. In addition, a low- NO_x burner with fuel staging still reduces emissions by only 80%.

Downstream removal of the gas has been traditionally carried out by the selective non-catalytic reduction of ammonia, at temperatures of approximately 870-1100° C⁵. While an 80% reduction may be achievable, the high temperatures involved greatly increase the cost and hazard involved. A selective catalytic reduction method, using a catalyst such as vanadium or platinum, will operate at lower temperatures (375-400° C), but the rapid degradation of the costly catalyst increases the expenses of this process.⁵ Removal is once again on the level of 80% or better.

Electrochemical process have the distinct advantage of the efficient use of energy for the direct removal, transport, or decomposition of products. The upper limit of 35-40% efficiency of Carnot-type cycles is the minimum efficiency for the practical electrochemical cells. The theoretical free energy efficiencies for electrochemical cells is approximately 100%, while free energy efficiencies actually obtained are on the order of 60-80%⁶. Other advantages of the use of electrochemical cells are the virtually non-existent side products from well-developed systems. These include low noise pollution (no mechanical parts excepts for pumps and compressors where needed), little thermal pollution in its efficient energy usage, and a relatively small footprint, electrochemical cells can be used in virtually any environment and under various conditions.

The electrochemical process envisioned contains two stacks of electrochemical cells, each removing 90% of the incoming pollutant (thus 99% removal with two stacks) at a temperature of 400° C. Each stack (see Figure 6) would consist of a series of electrochemical cells, stacked one upon the other separated by bipolar plates and flow channels, much in the same manner as the manufacture of the Molten Carbonate Fuel

Cut-Away of Flow Channels

Figure 6: Model Molten Carbonate Fuel Cell electrochemical stack.

Cell (MCFC). Each electrochemical cell would consist of a ceramic matrix which would be impregnated in situ with electrolyte. Lithiated nickel oxide porous electrodes will be placed on both sides of the electrolytic matrix. Flow channels would be located above each of these electrodes to allow the gas stream to contact the electrolyte through the porous material. A bipolar plate would separate one cell from its two neighbors. Each cell would be approximately 0.53 cm in height, and 1.5 m in width and length (see Figure 6). In the presented process, the gas containing the NO_x flows past the anode, where it is decomposed into oxygen at the anode and nitrogen at the cathode. The captured species is believed to be a vanadium complex, which is transported across the membrane to the cathodic side, where it forms nitrogen, and is removed from the cell by a sweep stream of. The exiting streams are thus virtually NO_x -free.

Theory

The selective removal of NO_x from flue gas can be accomplished through the decomposition of NO_x , and the transport of a vanadium complex across a membrane. The decomposition and resulting transport requires a driving force. This driving force will be electrochemical.

Most membrane processes require a pressure gradient or mass gradient as the driving force for removal such as filtration and osmosis. To accomplish these removals, the process must overcome a chemical potential gradient:

$$\Delta \mu_i = \mu_i - \mu'_i = RT \ln \left(\frac{a_i}{a'_i} \right) \quad (1)$$

where the activities of component i in each phase separated by the membrane is denoted by a_i and a'_i . High pressures are usually required to overcome osmotic or partial pressures, and removal is not necessarily highly selective.

If a species is a strong electron donor or acceptor, it can be preferentially removed through its ionization in electrolyte, and transport through the electrolyte. For a species with a net charge z_i , and a potential difference across the membrane of $\Delta \Phi$, the driving force must exceed the electrochemical potential:

$$\Delta \bar{\mu}_i = \bar{\mu}_i - \bar{\mu}'_i = RT \ln \left(\frac{a_i}{a'_i} \right) + z_i F \Delta \Phi \quad (2)$$

Using an electrochemical process, a highly selective and energy efficient removal can be accomplished with virtually no side effects.

The NO_x present can act as a strong Lewis base in our system. The reaction is believed to follow the proposed pathway:

NO_2 present in the system can be converted to NO as seen in Equation (3)⁷.

Bontempelli⁸ studied the effects of nitrogen oxide oxidation in concentrated sulfuric acid. He suggests NO from the gas stream can be oxidized through current

As NO is consumed through Equation (4), the partial pressure of O₂ increases, increasing the solubility of O₂ in the electrolyte, but limiting the extent of equilibrium in Equation (3). While the exact transport mechanism is not known, the solvated NO⁺ could then complex with vanadium present in the molten pyrosulfate as alluded by Franke⁹ and McHenry¹⁰:

The alternate to this type of complexing is the formation of a peroxide species in the melt. Many authors^{11,12,13,14,15} have suggest the presence of peroxide at high temperatures, and the complex reaction may be as seen in Equation (6):

If Equation (6) is the method of complexing, NO⁺ would become the species migrating to the cathode interface, where it could form the peroxide. The peroxide would then transport back to the anode. The complex formed would remain at the cathode, where

reduction would occur. This reaction, however, would require additional current for the complete system reaction. Because the extent of this possibility is unknown, this reaction will not be considered in the overall evaluation.

The complex formed in Equation (5) is then transported across the cell to the cathode, where it can take place in the chemical reduction of the species as seen in Equation (7)

where the gaseous N_2 diffuses into the cathodic sweep stream for transport out of the cell.

The overall cell reaction, a one electron transfer redox reaction, is then found by the addition of Equations (4), (5), and (7) to be:

the decomposition of nitrogen monoxide at 400° C, where the gibbs free energy of formation was determined from JANAF¹⁶ tables.

To produce decomposition in this cell, the ability of the current supplied to force the desired reactions must be maximized. While increasing the contact time of the species to be decomposed will allow a higher percentage of removal, some optimum must be achieved between the contact time, the current efficiency, and most importantly, the cost.

To determine the limit of the electrochemical decomposition, the limit of each removal step must be examined. These steps are as follows:

1. transport of NO_x from the bulk stream to the gas/electrolyte interface;
2. electrolysis of electrolyte to form the transporting species at the anode;
3. ionic transport across the membrane;
4. electrolysis of the transporting species to cathodic product species;
5. transport of cathodic product species to the gas sweep stream.

The development of a system for the removal of NO_x must make assumptions to determine the best available removal. The major assumption is that, at steady-state with efficient current usage, steps 2 through 5 are not limiting. The limiting step in the system is therefore the ability of the NO_x to transport from the gas stream to the gas/electrolyte interface for the reactions to occur.

The main mechanism for transport of the gas-phase species to the gas/electrolyte interface, in a laminar system, is the ability of the species to diffuse through the transporting medium, assumed to be primarily nitrogen.

Gas phase diffusivity has been fairly well defined through the use of molecular models. Welty, Wicks and Wilson¹⁷ suggest Equation (9) for non-polar, non-reacting molecules,

$$D_{AB} = \frac{0.001858 T^{\frac{3}{2}} \left[\frac{1}{M_A} + \frac{1}{M_B} \right]^{\frac{1}{2}}}{P \sigma_{AB}^2 \Omega_D} \quad (9)$$

where D_{AB} is the mass diffusivity of A through B in cm^2/sec ; T is the absolute temperature in degrees Kelvin; M_i is the molecular weight of component i ; P is the absolute pressure in atmospheres; σ_{AB} is the Leonard-Jones collision diameter in Angstroms, and Ω_D is the collision integral, a function of Leonard-Jones parameters and the temperature. At 400°C , the diffusivity of NO (A) through N_2 (B) is $0.8336 \text{ cm}^2/\text{sec}$.

This diffusivity can then be related to a mass transfer coefficient (k_m) through the Nusselt number (N_{Nu}), for a given hydraulic diameter as seen in Equation (10)

$$N_{Nu} = \frac{k_m D_h}{D_{AB}} \quad (10)$$

where D_h is the hydraulic diameter as defined by Incropera and Dewitt¹⁸. Incropera and Dewitt also suggest a Nusselt number in laminar flow for given aspect ratios. For an aspect ratio (height of channel to length of channel) of a square channel, the Nusselt number was determined to be 2.98. By application of this to a system in which there is a zero concentration of A at one surface (infinite mass flux at the surface), and an infinite flux through the membrane separating the two sides, we can determine the diffusion limited current density (i_d) needed to provide for the transport for given concentrations through Equation (11)

$$i_d = nFk_m \rho_{molar} \Delta x_{lm} \quad (11)$$

where n is equivalents/mol; F is Faraday's constant, ρ_{molar} is the molar density, a function of temperature in the gas phase; and Δx_{lm} is the log-mean mole fraction difference. This diffusional current density represents the best possible removal for a given system geometry at set system parameters. It does not take into account the effects of transport at any other point in the system. While achievement of the diffusional current density is very possible, initial testing of systems, in general, will fail to yield the high fluxes predicted from a diffusion limited transfer.

In addition, the equilibrium potential of the system can be predicted through the Nernst Equation (Equation (12)).

$$E_e = E_o - \frac{RT}{nF} \ln \left(\frac{a_{products}}{a_{reactants}} \right) \quad (12)$$

where a is the activity of the species involved in the reaction. The activity of gaseous species can be approximated as their partial pressures in atmospheres, and the standard potential can be determined from Equation (13).

$$E_o = \frac{-\Delta G_f}{zF} \quad (13)$$

where z is charge; in this case equal to +1. The gibbs free energy of formation has already been determined to be -81.904kJ/mol based on Equation (8). E_o is then 0.849V. Taking these factors into account, Equation (12) at 400° C becomes:

where p_i is the partial pressure of component i in atmospheres. For a given system configuration, and known partial pressures, the potential and current required for a

$$E_e = 0.849V - 0.058V \ln \left(\frac{p_{O_2}^{\frac{1}{2}} p_{N_2}^{\frac{1}{2}}}{p_{NO}} \right) \quad (14)$$

known separation can be calculated. Due to the inefficiency of current in testing up to this point (see Results section), the total cell voltage will be assumed to be 1V under ideal conditions. This voltage should be attainable for an understood system.

Results

The modeling cell consists of two 316L stainless steel housings with flow channels and electrode supports bored in. These housings are separated by a ceramic matrix, which holds the electrolyte in situ (see Figure 7). Solid electrolyte is incorporated into the cell initially, but melts to flood the ceramic matrix and wet the porous electrodes upon reaching its melting temperature of approximately 325° C.

The electrode used are porous Lithiated NiO. Porous Fibrex Ni sheets have been obtained courtesy National-Standard. Lithiation and oxidation occurs prior to usage in the cell, creating a p-type semiconductor. Conductivity measurements at room temperature yield a resistivity of less than 1Ω, and generally on the order of 0.2 Ω.

The electrolyte is 99.8% pure potassium pyrosulfate ($K_2S_2O_7$) with vanadium pentoxide (V_2O_5) in a 90% $K_2S_2O_7$ /10% V_2O_5 mixture by weight. The exact melting point of this mixture is a function of the bisulfate formation in the pyrosulfate i.e. the extent of contact with water vapor. These bisulfates, while reducing the melting point, will decompose into pyrosulfate upon melting in a predominately pyrosulfate environment.

Figure 7: Full scale testing housing and geometry.

NO_x Removal by McHenry

Figure 8: Electrochemical removal of NO_x from flue gas achieved by D.J. McHenry.

90% removal of NO_x from gas streams at 400°C has been accomplished by McHenry¹⁹ in a full cell test model. The electrolyte used was $\text{K}_2\text{S}_2\text{O}_7/\text{V}_2\text{O}_5$ in a 90/10 respective weight ratio. Inlet levels of NO_x were 850ppm in N_2 . Removal achieved a level of 75ppm NO_x (see Figure 8) with a corresponding current density of $25\text{mA}/\text{cm}^2$. The ceramic matrix was made of Si_3N_4 particles of $2\mu\text{m}$ diameter obtained courtesy Phillips Petroleum.

In addition, testing of the removal ability was performed with the use of a ZrO_2 membrane obtained from Zircar Fibrous Ceramics Company. This removal was attempted with higher flow rates, and yielded excellent removal (see Figure 9). While removal was not as high on a percentage basis, the flux achieved with lower current densities was as good as or better than those achieved by McHenry. Table I shows the fluxes achieved are not as high as those predicted by the diffusion limited current for the system, but show excellent results, nonetheless. The cell test with the ZrO

NO_x Removal ZrO₂ Membrane

Figure 9: Removal with the use of the ZrO₂ membrane.

2 membrane in fact achieved an excellent flux. Because this last flux is so close to that of the diffusion limiting case, the diffusion limited current will be used to predict the various aspects of the stack envisioned for the process.

Experimental current efficiency for these experiments was on the order of 10% for a one electron process, where one electron removes one molecule of NO. This low efficiency could indicate a more complex mechanism than proposed (see Theory). It could also be an indication of more electron usage per molecule transferred. The exact number of electrons need for the transfer mechanism has not been determined.

By considering Equation (8), a cause of the less-than-ideal removal of the system may be the fact that the sweep stream that has been used to this point is N₂. The high pressure of

nitrogen may force the overall

reaction in the reverse direction to an extent, requiring higher currents and overpotentials to achieve the desired removal.

In the same

Table I: Comparison of achieved and diffusion limited fluxes.

Run Type, membrane	Removal, ppm	Flux, mol/cm ² /sec	Diffusion limited flux, mol/cm ² /sec
McHenry, Si ₃ N ₄ (Case 3)	850 to 568	2.000×10^{-9}	2.551×10^{-7}
McHenry, Si ₃ N ₄ (Case 2)	850 to 74	5.921×10^{-9}	1.159×10^{-7}
Present, ZrO ₂ (Case 1)	865 to 308	6.079×10^{-9}	9.834×10^{-9}

respect, any O_2 produced in Equation (3) will also decrease the removal at a given current, by, once again, forcing Equation (8) to the left.

References:

1. Hodgman, C.D., handbook of Chemistry and Physics, 42nd Edition, 1960-1961, Chemical Rubber Company, Cleveland, 1960.
2. McHenry, D.J., personal communication.
3. Wark, Kenneth and Warner, Cecil, Air Pollution, It's Origin and Control, 2nd Ed., Harper Collins, New York, 1981, p. 391.
4. More, Taylor, "The Retrofit Challenge in NO_x Control," EPRI Journal, November 1984, p.26-33.
5. Makansi, Jason, "Reducing NO_x Emissions," Special Report, Power, September, 1988, p.s1-s13.
6. Appleby, A.J., and Foulkes, J.R., Fuel Cell Handbook, Van Nostrand Reinhold, New York, 1989, p.28.
7. Wark, K., and Warner, C.F., Air Pollution: Its Origin and Control, 2nd ed., harper Collins, New York, 1981, p.377.
8. Bontempelli, Gino, *et. al.*, "Electrode Processes of Oxygenated Nitrogen Compounds in Acetonitrile Medium," Electroanalytical Chemistry and Interfacial Electrochemistry, 55 (1974) 91-100.
9. Franke, M.D., Electrochemical Flue Gas Clean-Up, Ph.D. Thesis, Georgia Institute of Technology, 1988.
10. McHenry, D.J., Development of an Electrochemical Membrane Process for Removal of SO_x/NO_x from Flue Gas, Ph.D. Thesis, Georgia Institute of Technology, 1992.
11. Il'ya Ivanovich Vol'nov, Peroxides, Superoxides, and Ozonides of Alkali and Alkaline Earth Metals, Plenum Press, New York, 1966.
12. Pati, S., The Chemistry of Peroxides, John Wiley and Sons, New York, 1983.
13. Striebal, K.A., "Oxygen Reduction on Pt in Aqueous K₂CO₃ and KOH," Journal of the Electrochemical Society, 137, 3351, (1990).
14. Makkus, R.C., Hemmes, K., and de Witt, J.H.W., "Impedance Measurements on Oxygen Reduction Reaction in Molten Carbonate," International Journal of Physical Chemistry, 94, 960, (1990).
15. Fischer, P., and Heitbaum, J., "Mechanistic Aspects of Cathodic Oxygen Reduction," Journal of Electroanalytical Chemistry, 112, 231, (1980).

16. Chase, Davies, Downey, Frurip, McDonald, Syverud, IANAFT thermochemical tables, 3rd Edition, US Secretary of Commerce, 1986.
17. Welty, J.R., Wicks, C.E., Wilson, R.E., Fundamentals of Momentum, Heat and Mass Transfer, 3rd Ed., John Wiley and Sons, New York, 1984, p.487.
18. Incropera, F.D. and DeWitt, D.P., Fundamentals of Heat and Mass Transfer, 2nd Ed., Wiley, New York, 1987, p.398.
19. McHenry, D.J., Development of an Electrochemical Membrane Process for Removal of SO₂/NO_x from Flue Gas, Ph.D. Thesis, Georgia Institute of Technology, March 1989, p. 237.

II. H₂S Removal Cell

Introduction

This electrochemical cell purges a fuel gas contaminated with H₂S. This is done by reducing the best lewis acid in the gas stream. In this case H₂S is electronated by the following:

A membrane which contains sulfide ions in a molten salt electrolyte will act to transport the sulfide ions across to the anode. If the membrane is impermeable to H₂ diffusion from the cathode side, an inert sweep gas can be used to carry the vaporous oxidized sulfur away to be condensed later.

Research Summary

New experiments are being done using a Zircar Manufactured membrane for removal of H₂S from a fuel gas stream. The manufactured membrane is advantageous due to the lack of warping and uniform porosity. This allows equal migration of sulfide ions throughout which in turn gives a uniform current density. Both stainless steel and MACOR cell housings have been used with promising results. Although no removal was seen with the stainless steel housings (run #1), the seals lasted strongly throughout, holding back pressures up to 30 mm H₂O. Over 90% removal with applied current was shown using the MACOR housings, even at high flow rates (200 cc/min - 800 cc/min)(run #5). Another alternative membrane was produced in our laboratory which

was used with the MACOR housings (run #4). Over 90% removal of H_2S with applied current was also recorded with this membrane, but using low flow rates (200 cc/min). All runs operated at 650°C . Work has continued with an attempt to focus on sealing the housing for more accurate removal data.

A. Experimental Run Results

Run #4

A self-produced rigid Zirconia mat worked in this experiment. The mat began as a weave of zirconia cloth, then hardened with the zirconia rigidizer. All other equipment remained the same as runs 2 - 5. The temperature and flow rate were maintained at 650°C and 215 cc/min respectively. Inlet concentration was held between 6 and 20 ppm H_2S . As much as 94% removal with applied current was seen in this experiment as shown. Exit H_2S and applied current vs potential difference (cathode to anode) are shown in figures 1 & 2. The results of both run 4 & 5 are tabulated in Table 1. The experiment was shut down due to hydrogen cross-over. Run #4 lasted 163 hours.

Figure 1

Run #5

A manufactured Zircar membrane provided the medium for electrolyte support. The membrane is advantageous, due to uniform porosity (66%) and no warping. The flow rates varied (200 cc/min - 800 cc/min), temperature remaining constant (650° C). Removals over 90% were recorded with applied current. Exit H₂S and applied current vs cross-cell potential (cathode-anode) are shown in figures 3 & 4. The cell was shut down after 208 hours, due to an increase in membrane thickness, limiting sulfide migration.

Figure 3

Figure 4

Table I. Experimental Results for Runs #4 & #5

Temp. (°C)	Flow-Rate (cc/min)	Residence Time (sec.)	Inlet H ₂ S (ppm)	Exit H ₂ S (@ I _{app})	I _{app} (mA)	E _{c-a} (Volts)
650	170	0.197	25	1	1	-0.190
	225	0.146	8.5	1	2	-0.013
	375	0.089	22	1	2	-0.003
	580	0.058	20	1	5	-0.047
	814	0.041	22	1	5	-0.199

Run #1

Stainless steel housings were used to test resilience. Seals were formed from painting the housings with Al paint (29% Al). The housings were then baked in an oxygen atmosphere to form alumina, later forming a seal in-situ by reacting with Li in the electrolyte to form LiAlO_2 . This run was successful in sealing the housings which was shown by holding up under back pressures as high as 30 mm H_2O . No effective removal data was taken from this run, but the experiment lasted for 453 hrs, keeping strong seals throughout.

Run #2 - #3

These experiments are combined due to the usage of the same type Zircar manufactured membrane for both. Lithiated Ni were used as electrodes and aluminum paint was applied to the MACOR housings for sealant. The electrolyte was a prepressed disk.

Run #2 lasted only 48 hrs due to carbon build up between the cathode electrode and the membrane. This was caused by the bourdouart reaction, avoidable by increased hydration of the fuel gas.

Run #3 lasted only 24 hrs due to the cracking of the membrane and lack of seals. There was no outflow of gas.

Summary

Polishing of 10 ppm hydrogen sulfide to ~1 ppm has been demonstrated this quarter with varying flow rates. Hydrogen cross-over has been slowed but not completely cured, although the Zircar manufactured membranes sustained runs for several weeks. Sealing the cell housings presents the biggest challenge in the upcoming quarter in order to maintain adequate data collection.

Planned work for Next Quarter

Work will continue with improving seals as well as working with the Zircar manufactured membranes, but producing our own membranes (Run #4) is becoming more important due to economic reasons. Both Stainless steel and MACOR housings will be used in the next quarter.

References

1. Weaver, D., Electrochemical Removal of Hydrogen Sulfide from Multi-Component Gas Streams, PhD Thesis, Georgia Institute of Technology, 1988.
2. Alexander, S., Electrochemical Removal of H₂S from Fuel Gas Streams, PhD Thesis, Georgia Institute of Technology, 1992.

**DATE
FILMED**

2 / 17 / 93