2
WSRC-RP-92-1078

STATISTICAL ANALYSIS OF DWPF REFERENCE CANISTER DIMENSIONS (U)

by M. A. Pickett

WSRC-RP--92-1078

Westinghouse Savannah River Company
Savannah River Site
Aiken, South Carolina 29808

DE93 006323

Other Authors:

K. G. Brown
(WSRC)

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

This paper was prepared in connection with work done under Contract No. DE-AC09-89SR18035 with the U. S. Department of Energy. By acceptance of this paper, the publisher and/or recipient acknowledges the U. S. Government's right to retain a nonexclusive, royalty-free license in and to any copyright covering this paper, along with the right to reproduce and to authorize others to reproduce all or part of the copyrighted paper.

MASTER

2
DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

Keywords: DWPF, canister,
dimensions

cc: E. W. Holtzscheiter, 773-A
C. T. Randall, 704-1T
C. M. Jantzen, 773-A
J. R. Harbour, 773-43A
A. A. Ramsey, 704-15S
S. L. Marra, 704-15S

SRL Records (4)

September 10, 1992

TO: M. J. Plodinec, 773-A

FROM: M. A. Pickett, 704-1T
K. G. Brown, 704-1T

Statistical Analysis of DWPF Reference Canister Dimensions (U)

Introduction and Summary

Twenty dimensional measurements were conducted on seven empty Defense Waste Processing Facility (DWPF) reference canisters. These measurements were repeated after the canisters were filled with simulated nuclear waste glass. An in-depth statistical analysis of the results indicated that changes do occur as a result of filling the steel canisters with glass poured at 1150°C for four of the parameters. While small, these changes were *statistically* significant.

The analysis indicates the maximum dimensional change found to occur after the filling for each variable. Statistical tests were used to determine if canister dimensions do significantly change, and corresponding variance information is presented.

The results showed that the four measured parameters affected by filling are bottom diameter, bottom end diameter, flange tilt, and lower head mismatch. Significant variability also existed for height, upper weld, ID label, lower head mismatch, and lower head ovality due to the measurements coming from different canisters. Finally, lower head mismatch showed variability caused by the data being taken at different locations on the canister. This location effect did not affect any of the other variables in this way.

C. T. Randall
Authorized Derivative Classifier

Background

The seven containers in this study are prototypic DWPF canisters intended for storage of nuclear waste glass. These measurements are being performed to insure that canisters will comply with the dimensional requirements set forth by the Waste Acceptance Preliminary Specifications¹ and thus will fit inside their respective storage areas. The measurements were performed at the SRS pilot plant facility.² The canisters were first measured empty and then filled and remeasured. The variables for canister bow and head mismatch were measured using a transit device, diameter measurements were obtained with micrometers, and thickness measurements were obtained using an ultrasonic thickness gage.³ Appendix 1 contains a diagram detailing measurement locations. The measurement data⁴ for both before and after filling of the canisters can be found in Appendix 2. Because both before filling and after filling measurements are taken from the same radial position on a given canister, these observations are paired.

Results and Discussion

Histograms showed most of the data for these parameters were normally distributed. The lack of normality in some histograms was probably due to the smallish number of data points, i.e., between 7 and 28 measurements.

Maximum Changes in Canister Dimensions

All canister dimensions were measured in inches, except for flange tilt which was measured in degrees. The maximum change in measurements (as a result of filling) was calculated over all paired observations for each variable.⁵ These numbers were based on individual measurements (not averages of the replicate observations). Maximum change due to filling for each variable, number of paired observations (n), means of all changes, and their respective standard deviations are reported in Table 1.

¹ "Waste Acceptance Preliminary Specifications for the Defense Waste Processing Facility High Level Waste Form", Revision 1, April, 1998.

² "DWPF Waste Form Compliance Plan", WSRC-IM-91-116-0, Revision 1, p. 3.

³ S. L. Goudelock, "Summary of Post-filling Operations for DWPF Reference Drop Test Canisters", WSRC-RP-89-510, June 29, 1989, p. 4.

⁴ Ibid., pp.17,19.

⁵ There is no maximum difference value for the following variables: nozzle flange thickness, nozzle sleeve ID, nozzle sleeve depth, plug top diameter, plug bottom diameter, plug depth, and cold protrusion due to the lack of data for the variables after filling.

Table 1
Maximum Observed Value, Means, and Standard Deviations of Differences

Variable	Maximum Change	n	Mean Difference	Standard Deviation
Height	0.0938	28	0.0050	0.0330
Upper weld	-0.0625	7	-0.0089	0.0236
ID label	0.1250	7	0.0179	0.0472
Nozzle	0.0141	7	0.0156	0.0571
Top end diameter	0.1060	12	0.0140	0.0664
Top diameter	-0.0530	12	-0.0021	0.0206
Middle diameter	0.0570	12	0.0105	0.0260
Bottom diameter	0.0600	12	0.0168	0.0243
Bottom end diameter	0.1610	12	0.0445	0.0618
Flange diameter nozzle	0.0050	7	0.0007	0.0029
Flange tilt	-0.7800	7	-0.3186	0.2558
Upper head mismatch	0.1094	28	0.0379	0.0478
Lower head mismatch	0.0781	28	0.0234	0.0280
Bow middle	0.1562	28	0.0017	0.0596
Bow top	-0.1875	28	0.0116	0.0697
Upper head oval	-0.1200	6	-0.0313	0.0501
Top ovality	-0.0720	6	-0.0208	0.0282
Middle ovality	-0.0690	6	-0.0090	0.0440
Bottom ovality	-0.0510	6	-0.0247	0.0266
Lower head ovality	-0.0740	6	-0.0240	0.0294

F-test for the Statistical Significance in Canister Dimensions

F-tests were done to determine whether the after value was significantly different from the before value for a given parameter.⁶ The F-test is obtained from the analysis of variance (ANOVA) based on the number of effects. ANOVA procedures are used when there are different effects or treatments done to a given set of data, and one wishes to see the difference between the results of those various treatments as well as the overall significance due to all effects.

Filling, radial position, and canister identity are the 3 factors that may contribute significantly to the change in canister dimensions.⁷ The ANOVA for a 3-factor experiment tests the hypothesis that the mean of the observations before minus the mean after equals zero ($\mu_1 - \mu_2 = 0$). SAS PROC ANOVA® and SAS PROC GLM® for unbalanced tests were used to assess the effects each of the 3 factors had upon changes in canister dimensions.

⁶ Since there was more than one effect (i.e., filling), paired t-tests were not used. F-tests are better suited for such types of data because of the added ability to discern where the variability came from.

⁷ In the case of only one measurement per can, there are only 2 factors: filling and canister.

Table 2
ANOVA to test $\mu_1 = \mu_2$

Variable	F-test	Standard Deviation	F-statistic at 5%
Height	5.52	0.0383	2.0524
Upper weld	23.86	0.0167	4.2066
ID label	29.57	0.0334	4.2066
Nozzle	2.81	0.0403	4.2066
Top end diameter	1.01	0.0407	2.5480
Top diameter	0.89	0.0139	2.5480
Middle diameter	0.58	0.0190	2.5480
Bottom diameter	1.78	0.0155	2.5480
Bottom end diameter	2.69	0.0399	2.5480
Flange diameter nozzle	0.71	0.0020	4.2066
Flange tilt	4.43	0.1809	4.2066
Upper head mismatch	0.57	0.0864	2.0524
Lower head mismatch	5.06	0.0197	2.0524
Bow middle	0.99	0.0647	2.0524
Bow top	0.14	0.0841	2.0524
Upper head ovality	1.25	0.0354	4.8759
Top ovality	1.16	0.0200	4.8759
Middle ovality	0.75	0.0311	4.8759
Bottom ovality	1.41	0.0188	4.8759
Lower head ovality	4.52	0.0208	4.8759

In Table 2, the standard deviation is the root mean square error obtained from SAS®. The F-statistics for six of the parameters in Table 2 were significant and therefore failed the null hypothesis at the 95% significance level. F-statistics shaded in Table 2 are those that have failed this test; the corresponding variables have significant differences in the observations. Statistical significance of the contributing effects is examined in the next section.

Statistical Significance of Contributing Effects

Table 3 shows the significance of the individual effects of canister, radial position, and filling. These F-statistics, as judged against F-values from statistical tables, indicate whether the observed change is due to filling, location, and/or canister effects.

Table 3
Significance of component effects on canister differences

Variable	F-test for Canister effect	F-test for Location effect	F-test for Filling effect
Height	8.52	1.28	0.24
Upper weld	27.67		1.00
ID label	34.33		1.00
Nozzle	3.19		0.53
Top end diameter	1.23	0.03	0.71
Top diameter	0.45	4.24	0.13
Middle diameter	0.37	0.60	1.83
Bottom diameter	0.66	3.22	7.06
Bottom end diameter	2.32	0.10	7.48
Flange diameter nozzle	0.76		0.43
Flange tilt	3.36		10.85
Upper head mismatch	0.21	0.56	2.70
Lower head mismatch	3.22	3.85	19.78
Bow middle	0.17	2.94	0.01
Bow top	0.06	0.24	0.27
Upper head ovality	0.94		3.10
Top ovality	0.53		4.90
Middle ovality	0.85		0.16
Bottom ovality	0.73		5.52
Lower head ovality	5.20		0.43

If the effect from either canister, location, or filling is greater than its corresponding F-statistic at the 95% confidence limit, $F_{0.95}(v_1, v_2)$, then it can be said that this effect has a significant contribution. Those F-statistics shaded in Table 3 indicate the effects that are significant for specific variables. Because the general F-test done previously examines the overall effect while Table 3 shows a closer look at the individual contributory effects, some variables have effects which are significant in Table 3 which did not show significance in Table 2.

Standard Deviations of Significant Contributory Effects

The standard deviations are calculated (Table 4) for the error associated with individual effects (canister, location and filling) using SAS PROC VARCOMP®. Table 4 shows the unbiased estimators of variance for canister, location and filling effects. Overall standard deviation was shown previously in Table 2. Negative variances are indicative of very small errors, and they correspond to those effects with small F-statistics in Table 3.

Table 4
Unbiased Variance Component Estimators for All Effects

Variable	Canister	Location	Filling
<u>Height</u>	0.0014	0.0000	0.0000
<u>Upper weld</u>	0.0037		0.0000
<u>ID label</u>	0.0186		0.0000
<u>Nozzle</u>	0.0018		-0.0001
<u>Top end diameter</u>	0.0001	-0.0001	0.0000
<u>Top diameter</u>	0.0000	0.0000	0.0000
<u>Middle diameter</u>	-0.0001	0.0000	0.0000
<u>Bottom diameter</u>	0.0000	0.0000	0.0001
<u>Bottom end diameter</u>	0.0005	-0.0001	0.0009
<u>Flange diameter nozzle</u>	0.0000		0.0000
<u>Flange tilt</u>	0.0387		0.0461
<u>Upper head mismatch</u>	-0.0007	-0.0002	0.0005
<u>Lower head mismatch</u>	0.0001	0.0001	0.0003
<u>Bow middle</u>	-0.0004	0.0006	-0.0001
<u>Bow top</u>	-0.0008	-0.0004	-0.0002
<u>Upper head ovality</u>	0.0000		0.0004
<u>Top ovality</u>	-0.0001		0.0002
<u>Middle ovality</u>	-0.0001		-0.0001
<u>Bottom ovality</u>	-0.0001		0.0002
<u>Lower head ovality</u>	0.0010		-0.0001

Conclusions

The results show that the four measured parameters that change due to filling the canisters are bottom diameter, bottom end diameter, flange tilt, and lower head mismatch. Canister difference had a significant effect upon height, upper weld, ID label, lower head mismatch, and lower head ovality, while filling significantly affected canister dimensions for lower head mismatch only (Table 2).

Appendix 1
Canister Dimension Locations

Figure 1. Components and Dimensions of a Reference DWPF Canister⁸

⁸ Goudelock, S. L. "Summary of Post-Filling Operations for DWPF Reference Drop Test Canisters," WSRC-RP-89-510, June 29, 1989, p. 16.

Appendix 2
Canister Dimension Information

Pre-filling dimensions

	A-19	A-29	A-38	A-23	A-31	A-28	A-39
Height							
1	118.046875	117.9375	118	117.9375	117.9375	117.875	118
2	117.9375	118	118	118	118.046875	117.78125	117.96875
3	118.0625	118	117.984375	118	118	117.96875	118
4	118.0625	117.875	117.9375	118	117.96875	117.90625	118
Upper Weld	103.875	103.75	103.875	103.875	103.8125	103.75	103.875
ID Label	93.75	93.375	93.875	93.75	93.625	93.75	93.75
Nozzle	9.236875	9.484375	9.515625	9.5	9.5	9.4375	9.5
DIAMETERS							
Top End							
1	23.898		23.897	24.001	24.004	23.998	24.002
2	23.887		23.893	24.007	24.013	23.897	24.008
Top							
1	24.005		24.017	24.018	24.027	24.036	24.029
2	24.016		24.022	24.026	24.011	24.03	24.015
Middle							
1	24.019		24.028	24.015	24.01	24.034	24.038
2	24.023		24.039	24.022	24.017	24.028	24.027
Bottom							
1	24.023		24.01	24.012	24.021	24.028	24.026
2	24.011		24.007	24.014	24.028	24.029	24.017
Bottom end							
1	23.894		23.893	23.996	24	24.009	24.006
2	23.898		23.884	24.004	24.002	24.011	24.004
NOZZLE							
Flange Diameter	9.124	9.119	9.121	9.124	9.124	9.126	9.125
Flange thickness	1.999	2	2.002	2.007	2.009	2	2.001
Sleeve I.D. (top)	4.627	4.622	4.637	4.623	4.621	4.627	4.625
Sleeve Depth	2.127	2.006	2.123	2.129	2.127	2.12	2.126
PLUG							
Top diameter	4.6442	4.645	4.6443	4.6441	4.6444	4.6442	4.6442
Bottom diameter	4.506	4.503	4.508	4.507	4.507	4.507	4.508
Depth	2.068	2.063	2.066	2.069	2.067	2.069	2.065
Cold protrusion	0.248	0.251	0.245	0.247	0.251	0.248	0.245
Flange tilt (deg)	0.78	0.78	0.39	0.39	0.68	1.17	0.2
Upper Head Mismatch							
1	0.03125	-0.140625	-0.046875	-0.125	-0.03125	-0.09375	-0.171875
2	-0.09375	-0.046875	-0.1875	-0.3125	-0.15625	0.03125	-0.171875
3	-0.125	-0.0625	-0.15625	-0.0625	-0.1875	-0.15625	-0.015625
4	-0.0625	-0.1875	-0.140625	0.046875	-0.015625	-0.1875	-0.125
Lower Head Mismatch							
1	-0.03125	-0.03125	-0.03125	-0.0625	-0.0625	-0.0625	-0.0625
2	-0.03125	-0.015625	-0.0625	-0.09375	-0.0625	-0.0625	-0.0625
3	-0.0625	-0.0625	-0.046875	-0.046875	-0.078125	-0.0625	-0.078125
4	-0.046875	0	-0.0625	-0.0625	-0.0625	-0.078125	-0.078125
Bow (Middle)							
1	0.03125	-0.03125	0.03125	0	0.046875	0.0625	-0.0625
2	-0.03125	-0.03125	-0.0625	-0.125	-0.046875	0.046875	-0.0625
3	-0.0625	0.0625	-0.03125	0.0625	-0.015625	-0.03125	0.0625
4	0.0625	0.015625	0.09375	0.078125	0.0625	-0.046875	0.0625
Bow (Top)							
1	0.0625	-0.09375	0.015625	-0.0625	0.03125	0.03125	-0.0625
2	-0.03125	0.03125	-0.125	-0.15625	0.09375	0.09375	-0.09375
3	-0.0625	0.03125	-0.09375	0.03125	-0.109375	-0.125	0.046875
4	-0.03125	-0.09375	0.046875	0.046875	0.03125	-0.140625	0.03125
OVALITY							
Upper Head	0.011		0.004	-0.006	-0.009	0.101	-0.006
Top	-0.011		-0.005	-0.008	0.016	0.006	0.014
Middle	-0.004		-0.011	-0.007	-0.007	0.006	0.011
Bottom	0.012		0.003	-0.002	-0.007	-0.001	0.009
Lower Head	-0.004		0.009	-0.008	-0.002	-0.002	0.002

Post-filling Dimensions

	A-19	A-29	A-38	A-23	A-31	A-28	A-39
Height							
1	118.0313	117.9375	118	117.96875	117.96875	117.9375	118
2	118	118	118	118	118	117.875	118
3	118.0625	117.9688	117.9375	117.96875	118	117.9375	118
4	118.0313	117.9063	117.9375	118	117.96875	117.9375	118
Upper Weld	103.875	103.75	103.875	103.875	103.75	103.75	103.875
ID Label	93.75	93.5	93.875	93.75	93.625	93.75	93.75
Nozzle	9.4375	9.5	9.5	9.5	9.46875	9.4375	9.5
DIAMETERS							
Top End							
1	23.997	23.952	23.975	23.959	23.964	23.956	23.939
2	23.993	23.991	23.966	23.978	23.965	23.975	24.006
Top							
1	24.017	24.003	24.023	24.019	24.015	24.007	23.976
2	24.022	24.048	24.028	24.035	24.025	24.026	24.034
Middle							
1	24.021	24.038	24.001	24.042	24.067	24.046	24.003
2	24.023	24.035	24.081	24.022	24.037	24.034	24.049
Bottom							
1	24.022	24.034	24.032	24.038	24.04	24.002	24.013
2	24.019	24.056	24.067	24.057	24.03	24.053	24.055
Bottom end							
1	23.997	24.09	24.019	23.991	24.004	23.986	23.996
2	23.996	24	24.045	24.025	24.001	24.062	24.013
NOZZLE							
Flange Diameter	9.125	9.123	9.126	9.124	9.123	9.123	9.124
Flange thickness							
Sleeve I.D. (top)							
Sleeve Depth							
PLUG							
Top diameter							
Bottom diameter							
Depth							
Cold protrusion							
Flange tilt (deg)	0.39	0.59	0.39	0.2	0.2	0.39	0
Upper Head Mismatch							
1	0.0625	-0.15625	0.03125	-0.09375	-0.03125	-0.0625	-0.1875
2	-0.046875	-0.03125	-0.09375	-0.21875	-0.109375	0.03125	-0.109375
3	-0.125	0	-0.109375	-0.125	-0.125	-0.0625	0.015625
4	-0.15625	-0.09375	-0.03125	0.125	0.03125	-0.125	-0.09375
Lower Head Mismatch							
1	-0.046875	-0.03125	0	0	-0.03125	-0.03125	-0.03125
2	-0.03125	-0.015625	0	-0.03125	0	-0.03125	-0.03125
3	-0.0313	-0.078125	-0.03125	-0.03125	-0.0625	-0.09375	-0.0625
4	-0.046875	-0.015625	0.015625	-0.03125	0	-0.0625	-0.0625
Bow (middle)							
1	0.03125	-0.03125	0.0625	0	-0.015625	0.046875	-0.109375
2	0.046875	0.125	-0.03125	-0.140625	-0.09375	0	-0.015625
3	-0.03125	0.046875	-0.015625	0.046875	0.0625	-0.125	0.0625
4	-0.078125	-0.015625	0.0625	0.15625	0.09375	0.015625	0.03125
Bow (top)							
1	0.125	-0.09375	0.0625	-0.03125	-0.046875	0.08375	-0.09375
2	-0.015625	0.0625	-0.03125	-0.171875	-0.09375	0.09375	-0.03125
3	-0.046875	0.03125	-0.03125	0.03125	-0.03125	-0.140625	0.09375
4	-0.09375	-0.03125	-0.015625	0.15625	0.09375	-0.046875	-0.015625
OVALITY							
Upper Head	0.004	-0.039	0.009	-0.019	-0.001	-0.019	-0.067
Top	-0.005	-0.045	-0.005	-0.016	-0.01	-0.019	-0.058
Middle	-0.002	0.003	-0.08	0.02	0.03	0.012	-0.046
Bottom	0.003	-0.022	-0.035	-0.019	0.01	-0.051	-0.042
Lower Head	0.001	0.09	-0.026	-0.034	0.003	-0.076	-0.017

**DATE
FILMED**

4 129/93