DOE/PC/91294--T4

The Role of Pore Structure on Char Reactivity

DOE Grant No.: DE-FG 22-91PC91294

DOE/PC/91294--T4

Quarterly Progress Report

DE93 008934

P.I.: Adel F. Sarofim

Student: Angelo Kandas

**Massachusetts Institute of Technology
Department of Chemical Engineering
Cambridge, MA 02139-4307**

RECEIVED
MAR 24 1993
OSTI

**Prepared for U.S. Department of Energy
Morgantown Energy Technology Center
P.O. Box 880
Morgantown, WV 26507-0880
Attention: Wu K. Lan**

Date Submitted: January, 1993

MASTER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

js

Introduction

In order to examine the role of pore structure, studies will be conducted on coal chars in the electrodynamic balance. Larger particles will also be examined using a fluidized bed to examine diffusion control reactions, and soots will also be investigated to examine the role of meso- and micro-pores without macro-pore interference. These studies will allow a full range of particles sizes and temperatures to be investigated and eventually modelled.

Progress Report

The project is beginning to take shape after the slow start expected in any research project. The preliminary work has focused on soot and large particle experimental setup and analysis methods.

The principal areas being looked at currently are using the fluidized bed for large particles and thermo-gravimetric analyzer(TGA) for soot reactions. The electrodynamic balance(EDB) is currently being worked on largely by Gernot Kramer and Changhe Chen, two post doctoral students that will be here for the next six months. Unfortunately, they are still encountering stabilization problems with the EDB, most probably due to the construction of a new biology building next door. The student is helping them in their work and the EDB is expected to be operational soon

The fluidized bed will be used to work on the large particles. Early on, it was decided that only one particle would be examined, that it should be removable at any point in the reaction, and that a continuous CO₂ analyzer be used to give better resolution in the bed. To allow for work with a removable single particle, a small cage has been designed and fabricated from wire mesh, and will be tested shortly. This cage will function much like a deep frying cage in a fryer, with sand replacing the oil. Much work was done with a computerized data acquisition system for the CO₂ analyzer. Unfortunately, as the student was nearing completion, the A/D board being used stopped working. Currently, a replacement is on order. Work to modify the system to lessen back mixing is also being done by examining the cooling system of the outlet piping.

The soot particles needed to test the TGA are being examined and modified to meet our needs. Since we wish to examine the evolution of the distance between graphite planes as the soot reacts, we felt that slight graphitization needed to take place in order to give good X-ray diffraction results. The corresponding TEM pictures of the soots at for the base soot and after 1500°C graphitization are shown in Figures 1 and 2. As can be seen, there is a fairly substantial amount of graphitization by 1500°C, as expected from Busek's work. However, the initial X-ray diffraction patterns tended to be more difficult to read as temperatures increased. We suspect that this was due to inadequate amounts of sample being prepared, and we will prepare more sample to test this hypothesis. The TGA that will be used to react these soots is in the final stages of modification of its data acquisition system.

Analysis methods to examine the particles are also being learned. The student

Figure 1. TEM of original Diesel Soot to be used, 590,000x magnification. Only small graphite regions are visible.

Figure 2. Diesel soot after heat treating at 1500°C for 1 hour, 590,000x magnification. The region of developed graphite planes is significantly enlarged.

is now fully capable of running BET analysis. However, the BET in the lab is not capable of running multiple point analysis, used in pore size distribution analysis, without much work that quite consuming and of questionable accuracy. The BET is also of limited usefulness for small sample sizes, as its accuracy decreases as surface area declines. Therefore, the student is looking into CO₂ adsorption or mercury porosimetry to determine the pore structure. The CO₂ method is preferred, as it is non-destructive, although both methods will be examined.

The X-ray diffraction techniques used to determine the soot characteristics are currently being learned. The student is expected to be fully certified to run the X-ray equipment here at MIT by the end of January. The goal of this certification is to allow the student to run an X-ray machine located off-campus that, while older, provides a tungsten anode capable of providing the wavelengths necessary to give good counting statistics(intensity) necessary to provide reasonable resolution.

Future Work

Experimental work involving soots and the TGA and single particle fluidized bed work should begin sometime around mid February. Both systems are awaiting work to be done on their data acquisition systems. The EDB will hopefully be running satisfactorily by the next progress report. A variety of samples will then be run at various operating conditions to test the equipment and theories.

The student will be able to run the samples generated using X-ray diffraction, and CO₂ Dubinin surface area measurements by the next report to characterize the samples.

References:

Busek, P., Bo-Jun, H., Keller, L., Energy & Fuels 1987, Vol 1, 105-110
Dubinin, M., Astakhov, V., Molecular Sieve Zeolites -II, p 44

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

END

DATE
FILMED

4 / 12 / 93