DOE/PC/91334-T97
DOE/PC/91334--T97
DE93 000945

TECHNICAL REPORT
March 1, 1992 through May 31, 1992

Project Title: HIGH TEMPERATURE CORROSION DURING USE OF CHLORINE
CONTAINING COAL
DE-FG22-91PC91334

Principal Investigator: Michael McNallan, University of Illinois at Chicago
Other Investigators: Steven Danyluk, J.E. Indacochea, University of Illinois at Chicago
Project Monitor: Dr. Dan Banerjee, CRSC

ABSTRACT

The goal of this project is to characterize the role of chlorine in coal on the high temperature corrosion processes which can occur in coal combustion and conversion processes. The experiments include laboratory tests performed in well-controlled high temperature environments and field tests in industrial coal fired boilers. Evaluation of samples of boiler tubes which have been recovered from boilers which used both high and low chlorine coals does not indicate that the higher chlorine levels are associated with accelerated corrosion of either water wall tubes or superheater tubes in pulverized coal boilers. Laboratory testing of metal coupons in combustion gas environments produced from low sulfur, high chlorine coal IBC-109 and high sulfur-low chlorine coal IBC-101 has been performed at 700 and 800°C. Initial results indicate that more overall corrosion is produced in the high sulfur environment than in the high chlorine environment. Internal attack in the highly alloyed metals alloy 800 and 310 stainless steel is accelerated by the presence of chlorine in the environment, but the level of chlorine required to produce this attack has not yet been determined. Further testing at other temperatures and gas compositions is in progress.

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

MASTER

This project is funded by the U. S. Department of Energy (METC) and by the Illinois Department of Energy and Natural Resources as part of their cost-shared program.

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

EXECUTIVE SUMMARY

Illinois basin coals have the highest chlorine contents of any coals mined in North America in addition to high sulfur contents. The perception that chlorine in coal contributes to boiler corrosion is a hindrance to the marketing of Illinois coal. Although this perception is widespread, it is not supported by definitive data. The goal of this program is to investigate the corrosion of several important high temperature structural materials in environments produced by the combustion of coals, and to clarify the role of chlorine in these processes.

The research includes laboratory exposure tests as well as field tests in industrial boilers. Corrosion tests are performed on metal specimens in environments generated by combusting high sulfur, low chlorine coal (IBC-101) and low sulfur, high chlorine coal (IBC-109) at controlled fuel to air ratios and temperatures and in artificial combustion environments produced by mixing reagent grade gases including CO₂, Cl₂, HCl, and H₂O. Test coupons of AISI 310 stainless steel and alloy 800 have been exposed to the gases at 700 and 800°C. The alloys suffer from internal attack in these environments characterized by the penetration of pores into the surface of the alloys. The microstructure of the internal corrosion process has been characterized and a mechanism is postulated in which the attack occurs by penetration of carbon into the surfaces of the alloys. The carbon ties up the chromium as chromium carbides so that it is not available to produce a protective oxide scale. The chlorine selectively attacks the carbides to produce pores which penetrate the surface. The rate of the internal corrosion process is affected by the chlorine potential in the environment and the temperature, decreasing as either of these is reduced. The levels of chlorine contamination and temperature necessary to produce significant internal attack by this mechanism are currently being evaluated.

Evaluation of test coupons which have been exposed to combustion gases from coal in working boilers is addressed in a second phase of the program. Tubes have been collected and evaluated from several pulverized coal boilers which burned Illinois coals. The results do not indicate that there is any correlation between chlorine content of coal and fire-side corrosion in pulverized coal boilers. Test coupons of low carbon steel, 1 1/4Cr-1/2Mo steel, 2 1/4Cr-1Mo steel, and AISI 304 stainless steel were placed in the low temperature superheater of a boiler last year. These coupons were recovered in April after approximately one year of exposure to the environment. Very little attack of the coupons could be detected by external evaluation of the samples. This may be due to the relatively low gas temperature at the location where they were attached to the boiler tubes.

OBJECTIVES

The goal of this project is to characterize the conditions under which corrosion in coal fired boilers and coal conversion systems can be produced by chlorine in coal and to investigate the mechanisms of this corrosion. The program focusses on high temperature fireside corrosion and includes laboratory scale tests under well controlled conditions in the laboratory as well as coupon tests in utility boilers using high and low sulfur coal. A laboratory furnace is used to expose coupons of important structural materials to combustion gases under well characterized conditions. The apparatus permits control of the temperature, feed rate of well characterized coal, and composition and feed rate of the other combustion gases. The tests are supplemented by similar tests performed in a furnace containing a mixture of laboratory reagent grade gases with compositions similar to those of the combustion gases at thermodynamic equilibrium. Exposure tests are performed over a range of fuel to air ratios, temperatures, and other relevant parameters and the response of the materials is characterized using weight change and microstructural examination. The laboratory work is supplemented by coupon testing in industrial boilers to verify that the corrosion mechanisms identified in the laboratory correspond to the corrosion observed in practice.

INTRODUCTION AND BACKGROUND

In addition to their high sulfur contents, Illinois basin coals have the highest chlorine contents of any coals mined in North America. The perception on the part of many coal users that chlorine in coal contributes to boiler corrosion problems is a hindrance to the marketing of Illinois

coal. Although this perception is widespread, it is not well documented, and chlorine containing coals have been used in many applications without serious problems. The materials degradation processes which occur in many coal combustion and conversion systems are complex and there is presently no clear knowledge of whether chlorine in coal can accelerate corrosion in combustion or in gasifiers or other coal conversion systems.

This research program addresses the influence of chlorine in coal on corrosion problems experienced by important structural materials in atmospheres produced by combustion of coal. The research is performed in two sections: (1) Laboratory studies and (2) in plant coupon tests. In the laboratory studies, care is taken to insure that the materials are exposed only to the gaseous atmosphere produced by combustion of the coal so that damage by erosion or other degradation processes is avoided. The mechanisms and rates of corrosion will be characterized as a function of the material, temperature and composition of the atmosphere. The results will provide definitive information on the effects of chlorine on corrosion in atmospheres typical of coal combustion and conversion systems, so that the significance of chlorine to high temperature corrosion problems can be assessed. The plant tests provide verification of the laboratory generated data, as well as documenting data on the actual effects of varying chlorine levels in coal on corrosion problems experienced by coal users.

EXPERIMENTAL PROCEDURES

The laboratory experiments consist of exposures of well characterized materials to gas environments produced by combustion of coals under well

characterized conditions. They are performed in a specially designed furnace in which the composition of the corrosive environment can be accurately controlled. Considerable effort has gone into the design and construction of this unit, and improvements in the performance of the furnace have continued as we have gained experience in its operation. The combustion of coal in a small scale continuous furnace operation under sufficiently well controlled conditions that reproducible high temperature corrosive gas mixtures are produced is much more difficult than the preparation of gas mixtures of similar composition from reagent gases. The effort is worthwhile, however, because this provides the only means to evaluate the corrosiveness of combustion gases produced when specific coals are burned at specified fuel to air ratios. We have had continuing problems ensuring complete combustion of the coal under conditions which are both well controlled and compatible with the materials used in the reactor. Several additional modifications in the furnace have been made during the past quarter to address these problems.

Combustion is performed in the upper zone of the furnace which is maintained at a temperature of 800°C , and the combustion gases are fed to the lower zone of the furnace where metal test coupons are exposed to the gases at temperatures between 400 and 800°C . We are interested in simulating the exposure conditions of tubes in a pulverized coal boiler where the coal has been essentially all combusted before the gases reach the superheater tubes. However, the temperatures in the combustion zone of the test furnace are still much lower than those in the fireball of coal boiler where they may approach the adiabatic flame temperature of the coal. The thermal history of the combustion gases before they come in

contact with the metals would not be expected to affect the corrosion rates, but it is important that the coal be fully combusted. Problems have been encountered because of the formation of deposits in the exit line from the test furnace. These deposits indicate that the coal has not been completely combusted during its passage through the furnaces. Once the deposits begin to form, the problem worsens, because they reduce the flow of air into the furnace. Because the coal feeding rate is fixed, this changes the fuel to air ratio to produce more reducing conditions. The problem is to insure complete combustion of the coal within the furnace so that no uncombusted hydrocarbons reach the exhaust line.

Faster combustion could be achieved by higher temperatures, however, it is not practical to increase the temperature of the combustion furnace, because at higher temperatures the coal ash fuses to the silica reaction tube, causing sticking and cracking of the tube. Ceramic baffles placed in the combustion furnace to increase the residence time of the coal in the combustion furnace appeared to worsen the problem by reducing the residence time of the gases in the furnace. A substantial improvement in the performance of the furnace was achieved when the control point for the air flow through the furnace was changed from the inlet side to the exhaust side. When the airflow control was on the inlet side, air was pumped through a flowmeter into the furnace and the furnace operated under a slight positive pressure. This prevented leakage of laboratory air into the furnace, but when the exit flow was restricted, the air flow rate to the furnace was immediately reduced and the combustion conditions were altered. To control the air flow from the exhaust side of the furnace, an aspirator pump is used to maintain the furnace at a slight neg-

ative pressure, and the flow rate of gas out of the furnace is monitored. Under these conditions, the gas flow through the furnace is less sensitive to plugging because the furnace pressure can drop allowing laboratory air to leak in and maintain oxidizing conditions. Nevertheless, there have still been occasional incidents of catastrophic plugging.

The plugs typically form where the narrow exhaust line passes through the water cooled cap on the top of the furnace. We are currently modifying the design to increase the diameter of the exhaust line and replace the water cooled copper cap by an insulating refractory cap. This will increase the amount of obstruction required to cause a plug and the higher temperature refractory will reduce the driving force for formation of condensates. If plugging problems are still encountered with the modified design, then the design of the furnace will be modified further so that the combustion will occur in a separate refractory lined furnace which will operate at a high enough temperature to insure complete combustion and the combustion gases will be drawn into the test furnace through a separate line. The refractory can operate above the slagging temperature of the coal ash, but will not be as impermeable to gases as the fused silica tube. By operating at a slight reduced pressure, we will avoid leakage of combustion gases into the laboratory during this operation.

In addition to the coal combustion furnace, an additional test furnace has been committed to the program in which supplementary tests are performed in simulated combustion gases produced by mixing reagent gases. These tests can be performed more rapidly, and have the advantage that

the composition of the gas is not dependent on the efficiency of the combustion process. They are being performed to supplement the results obtained in the coal combustion furnace and to verify the effects of the corrosive species found in the coal combustion tests.

RESULTS AND DISCUSSION

1. Laboratory Corrosion Tests

Research performed during the previous quarter has focussed on the metallographic analysis of the alloys for internal attack in environments containing chlorine. This phenomenon is most serious for the highly alloyed materials such as alloy 800 and 310 stainless steel at high temperatures such as 800°C. Figure 1 is an optical micrograph of a cross section of the 310 stainless steel specimen after exposure to Ar-20%CO₂-0.25%Cl₂-2%H₂O for 24 hours at 800°C. It shows internal penetration penetrating into the specimen to a depth of micrometers. This type of attack is associated with the simultaneous presence of both chlorine and carbon in the environment. Carbon penetrates into the metal producing internal carburization and chlorine follows, attacking the carbides and leaving behind a layer of porous metal. Figure 2 is a similar micrograph after etching the metal to reveal the carbides. The large grains which are surrounded by the internal corrosion are carburized, and a region of carburization precedes the internal corrosion layer growing into the metal. Carburization along grain boundaries is visible penetrating even deeper into the metal.

The importance of chlorine in this corrosion process is indicated by comparing these structures with those produced in the same alloy by exposure to Ar-20%CO₂ at 800°C for the same period of time. Figure 3 shows that no internal corrosion is produced by this exposure, and the etched micrograph shown in Figure 4 shows that the amount of internal carburization produced under these conditions is much smaller than in the case where chlorine is present.

These results are consistent with the hypothesis that the principal effect of chlorine in the environment is to reduce the protectiveness of the oxide scale which forms on the alloys. The dense, protective chromium oxide layer which forms on 310 stainless steel in Ar-CO₂ separates the alloy from the environment and prevents the formation of carbides. In the presence of sufficient chlorine contamination, the oxide is porous and is penetrated by carbon, allowing internal carburization to occur, and internal oxidation and chlorination follow the carburization. This interpretation is supported by the results of X-ray diffraction analysis of the surface of the 310 stainless steel specimen exposed to Ar-20%CO₂-0.25%Cl₂ at 800°C for 24 alloys and summarized in Table I. Diffraction peaks associated with Cr₂O₃ and two similar austenite structures are identified, but only one peak associated with a chromium chloride could be found. This is because most of the chloride reaction products would be expected to be volatile at the reaction temperature and to be transported away from the corroding surface.

Internal attack occurs because the normally protective chromium in the alloy is consumed by the simultaneous attack of carbon and chlorine.

Figure 5 is a plot of the chromium content of the alloy as determined by Energy dispersive X-ray fluorescence microanalysis as a function of distance from the surface of the 310 stainless steel specimen after 24 hours exposure to $\text{Ar-20\%CO}_2$ - $0.25\%\text{Cl}_2$ at 800°C . The surface of the specimen is high in chromium because of the presence of the non-protective chromium oxide layer there. Beneath this is a region extending up to 50 micrometers below the surface where the chromium content is low and the material has been affected by internal attack. Between approximately 50 micrometers and 100 micrometers below the surface is the carburized layer where the apparent chromium content is slightly enriched, but this chromium is primarily in the form of carbides which do not provide much protection for the alloy. Beyond 100 micrometers into the alloy, the chromium content of the alloy is unaffected.

The depth of internal attack would be expected to be affected by the carbon and chlorine potentials in the environment and by the temperature, which determines the diffusion coefficient of carbon in the alloy. Figure 6 shows the composition profiles for iron, nickel, and chromium in the 310 stainless steel specimen which was exposed to $\text{Ar-20\%CO}_2$ - $0.25\%\text{Cl}_2$ - $2\%\text{H}_2\text{O}$ for 24 hours at 800°C . At thermodynamic equilibrium, the hydrogen in the water vapor would be expected to combine with the chlorine to form HCl and lower the effective chlorine potential in the environment. Although the morphology of the corrosion was approximately the same in this environment as in the dry environment, the depth of internal attack is only about 25 micrometers compared with 100 micrometers in the dry environment, indicating that the chlorine potential affects the depth of the internal corrosion.

Similar microstructures and corrosion processes were observed on the specimens exposed at 700°C, but the depth of the attack is smaller, with the penetration being less than 20 microns after 24 hours of exposure to the same gas mixtures. Similar results have been obtained with alloy 800. No internal attack was observed in the 1010 stainless steel or the 2-1/4Cr-1Mo alloy, which suffer from rapid external attack at this temperature. Lower temperature tests are currently being performed on these alloys.

Chlorine potentials produced in coal combustion environments would be expected to be substantially lower than the ones used in these tests, so that the extent of internal attack would also be expected to be smaller. However, some internal attack was observed in the 310 stainless steel specimen exposed to the combustion gases generated from the high chlorine IBC-109 coal at 800°C as shown in Figure 7. The depth of the internal attack in this specimen was greater than that produced in the uncontaminated Ar-20%CO₂ environment, but smaller than that produced in any of the intentionally produced chlorine containing environments. The internal corrosion was also associated with the formation of a carburized layer as shown in Figure 8. Future work will focus on identifying the level of chlorine contamination in the environment required to produce internal corrosion as a function of temperature.

Several publications based on work performed in this program have been completed during the past quarter and are appended to this report. The contents of the publications are summarized in the following section:

Appendix A. "Oxidation-Chlorination of Binary Ni-Cr Alloys in Flowing Ar-O₂-Cl₂ Gas Mixtures at 1200 K" by M.J. McNallan, Y.Y. Lee, Y.W. Chang, N.S. Jacobson, and J.Doychak, appeared in the December, 1991 issue of the Journal of the Electrochemical Society, Vol 138. The experimental work described in this paper was performed preliminary to the beginning of this project, but the writing was completed after the beginning of the program and therefore support is acknowledged.

Appendix B. "Corrosion of Chromium Containing Alloys in Non-Steady State Environments Containing Oxygen, Carbon, and Chlorine" by M.J. McNallan, S. Thongtem, J.C. Liu, Y.S. Park, and P. Shyu was presented at the 3rd International Symposium on High Temperature Corrosion and Protection of Materials in May 25-29, 1992. No travel funds from this program were used to attend this meeting. The paper has been accepted for publication in the Journal de Physique later this year.

Appendix C. "Mixed Oxidation of Chromium Containing Alloys in Gases Produced by Combustion of Coal with High Chlorine Content" by Y.S. Park, M.J. McNallan, Z. Niemczura, and H.H. Lu has been submitted for presentation at the symposium on High Temperature Corrosion and Erosion in Energy Conversion Systems to be held at the ASM Materials Week, November 2-5, 1992 in Chicago, IL.

An additional presentation entitled "Carbide Formation and Oxidation of Austenitic Alloys in Oxidizing/Carburizing Environments Contaminated by Chlorine" by M.J. McNallan, Z. Niemczura, H.H. Lu, and Y.S. Park has been accepted for presentation at the NACE Corrosion/93 Meeting in New Orleans, March 7-12, 1993. The abstract and text of the paper will be prepared during the coming quarter.

2. Evaluation of Test Coupons from Operating Plants

In late April, 1992, the test coupons which had been installed at the Dahlman power station of Springfield City Water, Light, and Power were recovered during the normal maintenance outage of that power plant. We appreciate the assistance of Mr. Brad Buecker in this effort. The specimens, which had been welded around boiler tubes in the low temperature superheater of the boiler, were in surprisingly good condition after approximately one year of exposure to the combustion gases. No significant change in the exterior dimensions of the specimens were evident. This is likely to be due primarily to the fact that the gas temperature was relatively low in this particular location in the boiler. Metallographic and microstructural evaluation of the specimens is currently in progress.

CONCLUSION AND RECOMMENDATION

Examination of exposed tubes recovered from boilers burning coals with chlorine contents ranging from 0.07% to 0.5% Cl have not indicated that the higher chlorine coals cause more severe corrosion of either superheater tubes or water wall tubes.

Laboratory furnace tests of four common boiler materials are in progress. Initial tests in combustion gases from IBC-101 and IBC109 coals burned with at 700 and 800°C indicate less overall corrosion with the higher chlorine IBC-109 coal than with the higher sulfur IBC-101 coal over 24 hours. Tests performed in reagent Ar-CO₂ gas mixtures containing Cl₂ or HCl indicate that the HCl is much less aggressive than the Cl₂ to the

high alloyed steels at 800°C . More internal attack is produced when chlorine is present along with carbon and oxygen at this temperature, and this type of attack has also been detected in the gases produced by combustion of high chlorine coal.

TABLE 1

X-ray Identification Results from the Surface of Sample #3005

Line #1	α_{hkl}	hkl	$d_{hki}(\text{standard})$	Notes
1	5.798	(00.3) Cr Cl ₃	5.804	a
2	3.634	(01.2)Cr ₂ O ₃	3.633	
3	2.659	(10.4)Cr ₂ O ₃	2.666	
4	2.478	(11.0)Cr ₂ O ₃	2.480	b
5	2.178	(11.3)Cr ₂ O ₃	2.176	
6	2.065	(111) γ	2.07	
7	2.053	(111) γ'		
8	1.789	(200) γ	1.80	
9	1.776	(200) γ'		c
10	1.675	(11.6)Cr ₂ O ₃	1.672	
11	1.433	(30.0)Cr ₂ O ₃	1.431	
12	1.270	(220) γ	1.27	
13	1.257	(220) γ'		

a: is possible but only the biggest line appears.

b: covered line (11.4) Cr Cl₃c: covered possible (30.0) Cr Cl₃

Figure 1.

#3007

Cross section (without etching)
800 °C, 24 hours,
20% CO₂ + 0.25% CL₂ + Balanced Ar
With water vapor
800 X

Figure 2.

#3007

Cross section (with etching)

800 °C, 24 hours,

20% CO₂ + 0.25% CL₂ + Balanced Ar

With water vapor

800 X

Figure 3.

#3003

Cross section (without etching)
800 °C, 24 hours,
20% CO₂ + 80% Ar
1000 X

Figure 4. #3003 Cross section (with etching)
800 °C, 24 hours,
20% CO₂ + 80% Ar
1000 X

Figure 6. Elemental concentration profiles for 310 stainless steel after exposure to Ar-20%CO₂-0.25%Cl₂-2%H₂O at 800°C for 24 hours.

Figure 5. Chromium concentration profile for 310 stainless steel specimen after exposure to Ar-20%CO₂-0.25%Cl₂ at 800°C for 24 hours.

Figure 7. Internal attack in 310 stainless steel specimen after 24 hours exposure to combustion gases from IBC-109 coal at 800°C. (unetched specimen at 1000X).

Figure 8. Internal attack in 310 stainless steel specimen after 24 hours exposure to combustion gases from IBC-109 coal at 800°C. Specimen etched to reveal carbides. (1000X)

*Reprint removed
& copied separately*

Corrosion of Chromium Containing Alloys in Non-Steady State
Environments Containing Oxygen, Carbon, and Chlorine

M.J. McNallan, S. Thongtem, J.C. Liu, Y.S. Park, P. Shyu

CEMM Dept., m/c 246

University of Illinois at Chicago

P.O. Box 4348

Chicago, IL 60680

ABSTRACT

Internal attack of chromium containing alloys in mixed oxygen-chlorine environments occurs by the formation of pores which penetrate down grain boundaries of the alloys. No internal attack was detected in a binary Fe-20%Cr alloy at 1200 K in environments containing 2500 ppm Cl₂. The rate of internal attack of alloy 800H in such environments was increased by replacing the O₂ in the gas by CO₂. In mixed oxygen-carbon-chlorine environments, the internal attack occurs by selective chlorination of chromium carbides which precipitate along the grain boundaries.

INTRODUCTION

Alloys intended for service at elevated temperatures in reactive environments obtain their resistance to corrosion by the formation of a dense, adherent oxide layer which separates the metal from the environment.¹ Because chromium oxide has protective characteristics and is more thermodynamically stable than the oxides of iron, nickel or cobalt, chromium is the element which provides the oxidation resistance in many such alloys used in the range of 600 to 900°C.²

In complex industrial environments which contain more than one oxidizing species, the protective character of the chromium oxide film may be compromised, and corrosion may occur at a higher rate than in only oxygen.³ Chlorine is present in some high temperature environments produced during incineration of municipal and industrial wastes,^{4,5} waste heat recovery from chemical and metallurgical processes,^{6,7} and combustion or conversion of low quality chlorine contaminated fuels.^{8,9}

High temperature corrosion by chlorine differs from corrosion by other oxidizing gases because of the volatility of many chlorides and oxychlorides at elevated temperatures.¹⁰ In mixed environments containing both oxygen and chlorine, the corrosion products can include both condensed species, typically oxides, and volatile species, typically chlorides or oxychlorides.¹¹ The kinetics of the overall corrosion process are determined by the order in which the corrosion products form and by the morphology of the condensed corrosion products.¹² The rate of mixed oxidation-chlorination may be higher or lower than the rate of oxidation in uncontaminated oxygen depending on the chemistry of the system and temperature.¹³⁻¹⁵

In chromium containing alloys, the formation of a protective oxide scale occurs by selective oxidation. Fe-Cr alloys and Ni-Cr alloys can both be subject to accelerated oxidation in the presence of chlorine.^{16,17} Chromium containing alloys are also subject to accelerated attack in mixed carbon-oxygen environments.¹⁸ Carbon penetrates into the alloy and reacts with chromium to form chromium carbides

preventing formation of a protective chromium oxide layer at the surface. Carbon is always present in combustion gases, so that corrosion in chlorine contaminated combustion gases is influenced by carbon, oxygen, and chlorine. This paper describes the results of experiments on iron-chromium and iron-nickel-chromium alloys in environments containing oxygen, carbon, and chlorine.

EXPERIMENTAL DETAILS

Results on two alloys are described: A binary Fe-Cr alloy containing approximately 20% Cr by weight, and the austenitic Fe-Ni-Cr alloy 800H. The compositions of the two alloys are given in Table I. The binary alloy had a composition close to that of AISI 430 stainless steel, but was prepared by induction melting electrolytic iron and chromium in air. It contained a higher concentration of the non-metal impurities nitrogen and oxygen and a correspondingly lower concentration of carbon than a commercial alloy.

The alloys were exposed to corrosive gas mixtures containing: 1) argon, oxygen and chlorine or 2) argon, carbon dioxide and chlorine in the apparatus shown schematically in Figure 1. Square test coupons approximately 1 cm x 1 cm x 1 mm were suspended from a fused silica rack in the center of a fused silica reaction tube. The reaction tube was heated to the test temperature using an electrical resistance furnace with Kanthal heating elements. To exclude air from the tube, it was closed at the bottom and sealed at the top by a water cooled brass cap. The spine of the sample rack was a fused silica tube which also

carried the reactive gas mixture into the furnace. Gas mixtures were prepared by mixing technical grades of argon, oxygen, carbon dioxide and chlorine, supplied as mixture of argon-3.5% Cl_2 by volume. The argon and oxygen were purified by passage through packed columns of anhydrous calcium sulfate for water removal and Ascarite for CO_2 removal. The Ar-3,5% Cl_2 mixture was dried by bubbling it through concentrated sulfuric acid, and the CO_2 was dried in a column of anhydrous calcium sulfate.

Experiments were initiated by suspending four specimens of the test alloy from the rack and purging the reaction tube with purified argon. The furnace was heated to the test temperature in this inert environment. When the temperature was stable, the argon was replaced by the corrosive gas mixture flowing at a velocity of 1.5 cm s^{-1} at the reaction temperature. After 50, 100, and 200, hours of exposure, the furnace was cooled to room temperature and one specimen was removed. The fourth specimen was removed after 400 hours of exposure.

After removal from the furnace, the specimens were weighed to determine the change in mass. They were then mounted and cross sectioned to determine the loss in section thickness and to characterize the internal attack by optical and electron microscopy.

RESULTS

A. Ar- O_2 - Cl_2 Environment.

Figure 2 shows the loss in section thickness from the Fe-20%Cr and alloy 800H specimens tested in Ar-20% O_2 -2500 ppm Cl_2 at

1200 K. The mass changes in the specimens were appropriate to the changes in section thickness. The metal loss from the Fe-20%Cr alloy was approximately parabolic with time as would be expected when a protective scale is formed, while that from the 800H alloy had a linear time dependence, but a significantly smaller total magnitude.

Specimens from the two alloys were examined for internal attack. None was detected in the Fe-20%Cr alloy, while for the 800H alloy, internal corrosion was detected as shown in Figure 3. The internal corrosion took the form of porosity along the grain boundaries of the alloy near the corroded surface. The depth of penetration of the internal corrosion from the surface of the specimen was a parabolic function of time as shown in Figure 4.

Internal corrosion has also been observed in a number of commercial alloys exposed to mixed oxygen-chlorine gases at elevated temperatures.^{19,20} The lack of internal corrosion in the binary alloy provoked interest in the role of carbon in the internal corrosion process. The binary alloy, which did not experience internal corrosion, differed from the commercial alloys in that it contained a lower concentration of carbon and it had a ferritic structure in which carbon has a lower solubility.

B. Ar-CO₂-Cl₂ Environment.

Figure 5 shows the metal losses from the Fe-20%Cr and 800H specimens exposed to Ar-20%CO₂-2500 ppmCl₂ at 1200 K. Both alloys were attacked much more rapidly in this gas mixture than

in Ar-0₂-Cl₂. The Fe-20%Cr alloy specimen was completely consumed before the end of the 400 hour exposure but examination of the specimens exposed for shorter periods showed that there was no internal attack. The rate of consumption of the 800H specimen was substantially lower than that from the Fe-20%Cr specimen, was a parabolic rather than linear function of time, but was still substantially higher than it had been in the environment which did not contain carbon.

In addition to the increased metal consumption, the 800H specimen also experienced accelerated internal attack as shown in Figure 4. The form of the internal corrosion was similar to that produced in Ar-20%O₂-2500 ppm Cl₂, as shown in figure 6, but the depth of attack was much greater. After 400 hours of exposure, the internal corrosion had penetrated to the center of the specimen in some regions. The kinetics of the internal attack were also approximately parabolic as shown in Figure 4.

DISCUSSION

Although the overall rate of oxidation of the alloys was increased by the addition of chlorine to the oxidizing environments, internal corrosion was the primary focus of this work. No internal corrosion was found in the binary Fe-Cr alloy and the rate of internal attack in the commercial alloy 800H increased when carbon was present in the environment. The rate of internal attack of alloy 800H in the carbon containing environment was much higher than the rate of internal chloridation of a binary Ni-Cr alloy at a similar temperature²¹, indicating that the mechanism is more complex

than simple internal chloridation. These results suggest that carbon plays a critical role in the internal attack of chromium containing alloys in chlorine containing environments at elevated temperatures.

The following mechanism is hypothesized for the internal corrosion: Carbon contained in the environment dissolves in the alloy, and combines with chromium in the alloy to form chromium carbides at the grain boundaries. The surrounding grains are depleted in chromium. Chromium forms a more stable chloride than iron or nickel, and therefore the chlorine consumes the chromium carbides to form volatile chromium chlorides but its reaction with the surrounding metal is limited by the low chromium content of this metal. The corrosion takes the form of tortuous pores which follow the grain boundaries into the alloy. The volatile chlorides diffuse out of the alloy through the pores while the carbon combines with chromium in the alloy to form additional carbides on the grain boundaries ahead of the pores. The overall rate of the process is controlled by transport of chlorine and/or chlorides through the pores, leading to parabolic kinetics. A similar mechanism has been proposed to explain internal corrosion in cobalt based alloys in chloride containing molten salt environments.²²

The binary Fe-Cr alloy had a lower carbon content than the 800H and was ferritic at the test temperature. It experienced only external corrosion in both test environments. When the 800H was corroded in Ar-20%O₂-2500 ppm Cl₂, the carbon content of the alloy was sufficient to cause chromium carbide

precipitation on the grain boundaries and support internal corrosion. In Ar-20%CO₂-2500 ppm Cl₂, the additional carbon in the environment accelerated the internal attack.

CONCLUSION

Internal corrosion of chromium containing alloys in chlorine containing environments is accelerated by the presence of carbon. Because carbon is present in most combustion environments, internal attack is likely to be more severe in such environments than would be expected based on laboratory studies performed in environments without carbon.

TABLE I Alloy compositions (weight %)

Element	Fe-20%Cr	Alloy 800H
Fe	Balance	Balance
Ni	-	33
Cr	19.02	21
Al	<0.01	0.38
Ti	-	0.38
C	0.01	0.08
N	0.074	-
O	0.10	-

Acknowledgement: This work has been sponsored by the Illinois Department of Energy and Natural Resources through its Coal Development Board and Center for Research on Sulfur in Coal.

REFERENCES

1. KOFSTAD, P. High Temperature Corrosion, (Elsevier Applied Science, Essex, U.K., 1988)
2. WRIGHT, I.G. , in Metals Handbook, 9th Edition, Vol 13, Corrosion, (ASM International, Materials Park, OH, 1987) p 97
3. MEIER, G.H., BIRKS, N., PETTIT, F., GIGGINS, G.S., in RAPP, R.A. (ed), High Temperature Corrosion, (National Association of Corrosion Engineers, Houston, TX, 1983) pp 327-335
4. LAI, G.Y., J. Metals, 37, (1985) P 14
5. KRAUSE, H.H., VAUGHAN, D.A., MILLER, P.D., Trans ASME, Journal of Engineering for Power, 96, (1974) 216-222
6. FEDERER, J.I., JONES, P.J., ORNL/TM-9741, (1985)
7. VAN ROODE, M., PRICE, J.R., GILDERSLEEVE, R.E., SMELTZER, C.E., Ceramics Engineering and Science Proceedings, 9 (1988) 1245-1259
8. BANNERJEE, D., STRINGER, J. (Eds), Chlorine in Coal, Coal Science and Technology Series, 17, (Elsevier Science Publishers, Amsterdam, the Netherlands, 1991)
9. WRIGHT, I.G., SETHI, V.K., KRAUSE, H.H., STRINGER, J., in NATESAN, K., TILLACH, D.J. (Eds.) Heat Resistant Materials, (ASM International, Materials Park, OH, 1991) pp 415-427
10. DANIEL, P.L., RAPP, R.A., in FONTANA, M.G., STAEHLE, R.G., (Eds.) Advances in Corrosion Science and Technology, 5, (Plenum Press, New York, NY, 1976), PP 55-176
11. JACOBSON, N.S., MCNALLAN, M.J., KREIDLER, E.R., High Temperature Science, 27, (1990) PP 381-392
12. MCNALLAN, M.J., LIANG, W.W., OH, J.M., KANG, C.T., Oxidation of Metals, 17 (1982) PP 371-389
13. MALONEY, M.J., MCNALLAN, M.J., Metallurgical Transactions, 16B (1985) pp 751-761
14. LEE, Y.Y., MCNALLAN, M.J., Metallurgical Transactions, 18A (1987) pp 1099-1107
15. LEE, S.Y., MCNALLAN, M.J., Journal of the Electrochemical Society, 137 (1990)pp 472-479
16. KIM, A.S., MCNALLAN, M.J., CORROSION, 46 (1990) pp 746-755

17. MCNALLAN, M.J., JACOBSON, N.S., LEE, Y.Y., CHANG, Y.W., DOYCHAK, J., Journal of the Electrochemical Society, 138 (1991) pp 3692-3696
18. GRABKE, H., GRAVENHORST, U., STEINKUSCH, W., Werkstoffe und Korrosion, 27 (1976) pp 291-296
19. OH, J.M. MCNALLAN, M.J., ROTHMAN, M.F., LAI, G.Y., Metallurgical Transactions, 17A, (1986), pp 1087-1094
20. PRESCOTT, R. STOTT, F.H., ELLIOTT, P., Oxidation of Metals, 31, (1989), pp 145-166
21. LI, Y.K., RAPP, R.A., Metallurgical Transactions, 14B, (1983) pp 509-510
22. EL DAHSAN, M., STRINGER, J., WHITTLE, D.P., Cobalt, 57, (1972), pp182-191

Figure 1. Schematic diagram of apparatus for long term testing of metal coupons in chlorine containing gas mixtures.

Figure 2. Loss in thickness versus time for Fe-20%Cr and Alloy 800H in Ar-20%O₂-2500 ppm Cl₂ at 1200 K.

Figure 4. Internal attack of alloy 800H at 1200 K in Ar-20%O₂-2500 ppm Cl₂ and Ar-20%CO₂-2500 ppm Cl₂

Figure 3. Internal corrosion in alloy 800H after 200 hours exposure to Ar-20%O₂-2500 ppm Cl₂ at 1200 K.

Figure 5. Loss in thickness versus time for Fe-20%Cr and alloy 800H in Ar-20%CO₂-2500 ppm Cl₂ at 1200 K.

Figure 6. Internal corrosion in alloy 800H after 100 hours exposure to Ar-20%CO₂-2500 ppm Cl₂ at 1200 K.

MIXED OXIDATION OF CHROMIUM CONTAINING ALLOYS IN GASES PRODUCED BY
COMBUSTION OF COAL WITH HIGH CHLORINE CONTENT

Y.S. Park, M.J. McNallan, Z. Niemczura, H.H. Lu

CEMM Dept., m/c 246

University of Illinois at Chicago

P.O. Box 4348

Chicago, IL 60680

The rates of oxidation of metals can be accelerated in the presence of second oxidizing species such as sulfur or chlorine. Although chlorine is a minor component in most U.S. coal, the chlorine contents of some midwestern coals can be as high as 0.5%. The role of the chlorine in high temperature fireside corrosion in coal combustion systems is complicated by the presence of a range of other species in the combustion atmosphere, including carbon, sulfur, and ash constituents. Therefore, the corrosion processes in these systems may be more complex than those in laboratory environments.

A two stage furnace has been constructed in which coal with known chemistry can be combusted with controlled fuel to air stoichiometry to generate corrosive combustion gases. Coupons of structural metals including mild steel, low alloy steel, stainless steel and alloy 800 have been exposed to these gases at controlled temperatures. The corrosive effects produced by coals with different chlorine and sulfur contents have been evaluated. These include general metal consumption by oxidation, and internal attack by combined chloridation/carburization along grain boundaries. The effects produced by coal combustion and in clean laboratory environments with similar chlorine, sulfur and oxygen potentials are compared.

This work has been sponsored by the Illinois Department of Energy and Natural Resources through its Coal Development Board and Center for Research on Sulfur in Coal.

END

**DATE
FILMED**

12 / 15 / 92