006511

1 OF 1

DOE/CE/15974--T2

PROGRESS REPORT

DOE/CE/15974--T2

DE93 006511

ON

CONDUCTIVE PAINTS

October 1, 1992 - December 1, 1992

Submitted by

R.J. Soukup

N.J. Ianno

Department of Electrical Engineering
University of Nebraska-Lincoln
Lincoln, NE 68588-0511

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

MASTER

This report covers the work performed from October 1, 1992 - December 1, 1992, under a subcontract from Sayles Enterprises entitled "A Study of Conductive Paints".

I. Paint Deposition

Electrical resistivity measurements require uniformly thick, pinhole free, smooth films deposited on insulating substrates. In order to accomplish this, a paint preparation procedure and deposition procedure has been developed.

The paint preparation procedure is:

1. Filter through a 1000 mesh aluminum paint screen.
2. Continuously shake on a 100 rpm orbital shaker for one hour.
3. Immediately deposit after removal from shaker.

The deposition procedure is as follows:

Apply a fixed amount of paint through a syringe onto a large area (1 - 2 inches in diameter) substrate, and spin at 100 rpm. Small areas of the film, 0.5 x 0.5 inches, taken between the center and edge of the substrate have a uniformity variation on the order of $\pm 5\%$. This size area can be isolated, and used to obtain the film resistivity.

II. Adhesion Strength Testing

Virtually any application involving a coating requires that the coating adhere well to the underlying substrate. The adhesion strength of the Sayles Enterprises paints is directly measured by the Sebastian IV Thin Film Adhesion Strength Measurement system manufactured by Quad Group Inc..

The paint is spun on the substrate as described previously, where adjustments are made for the specific substrate under study. The paint is then dried by inserting it into a preheated furnace for 30 minutes in a forming gas (80% N₂/20% H₂) atmosphere. The forming gas atmosphere minimizes oxidation.

Preparation for the adhesion test entails fastening a metal slug to the paint surface with epoxy, as seen in Figure 1. The slugs are precoated with high strength epoxy, and are supplied as part of the Quad Group system. The slug is held perpendicular to the paint surface while the epoxy is cured at 150 C. It should be pointed out that the epoxy contact area is less than 0.25 inches in diameter, and contact is made in the center of substrate 0.5 x 0.5 inches square. Therefore a uniform thickness of the paint is sampled.

Figure 1. Diagram of epoxy coated slug, paint film, and substrate.

The sample is then inserted into the adhesion strength measurement system, where a steadily increasing force is applied to the end of the metal slug. When failure occurs the system displays the force applied at the failure point. Table I shows the results obtained for Paints #2002, #3003, #4004, and silver sensor on SiO_2 coated silicon substrates, and glass substrates for process temperatures of 100, 200, and 300 C. All samples were processed for 30 minutes in the forming gas atmosphere. Four samples for each set of conditions were made. A complete set of data exists for paints #2002, #3003, and silver sensor. Silver sensor is the base paint that contains no carbon, while #2002 has carbon, and #3003 contains twice as much carbon as #2002.

T	2002				3003				4004				Silver Sensor			
	SiO_2		Glass		SiO_2		Glass		SiO_2		Glass		SiO_2		Glass	
100	13	20	51	52	80	77	15	33	24	25	26	35	61	**	71	136
	24	**	**	**	94	**	**	**	36	59	39	54	**	**	83	161
200	45	33	59	25	9	13	*	*	20	19			19	10	79	23
	47	41	44	16	21	**	*	*	**	**			**	**	112	69
300	17	17	27	**	55	36	77	76					43	**	244	77
	**	**	**	**	**	**	56	54					**	**	77	**

* Made but not tested.

** Broke before testing.

Table I. Adhesion Strength as a Function of Temperature

Figure 2 is a graph of the adhesion strength of these paints on silicon dioxide as a function of process temperature. Each data point was determined by throwing out the high

and low value of adhesion and averaging the remaining values. If 2 points are all that is available, they were averaged. The silver sensor and #3003 behave similarly, while #2002 has the opposite dependence. Silver sensor and paint #3003 have a minimum at 200 C, while #2002 has a maximum at this temperature. At the low and high ends of the range silver sensor and #3003 adhere better to silicon dioxide than #2002 does, while #2002

Figure 2. Adhesion Strength on silicon dioxide Vs Temperature

dominates in the center of the temperature range.

Figure 3 is a graph of adhesion strength of the paints to glass. In this case the dependencies are all approximately linear with temperature. However, unlike Figure 2, silver sensor and #2002 have similar dependencies, while #3003 is opposite. Also, silver sensor exhibits a superior adhesion strength over the entire range of temperatures investigated.

Figure 3. Adhesion Strength on Glass Vs Temperature

In summary, silver sensor, #2002, and #3003 can be made to adhere to silicon dioxide coated silicon, and glass with adequate bond strength. It is clear that the substrate dramatically influences the temperature dependence, while the absolute value of adhesion strength is a function of the paint composition. This work clearly demonstrates that application specific paints can be formulated by composition control.

III. Electrical Resistivity Measurements

The paint samples were prepared as described in Section II, however, the initial substrate was a 2 inch diameter SiO_2 coated silicon wafer where a region 0.5 x 0.5 inches between the center and edge was isolated to yield a relatively uniform film for electrical measurements.

Previously, the van der Pauw configuration was used to measure the paint resistivity. While this is a reliable method, it does require the paint to be uniform over the entire area of the region being measured. While we have successfully fabricated coatings with a uniformity of $\pm 10\%$, the effect of even this variation in film thickness on the van der Pauw measurement is not obvious. In view of this a four point probe region, seen in Figure 4, was defined in the most uniform portion of the paint film. The length and width were kept small to minimize thickness non-uniformity. We estimate the variation to less than 2% over the conducting path.

Figure 4. Four Point Probe pattern for resistivity measurements.

The resistivity is determined from the following relation:

$$\rho = VA/IL$$

where A is the cross section area, V is the measured voltage, I is the current, and L is the distance between the voltage pads. The main uncertainty in this method arises from the non-zero width of the region in contact with the current path which is reflected L. We have defined $L_{\min}$ and $L_{\max}$ in Figure 4 and used them to calculate $\rho_{\max}$ and $\rho_{\min}$ respectively. These values are seen in Table II for three samples each of paint #3003, and #2002 deposited on silicon dioxide coated silicon, and processed in forming gas for 30 minutes at 200 C. There is scatter in the data, which can be reduced by minimizing the difference between $L_{\min}$ and $L_{\max}$ and maximizing the voltage probe spacing with respect to $L_{\max} - L_{\min}$. The average resistivity for #3003 is $10.27 \mu\Omega\text{-cm}$, and for #2002 it is $9.17 \mu\Omega\text{-cm}$. At this point we do not feel these values are statistically different from each other. However, we feel these values are reasonable accurate.

We will continue to improve our measurement technique, and compare 4 point probe measurements to van der Pauw measurements.

Paint #	V, mV	$L_{\max}$, cm $L_{\min}$, cm	A_1 , cm ² A_2 , cm ²	$\rho_{\min}$, $\mu\Omega\text{-cm}$ $\rho_{\max}$, $\mu\Omega\text{-cm}$
3003	0.56	0.84	120 μ	8.0
		0.7	120 μ	9.6
	0.53	0.57	131 μ	14
		0.44	180 μ	19
	0.85	1.1	65 μ	5.0
		0.97	68 μ	6.0
2002	0.48	0.61	84 μ	6.0
		0.47	78 μ	14
	0.24	0.76	85 μ	2.7
		0.63	92 μ	3.3
	0.60	0.83	137 μ	10
		0.44	138 μ	19

Table II. Resistivity of #3003, and #2002 on silicon dioxide coated silicon. Samples were processed in forming gas at 200 C for 30 minutes.

IV. Next Phase

We will finish adhesion strength testing on silicon dioxide and glass, and continue testing on silicon, Delrin, Teflon, and Aluminum Silicate. The paints will be processed at 100, 200, and 300 C in forming gas. The adhesion strength of each sample will be measured, and compared with the others. Further, these results will be compared with samples prepared from Ernest F. Fullam Silver Paint, and G-C silver Paint.

We will also continue the resistivity measurements, and expand to all paints.

END

DATE
FILMED

02/19/93