**COAL SURFACE CONTROL FOR ADVANCED
PHYSICAL FINE COAL CLEANING TECHNOLOGIES**

DOE CONTRACT No. DE-AC22-88PC88877

FINAL REPORT

(September 19, 1988 - August 31, 1992)

**B. I. Morsi
S.-H. Chiang
A. Sharkey
J. Blachere
G. Klinzing
G. Araujo
Y. S. Cheng
R. Gray
R. Streeter**

**H. Bi
P. Campbell
P. Chiarlli
M. Ciocco
L. Hittle
S. Kim
Y. Kim
L. Perez
R. Venkatadri**

**Chemical and Petroleum Engineering Department
University of Pittsburgh
Pittsburgh, PA 15261**

TABLE OF CONTENTS

	Page
ACKNOWLEDGMENTS	xxx
SUMMARY	xxxi
1.0 INTRODUCTION	1-1
2.0 TASK 1: PROJECT PLANNING	2-1
3.0 TASK 3: METHODS FOR ANALYSIS OF SAMPLES	3-1
3.1 Standard ASTM Characterization	3-1
3.1.1 Calorific Value Determination	3-2
3.1.2 Proximate Analysis	3-2
3.1.3 Ultimate Analysis	3-2
3.1.4 Sulfur Forms Analysis	3-2
3.2 Petrographic Characterization	3-3
3.2.1 Maceral Analysis	3-3
3.2.1.1 Petrographic Composition of Upper Freeport Coal	3-4
3.2.1.2 Petrographic Composition of Pittsburgh #8 Coal	3-4
3.2.1.3 Petrographic Composition of Illinois #6 Coal	3-5
3.2.2 Identification of Accessory Minerals	3-5
3.3 Particle Size Distribution	3-6
3.3.1 Coal Samples Ground to 200 mesh x 0	3-6
3.3.2 Coal Samples Ground to 28 mesh x 0	3-8
3.4 Washability Analysis	3-8
3.5 Pyrite Size and Association	3-10
3.6 Morphological Characterization	3-12
3.6.1 Morphology of Coal Particles	3-12
3.6.2 Fourier Analysis	3-13
3.6.3 Size and Morphology of Pyrite	3-13
3.7 Surface Functional Groups	3-14
3.8 Surface Composition	3-15
3.8.1 Laser Microprobe Mass Analysis (LAMMA)	3-15
3.8.2 Electron Spectroscopy for Chemical Analysis (ESCA)	3-16

3.9	Quantitative Distribution of Iron Species	3-18
3.10	Coal Wettability	3-19
3.11	Zeta Potential and pH Measurement	3-20
3.12	Gieseler Test	2-21
3.13	Surface Area	3-22
3.14	Available Inorganic Ions Analysis	3-22
4.0	TASK 4: DEVELOPMENT OF STANDARD AGGLOMERATION TEST	4-1
4.1	Experimental Apparatus	4-1
4.2	Experimental Procedure	4-1
4.2.1	Coal Sample Preparation	4-1
4.2.2	Standardized Agglomeration Tests	4-2
4.3	Calorific Values Calibration	4-3
4.4	Results and Discussion	4-4
5.0	TASK 5: GRINDING STUDIES	5-1
5.1	Experimental	5-1
5.1.1	Grinding Equipment	5-1
5.1.2	Grinding Equipment Calibrations	5-2
5.1.2.1	Dry Grinding in the Stirred-ball Mill	5-2
5.1.2.2	Wet Grinding in the Stirred-ball Mill	5-2
5.1.2.3	Dry Grinding in the Holmes Pulverizer	5-3
5.1.2.4	Wet Grinding in the Ceramic Jar Mill	5-3
5.1.3	Sampling and Grinding Procedure	5-3
5.2	Comparison Between Grinding in Air and in Argon Atmospheres	5-4
5.2.1	Surface Functional Groups	5-5
5.2.2	Surface Composition (LAMMA)	5-6
5.2.3	Moisture Content	5-6
5.3	Two-Level Factorial Design Agglomeration Study	5-6
5.4	Comparison Between Dry and Wet Grinding	5-9
5.4.1	Morphology	5-9
5.4.2	Surface Functional Groups	5-9
5.4.3	Surface Composition (LAMMA)	5-10
5.4.4	Quantitative Distribution of Iron Species	5-10
5.4.5	Wettability	5-11

5.4.6	Zeta Potential and pH Measurements	5-12
5.4.7	Surface Area	5-12
5.4.8	Filtrate Analysis	5-13
5.5	Wet Grinding in the Presence of Light Hydrocarbons	5-13
5.5.1	Agglomeration Tests	5-14
5.5.2	Sample Characterization	5-15
5.5.2.1	Surface Functional Groups	5-16
5.5.2.2	Surface Composition (LAMMA)	5-16
5.5.2.3	Zeta Potential and pH Measurements	5-16
5.5.2.4	Contact Angle Measurements	5-17
6.0	TASK 6: MODIFICATION OF PARTICLE SURFACE	6-1
6.1	Wet Grinding in the Presence of Surfactants	6-1
6.2	Addition of Alcohols Prior to Agglomeration	6-3
6.3	Wet Grinding in the Presence of Monomers	6-4
7.0	TASK 7: EXPLORATORY RESEARCH & DEVELOPMENT AND SUPPORT	7-1
7.1	Examination of the Agglomeration Process Experimental Procedure	7-1
7.1.1	Material Balances for the Agglomeration Process	7-2
7.1.2	Comparison Between the Composition of First and Second Drums	7-3
7.1.3	ESCA Analysis of Pulverized and Wet Ground Coal	7-5
7.2	Optimization of the Agglomeration Process Using N-Pentane	7-7
7.2.1	Effect of Agglomeration Time on the Agglomeration Performance	7-7
7.2.2	Effect of Grinding Method on the Agglomeration Performance	7-9
7.2.3	Effect of pH on the Agglomeration Performance	7-9
7.2.4	Characterization of Agglomeration Test Samples	7-10
7.2.4.1	Surface Composition (LAMMA)	7-10
7.2.4.2	Surface Composition (ESCA)	7-11
7.2.4.3	Surface Functional Groups	7-11
7.3	Optimization of the Agglomeration Process Using N-Heptane	7-12
7.3.1	Comparison with N-Pentane	7-12

7.3.2	Agglomeration Tests Followed by High-Shear Washing Steps	7-13
7.3.3	Use of Pyrite Depressants	7-14
7.3.3.1	Agglomeration Tests Using Lime as Pyrite Depressant	7-14
7.3.3.2	Agglomeration Tests Using FeCl_3 as Pyrite Depressant	7-14
7.3.4	Use of Tall Oil as Binder	7-15
7.3.5	Use of Finer Sieve for Product/Refuse Separation	7-15
7.4	Fine Wet Grinding Using Ceramic Balls	7-16
7.4.1	Pyrite Size and Association	7-16
7.4.2	Upper Freeport Coal	7-16
7.4.3	Pittsburgh #8 Coal	7-17
7.4.4	Illinois #6 Coal	7-19
7.5	Selective Grinding	7-21
7.6	Agglomeration Tests Using the Additional Coals	7-22
7.6.1	Upper Freeport Coal (Grant County, WV)	7-23
7.6.2	Wyodak Coal (Campbell County, WY)	7-24
7.6.3	Kentucky #9 Coal (Hopkins County, KY)	7-24
7.7	Trace Elements Removal	7-25
7.8	Morphology of Agglomerates	7-27
7.9	Coal Wettability	7-30
7.10	Direct Determination of Pyrite by X-Ray Diffraction	7-31
7.11	Agglomeration Tests Using Alberta Research Council (ARC) Coal	7-32
8.0	CONCLUSIONS	8-1
9.0	REFERENCES	9-1
	APPENDIX A: TABLES	A-1
	APPENDIX B: FIGURES	B-1
	APPENDIX C: PYRITE SIZE DISTRIBUTION CALCULATION	C-1
	APPENDIX D: TWO-LEVEL FACTORIAL DESIGN AGGLOMERATION TEST RESULTS	D-1

APPENDIX E: AGGLOMERATION TEST RESULTS USING LIGHT HYDROCARBONS DURING GRINDING	E-1
APPENDIX F: AGGLOMERATION TEST RESULTS USING SURFACTANTS DURING GRINDING	F-1
APPENDIX G: AGGLOMERATION TEST RESULTS USING ALCOHOLS BEFORE AGGLOMERATION	G-1
APPENDIX H: AGGLOMERATION TEST RESULTS USING MONOMERS DURING GRINDING	H-1
APPENDIX I: AGGLOMERATION TEST RESULTS USING N-PENTANE AS AGGLOMERANT	I-1
APPENDIX J: AGGLOMERATION TEST RESULTS USING N-HEPTANE AS AGGLOMERANT	J-1
APPENDIX K: EXPERIMENTAL DATA FOR FINE WET GROUND COAL SAMPLES	K-1
APPENDIX L: AGGLOMERATION TEST RESULTS FOR THE ADDITIONAL COALS	L-1

LIST OF TABLES

	<u>Page</u>
Table 1.0-1 Summary of Coal Samples Received	A-2
Table 3.1-1 Standard ASTM Characterization of Three Base Coal Samples	A-3
Table 3.2.1.1-1 Petrographic Maceral Composition of Upper Freeport Coal	A-4
Table 3.2.1.1-2 Vitrinite Reflectance Distribution for Upper Freeport Coal	A-5
Table 3.2.1.1-3 Non-maceral Microstructures in Upper Freeport Coal	A-6
Table 3.2.1.2-1 Petrographic Maceral Composition of Pittsburgh #8 Coal	A-7
Table 3.2.1.2-2 Vitrinite Reflectance Distribution for Pittsburgh #8 Coal	A-8
Table 3.2.1.2-3 Non-maceral Microstructures in Pittsburgh #8 Coal	A-9
Table 3.2.1.3-1 Petrographic Maceral Composition of Illinois #6 Coal	A-10
Table 3.2.1.3-2 Vitrinite Reflectance Distribution for Illinois #6 Coal	A-11
Table 3.2.1.3-3 Non-Maceral Microstructures in Illinois #6 Coal	A-12
Table 3.3.1-1 Particle Size Distribution of 200 mesh x 0 Samples of the Three Base Coals Measured by Optical Microscopy (32x)	A-13
Table 3.3.1-2 SEM Particle Size Distributions of the Three Base Coals	A-14
Table 3.3.1-3 Compound Particle Size Distributions of the Three Base Coals	A-14
Table 3.3.1-4 Particle Size Distribution of 200 mesh x 0 Samples of the Three Base Coals on Weight Percent Basis Measured by Optical Microscopy (10x)	A-15
Table 3.4-1 Washability Analysis for Upper Freeport Coal Crushed to 200 mesh x 0	A-16
Table 3.4-2 Washability Analysis for Pittsburgh #8 Coal Crushed to 200 mesh 0	A-17
Table 3.4-3 Washability Analysis for Illinois #6 Coal Crushed to 200 mesh x 0	A-17
Table 3.4-4 Analysis of Washability Data Obtained from 200 mesh x 0 As- received Samples of Pittsburgh #8 Coal	A-17

Table 3.4-5	Analysis of Washability Data Obtained from 200 mesh x 0 Moisture-Corrected Samples of Pittsburgh #8 Coal	A-18
Table 3.5-1	Pyrite Size Distribution for 28 mesh x 0 Upper Freeport Coal	A-19
Table 3.5-2	Pyrite Size Distribution for 28 mesh x 0 Pittsburgh #8 Coal	A-20
Table 3.5-3	Pyrite Size Distribution for 28 mesh x 0 Illinois #6 Coal	A-21
Table 3.5-4	Pyrite Size Distribution for 200 mesh x 0 Upper Freeport Coal	A-22
Table 3.5-5	Pyrite Size Distribution for 200 mesh x 0 Pittsburgh #8 Coal	A-23
Table 3.5-6	Pyrite Size Distribution for 200 mesh x 0 Illinois #6 Coal	A-24
Table 3.6.2-1	Fourier Analysis of Shape for Upper Freeport Coal	A-25
Table 3.7-1	Oxidation Indices for the Upper Freeport Coal Test Sample	A-26
Table 3.8.1-1	Duplicate Runs of LAMMA Analysis of Upper Freeport Coal Test Sample	A-26
Table 3.9-1	Mössbauer Hyperfine Parameters and Percent Spectral Areas for 28 mesh x 0 Samples of the Three Base Coals	A-27
Table 3.10-1	Data Analysis of Contact Angle Measurements	A-28
Table 3.11-1	Zeta Potentials and pH Values for the Three Base Coals in Fine Coal Suspensions	A-29
Table 3.11-2	Analysis of Variance on Zeta Potential Measurements	A-29
Table 3.11-3	Analysis of Operator Particle Tracking	A-30
Table 3.12-1	Gieseler Plasticity Data for Three Base Coal Samples	A-31
Table 3.14-1	Quantitative ICP Analysis of Filtrate Samples Obtained from 200 mesh x 0 Wet Ground Illinois #6 Coal	A-31
Table 4.1-1	Calibration of Mixing Speed of Waring Blender	A-32
Table 4.4-1	Experimental Conditions Used in Agglomeration Tests for 28 mesh x 0 Coal Samples	A-33
Table 4.4-2	Experimental Conditions Used in Agglomeration Tests for 200 mesh x 0 Coal Samples	A-34

Table 4.4-3	Nomenclature Used in Agglomeration Tests	A-35
Table 4.4-4	Results of Agglomeration Tests on 28 mesh x 0 Illinois #6 Coal	A-36
Table 4.4-5	Results of Agglomeration Tests on 200 mesh x 0 Illinois #6 Coal	A-37
Table 4.4-6	Results of Agglomeration Tests on 28 mesh x 0 Pittsburgh #8 Coal	A-38
Table 4.4-7	Results of Agglomeration Tests on 200 mesh x 0 Pittsburgh #8 Coal	A-39
Table 4.4-8	Effect of Entrapment of Coal Particles in Filter Paper on Mass and Ash Balance	A-40
Table 5.1.3-1	Coal Sample Designation	A-41
Table 5.2.1-1	Oxidation Indices and 95% Confidence Intervals for the Three Base Coals	A-42
Table 5.2.1-2	Summary of Oxidation Indices for 200 mesh x 0 Upper Freeport Coal Ground in Air	A-42
Table 5.2.1-3	Summary of Oxidation Indices for 200 mesh x 0 Pittsburgh #8 Coal Ground in Air	A-43
Table 5.2.1-4	Summary of Oxidation Indices for 200 mesh x 0 Illinois #6 Coal Ground in Air	A-43
Table 5.2.3-1	Moisture Contents of Dry Ground Coal Samples	A-44
Table 5.3-1	Particle Size Analysis for Two-Level Factorial Design Coal Samples	A-44
Table 5.3-2	Washability Analysis for Upper Freeport Coal	A-45
Table 5.3-3	Washability Analysis for Pittsburgh #8 Coal	A-46
Table 5.3-4	Washability Analysis for Illinois #6 Coal	A-47
Table 5.3-5	Two-Level Factorial Design Experimental Conditions	A-48
Table 5.3-6	Analysis of Variance Results for Energy Recovery	A-49
Table 5.3-7	Analysis of Variance for Ash Rejection	A-50
Table 5.3-8	Standard Deviation Within Replicates for Two-Level Factorial Design Experiments	A-51

Table 5.3-9	Average Values of Energy Recovery	A-52
Table 5.3-10	Average Values of Ash Rejection	A-55
Table 5.4.2-1	Comparison Between Oxidation Indices for Coal Samples Dry and Wet Ground to 200 mesh x 0	A-58
Table 5.4.4-1	Mössbauer Spectroscopy Percent Spectral Areas for the Three Base Coals	A-58
Table 5.4.5-1	Advancing Contact Angles Measured on Pellets Made of Dry and Wet Ground Coal	A-59
Table 5.4.6-1	Zeta Potentials and pH of Dry and Wet Ground Samples for the Three Base Coals in Fine Coal Suspensions	A-59
Table 5.3.7-1	BET Surface Areas of 200 mesh x 0 Coal Samples Dry and Wet Ground	A-60
Table 5.5-1	Light Hydrocarbons Properties	A-60
Table 5.5.1-1	Experimental Conditions for the Agglomeration Tests Using Samples Ground in the Presence of Light Hydrocarbons	A-61
Table 5.5.1-2	Standard Deviations Within Replicates for the Grinding Using Hydrocarbons Agglomeration Results	A-61
Table 5.5.1-3	Statistical Analysis of the Agglomeration Results for Upper Freeport Coal	A-62
Table 5.5.1-4	Statistical Analysis of the Agglomeration Results for Pittsburgh #8 Coal	A-62
Table 5.5.1-6	Statistical Analysis of the Agglomeration Results for Illinois #6 Coal	A-63
Table 5.5.2.1-1	Effect of the Presence of Light Hydrocarbons on the Oxidation Index for Illinois #6 Coal Samples Wet Ground to 200 mesh x 0	A-63
Table 5.5.2.3-1	Effect of Grinding in the Presence of Light Hydrocarbons on the Zeta Potential and pH of Feed Samples	A-64
Table 5.5.2.4-1	Contact Angles for Pittsburgh #8 and Illinois #6 Coals Wet Ground in the Presence of Light Hydrocarbons	A-65

Table 6.0-1	Experimental Conditions for Surface Modification Agglomeration Tests	A-66
Table 6.0-2	Standard Deviations Within Replicates for the Surface Modification Agglomeration Results	A-66
Table 6.1-1	Statistical Analysis of Results from Agglomeration Tests Performed Using Samples Ground in the Presence of Aerosol-OT	A-67
Table 6.1-2	Statistical Analysis of Results from Agglomeration Tests Performed Using Samples Ground in the Presence of Arosurf MG-83A	A-67
Table 6.1-3	Zeta Potentials of the Three Base Coals Wet Ground in the Presence of Surfactants	A-68
Table 6.1-4	Contact Angles for Pittsburgh #8 and Illinois #6 Coals Wet Ground in the Presence of Surfactants	A-68
Table 6.2-1	Statistical Analysis of Results from Experiments Performed with Methanol Added Before Agglomeration	A-69
Table 6.2-2	Statistical Analysis of Results from Experiments Performed with Ethanol Added Before Agglomeration	A-69
Table 6.2-3	Oxidation Indices and 95% Confidence Intervals for Illinois #6 Coal Wet Ground to 200 mesh x 0 in the Presence of Alcohols	A-70
Table 6.2-4	Effect of Methanol on Zeta Potential	A-70
Table 6.2-5	Effect of Ethanol on Zeta Potential	A-71
Table 6.3-1	Statistical Analysis of Results from Agglomeration Tests Performed Using Samples Ground in the Presence of Styrene	A-72
Table 6.3-2	Statistical Analysis of Results from Agglomeration Tests Performed Using Samples Ground in the Presence of Tall Oil	A-72
Table 6.3-3	Oxidation Indices and 95% Confidence Intervals for Illinois #6 and Pittsburgh #8 Coals Wet Ground to 200 mesh x 0 in the Presence of Monomers	A-73
Table 6.3-4	Contact Angles for Pittsburgh #8 and Illinois #6 Coals Wet Ground in the Presence of Monomers	A-74

Table 6.3-5	Mössbauer Spectroscopy Results for Pittsburgh #8 Coal Wet Ground to 200 mesh x 0 with 200 ppm of Tall Oil	A-74
Table 7.1.1-1	Material Balance for Wet Ground Illinois #6 Coal (First Drum)	A-75
Table 7.1.1-2	Material Balance for Wet Ground and Split Illinois #6 Coal (First Drum)	A-76
Table 7.1.1-3	Material Balance for Wet Ground, Split and Filtered Illinois #6 Coal (First Drum)	A-77
Table 7.1.1-4	Material Balance for Wet Ground, Split and Subjected to Agglomeration Test Illinois #6 Coal (First Drum)	A-78
Table 7.1.2-1	Sulfur Forms Analysis for Illinois #6 Coal (First Drum)	A-79
Table 7.1.2-2	Sulfur Forms Analysis for Pittsburgh #8 Coal (First Drum)	A-81
Table 7.1.2-3	Average Results of Sulfur Forms Analysis (First Drum)	A-83
Table 7.1.2-4	LECO Sulfur Analyses for Upper Freeport Coal (Second Drum)	A-84
Table 7.1.2-5	LECO Sulfur Analyses for Pittsburgh #8 Coal (Second Drum)	A-85
Table 7.1.2-6	LECO Sulfur Analyses for Illinois #6 Coal (Second Drum)	A-86
Table 7.1.2-7	ICP Analysis Results (Second Drums)	A-87
Table 7.1.2-8	Comparison Between the Total and Sulfate Sulfur Analyses for the First and Second Drums of the Three Base Coals	A-87
Table 7.1.2-9	Ash Analysis Results (Second Drums)	A-88
Table 7.1.3-1	Peak Positions (ESCA Analysis) for Pulverized (60 mesh x 0) Pittsburgh #8 Coal	A-89
Table 7.1.3-2	Peak Positions (ESCA Analysis) for Wet Ground (200 mesh x 0) Pittsburgh #8 Coal	A-89
Table 7.1.3-3	Percent Atomic Abundances (ESCA Analysis) for Pulverized (60 mesh x 0) Pittsburgh #8 Coal	A-90
Table 7.1.3-4	Percent Atomic Abundances (ESCA Analysis) for Wet Ground (200 mesh x 0) Pittsburgh #8 Coal	A-90
Table 7.1.3-5	Peak Positions (ESCA Analysis) for Pulverized (14 mesh x 0) Illinois #6 Coal	A-91

Table 7.1.3-6	Peak Positions (ESCA Analysis) for Wet Ground (200 mesh x 0) Illinois #6 Coal	A-91
Table 7.1.3-7	Percent Atomic Abundances (ESCA Analysis) for Pulverized (14 mesh x 0) Illinois #6 Coal	A-92
Table 7.1.3-8	Percent Atomic Abundances (ESCA Analysis) for Wet Ground (200 mesh x 0) Illinois #6 Coal	A-92
Table 7.2.1-1	Analysis of Variance for the Effect of Agglomeration Time on the Agglomeration Performance for Upper Freeport Coal	A-93
Table 7.2.1-2	Duncan's Range Test for the Effect of Agglomeration Time on the Agglomeration Performance for Upper Freeport Coal	A-93
Table 7.2.1-3	Analysis of Variance for the Effect of Agglomeration Time and N-Pentane to Coal Ratio (PCR) on the Agglomeration Performance for Pittsburgh #8 Coal	A-94
Table 7.2.1-4	Duncan's Range Test for the Effect of Agglomeration Time and N-Pentane to Coal Ratio (PCR) on the Energy Recovery for Pittsburgh #8 Coal	A-94
Table 7.2.1-5	Analysis of Variance for the Effect of Agglomeration Time on the Agglomeration Performance for Illinois #6 Coal	A-95
Table 7.2.1-6	Duncan's Range Test for the Effect of Agglomeration Time on the Energy Recovery for Illinois #6 Coal	A-95
Table 7.2.1-7	Analysis of Variance for the Effect of Agglomeration Time on the Agglomeration Performance for Illinois #6 Coal	A-96
Table 7.2.1-8	Duncan's Range Test for the Effect of Agglomeration Time on the Agglomeration Performance for Illinois #6 Coal	A-96
Table 7.2.1-9	Effect of Agglomeration Time on Oxidation Index for Illinois #6 Coal	A-97
Table 7.2.1-10	ESCA Results for Illinois #6 Coal (Agglomeration Tests Samples)	A-97
Table 7.2.2-1	Analysis of Variance for the Effect of Grinding Method and Agglomeration Time on the Agglomeration Performance for Pittsburgh #8 Coal	A-98
Table 7.2.3-1	Effect of pH on the Agglomeration Performance for Illinois #6 Coal	A-98

Table 7.2.3-2	Analysis of Variance for the Effect of N-Pentane to Coal Ratio (PCR) and pH on the Agglomeration Performance for Illinois #6 Coal	A-99
Table 7.2.4.2-1	ESCA Results for Agglomeration Tests Samples	A-99
Table 7.2.4.3-1	Oxidation Indices and 95% Confidence Intervals for the Three Base Coals Wet Ground to 200 mesh x 0	A-100
Table 7.3.1-1	Analysis of Variance and Duncan's Range Test for the Effect of N-Heptane to Coal Ratio (HCR) on the Agglomeration Performance for Upper Freeport Coal	A-101
Table 7.3.1-2	Analysis of Variance and Duncan's Range Test for the Effect of N-Heptane to Coal Ratio (HCR) on the Agglomeration Performance for Illinois #6 Coal	A-102
Table 7.3.1-3	Oxidation Indices for Illinois #6 Coal Feed, Product, and Refuse Samples from Agglomeration Tests Conducted Using N-Heptane as Agglomerant	A-103
Table 7.3.3.2-1	Use of FeCl ₃ as Pyrite Depressant	A-103
Table 7.4.2-1	Central Composite Design Average Results for Upper Freeport Coal	A-104
Table 7.4.3-1	Effect of Grinding Time on the Agglomeration Performance for Pittsburgh #8 Coal	A-105
Table 7.4.3-2	Effect of Grinding at High pH on the Agglomeration Performance for Pittsburgh #8 Coal	A-106
Table 7.4.3-3	Central Composite Design Average Results for Pittsburgh #8 Coal	A-107
Table 7.4.4-1	Average Particle Size for Illinois #6 Coal	A-108
Table 7.4.4-2	Agglomeration Results as a Function of Grinding Time for Illinois #6 Coal	A-108
Table 7.4.4-3	Agglomeration Results for Finely Ground (d ₅₀ = 6.9 mm) Illinois #6 Coal	A-109
Table 7.4.4-4	Effect of Sieve Size and pH on the Agglomeration Performance for Illinois #6 Coal (d ₅₀ = 3.7 mm)	A-110

Table 7.4.4-5	Statistical Analysis of the Agglomeration Results for Finely Ground Illinois #6 Coal ($d_{50} = 3.7$ mm)	A-110
Table 7.4.4-6	Effect of pH and Particle Size on the Product Ash Content for Illinois #6 Coal	A-111
Table 7.5-1	Selective Grinding Results	A-112
Table 7.5-2	Selective Grinding Agglomeration Results for Illinois #6 Coal	A-112
Table 7.6-1	Ultimate Analyses of the Additional Coals	A-113
Table 7.6-2	Proximate Analyses of the Additional Coals	A-113
Table 7.6-3	Classification of Additional Coals by Rank	A-114
Table 7.6-4	Trace Elements Analyses of the Additional Coals	A-114
Table 7.6.1-2	Average Agglomeration Results for Upper Freeport Coal, Grant County, WV	A-115
Table 7.6.1-2	Statistical Analysis Results for Upper Freeport Coal, Grant County, WV	A-115
Table 7.6.2-1	ANOVA Results for the Effect of Sieve Size and Agglomeration Time on the Process Performance for Wyodak Coal	A-116
Table 7.6.2-2	ANOVA Results for the Effect of Sieve Size and N-Heptane to Coal Ratio on the Process Performance for Wyodak Coal	A-116
Table 7.6.3-1	Central Composite Design Average Results for Kentucky #9 Coal	A-117
Table 7.7-1	Trace Elements Analyses and Agglomeration Test Results for Pittsburgh #8 Coal	A-118
Table 7.7-2	Trace Elements Analyses and Agglomeration Test Results for Upper Freeport Coal	A-119
Table 7.7-3	Calculated Trace Elements Distribution for Upper Freeport and Pittsburgh #8 Coals	A-120
Table 7.9-1	Contact Angle Measurements Using Different Media	A-121
Table 7.9-2	Contact Angle Measurements on Agglomeration Test Samples	A-121

Table 7.11-1 Alberta Research Coal (ARC) Agglomeration Results

A-122

Table 9.0-1 Work Schedule

A-123

LIST OF FIGURES

	<u>Page</u>
Figure 2.0-1 Work Breakdown Structure	B-2
Figure 3.2.1.1-1 Photographs of Pulverized (14 mesh x 0) Upper Freeport Coal Showing: Vitrinite = V, Dense Pyrite = P, Fusinite = F and Mounting Media = N. Reflected Light in Oil, x443.	B-3
Figure 3.2.1.1-2 Photographs of Pulverized (14 mesh x 0) Upper Freeport Coal Showing: Pyrite = P, Exinite = E, Semifusinite = SF, Vitrinite = V, Micrinite = M, Fusinite = F, and Mounting Media = N. Reflected Light in Oil, x443.	B-4
Figure 3.2.1.1-3 Photographs of Pulverized (14 mesh x 0) Upper Freeport Coal Showing: Vitrinite = V, Framboidal Pyrite = FP, Highly Irregular Snowflake-Like Pyrite = IP and Clay = C. Reflected Light in Oil, x443.	B-5
Figure 3.2.1.1-4 Photographs of Pulverized (14 mesh x 0) Upper Freeport Coal Showing: Quartz = Q, Exinite = E, Vitrinite = V, Micrinite = M, Fusinite = F, and Very Irregular Particle Surfaces = B. Reflected Light in Oil, x443.	B-6
Figure 3.2.1.2-1 Photographs of Pulverized (14 mesh x 0) Pittsburgh #8 Coal Showing: Semifusinite = SF, Fine Coal = FC, Vitrinite = V, Exinite = E, Micrinite = M, Resinite? = R, Fusinite = F, and Mounting Media = N. Reflected Light in Oil, x443.	B-7
Figure 3.2.1.2-2 Photographs of Pulverized (14 mesh x 0) Pittsburgh #8 Coal Showing: Semifusinite = SF, Vitrinite = V, Exinite = E, Quartz = Q, Pyrite = P, Fusinite = F, Micrinite = M, and Mounting Media = N. Reflected Light in Oil, x443.	B-8
Figure 3.2.1.2-3 Photographs of Pulverized (14 mesh x 0) Pittsburgh #8 Coal Showing: A Bone Coal Particle (Interlayered Coal and Mineral) in Top Photo and Vitrinite = V, Grading to Clay = C. Reflected Light in Oil, x443.	B-9
Figure 3.2.1.2-4 Photographs of Pulverized (14 mesh x 0) Pittsburgh #8 Coal Showing: Pyrite = P in Top Photo and Shale = SH in Bottom Photo. Reflected Light in Oil, x443.	B-10

Figure 3.2.1.3-1	Photographs of Pulverized (14 mesh x 0) Illinois #6 Coal Showing: Vitrinite = V, Resinite = R, Exinite (Leaf Culticle) = EC, Semifusinite = SF, Fusinite = F, Pyrite = P and Mounting Media = N. Reflected Light in Oil, x443.	B-11
Figure 3.2.1.3-2	Photographs of Pulverized (14 mesh x 0) Illinois #6 Coal Showing: Vitrinite = V, Exinite = E, Micrinite = M, Semifusinite = SF, Fusinite = F, and Pyrite = P. Reflected Light in Oil, x443.	B-12
Figure 3.2.1.3-3	Photographs of Pulverized (14 mesh x 0) Illinois #6 Coal Showing: Quartz = Q, Clay = C, Micrinite = M, Exinite = E, Fusinite = F, and Vitrinite = V. Reflected Light in Oil, x443.	B-13
Figure 3.2.1.3-4	Photographs of Pulverized (14 mesh x 0) Illinois #6 Coal Showing: Vitrinite = V, Pyrite = P, Calcite = CA, and Mounting Media = N. Reflected Light in Oil, x443.	B-14
Figure 3.3.1-1	Particle Size Distributions of 200 mesh x 0 Three Base Coal Samples Measured by Optical Microscopy	B-15
Figure 3.3.1-2	Fine Particle Size Distributions of Three Base Coals by SEM	B-16
Figure 3.3.1-3	Compound Particle Size Distributions of Three Base Coals	B-17
Figure 3.3.1-4	Particle Size Distributions of the Three Base Coals Ground to 200 mesh x 0 Measured by Optical Image Analyzer	B-18
Figure 3.3.1-5	Particle Size Distribution of Glass Beads Measured with Optical Image Analyzer and Microtrac	B-19
Figure 3.3.1-6	Particle Size Distribution of Illinois #6 Coal 200 mesh x 0 Sample Measured with Optical Image Analyzer and Microtrac	B-20
Figure 3.3.2-1	Particle Size Distribution of 28 mesh x 0 Pittsburgh #8 Coal	B-21
Figure 3.5-1	Photomicrographs of 200 mesh x 0 Upper Freeport Coal Showing Microscopic Appearance of the Coal and Associated Minerals. Reflected Light in Air, x215	B-22
Figure 3.5-2	Photomicrographs of 200 mesh x 0 Pittsburgh #8 Coal Showing Microscopic Appearance of the Coal and Associated Minerals. Reflected Light in Air, x215.	B-23

Figure 3.5-3	Photomicrographs of 200 mesh x 0 Illinois #6 Coal Showing Microscopic Appearance of the Coal and Associated Minerals. Reflected Light in Air, x215.	B-24
Figure 3.5-4	Pyrite Association for 28 mesh x 0 Samples	B-25
Figure 3.5-5	Pyrite Association for 200 mesh x 0 Samples	B-26
Figure 3.6.1-1	Chord Ratio (Length of Horizontal Chords to Vertical Chords) Distributions of Coal Particles for the Three Base Coals	B-27
Figure 3.6.2-1	Fourier Harmonics for $n = 2, 3$, and 11 . The arrows indicate the corresponding amplitudes.	B-28
Figure 3.6.3-1	SEM Image of Polished Refuse Cake at High Magnification (2400). Top: Secondary Electron Image Showing Pyrite (White) and Silicates (Grey); Bottom: Back Scattered Electron Image. The white spots are pyrite down to specks.	B-29
Figure 3.6.3-2	Pyrite Size Distributions for Three Base Coals by SEM	B-30
Figure 3.6.3-3	Chord Ratio (Length of Horizontal Chords to Vertical Chords) Distributions of Pyrite Particles for Three Base Coals	B-31
Figure 3.7-1	Typical DRIFT Spectrum. The shaded areas are the ones ratioed for the calculation of the oxidation index.	B-32
Figure 3.8.1-1	LAMMA Spectra (an average of 50 spectra) of Upper Freeport Coal	B-33
Figure 3.8.2-1	Survey ESCA Spectra for the Three Base Coals	B-34
Figure 3.8.2-2	Sulfur 2p and Silicon 2p Spectra for the Three Base Coals	B-35
Figure 3.8.2-3	Iron 2p Spectra for the Three Base Coals	B-36
Figure 3.8.2-4	Carbon 1s Spectra for the Three Base Coals	B-37
Figure 3.8.2-5	Oxygen 1s Spectra for the Three Base Coals	B-38
Figure 3.9-1	Representative Curve Fit Spectra for 28 mesh x 0 Argon Preserved Samples (Upper Freeport Coal)	B-39
Figure 3.9-2	Representative Curve Fit Spectra for 28 mesh x 0 Argon Preserved Samples (Pittsburgh #8 Coal)	B-40

Figure 3.9-3	Representative Curve Fit Spectra for 28 mesh x 0 Argon Preserved Samples (Illinois #6 Coal)	B-41
Figure 3.11-1	Zeta Potentials of the Three Base Coals at Different pH	B-42
Figure 3.13-1	Dubinin-Polanyi Plots of Adsorption of CO ₂ on Upper Freeport Coal. (W = Volume adsorbed STP/g of coal, P/P ₃ = Relative CO ₂ pressure)	B-43
Figure 4.1-1	Schematic Diagram of Agglomeration Unit (Waring Blender)	B-44
Figure 4.1-2	Blender Speeds Measured at Various Conditions	B-45
Figure 4.1-3	Calibration Curves Obtained from Four Different Coal Slurries	B-46
Figure 4.2.2-1	Schematic Diagram of the Experimental Procedure for the Agglomeration Test	B-47
Figure 4.3-1	Calorific Value versus Ash Content for the Three Base Coals	B-48
Figure 5.1.1-1	Schematic Diagram of Environmental Chamber	B-49
Figure 5.1.1-2	Top and Bottom View of Stirred Ball Mill Lid	B-50
Figure 5.1.1-3	Side View of Stirred Ball Mill Lid	B-51
Figure 5.1.1-4	O-Ring Section of the Shaft	B-51
Figure 5.1.2.1-1	Calibration Curve for Dry Grinding to 200 mesh x 0	B-52
Figure 5.1.2.2-1	Calibration Curve for Wet Grinding to 200 mesh x 0	B-53
Figure 5.1.2.3-1	Calibration Curves for Dry Grinding to 28 mesh x 0	B-54
Figure 5.1.2.4-1	Calibration Curves for Wet Grinding to 28 mesh x 0	B-55
Figure 5.2.1-1	Comparison of Oxidation Indices for the Three Base Coals Ground under Argon and in Air	B-56
Figure 5.2.2-1	Comparison of LAMMA Results for Upper Freeport Coal Samples Prepared under Argon and in Air	B-57
Figure 5.2.2-2	Comparison of LAMMA Results for Pittsburgh #8 Coal Samples Prepared under Argon and in Air	B-58

Figure 5.2.2-3	Comparison of LAMMA Results for Illinois #6 Coal Samples Prepared under Argon and in Air	B-59
Figure 5.3-1	Washability Analysis Data of Energy Recovery versus Ash Rejection for Upper Freeport Coal	B-60
Figure 5.3-2	Washability Analysis Data of Energy Recovery versus Pyritic Sulfur Rejection for Upper Freeport Coal	B-61
Figure 5.3-3	Washability Analysis Data of Energy Recovery versus Ash Rejection for Pittsburgh #8 Coal	B-62
Figure 5.3-4	Washability Analysis Data of Energy Recovery versus Pyritic Sulfur Rejection for Pittsburgh #8 Coal	B-63
Figure 5.3-5	Washability Analysis Data of Energy Recovery versus Ash Rejection for Illinois #6 Coal	B-64
Figure 5.3-6	Washability Analysis Data of Energy Recovery versus Pyritic Sulfur Rejection for Illinois #6 Coal	B-65
Figure 5.3-7	Two-Level Factorial Design Agglomeration Results for Upper Freeport Coal	B-66
Figure 5.3-8	Two-Level Factorial Design Agglomeration Results for Pittsburgh #8 Coal	B-67
Figure 5.3-9	Two-Level Factorial Design Agglomeration Results for Illinois #6 Coal	B-68
Figure 5.3-10	Effect of Particle Size on Energy Recovery	B-69
Figure 5.3-11	Effect of Particle Size and Grinding Method on Energy Recovery	B-70
Figure 5.3-12	Effect of Grinding Method on Ash Rejection	B-71
Figure 5.3-13	Effect of Particle Size and Grinding Method on Ash Rejection	B-72
Figure 5.4.1-1	SEM Micrographs of Dry Ground (200 mesh x 0) Illinois #6 (Top) and Pittsburgh #8 (Bottom) Coals	B-73
Figure 5.4.1-2	SEM Micrograph of Wet Ground (200 mesh x 0) Pittsburgh #8 Coal	B-74

Figure 5.4.1-3	SEM Micrograph of Wet Ground (200 mesh x 0) Illinois #6 Coal	B-75
Figure 5.4.1-4	SEM Micrograph of Dry Ground (200 mesh x 0) Upper Freeport Coal	B-76
Figure 5.4.1-5	SEM Micrograph of Wet Ground (200 mesh x 0) Upper Freeport Coal	B-77
Figure 5.4.3-1	Comparison of LAMMA Results for 200 mesh x 0 Dry and Wet Ground Upper Freeport Coal Samples	B-78
Figure 5.4.3-2	Comparison of LAMMA Results for 200 mesh x 0 Dry and Wet Ground Pittsburgh #8 Coal Samples	B-79
Figure 5.4.3-3	Comparison of LAMMA Results for 200 mesh x 0 Dry and Wet Ground Illinois #6 Coal Samples	B-80
Figure 5.4.3-4	Effect of Grinding Method on Surface Composition (LAMMA) for Upper Freeport Coal	B-81
Figure 5.4.6-1	pH Values of Dry and Wet Ground Upper Freeport Coal Slurries	B-82
Figure 5.4.6-2	pH Values of Dry and Wet Ground Pittsburgh #8 Coal Slurries	B-83
Figure 5.4.6-3	pH Values of Dry and Wet Ground Illinois #6 Coal Slurries	B-84
Figure 5.4.8-1	Comparisons of ICP Analysis Results on Filtrate Samples Obtained from Dry and Wet Ground 200 mesh x 0 Upper Freeport Coal	B-85
Figure 5.4.8-2	Comparisons of ICP Analysis Results on Filtrate Samples Obtained from Dry and Wet Ground 200 mesh x 0 Pittsburgh #8 Coal	B-86
Figure 5.4.8-3	Comparisons of ICP Analysis Results on Filtrate Samples Obtained from Dry and Wet Ground 200 mesh x 0 Illinois #6 Coal	B-87
Figure 5.5.1-1	Effect of Grinding in the Presence of Light Hydrocarbons on the Agglomeration Performance for Upper Freeport Coal	B-88
Figure 5.5.1-2	Effect of Grinding in the Presence of Light Hydrocarbons on the Agglomeration Performance for Pittsburgh #8 Coal	B-89

Figure 5.5.1-3	Effect of Grinding in the Presence of Light Hydrocarbons on the Agglomeration Performance for Illinois #6 Coal	B-90
Figure 5.5.2.1-1	Effect of Grinding in the Presence of Light Hydrocarbons on the Oxidation Index for Illinois #6 Coal	B-91
Figure 5.5.2.2-1	Effect of Grinding in the Presence of Light Hydrocarbons on the Surface Composition (LAMMA) for Illinois #6 Coal	B-92
Figure 5.5.2.2-2	Effect of Grinding in the Presence of Light Hydrocarbons on the Surface Composition (LAMMA) for Pittsburgh #8 Coal	B-93
Figure 5.5.2.4-1	Effect of Grinding in the Presence of Hydrocarbons on Contact Angle for Upper Freeport Coal	B-94
Figure 6.1-1	Agglomeration Results for Upper Freeport Coal Wet Ground to 200 mesh x 0 in the Presence of Surfactants	B-95
Figure 6.1-2	Agglomeration Results for Pittsburgh #8 Coal Wet Ground to 200 mesh x 0 in the Presence of Surfactants	B-96
Figure 6.1-3	Agglomeration Results for Illinois #6 Coal Wet Ground to 200 mesh x 0 in the Presence of Surfactants	B-97
Figure 6.1-4	LAMMA Results for Upper Freeport Coal Wet Ground to 200 mesh x 0 in the Presence of Aerosol-OT	B-98
Figure 6.1-5	Effect of Grinding in the Presence of Surfactants on Contact Angle for Upper Freeport Coal	B-99
Figure 6.2-1	Agglomeration Results for Upper Freeport Coal with Alcohols Added Prior to Agglomeration	B-100
Figure 6.2-2	Agglomeration Results for Pittsburgh #8 Coal with Alcohols Added Prior to Agglomeration	B-101
Figure 6.2-3	Agglomeration Results for Illinois #6 Coal with Alcohols Added Prior to Agglomeration	B-102
Figure 6.2-4	LAMMA Results for Illinois #6 Coal with Methanol Added Prior to Agglomeration	B-103
Figure 6.2-5	Effect of Adding Alcohols on the Oxidation Index for Illinois #6 Coal	B-104

Figure 6.2-6	Effect of Methanol on Advancing Contact Angle for the Three Base Coals	B-105
Figure 6.2-7	Effect of Ethanol on Advancing Contact Angle for the Three Base Coals	B-106
Figure 6.3-1	Agglomeration Results for Upper Freeport Coal Wet Ground to 200 mesh x 0 in the Presence of Monomers	B-107
Figure 6.3-2	Agglomeration Results for Pittsburgh #8 Coal Wet Ground to 200 mesh x 0 in the Presence of Monomers	B-108
Figure 6.3-3	Agglomeration Results for Illinois #6 Coal Wet Ground to 200 mesh x 0 in the Presence of Monomers	B-109
Figure 6.3-4	LAMMA Results for Illinois #6 Coal Wet Ground to 200 mesh x 0 in the Presence of Monomers	B110
Figure 6.3-5	LAMMA Results for Pittsburgh #8 Coal Wet Ground to 200 mesh x 0 with 200 ppm of Tall Oil	B-111
Figure 6.3-6	LAMMA Results for Illinois #6 Coal Wet Ground to 200 mesh x 0 With 200 ppm of Tall Oil	B-112
Figure 6.3-7	Comparison Between Agglomeration Results and LAMMA Data for Pittsburgh #8 Coal	B-113
Figure 6.3-8	Comparison of Oxidation Indices for Feed and Product Samples of 200 mesh x 0 Illinois #6 Coal Wet Ground With and Without Tall Oil	B-114
Figure 6.3-9	Comparison of Oxidation Indices for Samples of 200 mesh x 0 Pittsburgh #8 Coal Wet Ground With and Without Tall Oil	B-115
Figure 6.3-10	Effect of Tall Oil on Zeta Potentials of the Three Base Coals at Various pH Values	B-116
Figure 6.3-11	Effect of Grinding in the Presence of Monomers on Contact Angle for Upper Freeport Coal	B-117
Figure 7.1.1-1	Overall Material Balance for Agglomeration Process	B-118
Figure 7.1.1-2	Ash Balance for Agglomeration Process	B-119
Figure 7.1.1-3	Total Sulfur Balance for Agglomeration Process	B-120

Figure 7.1.1-4	Inorganic Sulfur Balance for Agglomeration Process	B-121
Figure 7.1.2-1	Comparison Between LECO and ICP Sulfate Sulfur Analyses	B-122
Figure 7.1.2-2	Comparison Between LECO and ICP Pyritic Sulfur Analyses	B-123
Figure 7.1.3-1	ESCA SO_4^{2-} , S^{2-} , and Si Peaks for Pulverized (14 mesh x 0) Pittsburgh #8 Coal	B-124
Figure 7.1.3-2	ESCA SO_4^{2-} , S^{2-} , and Si Peaks for Wet Ground (200 mesh x 0) Pittsburgh #8 Coal	B-125
Figure 7.1.3-3	ESCA Fe Peaks for Pittsburgh #8 Coal	B-126
Figure 7.1.3-4	ESCA SO_4^{2-} and S^{2-} Peaks for Pulverized (60 mesh x 0) Illinois #6 Coal	B-127
Figure 7.1.3-5	ESCA SO_4^{2-} , S^{2-} , and Si Peaks for Wet Ground (200 mesh x 0) Illinois #6 Coal	B-128
Figure 7.1.3-6	ESCA Fe Peaks for Illinois #6 Coal	B-129
Figure 7.2.1-1	Effect of Agglomeration Time on the Agglomeration Performance for Upper Freeport Coal	B-130
Figure 7.2.1-2	Effect of Agglomeration Time on the Energy Recovery for Pittsburgh #8 Coal	B-131
Figure 7.2.1-3	Effect of Agglomeration Time on the Agglomeration Performance for Illinois #6 Coal (Slurry Concentration = 2% by weight)	B-132
Figure 7.2.1-4	Effect of Agglomeration Time on the Agglomeration Performance for Illinois #6 Coal (Slurry Concentration = 4% by weight)	B-133
Figure 7.2.1-5	Effect of Agglomeration Time on Carbon, Oxygen, and Silicon Surface Concentrations for Illinois #6 Coal (ESCA)	B-134
Figure 7.2.1-6	Effect of Agglomeration Time on Iron and Sulfur Surface Concentrations for Illinois #6 Coal (ESCA)	B-135
Figure 7.2.1-7	Effect of Agglomeration Time on the Surface Composition (LAMMA) for Illinois #6 Coal	B-136

Figure 7.2.2-1	Effect of Grinding Method on the Energy Recovery for Pittsburgh #8 Coal	B-137
Figure 7.2.3-1	Effect of pH on the Ash Rejection for Illinois #6 Coal	B-138
Figure 7.2.4.1-1	LAMMA Results for Pittsburgh #8 Coal Wet Ground to 200 mesh x 0	B-139
Figure 7.2.4.1-2	LAMMA Results for Illinois #6 Coal Wet Ground to 200 mesh x 0	B-140
Figure 7.2.4.2-1	Carbon, Oxygen, and Silicon Surface Concentrations for Agglomeration Tests Samples (ESCA)	B-141
Figure 7.2.4.2-2	Iron and Sulfur Surface Concentrations for Agglomeration Tests Samples (ESCA)	B-142
Figure 7.2.4.3-1	Oxidation Indices for the Three Base Coals	B-143
Figure 7.3.1-1	Comparison of Energy Recoveries and Pyritic Sulfur Rejections Between Agglomerants for Upper Freeport Coal	B-144
Figure 7.3.1-2	Comparison Between Agglomerants for Pittsburgh #8 Coal	B-145
Figure 7.3.1-3	Effect of N-Heptane to Coal Ratio on the Agglomeration Performance for Illinois #6 Coal	B-146
Figure 7.3.2-1	Agglomeration Plus High-Shear Washing Tests Results for Upper Freeport Coal	B-147
Figure 7.3.2-2	Agglomeration Plus High-Shear Washing Tests Results for Pittsburgh #8 Coal	B-148
Figure 7.3.3.1-1	Effect of Lime Addition on the Agglomeration Performance for Pittsburgh #8 Coal	B-149
Figure 7.3.3.1-2	Effect of Lime on Surface Composition (LAMMA) for Pittsburgh #8 Coal	B-150
Figure 7.3.4-1	Use of Tall Oil as Binder for Illinois #6 Coal	B-151
Figure 7.3.5-1	Effect of Sieve Size on the Agglomeration Process Performance for Illinois #6 Coal	B-152

Figure 7.4-1	Particle Size Distribution for Upper Freeport Coal Wet Ground Using 7/32" Ceramic Balls	B-153
Figure 7.4-2	Particle Size Distribution for Pittsburgh #8 Coal Wet Ground Using 7/32" Ceramic Balls	B-154
Figure 7.4-3	Particle Size Distribution for Illinois #6 Coal Wet Ground Using 7/32" Ceramic Balls	B-155
Figure 7.4-4	Average Particle Size (d_{50}) for the Three Base Coals Wet Ground Using 7/32" Ceramic Balls	B-156
Figure 7.4.1-1	Pyrite Association for Upper Freeport Coal Wet Ground Using 7/32" Ceramic Balls	B-157
Figure 7.4.1-2	Pyrite Association for Pittsburgh #8 Coal Wet Ground Using 7/32" Ceramic Balls	B-158
Figure 7.4.1-3	Pyrite Association for Illinois #6 Coal Wet Ground Using 7/32" Ceramic Balls	B-159
Figure 7.4.2-1	Central Composite Design for $k = 3$	B-160
Figure 7.4.2-2	Effect of Grinding Time and pH on the Ash Rejection for Upper Freeport Coal	B-161
Figure 7.4.3-1	Effect of Agglomeration Time and Grinding Time on the Agglomeration Process Performance for Fine Ground Pittsburgh #8 Coal	B-162
Figure 7.4.3-2	Effect of pH and High-Shear Washing on the Agglomeration Process Performance for Fine Ground Pittsburgh #8 Coal	B-163
Figure 7.4.3-3	Effect of Grinding Time and pH on the Inorganic Sulfur Rejection for Pittsburgh #8 Coal (Second Order Response Model)	B-164
Figure 7.4.3-4	Effect of Agglomeration Time and pH on the Inorganic Sulfur Rejection for Pittsburgh #8 Coal (Second Order Response Model)	B-165
Figure 7.4.4-1	Particle Size Distribution of Illinois #6 Coal Samples	B-166
Figure 7.4.4-2	Effect of Grinding Time on the Agglomeration Performance for Illinois #6 Coal	B-167

Figure 7.4.4-3	Effect of the N-Heptane to Coal Ratio on the Agglomeration Process Performance for Fine Ground Illinois #6 Coal	B-168
Figure 7.4.4-4	Effect of the pH on the Agglomeration Process Performance for Fine Ground Illinois #6 Coal	B-169
Figure 7.6.2-1	Clean Coal Yield for Wyodak Coal	B-170
Figure 7.6.2-2	Ash Rejection for Wyodak Coal	B-171
Figure 7.6.2-3	Inorganic Sulfur Rejection for Wyodak Coal	B-172
Figure 7.8-1	Microagglomerates of Upper Freeport Coal (Dispersion Method). SEI Micrograph showing well defined, tight, round agglomerates, sometimes clustered (Bottom).	B-173
Figure 7.8-2	Microagglomerates of Upper Freeport Coal (Dispersion Method, SEI).	B-174
Figure 7.8-3	Freeze-dried Agglomerates of Upper Freeport Coal, BSE Imaging. The very white spots are pyrite particles.	B-175
Figure 7.8-4	Microagglomerates of Illinois #6 Coal (Dispersion Method, Top: SEI, Bottom: BSE Imaging). Note the lack of cohesion of these agglomerates.	B-176
Figure 7.8-5	Microagglomerate of Illinois #6 Coal (Dispersion Method, BSE Imaging).	B-177
Figure 7.8-6	Freeze-dried Agglomerates of Illinois #6 Coal (Top: SEI, Bottom: BSE Imaging of Same Area). Note the very open rough texture. Pyrite is white in lower micrograph.	B-178
Figure 7.8-7	Freeze-dried Agglomerate of Illinois #6 Coal, BSE Imaging.	B-179
Figure 7.8-8	Microagglomerates of Pittsburgh #8 Coal (Dispersion Method, SEI Mode). The microagglomerates are irregular and tend to aggregate together.	B-180
Figure 7.8-9	Microagglomerates of Pittsburgh #8 Coal (Dispersion Method, SEI Mode). The agglomerates tend to break up on drying with the formation of a coarse "skin".	B-181

Figure 7.8-10	Freeze-dried Agglomerates of Pittsburgh #8 Coal. The Matrix is Tight in Texture and Fairly Continuous with Large Voids. Same Area in SEI (Top) and BSE Imaging (Bottom).	B-182
Figure 7.8-11	Freeze-dried Agglomerates of Pittsburgh #8 Coal, SEI.	B-183
Figure 7.8-12	Microagglomerates of Pittsburgh #8 Coal (Dispersion Method, SEI Mode) Prepared Using a N-Heptane to Coal Ratio of 0.05 and an Agglomeration Time of 60 s.	B-184
Figure 7.8-13	Microagglomerates of Pittsburgh #8 Coal (Dispersion Method, SEI Mode) Prepared Using a N-Heptane to Coal Ratio of 0.10 and an Agglomeration Time of 60 s.	B-184
Figure 7.8-14	Microagglomerates of Pittsburgh #8 Coal (Dispersion Method, SEI Mode) Prepared Using a N-Heptane to Coal Ratio of 0.20 and an Agglomeration Time of 60 s.	B-185
Figure 7.8-15	Microagglomerates of Pittsburgh #8 Coal (Dispersion Method, SEI Mode) Prepared Using a N-Heptane to Coal Ratio of 0.50 and an Agglomeration Time of 60 s.	B-185
Figure 7.8-16	Microagglomerates of Pittsburgh #8 Coal (Dispersion Method, SEI Mode) Prepared Using a N-Heptane to Coal Ratio of 0.50 and an Agglomeration Time of 15 s.	B-186
Figure 7.8-17	Microagglomerates of Pittsburgh #8 Coal (Dispersion Method, SEI Mode) Prepared Using a N-Heptane to Coal Ratio of 0.50 and an Agglomeration Time of 120 s.	B-186
Figure 7.9-1	Contact Angle Measurement	B-187
Figure 7.10-1	XRD Determination of Pyrite	B-188
Figure C-1	Geometry Involved in the Intersection of a Sphere by a Plane Within the Slice h	C-4

ACKNOWLEDGMENTS

This research work was the result of considerable time and effort by all the participants of the project and Mr. Thomas J. Feeley, III the Contracting Officer's Representative (COR) of the DOE/PETC. The project was led by the University of Pittsburgh whereas Westinghouse, BCR National Laboratory, and Ralph Gray Services were the subcontractors. The project was divided into seven Tasks: (1) Project Planning, (2) Coal Procurement & Weathering Tests, (3) Analytical Methods for Coal Samples, (4) Development of Standard Agglomeration Test, (5) Grinding Studies, (6) Modification of Particle Surface, and (7) Exploratory R&D and Support. Task 2 was entirely carried out by Praxis Engineers Inc., Milpitas, California and the University of Pittsburgh was responsible for the other six tasks.

Task 1 was a combined effort of all participants of the project and was supervised by Dr. Badie I. Morsi (project manager). Dr. Jean R. Blachere, from the Materials Science and Engineering Department, and Professor Andrew G. Sharkey, Jr., from the Department of Geology and Planetary Sciences, served as co-leaders for Task 3. Dr. Blachere supervised particle size distribution/analysis, surface area, and morphological analyses and he was assisted by Ms. H. Bi. Professor Sharkey supervised surface functional groups and surface composition analyses and he was assisted by Ms. P. Campbell, Mr. P. Chiarelli, Ms. L. Hittle, and Ms. Y. Kim. Additional support for Task 3 was provided by Mr. Ralph Gray, of Ralph Gray Services, who conducted coal petrographic studies. Washability analysis and sulfur forms were carried by R. Moses and R. Streeter from BCR National Laboratory. The contact angle and Zeta potential measurements were conducted by Mr. L. Perez. The ICP analysis was carried out by J. Fabec from PARC and trace elements analysis was supervised by R. Patalsky of Coal Petrographic Associates, Inc.

Tasks 4, 5, 6, and 7 were supervised by Dr. Badie I. Morsi. The majority of the work of Task 4 was conducted by Mr. S. Kim, while the majority of the work of Task 5 was conducted by Mr. M. Ciocco. The research effort in Tasks 6 and 7 was shared by Mr. S. Kim and Mr. M. Ciocco. Westinghouse under the supervision of M. Cooper carried out the Quality Assurance and Quality Control of the project.

Additional support and supervision for the project was provided by Professors S.-H. Chiang and G. E. Klinzing and Drs. R. Venkatadri and G. Araujo. Although the emphasis of the project was research, the preparation of reports was an important and time consuming task. A significant portion of this report was written by Dr. G. Araujo.

EXECUTIVE SUMMARY

This summary outlines the research work conducted in the Coal Surface Control for Advanced Physical Fine Coal Cleaning Technologies project which was sponsored by the U.S. Department of Energy (DOE), Pittsburgh Energy Technology Center (PETC). The project was funded to support the engineering development of the advanced physical coal cleaning technologies (selective agglomeration) in order to reduce the sulfur content of U.S. coals for controlling SO₂ emissions (i.e., acid rain precursors). The overall effort was an integral part of the DOE/PETC's Acid Rain Control Initiative (ARCI).

The objective of the project was to develop techniques for coal surface control prior to the advanced physical fine coal cleaning process of selective agglomeration in order to achieve 85% pyritic sulfur rejection at an energy recovery (Btu recovery) greater than 85% based on run-of-mine coal. Three base coals were used in this project: Upper Freeport (Indiana County, PA), Pittsburgh #8 (Belmont County, OH), and Illinois #6 (Randolph County, IL). Three additional coals were also tested: Upper Freeport (Grant County, WV), Kentucky #9 (Hopkins County, KY), and Wyodak (Campbell County, WY).

TASK 1: PROJECT PLANNING

The project work plan was completed and modified in accordance with comments and suggestions by the Contracting Officer's Representative (COR) of the DOE/PETC. The final version of the work plan was approved on 12/5/1988.

TASK 3: ANALYTICAL METHODS FOR COAL SAMPLES

Several drums of the three base coals were delumped and pulverized. The pulverized samples were further ground to two sizes, 28 mesh x 0 and 200 mesh x 0 under different grinding conditions. The following methods were used to analyze and characterize the ground coal samples.

ASTM characterization including calorific value determination, proximate analysis, ultimate analysis, and sulfur forms analysis.

Petrographic characterization.

Particle size distribution using optical microscopy, scanning electron microscopy, and a Microtrac particle size analyzer.

Washability analysis.

Pyrite size and association.

Morphological characterization.

Surface functional groups in terms of the oxidation index determined using Diffuse Reflectance Infrared Fourier Transform (DRIFT) spectroscopy.

Surface composition using Laser Microprobe Mass Analysis (LAMMA) and Electron Spectroscopy for Chemical Analysis (ESCA).

Quantitative distribution of iron species using Mössbauer spectroscopy.

Zeta potential and pH measurements.

Gieseler Test.

Surface area using carbon dioxide adsorption.

Available inorganic ions using Inductively Coupled Plasma (ICP) spectrometry.

These techniques were used in parallel with the experimental work aimed at improving the agglomeration process performance. Their purpose was to characterize feed, product, and refuse samples as well as to help explain the agglomeration test results.

TASK 4: DEVELOPMENT OF STANDARD AGGLOMERATION TEST

A commercial Waring blender was modified by the addition of baffles, a stainless steel cover with an injection port for agglomerant, and a digital speed readout device. A standardized agglomeration procedure was developed. An excellent linear correlation between the calorific value and ash content was established for the three base coals.

TASK 5: GRINDING STUDIES

An environmental chamber was designed and built to carry out grinding under controlled conditions. The chamber consists of six compartments allowing for sampling, delumping, pulverizing, grinding, and packaging of coal samples. Procedures for sampling and pulverizing original coal samples inside the chamber in air and under argon atmosphere were developed. The original inerted coal samples of the three base coals were delumped to 0.5" x 0 and pulverized to 14 mesh x 0.

Calibration curves were obtained for dry and wet grinding to 200 mesh x 0 using a stirred-ball mill loaded with 3/8" stainless steel balls, dry grinding to 28 mesh x 0 using a Holmes pulverizer, and wet grinding to 28 mesh x 0 using a ceramic jar mill. Sampling, grinding, and splitting procedures were developed.

The surface composition (LAMMA) and oxidation indices were compared for the three base coals ground in air and under an argon atmosphere. The oxidation indices for the samples ground in argon were lower than those of samples ground in air. It is speculated that elevated temperatures encountered during grinding might have caused this effect. On the other hand, no systematic differences in surface composition were found.

A two-level factorial design was used to study the effect of particle size (28 mesh x 0 and 200 mesh x 0), grinding method (dry and wet), slurry concentration (2 and 4% by weight), n-pentane to coal ratio (0.5 and 1.0), agglomeration time (15 and 30 s), and mixing speed (9000 and 14000 rpm) on the performance of the agglomeration process using n-pentane as agglomerant. The statistical analysis of the data shows that particle size and grinding method are the most significant variables affecting the energy recovery and ash rejection. Because of their narrow range, only minor effects were detected for the other variables. Wet grinding to 200 mesh x 0 was found to be the most beneficial size reduction procedure for the agglomeration process.

A comparison of the surface and bulk properties between dry and wet ground coal samples was performed using some of the analytical techniques developed in Task 3. The results of the analyses indicate that pyrite oxidation, water adsorption, ion leaching, and particle morphology are strongly dependent on the grinding method. Surface compositions measured using LAMMA and ICP analyses of filtrates suggest that more extensive leaching occurs during wet grinding than during dry grinding. Although

Mössbauer spectroscopy results seem to show that pyrite is oxidized during dry grinding, contact angle and oxidation index measurements indicate a more hydrophilic character for the wet-ground samples. Water adsorption during wet grinding apparently causes this anomaly in the results.

Wet grinding in the presence of light hydrocarbons was investigated as a technique to improve agglomeration process performance. Pulverized (14 mesh x 0) samples of the three base coals were wet ground to 200 mesh x 0 using n-pentane, cyclohexane, and n-heptane. The response of the coals to wet grinding in the presence of light hydrocarbons was strongly influenced by their wetting character. For Upper Freeport coal, the most hydrophobic of the coals studied, it was not possible to complete grinding in most cases because of agglomeration in the stirred-ball mill. On the other hand, for Illinois #6 coal, the least hydrophobic of the coals studied, no tendency to agglomeration during grinding was observed. The agglomeration test results show that the only statistically significant improvement in performance as a result of this procedure was an increase in energy recovery for Pittsburgh #8 coal ground using n-heptane to coal ratios greater than 0.05.

TASK 6: MODIFICATION OF PARTICLE SURFACE

A study of the effect of using surface modification reagents on the agglomeration process performance was carried out with the three base coals wet ground to 200 mesh x 0. Agglomeration tests were conducted using coal samples treated with surfactants (Aerosol-OT and Arosurf MG-83A) and monomers (styrene and tall oil) during grinding and with alcohols (methanol and ethanol) prior to the experiments. The statistical analysis of the agglomeration data indicates that, in general, the use of these reagents did not improve the process performance. The only exception was an increase in energy recovery for Pittsburgh #8 coal when a tall oil dosage of 10.6 lb/ton was used.

TASK 7: EXPLORATORY R&D AND SUPPORT

Material balances on the coal, ash, sulfur, and sulfur forms (sulfate, pyritic, and organic sulfur) were performed for the grinding, splitting, and agglomeration test steps of the agglomeration process. The results of the material balances indicate that there are only

minor losses (about 3%) of coal during the grinding and splitting steps. The lost material is mostly mineral matter settled in the mechanical splitter during the splitting operation.

In order to determine whether oxidation had occurred during storage, sulfur forms analyses were conducted on run-of-mine coal samples kept in sealed drums under an argon atmosphere for two years. The analyses show that pyrite oxidation took place resulting in an increase in sulfate sulfur content to about 0.8% for Pittsburgh #8 and Illinois #6 coals and to 0.5% for Upper Freeport coal (from 0.12, 0.11, and 0.02%, respectively).

The information on coal agglomeration using n-pentane as agglomerant gathered in Tasks 5 and 6 was used as the basis for the optimization of the process. The effect of several operating variables on the agglomeration process performance was investigated for the three base coals wet ground to 200 mesh x 0. Among the most significant conclusions, it was found that for Upper Freeport and Pittsburgh #8 coals, the energy recovery increased as agglomeration time increased, reaching more than 95% for an agglomeration time of 60 s. For Illinois #6 coal, however, it was not possible to attain energy recoveries above 80%.

The agglomeration process was further studied using n-heptane as agglomerant. N-heptane was selected to replace n-pentane to take advantage of its higher boiling point that results in the formation of more stable product agglomerates. A comparison between agglomerants shows that, in general, similar results are obtained with both agglomerants.

Two post-agglomeration treatments, use of tall oil as a binder and high-shear product washing, were tested in order to improve the agglomeration process performance using n-heptane as agglomerant. Tall oil was added as binder to increase the energy recovery to about 98% (with a decrease in pyritic sulfur rejection of 10 percentage points) for Illinois #6 coal. High-shear washing was used to increase the ash and pyritic sulfur rejection for Pittsburgh #8 coal. The same treatment was applied to Upper Freeport coal but because of the great strength of the agglomerates no improvements in performance were observed.

The effect on the agglomeration performance of using different sieves sizes for the product/refuse separation was evaluated for Illinois #6 coal. Significantly higher energy

recoveries were obtained using a 230-mesh (63 mm) sieve when compared with a 120-mesh (125 mm) sieve.

Lime (CaO) and ferric chloride (FeCl_3) were utilized as pyrite depressants in agglomeration tests conducted using Pittsburgh #8 coal. An optimum lime dosage was found at 6.6 lb/ton that resulted in an increase in pyritic sulfur rejection from 62% without additives to 69%. Higher dosages decreased energy recovery without further gains in pyritic sulfur rejection. Ferric chloride did not result in performance improvements in the concentration range studied (3 to 5 lb/ton).

The pyrite size and association was determined for finely ground (smaller than 200 mesh x 0) samples of the three base coals. Fine grinding was conducted in the stirred-ball mill using 7/32" ceramic balls. The petrographic analysis shows that reducing the particle size from 14 mesh x 0 to an average of 10-30 microns (5 min grinding) increases the amount of free pyrite and reduces the amount of locked pyrite. For finer sizes, however, the technique does not work properly, producing unreasonable results.

Finely ground samples of Upper Freeport coal were investigated in a series of agglomeration tests organized according to central composite design. The data show that the ash rejection is improved by using a combination of fine grinding and high pH. The energy recovery, on the other hand, is mostly determined by the n-heptane to coal ratio. A n-heptane dosage above a certain minimum results in energy recoveries close to 100% independently of other operating conditions.

A central composite design was also used to study the agglomeration of finely ground Pittsburgh #8 coal. The interactions among grinding time, pH, and agglomeration time were found to determine the ash and pyritic sulfur rejections. For longer grinding time (finer particle size), high pH and longer agglomeration time translate into better performance. A threshold value for the n-heptane to coal ratio at about 0.3, above which the energy recovery is higher than 90% in all cases, was found.

Finely ground Illinois #6 coal was investigated in tests in which the effects of agglomeration time, n-heptane to coal ratio, sieve size, and pH on the agglomeration performance were determined. The data show that it is possible to obtain energy recoveries above 90% if a 230-mesh sieve is used for the product/refuse separation. It is also evident that as the particle size decreases, a longer agglomeration time and/or n-

heptane to coal ratio is needed to obtain high energy recoveries. The main effect of high pH is to increase pyritic sulfur rejection, specially for finer particle size.

Selective grinding, a treatment in which large, hard-to-grind particles are removed prior to agglomeration, was evaluated for the three base coals. An improvement in performance was observed for Illinois #6 coal which suggests that the addition of a particle size classifier to the agglomeration circuit could result in a significant improvement in the agglomeration process performance.

Wyodak coal was investigated in order to determine its agglomerating character. The agglomeration tests results indicate that this coal is not easily agglomerated. It requires the use of high agglomerant dosages in order to obtain a high energy recovery. The pyritic sulfur rejection is also low but since its total sulfur content is only 0.6%, cleaning may not be necessary.

The agglomeration process was studied using Upper Freeport coal from Grant County, WV. The experiments showed that this coal is very hydrophobic and therefore it was possible to achieve energy recoveries close to 100% and pyritic sulfur rejections near 80%.

Trace elements analysis of feed and product samples of Upper Freeport and Pittsburgh #8 coals were conducted. The data indicate that most elements are concentrated in the mineral matter fraction of the coals. The exceptions are beryllium, mercury, and selenium.

The morphology of agglomerates was studied using the Scanning Electron Microscope (SEM). Micrographs of Upper Freeport coal agglomerates show that these agglomerates are tight, round and of the order of 100 mm in size. Illinois #6 coal, on the other hand, formed extremely weak agglomerates with a loose texture. Pittsburgh #8 coal agglomerates are not as well shaped as those of Upper Freeport coal, apparently contain more water and are about 100 to 200 mm in diameter. The evolution of the morphology of the agglomerates was found to be a function of the agglomeration time and n-heptane to coal ratio.

A method for direct determination of the pyrite content of coal using X-ray diffraction was developed. Since this technique directly determines pyrite it could eliminate the need for acid leaching prior to pyritic sulfur analysis. Good reproducibility and results within the error of standard techniques were obtained.

1.0 INTRODUCTION

This final report presents the research work carried out on the Coal Surface Control for Advanced Physical Fine Coal Cleaning Technologies project, Contract No. DE-AC22-88PC88877, sponsored by the U. S. Department of Energy, Pittsburgh Energy Technology Center (DOE/PETC). The project was to support the engineering development of the selective agglomeration technology in order to reduce the sulfur content of U.S. coals for controlling SO₂ emissions (i. e., acid rain precursors). The overall effort was a part of the DOE/PETC's Acid Rain Control Initiative (ARCI).

The overall objective of the project is to develop techniques for coal surface control prior to the advanced physical fine coal cleaning process of selective agglomeration in order to achieve 85% pyrite sulfur rejection at an energy recovery greater than 85% based on run-of-mine coal. The surface control is meant to encompass surface modification during grinding and laboratory beneficiation testing. The project includes the following tasks:

Task 1: Project Planning

Task 3: Methods for Analysis of Samples

Task 4: Development of Standard Beneficiation Test

Task 5: Grinding Studies

Task 6: Modification of Particle Surface

Task 7: Exploratory R&D and Support

The coal samples used in this project include three base coals, Upper Freeport - Indiana County, PA, Pittsburgh #8 - Belmont County, OH, and Illinois #6 - Randolph County, IL, and three additional coals, Upper Freeport - Grant County, WV, Kentucky #9 - Hopkins County, KY, and Wyodak - Campbell County, WY. A total of 149 drums of coal were received. A summary of the samples received is shown in Table 1.0-1.

The project work plan (Task 1) was submitted to the DOE and was approved on 12/5/1988. Tasks 3, 4, 5, and 6 were completed in December 1989. Task 7 was initiated in October 1989 and completed in December 1991. The technical progress in this project from its inception through December 31, 1991, is presented in this report.

2.0 TASK 1: PROJECT PLANNING

The objective of work planning is to organize the overall program into a logical sequence of activities leading to the project goals. A detailed project work plan including work breakdown structure, project management, project schedule, milestones, labor as well as cost distribution plans was submitted to the DOE/PETC on October 24, 1988. The work plan was modified based on the comments and recommendations received from DOE/COR, and a revised project work plan was submitted to DOE/PETC on November 28, 1988. The revised project work plan was approved on December 5, 1988. The work breakdown structure is illustrated in Figure 2.0-1.

3.0 TASK 3: METHODS FOR ANALYSIS OF SAMPLES

The objective of Task 3 is to select appropriate standard analysis methods, and where needed, to modify existing methods or establish/adopt non-standard techniques for characterizing coal and its surface properties in order to evaluate surface control techniques in Tasks 4, 5, 6, and 7.

A drum of each of the three base coals was delumped and pulverized under atmospheric conditions (air). The original inerted coal samples have a particle size of about 5" x 0. In order to obtain a representative sample from each drum, grinding was performed according to the following procedure:

1. Thirty to forty lb of coal from different portions of the drum were stored. The rest of the drum (about 400 lb) was delumped to about 0.5" x 0 using a delumper manufactured by Franklin Miller, Inc., East Orange, NJ. The delumping was carried out in batches of 30 to 40 lb.
2. From each delumped batch, about 1 lb of coal was taken. The total collected coal was well mixed before pulverizing. The rest of the delumped coals were bagged.
3. The well mixed delumped coal was pulverized to 1 mm x 0 using a pulverizer manufactured by DHE FEN Machine Co., Cleveland, OH. The pulverized coal was sealed in 1 to 2 lb bags.
4. A 28 mesh x 0 coal sample was obtained by grinding a whole bag of the pulverized coal using a Holmes Pulverizer and sieving through a sieve tray. Large particles (+28 mesh) were recycled to the pulverizer. Four to five repetitions of the pulverizing and sieving operations were needed to reduce 99% (by weight) of the sample to 28 mesh x 0.
5. To reduce the particle size to 200 mesh x 0, the 28 mesh x 0 sample obtained in step 4 was further ground in a Fritsch Pulverisette. A similar pulverizing and sieving procedure was applied until about 99% (by weight) of particles were passed through the 200 mesh sieve.

Samples of Upper Freeport, Pittsburgh #8, Illinois #6 coals ground to two sizes, 28 mesh x 0 and 200 mesh x 0, were used in this task to establish and test analytical methods. These topsizes were selected because they represent sizes that the electric utility industry is capable of and comfortable with handling. Also, in order to minimize the degree of fine grinding and subsequent difficulties associated with handling fine clean coal and refuse, as coarse a top size as possible was used.

3.1 Standard ASTM Characterization

The objective of this subtask is to obtain basic information about the coals tested based on recognized standard ASTM methods. The specific analytical tests for calorific value, proximate analysis, ultimate analysis, and sulfur-forms analysis were performed using the three base coals. The experiments were carried out at BCR laboratory. The data obtained for the three base coals, listed in Table 3.1-1, are mean values based on results of duplicate determinations. The results of all duplicate determinations agreed within specified tolerances for

the individual ASTM analytical methods.

3.1.1 Calorific Value Determination

The calorific value (Btu/lb) was determined using a Parr 1241 adiabatic oxygen calorimeter in accordance with ASTM Method D2015⁽¹⁾. The precision limit in the method is 50 Btu/lb on a dry basis.

3.1.2 Proximate Analysis

Moisture, ash, volatile matter, and fixed carbon of each of the three base coal samples were measured using ASTM methods D3173⁽²⁾, D3174⁽³⁾, D3175⁽⁴⁾ and D3172⁽⁵⁾, respectively.

3.1.3 Ultimate Analysis

With acetanilide (C_8H_9NO) as a reference standard, carbon, hydrogen, nitrogen, and oxygen contents of each coal sample were analyzed using a Perkin-Elmer 240 B automated elemental analyzer. The total sulfur was determined using the conventional Eschka fusion method, ASTM D3177⁽⁶⁾.

3.1.4 Sulfur-Forms Analysis

The three commonly recognized forms of sulfur in coal: sulfate sulfur, pyritic sulfur, and organic sulfur, were determined according to the standard method ASTM D2492-84⁽⁷⁾. Sulfate sulfur was determined by extracting a two-gram sample of 60 mesh x 0 coal with dilute hydrochloric acid and determining the sulfur in the extract gravimetrically as barium sulfate. Sulfates are soluble in hydrochloric acid but pyrite and organic sulfur forms are not.

Pyritic sulfur was measured by extracting a one-gram sample of 60 mesh x 0 coal with dilute nitric acid. The extracted pyritic iron (from FeS_2) was determined by atomic absorption, and the pyritic sulfur was calculated as a stoichiometric combination with the iron. The pyritic iron value was first corrected for the amount of nonpyritic iron dissolved during the hydrochloric acid extraction step for sulfate sulfur (also determined by atomic absorption).

Organic sulfur was calculated by subtracting the percentage of sum of sulfate and pyritic sulfur from the percentage of total sulfur, as determined during the ultimate analysis.

3.2 Petrographic Characterization

The objective of this subtask is to apply existing petrographic analytical methods to characterize the coals used in this project. Maceral composition, vitrinite reflectance, and non-maceral microstructures were analyzed and identified as described in ASTM D2797-85⁽⁸⁾. In addition, the accessory minerals present in coal were identified using X-Ray Diffraction (XRD).

3.2.1 Maceral Analysis

The petrographic analysis provides basic information, such as maceral composition, vitrinite reflectance, non-maceral microstructures and mineral materials. Vitrinite reflectance is a preferred rank parameter for bituminous and higher rank coals as specified in ASTM D2798-95⁽⁹⁾. It increases as the coal rank and aromaticity increase. The maceral analysis is usually used to characterize the coal type determined by the amount, kind, and state of preservation of organic materials that constitute the coal.

Samples of the three base coals were prepared for petrographic analysis as described in Standard Method ASTM D2797-85⁽⁸⁾. Two pellets of 28 mesh x 0 coal were prepared per coal, rather than 20 mesh x 0 specified by ASTM. The samples were analyzed microscopically using a Leitz Ortholux microscope at a magnification of 720 diameters. A Whipple graticule was used to define four points per field for counting. A mechanical stage with fixed stops was used to advance in incremental steps across the samples.

The Standard Method ASTM D2799-86⁽¹⁰⁾ was used to count the macerals vitrinite (V), exinite (E), resinite (R), micrinite (M), semi-fusinite (SF), and fusinite (F). One thousand points per pellet were determined on each of the two pellets for a total of 2000 maceral and mineral counts per coal. All data were on a volume percent, and the mineral matter was calculated from ash and sulfur content determined in accordance with ASTM Test Method D3177⁽⁶⁾. The following formula was used to convert weight percent ash (A) and sulfur (S) to volume percent mineral matter (MM):

$$\text{MM \%} = \frac{100 [(1.08 \text{ A} + 0.55 \text{ S}) / 2.8]}{[100 - (1.08 \text{ A} + 0.55 \text{ S})] / 1.35 + (1.08 \text{ A} + 0.55 \text{ S}) / 2.8} \quad (3.1)$$

The petrographic maceral composition is shown in the format commonly used for metallurgical coals in which the macerals are reported in reactive and inert groups and in which the semifusinite is allocated 1/3 to the

reactives and 2/3 to the inerts. The Composition-Balance Index (Rank Index) and Calculated Stability Factor are also listed. The vitrinite is reported as Vitrinoid Types in which each V-Type equals 0.1% reflectance so that Type 10 contains all of the vitrinite with a mean maximum reflectance of 1.00 through 1.09 reflectance in green light and in oil. Non-maceral structures were also determined. The technique used for the determination of non-maceral microstructures is not defined by the ASTM but is described in detail by Gray⁽¹¹⁾.

3.2.1.1 Petrographic Composition of Upper Freeport Coal

Figures 3.2.1.1-1 through 3.2.1.1-4 depict micrographs showing the microscopic appearance of Upper Freeport coal. This coal contains 80.6% of vitrinite with 1.8% of exinite most of which is poorly defined optically as would be expected for medium volatile bituminous coal with a volatile matter of 30.82% daf, which is calculated from a dry volatile matter of 27.0% and 12.4% ash. There is 0.2% resinite and 0.9% reactive semifusinite bringing the reactive maceral total to 83.5%.

The inerts in Upper Freeport coal which total 16.6% consist mostly of mineral matter, 7.7% with 4.3% of micrinite which contains macrinite and inertodetrinite and 1.8% of inert semifusinite. The mineral matter was calculated from 12.4% ash and 2.36% total sulfur, on a dry basis.

Vitrinite Reflectance for Upper Freeport coal is shown in Tables 3.2.1.1-1 and 3.2.1.1-2. Upper Freeport coal contains Vitrinoid Types 10 through 13, with the greatest abundance, (61.2%) of Type 11, as shown in Table 3.2.1.1-1. The vitrinite reflectance distribution based on 100 determinations is shown in Table 3.2.1.1-2. The mean maximum reflectance for the coal is 1.149% which indicates the coal is medium volatile bituminous and very near the boundary with high volatile coal. Non-maceral Microstructures in the Upper Freeport coal are shown in Table 3.2.1.1-3.

Miscellaneous Tests show that Upper Freeport coal has a free-swelling index (FSI) of 8½ based on two buttons. The FSI coke shows lenticular domains that are the size expected from Vitrinoid Types 11 and 12. The domains are 2 to 4 microns wide and commonly up to 10 microns in length.

3.2.1.2 Petrographic Composition of Pittsburgh #8 Coal

Figures 3.2.1.2-1 through 3.2.1.2-4 depict micrographs showing the microscopic appearance of Pittsburgh #8 coal. The Petrographic Maceral Composition, shown in Table 3.2.1.2-1, indicates that Pittsburgh #8 coal contains 71.1% of vitrinite with 5.0% of exinite, 2.3% of resinite and 1.5% of reactive semifusinite for a total reactive content of 79.9%. The inerts total 20.1% and consist mostly of micrinite and mineral matter.

The Vitrinite Reflectance for Pittsburgh #8 coal is 0.713%. The frequency distribution of reflectance determinations, shown in Table 3.2.1.2-2, indicates that Pittsburgh #8 is a high volatile bituminous coal and

probably high volatile A in rank.

Non-macerai Microstructures for the Pittsburgh #8 coal are shown in Table 3.2.1.2-3. The coal is mostly a bright attrital coal or normal coal with a fairly large amount of coarse vitrinite and pseudovitrinite, most of which is telinite. A large portion of the coarse minerals consist of bone coal, shale and considerable amounts of relatively coarse (+20 microns) pyrite. There is a small amount of coal oxidation and brecciation.

Miscellaneous Tests show the coal has a free-swelling index (FSI) of 6½ based on two buttons and the coke in the FSI buttons has an anisotropic texture which consists of very fine size (0.5 microns) circular domains which are slightly larger than would be expected from a coal of this rank.

3.2.1.3 Petrographic Composition of Illinois #6 Coal

Figures 3.2.1.3-1 through 3.2.1.3-4 depict micrographs showing the microscopic appearance of Illinois #6 coal. The Petrographic Maceral Composition is shown in Table 3.2.1.3-1. Illinois #6 coal has 78.5% total reactives which consists of 67.7% vitrinite, 4.5% exinite, 5.0% resinite and 1.3% of reactive semifusinite. The inerts total 21.5% and much of the inert material, 11.5%, is mineral matter.

Vitrinite Reflectance is 0.487% which indicates Illinois #6 coal is high volatile bituminous and either B or C in rank. The frequency distribution of reflectance determinations is shown in Table 3.2.1.3-2.

Non-macerai Microstructures for Illinois #6 coal are shown in Table 3.2.1.3-3. The normal coal totals 40.0% with 24.5% of coarse vitrinite and 18.5% of pseudovitrinite, most of which has cellular texture. The coarse mineral matter is mostly bone coal, 4.2% with 3.0% of shale and 2.4% of carbonaceous shale. The coarse (> 20 microns) pyrite and the calcite each are 1.6% by volume. There is a small amount of oxidation and brecciation.

Miscellaneous Tests show the Illinois #6 coal has a free-swelling index (FSI) of 3½ based on 2 buttons. The coke from the buttons are isotropic with a zero domain size.

3.2.2 Identification of Accessory Minerals

Clays may play an important role in the beneficiation of coal since they have different tendencies to cause "slime" coating. They can modify the surface properties and the beneficiation potential of coals. This tendency depends on the nature of the clay(s) associated with a given coal and on the clay environment. Certain electrolytes and organics can dramatically modify the properties of clays. Their effect depends on the nature of the clays. In order to identify the clay species present in the coals, accessory minerals as a group were determined by X-Ray Diffraction.

Samples of the three base coals initially ground to 200 mesh x 0 were ground further in a mortar and packed in a 5 cm long XRD sample holder. The diffraction pattern was determined by scanning from $2Q = 5^\circ$ to 85° at $2^\circ/\text{min}$ on a GE XRD 700 Diffractometer equipped with a graphite monochromator. Q is the Bragg angle when the diffraction condition is satisfied. The diffraction pattern was recorded using $\text{Cu K}\alpha$ radiation with a 3° beam slit from $2Q = 5^\circ$ to $2Q = 15^\circ$ and a 1° slit from 15° to 85° . The X-ray tube was run at 40 kV and 20 mA. The minerals were identified using the ASTM Powder Data files and major clay mineralogy references^(12,13).

Quartz, kaolinite, and pyrite were found in all three base coals. Illinois #6 coal probably contains calcite which was not detected in the other coals. Upper Freeport coal appears to contain significantly more clay and kaolinite than the others. The pyrite intensities were of the same order in all three base coals. Quartz and pyrite were easily identified as accessory minerals. Low angle lines indicate the presence of clays. In general, specific identification of clays require extensive X-ray diffraction work. In this case, there is a good indication of the presence of kaolinite with all its major lines present. There is also a peak around the 10 Å lattice spacing, which suggests the presence of some illite, although the overlap of the other peaks with peaks for other minerals and the weakness of this general pattern do not permit the confirmation of this identification of illite.

3.3 Particle Size Distribution

The objective of this subtask is to establish experimental procedures for measuring coal particle size distributions. For 200 mesh x 0 samples, the number percent distributions were determined using both an optical microscope and a Scanning Electron Microscope (SEM), and the weight percent distributions were measured by the optical microscope with an objective of 10x and by the use of a Microtrac particle size analyzer. The weight percent distributions of the 28 mesh x 0 coal samples were analyzed with two objective lenses in order to obtain good statistical values for large particles.

3.3.1 Coal Samples Ground to 200 mesh x 0

For 200 mesh x 0 samples, the number percent distributions were determined using an optical microscope. The samples were prepared for observation by mixing them with immersion oil of refractive index $n = 1.515$ followed by immersion in an ultrasonic bath for about 10 min. when particle agglomeration was observed. A small portion of the sample was placed on a microscope slide, more oil was added to disperse particles, and gently overlaid with a coverglass. The image was obtained by transmission in an optical microscope (Leitz Orthoplan) and picked up with a video system. The image was digitized and stored in the dedicated computer of an Omnicon Bausch & Lomb image analyzer. The particle size analysis was performed with a 32x objective

which resulted in an overall magnification of 355x on the analyzer screen. About 90 to 100 fields were analyzed. This procedure was tested with 200 mesh x 0 samples of the three base coals and the particle size distributions (number percent) are given in Table 3.3.1-1 and plotted in Figure 3.3.1-1. Results of duplicate measurements agree with each other well.

The optical microscope is near its limit of resolution when 1-micron particles are measured. A procedure using the SEM to reach higher magnifications was used to complement the optical method described above. For observation under the SEM, the coal particles were dispersed in water containing a dispersant, and a drop of the dispersion was dried on a SEM stub. The dispersion was retained during drying. The fine particle size distribution was analyzed by the SEM in secondary electron mode. High contrast micrographs were obtained and analyzed with the image analyzer. This procedure is not totally random since fields with too few particles or very large particles are not photographed. About 20 micrographs were taken for each sample, corresponding to about 1000 particles. The duplicate size distributions obtained with the optical microscope were averaged. This average over the size range 2 - 5 microns was used to scale the SEM distribution. The two distributions, obtained in SEM and optical microscope, were then merged. In the resulting compound distributions, the SEM data were used only for the size classes below 2 microns. The number percent distributions of fine particles obtained in the SEM are listed in Table 3.3.1-2 and shown in Figure 3.3.1-2. The practical lower limit with the present procedure is about 0.2 micron. The compound distributions are given in Table 3.3.1-3 and plotted in Figure 3.3.1-3. The distributions are quite similar for the three base coals. The peaks of the distributions are in the 1 - 2 micron range. The data suggest that 10 - 20% of the coal particles are missed when the optical microscope is used routinely. These particles constitute a small weight or volume fraction, but have a large surface area which may affect the agglomeration process.

Since the fine particles (< 2 microns) do not significantly affect the weight percent distribution, the weight percent particle size distributions of 200 mesh x 0 coal samples were determined optically using a 10x objective. The image analysis was performed as described above using the optical microscope with the aid of the Omnicon image analyzer. A total of 50,000 - 100,000 particles were counted. The data were manipulated by the image analyzer, and the weight percent particle size distribution of the sample was obtained. The weight distributions of the 200 mesh x 0 samples obtained with the optical microscope at lower magnifications are shown in Tables 3.3.1-4 through 3.3.1-6 for the three base coals. They are plotted on a log-normal scale in Figure 3.3.1-4.

The optical microscopy method described above was compared with a Microtrac particle size analyzer. Figure 3.3.1-5 shows that when glass beads of almost monosize were measured by both methods, the particle size distributions obtained were in good agreement. However, Figure 3.3.1-6 shows that the two methods produced significantly different results when materials with broad size distributions are measured, Illinois #6 coal ground to 200 mesh x 0 in this case. It was concluded that the optical microscope should be used for

calibration of the grinding mills and detailed particle size distribution analysis, and the Microtrac analyzer should be used for routine analysis of particle size distributions and for comparison with results reported by other laboratories where Microtrac particle analyses are used.

3.3.2 Coal Samples Ground to 28 mesh x 0

There is a statistical problem to obtain reproducible distributions for 28 mesh x 0 samples by optical microscopy. Just one large particle of the order of 500 microns (about 28 mesh) can cause a significant shift of the cumulative distribution. To solve this problem, samples were separated into two fractions using a 120-mesh sieve. The two parts were measured separately and then combined. About 150 to 200 g of coal was weighed and screened with a 120 mesh sieve for 20 min. The two fractions were weighed and the loss after screening and collecting the fractions was maintained under 2%. The weight percent distributions were measured separately with the microscope using a 16x objective lens for -120 mesh fraction and a 4x objective lens for the +120 mesh fraction. By adding the two fractions together, the new total weight percent distribution was calculated. For the finer fraction, 20,000 particles were counted, and for the coarse section 2,000 particles were counted. A smaller number of counts was made for the coarser fraction because there are fewer particles per field on the image analyzer. In this way, the effect of large particles on the total distribution was minimized.

The procedures used for determination of particle size distributions of 28 mesh x 0 coal samples, as discussed earlier, were tested using Pittsburgh #8 coal. As shown in Figure 3.3.2-1, duplicate runs show excellent reproducibility of the data. Although sometimes there is a small break at the junction between the distributions of the two fractions, they fall on a straight line on the log-normal scale within experimental error as expected from the results of other workers⁽¹⁴⁾. In general, the particle size distributions measured with the optical microscopy method agreed very well with the results obtained from sieving (95% by weight of particles passing through a 28-mesh screen) for the three base coals.

3.4 Washability Analysis

The objective of this subtask is to collect washability data on the three base coals. The data can be used for comparison with agglomeration test results. Washability analysis on the three base coals was performed by BCR laboratory using standard ASTM method D4371⁽¹⁵⁾. The sink/float washability tests were conducted using 200 mesh x 0 coal samples of the three base coals at specific gravities of 1.3, 1.35, 1.4, 1.6, and 1.8. The following experimental procedure was used:

1. An aliquot (split) of as received sample (about 20 g, if available) was placed in drying oven set at

105 °C for 1 hour.

2. Four hundred fifty milliliter capacity centrifuge "tubes" were half-filled with gravity media.
3. A dried sample was poured into centrifuge tube, about 10 drops of Coal Dyne 100 (wetting agent) were added, and the coal/gravity slurry stirred.
4. The four sample/gravity centrifuge tubes were counter-balanced by adding gravity solution to within approximately 0.5" of the rim.
5. The tubes were then centrifuged at 1500 rpm for 20 min. The centrifuge was turned off and allowed to coast to a stop.
6. The tubes were removed. The "consolidated" coal particles were scooped from the top (float) and "poured" into a pre-weighed, identified fluted filter paper. The scoop was rinsed with the appropriate gravity media. A stopper was placed into the centrifuge tube (separating float and sink material). The sample/solution was poured into the filter paper and rinsed until "clean". The stopper was removed and was rinsed into the float containing filter paper.
7. The sink fraction retained in the lower portion of the tube was poured into a preweighed filter paper designated "sink" and rinsed with the gravity media until "clean".
8. The float and sink fractions were allowed to drain into beakers, and the gravity liquid was collected and retained for further use.
9. The float and sink samples were then rinsed with methanol. After draining, the sample-containing filter papers were placed into a 105 °C oven, dried and weighed. The sample weight was determined according to:

$$\text{Sample Weight} = \text{Sample} + \text{Filter paper} - \text{Filter paper (original)} \quad (3.2)$$

The experimental data are tabulated in Tables 3.4-1 through 3.4-3 for the three base coals. It was found that at the 200 mesh x 0 coal particle size, the separations did not show a "clear" interface between the float and sink layers (at any and all gravity levels), which may be interpreted as "high" percentages of near-gravity material (as a function of particle size and/or method of separation).

The washability analysis work was conducted by Mr. Richard G. Moses and Mr. Bob Tomich at BCR laboratory. QA/QC on their analytical activities was carried out by Westinghouse Advanced Energy Systems. During the surveillance, the following areas and activities were assessed:

- Coal sample handling and storage
- Sample preparation and process control
- Calibration of test equipment and measuring devices
- Personnel knowledge and process application
- Analytical data collection and recording

All these activities were found to be in compliance with good laboratory practice. Nine samples were gravity separated and analyzed for yield, ash content, and sulfur content. The samples were then oven-dried and reanalyzed to see if this would improve the repeatability and consistency of the results. The resulting data were statistically analyzed as reported in Tables 3.4-4 and 3.4-5. Based on the analysis of the data, the following conclusions were drawn:

1. Repeatability of composite ash content is good, both for as-received and moisture corrected samples, as reflected by a small standard deviation about the mean.
2. Repeatability of total ash content in float is reasonable, with a standard deviation of approximately 8% of the mean.
3. Yield repeatability is poor, with a standard deviation approaching 30% of the mean.
4. The t-test, with a 95% confidence interval, shows no discernible statistical difference between the as-received and moisture corrected data.

The poor yield repeatability in the washability analysis of 200 mesh x 0 coal samples is caused by suspended hang-up of near-gravity material which clouds the interface between float and sink material and significantly affects the determination of yield. Another possible source of error is the material retained on the filter paper used to remove the heavy liquid from the solids. In order to obtain the "best" yield values possible, the following steps were taken by BCR laboratory:

1. Individual separates from the sequential cumulative float analyses were calculated, and some fractions that showed anomalously high quality from higher gravity levels of separation were rewashed.
2. All cumulative float and sink fractions were retained and analyzed for ash and total sulfur to determine material consist relative to the feed material.
3. Random cumulative sink separates were selected and analyzed for pyritic sulfur and calorific value to compare with feed sample.
4. The filter paper from float and sink fractions were collected and analyzed to determine its effect on ash content.

3.5 Pyrite Size and Association

Pyritic mineral matter was analyzed microscopically in terms of frequency distribution by size and association. Splits of the 28 mesh x 0 and 200 mesh x 0 coal samples were mounted in an epoxy plastic and formed into cylindrical pellets under a pressure of 5000 psig. Each of the pellets was ground and polished for microscopic

analysis. Reflected light was used with a Leitz Ortholux microscope equipped with 60x fluoride oil-immersion objective, giving a magnification of 720 diameters. A whipple disc graticule was used in the 10x ocular for defining the count area and for measuring sizes.

To measure pyrite for the 28 mesh x 0 coal samples, the area within the boundaries of the whipple graticule was analyzed for each microscopic field of observation. The graticule is a square that is divided into 100 smaller squares and contains one of the smaller squares that is subdivided into 25 subsquares. At the magnification used for the analysis the graticule measured 100 microns on an edge so that each of the 100 smaller squares included on the graticule measured 10 microns on an edge and the subsquares into which one of the 10 micron squares is divided measured 2 microns on an edge.

For counting, the sample was advanced using a mechanical stage so that each field of observation connected to the adjacent field to form a continuous traverse through the sample. All pyrite particles that touched the left line of the traverse were included in the count, and all particles which touched the right edge of the traverse were excluded. Most of the pyrite particles were symmetrical. An average diameter was estimated for asymmetrical forms.

Each pyrite particle that was measured was placed in one of three categories of association which consisted of locked, semi-locked, and free. Locked pyrite is completely surrounded by coal while semi-locked pyrite is coated in part by coal but contains uncoated pyrite. Free pyrite contains no observable coal coating. A total of 500 particles of pyrite were measured per sample and assigned to one of the association categories.

In order to obtain a more useful representation of the pyrite size distribution it is desirable to have a three-dimensional frequency distribution of particle size. The three-dimensional frequency distribution can then be used to obtain a volume percent distribution as a function of pyrite particle size.

The problem of determining spatial size distributions from two-dimensional measurements was discussed by Underwood⁽¹⁶⁾. In general, the analyses are based on the assumptions that: (a) the particles are spherical; and (b) the distribution of particle sizes can be represented by a discontinuous distribution. Appendix C describes the procedure for generating a three-dimensional size distribution from a two-dimensional size distribution that satisfies the assumptions mentioned above. A computer program, also listed in Appendix C, was written in BASIC in order to perform this procedure.

The photomicrographs in Figures 3.5-1, 3.5-2, and 3.5-3 show the general microscopic appearance of the 200 mesh x 0 size coal from each of the three base coals. Tables 3.5-1 through 3.5-6 show the results obtained for the three base coals. For some of the 3-D frequency and volume distribution percentages, negative results were obtained due to inaccurate statistics in the two-dimensional distribution (see Appendix C). Because the particle size range studied is very wide (especially for 28 mesh x 0 samples), the number of particles counted

must be sufficiently large in order to obtain a statistically acceptable histogram of number frequency versus diameter.

A comparison of the volume distribution data for 28 mesh x 0 and 200 mesh x 0 pyrite particles reveals the importance of grinding for pyrite liberation. Figures 3.5-4 and 3.5-5 show the association characteristics of pyrite particles for the 28 mesh x 0 and the 200 mesh x 0 samples, respectively. For Upper Freeport and Pittsburgh #8 coals, the data indicate that a significant reduction in the amount of locked and semi-locked pyrite occurs when the sample is ground finer. For Illinois #6 coal, however, the data do not support the same finding. This coal may contain two types of pyrite particles: large (> 600 microns) and small (< 75 microns). The larger ones can be easily liberated at the 28 mesh x 0 grinding level while the smaller particles (< 75 microns) can not be liberated even at the 200 mesh x 0 grinding level.

3.6 Morphological Characterization

The objective of this subtask is to characterize the morphology of coal and pyrite particles in order to allow for comparisons among coals and to follow changes in morphology with coal grinding and surface modification methods.

3.6.1 Morphology of Coal Particles

The morphology of coal particles influences directly the behavior of coal in grinding and agglomeration processes. For instance, roughness affects both the attachment and detachment of coal particles to the agglomerant. Optical microscopic techniques coupled with image analysis have been used for morphological characterization of coal particles⁽¹⁷⁾. However, this method is limited to particles larger than 1 or 2 microns. The Scanning Electron Microscope (SEM), on the other hand, has a resolution in excess of 10 nm in the secondary electron imaging mode. This higher resolution makes the SEM well suited for morphological analysis of fine particles. The SEM images can also be processed in the Leitz TAS-plus image analyzer.

SEM micrographs are obtained from free particles dispersions in a volatile medium (such as alcohols). For observation, the volatile medium is evaporated and then the particles are coated with 20 nm of palladium.

The ratio of the length of horizontal chords to vertical chords were measured on all three base coals. The ratio distributions of the three base coals are similar to one another as shown in Figure 3.6.1-1.

3.6.2 Fourier Analysis

The morphology of 200 mesh x 0 Upper Freeport coal particles was studied by Fourier analysis of digitized optical microscope images generated and digitized on the semiautomatic analyzer of Professor Kennedy, Department of Geology and Planetary Sciences, University of Pittsburgh. Twenty four harmonics of Fourier components were generated. They could be summed, taking into account their phase angle, to regenerate the shape of the particles. Each component was a closed waveform around the perimeter of the particle. Low harmonics go around the particle in a few wavelengths and high harmonics circumscribe the particle with many closely spaced wavelengths (see Figure 3.6.2-1). Thus, the harmonic of $n = 2$ is indicative of the elongation of the particles and harmonics up to 6 are indicative of the gross shape of the particles while higher numbers are indicative of the fine scale of the perimeter of the particles, smoothness vs. roughness. A fine description of shape required more edge points than particle size analysis. The program used here requires 200 edge points per particle to be analyzed, so that under usual magnification conditions fine particles could not be analyzed. Thus the morphological analysis was performed on narrow size fractions. It is possible that the morphology of the particles may vary for different size fractions of the same coal.

The summary of the output of the Fourier analysis of the morphology of particles about 25 microns in diameter for Upper Freeport coal ground to 200 mesh x 0 is given in Table 3.6.2-1. The results shown here are for 25 particles. This analysis was also performed on 200 particles. The major amplitude components are for $n = 2$ and $n = 3$ which indicate an elongation and triangular distortion from the spherical shape as indicated in Figure 3.6.2-1. These specific harmonic amplitudes and one or two higher ones may be sufficient to compare the morphological characteristics of different coals or the influence of a surface modification process. On the other hand, the whole amplitude spectrum may be used easily for this comparison by plotting log mean amplitude versus n , for each coal or its beneficiated fraction.

3.6.3 Size and Morphology of Pyrite

Morphology and association of the pyrite was determined from SEM micrographs obtained using the SEM by backscattered electron imaging (BEI) with a segmented detector set up to respond mostly to atomic number contrast. This is performed with an accelerating voltage of 25 kV and a beam current of the order of 2 nanoamperes. Figure 3.6.3-1 illustrates the procedure and the initial problem. In the top micrograph, particles of pyrites (white) which are associated with some silicates can be seen, in particular a large grain of quartz (light grey). Thus with the more usual secondary electron imaging the shade of greys may not allow a consistent separation of pyrites from silicates by image analyzers. Once the identity of the phases has been checked by X-ray microanalysis, the BEI conditions are set to obtain the lower image in which the pyrites are bright and the phases of lower atomic number, silicates and coal macerals are black. This contrast is ideal for

image analysis.

The pyrite size distribution was measured on photographs of backscattered electron images obtained in the SEM. Distributions obtained with about 400 particles are given in Figure 3.6.3-2. A simple qualitative description of the particle shape was also obtained using the chord ratio method. The ratios of the chord lengths (horizontal/vertical) distribution, shown in Figure 3.6.3-3, indicate that the pyrite shapes are generally equiaxed and similar for the three base coals.

3.7 Surface Functional Groups

The objective of this analytical subtask is to monitor the functional group changes on the surface and in the bulk near the surface layer of the coal as a function of grinding and treatment. This was achieved by using Diffuse Reflectance Infrared Fourier Transform (DRIFT) Spectroscopy to obtain an oxidation index in the same manner employed by researchers at USX⁽¹⁸⁾ and CONOCO⁽¹⁹⁾. The oxidation index is defined as the ratio of the integrated intensity of the carbonyl band ($1635 - 1850 \text{ cm}^{-1}$) to that of the C-H stretching band ($2746 - 3194 \text{ cm}^{-1}$) in the diffused reflectance FTIR spectrum. The limits associated with the latter area may vary slightly depending upon the baseline of the spectrum. A decrease in the $2746 - 3194 \text{ cm}^{-1}$ band is attributed to the loss of C-H groups and an increase in the $1635 - 1850 \text{ cm}^{-1}$ band to the production of carbonyl groups. Both absorption bands are related to the organic structure of coal and the ratio may provide a good indication of changes in the organic matrix.

Sampling involves the loading of powdered coal into the sample holder (cup). The excess coal was smoothed off with a spatula leaving a visibly homogeneous surface to be irradiated. The sample was then placed in a Digilab 20 FTIR spectrometer. The sample cell was purged with N_2 and allowed to equilibrate for ten minutes while residual moisture was allowed to evaporate from the coal surface. One thousand scans were acquired and averaged. The resulting spectrum was presented in a standard KEBULKA-MUNG format. At least two introductions each resulting in spectra of 1000 scans are completed on a coal sample in a given day. The spectral areas of interest were digitized and integrated before computing an oxidation index. To establish the analytical procedure, samples of Texas Lignite (supplied by CONOCO Research), and internally generated Upper Freeport, Pittsburgh #8, and oxidized as well as unoxidized Illinois #6 coals were used.

A typical DRIFT spectrum for a 28 mesh x 0 Upper Freeport coal sample is presented in Figure 3.7-1. The shaded areas are the integrated intensities of the carbonyl band and the C-H stretching band. Table 3.7-1 shows that the precision in the oxidation index measurements is good. Column 2 (referring to the second loading) indicates the precision associated with replicate spectra is improved when the number of scans is increased from 200 to 1000. In addition, signal to noise is greatly enhanced when using 1000 scans. The

oxidation index obtained from the average of these spectra is 0.71 with a standard deviation of 0.05. This value is relatively low since for Pittsburgh #8 coal is 1.08, for Illinois #6 coal is 1.60, and for Lignite is near 4.0.

3.8 Surface Composition

The adsorption of colloidal precipitates of cations frequently found in coal, such as calcium, magnesium, iron, and aluminum is a function of the properties of the coal/water slurry. The modification of the slurry pH, the addition of salts or other chemicals may influence adsorption of slime, and therefore, the hydrophobicity of the coal surface. This, in turn, will affect the agglomeration performance. Two analytical techniques, the Laser Microprobe Mass Analysis (LAMMA) and the Electron Spectroscopy for Chemical Analysis (ESCA) were utilized to analyze coal surface composition.

3.8.1 Laser Microprobe Mass Analysis (LAMMA)

The LAMMA technique samples the surface to a depth of approximately one micron providing data for surface components and the bulk near the surface. LAMMA data are given in percent total ionization. While the percent total ionization does not represent absolute concentrations, changes in surface concentration caused by physical and chemical treatments can be followed. To determine absolute concentrations, extensive calibration and correction for ionization efficiency and other factors are required. Use of percent total ionization is a standard technique in mass spectrometry where sensitivity factors are not readily available. Changes in percent total ionization (changes in relative peak intensities) will be proportional to changes in concentrations of the elements.

Analyses of the surface composition of coal using LAMMA have been conducted by a number of investigators⁽²⁰⁻²⁴⁾. In this project, an experimental procedure was established for determining the percent total ionization of elements Li, Na, Mg, Al, Si, S, K, Ca, Ti, and Fe on the surfaces of coal particles. The procedure was tested with a 28 mesh x 0 Upper Freeport coal sample.

Surface composition analysis was performed using the Leybold-Heraeus LAMMA-1000. LAMMA analysis of coal constituents has been previously reported by Lyons and Hercules^(25,26). Samples were mounted on an x,y,z micromanipulator and could be viewed using a 250x microscope. The sample was then evacuated to a base pressure of 1×10^{-6} torr and ionized using a pulsed Nd:YAG laser; frequency quadrupled to 265 nm and having a diameter of approximately 5 microns. The ions were extracted normal to the sample surface, accelerated into a time-of-flight mass spectrometer, and detected by a Cu-Be secondary electron multiplier. A complete mass spectrum was obtained with each laser pulse at a spectral resolution of approximately 800 at a

mass to charge ratio (m/z) of 350. Samples were mounted on double sided sticky tape, supported by zinc foil, and placed directly into the LAMMA sample chamber.

A procedure was designed to analyze a representative surface of each coal particle, and from the analysis of 50 particles, an averaged value for each element could be assigned. This value should then be representative of the surface (1 micron depth) of the coal. The procedure is as follows:

1. Using the 250x LAMMA microscope, a coal particle was selected which has a surface area of at least 1×10^4 sq. microns in one focal plane. This was to insure that lateral movement of the sample would keep the laser at constant focus as long as analysis is done in the designated area.
2. The laser was fired, data were collected, and the sample was then moved laterally to a fresh surface. This sequence was continued ten times. A distance of approximately 100 microns was maintained between each laser crater.
3. Steps 1 and 2 were continued on 50 coal particles.
4. Data for each analysis site were averaged and converted to percent of total ionization for each element. Percent of total ionization was calculated by dividing the peak height for each element by the sum of the peak heights of the elements analyzed and then multiplying by 100.
5. Percent of total ionization data for each element at each analysis site was averaged to give average percent total ionization of each element for a given coal type.
6. The analysis of 50 coal particles constituted one spectrum. Ten spectra constituted one run. Repeat runs were conducted to determine consistency of the data.

Many of the inorganic compounds present in coal are found in a variety of different types of submicroscopic clays, each with its own elemental distribution, and each dispersed throughout the coal. When using a microprobe technique such as LAMMA, which has an analysis diameter of approximately 5 microns, one must then be aware that the consistency of the elemental distributions between spectra can vary, since each analysis site can contain a different type of clay. An average of many analysis sites must then be taken in order to obtain data representative of the coal surface.

A typical LAMMA spectrum (an average of 50 spectra) of Upper Freeport coal is shown in Figure 3.8.1-1. Percent of total ionization values are listed in Table 3.8.1-1 for duplicate runs.

3.8.2 Electron Spectroscopy for Chemical Analysis (ESCA)

X-ray Photoelectron Spectroscopy (XPS) or Electron Spectroscopy for Chemical Analysis (ESCA) was utilized as a spectroscopic tool for coal analysis. ESCA offers the advantage of sampling the surface region to a depth of approximately 20 to 50 angstroms. This should be contrasted with a technique such as LAMMA which samples the near surface region (approximately 1 micron depth). This technique was used to monitor changes

in surface composition as a result of performing treatments or agglomeration tests under different conditions.

An ESCA experiment involves the determination of the binding energies of both core and valence electrons. This is achieved by measuring the kinetic energies of electrons photoemitted from a solid when irradiated in vacuum with near monochromatic X-ray radiation. The kinetic energies of the photoelectrons are essentially the difference between the energy of the incident photon and the binding energy of the electrons. The electron binding energies are element specific. For a given element and energy level, the binding is also affected by the electronic environment. Any change in this environment will result in a corresponding change in the binding energy, which can be measured by ESCA. Identification of the oxidation state of an element and the nature of the functional group present is therefore possible. Due to the finite inelastic mean free path of the photoemitted electrons, ESCA signals originate from the surface. Typical mean free path values are 20 to 50 angstroms. ESCA signals are averaged from an area of approximately 10 mm².

A Leybold Heraeus LHS-10 photoelectron spectrometer was used for all data collection. The LHS-10 uses an Aluminum anode (Al K_a = 1486.6 eV) with a hemispherical analyzer operating in the constant pass energy mode (100 eV). The power of the X-ray source is 240 W (12 kV and 20 mA), and the operating pressure of the spectrometer during data acquisition is typically below 5 x 10⁻⁸ Torr. The spectrometer is interfaced with an IBM PC compatible where subsequent data analysis is performed. Samples are prepared by sprinkling the coal particles on double-sided sticky tape on silver foil. Peak areas are measured assuming an integral background.

Survey spectra of Upper Freeport, Pittsburgh #8, and Illinois #6 coals are shown in Figure 3.8.2-1. The carbon 1s and oxygen 1s were the most intense peaks in the spectra. Smaller peaks attributed to sulfur 2p, silicon 2p, and iron 2p were also detected. Narrow scan spectra for these five elements are shown in Figures 3.8.2-2 through 3.8.2-5. In general, little change in peak shape and position was observed for the three coals. The sulfur 2p spectra show two peaks, one at 171.5 eV due to sulfur in sulfate form, and one at 166 eV due to pyritic and organic sulfur (sulfide form).

3.9 Quantitative Distribution of Iron Species

The objective of this analysis is to monitor the transformation and/or decrease in concentration of FeS₂ (pyrite) in the three base coals as a function of particle size and treatment. The identification and quantification of the iron species can be obtained using Mössbauer spectroscopy. The utilization of Mössbauer for characterization of iron species in coal has been demonstrated by Montano et al.⁽²⁷⁻³¹⁾ and others⁽³²⁻³⁴⁾. It has been shown that the relative amount of iron sulfides (FeS₂, Fe_{3-x}S_x) and iron sulfate can be used to monitor the extent of thermal decomposition or the effect of other treatment on coals.

Transmission Mössbauer spectra were obtained using a Mössbauer Effect Spectrometer (Model AM-1), equipped with a 100 mCi ^{57}Co source at Nuclear Scientific and Engineering Corporation (Pittsburgh, PA). The source was calibrated with sodium nitroprusside, and all isomer shifts and velocity scales were referenced to this standard. The velocity scale was given in mm/s representing the Doppler velocity of the source. The Doppler effect was used to vary the energy of the 14.4 keV gamma ray which was emitted by the ^{57}Co source. The multichannel analyzer was interfaced to an Apple IIe microcomputer for data collection. Sample holders consisted of a 1 inch hole countersunk (1/16") into the center of a 1.5" x 1.5" x 0.125" piece of plexiglass. Powdered coal samples were covered and sealed with tape to protect from exposure to air. The samples were measured at ambient temperature ($T = 295\text{ K}$), and the scan time per sample ranged from 50 to 100 hours in order to obtain high quality spectra. The various spectral components (Isomer shift, Quadruple splitting, Hyperfine magnetic field) were determined from curve fitting analysis. The curve fitting procedure assumes Lorentzian line shapes using a non-linear least squares (NLLS) optimization routine⁽³⁵⁾. The percent area reported is the area for a given species with respect to the total area of the spectrum.

Figures 3.9-1 through 3.9-3 show representative curve fit spectra for the three base coals ground to 28 mesh x 0. It can be seen that the dominant spectral feature is a doublet centered about 0.60 mm/s. According to the hyperfine parameters listed in Table 3.9-1, this species is identified as FeS_2 . The spectra of the three base coals also indicate that an additional spectral feature is present at about 2.8 - 3.0 mm/s (the contribution to the Illinois #6 spectrum is small). It should be noted that while one half of the minor component spectrum ($\sim 2.8 - 3.0\text{ mm/s}$) can clearly be seen, the other half ($\sim 0.15\text{ mm/s}$) of the spectrum overlaps with the low velocity component of the FeS_2 doublet. From the hyperfine parameters (Table 3.9-1), the minor component is recognized to be an Fe^{+2} species. In addition, the results obtained also reveal that for the Upper Freeport and Pittsburgh #8 coals, two sets of doublets were required to obtain good curve fits of the spectra. From previous work^(27,28,32), these spectral components are known as either iron sulfate (FeSO_4) or iron based clays. The relative contribution of this minor component is dependent upon the type of base coal. While the identity of the remaining phase is unknown (clay or sulfate), this does not limit the use of Mössbauer for the analysis of the oxidation of coal. During the treatment of the coals, oxidation will cause a transformation of the pyrite phase into the sulfate phase. The clays are thermally stable, and their relative spectral contributions are not expected to vary upon oxidation. Thus the variation in the relative contribution of the pyrite phase, with respect to the entire spectral envelope, can be used to monitor the effect of the treatment on the state of the iron species present in the coals.

3.10 Coal Wettability

The objective of this subtask was to establish a reliable and accurate method to determine the relative surface wettability of different coal samples. An experimental procedure for measuring contact angle on coal pellets was established and tested with samples of three base coal dry ground to 200 mesh x 0.

The pellets were prepared by loading 5 g of coal in a Buehler Simplotter II pelletizer and applying a pressure of 1000 psi for one minute, 2000 psi for another minute, then 3000 psi for additional 10 min, and finally 4000 psi for 20 min. This procedure produced a 1 inch diameter by 1/2 inch thick pellet. The pellet was then removed and placed on a stage in front of an optical measurement device able to measure angles with a precision of $\pm 1^\circ$. A drop (0.2 - 0.3 ml) of double distilled water was placed at the center of the pellet with a syringe. The size of the drop was made large enough so that any further addition of water would not increase drop height. The contact angle was measured as a function of time using a goniometer manufactured by Gaertner Scientific Corporation, Chicago, IL.

Upper Freeport and Pittsburgh #8 coal samples exhibited a hydrophobic character, as evidenced by high contact angles of 118° and 92° , respectively. The Illinois #6 coal sample, on the other hand, exhibited zero contact angle, which is an indication of the extreme hydrophilic nature of this coal.

Surveillance of contact angle measurement practice was carried out by Westinghouse Advanced Energy Systems. It consists of inspection of the experimental procedure and evaluation of experimental data. Data were evaluated for four samples, two for Pittsburgh #8 coal (P8/S4 and P8/S5) and two for Upper Freeport coal (UI/S3 and UI/S4). The data reported for these samples are listed in Table 3.10-1. The statistics of the collected data are also given in the same table. The data analysis indicates that a confidence level of 99.7% can be obtained using the equipment, methods, and procedure presently developed with a spread of $\pm 7^\circ$ from the mean.

3.11 Zeta Potential and pH Measurement

The objective of this subtask is to characterize the electrochemical properties of coal particles at the solid/liquid interface in terms of pH value and zeta potential. The results are helpful in the selection of surface modification reagents and in the analysis of agglomeration test results. The following experimental procedure was developed for zeta potential and pH measurements using a Zeta-Meter (ZM-80) and a pH-Meter (Expandomatic SS-2):

1. Glassware Cleaning: All the glassware used in the experiments was subjected to a rigorous cleaning procedure. It was first washed with a soap solution and then soaked in a concentrated cleaning solution of sulfuric-chromic acids (chromerge) for 24 hours. Subsequently, the

glassware was rinsed with double distilled water and dried before usage. It is essential to maintain extreme cleanliness because slight contamination might adversely affect the results.

2. **Sample Preparation:** Representative coal samples were placed in a mortar and pestle and ground until a finely divided powder was obtained. A coal slurry with a concentration of less than 0.1% (by weight) was prepared using double distilled water with/without chemical additives. The coal fines were then mixed with the solution for 30 min. The slurry was further dispersed in an ultrasonic vibrator for 15 min before readings were taken. For all sample preparations, the double distilled water should have a specific conductance less than 5 microohms/cm in order to obtain accurate results.
3. To determine effects of pH values on the zeta potentials of the three base coals, a hydrochloric acid solution or an ammonium hydroxide solution were added to adjust the pH-value of the coal/water slurry. The slurry was mixed with a magnetic mixer until a stable pH value was reached.
4. **Measurement:** The sample was placed in an electrophoresis cell and observed under a microscope. When an appropriate D.C. voltage was applied, the particles with surface electrical charge moved toward the opposite electrode. The velocity of the particle movement was measured by timing individual particles on a microscope grid as they move from the start to the finish line. The average time was obtained by tracking 50 particles. The zeta potential of the sample was directly determined from a solution chart provided in the Zeta-Meter Manual⁽³⁶⁾.

Samples of the three base coals were used to test the experimental procedures. The double distilled water used had an original pH value of 5.6 and a specific conductance of 1 microohms/cm. The zeta potentials of the three base coals, together with pH values at a solid concentration of 0.1% (weight basis), are listed in Table 3.11-1. As can be seen, a good reproducibility was obtained from duplicate runs.

The zeta potential as a function of pH is shown in Figure 3.11-1 for the three base coals. The same trend was observed for all three coals, that is, the zeta potential decreases as the pH value of the slurry increases. The isoelectric point was found at pH 3.5, 4.3, and 3.5 for Upper Freeport, Pittsburgh #8, and Illinois #6 coals, respectively.

A QA/QC evaluation of the zeta potential measurement was conducted by Westinghouse Advanced Energy Systems. Statistical analysis of reproducibility and variance of the process and the operator for zeta potential measurements of fine coal suspensions was conducted during surveillance activities. The process variance analysis for the zeta potential measurements within any three samples was determined to be 1.949, and a variance of 8.3 between any sample (see Table 3.11-2). During this analysis, it was noted that only two data points were outside the two standard error (SE) of the mean resulting in a process confidence level of 95%.

A study of the operator's ability to measure the cumulative particles tracking time (the velocity of the particle movement through the electrophoresis cell) was performed as shown in Table 3.11-3. The data collected were from the three samples and totaled 15 data points. From this analysis, it is determined that the mean cumulative particles tracking time and the operators repeatability is $34.353 \pm$ two Standard Deviations (± 3.21

s) resulting in a operators confidence level of 95%. In summary, the QA/QC evaluation indicated that the process and operator's measurement techniques were under control.

3.12 Gieseler Test

The objective of this subtask is to use the Gieseler test, ASTM D2639-74⁽³⁷⁾, to detect the degree of oxidation of coal. The Gieseler test is used as an indication of state of oxidation, particularly to compare freshly mined samples, with these samples exposed to atmosphere following mining. It does not offer a direct comparison of the state of oxidation among different coals.

Plasticity of each of the three base coal samples was measured using the Gieseler Plastometer (manual unit) as specified under former ASTM method D3812-69. The experimental data are listed in Table 3.12-1. Repeatability is 10% of the maximum dial divisions with key temperatures within 5 °C. The numbers reported in Table 3.12-1 represent:

Maximum Dial Division indicates the maximum fluidity or maximum rate of dial movement in dial divisions per minute.

Start Temperature is the initial softening temperature or the point at which coal shows first softening.

Maximum Temperature is the maximum fluidity temperature, at which the dial movement reaches the maximum rate.

Finish Temperature is the solidification temperature, at which the dial movement stops.

Range is the fluid or plastic range defined as the difference between the finish and start temperatures.

As can be seen from Table 3.12-1, Upper Freeport coal has the highest maximum fluidity and the widest plastic range followed by Pittsburgh #8 and then Illinois #6 coals. These data provide some information about the type of the three base coals since strong-coking, high-and medium-volatile coals usually show high fluidities and wide plastic ranges while poor-coking high-volatile coals as well as low-volatile coals have low fluidities and narrow plastic ranges. In addition, these results may be used to compare fresh or unweathered with weathered or oxidized coals since weathering and oxidation tend to decrease the maximum fluidity of coal samples.

3.13 Surface Areas

The objective of this subtask is to measure surface areas of coal samples in order to establish a basis for comparison and correlation in coal grinding and surface modification studies. An experimental procedure for

surface area measurement of coal samples was established.

The surface areas were determined by adsorption of CO₂ on coal particles at room temperature in a BET apparatus (Micromeritics #2100) at pressures below atmospheric. Coal samples were degassed overnight by heating and pumping with a liquid nitrogen trapped vacuum system. Carbon dioxide was admitted in the evacuated sample tube, and the pressure (P) was read after equilibrium had been reached with the sample. Additional CO₂ was then admitted at a higher pressure, and the procedure was repeated with 3 or more adsorption points. The volumes of CO₂ adsorbed per gram of sample (V) measured at STP, as function of relative pressure P/P₀ were treated according to the Dubinin-Polanyi method⁽³⁸⁾. A plot of log V vs. [log (P/P₀)]² yielded a straight line. The extrapolation to P = P₀ gave the intercept V₀ and the surface area was calculated as:

$$S \text{ (m}^2\text{/g)} = 6.8 V_0 \text{ (cm}^3\text{/g)} \quad (3.2)$$

The experimental data of the surface area measurement for Upper Freeport coal are shown in Figure 3.13-1 for two independent runs. The two curves are slightly shifted showing the difference in the measured surface areas. The magnitude of the surface areas appear reasonable. The determination of the surface areas of coals by this method has been discussed in detail in the literature and has been claimed to give the best approximation to the total surface area of coal⁽³⁸⁻⁴⁰⁾.

3.14 Available Inorganic Ions Analysis

The objective of this analysis is to determine soluble inorganic ions including sulfate and alkali and alkaline earth cations leached from coal samples. Extensive work has been reported for the use of Inductively Coupled Plasma (ICP) technique for simultaneous multi-element determination of trace, minor, and/or major elements in various materials.

The method was tested using two batches of Illinois #6 coal sampled, delumped, pulverized, and wet ground independently on different days. The slurry was vacuum filtered using Whatman #42 filter paper to remove any solid particles in the filtrate. A sample of the distilled water used to prepare the slurry was analyzed serving as a blank reference. This was followed by a qualitative analysis to identify all possible elements present in the filtrate sample. Quantitative analysis was then conducted on the elements which showed significant amounts in the filtrate according to the results from the qualitative analysis. The ICP analyses were conducted at Pittsburgh Applied Research Corporation (PARC)⁽⁴¹⁻⁴³⁾. The spectrometer used was a Bausch and Lomb (Applied Research Laboratories) ARL Model S 34000 ICP. The instrumental control and data manipulation and storage were provided by a Digital Equipment Corp. PDP 11/03-L computer. The accuracy

of the quantitative analysis is 0.1 ppm. The concentration of each element analyzed was determined based on the calibration data. The results obtained from the quantitative analyses of the samples are listed in Table 3.14-1. In general, there is good agreement between the two sets of data. The small differences in the element concentrations are within the experimental errors introduced by sampling preparation, which involves delumping, pulverizing, grinding, and filtering.

4.0 TASK 4: DEVELOPMENT OF STANDARD AGGLOMERATION TEST

The objective of this task was to develop a standardized agglomeration test procedure for the three base coals using n-pentane ($n\text{-C}_5\text{H}_{12}$) as agglomerant. The developed standardized agglomeration test was used to establish a baseline for evaluating the effect of a given grinding environment, reagent, or method of storage on Btu recovery and pyritic-sulfur rejection. A Waring blender was used as the agglomeration unit. It was modified and calibrated under different operating conditions. The experimental apparatus and procedures were developed and tested using samples of Pittsburgh #8 and Illinois #6 coals delumped and pulverized under argon and then ground in air to 28 mesh x 0 and 200 mesh x 0 particles using a Holmes Pulverizer and a stirred-ball mill, respectively.

4.1 Experimental Apparatus

Modifications of a stainless steel Waring blender (model 554), manufactured by Hamilton Beach Inc, NC, were made in our laboratory. A stainless steel cover was added with an injection port to allow the injection of agglomerant during mixing; a digital readout device was connected to monitor the mixing speed of the blender at any given set point; and baffles were placed inside the blender to prevent vortex formation during operation. A schematic diagram of the modified Waring blender is shown in Figure 4.1-1.

The mixing speed of the Waring blender was calibrated with and without water and with coal/water slurries. Calibration data obtained under different conditions are given in Table 4.1-1. In all cases, a linear relationship was obtained as shown in Figure 4.1-2. An average calibration curve was obtained from the data listed in Table 4.1-1 and plotted in Figure 4.1-3.

4.2 Experimental Procedure

Details of the coal sample preparation method and the standard agglomeration test procedures are discussed in the following.

4.2.1 Coal Sample Preparation

The coal samples used in the agglomeration tests were prepared as follows:

1. Coal samples were first delumped by a delumper (manufactured by Franklin Miller, Inc., East Orange, NJ) and then pulverized using a Holmes Pulverizer.

2. One kg of the pulverized coal was taken and divided into two equal parts. One part (about 500 grams) was sieved using a 28-mesh screen on a mechanical shaker.
3. The over sized (+28 mesh) coal particles were recycled through the Holmes Pulverizer and sieved as in step 1.
4. The oversized (+28 mesh) coal particles obtained from step 2 were crushed using a mortar and pestle and sieved as in step 2 until 99% by weight of all the coal passed through the 28-mesh screen.
5. The entire 500 g of 28 mesh x 0 coal sample was homogenized and divided into 10-g samples using the conning and quartering method.
6. The second 500 g of the pulverized coal sample were further ground to 200 mesh x 0 size in a stirred-ball mill. The dry grinding to 200 mesh x 0 was carried out using 13 kg of 3/16" stainless steel balls as the grinding medium. The grinding time was kept at 12 min.
7. The 500 grams of 200 mesh x 0 coal were also homogenized and sampled into small bags of 10 g each.

4.2.2 Standardized Agglomeration Tests

A schematic flow diagram illustrating the experimental procedure is shown in Figure 4.2.2-1. A step-by-step operating sequence was developed as follows:

1. A predetermined weight of water (480 or 490 g) was charged to the Waring blender.
2. A predetermined weight of feed coal (10 or 20 g) was added to the water in the Waring blender to obtain a predetermined slurry concentration.
3. The coal/water slurry was preconditioned by mixing at 14000 ± 500 rpm for 30 s to assure homogeneity of the slurry. Wetting of coal particles was visually observed. When all coal particles sank in the water phase, they were considered to be completely wet.
4. A predetermined weight of liquid n-pentane (5, 10 or 20 g) was injected into the blender using a precision syringe.
5. The n-pentane/coal/water slurry was mixed at a constant mixing speed (9000 ± 500 or 14000 ± 500 rpm) for a predetermined mixing time (15 or 30 s).
6. The mixing was stopped and the content of the blender was poured onto a 100 mesh screen. The agglomerate was retained on the screen while the unagglomerated coal fines (refuse material) dispersed in water was collected in a Gouch crucible filter unit.
7. The agglomerate was transferred from the screen to a filter paper (Whatman #1). Distilled water was used to wash the agglomerate out of the screen on the filter paper. Vacuum was applied to assist the removal of water from the agglomerate.
8. The coal fines (refuse) dispersed in the water which were collected in a Gouch crucible (see step 6), were vacuum filtered using a Whatman #1 filter paper.

9. Both filter papers containing agglomerate (clean coal product) and refuse were dried in an oven for 12 hours at 60 °C. The papers were stored in a desiccator immediately after being removed from the oven, and allowed to cool down to room temperature.
10. The filter papers containing the product and refuse were weighed using an analytical balance.
11. After the coal particles of the product and those from the refuse were separated from the filter papers, the filter papers containing residue coal particles were weighed again.
12. The net amounts of product and refuse collected from and retained on the filter papers were then calculated.
13. The collected product and refuse were homogenized individually, and representative samples were taken for ash and total sulfur analyses.

4.3 Calorific Values Calibration

Five samples at various ash contents were prepared for each base coal. The calorific values were determined by Coal Petrographic Associates, Inc. The data obtained were plotted against the ash contents in Figure 4.3-1. Correlation of the calorific values versus ash contents was made using linear regression. A straight line was found for each of the three base coals. Mathematically, the relations can be expressed as follows:

$$Y = 15467 - 177.24 X \quad \text{for Upper Freeport} \quad (4.1)$$

$$Y = 14380 - 162.98 X \quad \text{for Pittsburgh \#8} \quad (4.2)$$

$$Y = 13646 - 154.13 X \quad \text{for Illinois \#6} \quad (4.3)$$

where Y represents Btu/lb, and X is ash content. The straight line correlations are excellent for all three coals, with correlation coefficients being 99.9, 99.9, and 99.4 for Upper Freeport, Pittsburgh #8, and Illinois #6 coals, respectively. The results were used to evaluate calorific values of product, refuse, and feed coal samples in the agglomeration tests. The objective variables set for the analysis were ash rejection (ARJ), energy recovery (BTU), total sulfur rejection (SRJ), and pyritic sulfur rejection (PSRJ) defined as follows:

$$ARJ = 100 - Y A_p/A_f \quad (4.4)$$

$$BTU = Y (Btu/lb)_p / (Btu/lb)_f \quad (4.5)$$

$$SRJ = 100 - Y S_p/S_f \quad (4.6)$$

$$PSRJ = 100 - Y PS_p/PS_f \quad (4.7)$$

where A is ash content; S is total sulfur content; PS is pyritic sulfur content; and Y is overall yield in percentage. Subscripts r, p, and f represent refuse, product and feed, respectively.

4.4 Results and Discussion

The runs were carried out using Illinois #6 and Pittsburgh #8 coals according to the operating conditions listed in Tables 4.4-1 and 4.4-2 for 28 mesh x 0 and 200 mesh x 0 samples, respectively. For each experiment, two samples from the product coal (agglomerate) and two samples from the refuse were taken for ash, total sulfur, and pyritic sulfur analyses. The experiments were repeated to check the reproducibility of the data. The nomenclature used in this Section is given in Table 4.4-3.

A summary of the experimental data for Illinois #6 and Pittsburgh #8 coals are given in Tables 4.4-4 to 4.4-7. These tables show the results of duplicate runs. Two samples of the product and refuse coal were analyzed for each run. The ash and sulfur contents of the feed coal were also determined. The data show very good reproducibility for all duplicate runs. In addition, the overall yield and energy recovery of the replicate runs are also in good agreement with each other.

The effect of entrapped coal particles retained in filter paper during filtration (in collecting product and refuse samples) was determined by the weight change and the ash contents of the filter paper before and after filtration. As shown in Table 4.4-8, the overall material balance and ash balance of two representative runs improve dramatically when the entrapped coal particles retained in the filter paper are considered. These results further validated the experimental procedures used for the agglomeration tests.

5.0 TASK 5: GRINDING STUDIES

The objective of this task was to determine the effect of grinding coal to two sizes (28 mesh x 0 and 200 mesh x 0) using four grinding environments and three grinding media on the coal properties and the agglomeration process performance. For this purpose, a special environmental chamber was designed and constructed for grinding under controlled environments. Experimental procedures for sampling and grinding raw coal samples in the chamber were developed. After calibration of grinding equipment, several drums of inerted coal were delumped and pulverized. Samples of the three base coals were ground to 28 mesh x 0 and 200 mesh x 0 either in air or under argon and with/without distilled water. Wet grinding of pulverized samples to 200 mesh x 0 in the presence of n-pentane, n-heptane, and cyclohexane was also conducted. The effects of the grinding methods and the addition of the three hydrocarbons during grinding were evaluated in terms of agglomeration test results. Selected coal samples were analyzed using the analytical methods established in Task 3.

5.1 Experimental

A special environmental chamber was designed and built to carry out dry and wet grinding operations under argon and air atmospheres. A modified stirred-ball mill, a Holmes pulverizer, and a ceramic jar mill were calibrated in terms of particle size as a function of grinding time in order to obtain 28 mesh x 0 and 200 mesh x 0 coal samples.

5.1.1 Grinding Equipment

As shown in Figure 5.1.1-1, the environmental chamber consists of six compartments allowing for sampling, delumping, pulverizing, grinding, and packaging coal samples. The chamber is constructed of plexiglass sheets glued to a wooden frame. Rubber gloves, glued to the holes on the plexiglass walls, are used to manipulate the samples and to operate the equipment in the chamber.

In preparing and grinding coal samples under argon, the chamber was sealed and purged with argon. A positive pressure of argon in the chamber, monitored by a manometer, was maintained during the operation, and the oxygen content was detected by a MSA Oxygen Indicator Model 245. It was found that the oxygen level in the chamber could be reduced from 21% to 2.5%.

A Holmes model 251 pulverizer was utilized for dry grinding to 14 mesh x 0 and 28 mesh x 0. A 2-liter ceramic Norton jar mill made by Fisher Scientific was used for wet grinding to 28 mesh x 0. A stirred-ball mill was used for wet grinding to 200 mesh x 0.

The stirred-ball mill was modified for grinding coal samples with light hydrocarbons. A stainless steel lid was designed for the stirred-ball mill container in order to: (1) control pressure buildup caused by the evaporation of the grinding additive; (2) control the release of the evaporated grinding additive and allow its vapors to be condensed in a cold trap and subsequently measured; (3) control the flow of inert gas into and out of the container; (4) allow for a thermocouple to be inserted into the container, while maintaining an air-tight seal, to monitor the temperature inside the container; and (5) allow for liquids to be introduced into the container. The design of the lid is shown in Figures 5.1.1-2 through 5.1.1-4. The lid is sealed to a metal lip, welded to the top of the container, by a static o-ring flange (see Figure 5.1.1-2). The lid provides a sealed opening for the shaft of the stirred-ball mill using a pair of o-rings on the shaft creating a dynamic seal, as can be seen in Figure 5.1.1-4. Three 1/4" Swagelok fittings are welded at the top of the lid to allow for venting and gas flow, for introducing liquids under a controlled environment, and for a thermocouple to be used to monitor the temperature inside the container.

5.1.2 Grinding Equipment Calibrations

Calibration curves were obtained for each equipment under dry and wet grinding conditions.

5.1.2.1 Dry Grinding in the Stirred-ball Mill

The dry grinding calibration of the stirred-ball mill was grinding container was carried out using 8.0 kg of 3/8" stainless steel balls and 0.25 kg of pulverized Upper Freeport coal (14 mesh x 0). After being ground for a specified time, the coal sample was sieved to determine the percentage of particles that passed through a 200 mesh screen. The particle size distribution of the sample was determined by optical microscopy.

The calibration curve, shown in Figure 5.1.2.1-1, was plotted as weight percent of coal passing through a 200 mesh sieve versus grinding time. It can be seen that after 5 min grinding time, the curve approaches to an asymptotic value of about 93%. A grinding time of 10 min was chosen to provide 200 mesh x 0 samples by dry grinding.

5.1.2.2 Wet Grinding in the Stirred-ball Mill

The wet grinding calibration of the stirred-ball mill was grinding container was carried out using 8.0 kg of 3/16" stainless steel balls, 0.25 kg of pulverized Upper Freeport coal (14 mesh x 0), and 1000 ml of water. The stirred-ball mill was operated for grinding times between 3 and 15 min, and the ground coal was filtered and dried in an oven for 48 hours at 60 °C. The particle size distribution of the samples was determined by screening and by optical microscopy. The calibration curve is shown in Figure 5.1.2.2-1. In this case, 5 min grinding time is sufficient to achieve about 93% (by weight) of the particles passing through a 200 mesh

screen. The curve levels off at about 15 min. grinding time. In order to obtain a 95% of particles passing through 200 mesh screen, a grinding time of 15 min was selected to wet grind the three base coals.

5.1.2.3 Dry Grinding in the Holmes Pulverizer

The Holmes pulverizer was calibrated for dry grinding to 28 mesh x 0 by feeding 0.25 kg of 14 mesh x 0 coal and recycling it several times. The resultant coal was sieved in order to measure the weight percent of the particles that passed through a 28 mesh sieve. As Figure 5.1.2.3-1 shows, two passes gave at least 95% passage through a 28 mesh sieve for all three base coals.

5.1.2.4 Wet Grinding in the Ceramic Jar Mill

Wet ground samples of 28 mesh x 0 were prepared using the 2-liter ceramic jar mill. Ceramic cylinders, 13/16" diameter and 13/16" long, were used in the jar to grind the samples. For each batch, the jar mill was loaded with 1.5 kg of ceramic cylinders, 0.25 kg of the pulverized (14 mesh x 0) coal, and 250 ml of water. The coal samples were filtered and dried after being ground. The coal was sieved to determine the amounts that pass through a 28 mesh sieve. As can be seen from the calibration curves in Figure 5.1.2.4-1, grinding times of 2 hours for Upper Freeport and Illinois #6 coals, and 4 hours for Pittsburgh #8 coal were sufficient to obtain 95% passage through a 28 mesh sieve.

5.1.3 Sampling and Grinding Procedure

The inerted raw coal samples contain a particle size of about 5" x 0. A procedure was developed in order to obtain a representative sample from each drum and to grind the sample to a desired size. The procedure includes sampling, delumping, pulverizing and final grinding as listed in the following:

1. A drum of coal sealed under argon (about 450 lb) was placed into the coal feed compartment, and the environmental chamber was closed and sealed.
2. When used, the chamber was purged with argon until it reached a desired oxygen level. A positive pressure of argon was maintained in the chamber during the operation.
3. The coal was fed into the delumper in 40 lb batches.
4. Each batch of the delumped coal (about 40 lb) was well mixed and collected in a 5 gal container. About 2 lb of the delumped coal were taken from each 5 gal container and evenly distributed into ten 0.5 gal containers. The rest of the delumped coal was sealed in bags and transferred to the packaging compartment.
5. The homogenized coal samples in the ten 0.5 gal containers were pulverized to about 14 mesh x 0 size using the Holmes Pulverizer. The pulverized samples were transferred to the packaging compartment where they were sealed in bags.

6. Final Grinding

- 6.1 For wet grinding to 28 mesh x 0, about 0.25 kg of pulverized samples were loaded in the ceramic jar mill.
- 6.2 For dry grinding to 28 mesh x 0, about 0.25 kg of pulverized samples were fed to the Holmes Pulverizer.
- 6.3 For dry grinding to 200 mesh x 0, about 0.25 kg of pulverized coal were fed into the stirred-ball mill. The desired particle size was controlled by adjusting the grinding time for different coals.
- 6.4 For wet grinding to 200 mesh x 0, about 0.25 kg of pulverized coal were fed to the stirred-ball mill with 1000 ml of distilled water.
- 6.5 For grinding in the presence of light hydrocarbons, 0.25 kg of pulverized coal samples (14 mesh x 0) were loaded in the stirred-ball mill with 1000 ml of distilled water. The light hydrocarbon reagent was injected into the stirred-ball mill through one of the 1/4" fittings on the lid. A steady flow of argon passed through the ball mill container at an average rate of 0.5 ml/min with a maximum rate of 1.0 ml/min. This flow from the container was passed through two dry ice traps in order to condense the vaporized reagents.

7. Sampling

- 7.1 For dry grinding operation, the samples were directly transferred to the packaging compartment and sealed in bags.
- 7.2 For wet grinding operation, the resultant coal/water slurry was split using a riffler (mechanical splitter). The coal/water slurry samples were directly used for the agglomeration test. The slurry samples were also filtered and dried for characterization studies. The dried coal sample were further sampled using the coning and quartering method.

A designation of ground coal samples is shown in Table 5.1.3-1. In addition to this designation, a grinding data sheet was completed for each run detailing the conditions of the run (i.e. date, environment, and media).

5.2 Comparison Between Grinding in Air and under Argon Atmospheres

The differences in surface composition (measured using LAMMA) and surface functional groups (in terms of oxidation indices determined using DRIFT) resulting from grinding in air and under an argon atmosphere were studied for the three base coals. The effects of storage time and particle size were addressed. The moisture content of the dry ground samples was also determined for 28 mesh x 0 and 200 mesh x 0 samples.

5.2.1 Surface Functional Groups

Measurements were made to determine the oxidation indices of the three base coal samples that were ground and stored in air and ground under argon and stored under nitrogen without being exposed to air during grinding and subsequent storage. The samples prepared in air were also analyzed over a period of two months to identify any possible changes in the oxidation index.

To conduct analysis on argon preserved samples, a glove box was constructed around the sample introduction unit. This was to permit introduction of the coal sample without exposure to air. Liquid nitrogen as the source of inert medium was charged into the box. Data were acquired from both 28 mesh x 0 and 200 mesh x 0 samples of the three base coals, prepared in air and under inert atmosphere. Listed in Table 5.2.1-1 are the oxidation indices for the three base coal samples averaged over a period of two months.

The analysis of these data indicates that Illinois #6 coal appears to have the most oxidized organic components followed by Pittsburgh #8 and Upper Freeport coals. This is qualitatively consistent with the wettability studies of the three base coals (see Section 3.10). These studies suggest that the order of decrease in wettability (increase in contact angle) from Illinois #6 to Pittsburgh #8 to Upper Freeport coal is the same as the order of decrease in oxidation indices.

Figure 5.2.1-1 shows that the average values of the oxidation indices for all argon preserved samples (both 28 mesh x 0 and 200 mesh x 0) are lower than those for the samples ground and stored in air. Previous research on the functionality of coals has shown that weathering temperatures in excess of 80 °C are necessary before noticeable changes in oxidation indices are observed. Although these coals were never stored at elevated temperatures, the temperatures they encountered during grinding in air may have been high enough to cause this slight increase in oxidation indices.

Figure 5.2.1-1 also shows that the oxidation indices are higher for the 28 mesh x 0 samples than for the 200 mesh x 0 samples. This is probably an effect related to particle size, and is not an indication of different surface oxidation. Because this is manifest in the oxidation index values, all comparisons of oxidation indices should be made within a given particle size range.

Replicate data were obtained on the samples ground and stored in air over the course of six months. The oxidation indices for all three base coals are summarized in Tables 5.2.1-2 through 5.2.1-4. These data obtained over several months show excellent confidence limits and form the base for following changes in the C-H and carbonyl groups on or near the surface with various treatment and agglomeration tests.

5.2.2 Surface Composition (LAMMA)

The surface elemental composition of the argon preserved samples (28 mesh x 0 and 200 mesh x 0 sizes) and air ground samples (28 mesh x 0) was determined using LAMMA and is shown in Figures 5.2.2-1 through 5.2.2-3. Each analysis represents averages obtained by sampling 500 points on the surface of coal particles. The data show that no systematic differences appeared in the elemental distribution between argon preserved samples and samples ground and stored in air. On the other hand, several differences in elemental composition can be seen in comparing the 28 mesh x 0 and 200 mesh x 0 samples. For example, there is an increase in ionization for K and a decrease in Ca, Si, and Ti as the particle size is decreased from 28 mesh x 0 to 200 mesh x 0.

5.2.3 Moisture Content

Moisture contents of dry ground samples of the three base coals were measured. As shown in Table 5.2.3-1, the moisture content is lower for the 200 mesh x 0 samples than for the 28 mesh x 0 samples. This is probably due to greater water evaporation as a result of longer grinding time and higher heat generation during grinding to 200 mesh x 0.

5.3 Two-Level Factorial Design Agglomeration Study

A two-level factorial design was used to study the effect of particle size, grinding method, slurry concentration, n-pentane to coal ratio (PCR), agglomeration time, and mixing speed on the performance of the agglomeration process using n-pentane as agglomerant.

The particle size of dry ground 28 mesh x 0 and 200 mesh x 0 and wet ground 200 mesh x 0 samples were analyzed for the three base coals using the optical microscope with image analyzer and SEM. The results are summarized in Table 5.3-1. The particle size distributions in all cases followed the trend that the distributions shift to finer sizes in the order of wet ground to 28 mesh x 0, dry ground to 28 mesh x 0, dry ground to 200 mesh x 0, and wet ground to 200 mesh x 0.

In order to compare with results from the agglomeration test, washability runs were conducted on 28 mesh x 0 and 200 mesh x 0 samples of the three base coals. The data are listed in Tables 5.3-2 through 5.3-4 and also plotted in Figures 5.3-1 through 5.3-6 as energy recovery versus ash rejection and versus pyritic sulfur rejection.

The experimental conditions used in the agglomeration tests are listed in Table 5.3-5. Figures 5.3-7 through 5.3-9 show some experimental values of the energy recovery plotted against ash rejection for the three coals used under different grinding conditions. As can be seen, the energy recovery generally decreases with increasing ash rejection though this decrease is not very pronounced for Upper Freeport coal. The complete set of data is presented in Appendix D. These data were statistically analyzed using the commercial software package, Number Cruncher Statistical System (NCSS)⁽⁵⁰⁾. The results of the Analysis of Variance (ANOVA) of the energy recovery and ash rejection data are presented in Tables 5.3-6 and 5.3-7. The standard deviations within replicates are shown in Table 5.3-8. Single variables and double interactions of variables were considered in the analysis. Tables 5.3-9 and 5.3-10 show the average values of energy recovery and ash rejection. The analysis of variance and the comparison of the results for different conditions clearly indicate that particle size and grinding method were the most important variables affecting the performance of the agglomeration process.

The data in Tables 5.3-6 and 5.3-9 show that the particle size of the coal samples has the most statistically significant effect on the energy recovery. For the three coals, finer particle size resulted in higher energy recoveries. For instance, Figure 5.3-10 shows that the differences between the average energy recoveries obtained for 200 mesh x 0 and 28 mesh x 0 samples are 7, 27, and 39 percentage points for Upper Freeport, Pittsburgh #8, and Illinois #6 coals, respectively. This behavior indicates that the effect of particle size on energy recovery increases with decreasing the coal rank index. The higher energy recovery obtained with finer particle size is believed to be a direct consequence of higher yields and it is probably due to the increase of the hydrophobicity of coal surfaces as a result of the liberation of mineral matter during grinding. This effect was found to be more pronounced for the lowest rank coal, Illinois #6, because it is the more hydrophilic and therefore larger increases in the hydrophobic character of the coal samples were achieved by grinding finer (200 mesh x 0).

Table 5.3-9 and Figure 5.3-11 also show that for both Illinois #6 and Pittsburgh #8 coals, wet grinding improved the energy recovery of 200 mesh x 0 samples, but had a detrimental effect on the energy recovery of 28 mesh x 0 samples. It is very likely that the dry and wet grinding mechanisms differ in a way such that for the 28 mesh x 0 samples better liberation was attained. For the 200 mesh x 0 samples, however, the negative effects of enhanced oxidation and coating of the clean coal particles by mineral-rich fine particles during dry grinding played a more dominant role that led to lower energy recoveries. An opposite behavior was observed for Upper Freeport coal, where a slight improvement of the energy recovery of 28 mesh x 0 coal and a slight decrease in the energy recovery of 200 mesh x 0 coal were obtained. This may be due to a different coal matrix and the extremely hydrophobic character of this coal.

Although the effect of wet grinding on energy recovery was beneficial or detrimental depending on particle size and coal type, the effect of wet grinding on ash rejection was beneficial for the three coals studied as can

be seen in Table 5.3-7 and Figure 5.3-12. A significant improvement that ranged between 13 and 25 percentage points was observed when the coal samples were wet ground when compared with those dry ground. It is suggested that the adhesion of ash-forming particles to clean coal particles significantly decreases when the particles are dispersed in water as in the case of wet grinding. Consequently, the quality of the product coal is improved and higher ash rejections are obtained.

Figure 5.3-13 shows that the ash rejection is significantly higher for the 28 mesh x 0 samples than that for the 200 mesh x 0 samples with dry grinding. As a matter of fact, dry grinding to 200 mesh x 0 yielded the worst ash rejection in all runs. Although for the 200 mesh x 0 samples there was better liberation of mineral matter, greater adhesion of mineral-rich fine particles to clean coal particles with dry grinding to 200 mesh x 0 than with dry grinding to 28 mesh x 0 resulted in a lower ash rejection. As indicated above, the adhesion of ash-forming particles to clean coal particles is reduced for wet grinding. This is corroborated by the fact that the improvement of ash rejection due to wet grinding was much more pronounced with 200 mesh x 0 than with 28 mesh x 0 coal particles.

The combination of the improvement in ash rejection due to wet grinding and the improvement in energy recovery due to finer grinding led to the conclusion that wet grinding to 200 mesh x 0 was the most beneficial size reduction procedure for the present agglomeration process. This condition combines better mineral matter liberation while preventing the adhesion of mineral-rich fine particles to clean coal.

Tables 5.3-6 and 5.3-7 show that the interactions between grinding method and particle size with other variables were not statistically significant in most cases. This is probably due to masking of the effects of these interactions because of the magnitude of the grinding method and particle size effects. A few statistically significant interactions that resulted in differences in the average values for ash rejection and energy recovery of one to two percentage points are probably due to simple coincidence.

Table 5.3-7 also shows that the slurry concentration had a statistically significant effect on ash rejection for the three coals although these were at most in the order of two to six percentage points. Table 5.3-10 shows that when the slurry concentration was increased from 2 to 4% by weight, ash rejections for the three coals decreased significantly. This can be attributed to the increased entrapment of mineral matter into the agglomerates formed at higher coal concentration.

The n-pentane to coal ratio (PCR) also was found to have a small but statistically significant effect on energy recovery and ash rejection for the three coals used. For the higher PCRs, the energy recovery was higher. However, the higher energy recovery was accompanied by additional entrapment of ash-forming minerals into the agglomerates. As a result, ash rejection was lower for higher PCR.

In addition, agglomeration time and mixing speed did not have a statistically significant effect on agglomeration performance. This finding may be due to the narrow range used for these two variables.

5.4 Comparison Between Dry and Wet Grinding

The results of the agglomeration tests conducted in the 2-level factorial design indicated that the grinding method had significant effect on the performance of the agglomeration process. The techniques established in Task 3 were used to compare the effect of dry and wet grinding on the properties of the coal samples.

5.4.1 Morphology

The morphology of 200 mesh x 0 dry and wet ground samples of the three base coals were compared qualitatively, using the SEM in secondary electron imaging mode. Pittsburgh #8 coal and Illinois #6 coal have fairly similar characteristics. The dry ground samples of these two coals contain a mixture of grains which are rounded agglomerates and others with essentially clean surfaces. These surfaces have the characteristic features of the brittle fracture (Figure 5.4.1-1). However, associated with these features there is evidence of plastic deformation associated with cracking without complete propagation of the cracks. The wet ground samples of these two coals were very similar. Both coals showed a fracture with significant plasticity resulting in partial cracking of particles and many surface cracks. These findings are illustrated in Figure 5.4.1-2 for Pittsburgh #8 coal and Figure 5.4.1-3 for Illinois #6 coal.

Upper Freeport coal is characterized by extensive agglomeration during dry grinding. Even the fines have a significant fraction of rounded agglomerates (see Figure 5.4.1-4), which is not seen in the other two coals. Wet ground Upper Freeport coal showed cleaner fractures (see Figure 5.4.1-5) which result in a flaky habit of the ground coal. Its behavior is indicative of a more brittle nature leading to clean cleavage and less tendency to reagglomerate in water.

The differences in morphology among the coals are mirrored in the rank of the coal (Upper Freeport coal belongs to a higher rank). They may play a role on grinding efficiency and agglomeration performance.

5.4.2 Surface Functional Groups

The oxidation indices for dry and wet ground 200 mesh x 0 samples of Pittsburgh #8 and Illinois #6 coals were determined and are shown in Table 5.4.2-1. For wet ground feed coal, the samples were dried in an oven at 60°C for one day. In the case of product and refuse from agglomeration tests, the samples were dried for two days at 60°C.

The DRIFT data for Pittsburgh #8 and Illinois #6 coals indicate that the oxidation indices of 200 mesh x 0 wet ground samples are higher than those for dry ground samples. This indicates that the presence of water during grinding increased the area measured attributable to carbonyl groups relative to the area for aromatic/aliphatic bonds. The presence of additional water on the wet-ground sample, relative to the dry-ground, could increase the area measured for the carbonyl groups resulting in a higher oxidation index. Additional water on the wet ground sample could therefore result in a higher oxidation index. Other factors such as particle morphology might also be involved. It was shown in Section 5.4.1 that wet- and dry- ground samples have different morphology.

For both Pittsburgh #8 and Illinois #6 coals, the feed and product samples show similar oxidation indices. The oxidation index of the Pittsburgh #8 refuse sample was lower, but this result may be caused by the relatively high concentration of mineral matter in the sample.

5.4.3 Surface Composition (LAMMA)

The surface contents of iron measured using LAMMA for the three base coals wet ground to 200 mesh x 0 are significantly higher than those for the dry ground samples as Figures 5.4.3-1 through 5.4.3-3 indicate. A possible explanation for this difference in near surface (1 micron depth) composition is leaching in the wet grinding process. Differences in morphology (such as cracks on surface), as described in Section 5.4.1, that might alter leaching and subsequent deposition of the iron on the surface is a possible mechanism.

The largest increase in percent total ionization for wet ground versus dry ground is shown for Upper Freeport coal. A factor of approximately four increase in the percent total ionization of iron is observed for the wet ground Upper Freeport coal. The increased iron concentration observed is consistent with ICP analysis of the filtrate from the wet grinding process which is discussed in Section 5.4.8.

Since the stirred-ball mill loaded with stainless steel balls was used to prepare both the wet and dry ground 200 mesh x 0 samples, an attempt was made to determine if the source of the increased iron is the coal or possibly arises from the steel balls during wet grinding. Samples of Upper Freeport coal were both dry and wet ground in a ceramic jar mill to 200 mesh x 0. Results of the analyses from this test are shown in Figure 5.4.3-4. Data for coal dry ground with the steel ball mill are also given for comparison. Analysis of the coal ground in the ceramic jar mill shows an increase in iron with wet grinding over dry grinding. The increase (less than a factor of 2), however, is much smaller than that observed with the stirred-ball mill. Thus, the source of the increase in surface iron can be attributed to both the coal and the grinding medium (steel balls).

5.4.4 Quantitative Distribution of Iron Species

Transmission Mossbauer spectra of Illinois #6 coal dry ground to 200 mesh x 0 and Upper Freeport coal wet ground to 200 mesh x 0 were obtained. For both coals, the dominant spectral features are the FeS_2 doublet centered at about 0.60 mm/s and a feature recognized as an Fe^{+2} species present at about 2.8 - 3.0 mm/s. Table 5.4.4-1 summarizes the percent area determinations for the pyrite and sulfate/clays for both coals. The sample of Illinois #6 coal dry ground to 200 mesh x 0 shows a decrease in the pyritic sulfur from 98% to approximately 77% and an increase in the sulfate/clays from 2% to 23%, relative to the argon preserved 28 mesh x 0 coal sample. Data for the 200 mesh x 0 wet ground sample of Upper Freeport coal, on the other hand, show essentially the same distribution of pyrite and sulfate/clays as the argon preserved 28 mesh x 0 coal. These findings may indicate that dry grinding caused the oxidation of pyritic sulfur forming sulfate sulfur while wet grinding kept the pyritic sulfur unchanged.

5.4.5 Coal Wettability

In order to determine the effect of grinding method on the surface wettability of coal particles, contact angle measurements were conducted using samples of the three base coals dry and wet ground to 200 mesh x 0. For the dry ground samples, the procedure discussed in Section 3.10 was used. The wet ground samples were dried in an oven at 60 °C for four days before they were used to make pellets. As shown in Table 5.4.5-1, all wet ground samples show zero contact angles. To determine if this is due to thermal drying or moisture content, a series of experiments were conducted.

A sample of 200 mesh x 0 wet ground Pittsburgh #8 coal (about 5 g) was vacuum filtered and dried in a vacuum dryer at room temperature for 12 days. When the sample reached constant weight, a pellet was made. The contact angle of the sample, however, was zero. This indicates that the zero contact angle on Pittsburgh #8 coal was not caused by the drying method. This finding is also supported by the results obtained from the surface functional group analysis, which show that the samples prepared in air, under argon and in water have a similar oxidation index.

To determine the possible effect of moisture content on the contact angle measurement, samples of Pittsburgh #8 and Upper Freeport coal dry ground to 200 mesh x 0 were dried in the oven at 60 °C for 4 days. The contact angles measured on the pellets made of these two samples were 0° and 110°, for Pittsburgh #8 coal and Upper Freeport coal, respectively. This finding seems to indicate that the contact angle measurement is affected by the moisture content. However, the effect is less pronounced for Upper Freeport coal than that for Pittsburgh #8 coal. It is believed that as coal samples are completely dried, the capillary moisture in the coal sample is evaporated. As a result, a drop of water on the coal may be sucked into the capillaries resulting in a smaller contact angle. Depending on the magnitude of the capillary forces, which are function of the coal structure,

this effect can be different for each coal.

From the findings discussed above, it may be concluded that the drying method does not affect the contact angle measurement, and the moisture content of the sample to be measured has some effect but is not the only factor. Another important factor which may affect the contact angle is the soluble salts dissolved during wet grinding and may be deposited on the surface of the particles because of the drying method adopted. This makes the surfaces completely water wet resulting in a zero contact angle.

5.4.6 Zeta Potential and pH Measurements

The surface charge properties of 200 mesh x 0 dry and wet ground samples were characterized in terms of zeta potential. For wet ground samples, the coal particles in the slurry were directly ground to micron sizes using a mortar and a pestle without filtering and drying. Table 5.4.6-1 lists the measured zeta potentials of both dry and wet ground 200 mesh x 0 samples for the three base coals. For all three coals, the zeta potentials of the wet ground samples are lower than those for the dry ground samples. Among the three coals, Pittsburgh #8 coal has the largest change in zeta potential. It should be also noted that the zeta potentials of the wet ground samples of Upper Freeport and Pittsburgh #8 coals are close to the iso-electrical point (IEP), which makes the particles easier to coagulate, thus producing a better yield in the agglomeration tests.

The pH of coal/water slurry was measured for each of the three base coals at various slurry concentrations. Dry ground samples of the three base coals at 28 mesh x 0 and 200 mesh x 0 were mixed with distilled water using a magnetic stirrer for 30 min. Slurry concentrations of wet ground coal were controlled by adding more distilled water to the slurry directly obtained from wet grinding. The actual concentrations of the samples were determined by filtering, drying, and weighing the solid particles in the samples after pH measurement. The wet ground samples were also mixed with distilled water for 30 min. before the measurement. The pH values of the slurries were measured using the pH meter after being calibrated with a buffer solution.

The experimental data for samples both dry and wet ground to 28 mesh x 0 and 200 mesh x 0 are shown in Figures 5.4.6-1 through 5.4.6-3 for the three base coals. It can be seen that the pH values of the 200 mesh x 0 coal samples are higher than those of the 28 mesh x 0 samples.

5.4.7 Surface Area

The surface areas of the three base coals were determined for 200 mesh x 0 dry and wet ground samples. Table 5.4.7-1 shows that as expected, no significant difference was found between the surface areas of the wet and dry ground samples. Since the surface area measured is essentially the internal surface area which mainly depends on the structures of the coal samples, and the internal surface area of coal particles is much larger than

the external area, it results that the grinding method has little effect on the surface area.

5.4.8 Filtrate Analysis

Filtrate samples of coal/water slurries (4% by weight) made of 200 mesh x 0 dry and wet ground coal samples were prepared under the same operating conditions as those used in the agglomeration tests. The ICP analysis was conducted to quantitatively determine the concentrations of the elements dissolved in the filtrate. The data obtained are plotted in Figures 5.4.8-1 through 5.4.8-3. The concentrations of the elements in the filtrates from wet ground samples are, in general, higher than those from the dry ground samples, particularly, Ca, Fe, and S. This may indicate that more ions were leached out by wet grinding than by dry grinding.

It is also noted that the dissolved sulfur, presumably sulfate, in the filtrate samples of the wet ground coals follow a trend of concentration increasing in the order of Upper Freeport, Illinois #6, and Pittsburgh #8 coals, which agrees well with the sulfur form analysis of the three base coals determined in the standard ASTM characterization (see Table 3.1-1). With the evidence of relative high concentrations of Fe and Ca ions in different coals, it can be speculated that the sulfate may be mainly of iron sulfate form in both Upper Freeport coal and Pittsburgh #8 coal and of calcium sulfate form in Illinois #6 coal.

5.5 Wet Grinding in the Presence of Light Hydrocarbons

In this study, attempts were made to modify the surface of coal particles by grinding in the presence of light hydrocarbons. It was envisioned that during grinding, light hydrocarbons might be adsorbed on freshly created clean coal surfaces rendering them more hydrophobic, and thus enhancing their agglomeration. It is well known that better selectivity can be achieved using light hydrocarbons in agglomeration processes⁽⁵¹⁾, and therefore, n-pentane, cyclohexane, and n-heptane were added before wet grinding to 200 mesh x 0 according to the experimental procedure described in Section 5.1.3. Some properties of these hydrocarbons are listed in Table 5.5-1.

The response of the coals to wet grinding in the presence of light hydrocarbons was strongly influenced by their wetting character. For Upper Freeport coal, the most hydrophobic of the coals studied, it was not possible to complete grinding using n-heptane or cyclohexane to coal ratios above 0.01, or n-pentane to coal ratios above 0.1. The formation of a cake ranging from 3 to 12 mm thick lining the inside of the grinding container did not allow the completion of the grinding operation. On the other hand, for Illinois #6 coal, the least hydrophobic of the coals studied, no tendency to agglomeration during grinding was observed. Pittsburgh #8 coal behavior fell in between that of these two coals, since no tendency to agglomerate was observed when n-pentane was added but it agglomerated at cyclohexane and n-heptane to coal ratios above 0.1.

The physical properties of the light hydrocarbons also played a role in the agglomeration observed during grinding. N-pentane did not induce agglomeration as strongly as cyclohexane and n-heptane. It is believed that because of its lower boiling point, some of the n-pentane might have evaporated during grinding, reducing its n-pentane to coal ratio and therefore its agglomerating effect. Cyclohexane and n-heptane also have higher viscosity than n-pentane which led to the formation of a strong cake in the grinding container that could not be broken by the stirring action of the shaft and the balls in the stirred-ball mill.

5.5.1 Agglomeration Tests

Agglomeration tests using n-pentane as agglomerant were performed with those samples for which the grinding step was completed. The agglomeration time and mixing speed were set according to the results of the two-level factorial design study and varied depending on the coal. A summary of the experimental conditions used is shown in Table 5.5.1-1. Twenty two sets of agglomeration tests and replicates totaling 104 runs were carried out. Appendix E lists the detailed results of these experiments. The entire set of energy recovery as well as ash and pyritic sulfur rejections data were used to determine the standard deviation within replicates for each response variable. The results listed in Table 5.5.1-2 show the excellent reproducibility of the data and serve as the basis for determining the significance of the effect of hydrocarbon addition on the agglomeration performance.

In order to statistically evaluate these effects, the average results were utilized in t-tests for the comparison with base data from experiments conducted without the addition of light hydrocarbons. The statistical analysis was performed using the commercial software package, Number Cruncher Statistical System (NCSS)⁽⁵⁰⁾.

The average results of the agglomeration tests conducted using Upper Freeport coal are depicted in Figure 5.5.1-1. These data show that the energy recovery was in all cases about 99%. The results of the statistical analysis of these data are shown in Table 5.5.1-3. It is customary that in order to be considered statistically significant, an average result must fall outside the 95% confidence limit of the t-test. This corresponds to having a probability less than 0.05 of having no effect with respect to the base case (no additives). The data in Table 5.5.1-3 indicate that the addition of cyclohexane and n-heptane at a hydrocarbon to coal ratio of 0.01 did not have any statistically significant effect on both ash and pyritic sulfur rejections. However, as indicated above, at higher cyclohexane and n-heptane dosages, Upper Freeport coal agglomerated during grinding.

The plot in Figure 5.5.1-1 also shows that there is a decrease in the ash and pyritic sulfur rejections as the n-pentane to coal ratio is increased. The statistical analysis presented in Table 5.5.1-3 indicates that for a n-pentane to coal ratio of 0.1, the reduction in ash rejection was statistically significant.

The agglomeration results and the behavior of Upper Freeport coal during grinding in the presence of these light hydrocarbons suggest that no gains can be achieved by this procedure since energy recoveries higher than 95% can be obtained without adding any reagents. The addition of the hydrocarbons during grinding only contributed to the agglomeration of mineral matter and pyrite, thus, decreasing the performance of the agglomeration process.

For Pittsburgh #8 coal, the addition of the three hydrocarbons increased the energy recovery and reduced the ash and pyritic sulfur rejections, as shown in Figure 5.5.1-2. The statistical analysis given in Table 5.5.1-4 indicates that these effects were significant for the coal samples ground using n-heptane to coal ratios of 0.05 and higher. In the case of cyclohexane, only the decrease in ash rejection was statistically significant while for n-pentane these effects were insignificant.

The light hydrocarbons appeared to act as an effective bridging medium for Pittsburgh #8 coal particles. However, the entrapment of mineral matter in the agglomerates contributed to the large decrease in ash and pyritic sulfur rejections. This effect became more pronounced as the molecular weight and dosage of the hydrocarbons were increased. The extreme case for this effect was the agglomeration that occurred during grinding at n-heptane and cyclohexane to coal ratios higher than 0.1.

For Illinois #6 coal, Figure 5.5.1-3 summarizes the agglomeration test results and Table 5.5.1-5 shows the statistical analysis of the data. For this coal, the samples ground using a n-pentane to coal ratio of 0.05 showed a statistically significant decrease in the ash and pyritic sulfur rejections, along with an increase in the energy recovery. At higher n-pentane dosages, however, these effects became less significant, and for a n-pentane to coal ratio of 0.5, the results did not differ from those obtained without additives. On the other hand, no statistically significant effects were observed in the experiments where cyclohexane and n-heptane were used during grinding.

Since Illinois #6 coal showed neither a trend towards agglomeration during grinding nor any statistically significant improvements in the agglomeration performance, it was possible to conclude that the addition of the light hydrocarbons did not change the strongly hydrophilic character of this coal.

5.5.2 Sample Characterization

An investigation of the effect of wet grinding in the presence of light hydrocarbons on the coal properties was carried out along with the study of the agglomeration process. Some of the techniques developed in Task 3 were used to determine oxidation indices, surface composition, zeta potential, pH, and contact angles for the coal samples wet ground using n-pentane, cyclohexane, and n-heptane.

5.5.2.1 Surface Functional Groups

The oxidation indices were determined for feed samples of Illinois #6 coal wet ground in the presence of cyclohexane and n-heptane. A sample of Illinois #6 coal wet ground without the addition of light hydrocarbons was analyzed for reference. The oxidation indices with their respective 95% confidence intervals are shown in Table 5.5.2.1-1 and Figure 5.5.2.1-1. The addition of light hydrocarbons during grinding did not have significant positive effects on the agglomeration process performance. Similarly, Figure 5.5.2.1-1 shows no significant difference between the oxidation indices of the samples ground with and without hydrocarbons.

5.5.2.2 Surface Composition (LAMMA)

Illinois #6 and Pittsburgh #8 coal samples wet ground in the presence of light hydrocarbons were analyzed using LAMMA to determine their surface elemental distribution. Figure 5.5.2.2-1 shows that for Illinois #6 coal, the addition of hydrocarbons increased the sulfur surface concentration relative to the base sample. An increase in the surface concentration of Ca and a decrease in the surface concentration of Na were also observed for all samples.

Pittsburgh #8 coal samples wet ground using a n-pentane to coal ratio of 1/5 were analyzed to determine changes in elemental distribution relative to samples ground without additives. The results of these analyses, shown in Figure 5.5.2.2-2, indicate that the surface concentration of Mg, Si, S, and Fe increased relative to the sample ground without additives. The surface concentration of Na, K, Al, and Ca decreased.

For Pittsburgh #8 coal, as well as for Illinois #6 coal, the addition of hydrocarbons during grinding seemed to have a modest effect on the surface elemental composition. The most significant result is that, in most cases, the addition of hydrocarbons during grinding increased the surface concentration of S and Fe. A decrease in the surface concentration of Na and K was also observed for most samples ground with additives. It might be speculated that the removal of these highly soluble cations from the surface of mineral matter exposed more pyrite resulting in the increases in sulfur and iron surface concentration.

5.5.2.3 Zeta Potential and pH Measurements

Table 5.5.2.3-1 shows the zeta potentials and pH of the samples ground in the presence of light hydrocarbons. These data indicate that for Upper Freeport coal, a strongly hydrophobic coal, the addition of light hydrocarbons had little effect on the particle charges, and therefore, no clear trends were observed for the zeta potentials. For Pittsburgh #8 and Illinois #6 coals the addition of hydrocarbons shifted the zeta potential toward the isoelectric point. The adsorption of the light hydrocarbons added during grinding on the coal particles might have formed a film on the surface that caused steric hindrance of the charges surrounding them.

This effect probably was pronounced for Illinois #6 and Pittsburgh #8 coals because of their hydrophilic nature compared with Upper Freeport. The behavior of the coals during grinding agrees with this assessment since a strong trend toward agglomeration was observed when light hydrocarbons were added.

5.5.2.4 Contact Angle Measurements

The contact angle of a water droplet placed on the surface of a coal pellet was measured as a function of time for Upper Freeport, Pittsburgh #8, and Illinois #6 coal samples wet ground in the presence of light hydrocarbons.

For Illinois #6 and Pittsburgh #8 coals, the droplet of water deposited on the pellet disappeared in less than a minute in all cases. These results reflect the hydrophilic character of the particles. During such a short life-span of the water droplet only the initial contact angle (or largest contact angle) and the life-span of the droplet were measured and they are reported in Table 5.5.2.4-1.

For Upper Freeport coal, Figure 5.5.2.4-1 shows that the contact angles were considerably larger (between 49° and 97°) and the drops lasted between 1 and 4 min. This finding agrees well with the data on the wettability character of Upper Freeport coal.

A reduction in drop life-span was observed in all the cases studied. For the sample ground using a n-pentane to coal ratio of 1/10, the drop life-span was about 1 minute and the largest angle only 50° (compared with 6.7 min and 88° for the sample ground without additives). A decrease in drop life-span could be related to a decrease in the hydrophobicity of the sample. It is speculated that this effect might be due to changes in surface roughness and to the evaporation of surface hydrophobic groups dissolved in the light hydrocarbons during drying.

6.0 TASK 6: MODIFICATION OF PARTICLE SURFACE

The objective of this task was to study the effect of using surface modification reagents in the agglomeration process. The surface modification study was carried out using two surfactants (Aerosol-OT and Arosurf MG-83A), two alcohols (methanol and ethanol), and two monomers (styrene and tall oil).

Aerosol-OT was supplied by American Cyanamide Company. The chemical name of Aerosol-OT is sodium di[2-ethylhexyl] sulfosuccinate. It is an anionic surfactant with an empirical formula of $C_{20}H_{37}SO_7Na$ and a molecular weight of 444.5. Arosurf MG-83A is a product of Sherex Chemical Company Inc., Dublin, OH. Arosurf MG-83A is a cationic flotation reagent with the chemical name of tridecyl ether diamine acetate. It has an empirical formula of $C_{21}H_{42}N_2O_3$ and molecular weight of 370. Both methanol and ethanol were obtained from Fisher Scientific. Styrene was provided by Aldrich Chemical Company with 4-tert-butylcatechol as an inhibitor. It has a chemical formula of $C_6H_5CH=CH_2$. Tall oil was supplied by Westvaco Chemical Company in the form of a fatty acid with a chemical formula $C_{17}H_{31-35}COOH$.

Standard agglomeration test runs were conducted using coal samples treated with surfactants and monomers during grinding and with alcohols prior to the agglomeration test. The experimental conditions used are listed in Table 6.0-1 and the experimental data are given in Appendices F, G, and H for the tests using surfactants, alcohols, and monomers, respectively.

The agglomeration test data were statistically analyzed to determine the significance of the effect of each reagent using a commercial software package, Number Cruncher Statistical System (NCSS)⁽⁵⁰⁾. In order to obtain good statistical values, the overall standard deviations of energy recovery, ash, total and pyritic sulfur rejections were calculated based on all the agglomeration test data. The results of the overall statistical analysis are listed in Table 6.0-2. Using the calculated overall standard deviations, the significance of the effect of each reagent was evaluated in terms of energy recovery, ash, and pyritic sulfur rejections.

6.1 Wet Grinding in the Presence of Surfactants

The pulverized coal samples (14 mesh x 0) were ground in the stirred-ball mill to 200 mesh x 0 in the presence of each surfactant. The water/coal ratio was kept at 3:1 for each run, and the surfactant concentration was controlled at 0.53 lb/ton and 4.22 lb/ton (10 and 80 ppm) during grinding. Agglomeration tests were then conducted using n-pentane as agglomerant. The average results for the agglomeration tests conducted using samples ground in the presence of surfactants are shown in Figures 6.1-1, 6.1-2, and 6.1-3 for Upper Freeport, Pittsburgh #8, and Illinois #6 coals, respectively.

The statistical analysis of the agglomeration results for the samples ground in the presence of Aerosol-OT, listed in Table 6.1-1, indicates that for Upper Freeport and Pittsburgh #8 coals no significant differences in energy recovery, ash and pyritic sulfur rejections exists between the samples ground in the presence of Aerosol-OT and those ground without additives. On the other hand, for Illinois #6 coal the data in Figure 6.1-3 show that the addition of Aerosol-OT decreases ash rejection.

The statistical analysis of the effect of Arosurf MG-83A on the agglomeration performance is shown in Table 6.1-2. For Upper Freeport coal the agglomeration performance remained essentially unchanged at all surfactant concentrations. For Pittsburgh #8 coal the energy recovery, ash and pyritic sulfur rejections decreased when compared with those of samples wet ground without any surfactant. The statistical analysis of the results indicates that the negative effects observed are significant. For Illinois #6 coal, ash rejection significantly increase when Arosurf MG-83A is added.

The results obtained at an Arosurf MG-83A concentration of 0.53 lb/ton (10 ppm) were significantly better than those obtained at 4.22 lb/ton (80 ppm) for all coals in terms of energy recovery, ash and pyritic sulfur rejections. Enustun et al.⁽⁵²⁾ investigated the effect of a cationic surfactant on wet grinding of Illinois #6 coal and claimed that the surface of mineral matters in the coal becomes more hydrophilic. At high surfactant concentrations, the formation of tail to tail attachment of additional surfactant molecules to the initially formed monolayer would also make coal particles hydrophilic⁽⁵³⁾ thus causing a worse performance.

LAMMA surface composition analysis was conducted on 200 mesh x 0 samples of Upper Freeport coal wet ground with 0.53 lb/ton (10 ppm) Aerosol-OT. The data, together with those for untreated samples, are shown in Figure 6.1-4. With the exception of lithium that showed a major decrease in the surfactant treated sample, data for the other elements are very comparable to those of coal samples ground without surfactant.

The oxidation index for the Illinois #6 coal feed sample ground in the presence of Aerosol-OT was 2.39 ± 0.15 , slightly higher than that of the sample ground without additives (2.25 ± 0.21).

The zeta potentials of coal samples ground in the presence of 0.53 lb/ton (10 ppm) and 4.22 lb/ton (80 ppm) of Aerosol-OT and Arosurf MG-83A were measured for the three base coals. It should be noted that the actual concentration of the surfactants in the dilute suspensions was much lower than that of the original coal slurries obtained from grinding since the slurries were vacuum filtered. The experimental data are listed in Table 6.1-3. As can be seen, the addition of Aerosol-OT decreases the zeta potentials for all three coals. This is not surprising because Aerosol-OT is an anionic surfactant. The effects of Arosurf MG-83A, on the other hand, show a different trend for the three base coal samples, i.e. the zeta potentials first increase at a low surfactant concentration of 0.53 lb/ton (10 ppm), and then decrease at a higher concentration of 4.22 lb/ton (80 ppm).

The contact angle of a water droplet placed on the surface of a coal pellet was measured as a function of time on the three base coal samples wet ground with Aerosol-OT and Arosurf MG-83A at two concentration levels, 0.53 lb/ton and 4.22 lb/ton (10 and 80 ppm). Table 6.1-3 shows that analogously to what was observed for the pellets prepared using Illinois #6 and Pittsburgh #8 coals wet ground in the presence of light hydrocarbons (Section 5.5.2.4), the droplet of water deposited on the pellet disappeared in less than a minute in all cases, indicating strong hydrophilic behavior of the particles. During such a short life-span of the water droplet only the initial contact angle (or largest contact angle) and the life-span of the droplet were recorded. In the case of Upper Freeport coal, the contact angles were considerably larger (between 49° and 97°) and the drops lasted between 3 and 30 min. This finding agrees with the data on the wettability character of Upper Freeport coal. Figure 6.1-5 shows that the longest life-span of the water droplets deposited on Upper Freeport coal pellets was observed for the samples treated with Aerosol-OT. The formation of a double layer of surfactant that gives a hydrophobic character to the coal particles might explain the increase in the droplet life-span. For the samples treated with Arosurf MG-83A, a similar phenomenon was observed at a concentration of 10 ppm, but at a concentration of 80 ppm the effect was reversed. This is in agreement with previous observations for the effect of surfactant addition on fine coal dewatering⁽⁵⁴⁾.

6.2 Addition of Alcohols Prior to Agglomeration

It has been reported that the use of methanol in physical coal cleaning processes could enhance the differences between coal and mineral matter, and therefore, the separation efficiency⁽⁵⁵⁾. It is believed that methanol attacks the hydrophilic polar regions on coal surfaces and converts them to hydrophobic non-polar surfaces. Two reactive reagents, methanol and ethanol, were used to modify the surface of 200 mesh x 0 wet ground coal particles. Either methanol or ethanol was added to the slurries at two concentration levels, 1.06 lb/ton and 10.56 lb/ton (20 and 200 ppm), prior to the agglomeration test. The agglomeration test results are shown in Figures 6.2-1, 6.2-2, and 6.2-3 for Upper Freeport, Pittsburgh #8, and Illinois #6 coals, respectively.

The statistical analyses of the agglomeration results obtained using methanol are given in Table 6.2-1. As indicated by the probabilities listed in this table, none of the changes in energy recovery, ash, sulfur, and pyritic sulfur rejections was statistically significant.

The data in Table 6.2-2 and Figure 6.2-2 show that the addition of ethanol at 10.56 lb/ton (200 ppm) caused a significant reduction in the ash rejection for Pittsburgh #8 coal. The statistical analysis of the results for Upper Freeport and Illinois #6 coals, on the other hand, indicate that the addition of ethanol at both 1.06 and 10.56 lb/ton (20 and 200 ppm) had no significant effects on the agglomeration test results.

Figure 6.2-4 shows the results of LAMMA analyses performed on samples of Illinois #6 coal with 0.53 lb/ton (10 ppm) of methanol added. The results obtained for these samples showed little variation from the base sample.

A comparison of oxidation indices for 200 mesh x 0 wet ground Illinois #6 coal samples from agglomeration tests in which alcohols were added before agglomeration is shown in Figure 6.2-5 and Table 6.2-3. The data show that the oxidation indices of the samples treated with alcohols were the same as those of the base samples.

The effects of the alcohols on zeta potential were studied using coal/water slurries of 0.1% solid concentration mixed with a predetermined amount of methanol or ethanol in a covered beaker for 30 min. As shown in Tables 6.2-4 and 6.2-5, the zeta potentials of all three base coals remain unchanged at low concentrations (< 1000 ppm) of both methanol and ethanol. Although variations were observed at higher concentration levels, it seems that the addition of both methanol and ethanol up to 100,000 ppm (10% by weight) does not strongly alter the zeta potentials for these coals.

The contact angles of methanol and ethanol solutions on dry ground samples of the three base coals are shown in Figures 6.2-6 and 6.2-7, respectively. It should be emphasized that the contact angles reported are advancing contact angles measured on rough surfaces of pellets formed with 200 mesh x 0 coal particles. These values tend to be larger than the equilibrium contact angles measured on flat/smooth hydrophobic surfaces. For both methanol and ethanol additions, the measured contact angles decrease with increasing alcohol concentration for Upper Freeport and Pittsburgh #8 coals. Complete wetting occurs at a specific solution concentration for each coal. As for Illinois #6 coal, the contact angle is zero for all solution concentrations (including pure water). These findings seem to indicate that both methanol and ethanol are good wetting reagents and can be used for enhancing particle dispersion rather than agglomeration.

6.3 Wet Grinding in the Presence of Monomers

The idea of using styrene to modify the surface of coal particles was originally from the patents registered by Horowitz et al.⁽⁵⁶⁾ and Burgess et al.⁽⁵⁷⁾. They claimed that the hydrophobicity of coal particles can be effectively enhanced by grafting of polymerizable monomers on the surface of the coal particles. In their work, surface activators were used for the grafting of monomers. It was expected that the monomer molecules could be adsorbed on the coal particle surface due to chemisorption. The pulverized coal samples (14 mesh x 0) were ground in the stirred-ball mill to 200 mesh x 0 in the presence of each monomer. Agglomeration tests were then conducted using n-pentane as agglomerant. The average results for the agglomeration tests conducted using samples ground in the presence of monomers are shown in Figures 6.1-1, 6.1-2, and 6.1-3 for

Upper Freeport, Pittsburgh #8, and Illinois #6 coals, respectively.

The statistical analysis of the agglomeration results of styrene treated samples of the three base coals are shown in Table 6.3-1. As can be seen, no improvement in either energy recovery, ash and pyritic sulfur rejections were obtained at both styrene concentrations for all three coals.

The surface modification experiments using tall oil were conducted using dosages of 1.06 and 10.56 lb/ton (20 and 200 ppm) for both Upper Freeport and Pittsburgh #8 coal while four tall oil dosages, 1.06, 2.12, 10.56, and 21.12 lb/ton (20, 40, 200, and 400 ppm) were used in the surface modification experiments with Illinois #6 coal. The agglomeration test results indicate that the effects of tall oil on the energy recovery, ash and pyritic sulfur rejections are not significant for Upper Freeport and Illinois #6 coals. On the other hand, the statistical analysis results listed in Table 6.3-2 and the data in Figure 6.3-3 show that the energy recovery of Pittsburgh #8 coal was significantly improved at a tall oil concentration of 10.56 lb/ton (200 ppm).

It is expected that organic acid molecules would be grafted onto the surface of coal particles rendering strong hydrophobicity of the surface^(56,57). From the results obtained in this work, it appears that the selective agglomeration performance of Upper Freeport and Illinois #6 coals was not improved by the use of tall oil. However, the overall yield and the energy recovery of Pittsburgh #8 coal were remarkably enhanced at a tall oil dosage of 10.56 lb/ton (200 ppm).

LAMMA measurements of the surface composition of Illinois #6 ground in the presence of monomers is shown in Figure 6.3-4. These data indicate that the addition of monomers increased the surface concentration of Na and Fe while the surface concentration of S, Si, K, and Ca decreased.

Figures 6.3-5 and 6.3-6 shows LAMMA analyses conducted on the feed, product, and refuse samples of Pittsburgh #8 and Illinois #6 coals wet ground in the presence of 200 ppm of tall oil. For Pittsburgh #8 coal, Na, Ca, and Ti increased in the product, while S, Fe, and Si increased in the refuse. These trends are in agreement with the surface elemental distributions obtained for samples ground without additives. Figure 6.3-7 compares the results of the LAMMA analysis and the agglomeration results for Pittsburgh #8 coal. The plots reveal the excellent agreement between the trend observed for the total sulfur content obtained by standard ASTM sulfur analysis and the surface sulfur concentration of the feed, product, and refuse samples. The trends for elemental distribution of the product and refuse samples of Illinois #6 coal treated with tall oil were similar to those for untreated samples. S, Na, Ca, and Ti increased in the product, while Fe, S, and Si showed a shift of concentration into the refuse.

A comparison of oxidation indices for 200 mesh x 0 Illinois #6 and Pittsburgh #8 coal samples wet ground in the presence of monomers is shown in Table 6.3-3. Figure 6.3-8 shows that oxidation indices of product and feed samples ground using 20 and 200 ppm of tall oil were higher than those obtained for samples ground

without any additives. On the other hand, for the product sample of the test performed using a sample ground using 200 ppm of tall oil, the oxidation index was lower than the product sample obtained from the test performed using a sample ground without any reagents. The oxidation indices of the Illinois #6 coal ground using styrene did not show any difference. A similar comparison of oxidation indices for 200 mesh x 0 Pittsburgh #8 coal wet ground samples is shown in Figure 6.3-9. The oxidation index of the feed sample ground with 200 ppm of tall oil added is similar to that of the sample ground without additives. The oxidation index of the product from an agglomeration test conducted using a sample ground using 200 ppm of tall oil was higher than that of the product from a test performed using a sample prepared with no reagents added.

The lack of clear trends among samples, and the overlapping error bars for the 95% confidence intervals (see Figures 6.3-8 and 6.3-9) suggests that there is no significant difference between the oxidation indices of samples wet ground with and without styrene or tall oil.

The effects of tall oil on zeta potentials of the three base coals were investigated at various pH values. For each measurement, tall oil was added to double-distilled water and mixed overnight. The excess (or undissolved) tall oil was separated from water. The water saturated with dissolved tall oil was used to prepare a coal/water slurry for the zeta potential measurement. As shown in Figure 6.3-10, the zeta potentials of the three base coals decrease as pH value increases. The addition of tall oil decreases the iso-electric point (IEP) to pH values of 3.3, 3.9, and 2.9 for Upper Freeport, Pittsburgh #8, and Illinois #6 coals, respectively.

The contact angle of a water droplet placed on the surface of a coal pellet was measured as a function of time for the three base coals wet ground in the presence of monomers. For Illinois #6 and Pittsburgh #8 coals, the droplet of water deposited on the pellet disappeared in less than a minute in all cases, which indicated strong hydrophilic behavior of the particles. During such a short life-span of the water droplet only the initial contact angle (or largest contact angle) and the life-span of the droplet were recorded. These data are shown in Table 6.3-4. Figure 6.3-11 shows the effect of grinding in the presence of monomers on the contact angle as a function of time for Upper Freeport coal. For styrene and tall oil, the observed contact angle and the drop life-span decreased when reagents were used.

The identification and quantification of iron sulfides (FeS_2 , $\text{Fe}_{(3-x)}\text{S}_x$) and iron sulfate was obtained using Mössbauer spectroscopy for feed, product, and refuse samples of Pittsburgh #8 coal wet ground to 200 mesh x 0 using 200 ppm of tall oil. For the three samples, the dominant spectral feature was the doublet centered about 0.60 mm/s corresponding to pyrite (FeS_2). An additional minor component was detected at 2.8 - 3.0 mm/s, originating from either iron sulfate (FeSO_4) or iron based clays. The data in Table 6.3-5 indicate that the same distribution was obtained for the wet ground feed and product samples, that is, 94% of iron in the form of pyrite and the remaining 6% in the form of sulfate and iron clays. The distribution of these components is different from the refuse sample in which 90% of the iron was in the pyrite form and 10% in the

form of sulfate and iron based clays. It is interesting to note that the fraction of iron in pyrite form was the same in the feed as in the product sample. The pyrite fraction was also approximately the same as that of the argon preserved 28 mesh x 0 sample of Pittsburgh #8 coal (94.0% versus 94.9%, respectively).

7.0 TASK 7: EXPLORATORY RESEARCH & DEVELOPMENT AND SUPPORT

The main goal of Task 7 was to explore new and promising avenues leading to effective surface control for selective agglomeration processes and to provide support services to the DOE's Engineering Development Program. In order to achieve this goal, the specific objectives to be carried out are:

1. To optimize the coal surface control techniques developed in Tasks 4, 5, and 6 in terms of improved energy recovery and pyritic sulfur rejection.
2. To explore and develop new and promising techniques for improving selective agglomeration processes.
3. To provide support services to the DOE/PETC and other DOE contractors.

The research work conducted in order to attain these objectives is presented in this report.

7.1 Examination of the Agglomeration Process Experimental Procedure

In order to verify the validity and reproducibility of the agglomeration test procedure developed in Task 4, material balances were carried out in November 1990 for the grinding, splitting, and agglomeration steps of the process. The material balance was conducted using Illinois #6 coal sampled from the drum utilized in the agglomeration tests conducted in Tasks 5, Task 6, and at the beginning of Task 7. This drum was opened, sampled, and the coal stored under argon atmosphere in sealed plastic bags in November 1988, 24 months prior to the material balances experiments. Drums opened in 1988 will be referred as first drums.

The results of the material balances for Illinois #6 coal indicated that oxidation had occurred for the samples from the first drum opened in 1988. The sulfate sulfur content of the coal was significantly higher than the values determined for the samples at the beginning of the project. Therefore, new drums (second drums) of the three base coals were opened, sampled, and delumped under argon atmosphere in November 1990. The drums were opened in the environmental chamber and delumped to obtain a size consist of 1/2" x 0. The delumped samples were split into 15-20 lb fractions and stored in sealed bags. The delumped samples were pulverized to 14 mesh x 0 and the pulverized coal was used for agglomeration studies. Sulfur forms analyses were conducted on these new samples. These analyses indicate that pyrite oxidized in the drums, thus resulting in higher sulfate sulfur contents for the three base coals.

The samples utilized for the sulfur forms analysis were also studied using ESCA. This technique confirmed the total removal of sulfate sulfur during the HCl leaching step of the sulfur forms analysis.

7.1.1 Material Balances for the Agglomeration Process

Material balances on the coal, ash, total sulfur, and sulfur forms were checked using Illinois #6 coal sampled from the first drum. The effects of grinding, grinding-splitting, grinding-splitting-filtration, and grinding-splitting-agglomeration steps on material balances were studied. The following experiments were performed:

1. Effect of grinding on material balance:

Samples of 250-g pulverized (14 mesh x 0) Illinois #6 coal were wet ground in the stirred-ball mill to 200 mesh x 0. The ground coal was dried in an oven at 60 °C until no change in its weight was observed. The dried coal was then weighed and the ash, total sulfur, and organic sulfur analyses were carried out. The LECO sulfur analyzer was used for total and organic sulfur analysis and inorganic sulfur was obtained by difference. The results of this experiment are shown in Table 7.1-1.

2. Effect of grinding-splitting on material balance

Samples of 250-g pulverized (14 mesh x 0) Illinois #6 coal were wet ground in the stirred-ball mill to 200 mesh x 0. The wet ground sample was split into four splits using a mechanical splitter. The four splits were dried in an oven at 60 °C until no change in their weights was observed. The samples were then weighed and ash, total sulfur, and organic sulfur analyses were conducted. The results of this experiment are shown in Table 7.1-2.

3. Effect of grinding-splitting-filtration on material balance:

Samples of 250-g pulverized (14 mesh x 0) Illinois #6 coal were wet ground in the stirred-ball mill to 200 mesh x 0. The wet ground coal was split into four splits using a mechanical splitter. The four splits were filtered using Whatman #2 filter paper. The solid particles retained on the filter paper were dried in an oven at 60 °C until no change in their weights was observed. The samples were weighed and ash, total sulfur, and organic sulfur analyses were performed. The filtrate from each split was weighed and analyzed using Infrared Coupled Plasma (ICP). The results of this experiment are shown in Table 7.1-3.

4. Effect of grinding-splitting-agglomeration on material balance:

Samples of 250-g pulverized (14 mesh x 0) Illinois #6 coal were wet ground in the stirred-ball mill to 200 mesh x 0. The wet ground coal was split using a mechanical splitter and the samples were subjected to the agglomeration test using n-heptane as agglomerant. The product and refuse were recovered and dried in an oven at 60 °C. The product and refuse of each run were weighed and ash, total sulfur and organic sulfur were analyzed. The experimental data collected in these experiments are shown in Table 7.1-4.

As can be seen in Table 7.1.1-1, the measured water content in Illinois #6 coal was 8.9% which results in an actual coal weight (feed to the stirred-ball mill) of 228 g (dry basis). The water content for Illinois #6 coal was found to be $8.9 \pm 0.5\%$ in other experimental runs performed in our laboratory.

Figures 7.1.1-1 through 7.1.1-4 depict the results of material balances for the total, ash, total sulfur, and inorganic sulfur weights of each sample. The error bars displayed in the plots were obtained from the statistical analysis of these experiments as well as several previous experiments.

The material balance data listed in Table 7.1.1-1 show that there was only a minimal coal loss during wet grinding (about 2 g). This may be due to the entrapment of some coal particles among the steel balls used in the grinding process. A loss of about 8 g of coal, however, was observed during splitting step as shown in Table 7.1.1-2. The comparison between the ash weights before and after splitting suggests that the lost material had a high ash content which may be due to settling of hard, large, heavy particles in the mechanical splitter used in the splitting operation.

Table 7.1.1-3 shows that the ICP analysis of the filtrate of the feed coal (4500 g) resulted in a sulfur concentration of 270 ppm and an iron concentration of 63 ppm. This means that 1.22 g of sulfur and 0.28 g of iron were leached out of the sample during grinding.

The material balance for the agglomeration tests, shown in Table 7.1.1-4, revealed no significant losses of coal. However, a reduction of about 1 percentage point was observed for the inorganic sulfur content.

7.1.2 Comparison Between the Composition of First and Second Drums

In order to determine the cause for the reduction in inorganic sulfur content observed in the material balances discussed in the previous section, an analysis of sulfur forms was conducted on pulverized (14 mesh x 0) and wet ground (200 mesh x 0) samples of Illinois #6 and Pittsburgh #8 coals from the first drums.

The total sulfur in the samples was determined using the LECO Sulfur Analyzer. The samples were then subjected to acid leaching to extract sulfate and pyritic sulfur. The sulfate sulfur was extracted with dilute hydrochloric acid. The sulfur in the extract was determined using ICP analysis. For Illinois #6 coal, sulfate was also determined gravimetrically by precipitating sulfates as BaSO_4 according to the standard method ASTM D2492⁽⁷⁾. The remaining sulfur content in the leached sample (corresponding to organic plus pyritic sulfur) was again measured using the LECO Sulfur Analyzer.

The pyrite (FeS_2) was extracted (from the sample treated with HCl) by dilute nitric acid. The extracted iron and sulfur were determined using ICP analysis. The remaining sulfur content in the leached sample (corresponding to organic sulfur) was determined using the LECO Sulfur Analyzer. The pyritic sulfur content was obtained by difference.

Tables 7.1.2-1 and 7.1.2-2 show the experimental data obtained in the analysis for Illinois #6 and Pittsburgh #8 coal, respectively. Table 7.1.2-3 summarizes the total, pyritic, sulfate, and organic sulfur contents for both coals. The data show that, in general, a good agreement among the analytical techniques was obtained for the sulfate and pyritic sulfur determinations.

The total and organic sulfur measurements are in agreement with the values obtained in the original ASTM analysis (Table 3.1-1). The values of the sulfate sulfur content, however, are higher than those determined by BCR Laboratory for the original samples. For Pittsburgh #8 coal, the sulfate sulfur content was found to be between 0.64 and 0.94%, and for Illinois #6 coal, the sulfate sulfur content varied between 0.63 and 1.05%. The values reported earlier were 0.12% for Pittsburgh #8 coal and 0.11% for Illinois #6 coal.

The data shown in Table 7.1.2-3 indicate that the coal samples used in these experiments were oxidized. In order to determine whether oxidation occurred during pulverizing, ASTM standard method D2492 was used to perform sulfate sulfur analyses on delumped (1/2" x 0) and pulverized (14 mesh x 0) samples of Illinois #6 coal. As can be seen in Table 7.1.2-3, the delumped samples exhibited sulfate sulfur contents which are very similar to those measured for the pulverized samples. This seems to indicate that little or no pyrite oxidation occurred during the pulverizing step. It can be concluded that oxidation occurred during storage in the sealed bags.

In order to determine whether oxidation also occurred in the unopened drums, pulverized coal samples obtained from the second drums were analyzed to determine their ash and total, sulfate, pyritic, and organic sulfur contents according to the techniques described previously. The results of the sulfur analyses are summarized in Tables 7.1.2-4, 7.1.2-5, and 7.1.2-6 for Upper Freeport, Pittsburgh #8, and Illinois #6 coals, respectively. Table 7.1.2-7 lists the sulfate and pyritic sulfur contents obtained using ICP.

Figures 7.1.2-1 and 7.1.2-2 compare the sulfate and pyritic sulfur contents obtained using the LECO-132 analyzer and ICP. The error bars indicate the 95% confidence intervals for the LECO-132 measurements (only one analysis of the filtrate was performed and thus no error bars were calculated for the ICP data). The main source of the variation in the data is the inconsistency of the pyrite content of the samples. This may be due to the fact that pyritic sulfur is not uniformly distributed in the coal matrix, and the presence or absence of a few pyrite particles can greatly alter the sulfur content of the sample.

The data depicted in Figure 7.1.2-1 show a very good agreement between the sulfate sulfur results obtained with both techniques. The pyritic sulfur data show that for Upper Freeport and Pittsburgh #8 coals, the ICP results fell within the 95% confidence level of the values determined using the LECO-132 analyzer. For Illinois #6 coal, the pyritic sulfur contents obtained using ICP were slightly lower than those measured using the LECO-132 analyzer. These differences are probably due to changes in the weight of the solid samples during the leaching steps.

Table 7.1.2-8 compares the total and sulfate sulfur of the first and second drums. For the three coals, the sulfate sulfur content in the new drums are significantly higher than in the first drums. The large increase in sulfate sulfur content suggests that the coals in the new drums are oxidized.

The results of the ash analyses for the second drums are listed in Table 7.1.2-9. The data agree well with those determined for the first drums: 12.4%, 11.4%, and 17.2% for Upper Freeport, Pittsburgh #8, and Illinois #6 coals, respectively.

7.1.3 ESCA Analysis of Pulverized and Wet Ground Coal

X-ray Photoelectron Spectroscopy (XPS) or Electron Spectroscopy for Chemical Analysis (ESCA) was utilized monitoring changes in coal surface composition as a result of acid leaching. According to the ASTM standard method D2492, hydrochloric acid leaching removes the sulfate sulfur in coal, and leaching with nitric acid removes pyritic sulfur⁽⁷⁾. The remaining sulfur is attributed to the organic sulfur. Using this method it is possible to determine the amounts of these three sulfur forms in coal by analyzing the extracts for sulfur and by measuring the sulfur content of the leached samples. ESCA analysis can be used to provide both qualitative and semi-quantitative information about the presence and relative abundance of the three sulfur forms on the coal surface.

Pulverized and wet ground (200 mesh x 0) samples of Pittsburgh #8 and Illinois #6 coals (first drums) were examined. For Illinois #6 coal, the original 14 mesh x 0 pulverized sample was analyzed, while for Pittsburgh #8 coal, the pulverized sample was manually ground (for ASTM sulfur analysis purposes) to 60 mesh x 0 prior to the ESCA analysis. Three samples in each series were analyzed using ESCA: a base coal sample, a sample leached with a hydrochloric acid solution to remove sulfates, and a sample leached with nitric acid solution (after HCl leaching) to remove pyrite.

For ESCA analysis, the 200 mesh x 0 samples were prepared by making a slurry of coal and methanol using approximately 0.1 g of coal and 1 ml of methanol. This slurry was then deposited onto a silver foil and dried for approximately 10 minutes, allowing enough time for the methanol to evaporate. Pulverized coal samples were prepared by sprinkling the coal particles onto double sided sticky tape mounted on a silver foil.

Figures 7.1.3-1 and 7.1.3-2 show the ESCA S 2p and Si 2s spectra for the pulverized and wet ground Pittsburgh #8 coal samples. The bottom spectrum is for base coal, the middle spectrum is for coal after leaching with HCl, and the top spectrum is for the sample after leaching with HCl and HNO₃. The sulfur spectral window shows two distinct peaks. The first peak at approximately 170 eV is due to sulfur in the form of sulfate, and the second peak, at approximately 164 eV, can be attributed to sulfides, a combination of organic and pyritic sulfur. The removal of sulfate is illustrated by the absence of a sulfate peak in the HCl leached coal spectrum.

Tables 7.1.3-1 and 7.1.3-2 list the binding energy values from ESCA analysis for the Pittsburgh #8 coal samples. These values agree well with those reported in the literature⁽⁵⁸⁻⁶⁰⁾. The precision of the binding energy values is approximately 1 eV.

The percent atomic abundance for the Pittsburgh #8 coal samples is shown in Tables 7.1.3-3 and 7.1.3-4. The detected elements in decreasing order of abundance are carbon (75%), oxygen (21%), silicon (2.5%), sulfur (1%), and iron (0.2%). These concentrations were calculated using sensitivity factors obtained from literature values⁽⁶¹⁾. The abundance of carbon and oxygen is approximately the same regardless of sample treatment for the 200 mesh x 0 and 60 mesh x 0 samples of Pittsburgh #8 coal. A decrease in percent atomic abundance for sulfur and iron is seen after both acid treatments.

Figures 7.1.3-1 and 7.1.3-2 show that for Pittsburgh #8 coal the peak corresponding to the organic and pyritic sulfur decreased in atomic abundance as a result of HNO_3 leaching. This effect is probably caused by the removal of pyritic sulfur. This hypothesis is supported by the ESCA Fe 2p spectra for the same series, shown in Figure 7.1.3-3, which showed a decrease in intensity following acid treatment.

For both samples of Pittsburgh #8 coal, the percent atomic abundances were very similar, and the same trend was observed for sulfur and iron removal after acid leaching. The weak signals made it difficult to detect any changes that might be caused by particle size.

The ESCA S 2p and Si 2s spectra for Illinois #6 coal are shown in Figures 7.1.3-4 and 7.1.3-5, and the ESCA Fe 2p spectra are shown in Figure 7.1.3-6. The total removal of the sulfate peak is seen after treatment with HCl. The sulfide peak area also decreased after treatment with HNO_3 . The binding energy values from ESCA analysis for Illinois #6 coal are shown in Tables 7.1.3-5 and 7.1.3-6. These values agree very well with the literature and with the values found for Pittsburgh #8 coal.

The surface compositions for Illinois #6 coal, expressed as percent atomic abundance of a given element, are listed Tables 7.1.3-7 and 7.1.3-8. The primary components detected on the coal surface are carbon and oxygen. The percent atomic abundances of carbon (65%), oxygen (30%), and silicon (4%), remained relatively constant (within 10% range of each other). The percent atomic abundance decreased for sulfur after treatment with HCl (from ~1% to ~0.5%), and also decreased after the HNO_3 treatment (from ~0.5% to ~0.4%).

Figure 7.1.3-5 shows that for wet ground Illinois #6 coal the peak corresponding to the organic and pyritic sulfur decreased in atomic abundance as a result of HNO_3 leaching, which, as in the case for Pittsburgh #8 coal, could be caused by the removal of pyritic sulfur. This hypothesis is supported by the ESCA Fe 2p spectra for the same series, shown in Figure 7.1.3-6, which showed a large decrease in intensity following acid treatment. For the pulverized sample of Illinois #6 coal, however, although the sulfide peak decreased as a result of HNO_3 leaching, the iron peak remained unchanged. This discrepancy could be due to the large particle size of the sample and will be further investigated.

In conclusion, for both coals, after treatment with HCl, the sulfur in the form of sulfate was completely removed from the coal surface. Subsequent leaching with HNO_3 decreased the percent atomic abundance of

the sulfide forms (organic and pyritic sulfur). The percent abundance of surface iron also showed a decrease in signal intensity in most cases. Thus, it can be postulated that the pyritic sulfur was removed and the sulfide peak reflects the presence of organic sulfur.

7.2 Optimization of the Agglomeration Process Using N-Pentane

The agglomeration process using n-pentane as agglomerant was studied using 200 mesh x 0 wet ground samples of Upper Freeport, Pittsburgh #8, and Illinois #6 coals. The effects of different sample treatments and operation variables on the agglomeration performance were investigated. Appendix I lists the detailed results of the agglomeration tests. The analysis of the experimental results in terms of the agglomeration performance and changes in samples properties are presented in the following.

7.2.1 Effect of Agglomeration Time on the Agglomeration Performance

The effect of agglomeration time on agglomeration performance was studied using a slurry concentration of 2% by weight and agglomeration times ranging from 15 to 60 s. Figure 7.2.1-1 shows the agglomeration results obtained for Upper Freeport coal. As can be seen in this plot, longer agglomeration time results in higher energy recovery but lower ash and pyritic sulfur rejections. The analysis of variance (ANOVA) of the data, listed in Table 7.2.1-1, indicates that the effect of agglomeration time on ash rejection and energy recovery is statistically significant while in the case of pyritic sulfur rejection it is not. It is customary to consider a probability smaller than 0.05 as an indication that a source has a statistically significant effect on the response variable.

Table 7.2.1-2 shows the results of Duncan's Range tests conducted to compare the agglomeration test results for different agglomeration times. In the Duncan's Range Test tables, the responses are displayed in a linear scale and underlined with XXXXs if there is not a difference among them at the significance level used in the analysis (0.05 in this case).

For Upper Freeport coal, Figure 7.2.1-1 shows that for an agglomeration time of 60 s an energy recovery close to 100% was obtained. The Duncan's Range test in Table 7.2.1-2 indicates that for an agglomeration time of 60 s the energy recovery is significantly better than for shorter agglomeration times. The same table shows that for ash rejection, a statistically significant reduction was observed as agglomeration time increased.

For Pittsburgh #8 coal, the effect of the agglomeration time on the agglomeration performance was studied at two n-pentane to coal ratios (PCR). The analysis of variance of the data, shown in Table 7.2.1-3, shows that neither the agglomeration time nor the PCR had a significant effect on the ash and pyritic sulfur rejections.

The average values of the ash and pyritic sulfur rejections were $72\% \pm 2$ and $73\% \pm 3$, respectively. The energy recovery, however, was strongly influenced by both the independent variables as well as by the interaction between them. As the Duncan's range Test in Table 7.2.1-4 shows, longer agglomeration time and higher PCR resulted in significantly higher energy recoveries. Figure 7.2.1-2 shows that for an agglomeration time of 15 s, a higher PCR increases the energy recovery but for longer agglomeration time this effect diminishes (making the interaction between agglomeration time and PCR also statistically significant).

For Illinois #6 coal, the ash and pyritic sulfur rejections obtained in tests conducted using a slurry concentration of 2% by weight were not affected by agglomeration time. Figure 7.2.1-3 and the analysis of variance shown in Table 7.2.1-5 illustrate this finding. A significant effect of the agglomeration time on energy recovery was observed, as Table 7.2.1-5 shows. The Duncan's Range test, shown in Table 7.2.1-6, indicates that longer agglomeration time results in an increase in energy recovery. The highest value of the energy recovery for Illinois #6 coal, however, was only about 70%, significantly lower than the values obtained for Upper Freeport and Pittsburgh #8 coals at the same operating conditions.

In summary, at a slurry concentration of 2% by weight, for the three base coals, no significant effect of the agglomeration time (between 15 and 60 s) on pyritic sulfur rejection was observed. Energy recovery, on the other hand, significantly increased in all cases as agglomeration time increased.

The effect of agglomeration time on performance was further studied for Illinois #6 coal using a slurry concentration of 4% by weight and agglomeration times between 30 and 360 s. The experiments were carried out using a n-pentane to coal ratio of 0.5, and a mixing speed of 9000 rpm. Figure 7.2.1-4 shows the agglomeration test results. The analysis of variance and Duncan's Range tests performed on these data, shown in Tables 7.2.1-7 and 7.2.1-8, indicate that there was no significant effect of the agglomeration time on energy recovery. Ash rejection, on the other hand, was significantly lower for agglomeration times longer than 120 s. A similar behavior was observed for pyritic sulfur rejection, which decreased markedly for agglomeration times longer than 180 s.

These results suggest that in the case of Illinois #6 coal, improvements in performance can not be achieved by increasing the agglomeration time. Therefore, other methods such as using additives, should be considered.

Oxidation indices for Illinois #6 coal samples obtained from agglomeration tests conducted using agglomeration times of 30 and 360 seconds were determined and are shown in Table 7.2.1-9. Significant differences in ash rejection were observed between these two tests. For an agglomeration time of 30 seconds, the ash rejection was 69%, while for 360 seconds, it was 57%. The oxidation indices of product and refuse, however, did not differ significantly.

ESCA and LAMMA analyses of Illinois #6 coal samples obtained from agglomeration tests conducted using agglomeration times of 60 and 360 seconds were carried out. Table 7.2.1-10 and Figures 7.2.1-5 and 7.2.1-6 show the results of the ESCA analyses for the feed, product, and refuse samples. These data illustrate the differences between the bulk and surface compositions of coal samples. While the surface concentration of oxygen follows the expected trends, that is, higher for the refuse and lower for the product, the surface concentration of the other elements analyzed do not always agree with the bulk values.

The main discrepancies between bulk and surface concentrations were observed for sulfur. For both samples the surface sulfur concentration is higher in the product than in the feed. This finding suggests that slime coating may have occurred during the agglomeration process.

The LAMMA results for product samples of Illinois #6 coal are shown in Figure 7.2.1-7. These data indicate that the surface concentrations of Al and K were lower whereas those of Si and Fe were higher for the sample agglomerated for 360 s. The surface concentration of sulfur, on the other hand, was not affected by the agglomeration time.

7.2.2 Effect of Grinding Method on the Agglomeration Performance

The effect of grinding method on the agglomeration performance was studied using Pittsburgh #8 coal. Coal samples were ground for 15 min in the stirred-ball mill and for 20 hours in the ceramic-jar mill. The average volume particle size ($d_{50} = 19 \mu\text{m}$), of both samples was about the same within the experimental error of Microtrac measurements. Three mixing times were used in each case: 15, 30, and 60 s. The analysis of variance of the data, shown in Table 7.2.2-1, indicates that no significant effect of the grinding method on ash and pyritic rejection was observed. The average values of the ash and pyritic sulfur rejections were both $72\% \pm 3$. On the other hand, Figure 7.2.2-1 shows that grinding in the jar mill for 20 hours was particularly detrimental to the energy recoveries, which were on the average 15 percentage points lower (statistically significant) than those obtained for the samples ground in the ball mill. This behavior may be attributed to excessive hydration of the coal particles due to the longer grinding time in the ceramic-jar mill.

7.2.3 Effect of pH on the Agglomeration Performance

The effect of wet grinding and performing agglomeration tests at high pH was studied using Illinois #6 coal. Pulverized coal (14 mesh x 0) was wet ground to 200 mesh x 0 at pH values of 4.5 (natural pH) and 10.2. The agglomeration tests were conducted using a slurry concentration of 2% by weight and an agglomeration time of 60 s. N-pentane to coal ratios of 0.5 and 1.0 were utilized. For the agglomeration tests at high pH, sodium hydroxide (NaOH) was added during grinding to adjust the pH to 10.2 ± 0.3 .

The results of the agglomeration tests are listed in Table 7.2.3-1 and plotted in Figures 7.2.3-1 through 7.2.3-3. These data, as well as the analysis of variance summarized in Table 7.2.3-2 indicate that the pH had no effect on either the pyritic sulfur rejection or the energy recovery. Figure 7.2.3-1, on the other hand, shows that a lower ash rejection was obtained in the tests at high pH compared with the tests conducted at low pH. The analysis of variance indicates that this effect is statistically significant. It may be speculated that this effect is due to an increase in the hydrophobicity of mineral matter caused by precipitation of metal hydroxides on the surface of coal particles.

7.2.4 Characterization of Agglomeration Test Samples

The agglomeration test samples obtained from tests conducted using n-pentane as agglomerant were analyzed using some of the techniques summarized in Task 3. Surface composition was studied using LAMMA and ESCA. Oxidation indices were also determined for feed, product, and refuse from agglomeration tests.

7.2.4.1 Surface Composition (LAMMA)

LAMMA analysis was conducted on Pittsburgh #8 and Illinois #6 coal samples from agglomeration tests carried out using n-pentane as agglomerant. The LAMMA results are shown in Figures 7.2.4.1-1 and 7.2.4.1-2 for Pittsburgh #8 and Illinois #6 coals, respectively. These figures show that for product and refuse, the surface concentration of K decreased. For the refuse samples of both coals, the surface concentrations of S, Si, Fe, and Mg increased and the surface concentrations of Na, K, and Ca decreased. For the product samples, common trends for both coals were observed for the surface concentrations of Na and Ti, that increased, and for the surface concentration of S, that decreased.

For Pittsburgh #8 coal, S, Fe, Mg and Si increased in the refuse and decreased in the product. Na, Al, Ca, and Ti segregated in the opposite fashion, increasing in the product and decreasing in the refuse. For Illinois #6 coal, Na distributed preferentially into the product, while Al and S segregated preferentially into the refuse.

For Pittsburgh #8 coal, the iron and sulfur percent total ionization decreased from feed to product and increased in the refuse. For Illinois #6 coal samples, the same general trend was observed, that is, for iron and sulfur the surface concentrations higher in the refuse than in the product. Some anomalies, however, were observed for iron. The iron concentration increased in both the product and refuse, instead of decreasing in the product and increasing in the refuse.

7.2.4.2 Surface Composition (ESCA)

ESCA analyses of feed, product, and refuse samples from previous agglomeration tests performed using n-pentane as agglomerant were conducted. The results of the analyses for Upper Freeport, Pittsburgh #8, and

Illinois #6 coals are listed in Table 7.2.4.2-1 and plotted in Figures 7.2.4.2-1 and 7.2.4.2-2.

Figure 7.2.4.2-1 shows that there is a strong correlation among the percent atomic abundances for carbon, oxygen, and silicon. The data indicate that an increase in surface carbon concentration always occurs together with decreases in the surface concentration of oxygen and silicon. For Upper Freeport and Pittsburgh #8 coals, it can also be observed that the product exhibits higher carbon and lower oxygen and silicon concentrations than the feed. As expected, the refuse exhibits the opposite trend.

The changes in surface concentration were more pronounced for Upper Freeport coal. This finding agreed with the results of the agglomeration tests in which the differences between the product and refuse compositions were larger because of the higher yields obtained for Upper Freeport coal, as compared to Pittsburgh #8 coal.

For Illinois #6 coal, however, the surface concentration data showed an increase in oxygen and silicon together with a decrease in carbon for both the product and refuse when compared with the feed. The changes in surface concentration were larger for the refuse, as expected, since its mineral matter content was higher. The changes in surface oxygen concentration for the product suggested that this sample was "oxidized". This phenomenon could also be due to slime coating of the coal particles which in turn may explain the relatively poor performance generally obtained with Illinois #6 coal.

The surface concentrations of iron and sulfur, shown in Figure 7.2.4.2-2, follow similar trends as those observed for the silicon and oxygen. The percent atomic abundances for these two elements are in most cases smaller than 1% (the exception is iron for Upper Freeport coal refuse which reaches 1.13% atomic abundance).

7.2.4.3 Surface Functional Groups

The oxidation indices for agglomeration test samples of Upper Freeport, Pittsburgh #8, and Illinois #6 coals were determined and the results of these measurements are shown in Table 7.2.4.3-1 and Figure 7.2.4.3-1.

For Upper Freeport coal, no significant difference was detected between the feed and product. The oxidation index of the refuse was significantly higher than the feed and product. This could result from the relatively high concentration of mineral matter in the refuse. For Pittsburgh #8 and Illinois #6 coals, the feed and product showed the same oxidation indices.

7.3 Optimization of the Agglomeration Process Using N-Heptane

Although a good performance was obtained using n-pentane as agglomerant, its low boiling point meant that the agglomerates formed were very unstable. For this reason an investigation of the agglomeration process was carried out using n-heptane as agglomerant. This study was conducted by performing several series of tests in which the effect of operating variables on the agglomeration performance was investigated for the three base coals. Appendix J lists the detailed results of these tests.

7.3.1 Comparison with N-Pentane

The effect of the n-heptane-to-coal ratio (HCR) on performance was studied for Upper Freeport by conducting agglomeration tests using a slurry concentration of 4% by weight, a mixing speed of 14000 rpm, and an agglomeration time of 30 s. The HCRs used were 0.25, 0.50, and 0.75. For comparison purposes, a test was also conducted using n-pentane as agglomerant at a n-pentane to coal ratio of 0.5.

The analysis of variance listed in Table 7.3.1-1 shows that no significant difference was observed between the ash rejections obtained using n-pentane and n-heptane. This table also shows that the HCR had a significant influence on energy recovery. This finding, however, seems to be an artifact of the statistical analysis without any practical interest since the energy recoveries varied between 96% and 99%.

The pyritic sulfur rejections were greatly affected by the agglomerant and the HCR, as Figure 7.3.1-1 shows. The pyritic sulfur rejections obtained using n-heptane were lower than those obtained using n-pentane. The Duncan's Range test, shown in Table 7.3.1-1, indicates that for an HCR of 0.25 the pyritic sulfur rejection was not significantly different from that obtained using n-pentane ($\alpha = 0$ case). For higher HCRs, however, the pyritic sulfur rejection was significantly lower.

A comparison between the agglomeration performance of n-pentane and n-heptane for Pittsburgh #8 coal was also carried out. The agglomeration tests were conducted using an agglomerant to coal ratio of 0.5, a mixing speed of 9000 rpm, a slurry concentration of 4% by weight, and an agglomeration time of 60 s. The results of the experiments, shown in Figure 7.3.1-2, indicate that higher energy recovery, ash and pyritic sulfur rejections are obtained with n-heptane when compared with n-pentane.

Further research on the effect of the HCR on the agglomeration performance for Illinois #6 coal was performed using a slurry concentration of 4% by weight and HCRs ranging from 1.0 to 2.0. An agglomeration time of 180 s and a mixing speed of 9000 rpm were employed. Figure 7.3.1-3 shows the results of these tests.

The analysis of variance, summarized in Table 7.3.1-2, indicates that the HCR had a significant effect on energy recovery. The Duncan's Range test, also listed in Table 7.3.1-2, shows that as the HCR increased from

1.0 to 1.5, the energy recovery increased but for higher values no significant improvement was observed. On the other hand, Figure 7.3.1-3 shows that increasing the HCR from 1.0 to 1.25 resulted in a reduction in the ash and pyritic sulfur rejections. For higher HCRs, no further decrease in the ash and pyritic sulfur rejections was observed. The results of these experiments suggest that an agglomeration time of at least 60 s and a HCR between 1.0 and 1.5 yields the optimum agglomeration performance for Illinois #6 coal. These results are in the same range as those obtained using n-pentane as agglomerant.

The oxidation indices of feed, product, and refuse samples were determined. Table 7.3.1-3 shows that similarly to the behavior observed in the agglomeration tests conducted using n-pentane as agglomerant, no difference between the oxidation indices of the samples was observed.

7.3.2 Agglomeration Tests Followed by High-Shear Washing Steps

Agglomeration tests followed by high-shear washing steps were conducted using Upper Freeport and Pittsburgh #8 coals. The washing steps were performed by adding water to the clean coal product to form a slurry. The slurry was then agitated in the Waring blender without adding any agglomerant.

In the agglomeration experiments, a slurry concentration of 4% by weight, a mixing speed of 9000 rpm, and a HCR of 0.5 were employed for both coals. Agglomeration times of 15 and 60 seconds were used for Upper Freeport and Pittsburgh #8 coals, respectively. The same mixing times were used in the washing steps.

Figure 7.3.2-1 shows that for Upper Freeport coal, the washing step did not improve the ash and total sulfur rejections. A minor decrease in energy recovery was observed for both washing steps. These results suggested that strong agglomerates were formed in the agglomeration step, and therefore, the washing steps did not release entrapped mineral particles (including pyrite) within the agglomerates.

Figure 7.3.2-2 shows that for Pittsburgh #8 coal, ash and total sulfur rejections increased as a result of the washing step. Ash rejection increased about 8 percentage points while the total sulfur rejection increased about 6 percentage points. A minor reduction of about 2 percentage points in the energy recovery was also observed. It is believed that for Pittsburgh #8 coal, the agglomerates were weaker than those formed using Upper Freeport coal. It was possible then to release mineral matter and pyrite from the agglomerates during the washing step resulting in an increase in ash and total sulfur rejections.

7.3.3 Use of Pyrite Depressants

Lime (CaO) and ferric chloride (FeCl₃) were employed as pyrite depressants in agglomeration tests carried out using Pittsburgh #8 coal. Only lime resulted in a significant improvement in the pyritic sulfur rejection.

7.3.3.1 Agglomeration Tests Using Lime as Pyrite Depressant

Agglomeration tests utilizing lime (CaO) as pyrite depressant were performed using Pittsburgh #8 coal. The experiments were conducted using a HCR of 0.5, an agglomeration time of 60 s, a mixing speed of 9000 rpm, and a slurry concentration of 4% by weight. The agglomeration results are plotted in Figure 7.3.3.1-1.

The data show that as the lime dosage increased up to 6.6 lb/ton, pyritic sulfur rejection increased, but for higher dosages, a reduction was observed. The pyritic sulfur rejection increased from 62% with no lime added to 69% for a dosage of 6.6 lb/ton. The energy recovery, on the other hand, remained at about 99% for lime dosages between 0 and 3 lb/ton. At 6.6 lb/ton, the energy recovery was about 97%. At higher lime dosages, the energy recovery decreased further, reaching 89% for a lime concentration of 10.8 lb/ton. An increase of about 2 percentage points in ash rejection was also observed for a lime dosage of 6.6 lb/ton. The depression of pyrite can be attributed to preferential adsorption of Ca cations on pyrite particles⁽⁶²⁾. The adsorption of cations on surface renders it more hydrophilic, resulting in an increase in the pyritic sulfur rejection.

Thus, the optimum lime dosage under these operating conditions is about 6.6 lb/ton, since at this concentration a maximum in pyritic sulfur rejection is obtained with only a loss of about 2 percentage points in energy recovery.

LAMMA analyses were conducted on Pittsburgh #8 coal product obtained from agglomeration tests carried out using a lime dosage of 6.6 lb/ton. The results of the LAMMA analyses, shown in Figure 7.3.3.1-2, indicate that the surface elemental concentration of iron, sulfur and silicon were lower in the samples obtained in the presence of lime. The trend for these elements agrees with the bulk analyses of the total sulfur, pyritic sulfur, and ash contents of the products. The surface concentration of calcium, on the other hand, was higher in the coal sample obtained using lime as pyrite depressant which was expected.

7.3.3.2 Agglomeration Tests Using FeCl₃ as Pyrite Depressant

Agglomeration tests using FeCl₃ as pyrite depressant were carried out with Pittsburgh #8 coal. The experiments were conducted using a slurry concentration of 4% by weight, a mixing speed of 9000 rpm, a HCR of 0.5, and an agglomeration time of 60 seconds. Table 7.3.3.2-1 shows the agglomeration data for FeCl₃ dosages of 0, 3, and 5 lb/ton. As can be seen, no significant effects on the agglomeration performance are obtained as a result of FeCl₃ addition.

7.3.4 Use of Tall Oil as Binder

Agglomeration tests using n-heptane as agglomerant followed by the addition of tall oil as binding agent were conducted using Illinois #6 coal. The following experimental procedure was utilized:

1. 500 g of a 4% by weight coal/water slurry with 20 g of n-heptane ($HCR = 1.0$) were mixed for 3 min at a mixing speed of 9000 rpm in the high-shear Waring blender.
2. The slurry was transferred to a container and 200 g of water were added.
3. 2 g of tall oil (tall oil to coal ratio of 1/10) were added.
4. The container was shaken gently until large and strong agglomerates were formed.

The results of this test are shown in Figure 7.3.4-1 together with the results obtained without using tall oil as a binder. These data show a large increase in the yield and energy recovery as a result of the addition of tall oil as a binder after the high-shear agglomeration step. However, the pyritic sulfur rejection was lower, probably due to entrapment of pyrite during the formation of the large agglomerates.

7.3.5 Use of Finer Sieve for Product/Refuse Separation

The study of the agglomerate size and structure performed using the SEM showed that Illinois #6 coal agglomerates were weak and smaller than 150 mm (see Section 7.8). Visual observation also indicated that the 120-mesh (125 mm) sieve currently used in the agglomeration experiments did not retain all the agglomerates formed in the high-shear mixing step of the process. In order to limit the amount of clean coal product reporting to the refuse, a 230-mesh (63 mm) sieve was utilized to separate the product from refuse.

The agglomeration tests were conducted using a slurry concentration of 4% by weight, a mixing speed of 9000 rpm, and in the case of the 230-mesh tests at two pH values: 3.8 (natural pH) and 12.0. A comparison between the results obtained using the 120 and 230 mesh sieves is shown in Figure 7.3.5-1. The data indicate that at the natural pH of the coal, the use of a 230-mesh sieve increases the energy recovery from 83% to 93% without detrimental effects on the ash and inorganic sulfur rejections. At pH 12, an increase in the inorganic sulfur rejection is observed, but this is at the expense of a reduction in the energy recovery. As observed for the experiments conducted using n-pentane (Section 7.2.3), high pH causes a decrease in ash rejection.

7.4 Fine Wet Grinding Using Ceramic Balls

The effect of fine grinding on the agglomeration performance was studied using the three base coals. The influence of the interaction between grinding time and several other operating variables such as pH, HCR, and agglomeration time on the process performance was analyzed.

Pulverized (14 mesh x 0) samples of the three base coals were wet ground using 7/32" ceramic balls as grinding medium. Samples of 0.25 kg of pulverized coal were ground in the stirred-ball mill with 1 kg of water and 3.5 kg of ceramic balls. The Microtrac particle size analyzer was utilized to determine the particle size distributions shown in Figures 7.4-1 through 7.4-3. Figure 7.4-4 also shows that, as expected, the average particle size (d_{50}) decreased as grinding time increased.

The agglomeration tests were conducted using n-heptane as agglomerant, a mixing speed of 9000 rpm, and a slurry concentration of 4% by weight. The detailed data for the particle size distributions, pyrite size and association, and agglomeration tests are listed in Appendix K.

7.4.1 Pyrite Size and Association

Particle size distribution and pyrite size and association were determined for pulverized and wet ground coal samples. The results of these analyses are summarized in Figures 7.4.1-1 through 7.4.1-3.

The data show that for the three base coals, 5 min grinding time greatly increases the amount of free pyrite and decreases the amount of locked pyrite. For longer grinding times, however, the free and locked pyrite fractions do not follow a clear trend. For instance, for Pittsburgh #8 and Illinois #6 coals, 20 min grinding time resulted in an increase in the amount of locked pyrite when compared with the sample ground for 5 min. A similar anomalous effect was observed for the samples of Upper Freeport coal ground for 10 and 30 min. This finding can only be explained as an artifact of the analysis, such as poor dispersion of the fine coal particles during the sample preparation.

7.4.2 Upper Freeport Coal

An optimization program for the agglomeration process performance was conducted using Upper Freeport coal ground between 12 and 98 min. The experiments were arranged according to a central composite design with three independent variables.

A central composite design is a 2^k factorial design augmented with additional points to allow the estimation of the coefficients of a second order surface. A geometric representation of a three variable ($k = 3$) central composite design is given in Figure 7.4.2-1. As can be seen in this figure, the first eight points are the usual factorial points for fitting a first order model, the ninth point is the center point of the design, and the six remaining points are the axial points of the cube⁽⁶³⁾.

The effect of the grinding time, n-heptane to coal ratio (HCR), and pH on the agglomeration performance was studied. Agglomeration tests were conducted for 15 different experimental conditions (points). For the central

point (HCR = 0.40, Grinding Time = 55 min, and pH = 7.0), six agglomeration tests were performed and for the other points, 2 or 3 tests were carried out resulting in a total of 39 tests. The results of the agglomeration tests are summarized in Table 7.4.2-1.

A statistical analysis of the data was carried out in order to obtain response curves that can be used to indicate an optimum point or trends/interactions between the variables. The statistical analysis was performed using a commercial software package, Number Cruncher Statistical System (NCSS)⁽⁵⁰⁾. The response surface coefficients and their respective levels of significance were determined for the energy recovery, ash and inorganic sulfur rejections.

The statistical analysis of the data indicates that the energy recovery is strongly affected by the HCR. The data in Table 7.4.2-1 show that a HCR of 0.10 results in an energy recovery of 87% while for larger HCRs, the energy recoveries are about 99%. Because of the narrow range of energy recoveries for HCR larger than 0.10, the effect of the other variables on this response can not be discerned since the effect is of same order of magnitude as the standard deviation of the data.

The statistical analysis of the also data shows that the grinding time and pH have a significant effect on the ash rejection. A plot of these data in Figure 7.4.2-1 shows a clear trend for the effect of the grinding time on the ash rejection. In this case a longer grinding time increases the ash rejection until it reaches an asymptotic maximum of about 65% for a grinding time of 55 min.

In the case of the inorganic sulfur rejection, the statistical analysis of the data indicates that only the grinding time has a significant effect on this response. A close look at the data also shows that no significant effect is obvious for the inorganic sulfur rejections.

7.4.3 Pittsburgh #8 Coal

Pittsburgh #8 coal samples were wet ground for 60, 80, and 120 min and subjected to agglomeration tests carried out using a n-heptane to coal ratio of 0.5. The results of these tests are shown in Table 7.4.3-1 along with the average particle size of the samples (d_{50} measured with Microtrac).

Figure 7.4.3-1 shows that as the grinding time increased, the agglomeration time required to achieve an energy recovery of 99% increased. For the samples ground for 60 min, an energy recovery of 99% was obtained at an agglomeration time of 150 s, while for the samples ground for longer time, an agglomeration time of 180 s was required to achieve the same result. The data also showed an improvement in ash rejection when the agglomeration time was increased from 120 to 150 s. Agglomeration time longer than 150 s, however, did not

result in further improvement in the ash rejection. The inorganic sulfur rejection, on the other hand, was found to decrease when the agglomeration time was increased from 150 to 180 s.

The effect of grinding at high pH on the performance of the agglomeration process was also studied using 80 min grinding time at an initial pH equal to 11 (the final pH after grinding was 6.1). The wet ground coal was subjected to agglomeration tests conducted using HCRs of 0.50 and 0.75, and agglomeration times ranging from 90 to 150 s. The agglomeration results of these tests are shown in Table 7.4.3-2. In some cases, the agglomerate was subjected to a high-shear washing step, where the product was diluted with 1 liter of water, mixed in the Waring blender for 1 min, and then separated using a 115-mesh sieve.

The agglomeration results given in Table 7.4.3-2 show higher ash and inorganic sulfur rejections for the samples ground for 80 min at high pH when compared with those obtained for the samples at the natural pH of the coal (Table 7.4.3-1). This finding is illustrated in Figure 7.4.3-2. It is believed that grinding at high pH caused a better dispersion of the coal and mineral particles during agglomeration resulting in higher product quality.

Figure 7.4.3-2 also shows that high-shear washing of the agglomerates had a beneficial effect on the product quality. It is believed that washing releases the mineral matter and pyrite entrapped in the agglomerates and as a result the product quality increases.

The above data indicate that the interactions among the operating variables play a significant role in the agglomeration performance for finely ground Pittsburgh #8 coal. In order to optimize the agglomeration process performance, an experimental program was conducted using a central composite design to organize the tests. Four variables were studied: n-heptane to coal ratio (HCR), pH, agglomeration time, and grinding time. For $k = 4$, a total of 25 ($16 + 9$) points have to be determined. For the central point (HCR = 0.5, Grnd. Time = 60 min, pH = 7, and Agg. Time = 150 s), nine agglomeration tests were performed and for the other points, 2 or 3 tests were performed resulting in a total of 63 tests. The results of the agglomeration tests are summarized in Table 7.4.3-3.

A statistical analysis of the data was carried out in order to obtain response curves that can be used to indicate an optimum point or trends/interactions between the variables. The response surface coefficients and their respective levels of significance were determined for the energy recovery, ash and inorganic sulfur rejections.

The statistical analysis of the data indicates that the energy recovery is strongly affected by the HCR. The data in Table 7.4.3-3 show that a HCR lower than 0.3 results in a significant decrease in energy recovery. On the other hand, as long as the HCR is equal or higher than 0.3, energy recoveries above 90% are obtained. Because of the narrow range of energy recoveries, the effect of the other variables on this response can not be discerned since the effect is of same order of magnitude as the standard deviation of the data.

The analysis of the data also shows that the grinding time, pH, and agglomeration time as well as their interactions have a statistically significant effect on the ash and inorganic sulfur rejections. The second order response model for the inorganic sulfur rejection is illustrated in Figures 7.4.3-3 and 7.4.3-4. The plot in Figure 7.4.3-3 shows that as the grinding time increases the effect of pH on the inorganic sulfur rejection becomes stronger. This plot also suggests that using longer grinding time and higher pH results in higher pyritic sulfur rejection.

The plot in Figure 7.4.3-4 shows the effect of the interaction between agglomeration time and pH on the pyritic sulfur rejection. The response model indicates that at higher pH and longer agglomeration times the effects of both variables on the inorganic sulfur rejection are stronger. The data also point out that better results can be obtained for long agglomeration time and high pH.

7.4.4 Illinois #6 Coal

The effect of grinding time on the agglomeration performance was studied using Illinois #6 coal. Samples wet ground for 5, 20, and 60 min were subjected to the standardized agglomeration procedure using a HCR of 1.0 and an agglomeration time of 60 s. The particle size distributions of the feed, product, and refuse, shown in Figure 7.4.4-1, were determined using Microtrac. The average diameters (d_{50} by volume) are listed in Table 7.4.4-1. These data indicate that for the sample ground for 5 min there was a reduction of about 7 microns in the average particle size of the refuse sample. This could be the result of retaining some large particles (> 125 microns) on the 120-mesh screen used to separate the product from refuse in the agglomeration process. For the samples ground for 20 and 60 min, no significant differences among feed, product, and refuse particle size distributions were observed.

The results of the agglomeration tests are listed in Table 7.4.4-2 and summarized in Figure 7.4.4-2. These data show that the yield and the quality of the product (in terms of its ash, sulfur, and inorganic sulfur contents) were greater for shorter grinding time. This resulted in increasing energy recovery, and decreasing ash and inorganic sulfur rejections (the improvement in product quality is not enough to offset the increase in yield) for longer grinding times. The decrease in energy recovery for smaller particle sizes is probably due to insufficient agglomeration time and/or n-heptane to coal ratio. Because of the increased external surface area of finely ground coal samples, longer agglomeration times and higher agglomerant dosages may be required to achieve the same performance as large particles. Furthermore, oxidation may occur as the coal is ground for a longer period of time, decreasing the hydrophobicity of the sample and thus reducing its potential for agglomeration.

Further studies were carried out using Illinois #6 coal wet ground for 60 min. The data in Table 7.4.4-3 indicate that the HCR and the agglomeration time have a strong effect on the energy recovery, ash and

inorganic sulfur rejections. These data show that a longer agglomeration time, up to 180 s, results in higher energy recovery. Figure 7.4.4-3 indicates that the energy recovery sharply increases as the HCR is increased from 0.5 to 2.0. For HCRs greater than 2.0, only a small increase in energy recovery can be observed.

The effect of the HCR on the inorganic sulfur rejection can also be delineated from the data shown in Figure 7.4.4-3. As can be seen, the inorganic sulfur rejection decreases as the HCR increases, reaching an asymptotic value of 60% for a HCRs higher than 2.0. The data in Table 7.4.4-3 show that the agglomeration time, on the other hand, does not have a significant effect on the inorganic sulfur rejection. It can also be seen that the ash rejection is found to follow closely the trend observed for the inorganic sulfur rejection.

The effect of pH on the agglomeration process performance was also studied using finely ground samples of Illinois #6 coal. The agglomeration tests were carried out using a HCR of 4.0. The results of the experiments, plotted in Figure 7.4.4-4, show that increasing the agglomeration test pH from 3.5 (natural pH) to 8.0 results in a significant increase in the inorganic sulfur rejection without detrimental effects in the energy recovery. At an agglomeration test pH of 11.5, the inorganic sulfur rejections is even higher, reaching a 76%. At pH 11.5, however, the energy recovery decreased more than 10 percentage points when compared with those obtained at lower pH.

The use of the 230-mesh (63 μ m) sieve to separate product and refuse was tested using Illinois #6 coal wet ground for 4 hours to reach an average particle size (d_{50} measured with Microtrac) of 3.7 mm. The agglomeration tests were conducted using a HCR of 4.0 at the natural pH of the slurry (3.8) using an agglomeration time of 180 s and at a pH of 11 using an agglomeration time of 360 s. The agglomeration time for each pH was determined as the optima for the pertinent conditions. The average results of the agglomeration tests are listed in Table 7.4.4-4. It can also be seen that energy recoveries above 90% were obtained in all cases when a 230-mesh sieve was used. The statistical analysis of the data, summarized in Table 7.4.4-5, indicates that the effect of pH on the inorganic sulfur rejection is significant. The inorganic sulfur rejection increased about 20 percentage points when high pH was employed. The energy recovery, on the other hand, was only significantly affected by the sieve size. The use of the 230-mesh sieve resulted, on the average, in an increase of about 18 percentage points in energy recovery when compared with the 120-mesh sieve.

From this analysis, it is possible to point out that for finely ground Illinois #6 coal the use of high pH and a 230-mesh sieve gives the best results in terms of energy recovery and inorganic sulfur rejection. In the case of mineral matter removal, however, a comparison among the product ash contents obtained for different particle sizes suggests a strong correlation between particle size and pH. Table 7.4.4-6 shows that at the natural pH of the coal (about 3.8), a smaller particle size results in a higher ash content but at high pH the opposite occurs. This effect may be due to an increase in the hydrophobic character (relative to clean coal) of the mineral matter

at high pH due to metal hydroxides precipitation combined with better particle dispersion. Thus, at low pH, mineral matter entrapment due to poor particle dispersion increases as the particle size decreases, resulting in higher ash contents. At high pH, the mineral matter becomes more hydrophobic but this effect is counteracted by better particle dispersion, resulting in lower ash content for smaller particle sizes.

7.5 Selective Grinding

Selective grinding experiments were conducted using the three base coals. Pulverized coal samples (14 mesh x 0) were wet ground for 5 min. The ground samples were then wet sieved using a 70-mesh screen (240 μ m). The coal fractions retained on and passed through the screen were dried, weighed, and analyzed for ash, total and pyritic sulfur contents. These data were used to calculate yield, energy recovery, ash, total sulfur, and inorganic sulfur rejections by considering the fraction passing through the screen as product and the fraction retained on the screen as refuse.

The objective of these experiments was to assess the effect of prior to fine grinding removal of hard-to-grind large particles containing mineral matter and pyrite on the performance of the agglomeration process. The results of the experiments are shown in Table 7.5-1. As can be seen, for Upper Freeport and Pittsburgh #8 coals, only a small amount of ash and inorganic sulfur was rejected by this procedure. For Illinois #6 coal, however, the ash and inorganic sulfur rejections were 17% and 26%, respectively. These data suggest that the addition of a pre-cleaning step, such a particle size classifier, to the agglomeration circuit, could result in a significant improvement in the agglomeration process performance using Illinois #6 coal.

The effects of this procedure on the agglomeration process performance were studied using Illinois #6 coal by regrinding the passed through fraction to an average particle size of 3.7 mm and then conducting agglomeration tests at three different pH: 11.4, 12.0, and 12.5. The regrinding step was carried out in the stirred-ball mill using 640 g of coal, 3.5 kg of 7/32" ceramic balls and 1 liter of water. The grinding time was 4 hours. For comparison purposes, a pulverized coal sample (14 mesh x 0) was also ground to an average particle size of 3.7 mm without including the large particles removal step. The agglomeration tests were performed using a slurry concentration of 4% by weight, a mixing speed of 9000 rpm, an HCR of 4.0, and an agglomeration time of 360 s. The product was separated using a 230-mesh (63 μ m) sieve. These conditions were previously determined to yield the best performance for finely ground Illinois #6 coal.

The results of the agglomeration tests are shown in Table 7.5-2. The data for a pH of 12.5 show that selective grinding increases the ash and pyritic sulfur rejections and decreases the energy recovery. The most pronounced effect is observed for the ash rejection which increases more than 20 percentage points.

The data also show that a higher pH results in a lower energy recovery and ash rejection and a higher inorganic sulfur rejection.

7.6 Agglomeration Tests Using the Additional Coals

The agglomeration process was studied using the three additional coals being investigated in the project. They are: Upper Freeport (Grant County, WV), Wyodak (Campbell County, WY), and Kentucky #9 (Hopkins County, KY). The detailed agglomeration tests results are listed in Appendix L.

Proximate, total sulfur, ultimate, and trace elements analyses were carried out for the three additional coals. Run-of-mine samples of these coals were received in November 1988 in sealed drums under argon atmosphere. The drums were opened, sampled, delumped to 1/2" x 0, and stored in sealed bags under argon atmosphere in November 1991. The delumped samples were then pulverized to 14 mesh x 0 as needed for conducting the experiments. Several pulverized samples of the three additional coals were sent to COAL PETROGRAPHICS ASSOCIATES, INC. for analysis.

Table 7.6-1 shows the results of the ultimate analyses and the gross calorific values (Btu), estimated using Dulong's formula⁽⁶⁴⁾:

$$\text{Btu} = 145.44 \text{ C} + 620 \left[\text{H} - \frac{\text{O}}{8} \right] + 41 \text{ S}$$

where C, H, O, and S are the weight percents of carbon, hydrogen, oxygen, and sulfur, respectively. Table 7.6-2 shows the results of the approximate analyses and the moist, mineral-matter free (Mm-free) calorific value calculated according to⁽⁶⁵⁾:

$$\text{Moist, Mm-free Btu} = \frac{100 \text{ Btu}}{100 - (1.1 \text{ A} + 0.1 \text{ S})}$$

where A and S are the ash and total sulfur weight percents, respectively.

The values of the moist, mineral-matter-free calorific value and the dry, mineral-matter-free fixed carbon content can be used to classify the coals by rank according to the standard designation ASTM D388-84⁽⁶⁵⁾. In the present case the three additional coals belong to the bituminous class and to the groups indicated in Table 7.6-3.

According to the same standard, the agglomerating character of three additional coals is *commonly agglomerating*, although it is warned that there may be some non-agglomerating coals among the bituminous class and that there are notable exceptions in the high volatile C bituminous group.

The trace elements analyses of the three additional coals are shown in Table 7.6-4. In general Upper Freeport coal has a higher content of trace elements than the other two coals. The only exception is the manganese content of Kentucky #9 coal which is the highest.

7.6.1 Upper Freeport Coal (Grant County, WV)

Upper Freeport coal, from Grant County, WV was subjected to agglomeration tests using n-pentane and n-heptane as agglomerants. A drum (about 400 lb) of run-of-mine Upper Freeport coal was delumped to 1/2" x 0, pulverized to 14 mesh x 0, and then wet ground in the stirred-ball mill. The pulverized samples were ground for 60 min using 0.64 kg of coal, 3.5 kg of 7/32" ceramic balls, and 1 liter of water.

The agglomeration tests were conducted using a slurry concentration of 4% by weight, a mixing speed of 9000 rpm, and an agglomeration time of 30 s. The experiments were organized according to a 2-level factorial design with 3 replicates in which the independent variables were the agglomerant type, sieve size, and pH. Two sieve sizes were used for separating product from refuse: 60-mesh (250 μ m) and 120-mesh (125 μ m). The natural pH of the coal, 4.0 in this case, and a pH equal to 11.8 (adjusted prior to the agglomeration test by adding NaOH) were used.

This coal shows an agglomerating behavior very similar to Upper Freeport from Indiana County, PA. Energy recoveries close to 100% and inorganic sulfur rejections of 80% were obtained in the high pH tests. The results of the tests are shown in Table 7.6.1-1 and the statistical analysis of the data is summarized in Table 7.6.1-2. The data show that the pH had a statistically significant effect on the agglomeration performance. A higher pH resulted in average increases of 7 and 18 percentage points in ash rejection and inorganic sulfur rejection, respectively. A small decrease in clean coal yield ($\gg$ energy recovery), about 2%, was also observed at high pH. No statistically significant effect of the sieve size was observed for both agglomerants. Also, no significant effect of the agglomerant type was detected.

7.6.2 Wyodak Coal (Campbell County, WY)

Wyodak coal, from Campbell County, WY was subjected to the agglomeration process using n-heptane as agglomerant. Pulverized coal samples (14 mesh x 0) of 0.64 kg were wet ground for 4 hours in the stirred-ball mill using 3.5 kg of 7/32" ceramic balls and 1 liter of water. The average particle size, d_{50} , of the samples (measured using Microtrac) was 6.0 mm. The agglomeration tests were conducted using a slurry concentration of 4% by weight and a mixing speed of 9000 rpm. The effect of agglomeration time, sieve size (for product/refuse separation), and n-heptane to coal ratio (HCR) on the process performance were studied.

Figures 7.6.2-1 through 7.6.2-3 show the results of the agglomeration tests. These data indicate that the clean coal yield ($\gg$ energy recovery) is higher for longer agglomeration time, higher HCR, and finer sieve size. The ash and inorganic sulfur rejections, on the other hand, follow an opposite trend. The analysis of variance (ANOVA) of the experiments conducted using a HCR of 1.0 is shown in Table 7.6.2-1. It indicates that both the effect of the sieve size and agglomeration time are statistically significant. The agglomeration results indicate that a higher clean coal yield (and consequently lower ash and inorganic sulfur rejections) are obtained for a sieve size of 230-mesh and for an agglomeration time of 360 s.

The effect of sieve size and HCR on the agglomeration process performance were evaluated for an agglomeration time of 360 s. The data show that a higher HCR and a finer sieve size result in higher clean coal yields and lower ash and inorganic sulfur rejections. The analysis of variance of these data, summarized in Table 7.6.2-2, indicates that these effects are statistically significant. The effect of the HCR on the three response variables is more pronounced for the 120-mesh than for 230-mesh experiments. This interaction is statistically significant as the data in Table 7.6.2-2 show.

In summary, Wyodak coal is not "commonly agglomerating." In order to obtain an energy recovery close to 90%, it is necessary to use extreme conditions such as an agglomeration time of 6 minutes, a HCR of 4, and a 230-mesh sieve for product/refuse separation. The inorganic sulfur rejections are less than 40% but it should be kept in mind that the total sulfur content of this coal is only 0.6%.

7.6.3 Kentucky #9 Coal (Hopkins County, KY)

An optimization program for the agglomeration process performance was conducted using Kentucky #9 coal. The experiments were arranged according to a central composite design. A central composite design is a 2^k factorial design augmented with additional points to allow the estimation of the coefficients of a second order surface. A description of a central composite design was presented in the Section 7.4.2.

In order to reduce the required agglomeration time, a mixture, of #6 Fuel Oil and heptane (4g/100g), was used in the agglomeration process. In this case, four variables were studied: hydrocarbon to coal ratio (HYCR), pH, agglomeration time, and grinding time. For $k = 4$, a total of 25 (16 + 9) points have to be determined. For the central point (HYCR = 0.5, Grnd. Time = 60 min, pH = 7, and Agg. Time = 180 s), nine agglomeration tests were performed and for the other points, 2 or 3 tests were performed resulting in a total of 62 tests. The process performance was evaluated in terms of ash rejection, inorganic sulfur rejection, and energy recovery. The results of the agglomeration tests are summarized in Table 7.6.3-1.

A statistical analysis of the data was carried out in order to obtain response curves that can be used to indicate trends/interactions between the variables. The statistical analysis was performed using NCSS, a commercial statistical software. The response surface coefficients and their respective levels of significance were determined for the energy recovery, ash and inorganic sulfur rejections.

The statistical analysis of the data indicates that the energy recovery is strongly affected by the HYCR. The data in Table 7.6.3-1 show that a HCR lower than 0.3 results in a significant decrease in energy recovery. On the other hand, as long as the HCR is equal or higher than 0.3, energy recoveries above 90% are obtained. Because of the narrow range of energy recoveries, the effect of the other variables on this response can not be discerned since the effect is of same order of magnitude as the standard deviation of the data.

The statistical analysis shows that the HCR, grinding time, pH, and agglomeration time as well as their interactions have no statistically significant effect on the ash and inorganic sulfur rejections.

7.7 Trace Element Removal

The U. S. utilities may face serious compliance problems concerning the emission of trace elements due to coal combustion. Although the levels of heavy metals in coal are generally low, the potential environmental hazard may be significant because U. S. power plants consume about 800 million tons of coal annually⁽⁶⁶⁾, releasing thousands of tons of trace elements into the environment each year. Currently, there is no clear understanding of the impact of trace elements on the environment. However, from a legal point of view, the U. S. Congress has listed the compounds of the following elements as hazardous air pollutants in the 1990 Clean Air Act: antimony, arsenic, beryllium, cadmium, chromium, cobalt, lead, manganese, mercury, nickel, and selenium⁽⁶⁷⁾.

An evaluation of the potential of the agglomeration process for the removal of these trace elements was performed using Pittsburgh #8 and Upper Freeport coals. Pittsburgh #8 coal was wet ground to an average particle size (measured using Microtrac) of 9.3 μm and subjected to agglomeration tests conducted using a

HCR of 0.5. The experiments were conducted using an agglomeration time of 60 s, a mixing speed of 9000 rpm, and a slurry concentration of 4% by weight. The trace elements analyses were carried out by COMMERCIAL TESTING & ENGINEERING CO. using the following procedure:

1. The samples were prepared according to ASTM Method D3683⁽⁶⁸⁾. This preparation procedure consists of ashing of the coal sample followed by its dissolution using mineral acids.
2. Antimony, beryllium, cadmium, chromium, cobalt, lead, manganese, and nickel were determined using Inductively Coupled Plasma Emission Spectroscopy.
3. Arsenic and selenium were determined by Graphite Furnace Atomic Absorption.
4. Mercury was determined by Double Gold Amalgamation Cold Vapor Atomic Absorption.

The trace elements concentrations for the feed and product are presented in Table 7.7-1 together with the results of the agglomeration tests. Arsenic, chromium, and manganese show the largest decrease in concentration while beryllium appears to increase in the product.

Trace elements analyses were also conducted for Upper Freeport coal (Indiana County, PA) product and feed samples. The product samples were obtained from agglomeration tests performed using a slurry concentration of 4% by weight, a n-heptane to coal ratio of 0.5, an agglomeration time of 30 s, and a mixing speed of 9000 rpm. The experiments were conducted at the natural pH of the coal, 4.0, and at a pH equal to 12.3. The results of the agglomeration tests and trace element analysis are shown in Table 7.7-2. The data show that lower ash, total sulfur, and pyritic sulfur contents were obtained at high pH. On the other hand, the data do not show a significant difference between the trace element contents of the high and low pH samples. The major reductions in concentration were observed for arsenic, cadmium, chromium, lead, manganese, and nickel which is in agreement with the ash content data of the same samples.

The trace element contents for the product and feed samples can be used to estimate the percentage of each element present in the mineral matter fraction of the coals. These data are tabulated in Table 7.7-3. They show that most of the elements are heavily concentrated in the mineral matter fraction of the coal. The exceptions are beryllium, mercury, and selenium.

These data indicate that selective agglomeration process can indeed remove a significant amount of trace elements. However, there is a large room for improving the efficiency of the agglomeration process in this regard.

7.8 Morphology of Agglomerates

During selective agglomeration processes, the coal particles dispersed in water form "agglomerates" with the addition of small amounts of hydrocarbons. The hydrophobic coal particles form hydrocarbon rich coal agglomerates and the free hydrophilic minerals remain in the water phase. The mechanism and procedures for selective coal agglomeration have been discussed in the literature⁽⁶⁹⁾. However, this mechanism has been described in general surface chemistry terms but little attention has been given to the structure and morphology of the agglomerates. A study aiming to compare the morphology of agglomerates formed with different coals and to define the location of the minerals entrapped in the agglomerates was conducted. This investigation may lead to a better understanding of the agglomeration process and possibly help determine the optimum conditions for agglomeration.

Two methods based on observation and analysis in the Scanning Electron Microscope (SEM) were used in this research. In the first method (quick-freeze method), a sample of coal agglomerates (product) was removed from the screen during selective agglomeration experiments and dropped into liquid nitrogen. The agglomerates were then freeze-dried in order to remove the water without changing their texture. Significant amounts of n-heptane were probably removed in this process. The sample was examined in the SEM in the secondary electron imaging mode (SEI) and backscattered electron imaging modes (BSE). The BSE micrographs taken in the "compo" mode, also showed the location of minerals which have atomic numbers higher than 12 (carbon). These minerals can be identified, as needed, by X-ray microanalysis and X-ray mapping.

In the second method (dispersion method), the agglomerates were placed in water and dispersed by mild shaking. The agglomerates usually float on the surface of the water and, when sufficiently diluted, a sample was picked up on a SEM stub and left to air-dry at room temperature before observation in the SEM.

Micrographs of the agglomerated Upper Freeport coal are presented in Figures 7.8-1 through 7.8-3. Figure 7.8-1 shows the microagglomerates of Upper Freeport coal prepared by the dispersion method. These microagglomerates are tight, round and of the order of 100 μ m in size. Some of them are clustered (Figure 7.8-1, bottom). Two of the larger microagglomerates are shown in Figure 7.8-2. It remains to be determined whether this morphology is reproducible, i.e. independent of the "shaking" process. Specific experiments will be performed to test this hypothesis. It should be mentioned, however, that experiments carried out using product with successive rewashing in the Waring blender (see Section 7.3.4) showed that Upper Freeport coal microagglomerates were stable under much greater shear than that generated in the gentle dispersion procedure used in the present study.

Freeze-dried Upper Freeport coal agglomerates are shown in Figure 7.8-3. Only BSE micrographs are available since charging of the sample in the electron beam deteriorates the image quality of SEI micrographs. The BSE micrographs are very informative but it must be kept in mind that the "compo" mode flattens somewhat the relief of the sample. It appears from these micrographs that the freeze-dried Upper Freeport coal agglomerates tend to fracture along the boundaries between individual microagglomerates. The BSE imaging shows these cracks much better than SEI imaging. The regions between the cracks are of the same size as the microagglomerates in Figures 7.8-1 and 7.8-2. It is expected that the boundaries between the microagglomerates contain more water than the inside of the agglomerates. The agglomerates would tend to fracture more readily along these boundaries on freezing due to the volume expansion of the water turning into ice. The micrographs of Figure 7.8-3 are darkened to highlight the pyrite as the perfectly white small grains. The grayish specks are either silicate or due to charging. Fractures through the microagglomerates are not clearly observed and apparently not common, therefore the minerals in Figure 7.8-3 are mostly on the surfaces or in between the microagglomerates.

A comparison between Illinois #6 and Upper Freeport coals shows dramatic differences in the morphology and texture of their agglomerates. Illinois #6 coal formed extremely weak microagglomerates which tended to sink in the water and to break down during the dispersion procedure. On the other hand, Upper Freeport coal formed very stable microagglomerates which floated on the surface of the water used for dispersion and remained there for days.

Figure 7.8-4 shows Illinois #6 coal microagglomerates with practically no cohesion. Figure 7.8-5 presents an example of some of the microagglomerates which maintained their shape. They are generally smaller than the microagglomerates of Upper Freeport coal. However, even in Figure 7.8-5 it can be seen that the texture of the microagglomerates is not tight. In Figure 7.8-6, an SEI micrograph and the corresponding BSE image of freeze-dried Illinois #6 coal illustrate a very open texture in which microagglomerates cannot be identified. The denser regions lack cohesion, they are loosely packed and appear to contain grains coarser than those observed for Upper Freeport coal. With this loose structure, it is expected that fracture will propagate more readily through the agglomerated material rather than through the boundaries between individual microagglomerates as was observed in Upper Freeport coal. Therefore, for Illinois #6 coal the internal texture of the agglomerates can be observed. In Figure 7.8-6 for instance, two relatively large pyrite particles are clearly visible which are part of the agglomerated particles. Also, in Figure 7.8-7, the open texture characteristic of the agglomerated Illinois #6 coal can be observed.

Pittsburgh #8 coal agglomerates obtained from agglomeration tests carried out using a n-heptane to coal ratio of 0.5 and an agglomeration time of 60 seconds were examined using the quick-freeze and the dispersion method. Figures 7.8-8 and 7.8-9 show agglomerates dispersed in water. They are not well shaped and their size is not as consistent as those of Upper Freeport coal. They are generally composed (see Figure 7.8-8) of

microagglomerates of 100 to 200 μm in size clustered together. The microagglomerates are rougher in surface texture than those of Upper Freeport coal. They tend to break up during drying leading to the formation of a coarse "skin" which cracks and spalls. This is illustrated by the agglomerate shown in Figure 7.8-9 which appears made of several microagglomerates including a larger one about 500 μm in diameter. The increased cracking during drying suggests that the Pittsburgh #8 coal agglomerates contain more water than those of Upper Freeport coal.

Freeze-dried agglomerates of Pittsburgh #8 coal are shown in Figures 7.8-10 and 7.8-11 for the same area. The SEI micrograph in Figure 7.8-10 has more relief than the BSE micrograph. However, the former has more apparent defects due to charging. The texture of the agglomerates shown in Figure 7.8-10 is tight with large voids that probably contained water (ice). Compared with Upper Freeport coal agglomerates, the identity of these microagglomerates is not as clear. They form a fairly continuous mass, with less cracks than for Upper Freeport coal. These findings are consistent with the observed flexible structure for Pittsburgh #8 coal agglomerates.

The evolution of the morphology of agglomerates was also studied for Pittsburgh #8 coal using the dispersion method for different agglomeration times and n-heptane dosages. The influence of the HCR was clearly demonstrated from the characteristics of the agglomerates generated for HCR of 0.05, 0.1, 0.2, and 0.5, all prepared using an agglomeration time of 60 seconds. Micrographs of these agglomerates are shown in Figures 7.8-12 through 7.8-15. For a HCR of 0.05, loose, weak microagglomerates have started to form (see Figure 7.8-12); many are larger than 100 μm . At the intermediate HCR of 0.1 and 0.2 (Figures 7.8-13 and 7.8-14, respectively), the microagglomerates are fairly well formed with a size of the order of 100 μm and a little larger. These agglomerates tend to form a skin on drying which tends to spall apparently under the drying stresses. An HCR of 0.5 results in well formed microagglomerates of about 100 μm in size which tend to join into larger units (see Figure 7.8-15).

The effect of agglomeration time on the agglomerate structure was also studied at a HCR equal to 0.5. For 15 s of agglomeration time, Figure 7.8-16 shows that microagglomerates similar to those produced at 60 s of agglomeration time and HCR of 0.05 were obtained. The morphology of agglomerates formed at 120 s of agglomeration time was similar to that produced at 60 s of agglomeration time but these agglomerates tend to be slightly larger and the individual microagglomerates are less clearly distinguishable (see Figure 7.8-17).

7.9 Coal Wettability

The surface wettability of coal samples obtained from agglomeration was studied by measuring contact angles on coal pellets. Contact angles were measured with n-pentane and n-heptane droplets, and with air bubbles immersed in water as shown in Figure 7.9-1.

The contact angle of n-pentane and n-heptane droplets placed on a coal pellet immersed in water were measured for feed samples of Upper Freeport, Pittsburgh #8, and Illinois #6 coals. The pellets were prepared using a wet ground 200 mesh x 0 coal/water slurry and were not subjected to drying during preparation. The results of these measurements, together with the contact angles for air bubbles measured in the same manner, are shown in Table 7.9-1. The contact angles in the aqueous phase are exceedingly low (smaller than 55° for n-pentane and smaller than 45° for n-heptane) and do not vary with time. These results indicate a hydrophilic behavior of the coal which can be explained by the presence of an adsorbed water film on the surface of the coal pellet.

A second set of pellets was treated by conditioning them in n-heptane for 20 hours before immersion in water. The contact angle of a n-heptane droplet immersed in water was measured for Upper Freeport, Pittsburgh #8, and Illinois #6 coals. These data are also shown in Table 7.9-1. In this case, the contact angles in the aqueous phase were larger than 90 degrees. This result suggests that wetting first by n-heptane enhances the hydrophobicity of the coal surface.

Product and refuse samples of Upper Freeport and Illinois #6 coals were also used for contact angle measurements using n-heptane droplets placed on pellets immersed in water. Table 7.9-2 shows the contact angles obtained with pellets prepared with wet ground samples and the contact angles determined after the same pellets had been immersed in n-heptane for four days prior to the measurements.

The data in Table 7.9-2 show that the contact angles of feed samples exposed to n-heptane increased to values similar to those of the product and refuse samples from the agglomeration tests. These data indicate that as a result of the agglomeration test, n-heptane was adsorbed on the surface of the product and refuse particles conferring them a hydrophobic character when compared with the feed sample.

Still, for both the untreated and treated pellets, the contact angle for the product sample was larger than for the refuse, indicating a more hydrophobic character.

These findings suggest that after the particles are exposed to the agglomerant, it is difficult to distinguish between their surface properties unless external forces that remove the adsorbed film of agglomerant are

applied. High shear mixing in the blender serves this purpose as well as providing a high collision rate between the particles.

7.10 Direct Determination of Pyrite by X-Ray Diffraction

A method for direct determination of the pyrite content of coal using X-ray diffraction (XRD) was developed. Since this technique directly determines pyrite it could eliminate the need for acid leaching prior to pyritic sulfur analysis. There is evidence that the amount and type of sulfur leached is very sensitive to the experimental procedure employed and to the presence of chemicals used in the treatment of the samples. Direct determination of pyrite using XRD could be used in cases where traditional techniques produce unreliable results.

When a crystalline mineral such as pyrite is irradiated by X-rays, these X-rays are diffracted according to Bragg's law. Thus, when a powder sample containing pyrite is placed in a diffractometer and irradiated by monochromatic X-rays (e.g. CuK_α), a number of peaks can be recorded for corresponding pairs of angles of incidence, Q_i , and spacings of the atomic planes of the mineral, d_i . The pattern represents a fingerprint for that mineral and the intensity of the peaks is proportional to the amount of mineral in the sample. Therefore, it can be used for quantitative determination of pyrite.

The quantitative analysis of mixtures of crystalline powders is well established and has been described extensively by Klug and Alexander⁽⁷⁰⁾. Fundamentally, the intensity of the diffraction peaks is proportional to the concentration of the phase responsible for these peaks in the mixture. Several sample preparation methods were tested in order to improve reproducibility. The segregation of pyrite from the coal powder was the main problem affecting the measurements. It was found that grinding the crystalline powders (unknown and standards) to about 5 μm , increased the intensity of the pyrite peaks and improved the reproducibility of the results.

The coal samples were ground with tungsten-carbide (WC) balls in a Spex mill lined with WC. Ground mineral pyrite and 5% by weight of magnesia were added as a standard and mixed in the Spex mill. Each mixture was based on 2 g of coal to which 3%, 5%, or 8% of pyrite were added. The powders were packed in a flat powder holder in order to minimize preferential orientation. The XRD patterns were obtained using a GE XRD700 diffractometer fitted with a monochromator. The sample was scanned at 2 deg/min between $2\theta = 30$ and 65 degrees with CuK_α radiation. The intensities of selected pyrite peaks were plotted as a function of pyrite content. Each point of the plot was an average of 8 to 10 determinations in which the sample was mixed and repacked before recording each X-ray pattern. The integrated intensities corrected for background were determined by measuring peak areas. The pyrite peak intensities were referred to that of the (200) line of

periclase (MgO) in order to improve reproducibility. The corrected peak intensities were then plotted as a function of the pyrite additions and the pyrite content of the sample was given by the intercept of the best fit line through the points.

The experimental procedure was tested on an Illinois #6 feed coal sample. The results are plotted in Figure 7.10-1. The solid line was obtained with the (200) line of pyrite. The dashed line was obtained with the sum of the intensities of the (200) and (311) lines of pyrite. The intercepts gave pyrite contents of 3.5% and 4.3%, corresponding to pyritic sulfur contents of 1.86% and 2.32%. The pyritic sulfur content measured using a conventional sulfur analyzer was 2.39%. Thus, the value obtained using both the (200) and (311) lines was comparable to that obtained by conventional sulfur analysis method. The value obtained with the (200) line of pyrite, however, appears to be lower. The individual points showed good reproducibility but the extrapolation is a source of uncertainty as illustrated by the variation in intercepts in Figure 7.10-1.

7.11 Agglomeration Tests Using Alberta Research Council (ARC) Coal

Agglomeration tests were conducted using a coal sample provided by the Alberta Research Council (ARC). The experiments were performed using n-heptane as agglomerant at n-heptane to coal ratios of 0.5 and 0.3. A slurry concentration of 4% by weight, an agglomeration time of 60 seconds, and a mixing speed of 9000 rpm were utilized

The agglomeration test results are listed in Table 7.11-1. A slightly higher yield and clean coal yield but at the expense of lower ash rejection were obtained in the tests conducted at an HCR of 0.5. The same trend was observed for the total sulfur and inorganic sulfur rejections.

8.0 CONCLUSIONS

The research effort carried out in this project has led to several findings dealing with grinding procedures, surface modification methods, coal samples properties, and the optimization of the agglomeration process using n-pentane and n-heptane as agglomerants. The analytical techniques established in Task 3 and the standardized agglomeration procedure developed in Task 4 were the basis for the experimental work performed in Tasks 5, 6, and 7. The analysis of the information generated in these tasks resulted in the following conclusions:

- » Fine coal beneficiation using selective agglomeration is a very complex process in which the coal properties, grinding procedures, high-shear agglomeration, pre- and post-treatments, and coal surface modification techniques as well as the interactions among these factors play a role in its final performance.
- » Because of the above and the inherent error in sampling and analysis, any study of the agglomeration process should take advantage of statistical design of experiments techniques in order to obtain conclusions that consider the interactions among variables, take into account differences between samples, and determine the statistical significance of each effect on the process.
- » The research work conducted in this project using six different coals shows that achieving a performance goal, such as 85% pyritic sulfur rejection at 85% energy recovery in this case, is strongly dependent on the properties of the coals. There is therefore, no unique solution for all coals, and even for a given coal, the same objective can be attained in several ways.
- » Although the analytical techniques employed in this project provided valuable data regarding the characterization of coal samples, they were not satisfactory in terms of explaining the effects on performance of the surface modification techniques and operating conditions used in the experiments. It is evident that the development of analytical techniques, in special those that examine in-situ surface properties relevant to agglomeration, is in great need.
- » The structure of agglomerates is closely related with the hydrophobicity of the coals. Very hydrophobic coals, such as Upper Freeport, form strong, tight, round agglomerates. Very hydrophilic coals, such as Illinois #6, form loose, weak agglomerates. This behavior is mirrored in contact angle and oxidation index measurements showing that Illinois #6 is the most hydrophilic of the three base coals followed by Pittsburgh #8 and Upper Freeport.
- » Upper Freeport is the most hydrophobic of the three base coals. It agglomerates very easily, and therefore, it is possible to achieve energy recoveries close to 100% using very low agglomerant dosages and very short agglomeration times. For the same reason, entrapment of mineral matter and pyrite in the product is the main problem to be addressed when cleaning this coal.
- » Pittsburgh #8 is a hydrophobic coal, even though not as hydrophobic as Upper Freeport. It is possible to achieve energy recoveries close to 100% using moderate agglomerant dosages and agglomeration times. This coal responds well to treatments aimed at improving ash and pyritic sulfur rejection without decreasing the energy recovery.

- » Illinois #6 is the most hydrophilic of the three base coals. It is not possible to achieve energy recoveries above 90% unless extreme operating conditions are used (very fine grinding, fine mesh product screening, long agglomeration time, and high agglomerant dosage) or a binder is added. Because of the nature of its mineral matter (high content of clays) it is also hard to obtain good ash and pyritic sulfur rejections.
- » Wet grinding results in significantly better ash rejection when compared to dry grinding. Morphological studies indicate that the adhesion of ash-forming particles to clean coal particles significantly decreases when the particles are dispersed in water as in the case of wet grinding. Consequently, the quality of the product coal is improved and higher ash rejections are obtained.
- » Decreasing the coal sample top size from 28 mesh (600 μ m) to 200 mesh (75 μ m) results in a significant increase in energy recovery. This is due to an increase of the hydrophobicity of coal surfaces as a consequence of the liberation of mineral matter during grinding. This effect is found to be more pronounced for more hydrophilic coals, because greater increases in the hydrophobic character of the samples are achieved by grinding finer.
- » Wet grinding in the presence of light hydrocarbons (n-pentane, cyclohexane, and n-heptane) promotes agglomeration that translates into significant decreases in ash and pyritic sulfur rejection. For hydrophobic coals, this effect is stronger and may even impede grinding. As the hydrophobicity decreases, this effect may result in increases in energy recovery but at the expense of lower product quality.
- » Wet grinding in the presence of surfactants, Aerosol-OT and Arosurf MG-83A, or styrene does not result in improvements in the agglomeration process performance. Similarly, the addition of ethanol or methanol prior to agglomeration does not improve performance. The addition of tall oil during grinding increases the energy recovery for Pittsburgh #8 coal. However, this effect is not observed for other coals.
- » In general, increasing the agglomeration time and agglomerant (n-pentane or n-heptane) to coal ratio increases the energy recovery. This effect is more pronounced for lower values of these variables and decreases as they increase resulting in an asymptotic maximum energy recovery which is close to 100% for hydrophobic coals (e.g. Upper Freeport, Pittsburgh #8) and lower for hydrophilic coals.
- » No major differences in the agglomeration performance that can be obtained using either n-pentane or n-heptane are apparent. Different dosages may be needed to achieve the same results but, in general, the optimum performance is the same. The selection of the agglomerant, thus, has to be based in other considerations such as ease of use, recovery and recycling techniques, and cost.
- » The use of a binder can significantly increase the energy recovery for hydrophilic coals and allows the use of shorter agglomeration times and/or lower agglomerant to coal ratios in the agglomeration tests. However, a reduction in the pyritic sulfur rejection caused by pyrite entrapment in the agglomerates accompanies the improvement in energy recovery.
- » High-shear washing of the product agglomerates can improve ash and pyritic sulfur rejection without major detrimental effects on energy recovery. The success of this treatment, however, is coal dependent. For a very hydrophobic coal (e.g. Upper Freeport), no improvement is possible since the agglomerates are too strong and the refuse particles can not be released. On the other hand, for a hydrophilic coal (e.g. Illinois #6), high-shear destroys the agglomerates.

- » The use of a 230-mesh (63 mm) sieve to separate product and refuse of Illinois #6 coal results in a significantly higher energy recovery than that obtained using a 120-mesh (125 mm) sieve. Agglomerate morphology data indicate that for this hydrophilic coal weaker agglomerates are formed which are better retained in a finer sieve.
- » The pyritic sulfur rejection can be increased by the addition of lime. An optimum dosage of 6.6 lb/ton at which the improvement in pyritic sulfur rejection is not offset by a decrease in energy recovery was found for Pittsburgh #8 coal.
- » The amount of locked pyrite decreases and of free pyrite increases when pulverized coal (14 mesh x 0) is wet ground to an average particle size of 30 to 10 microns. The pyrite association analysis, however, can not determine whether further liberation occurs when finer grinding is used.
- » For finely ground coal, less than 200 mesh x 0, high pH (> 9) results in significant improvements in the pyritic sulfur rejection. This effect is, in general, stronger for longer grinding times. It is believed that this is due to better dispersion of the coal particles at high pH (as zeta potential data suggest) which reduces entrapment of pyrite in the clean coal product.
- » Coal samples ground longer (i.e. smaller particle size) require higher agglomerant dosages and longer agglomeration times to achieve the same level of energy recovery obtained with 200 mesh x 0 coal samples. A larger external surface area and increased surface oxidation during longer grinding time are the probable causes for these effects.
- » Wyodak coal is very hard to agglomerate. It requires drastic conditions in order to obtain energy recoveries close to 90% and under these conditions the pyritic sulfur rejection is low. However, its total sulfur content is only 0.6%, which suggests that advanced cleaning might be unnecessary.
- » The agglomerating behavior of Upper Freeport coal from Grant County, WV, is very similar to that of Upper Freeport coal from Indiana County, PA. Both coals are very hydrophobic and therefore it is possible to achieve energy recoveries close to 100% with them.
- » The analysis of trace elements for feed and product samples of Upper Freeport and Pittsburgh #8 coals indicates that most elements are concentrated in the mineral matter fraction of the coals. The exceptions are beryllium, mercury, and selenium.

9.0 REFERENCES

1. Standard Test Method for GROSS CALORIFIC VALUE OF COAL AND COKE BY THE ADIABATIC BOMB CALORIMETER, Designation D2015-85, *1986 Annual Book of ASTM Standards*, Section 5, Volume 05.05, Gaseous Fuels; Coal and Coke, pp. 325-35.
2. Standard Test Method for MOISTURE IN THE ANALYSIS SAMPLE OF COAL AND COKE, Designation D3173-85, *1986 Annual Book of ASTM Standards*, Section 5, Volume 05.05, Gaseous Fuels; Coal and Coke, pp. 403-5.
3. Standard Test Method for ASH IN THE ANALYSIS SAMPLE OF COAL AND COKE FROM COAL, Designation D3174-82, *1986 Annual Book of ASTM Standards*, Section 5, Volume 05.05, Gaseous Fuels; Coal and Coke, pp. 406-9.
4. Standard Test Method for VOLATILE MATTER IN THE ANALYSIS SAMPLE OF COAL AND COKE, Designation D3175-82, *1986 Annual Book of ASTM Standards*, Section 5, Volume 05.05, Gaseous Fuels; Coal and Coke, pp. 410-13.
5. Standard Test Method for PROXIMATE ANALYSIS OF COAL AND COKE, Designation D3172-73, *1986 Annual Book of ASTM Standards*, Section 5, Volume 05.05, Gaseous Fuels; Coal and Coke, pp. 401-2.
6. Standard Test Method for TOTAL SULFUR IN THE ANALYSIS SAMPLE OF COAL AND COKE, Designation D3177-84, *1986 Annual Book of ASTM Standards*, Section 5, Volume 05.05, Gaseous Fuels; Coal and Coke, pp. 418-22.
7. Standard Test Method for FORMS OF SULFUR IN COAL, Designation D2492-84, *1986 Annual Book of ASTM Standards*, Section 5, Volume 05.05, Gaseous Fuels; Coal and Coke, pp. 357-61.
8. Standard Test Method for PREPARING SAMPLES FOR MICROSCOPICAL ANALYSIS BY REFLECTED LIGHT, Designation D2797-85, *1986 Annual Book of ASTM Standards*, Section 5, Volume 05.05, Gaseous Fuels; Coal and Coke, pp. 382-87.
9. Standard Test Method for MICROSCOPICAL DETERMINATION OF THE REFLECTANCE OF THE ORGANIC COMPONENTS IN A POLISHED SPECIMEN OF COAL, Designation D2798-95, *1986 Annual Book of ASTM Standards*, Section 5, Volume 05.05, Gaseous Fuels; Coal and Coke, pp. 388-91.
10. Standard Test Method for Designation MICROSCOPICAL DETERMINATION OF VOLUME PERCENT OF PHYSICAL COMPONENTS OF COAL, D2799-86, *1986 Annual Book of ASTM Standards*, Section 5, Volume 05.05, Gaseous Fuels; Coal and Coke, pp. 392-93.
11. Gray, R. J., *International Journal of Coal Geology*, 2, pp. 79-97, 1982.
12. Brown, G., *The X-ray Identification and Crystal Structures of Clay Minerals*, Mineralogical Soc., London, 1960.
13. Grim, R. E., *Clay Mineralogy*, Mc Graw Hill, 1968.
14. Kakwani, R. M., "Study of Microscopic Structure of Porous Media -- Fine Coal Filter Cakes", Ph.D. Dissertation, School of Engineering, University of Pittsburgh, 1983.
15. Standard Test Method for DETERMINING THE WASHABILITY CHARACTERISTICS OF COAL,

- Designation D4371-84, *1986 Annual Book of ASTM Standards*, Section 5, Volume 05.05, Gaseous Fuels; Coal and Coke, pp. 506-18.
16. Underwood, E. E., *Quantitative Stereology*, (Reading, MA: Addison Wesley Publishing Co., 1970), Chapter 5, pp. 109-17.
 17. Chi, M.-S., "Interfacial Properties and Coal Cleaning in the LICADO Process," Ph. D. Thesis, University of Pittsburgh, 1986.
 18. Fuller, E. L. Jr. and Smyrl, N. R., *Fuel*, 64, p. 1134, 1985.
 19. Wu, M. M., Robbins, G. A., Winschel, R. A. and Burke, F. P., *Energy & Fuel*, 2, 2, p. 150, 1988.
 20. Dutta, P. K., Talmi, Y., *Fuel*, 61, p. 1241, 1982.
 21. Vanderborgh, N. E., Jones, C.E.R., *Anal. Chem.*, 55, p. 527, 1983.
 22. Lyons, P. C., Hosterman, J. W., Lineman, D. N., Morelli, J. J., Hercules, D. M., *Proceedings of The Eleventh International Congress of Carboniferous Stratigraphy and Geology*, Beijing, China, 1987.
 23. Lyons, P. C., Hercules, D. M., Morelli, J. J., Sellers, G. A., Martin, D., Thompson-Rizer, C. L., Brown, F. W., Millay, M. A., *International Journal of Coal Geology*, 7, p. 6, 1987.
 24. Jensen, N. J., Sharkey, A. G., Viswanadham, S. K., Lineman, D. N. and Hercules, D. M., *Proceedings of the 36th ASMS Conference on Mass Spectrometry and Applied Topics*, June 5-6, p. 318, San Francisco, CA, 1988.
 25. Lyons, P. C., Hercules, D. M., Morelli, J. J., Sellers, G. A., Martin, D., Thompson-Rizer, C.L., Brown, F.W., Millay, M.A., *International Journal of Coal Geology*, 7, p. 6, 1987.
 26. Lyons, P. C., Hosterman, J. W., Lineman, D. N., Morelli, J. J., Hercules, D. M., *Proceedings of The Eleventh International Congress of Carboniferous Stratigraphy and Geology-Beijing, China*, 1987.
 27. Montano, P. A., *Coal Structure*, ACS, Washington, DC, 192, Ch. 22.
 28. Montano, P. A., *Mossbauer Spectroscopy and Its Chemical Applications*, ACS, Washington, DC, 194, 1981.
 29. Montano, P. A. and Bommanavar, A. S., *J. Mol. Catal.*, 20, 393-403, 1983.
 30. Montano, P. A. and Bommanavar, A. S., *Fuel*, 61, 1288-1290, 1982.
 31. Montano, P. A. and Bommanavar, A. S., *Fuel*, 61, 523-528, 1982.
 32. Williamson, D. L., Guettinger, T.W., and Dickerhoof, D.W., *Mossbauer Spectroscopy and Its Chemical Applications*, ACS, Washington, DC, 194, 1981.
 33. Cashion, J. D., Maguire, B., and Kiss, L. T., *Mossbauer Spectroscopy and Its Chemical Applications*, ACS, Washington, DC, 194, 1981.
 34. Karl, R. E. and Zuckerman, J. J., *Mossbauer Spectroscopy and Its Chemical Applications*, ACS, Washington, DC, 194, 1981.
 35. Proctor, A. and Hercules, D. M., *Applied Spectrosc.*, 38, 4, pp. 505-517, 1984.

36. Instruction Manual, Zeta-Meter Model ZM-80, Zeta Meter Incorporated, New York, NY.
37. Standard Test Method for PLASTIC PROPERTIES OF COAL BY THE CONSTANT-TORQUE GIESELER PLASTOMETER, Designation D2639-74, *198 Annual Book of ASTM Standards*, Section 5, Volume 05.05, Gaseous Fuels; Coal and Coke, pp. 362-68.
38. Marsh, H., *Fuel*, 44, pp. 253-268, 1965.
39. Marsh, H., and T. Siemieniewska, *Fuel*, 44, pp. 355-367, 1965.
40. Walker, P. L. and Patel, R. L., *Fuel*, 49, pp. 91-94, 1970.
41. Fabec, J. L. and Ruschak, M. L., *Atomic Spectroscopy*, 6, 4, July-August, pp. 81-87, 1985.
42. Fabec, J. L. and Ruschak, M. L., *Analytical Chemistry*, 55, 14, pp. 2241-2246, 1983.
43. Fabec, J. L. and Ruschak, M. L., *Analytical Chemistry*, 57, 9, pp. 1853-1863, 1985.
44. *International Critical Tables*, E. W. Washburn Ed., New York: McGraw Hill Book Co., Vol. III, pp. 215-227 (1928).
45. *Ibid*, Vol. III, pp. 27-30.
46. *Ibid*, Vol. VII, pp. 211-224.
47. Dreisbach, R. R., *Physical Properties of Chemical Compounds*, published by the American Chemical Society, No. 22 the Advanced in Chemistry Science Series (1959).
48. Dreisbach, R. R., *Physical Properties of Chemical Compounds*, published by the American Chemical Society, No. 15 the Advanced in Chemistry Science Series (1955).
49. Good, R. J. and Ebling, E., "Generalization of the Theory for Estimation of Interfacial Energies," *Ind. Eng. Chem.*, 62(3), pp. 54-78 (1970).
50. Hintze, J. L., *Number Cruncher Statistical System (NCSS)*, version 5.3 - Power Pack, Reference Manual, 865 East 400 North, Kaysville, Utah 84037, 1988.
51. V. P. Mehrotra, K. V. S. Sastry and B. W. Morey, "Review of Oil Agglomeration Techniques for Processing of Fine Coals," *International Journal of Mineral Processing*, 11, pp. 175-201 (1983).
52. Enustun, B. V., Liu, D. C., Lin, K. L., and Markuszewski, R., *Use of a Surfactants as a Coal Grinding Additive*, *Coal Preparation*, Vol. 4, pp 193-207, 1987.
53. Venkatadri, R. A., *Effect of Surface Active Agents on Filtration and Post-Filtration Characteristics of Fine Coal*, Ph.D. Dissertation, University of Pittsburgh, 1985.
54. Gala, H. B., *Use of Surfactants in Fine Coal Dewatering*, Ph. D. Dissertation Thesis, Department of Chemical Engineering, University of Pittsburgh, 1982.
55. Gala, H. B., "Surface Science of Coal Preparation", prepared for the U. S. DOE - Contract No. DE-AC22-84PC72571, May, 1987.
56. Horowitz et al., *Process for Treating Coal and Products Produced Thereby*, U. S. Patent No. 4,033,852, July 5, 1977.

57. Burgess et al., Process of Beneficiating Coal and Products, U. S. Patent No. 4,304,573, December 8, 1981.
58. Clark, D. T. and Wilson, R., Fuel, 62, pp.1034-39 (1983).
59. Perry, D. L. and Grint, A., Fuel, 62, pp. 1024-33 (1983).
60. Frost, D. C., Leeder, W. R., Tapping, R. L., Wallbank, B., Fuel, 56, pp. 277-80 (1977).
61. Wagner, C. D., Davis, L. E., Zeller, M. V., Taylor, J. A., Raymond, R. M., Gale, L. A., Surf. Interface Anal., 3, p. 211 (1981).
62. Gaudin, A. M. and Charles, W. D., "Adsorption of Calcium and Sodium on Pyrite," Trans. AIME, February, pp. 195-200 (1953).
63. C. K. Bayne and I. B. Rubin, Practical Experimental Designs and Optimization Methods for Chemists, VCH Publishers, Inc., Deerfield Beach, FL (1986).
64. Chemical Engineers' Handbook, Fifth Edition, R. H. Perry and C. H. Chilton, Editors, McGraw Hill Book Co., p. 9-4 (1973).
65. "Standard Classification of Coals by Rank," Annual Book of ASTM Standards, Volume 05.05, Gaseous Fuels; Coal and Coke, pp. 247-251 (1986).
66. L. F. Metzroth and K. S. Knuston, "Phase I and Phase II Acid Rain Compliance Approaches," Proceedings of the 8th Annual International Pittsburgh Coal Conference, pp. 363-389, Pittsburgh, PA, October 14-18, 1991.
67. Clean Air Act Amendments of 1990, Section 112 (b).
68. "Standard Test Method for TRACE ELEMENTS IN COAL AND COKE ASH BY ATOMIC ABSORPTION," Annual Book of ASTM Standards, Volume 05.05, Gaseous Fuels; Coal and Coke, pp. 472-475 (1986).
69. Berner, G. G. and Suiderweg, F. J., "Growth Regimes in the Spherical Agglomeration Process," Proceedings of the International Symposium on Fine Particles Processing, Vol. 2, pp. 1524-46 (1980).
70. Klug, H. P. and Alexander, L. E., X-Ray Diffraction Procedures, Wiley, 1974.

APPENDIX A: TABLES

Table 1.0-1 Summary of Coal Samples Received

Code	Seam	Mine	County, State	Condition	No. Drums
UI	Upper Freeport	NCFC	Indiana, PA	Inerted	5
UI	Upper Freeport	NCFC	Indiana, PA	Weathered	41
P8	Pittsburgh #8	R&F	Belmont, OH	Inerted	5
P8	Pittsburgh #8	R&F	Belmont, OH	Weathered	40
I6	Illinois #6	Peabody	Randolph, IL	Inerted	6
I6	Illinois #6	Peabody	Randolph, IL	Weathered	36
UG	Upper Freeport	Buffalo	Grant, WV	Inerted	5
WC	Wyodak	Cordero	Campbell, WY	Inerted	5
K9	Kentucky #9	P&M	Hopkins, KY	Inerted	5
Drums with missing labels					1
Total					149

**Table 3.1-1 Standard ASTM Characterization
on Three Base Coal Samples**

Coal	Weight Percent (Dry Basis)		
	Upper Freeport	Pittsburgh #8	Illinois #6
H ₂ O, As Det'd	1.74	3.50	10.1
Ash	12.4	11.4	17.2
Volatile Matter	27.0	38.0	38.8
Fixed Carbon*	60.6	50.6	44.0
Carbon	76.7	71.9	70.2
Hydrogen	4.69	4.88	4.85
Nitrogen	1.67	1.61	1.71
Sulfur	2.36	4.27	4.77
Oxygen*	2.18	5.94	1.27
<u>Sulfur Forms</u>			
Sulfate	0.02	0.12	0.11
Pyrite	1.98	3.15	2.83
Organic*	0.36	1.00	1.83
<u>Calorific Value</u> (Btu/lb)	13,608	13,032	11,709

* Calculated by difference

Table 3.2.1.1-1 Petrographic Maceral Composition of Upper Freeport Coal

REACTIVES		
VITRINOID TYPE	10	10.5
	11	61.2
	12	8.1
	13	0.8
TOTAL, %		80.6
EXINITE		1.8
RESINITE		0.2
SEMIFUSINITE		0.9
TOTAL, %		83.5
INERTS		
SEMIFUSINITE		1.8
MICRINITE		4.3
FUSINITE		2.8
MINERAL MATTER		7.7
TOTAL, %		16.6
MEAN MAX. REFLECTANCE %, IN COAL		1.15
COMPOSITION-BALANCE INDEX		0.55
RANK INDEX		4.42
CALCULATED STABILITY FACTOR		58

Table 3.2.1.1-2 Vitrinite Reflectance Distribution for Upper Freeport Coal

MEAN MAX. REFLECTANCE	No. OF READINGS	PERCENT
1.02	1	1.0
1.03	1	1.0
1.04	1	1.0
1.05	1	1.0
1.06	1	1.0
1.07	1	1.0
1.08	4	4.0
1.09	3	3.0
1.10	7	7.0
1.11	4	4.0
1.12	8	8.0
1.13	13	13.0
1.14	12	12.0
1.15	11	11.0
1.16	8	8.0
1.17	8	8.0
1.18	4	4.0
1.19	1	1.0
1.20	2	2.0
1.21	2	2.0
1.22	4	4.0
1.24	2	2.0
1.30	1	1.0

Average Mean Max. Reflectance = 1.149%

Table 3.2.1.1-3 Non-maceral Microstructures in Upper Freeport Coal

CATEGORY	VOLUME, PERCENT
NORMAL COAL	46.9
FINE COAL < 5 microns	7.4
PSEUDOVITRINITE	14.3 ?
COARSE VITRINITE < 30 microns	22.0
MINERAL MATTER (OTHER THAN FINE CLAY)	
BONE COAL	3.8
CARBONACEOUS SHALE	1.2
SHALE	0.4
QUARTZ	1.0
PYRITE	1.4
OXIDIZED COAL	
SLIGHT	0.8
MODERATE	0.4
BADLY	-
BRECCIATED COAL	0.4

Table 3.2.1.2-1 Petrographic Maceral Composition of Pittsburgh #8 Coal

REACTIVES		
VITRINOID TYPE	6	26.3
	7	44.8
TOTAL, %		71.1
EXINITE		5.0
RESINITE		2.3
SEMIFUSINITE		1.5
TOTAL, %		79.9
INERTS		
SEMIFUSINITE		2.9
MICRINITE		6.3
FUSINITE		3.3
MINERAL MATTER		7.6
TOTAL, %		20.1
MEAN MAX. REFLECTANCE %, IN COAL		0.71
COMPOSITION-BALANCE INDEX		0.80
RANK INDEX		2.80
CALCULATED STABILITY FACTOR		29

Table 3.2.1.2-2 Vitrinite Reflectance Distribution for Pittsburgh #8 Coal

MEAN MAX. REFLECTANCE	No. OF READINGS	PERCENT
0.63	2	2.0
0.64	2	2.0
0.65	2	2.0
0.66	8	8.0
0.67	5	5.0
0.68	10	10.0
0.69	8	8.0
0.70	15	15.0
0.71	19	19.0
0.72	12	12.0
0.73	8	8.0
0.74	3	3.0
0.75	2	2.0
0.76	2	2.0
0.77	2	2.0

AVERAGE MEAN MAX. REFLECTANCE = 0.713%

Table 3.2.1.2-3 Non-maceral Microstructures in Pittsburgh #8 Coal

CATEGORY	VOLUME, PERCENT
NORMAL COAL	51.5
FINE COAL < 5 microns	3.6
PSEUDOVITRINITE	16.0 TELINITIC
COARSE VITRINITE < 30 microns	19.9
MINERAL MATTER (OTHER THAN FINE CLAY)	
BONE COAL	1.8
CARBONACEOUS SHALE	0.6
SHALE	1.8
QUARTZ	0.2
CALCITE	0.4
RUST	2.4
PYRITE	0.2
OXIDIZED COAL	
SLIGHT	0.2
MODERATE	0.4
BADLY	-
BRECCIATED COAL	1.0

Table 3.2.1.3-1 Petrographic Maceral Composition of Illinois #6 Coal

REACTIVES		
VITRINOID TYPE	4	41.3
	5	22.3
	6	4.1
TOTAL, %		67.7
EXINITE		4.5
RESINITE		5.0
SEMIFUSINITE		1.3
TOTAL, %		78.5
INERTS		
SEMIFUSINITE		2.6
MICRINITE		3.2
FUSINITE		4.2
MINERAL MATTER		11.5
TOTAL, %		21.5
MEAN MAX. REFLECTANCE %, IN COAL		0.49
COMPOSITION-BALANCE INDEX		1.05
RANK INDEX		2.46
CALCULATED STABILITY FACTOR		15

Table 3.2.1.3-2 Vitrinite Reflectance Distribution for Illinois #6 Coal

MEAN MAX. REFLECTANCE	No. OF READINGS	PERCENT
0.38	1	1.0
0.39	-	-
0.40	2	2.0
0.41	5	5.0
0.42	4	4.0
0.43	6	6.0
0.44	3	3.0
0.45	12	12.0
0.46	7	7.0
0.47	10	10.0
0.48	6	6.0
0.49	6	6.0
0.50	3	3.0
0.51	3	3.0
0.52	9	9.0
0.53	8	8.0
0.54	1	1.0
0.55	2	2.0
0.56	3	3.0
0.57	4	4.0
0.58	-	-
0.59	1	1.0
0.60	2	2.0
-	-	-
0.68	1	1.0
-	-	-
0.75	1	1.0

AVERAGE MEAN MAX. REFLECTANCE = 0.487%

Table 3.2.1.3-3 Non-Maceral Microstructures in Illinois #6 Coal

CATEGORY	VOLUME, PERCENT
NORMAL COAL	40.0
FINE COAL < 5 microns	2.8
PSEUDOVITRINITE	18.5 Textured only
COARSE VITRINITE < 30 microns	24.5
MINERAL MATTER (OTHER THAN FINE CLAY)	
BONE COAL	4.2
CARBONACEOUS SHALE	2.4
SHALE	3.0
QUARTZ	0.4
CALCITE	1.6
PYRITE	1.6
OXIDIZED COAL	
SLIGHT	0.6
MODERATE	-
BADLY	-
BRECCIATED COAL	0.4

**Table 3.3.1-1 Particle Size Distribution of 200 mesh x 0 Samples of the
Three Base Coals Measured by Optical Microscopy (32x)**

Number %	Upper Freeport		Pittsburgh #8		Illinois #6	
	Run #1	Run #2	Run #1	Run #2	Run #1	Run #2
1.0 - 2.0	42.2	43.35	31.1	35.5	39.2	43.2
2.0 - 3.1	27.9	28.9	25.6	26.8	23.8	25.3
3.1 - 5.0	18.3	17.7	22.7	20.9	19.3	15.9
5.0 - 6.3	5.3	4.7	8.5	7.3	6.8	5.5
6.3 - 7.9	2.6	2.3	4.7	3.7	4.0	3.4
7.9 - 10.0	1.5	1.2	3.1	2.3	2.6	2.3
10.0 - 12.5	0.94	0.77	1.8	1.6	1.7	1.5
12.5 - 15.8	0.57	0.39	0.92	0.87	0.9	1.0
15.8 - 19.9	0.27	0.24	0.79	0.55	0.75	0.87
19.9 - 25.0	0.24	0.10	0.37	0.19	0.58	0.49
25.0 - 31.6	0.08	0.13	0.22	0.11	0.28	0.31
31.6 - 39.7	0.12	0.03	0.09	0.17	0.09	0.10
39.7 - 50.0	0.03	0.02	0.08	0.04	0.05	0.09
50.0 - 67.9			0.08	-	0.00	0.05
67.9 - 79.2						0.02
Length Diameter, micron	3.1	2.9	3.9	3.5	3.6	3.5

Table 3.3.1-2 SEM Particle Size Distributions of the Three Base Coals

Size, micron	Number Percent		
	Upper Freeport	Pittsburgh #8	Illinois #6
1	4.16	3.62	3.20
2	5.31	11.27	14.36
3	36.67	34.49	42.54
4	24.27	23.92	19.59
5	18.33	29.89	17.10
6	11.25	6.82	3.20

Table 3.3.1-3 Compound Particle Size Distributions of the Three Base Coals

Size Range, micron	Number Percent		
	Upper Freeport	Pittsburgh #8	Illinois #6
0.2 - 0.5	3.9	3.3	3.0
0.5 - 1.0	5.0	10.2	13.7
1.0 - 2.0	34.3	31.3	40.4
2.0 - 3.1	23.7	21.7	21.3
3.1 - 5.0	16.9	18.0	13.4
5.0 - 6.3	6.0	6.5	3.8
6.3 - 7.9	3.6	3.5	1.9
7.9 - 10.0	2.4	2.2	1.1
10.0 - 12.5	1.5	1.4	0.65
12.5 - 15.8	0.92	0.74	0.36
15.8 - 19.9	0.78	0.55	0.20
19.9 - 25.0	0.52	0.23	0.13
25.0 - 31.6	0.29	0.13	0.08
31.6 - 39.7	0.10	0.11	0.06
39.7 - 50.0	0.07	0.05	0.02
50.0 - 67.9	0.03	0.03	-
67.9 - 79.2	0.01	-	-

**Table 3.3.1-4 Particle Size Distribution of 200 mesh x 0 Samples of the Three Base Coals
on Weight Percent Basis Measured by Optical Microscopy (10x)**

Weight % Size Range, micron	Upper Freeport		Pittsburgh #8		Illinois #6	
	Run #1	Run #2	Run #1	Run #2	Run #1	Run #2
2.0 - 4.0	0.884	1.321	0.728	0.607	0.767	1.051
4.0 - 6.3	3.140	4.048	2.193	2.399	2.761	3.140
6.3 - 10.0	7.654	8.829	5.346	6.549	6.922	7.033
10.0 - 12.6	4.839	5.535	3.252	3.951	4.415	4.637
12.6 - 15.8	8.184	9.151	5.570	6.859	8.029	7.423
15.8 - 19.8	8.140	8.776	5.903	6.823	8.701	7.984
19.9 - 25.1	10.999	12.734	7.813	10.217	11.532	11.310
25.1 - 31.6	12.769	14.695	7.773	10.883	14.845	11.702
31.6 - 39.8	11.769	11.086	8.256	13.437	12.787	12.018
39.8 - 50.1	8.222	9.112	9.888	10.597	10.152	10.662
50.1 - 63.1	12.506	9.529	14.477	9.256	13.319	15.964
63.1 - 79.4	1.559	5.184	10.501	7.913	3.466	7.077
79.4 - 100.0	9.330	0.000	7.858	5.263	2.305	0.000
100.0 - 128.0	-	-	10.445	5.247	-	-

**Table 3.4-1 Washability Analysis for Upper Freeport
Coal Crushed to 200 mesh x 0**

Gravity Fraction	Yield, %	Moisture, %	Ash, %	Sulfur, %	Calorific Value, Btu/lb
1.30 Float	44.7	0.61	2.16	0.71	15,222
1.35 Float	67.9	0.55	3.42	0.90	15,160
1.40 Float	75.2	0.57	3.96	0.87	15,021
1.60 Float	87.7	0.50	6.42	0.99	14,476
1.80 Float	90.6	0.81	7.37	0.96	14,375
1.80 Sink	9.4	0.50	63.00	14.90	4,152
Calc. Feed	100.0	0.78	12.60	2.27	13,414

**Table 3.4-2 Washability Analysis for Pittsburgh #8
Coal Crushed to 200 mesh x 0**

Gravity Fraction	Yield, %	Moisture, %	Ash, %	Sulfur, %	Calorific Value, Btu/lb
1.30 Float	72.0	1.26	2.26	1.46	14,652
1.35 Float	82.2	1.40	2.86	1.55	14,517
1.40 Float	84.6	0.93	3.33	1.53	14,388
1.60 Float	89.8	1.60	3.98	1.62	14,351
1.80 Float	93.8	1.58	4.36	1.76	14,248
1.80 Sink	6.2	0.88	53.60	21.70	5,290
Calc. Feed	100.0	1.54	7.41	3.00	13,693

**Table 3.4-3 Washability Analysis for Illinois #6
Coal Crushed to 200 mesh x 0**

Gravity Fraction	Yield, %	Moisture, %	Ash, %	Sulfur, %	Calorific Value, Btu/lb
1.30 Float	28.4	1.57	2.32	2.73	13,961
1.35 Float	58.3	1.97	3.24	2.65	13,747
1.40 Float	68.5	1.39	3.86	2.80	13,659
1.60 Float	81.5	1.66	6.10	2.78	13,288
1.80 Float	86.7	1.90	7.03	2.74	12,898
1.80 Sink	13.3	0.52	63.90	22.20	3,674
Calc. Feed	100.0	1.72	14.59	5.33	11,671

**Table 3.4-4 Analysis of Washability Data Obtained from 200 mesh x 0
As-received Samples of Pittsburgh #8 Coal**

Sample	Composite Ash, %	Yield, %	Sulfur, %	Float Ash, %	Total Ash in Float, %
1	9.61	6.00	1.59	1.94	20.20
2	10.60	8.70	1.56	1.83	17.30
3	9.97	10.40	1.62	1.91	19.20
4	9.92	7.70	1.58	1.76	17.70
5	9.82	7.80	1.53	1.72	17.50
6	9.80	6.80	1.53	1.63	16.60
7	10.10	6.10	1.57	1.74	17.20
8	10.10	3.40	1.56	1.61	15.90
9	9.72	5.60	1.59	1.66	17.10
Mean	9.96	6.94	1.57	1.76	17.63
Std. Dev.	0.29	2.01	0.03	0.12	1.31
Samples	9	9	9	9	9
t (95 %)	2.31	2.31	2.31	2.31	2.31
Hi Mean	10.18	8.49	1.59	1.85	18.64
Lo Mean	9.74	5.40	1.55	1.67	16.63

**Table 3.4-5 Analysis of Washability Data Obtained from 200 mesh x 0
Moisture-Corrected Samples of Pittsburgh #8 Coal**

Sample	Composite Ash, %	Yield, %	Float Ash, %	Total Ash in Float, %
1	9.55	6.70	1.94	20.30
2	11.40	9.70	1.83	16.10
3	9.88	11.40	1.91	19.30
4	9.86	8.30	1.76	17.80
5	9.80	8.00	1.72	17.60
6	9.80	6.80	1.63	16.60
7	10.20	6.30	1.74	17.10
8	10.10	3.40	1.61	15.90
9	9.81	5.70	1.66	16.90
Mean	10.04	7.37	1.76	17.51
Std. Dev.	0.54	2.33	0.12	1.46
Samples	9	9	9	9
t (95 %)	2.31	2.31	2.31	2.31
Hi Mean	10.46	9.16	1.85	18.63
Lo Mean	9.63	5.58	1.67	16.39

Table 3.5-1 Pyrite Size Distribution for 28 mesh x 0 Upper Freeport Coal

Pyrite Size, microns	2-D Number Distribution, %	Accumulated 2-D Number Distribution, %	Accumulated 3-D Number Distribution, %	Accumulated 3-D Volume Distribution, %
Locked				
2	16.60	16.60	25.18	0.28
4	12.40	29.00	35.68	1.23
6	6.60	35.60	40.04	2.56
8	2.90	38.50	41.68	3.75
10	1.00	39.50	42.13	4.38
12	0.50	40.00	42.31	4.82
14	0.30	40.30	42.39	5.12
16	0.30	40.60	42.50	5.74
24	0.30	40.90		
26	0.30	41.20		
28	0.30	41.50	42.53	7.11
30	0.30	41.80	42.58	9.14
32	0.30	42.10	42.66	12.89
38	0.30	42.40	42.71	16.85
Semi-Locked				
2	11.30	11.30	18.08	0.20
4	5.60	16.90	23.09	0.65
6	1.80	18.70	24.03	0.94
8	1.30	20.00	24.46	1.25
10	1.60	21.60	25.21	2.31
12	0.50	22.10	25.27	2.46
14	0.80	22.90	25.53	3.47
16	0.50	23.40	25.67	4.29
18	0.30	23.70	25.72	4.70
20	0.30	24.00	25.77	5.31
22	0.30	24.30	25.84	6.43
28	0.30	24.60		
30	0.50	25.10	25.86	7.95
32	0.30	25.40	25.90	9.76
34	0.30	25.70	25.95	12.36
36	0.30	26.00	26.02	17.10
42	0.30	26.30	26.05	20.47
54	0.30	26.60		
58	0.30	26.90	26.09	30.73
70	0.30	27.20	26.11	38.20
80	0.30	27.50	26.14	57.74
Free				
2	13.20	13.20	20.85	0.23
4	7.40	20.60	27.41	0.82
6	2.60	23.20	28.78	1.24
8	2.40	25.60	30.14	2.22
10	0.80	26.40	30.48	2.70
12	0.30	26.70		
14	0.80	27.50	30.78	3.86
16	0.30	27.80	30.88	4.42
22	0.30	28.10		
24	0.50	28.60	30.95	6.02
26	0.30	28.90	31.04	8.21
34	0.30	29.20	31.05	8.78
38	0.30	29.50	31.10	12.73
50	0.30	29.80	31.12	15.62
58	0.30	30.10	31.16	25.43

Table 3.5-2 Pyrite Size Distribution for 28 mesh x 0 Pittsburgh #8 Coal

Pyrite Size, microns	2-D Number Distribution, %	Accumulated 2-D Number Distribution, %	Accumulated 3-D Number Distribution, %	Accumulated 3-D Volume Distribution, %
Locked				
2	21.70	21.70	33.12	0.37
4	8.60	30.30	40.20	1.01
6	3.20	33.50	41.78	1.49
8	2.80	36.30	43.14	2.47
10	1.40	37.70	43.69	3.25
12	0.80	38.50	43.94	3.85
14	0.60	39.10	44.11	4.51
16	0.40	39.50	44.19	4.98
18	0.40	39.90	44.30	5.85
20	0.20	40.10	44.32	6.11
22	0.20	40.30	44.34	6.38
24	0.20	40.50	44.34	6.40
26	0.40	40.90	44.44	8.76
28	0.20	41.10	44.48	9.86
30	0.20	41.30	44.54	11.96
40	0.20	41.50	44.56	13.85
75	0.20	41.70		
80	0.20	41.90	44.57	24.44
100	0.20	42.10	44.58	39.86
Semi-Locked				
2	10.60	10.60	15.90	0.18
4	4.80	15.40	19.40	0.50
6	3.60	19.00	21.61	1.17
8	1.40	20.40	22.17	1.58
10	1.20	21.60	22.68	2.30
12	0.60	22.20	22.91	2.85
14	0.20	22.40	22.93	2.92
16	0.20	22.60		
18	0.40	23.00	23.00	3.49
20	0.40	23.40	23.10	4.65
22	0.20	23.60	23.13	5.07
24	0.20	23.80	23.16	5.68
26	0.20	24.00	23.21	6.81
32	0.20	24.20		
34	0.20	24.40	23.21	7.21
36	0.20	24.60	23.25	9.54
40	0.20	24.80	23.25	9.90
42	0.20	25.00	23.29	14.25
52	0.20	25.20		
56	0.20	25.40		
58	0.20	25.60	23.30	16.12
60	0.20	25.80	23.33	23.81
62	0.20	26.00	23.37	37.76
120	0.20	26.20	23.38	53.32
Free				
2	13.70	13.70	19.59	0.22
4	10.20	23.90	28.10	0.99
6	4.00	27.90	30.58	1.75
8	1.80	29.70	31.59	2.48
10	0.40	30.10	31.75	2.70
12	0.20	30.30	31.79	2.80
14	0.20	30.50	31.83	2.94
16	0.20	30.70	31.86	3.13
18	0.20	30.90	31.89	3.40
20	0.20	31.10	31.92	3.78
22	0.20	31.30	31.96	4.36
24	0.20	31.50	32.01	5.43
28	0.20	31.70	32.06	6.84

Table 3.5-3 Pyrite Size Distribution for 28 mesh x 0 Illinois #6 Coal

Pyrite Size, microns	2-D Number Distribution, %	Accumulated 2-D Number Distribution, %	Accumulated 3-D Number Distribution, %	Accumulated 3-D Volume Distribution, %
Locked				
2	11.50	11.50	17.29	0.06
4	11.80	23.30	27.63	0.33
6	6.40	29.70	31.61	0.68
8	4.40	34.10	34.15	1.21
10	2.00	36.10	35.24	1.65
12	0.40	36.50	35.31	1.70
14	0.60	37.10	35.55	1.97
16	0.20	37.30	35.58	2.02
18	0.20	37.50	35.60	2.08
20	0.20	37.70	35.62	2.15
24	0.40	38.10		
26	0.40	38.50	35.70	2.73
28	0.20	38.70		
30	0.40	39.10	35.76	3.37
32	0.40	39.50	35.86	4.65
34	0.20	39.70	35.89	5.21
36	0.20	39.90	35.94	6.26
46	0.20	40.10	35.94	6.45
50	0.20	40.30	35.98	8.31
90	0.20	40.50	35.99	10.89
170	0.20	40.70	36.00	21.20
Semi-Locked				
2	8.30	8.30	12.91	0.04
4	7.70	16.00	20.30	0.23
6	2.20	18.20	21.53	0.34
8	2.00	20.20	22.73	0.59
10	0.60	20.80	22.98	0.69
12	0.20	21.00		
14	0.60	21.60	23.07	0.82
16	0.60	22.20	23.26	1.14
18	0.40	22.60	23.39	1.45
20	0.20	22.80	23.44	1.61
24	0.20	23.00		
26	0.20	23.20	23.46	1.74
28	0.20	23.40	23.49	2.00
30	0.20	23.60	23.52	2.37
32	0.20	23.80	23.57	3.03
38	0.20	24.00		
40	0.20	24.20	23.61	4.18
50	0.20	24.40		
54	0.20	24.60	23.62	5.26
60	0.20	24.80	23.63	6.02
64	0.20	25.00	23.65	8.62
70	0.20	25.20	23.68	12.28
Free				
2	17.00	17.00	28.89	0.09
4	7.70	24.70	35.97	0.28
6	3.30	28.00	38.13	0.47
8	1.60	29.60	38.84	0.62
10	1.30	30.90	39.35	0.83
12	1.10	32.00	39.80	1.15
14	0.70	32.70	40.11	1.50
16	0.20	32.90	40.18	1.62
20	0.20	33.10	40.22	1.76
26	0.20	33.30	40.26	2.02
40	0.20	33.50	40.27	2.37
50	0.20	33.70	40.29	3.58
120	0.20	33.90	40.30	8.21
430	0.20	34.10	40.30	66.49

Table 3.5-4 Pyrite Size Distribution for 200 mesh x 0 Upper Freeport Coal

Pyrite Size, microns	2-D Number Distribution, %	Accumulated 2-D Number Distribution, %	Accumulated 3-D Number Distribution, %	Accumulated 3-D Volume Distribution, %
Locked				
2	9.00	9.00	14.41	0.68
4	1.60	10.60	15.65	1.15
6	1.00	11.60	16.28	1.96
8	0.40	12.00	16.49	2.59
10	0.20	12.20	16.60	3.24
Semi-Locked				
2	15.90	15.90	23.48	1.10
4	9.60	25.50	31.20	4.01
6	4.80	30.30	34.05	7.63
8	2.60	32.90	35.37	11.61
10	1.20	34.10	35.89	14.65
12	0.60	34.70	36.12	16.99
14	0.20	34.90	36.13	17.08
16	0.40	35.30	36.25	20.08
18	0.20	35.50	36.29	21.55
20	0.20	35.70	36.35	24.36
24	0.20	35.90	36.40	28.08
40	0.20	36.10	36.42	35.86
Free				
2	18.90	18.90	26.99	1.27
4	14.60	33.50	38.79	5.71
6	7.00	40.50	42.86	10.88
8	3.60	44.10	44.32	15.27
10	3.20	47.30	45.76	23.72
12	1.20	48.50	46.11	27.29
14	1.00	49.50	46.39	31.83
16	0.80	50.30	46.62	37.31
18	0.60	50.90	46.81	43.99
20	0.20	51.10	46.85	45.70
22	0.20	51.30	46.89	48.37
24	0.20	51.50	46.96	53.69
38	0.20	51.70	46.98	60.93

Table 3.5-5 Pyrite Size Distribution for 200 mesh x 0 Pittsburgh #8 Coal

Pyrite Size, microns	2-D Number Distribution, %	Accumulated 2-D Number Distribution, %	Accumulated 3-D Number Distribution, %	Accumulated 3-D Volume Distribution, %
Locked				
2	5.80	5.80	8.92	0.36
4	2.20	8.00	10.57	0.90
6	1.60	9.60	11.63	2.06
8	0.40	10.00	11.78	2.44
10	0.40	10.40	11.95	3.30
12	0.20	10.60	12.01	3.83
14	0.20	10.80	12.09	5.00
22	0.20	11.00	12.13	7.11
Semi-Locked				
2	21.20	21.20	31.92	1.30
4	11.00	32.20	41.11	4.30
6	4.10	36.30	43.28	6.69
8	3.20	39.50	44.90	10.91
10	1.60	41.10	45.66	14.80
12	0.40	41.50	45.75	15.63
14	0.40	41.90	45.85	16.98
16	0.40	42.30	45.97	19.53
18	0.20	42.50	46.01	20.66
20	0.20	42.70	46.05	22.44
22	0.20	42.90	46.12	25.98
30	0.20	43.10	46.15	30.44
Free				
2	16.50	16.50	23.23	0.95
4	14.20	30.70	35.07	4.81
6	5.40	36.10	37.97	8.00
8	4.10	40.20	40.08	13.50
10	1.80	42.00	40.88	17.56
12	0.70	42.70	41.08	19.35
14	0.50	43.20	41.18	20.69
16	0.50	43.70	41.27	22.62
18	0.50	44.20	41.37	25.49
20	0.50	44.70	41.49	30.24
22	0.40	45.10	41.60	35.98
24	0.20	45.30	41.64	38.80
26	0.20	45.50	41.70	44.32
40	0.20	45.70	41.71	48.41
50	0.20	45.90	41.73	62.45

Table 3.5-6 Pyrite Size Distribution for 200 mesh x 0 Illinois #6 Coal

Pyrite Size, microns	2-D Number Distribution, %	Accumulated 2-D Number Distribution, %	Accumulated 3-D Number Distribution, %	Accumulated 3-D Volume Distribution, %
Locked				
2	5.30	5.30	7.42	0.29
4	3.40	8.70	9.85	1.06
6	2.50	11.20	11.36	2.68
8	1.10	12.30	11.97	4.21
10	0.20	12.50	12.03	4.53
12	0.20	12.70	12.12	5.27
20	0.20	12.90	12.15	6.62
40	0.20	13.10	12.16	9.36
50	0.20	13.30	12.18	22.44
Semi-Locked				
2	21.80	21.80	31.37	1.24
4	12.00	33.80	41.11	4.32
6	4.00	37.80	43.03	6.37
8	3.60	41.40	44.85	10.96
10	1.30	42.70	45.32	13.29
12	0.80	43.50	45.52	15.03
14	0.80	44.30	45.77	18.41
16	0.40	44.70	45.83	19.61
18	0.60	45.30	46.03	25.29
20	0.20	45.50	46.09	27.78
28	0.20	45.70	46.10	29.40
34	0.20	45.90	46.12	34.07
42	0.20	46.10	46.15	43.50
Free				
2	20.00	20.00	29.02	1.15
4	9.90	29.90	36.81	3.61
6	4.40	34.30	39.28	6.25
8	2.30	36.60	40.24	8.68
10	1.70	38.30	40.93	12.07
12	0.90	39.20	41.23	14.65
14	0.60	39.80	41.42	17.26
16	0.40	40.20	41.57	20.23
20	0.20	40.40	41.62	22.09
38	0.20	40.60		
40	0.20	40.80	41.65	34.06

Table 3.6.2-1 Fourier Analysis of Shape for Upper Freeport Coal

Average grain size for the 25 micron fraction

Harmonic Number	Mean Amplitude
1	0.00230
2	0.22678
3	0.11671
4	0.06982
5	0.05245
6	0.04587
7	0.02648
8	0.02485
9	0.02083
10	0.01862
11	0.01731
12	0.01506
13	0.01222
14	0.01145
15	0.00907
16	0.00957
17	0.00880
18	0.00666
19	0.00742
20	0.00584
21	0.00736
22	0.00660
23	0.00667
24	0.00546

Note: The amplitudes are normalized for size by dividing by radius of equivalent sphere.

Table 3.7-1 Oxidation Indices for the Upper Freeport Coal Test Sample

Spectrum No.	Loading No.		
	1	2	3
A	0.74	0.76	0.71
B	0.67	0.75	0.66
C	0.65	0.77	0.70

Table 3.8.1-1 Duplicate Runs of LAMMA Analysis of Upper Freeport Coal Test Sample

Element	Percent Total Ionization		Standard Deviation
	Trial 1	Trial 2	
Li	0.5	0.4	0.1
Na	3.5	3.1	0.3
Mg	1.0	1.1	0.1
Al	44.6	44.5	0.1
Si	3.4	3.7	0.2
S	2.0	0.1	1.3
K	28.6	30.8	1.6
Ca	7.8	4.7	2.2
Ti	8.1	8.3	0.1
Fe	3.4	3.2	0.1

Table 3.9-1 Mössbauer Hyperfine Parameters and Percent Spectral Areas for 28 mesh x 0 Samples of the Three Base Coals

Coal	Pyrite (FeS_2)			Sulfate/Clays (Fe^{+2})		
	QS ^a	IS ^b	A% ^c	QS ^a	IS ^b	A% ^c
Upper Freeport	0.62	0.58	90.4	2.79 3.09	1.37 1.53	5.3 4.3
Pittsburgh #8	0.61	0.57	94.9	2.92 2.92	1.46 1.65	3.6 1.5
Illinois #6	0.61	0.57	98.5	2.65	1.47	1.5
FeS_2^{d}	0.61	0.57				
FeSO_4^{d}				2.90	1.28	
$\text{FeSO}_4 \cdot 4\text{H}_2\text{O}^{\text{d}}$				3.17	1.32	

- (a) QS: Quadruple Splitting: ± 0.02 mm/s
(b) IS: Isomer Shift: ± 0.02 mm/s
(c) A%: Percent of total spectral area
(d) Values from reference (38). For a listing of values for clay materials see reference (37).

Table 3.10-1 Data Analysis of Contact Angle Measurements

Sample	Time, min	0	90	180	270	Average	Standard Deviation
P8/S4	1	114	111	111	109	111.2	1.7
	5	114	109	106	101	107.5	4.7
	10	106	108	112	104	107.5	2.9
P8/S5	1	104	104	107	108	105.7	1.7
	5	105	105	107	104	105.2	1.0
	10	105	107	106	107	106.2	0.8
UI/S3	1	118	117	115	122	118.0	2.5
	5	118	119	110	118	116.2	3.6
	10	118	117	122	117	118.5	2.0
UI/S4	1	122	116	123	119	120.0	2.7
	5	119	115	119	121	118.5	2.1
	10	121	120	116	119	119.0	1.8

Statistics of the Data

Sample	Group Average	Group Standard Deviation	Group Maximum	Group Minimum
P8/S4	108.7	3.810	114	101
P8/S5	105.7	1.361	108	104
UI/S3	117.5	2.984	122	110
UI/S4	119.1	2.374	123	115

**Table 3.11-1 Zeta Potentials and pH Values for the Three
Base Coals in Fine Coal Suspensions**

Coal	Upper Freeport	Pittsburgh #8	Illinois #6
pH Value	5.5 ± 0.0	5.7 ± 0.1	6.1 ± 0.1
Zeta Potential, mV	-26.0 ± 1.5	-22.0 ± 0.5	-15.0 ± 0.0

**Table 3.11-2 Analysis of Variance on Zeta Potential Measurements
(Water + Upper Freeport Coal @ pH 5.7 @ 27 °C)**

SAMPLE NUMBER	1	2	3
MEAN (X-BAR)	30.74	24.82	29.44
STD DEVIATION (S)	1.057	1.602	1.470
MAXIMUM	32.2	27.6	31.3
MINIMUM	29.4	23.9	27.6
RANGE	2.8	3.7	3.7

Analysis of Variance

BETWEEN SAMPLE	8.3
WITHIN SAMPLE	1.949
POOLED STD DEVIATION	1.396
GRAND MEAN + 3SE	30.206
GRAND MEAN + 2SE	29.582
GRAND MEAN	28.333
GRAND MEAN - 2SE	27.084
GRAND MEAN - 3SE	26.460

SE = STANDARD ERROR

Table 3.11-3 Analysis of Operator Particle Tracking

* DESTAT1 * DESCRIPTIVE STATISTICS 1 No. of data rows = 15

* TITLE * OPERATOR PARTICLE TRACKING STUDY

TOTAL (T)	515.3
MEAN (X bar)	34.35333
SAMPLE SIZE (n)	15
STANDARD DEVIATION (s)	3.218887
MAXIMUM (max)	40.2
MINIMUM (min)	29.6
RANGE (r)	10.6
STD ERROR OF MEAN (SE)	0.831113

MEAN + 3s	44.00999
MEAN + 2s	40.79110
MEAN	34.35333
MEAN - 3s	27.91555
MEAN - 3s	24.69667
MEAN + 3SE	36.84667
MEAN + 2SE	36.01555
MEAN	34.35333
MEAN - 2SE	32.69110
MEAN - 3SE	31.85999

DATA ROW	X
1	29.6
2	31.2
3	33.8
4	33.3
5	32.5
6	38.6
7	40.2
8	37.7
9	39.2
10	35.1
11	31.4
12	33.5
13	35.0
14	32.4
15	31.8

Table 3.12-1 Gieseler Plasticity Data for Three Base Coal Samples

Coal	Upper Freeport	Pittsburgh #8	Illinois #6
Maximum Dial, Divisions per minute	8,400	2,820	11
Temperature, °C			
Start	375	375	376
Maximum	440	420	405
Finish	474	450	423
Range	99	75	47

Table 3.14-1 Quantitative ICP Analysis of Filtrate Samples Obtained from 200 mesh x 0 Wet Ground Illinois #6 Coal

Sample I.D.	I602BW50	I602BW26
Date of Analysis	10/14/89	8/28/89
Element	Amount Leached, % (dry basis)	
Zn	0.00000	0.00000
Sr	0.00048	0.00072
Mg	0.00600	0.00984
Na	0.01968	0.02736
Ni	0.00024	0.00000
Mn	0.00168	0.00048
Al	0.00000	0.00000
Ca	0.44520	0.42888
Fe	0.00000	0.00000
K	0.00000	0.00000
B	0.00192	0.00264
Si	0.00012	0.00696
S	0.37032	0.36336

Table 4.1-1 Calibration of Mixing Speed of Waring Blender

COAL	Upper Freeport			Pittsburgh #8	
Particle Size	28 mesh x 0	28 mesh x 0	200 mesh x 0	200 mesh x 0	WATER
Slurry Concentration, % by weight	5	15	15	15	
SPEED SELECTOR	BLENDER SPEED, rpm				
1	9842	9532	9563	9486	9765
2	10075	9827	9827	9610	10090
3	10307	10121	10137	9734	10338
4	10679	10478	10524	10307	10679
5	11005	10912	10865	10664	11036
6	11377	11268	11237	10974	11346
7	11578	11625	11594	11361	11656
8	12725	12655	12508	12322	12601
9	13098	13020	12927	12726	13004
10	13454	13330	13190	13066	13376
11	13872	13857	13655	13486	13764
12	14275	14260	14151	13965	14198
13	14647	14610	14554	14353	14570
14	14942	15019	14958	14353	14895

Table 4.4-1 Experimental Conditions Used in Agglomeration Tests for 28 mesh x 0 Coal Samples

*Run No.	Slurry Concentration, % by weight	N-pentane to Coal Ratio	Time, s	Mixing Speed, rpm
W1-1	2.0	0.5	15	9238
W1-2	2.0	0.5	15	9114
W2-1	2.0	0.5	30	13702
W2-2	2.0	0.5	30	13671
W3-1	2.0	1.0	30	9269
W3-2	2.0	1.0	30	9176
W4-1	2.0	1.0	15	13454
W4-2	2.0	1.0	15	13720
W5-1	4.0	0.5	30	9207
W5-2	4.0	0.5	30	9362
W6-1	4.0	0.5	15	14384
W6-2	4.0	0.5	15	14640
W7-1	4.0	1.0	15	9207
W8-1	4.0	1.0	30	13733

* The first part of the run number corresponds to the work number given in the original work plan.

Table 4.4-2 Experimental Conditions Used in Agglomeration Tests for 200 mesh x 0 Coal Samples

*Run No.	Slurry Concentration, % by weight	N-pentane to Coal Ratio	Time, s	Mixing Speed, rpm
W9-1	2.0	0.5	30	8959
W9-1	2.0	0.5	30	8556
W10-1	2.0	0.5	15	13423
W10-2	2.0	0.5	15	13826
W11-1	2.0	1.0	15	9025
W11-2	2.0	1.0	15	9025
W12-1	2.0	1.0	30	13578
W12-1	2.0	1.0	30	13423
W13-1	4.0	0.5	15	9083
W13-2	4.0	0.5	15	9238
W14-1	4.0	0.5	30	13609
W14-2	4.0	0.5	30	13857
W15-1	4.0	1.0	30	9021
W16-1	4.0	1.0	15	13485

* The first part of the run number corresponds to the work number given in the original work plan.

Table 4.4-3 Nomenclature Used in Agglomeration Tests

1. ABD: Ash Balance Deviation %,

$$ABD = [1 - (P A_p + R A_r) / F A_f] \times 100$$

2. A_e : Ash Content of Entrapped (in Filter Paper) Coal

3. A_{ep} : Ash Content of Entrapped (in Filter Paper) Coal and Filter Paper

4. A_f : Ash Content of Feed Coal

5. A_p : Ash Content of Product

6. A'_p : Corrected Ash Content of Product

7. A_r : Ash Content of Refuse

8. A'_r : Corrected Ash Content of Refuse

9. ARD: Ash Reduction %,

$$ARD = (1 - A_p / A_f) \times 100$$

10. ARJ: Ash Rejection %,

$$ARJ = 100 - Y A_p / A_f$$

11. BTU: Energy Recovery (%),

$$BTU = Y (100 - A_r) / (100 - A_f)$$

12. C: Coal Slurry Concentration (Wt.%)

13. F: Feed Coal Weight (g)

14. MBD: Mass Balance Deviation %,

$$MBD = [1 - (R + P) / F] \times 100$$

15. N: Mixing Speed. (rpm)

16. P: Product Weight (g)

17. PCR: Pentane/Coal Ratio (Weight Basis)

18. R: Refuse Weight (g)

19. S_f : Sulfur Content of Feed (%)

20. S_p : Sulfur Content of Product (%)

21. T: Mixing Time (s)

- Y: Overall Yield (%),

$$Y = P / F \times 100$$

**Table 4.4-4 Results of Agglomeration Tests
on 28 mesh x 0 Illinois #6 Coal**

$A_f = 15.65\%$, $S_f = 4.51\%$

Run #	A_p , %	A_r , %	S_p , %	Y, %	ARJ, %	ARD, %	BTU, %	SRJ, %
W1-1-I6	8.13	15.80	-	33.7	82.5	48.1	36.7	-
W2-2-I6	8.45	16.58	3.24	38.3	79.3	46.0	41.5	72.5
Avg	8.29	16.19		36.0	80.9	47.1	39.1	
W2-1-I6	6.89	16.49	-	35.6	84.3	56.0	39.3	-
W2-2-I6	7.72	16.17	3.34	40.7	79.9	50.7	44.5	69.8
Avg	7.30	16.33		38.1	82.1	53.4	41.9	
W3-1-I6	7.54	17.67	-	37.9	81.7	51.8	41.5	-
W3-2-I6	8.15	17.29	3.15	43.2	77.5	47.9	47.0	69.9
Avg	7.85	17.48		40.5	79.6	49.9	44.3	
W4-1-I6	7.75	16.78	3.14	34.6	83.3	50.5	37.9	75.9
W4-2-I6	8.16	16.56	-	35.8	81.3	47.9	39.0	-
Avg	7.87	16.67		35.2	82.3	49.2	38.4	
W5-1-I6	8.53	18.39	-	36.9	79.9	45.5	40.0	-
W5-2-I6	9.58	18.08	3.25	41.4	74.7	38.8	44.3	70.2
Avg	9.05	18.24		39.1	77.3	42.2	42.2	
W6-1-I6	8.55	19.40	3.34	41.6	77.3	45.4	45.1	69.2
W6-2-I6	7.87	17.29	3.25	37.1	81.4	49.7	40.5	73.3
Avg	8.21	18.35	3.30	39.4	79.3	47.6	42.8	71.3
W7-1-I6	8.43	17.63	3.26	39.3	78.8	68.4	42.7	71.6
W8-1-I6	8.06	19.09	3.31	43.3	77.7	69.2	47.2	68.2

**Table 4.4-5 Results of Agglomeration Tests
on 200 mesh x 0 Illinois #6 Coal**

$A_f = 16.31\%$, $S_f = 4.59\%$

Run #	A_p , %	A_m %	S_p , %	Y, %	ARJ, %	ARD, %	BTU, %	SRJ, %
W9-1-I6	12.17	21.08	-	65.7	51.0	25.4	69.0	-
W9-2-I6	12.25	21.08	4.19	66.5	50.1	24.9	69.7	39.3
Avg	12.21	21.08		66.1	50.5	25.2	69.3	
W10-1-I6	12.17	21.01	-	66.9	50.1	25.4	70.2	-
W10-2-I6	12.20	21.04	4.22	68.0	49.2	25.2	71.3	37.5
Avg	12.18	21.03		67.4	49.6	25.3	70.7	
W11-1-I6	12.26	20.71	-	69.2	48.0	24.8	72.5	-
W11-2-I6	12.38	21.00	4.22	68.7	47.8	24.1	71.9	36.8
Avg	12.32	20.86		68.9	47.9	24.5	72.2	
W12-1-I6	11.80	20.27	4.22	70.3	49.1	27.7	74.1	35.4
W12-2-I6	11.98	20.71	-	68.9	49.4	26.5	72.5	-
Avg	11.89	20.49		69.6	49.3	27.1	73.3	
W13-1-I6	13.09	20.82	4.31	73.8	40.8	19.7	76.6	30.7
W13-2-I6	12.91	20.90	-	73.3	42.0	20.8	76.3	-
Avg	13.00	20.86		73.5	41.4	20.3	76.4	
W14-1-I6	12.88	22.68	4.32	77.1	39.1	21.0	80.2	27.5
W14-2-I6	12.64	21.19	-	73.4	43.1	22.5	76.6	-
Avg	12.76	21.93		75.2	41.1	21.8	78.4	
W15-1-I6	12.85	21.94	4.30	78.0	38.6	21.2	81.2	27.0
W16-1-I6	12.94	21.19	4.32	75.4	40.2	20.7	78.5	29.0

**Table 4.4-6 Results of Agglomeration Tests on
28 mesh x 0 Pittsburgh #8 Coal**

$A_f = 12.33\%$, $S_f = 3.74\%$

Run #	A_p , %	A_r , %	S_p , %	Y , %	ARJ , %	ARD , %	BTU , %	SRJ , %
W1-1-P8	5.97	18.02	-	61.7	70.1	51.6	66.2	-
W1-2-P8	6.47	17.48	2.54	60.3	68.3	47.5	64.4	59.0
Avg	6.22	17.75		61.0	69.2	49.6	65.3	
W2-1-P8	6.58	18.71	-	61.5	67.2	46.6	65.5	-
W2-2-P8	6.55	17.33	2.77	63.1	66.5	46.9	67.2	53.3
Avg	6.57	18.02		62.3	66.8	46.8	66.4	
W3-1-P8	7.06	18.12	-	66.9	61.7	42.7	70.9	-
W3-2-P8	6.92	17.39	2.70	67.1	62.3	43.9	71.3	51.6
Avg	6.99	17.76		67.0	62.0	43.6	71.1	
W4-1-P8	6.47	19.08	-	63.8	66.5	47.5	68.0	-
W4-2-P8	6.26	18.55	2.68	60.9	69.1	49.2	65.1	56.4
Avg	6.37	18.82		62.3	67.8	48.4	66.6	
W5-1-P8	6.86	17.59	-	59.6	66.8	44.4	63.3	-
W5-2-P8	6.56	17.21	2.74	57.0	69.7	46.8	60.8	58.2
Avg	6.71	17.40		58.3	68.2	45.6	62.1	
W6-1-P8	6.77	16.78	2.86	56.3	69.1	45.1	59.9	57.0
W6-2-P8	6.86	17.63	-	58.7	67.4	44.4	62.3	-
Avg	6.81	17.20		57.5	68.2	44.8	61.1	
W7-1-P8	6.77	18.57	2.81	63.4	65.2	45.1	67.4	52.4
W8-1-P8	6.80	18.89	2.80	67.8	62.6	44.8	72.1	49.2

**Table 4.4-7 Results of Agglomeration Tests on
200 mesh x 0 Pittsburgh #8 Coal**

$A_f = 12.72\%$, $S_f = 3.76\%$

Run #	A_p , %	A_r , %	S_p , %	Y, %	ARJ, %	ARD, %	BTU, %	SRJ, %
W9-1-P8	11.30	14.36	3.48	82.0	27.1	11.2	83.4	24.1
W9-2-P8	11.49	13.75	-	81.7	26.2	9.7	82.8	-
Avg	11.39	14.06		81.9	26.7	10.5	83.1	
W10-1-P8	11.49	14.55	-	78.5	29.1	9.7	79.6	-
W10-2-P8	11.54	13.77	3.46	76.6	30.5	9.3	77.6	29.5
Avg	11.52	14.16		77.5	29.8	9.5	78.6	
W11-1-P8	11.69	14.41	3.42	83.7	23.0	8.1	84.7	23.8
W11-2-P8	11.51	14.51	-	83.4	24.5	9.5	84.6	-
Avg	11.60	14.46		83.6	23.8	8.8	84.6	
W12-1-P8	11.48	15.91	3.50	85.8	22.5	9.7	87.1	20.1
W13-1-P8	11.54	13.88	3.49	74.2	32.7	9.3	75.2	31.2
W13-2-P8	11.60	13.98	-	72.6	33.8	8.8	73.6	-
Avg	11.57	13.93		73.4	33.3	9.1	74.4	
W14-1-P8	11.50	14.09	3.47	83.3	24.7	9.6	84.5	23.1
W14-2-P8	11.37	14.68	-	83.6	25.2	10.6	84.9	-
Avg	11.44	14.38		83.5	25.0	10.1	84.7	
W15-1-P8	11.42	14.57	3.48	83.3	25.2	10.2	84.6	22.9
W16-1-P8	11.65	14.68	3.46	85.5	21.7	8.4	86.6	21.3

**Table 4.4-8 Effect of Entrapment of Coal Particles in
Filter Paper on Mass and Ash Balance**

Coal (28 mesh x 0 and 200 mesh x 0 Samples):		Pittsburgh #8
Ash Content of Filter Paper (Average of 3 Samples):		0.05%
Weight of Entrapped Coal in Filter Paper: (Average of 10 Samples)		0.1867 g
Run #	W1-1-P8	W12-1-P8
Feed		
F	9.65	9.65
A _f %	12.33	12.72
Product		
P	5.46	7.73
A _p %	5.97	11.48
A _{ce} %	0.44	0.97
A _e %	9.02	19.11
A' _p %	6.07	11.66
Refuse		
R	3.38	1.28
A _r %	18.02	15.91
A _{ce} %	2.71	1.20
A _e %	61.32	23.79
A' _r %	20.28	16.92
ABD %		
Without Correction	14.2	4.8
With Correction	6.1	2.3
MBD %		
Without Correction	8.3	6.7
With Correction	4.4	2.8

Table 5.1.3-1 Coal Sample Designation

Coal	28 mesh x 0		200 mesh x 0	
	Dry	Wet	Dry	Wet
Upper Freeport Indiana, PA	UI-*-PP-#	UI-*-J-#	UI-*-B-#	UI-*-Bw-#
Pittsburgh #8 Belmont, OH	P8-*-PP-#	P8-*-J-#	P8-*-B-#	P8-*-Bw-#
Illinois #6, Randolph, IL	I6-*-PP-#	I6-*-J-#	I6-*-B-#	I6-*-Bw-#
Kentucky #9, Hopkins, KY	K9-*-PP-#	K9-*-J-#	K9-*-B-#	K9-*-Bw-#
Upper Freeport, Grant, WV	UG-*-PP-#	UG-*-J-#	UG-*-B-#	UG-*-Bw-#
Wyodak, Campbell, WY	WC-*-PP-#	WC-*-J-#	WC-*-B-#	WC-*-Bw-#

*: Drum Number

#: Sample Run

Table 5.2.1-1 Oxidation Indices and 95% Confidence Intervals for the Three Base Coals

Coal Sample	Oxidation Index	No. of Runs*
Ground and Preserved under Argon		
Upper Freeport, 28 mesh x 0	0.68 ± 0.04	24
Upper Freeport, 200 mesh x 0	0.60 ± 0.04	12
Pittsburgh #8, 28 mesh x 0	1.36 ± 0.08	26
Pittsburgh #8, 200 mesh x 0	0.92 ± 0.04	11
Illinois #6, 28 mesh x 0	1.91 ± 0.21	20
Illinois #6, 200 mesh x 0	1.19 ± 0.04	11
Ground and Stored in Air		
Upper Freeport, 28 mesh x 0	1.04 ± 0.17	8
Upper Freeport, 200 mesh x 0	0.74 ± 0.08	13
Pittsburgh #8, 28 mesh x 0	1.41 ± 0.15	16
Pittsburgh #8, 200 mesh x 0	1.12 ± 0.15	16
Illinois #6, 28 mesh x 0	1.93 ± 0.34	12
Illinois #6, 200 mesh x 0	1.53 ± 0.12	14

* Each run is the summation of 1000 scans.

Table 5.2.1-2 Summary of Oxidation Indices for 200 mesh x 0 Upper Freeport Coal Ground in Air

Intro	Scan A	Scan B	Date
1	0.65	0.68	1/18/89
2	0.65	-	1/18/89
3	0.76	0.85	1/24/89
4	0.94	1.02	1/24/89
5	0.71	0.71	2/14/89
6	0.73	0.65	2/14/89
7	0.63	0.60	3/1/89
8	0.51	0.53	7/18/89
9	0.58	0.54	7/18/89
10	0.53	0.55	7/20/89
11	0.54	0.50	7/20/89
12	0.58	0.68	10/19/89
13	0.67	0.61	10/19/89

Summary to 10/19/89: 0.66 ± 0.05

**Table 5.2.1-3 Summary of Oxidation Indices for 200 mesh x 0
Pittsburgh #8 Coal Ground in Air**

Intro	Scan A	Scan B	Date
1	1.95	1.90	1/18/89
2	1.32	1.23	1/18/89
3	0.95	0.95	2/14/89
4	0.96	1.06	2/14/89
5	0.97	0.99	3/1/89
6	0.98	1.00	3/1/89
7	0.88	0.90	3/2/89
8	0.90	0.93	3/2/89
9	0.97	0.96	7/14/89
10	1.05	0.90	7/14/89
11	1.23	1.04	7/18/89
12	1.17	1.12	7/18/89
13	0.99	0.95	7/20/89
14	0.96	0.93	7/20/89

Summary to 7/20/89: 1.08 ± 0.14

**Table 5.2.1-4 Summary of Oxidation Indices for 200 mesh x 0
Illinois #6 Coal Ground in Air**

Intro	Scan A	Scan B	Date
1	1.94	1.88	1/18/89
2	1.47	1.45	2/14/89
3	1.67	1.43	2/14/89
4	1.61	1.59	3/1/89
5	1.47	1.45	3/1/89
6	1.30	1.49	3/2/89
7	1.35	1.25	3/2/89
8	1.68	1.50	7/14/89
9	1.82	1.69	7/14/89
10	1.69	1.72	7/18/89
11	1.99	1.85	7/18/89

Summary to 7/18/89: 1.60 ± 0.12

Table 5.2.3-1 Moisture Contents of Dry Ground Coal Samples

Particle Size	Moisture Content, % by weight		
	Upper Freeport	Pittsburgh #8	Illinois #6
Original*	1.74	3.50	10.1
28 mesh x 0	0.98	2.03	7.52
200 mesh x 0	0.84	1.15	5.77

* ASTM characterization data

Table 5.3-1 Particle Size Analysis for Two-Level Factorial Design Coal Samples

COAL	Average Particle Size (d_{50}), microns			
	DRY GRINDING		WET GRINDING	
	28 mesh x 0	200 mesh x 0	28 mesh x 0	200 mesh x 0
Upper Freeport	120	62	300	16
Pittsburgh #8	130	31	400	20
Illinois #6	100	31	170	20

Table 5.3-2 Washability Analysis for Upper Freeport Coal

Dry Ground to 28 mesh x 0

Gravity Fraction	Yield, %	Ash, %	Sulfur, %	Pyr. S, %	Btu/lb	ARJ, %	SRJ, %	PSRJ, %	BTU, %
1.30 Float	35.6	1.91	0.92	0.08	15312	94.4	85.2	97.8	40.6
1.35 Float	59.1	3.42	1.01	0.13	15073	83.5	73.1	94.1	66.3
1.40 Float	70.6	4.44	1.10	0.19	14866	74.4	65.0	89.8	78.1
1.60 Float	85.9	6.65	1.10	0.26	14354	53.3	57.4	83.0	91.8
1.80 Float	90.6	7.68	1.16	0.34	14277	43.2	52.	76.5	96.3
1.80 Sink	100.0	12.24	2.22	1.31	13433	0.0	0.0	0.0	100.0
As-Rec'd	100.0	13.40	2.61	1.45	13134				

Wet Ground to 200 mesh x 0

Gravity Fraction	Yield, %	Ash, %	Sulfur, %	Pyr. S, %	Btu/lb	ARJ, %	SRJ, %	PSRJ, %	BTU, %
1.30 Float	5.2	1.96	0.81	0.06	15179	99.1	97.7	99.7	6.0
1.35 Float	29.3	3.98	0.96	0.24	14577	90.0	84.7	92.9	32.2
1.40 Float	63.1	5.66	1.09	0.36	14401	69.4	62.6	77.1	68.6
1.60 Float	90.1	7.17	1.19	0.37	13993	44.6	41.7	66.3	95.1
1.80 Float	93.1	8.27	1.29	0.53	13847	34.0	34.7	50.2	97.3
1.80 Sink	100.0	11.67	1.84	0.99	13253	0.0	0.0	0.0	100.0
As-Rec'd	100.0	12.20	1.90	1.26	13596				

Dry Ground to 200 mesh x 0

Gravity Fraction	Yield, %	Ash, %	Sulfur, %	Pyr. S, %	Btu/lb	ARJ, %	SRJ, %	PSRJ, %	BTU, %
1.30 Float	1.7	1.83	0.82	0.07	15252	99.8	99.4	99.9	2.0
1.35 Float	9.2	3.41	0.89	0.08	14933	97.5	96.3	99.3	10.5
1.40 Float	35.0	5.10	0.96	0.20	14558	85.7	84.7	93.8	38.8
1.60 Float	88.0	8.06	1.12	0.28	14043	43.2	55.2	78.0	94.1
1.80 Float	92.2	9.10	1.20	0.29	13764	32.8	49.7	76.1	96.6
1.80 Sink	100.0	12.49	2.20	1.12	13139	0.0	0.0	0.0	100.0
As-Rec'd	100.0	12.90	2.34	1.56	13212				

Table 5.3-3 Washability Analysis for Pittsburgh #8 Coal

Dry Ground to 28 mesh x 0

Gravity Fraction	Yield, %	Ash, %	Sulfur, %	Pyr. S, %	Btu/lb	ARJ, %	SRJ, %	PSRJ, %	BTU, %
1.30 Float	49.0	2.75	1.72	0.29	14263	87.8	81.3	95.1	54.7
1.35 Float	68.8	3.48	1.93	0.40	14091	78.4	70.5	90.5	75.9
1.40 Float	75.0	4.05	2.01	0.52	14009	72.6	66.5	86.6	82.3
1.60 Float	86.1	5.56	2.39	0.86	13685	56.8	54.3	74.6	92.3
1.80 Float	89.1	6.37	2.46	0.92	13612	48.8	51.3	71.8	95.0
1.80 Sink	100.0	11.08	4.50	2.91	12768	0.0	0.0	0.0	100.0
As-Rec'd	100.0	11.90	4.88	3.07	12556				

Wet Ground to 200 mesh x 0

Gravity Fraction	Yield, %	Ash, %	Sulfur, %	Pyr. S, %	Btu/lb	ARJ, %	SRJ, %	PSRJ, %	BTU, %
1.30 Float	2.1	2.98	1.64	0.31	14013	99.4	99.0	99.7	2.4
1.35 Float	48.6	4.58	1.85	0.47	13771	79.3	72.6	89.0	53.8
1.40 Float	63.9	5.70	2.00	0.87	13308	66.2	61.0	73.3	68.3
1.60 Float	90.6	7.15	2.36	1.03	13100	39.9	34.8	55.1	95.3
1.80 Float	92.2	7.36	2.37	1.17	13033	37.0	33.4	48.1	96.5
1.80 Sink	100.0	10.77	3.28	2.08	12448	0.0	0.0	0.0	100.0
As-Rec'd	100.0	11.30	3.46	1.53	12553				

Dry Ground to 200 mesh x 0

Gravity Fraction	Yield, %	Ash, %	Sulfur, %	Pyr. S, %	Btu/lb	ARJ, %	SRJ, %	PSRJ, %	BTU, %
1.30 Float	7.0	1.89	1.53	0.10	14198	98.7	97.5	99.7	7.9
1.35 Float	44.8	3.48	1.80	0.18	13908	84.1	81.2	96.6	49.3
1.40 Float	72.1	4.77	2.12	0.66	13630	65.0	64.3	79.8	77.7
1.60 Float	88.8	5.45	2.35	0.70	13452	50.7	51.2	73.5	94.4
1.80 Float	91.8	6.02	2.56	0.78	13321	43.7	45.1	69.5	96.7
1.80 Sink	100.0	9.82	4.28	2.35	12651	0.0	0.0	0.0	100.0
As-Rec'd	100.0	10.15	4.86	2.91	12835				

Table 5.3-4 Washability Analysis for Illinois #6 Coal

Dry Ground to 28 mesh x 0

Gravity Fraction	Yield, %	Ash, %	Sulfur, %	Pyr. S, %	Btu/lb	ARJ, %	SRJ, %	PSRJ, %	BTU, %
1.30 Float	25.5	2.34	2.78	0.22	13662	95.7	83.5	97.1	29.6
1.35 Float	51.5	3.79	3.04	0.29	13347	86.0	63.6	92.2	58.3
1.40 Float	60.6	4.62	2.72	0.31	13283	79.9	61.7	90.2	68.3
1.60 Float	81.6	7.64	2.94	0.59	12772	55.1	44.2	74.8	88.4
1.80 Float	89.6	8.82	2.96	0.61	12593	43.1	38.3	71.4	95.7
1.80 Sink	100.0	13.90	4.30	1.91	11785	0.0	0.0	0.0	100.0
As-Rec'd	100.0	15.	4.97	2.13	11700				

Wet Ground to 200 mesh x 0

Gravity Fraction	Yield, %	Ash, %	Sulfur, %	Pyr. S, %	Btu/lb	ARJ, %	SRJ, %	PSRJ, %	BTU, %
1.30 Float	1.7	4.11	2.78	0.31	13081	99.5	98.9	99.7	2.0
1.35 Float	19.6	5.79	2.93	0.42	12627	92.6	87.0	95.8	22.4
1.40 Float	28.6	6.88	2.94	0.64	12306	87.2	81.0	90.7	31.9
1.60 Float	85.8	10.76	3.42	1.23	11759	39.8	33.6	46.2	91.3
1.80 Float	93.2	12.44	3.63	1.28	11502	24.4	23.5	39.1	97.0
1.80 Sink	100.0	15.33	4.42	1.96	11048	0.0	0.0	0.0	100.0
As-Rec'd	100.0	17.20	5.12	2.42	10830				

Dry Ground to 200 mesh x 0

Gravity Fraction	Yield, %	Ash, %	Sulfur, %	Pyr. S, %	Btu/lb	ARJ, %	SRJ, %	PSRJ, %	BTU, %
1.30 Float	5.7	3.47	2.69	0.19	13472	98.8	97.0	99.6	6.8
1.35 Float	25.5	5.54	2.71	0.27	13444	91.2	86.4	97.5	30.4
1.40 Float	54.1	6.64	2.76	0.34	13162	77.5	70.6	93.2	63.2
1.60 Float	86.0	10.40	3.49	0.95	12263	44.0	40.9	70.0	93.6
1.80 Float	91.2	11.80	3.59	1.18	11912	32.6	35.5	60.4	96.4
1.80 Sink	100.0	15.97	5.08	2.72	11264	0.0	0.0	0.0	100.0
As-Rec'd	100.0	16.30	5.00	2.66	11391				

Table 5.3-5 Two-Level Factorial Design Experimental Conditions

Variable	Level 1	Level 2
Particle Size	28 mesh x 0	200 mesh x 0
Grinding Method	DRY	WET
Slurry Concentration, %	2	4
PCR*		
Upper Freeport	0.25	0.50
Pittsburgh #8	0.50	1.00
Illinois # 6	0.50	1.00
Agglomeration Time, s	15	30
Mixing Speed, rpm	9000	14000

*PCR: N-Pentane to Coal Ratio

Table 5.3-6 Analysis of Variance Results for Energy Recovery

Variable	Probability that the Variable has no Effect on Energy Recovery		
	Upper Freeport	Pittsburgh #8	Illinois #6
Particle Size	0.00	0.00	0.00
Grinding Method	0.02	0.00	0.59
P. Size/Grnd. Method	0.00	0.00	0.00
Concentration	0.00	0.00	0.02
P. Size/Conc.	0.11	0.38	0.60
Grnd. Method/Conc.	0.80	0.16	0.31
PCR	0.00	0.00	0.02
P. Size/PCR	0.15	0.06	0.68
Grnd. Method/PCR	0.20	0.01	0.30
Conc./PCR	0.00	0.00	0.8258
Agglomeration Time	0.75	0.00	0.12
P. Size/Agg. Time	0.01	0.04	0.54
Grnd. Method/Agg. Time	0.01	0.34	0.72
Conc./Agg. Time	0.03	0.84	0.85
PCR/Agg. Time	0.02	0.10	0.79
Mixing Speed	0.26	0.00	0.62
P. Size/Mix. Speed	0.00	0.07	0.15
Grnd. Method/Mix. Speed	0.05	0.02	0.44
Conc./Mix. Speed	0.44	0.16	0.96
PCR/Mix. Speed	0.58	0.06	0.41
Agg. Time/Mix. Speed	0.22	0.01	0.55

Table 5.3-7 Analysis of Variance for Ash Rejection

Variable	Probability that the Variable has no Effect on Ash Rejection		
	Upper Freeport	Pittsburgh #8	Illinois #6
Particle Size	0.87	0.00	0.00
Grinding Method	0.00	0.00	0.00
P. Size/Grnd. Method	0.00	0.00	0.00
Concentration	0.00	0.00	0.00
P. Size/Conc.	0.58	0.03	0.00
Grnd. Method/Conc.	0.59	0.00	0.58
PCR	0.08	0.00	0.03
P. Size/PCR	0.61	0.57	0.41
Grnd. Method/PCR	0.64	0.14	0.34
Conc./PCR	0.06	0.28	0.89
Agglomeration Time	0.40	0.18	0.42
P. Size/Agg. Time	0.55	0.96	0.62
Grnd. Method/Agg. Time	0.70	0.06	0.70
Conc./Agg. Time	0.69	0.96	0.51
PCR/Agg. Time	0.57	0.24	0.55
Mixing Speed	0.81	0.16	0.45
P. Size/Mix. Speed	0.38	0.31	0.11
Grnd. Method/Mix. Speed	0.21	0.84	0.74
Conc./Mix. Speed	0.60	0.01	0.93
PCR/Mix. Speed	0.92	0.43	0.62
Agg. Time/Mix. Speed	0.56	0.40	0.51

Table 5.3-8 Standard Deviation Within Replicates for Two-Level Factorial Design Experiments

		Mean Square, %		Standard Deviation, %	
COAL	Degrees of Freedom	Ash Rejection	Energy Recovery	Ash Rejection	Energy Recovery
Upper Freeport	14	24.26	3.03	4.9	1.7
Pittsburgh #8	17	5.66	4.94	2.4	2.2
Illinois #6	38	9.03	28.95	3.0	5.4
Overall	69	11.29	12.78	3.4	4.2

Table 5.3-9 Average Values of Energy Recovery

Term	Energy Recovery, %		
	Upper Freeport	Pittsburgh #8	Illinois #6
ALL	95	75	59
Particle Size			
28 mesh x 0	92	61	39
200 mesh x 0	98	88	78
Grinding Method			
DRY	94	75	59
WET	96	74	58
Particle Size, Grinding Method			
28 mesh x 0, DRY	90	67	43
28 mesh x 0, WET	94	54	36
200 mesh x 0, DRY	99	83	75
200 mesh x 0, WET	97	94	81
Slurry Concentration			
2%	93	75	57
4%	97	74	60
Particle Size, Slurry Concentration			
28 mesh x 0, 2%	90	61	38
28 mesh x 0, 4%	94	60	41
200 mesh x 0, 2%	97	89	76
200 mesh x 0, 4%	99	88	80
Grinding Method, Slurry Concentration			
DRY, 2%	93	76	57
DRY, 4%	96	75	62
WET, 2%	94	75	58
WET, 4%	97	73	59
PCR			
0.5*	93	72	57
1.0*	97	77	61
Particle Size, PCR			
28 mesh x 0, 0.5*	89	58	38
26 mesh x 0, 1.0*	94	64	41
200 mesh x 0, 0.5*	97	86	76
200 mesh x 0, 1.0*	~100	91	80

Table 5.3-9 Average Values of Energy Recovery (Continuation)

Term	Energy Recovery, %		
	Upper Freeport	Pittsburgh #8	Illinois #6
Grinding Method, PCR			
DRY, 0.5"	93	72	58
DRY, 1.0"	96	78	60
WET, 0.5"	93	72	56
WET, 1.0"	98	77	61
Slurry Concentration, PCR			
2%, 0.5"	90	74	55
2%, 1.0"	97	77	59
4%, 0.5"	96	70	59
4%, 1.0"	97	78	62
Agglomeration Time			
15 s	95	74	58
30 s	95	76	60
Particle Size, Agglomeration Time			
28 mesh x 0, 15 s	91	60	38
28 mesh x 0, 30 s	93	61	41
200 mesh x 0, 15 s	99	87	77
200 mesh x 0, 30 s	97	90	79
Grinding Method, Agglomeration Time			
DRY, 15 s	94	74	58
DRY, 30 s	95	77	60
WET, 15 s	96	74	57
WET, 30 s	95	74	60
Slurry Concentration, Agglomeration Time			
2%, 15 s	94	74	56
2%, 30 s	93	76	58
4%, 15 s	96	73	59
4%, 30 s	97	75	62
PCR, Agglomeration Time			
0.5", 15 s	94	70	56
0.5", 30 s	92	74	58
1.0", 15 s	96	77	59
1.0", 30 s	98	77	62

Table 5.3-9 Average Values of Energy Recovery (Continuation)

Term	Energy Recovery, %		
	Upper Freeport	Pittsburgh #8	Illinois #6
Mixing Speed			
9000 rpm	95	73	59
14000 rpm	95	76	58
Particle Size, Mixing Speed			
28 mesh x 0, 9000 rpm	90	60	41
28 mesh x 0, 14000 rpm	93	61	38
200 mesh x 0, 9000 rpm	99	86	77
200 mesh x 0, 14000 rpm	98	91	79
Grinding Method, Mixing Speed			
DRY, 9000 rpm	93	75	59
DRY, 14000 rpm	95	76	59
WET, 9000 rpm	96	71	59
WET, 14000 rpm	95	77	58
Slurry Concentration, Mixing Speed			
2%, 9000 rpm	93	75	57
2%, 14000 rpm	94	76	57
4%, 9000 rpm	96	71	61
4%, 14000 rpm	97	76	60
PCR, Mixing Speed			
0.5*, 9000 rpm	92	70	57
0.5*, 14000 rpm	94	74	57
1.0*, 9000 rpm	97	76	61
1.0*, 14000 rpm	97	79	60
Agglomeration Time, Mixing Speed			
15 s, 9000 rpm	95	73	58
15 s, 14000 rpm	95	74	57
30 s, 9000 rpm	94	73	60
30 s, 14000 rpm	96	78	60

*: PCR = 0.25 and 0.50 for Upper Freeport Coal

Table 5.3-10 Average Values of Ash Rejection

Term	Ash Rejection, %		
	Upper Freeport	Pittsburgh #8	Illinois #6
ALL	33	59	69
Particle Size			
28 mesh x 0	33	70	81
200 mesh x 0	33	47	57
Grinding Method			
DRY	21	46	62
WET	45	71	76
Particle Size, Grinding Method			
28 mesh x 0, DRY	34	66	80
28 mesh x 0, WET	33	73	82
200 mesh x 0, DRY	9	26	45
200 mesh x 0, WET	58	69	69
Slurry Concentration			
2%	36	59	72
4%	30	58	66
Particle Size, Slurry Concentration			
28 mesh x 0, 2%	37	70	82
28 mesh x 0, 4%	30	69	80
200 mesh x 0, 2%	36	48	62
200 mesh x 0, 4%	31	46	52
Grinding Method, Slurry Concentration			
DRY, 2%	24	46	65
DRY, 4%	19	46	59
WET, 2%	49	72	79
WET, 4%	42	70	73
PCR			
0.5*	35	61	70
1.0*	32	56	68
Particle Size, PCR			
28 mesh x 0, 0.5*	35	71	82
28 mesh x 0, 1.0*	32	68	81
200 mesh x 0, 0.5*	34	50	58
200 mesh x 0, 1.0*	32	45	56

Table 5.3-10 Average Values of Ash Rejection (Continuation)

Term	Ash Rejection, %		
	Upper Freeport	Pittsburgh #8	Illinois #6
Grinding Method, PCR			
DRY, 0.5"	23	48	63
DRY, 1.0"	20	44	62
WET, 0.5"	46	73	77
WET, 1.0"	44	69	75
Slurry Concentration, PCR			
2%, 0.5"	39	61	73
2%, 1.0"	33	57	71
4%, 0.5"	30	60	67
4%, 1.0"	31	56	65
Agglomeration Time			
15 s	34	59	69
30 s	33	58	69
Particle Size, Agglomeration Time			
28 mesh x 0, 15 s	35	70	82
28 mesh x 0, 30 s	32	69	81
200 mesh x 0, 15 s	33	47	57
200 mesh x 0, 30 s	33	47	57
Grinding Method, Agglomeration Time			
DRY, 15 s	22	47	62
DRY, 30 s	20	45	62
WET, 15 s	46	70	76
WET, 30 s	45	72	75
Slurry Concentration, Agglomeration Time			
2%, 15 s	37	60	72
2%, 30 s	36	58	72
4%, 15 s	31	58	67
4%, 30 s	30	58	65
PCR, Agglomeration Time			
0.5", 15 s	36	61	70
0.5", 30 s	34	60	70
1.0", 15 s	32	56	69
1.0", 30 s	32	57	68

Table 5.3-10 Average Values of Ash Rejection (Continuation)

Term	Ash Rejection, %		
	Upper Freeport	Pittsburgh #8	Illinois #6
Mixing Speed			
9000 rpm	34	59	69
14000 rpm	33	58	69
Particle Size, Mixing Speed			
28 mesh x 0, 9000 rpm	34	70	80
28 mesh x 0, 14000 rpm	33	70	82
200 mesh x 0, 9000 rpm	33	48	57
200 mesh x 0, 14000 rpm	34	47	57
Grinding Method, Mixing Speed			
DRY, 9000 rpm	23	47	62
DRY, 14000 rpm	20	45	63
WET, 9000 rpm	45	71	76
WET, 14000 rpm	46	71	76
Slurry Concentration, Mixing Speed			
2%, 9000 rpm	36	58	72
2%, 14000 rpm	36	60	73
4%, 9000 rpm	31	59	66
4%, 14000 rpm	30	57	66
PCR, Mixing Speed			
0.5*, 9000 rpm	35	61	70
0.5*, 14000 rpm	34	60	70
1.0*, 9000 rpm	32	57	68
1.0*, 14000 rpm	32	56	69
Agglomeration Time, Mixing Speed			
15 s, 9000 rpm	35	58	69
15 s, 14000 rpm	33	59	69
30 s, 9000 rpm	33	59	68
30 s, 14000 rpm	33	57	69

*: PCR = 0.25 and 0.50 for Upper Freeport Coal

Table 5.4.2-1 Comparison Between Oxidation Indices for Coal Samples Dry and Wet Ground to 200 mesh x 0

COAL	Grinding Method	Oxidation Index	No. of Runs
Upper Freeport	DRY	0.66 ± 0.05	26
	WET	0.60 ± 0.11	
Pittsburgh #8	DRY	1.08 ± 0.14	28
	WET	1.43 ± 0.17	16
Illinois #6	DRY	1.60 ± 0.09	22
	WET	2.25 ± 0.21	27

Table 5.4.4-1 Mössbauer Spectroscopy Percent Spectral Areas for the Three Base Coals

Coal	Sample	Pyrite (FeS ₂)	Sulfate/Clays
Illinois #6	28 mesh x 0 (Preserved in Ar)	98.5	1.5
	200 mesh x 0 (Dry ground)	77.1	22.9
Pittsburgh #8	28 mesh x 0 (Preserved in Ar)	94.9	5.1
Upper Freeport	28 mesh x 0 (Preserved in Ar)	90.4	9.6
	200 mesh x 0 (Wet ground)	89.4	10.6

**Table 5.4.5-1 Advancing Contact Angles Measured on
Pellets Made of Dry and Wet Ground Coal**

Sample	Contact Angle, degrees	
	Upper Freeport	Pittsburgh #8
Dry Ground without Drying	114	85
Dry Ground with 4 Days Drying (60 °C)	110	0
Wet Ground	0	0

**Table 5.4.6-1 Zeta Potentials and pH of Dry and Wet Ground Samples
for the Three Base Coals in Fine Coal Suspensions**

Coal	Upper Freeport		Pittsburgh #8		Illinois #6	
Grinding Method	Dry	Wet	Dry	Wet	Dry	Wet
pH Value	5.6	5.6	5.3	5.3	5.9	5.4
Zeta Potential	+13.7	0.0	+2.9	0.0	-17.7	-21.1

**Table 5.3.7-1 BET Surface Areas of 200 mesh x 0
Coal Samples Dry and Wet Ground**

Coal	Surface Area, m²/g	
	Dry Ground	Wet Ground
Upper Freeport	120	139
Pittsburgh #8	164	159
Illinois #6	172	168

Table 5.5-1 Light Hydrocarbons Properties

	N-pentane	Cyclohexane	N-heptane
Molecular Weight	72	84	100
Boiling Point, °C⁽⁴²⁾	36.1	80.8	98.4
Density, kg/m³ (20 °C)⁽⁴³⁾	626	779	684
Viscosity, kPaxs (20 °C)⁽⁴⁴⁾	0.23	0.96	0.41
Surface Tension, N/m (20 °C)	0.016 ⁽⁴⁵⁾	0.024 ⁽⁴⁶⁾	0.019 ⁽⁴⁵⁾
Interfacial Tension (with water), N/m (20 °C)⁽⁴⁷⁾	0.051	0.051	0.051

Table 5.5.1-1 Experimental Conditions for the Agglomeration Tests Using Samples Ground in the Presence of Light Hydrocarbons

	UPPER FREEPORT	PITTSBURGH #8	ILLINOIS #6
Slurry Concentration, % by weight	4	4	4
N-pentane to Coal Ratio	0.5	0.5	0.5
Agglomeration Time, s	30	15	30
Mixing Speed, rpm	14000	9000	14000

Table 5.5.1-2 Standard Deviations Within Replicates for the Grinding Using Hydrocarbons Agglomeration Results

Response Variable	Standard Deviation, %
Energy Recovery	3.3
Ash Rejection	4.4
Pyritic Sulfur Rejection	5.6

**Table 5.5.1-3 Statistical Analysis of the Agglomeration
Results for Upper Freeport Coal**

		Probability of Average Data of Being Equal to the Result Obtained Without Adding Hydrocarbons During Grinding		
HYDROCARBON	HCR*	Energy Recovery	Ash Rejection	Pyritic Sulfur Rejection
N-PENTANE	0.01	1.00	0.22	0.46
	0.10	0.59	0.01	0.11
CYCLOHEXANE	0.01	0.68	0.31	0.49
N-HEPTANE	0.01	0.65	0.31	0.92

* HCR: Hydrocarbon to Coal Ratio

**Table 5.5.1-4 Statistical Analysis of the Agglomeration
Results for Pittsburgh #8 Coal**

		Probability of Average Data of Being Equal to the Result Obtained Without Adding Hydrocarbons During Grinding		
HYDROCARBON	HCR*	Energy Recovery	Ash Rejection	Pyritic Sulfur Rejection
N-PENTANE	0.10	0.34	0.31	0.69
	0.20	0.25	0.61	0.38
CYCLOHEXANE	0.02	0.46	0.34	0.22
	0.05	0.29	0.05	0.91
	0.10	0.39	0.02	0.14
N-HEPTANE	0.02	0.09	0.05	0.33
	0.05	0.05	0.02	0.04
	0.10	0.06	0.02	0.05

* HCR: Hydrocarbon to Coal Ratio

**Table 5.5.1-6 Statistical Analysis of the Agglomeration
Results for Illinois #6 Coal**

		Probability of Average Data of Being Equal to the Result Obtained Without Adding Hydrocarbons During Grinding		
HYDROCARBON	HCR*	Energy Recovery	Ash Rejection	Pyritic Sulfur Rejection
N-PENTANE	0.05	0.03	0.00	0.00
	0.10	0.05	0.06	0.00
	0.20	0.24	0.05	0.01
	0.50	0.67	0.60	0.29
CYCLOHEXANE	0.05	0.18	0.74	0.61
	0.10	0.28	0.26	0.07
	0.20	0.84	0.34	0.61
N-HEPTANE	0.05	0.29	0.99	0.35
	0.10	0.62	0.24	0.09

* HCR: Hydrocarbon to Coal Ratio

**Table 5.5.2.1-1 Effect of the Presence of Light Hydrocarbons
on the Oxidation Index for Illinois #6 Coal
Samples Wet Ground to 200 mesh x 0**

SAMPLE	Oxidation Index	No. of Runs
No Additives	2.61 ± 0.41	4
Cyclohexane/Coal = 1/10	2.68 ± 0.13	4
Cyclohexane/Coal = 1/20	2.17 ± 0.48	4
N-heptane/Coal = 1/5	2.47 ± 0.48	4
N-heptane/Coal = 1/2	2.75 ± 0.81	2

Table 5.5.2.3-1 Effect of Grinding in the Presence of Light Hydrocarbons on the Zeta Potential and pH of Feed Samples

Coal	Reagent	HCR	pH	Zeta Potential, mV
Upper Freeport	None	0	4.4	+9.4
	N-pentane	1/100	5.0	+16.9
		1/10	5.3	+10.3
	Cyclohexane	1/100	5.1	0.0
	N-heptane	1/100	5.0	0.0
Pittsburgh #8	None	0	4.6	+14.8
	N-pentane	1/10	5.2	0.0
		1/5	5.1	0.0
	Cyclohexane	1/50	5.0	+11.0
		1/20	5.0	0.0
		1/10	5.1	0.0
	N-heptane	1/50	5.2	+5.5
		1/20	5.0	0.0
		1/10	5.2	0.0
Illinois #6	None	0	4.6	-20.4
	N-pentane	1/20	5.3	-18.8
		1/10	5.2	-14.6
		1/5	5.3	-16.2
		1/2	5.2	-12.9
	Cyclohexane	1/20	5.3	-11.8
		1/10	5.2	-9.6
		1/5	5.2	-7.2
	N-heptane	1/10	5.4	-11.3
		1/5	5.2	-18.1
		1/2	5.1	-16.7

HCR: Hydrocarbon to Coal Ratio

**Table 5.5.2.4-1 Contact Angles for Pittsburgh #8 and Illinois #6 Coals
Wet Ground in the Presence of Light Hydrocarbons**

COAL	REAGENT	RCR	Largest Angle Recorded, degrees	Drop Life-span, s
Pittsburgh #8	No Additives	0	56	28
	N-Pentane	1/10	45	25
		1/5	31	18
	N-Heptane	1/50	49	25
		1/20	40	25
		1/10	44	46
	Cyclohexane	1/50	45	24
		1/20	38	23
		1/10	44	26
Illinois #6	No Additives	0	38	20
	N-Pentane	1/20	39	26
		1/10	39	22
		1/10	32	17
		1/5	35	23
		1/2	26	19
	N-Heptane	1/10	27	19
		1/5	33	20
		1/2	31	21
	Cyclohexane	1/20	28	20
		1/10	35	20
		1/5	33	19

RCR: Reagent to Coal Ratio

**Table 6.0-1 Experimental Conditions for Surface
Modification Agglomeration Tests**

	UPPER FREEPORT	PITTSBURGH #8	ILLINOIS #6
Slurry Concentration, % by weight	4	4	4
N-pentane to Coal Ratio	0.5	0.5	0.5
Agglomeration Time, s	30	15	30
Mixing Speed, rpm	14000	9000	14000

**Table 6.0-2 Standard Deviations Within Replicates for the
Surface Modification Agglomeration Results**

Response Variable	Standard Deviation, %
Energy Recovery	2.6
Ash Rejection	3.5
Pyritic Sulfur Rejection	6.0

Table 6.1-1 Statistical Analysis of Results from Agglomeration Tests Performed Using Samples Ground in the Presence of Aerosol-OT

		Probability of Average Data of Being Equal to the Result Obtained Without Adding Aerosol-OT During Grinding		
COAL	Reagent Dosage, lb/ton	Ash Rejection	Pyritic Sulfur Rejection	Energy Recovery
Upper Freeport	0.53	0.20	0.43	1.00
	4.22	0.13	0.96	0.40
Pittsburgh #8	0.53	0.16	0.53	0.87
	4.22	0.47	0.32	0.19
Illinois #6	0.53	0.00	0.11	0.20
	4.22	0.00	0.25	0.03

Table 6.1-2 Statistical Analysis of Results from Agglomeration Tests Performed Using Samples Ground in the Presence of Arosurf MG-83A

		Probability of Average Data of Being Equal to the Result Obtained Without Adding Arosurf MG-83A During Grinding		
COAL	Reagent Dosage, lb/ton	Ash Rejection	Pyritic Sulfur Rejection	Energy Recovery
Upper Freeport	0.53	0.55	0.06	1.00
	4.22	0.09	0.11	0.40
Pittsburgh #8	0.53	0.02	0.09	0.01
	4.22	0.00	0.01	0.02
Illinois #6	0.53	0.01	0.84	0.31
	4.22	0.00	0.74	0.06

**Table 6.1-3 Zeta Potentials of the Three Base Coals
Wet Ground in the Presence of Surfactants**

Surfactant	Surfactant Dosage, lb/ton	COAL		
		Upper Freeport	Pittsburgh #8	Illinois #6
None	0	0.0	0.0	-21.1
Aerosol-OT	0.53	-6.8	-6.7	-29.8
	4.22	-20.6	-24.6	-29.1
Arosurf MG-83A	0.53	17.7	10.8	-11.1
	4.22	7.2	6.7	-20.3

**Table 6.1-4 Contact Angles for Pittsburgh #8 and Illinois #6
Coals Wet Ground in the Presence of Surfactants**

COAL	REAGENT	Concentration, ppm	Largest Angle Recorded, degrees	Drop Life-span, s
Pittsburgh #8	Aerosol-OT	10	46	29
		80	49	30
		150	29	18
	Arosurf MG-83A	10	45	20
Illinois #6	Aerosol-OT	80	48	33
		10	42	24
		80	34	
	Arosurf MG-83A	10	27	15
		80	32	14

**Table 6.2-1 Statistical Analysis of Results from Experiments
Performed with Methanol Added Before Agglomeration**

		Probability of Average Data of Being Equal to the Result Obtained Without Adding Methanol Before Agglomeration		
COAL	Reagent Dosage, lb/ton	Ash Rejection	Pyritic Sulfur Rejection	Energy Recovery
Upper Freeport	1.06	0.35	0.32	1.00
	10.56	0.42	0.39	1.00
Pittsburgh #8	1.06	-	-	-
	10.56	0.53	0.75	0.10
Illinois #6	1.06	0.34	0.95	0.43
	10.56	0.70	0.54	0.70

**Table 6.2-2 Statistical Analysis of Results from Experiments
Performed with Ethanol Added Before Agglomeration**

		Probability of Average Data of Being Equal to the Result Obtained Without Adding Ethanol Before Agglomeration		
COAL	Reagent Dosage, lb/ton	Ash Rejection	Pyritic Sulfur Rejection	Energy Recovery
Upper Freeport	1.06	0.07	0.15	1.00
	10.56	0.13	0.17	1.00
Pittsburgh #8	1.06	0.01	0.08	0.13
	10.56	0.16	0.51	0.20
Illinois #6	1.06	0.23	0.38	0.27
	10.56	0.20	0.23	0.15

Table 6.2-3 Oxidation Indices and 95% Confidence Intervals for Illinois #6 Coal Wet Ground to 200 mesh x 0 in the Presence of Alcohols

SAMPLE	Oxidation Index	No. of Runs
Feed, Wet Ground	2.25 ± 0.21	27
Product, Wet Ground	2.24 ± 0.11	30
Feed, 20 ppm Ethanol	1.71 ± 0.25	8
Product, 20 ppm Ethanol	1.81 ± 0.25	8
Feed, 20 ppm Methanol	1.88 ± 0.19	8
Product, 20 ppm Methanol	2.07 ± 0.23	8

Table 6.2-4 Effect of Methanol on Zeta Potential
Slurry Concentration = 0.01% by weight

COAL	Methanol Concentration, ppm	pH	Specific Conductance, μohms/cm	Zeta Potential, mV
Upper Freeport	0	5.6	3	+ 13.7
	100	5.4	2	+ 10.1
	1000	5.2	4	+ 12.5
	10000	5.4	4	- 6.9
Pittsburgh #8	0	5.3	5	+ 2.9
	100	5.3	4	+ 11.6
	1000	5.2	5	+ 11.1
	10000	5.2	6	+ 1.7
Illinois #6	0	5.9	4	- 17.7
	100	5.7	4	- 17.1
	1000	5.7	5	- 19.8
	10000	5.5	6	- 19.6

Table 6.2-5 Effect of Ethanol on Zeta Potential

Slurry Concentration = 0.01% by weight

COAL	Ethanol Concentration, ppm	pH	Specific Conductance, μohms/cm	Zeta Potential, mV
Upper Freeport	0	5.6	3	+ 13.7
	100	5.5	3	+ 15.2
	1000	5.4	2	+ 12.9
	10000	5.5	2	- 9.7
	50000	5.1	3	+ 8.1
	100000	5.0	3	+ 4.1
Pittsburgh #8	0	5.3	5	+ 2.9
	100	5.4	4	0.0
	1000	5.1	4	0.0
	10000	5.2	4	- 11.4
	50000	4.9	6	+ 11.4
	100000	5.2	3	+ 4.5
Illinois #6	0	5.9	4	- 17.7
	100	5.7	5	- 18.3
	1000	5.6	5	- 20.1
	10000	5.6	4	- 23.9
	50000	5.5	4	- 20.1
	100000	5.6	3	- 13.8

Table 6.3-1 Statistical Analysis of Results from Agglomeration Tests Performed Using Samples Ground in the Presence of Styrene

		Probability of Average Data of Being Equal to the Result Obtained Without Adding Styrene During Grinding		
COAL	Reagent Dosage, lb/ton	Ash Rejection	Pyritic Sulfur Rejection	Energy Recovery
Upper Freeport	1.06	0.30	0.12	0.85
	10.56	0.97	0.25	0.81
Pittsburgh #8	1.06	0.34	0.44	0.91
	10.56	0.34	0.59	0.05
Illinois #6	1.06	0.71	0.26	0.44
	10.56	0.28	0.61	0.54

Table 6.3-2 Statistical Analysis of Results from Agglomeration Tests Performed Using Samples Ground in the Presence of Tall Oil

		Probability of Average Data of Being Equal to the Result Obtained Without Adding Tall Oil During Grinding		
COAL	Reagent Dosage, lb/ton	Ash Rejection	Pyritic Sulfur Rejection	Energy Recovery
Upper Freeport	1.06	0.45	0.45	1.00
	10.56	0.76	0.46	1.00
Pittsburgh #8	1.06	0.16	0.18	0.32
	10.56	0.27	0.11	0.01
Illinois #6	1.06	0.19	0.41	0.11
	2.12	0.39	0.54	0.12
	10.56	0.24	0.97	0.83
	21.12	0.10	0.06	0.43

Table 6.3-3 Oxidation Indices and 95% Confidence Intervals for Illinois #6 and Pittsburgh #8 Coals Wet Ground to 200 mesh x 0 in the Presence of Monomers

COAL	Sample	Monomer	Monomer Dosage, lb/ton	Oxidation Index	No. of Runs
Illinois #6	Feed	None	0	2.25 ± 0.21	27
		Tall Oil	1.06 10.56	2.74 ± 0.24 2.15 ± 0.47	12 11
		Styrene	1.06 10.56	1.97 ± 0.29 2.21 ± 0.15	4 4
	Product	None	0	2.24 ± 0.11	30
		Tall Oil	1.06 10.56	2.54 ± 0.24 1.83 ± 0.51	16 12
Pittsburgh #8	Feed	None	0	1.43 ± 0.17	16
		Tall Oil	10.56	1.42 ± 0.32	8
	Product	None	0	1.51 ± 0.17	12
		Tall Oil	10.56	1.29 ± 0.23	8
	Refuse	Tall Oil	10.56	1.79 ± 0.21	4

**Table 6.3-4 Contact Angles for Pittsburgh #8 and Illinois #6
Coals Wet Ground in the Presence of Monomers**

COAL	REAGENT	Concentration, ppm	Largest Angle Recorded, degrees	Drop Life-span, s
Pittsburgh #8	Styrene	20	53	22
		200	50	23
	Tall Oil	20	55	23
		200	62	40
Illinois #6	Styrene	20	32	22
		200	34	20
	Tall Oil	20	30	22
		200	30	12

**Table 6.3-5 Mössbauer Spectroscopy Results for Pittsburgh #8 Coal
Wet Ground to 200 mesh x 0 with 200 ppm of Tall Oil**

Sample	Percentage of Iron as	
	Pyrite	Sulfate/Clays
Feed	94	6
Product	94	6
Refuse	90	10

**Table 7.1.1-1 Material Balance for Wet Ground
Illinois #6 Coal (First Drum)**

	Pulverized Coal	Wet Ground Coal
Total Weight, g	250.0	
Water Content, % (measured)	8.9	
Coal (dry), g	227.9	226.0
Ash Content (dry basis), % (measured)	15.36	14.81
	15.57	15.30
	14.90	15.14
		15.17
	AVERAGE = 15.28	15.11
Total Sulfur Content (dry basis), % (measured)	5.24	4.52
	5.16	4.62
	5.23	4.72
	5.19	
	AVERAGE = 5.21	4.62
Organic Sulfur (dry basis), % (measured)	1.66	1.54
	1.68	1.66
	1.68	1.50
		1.57
	AVERAGE = 1.67	
Inorganic Sulfur (dry basis), % (calculated)	3.53	3.05

Table 7.1.1-2 Material Balance for Wet Ground and Split Illinois #6 Coal (First Drum)

	Pulverized Coal	Split 1	Split 2	Split 3	Split 4	Feed Coal (After Splitting)
Coal (dry), g	227.9	53.4	55.5	51.5	59.5	219.9
Ash Content (dry basis), % (measured)	16.91 16.38 16.42 14.42 15.63 AVERAGE = 15.95	15.11 15.04 13.25 14.46	12.64 13.04 13.26 12.98	15.32 15.46 12.54 14.44	12.40 13.61 15.65 13.89	 13.93
Total Sulfur Content (dry basis), % (measured) AVERAGE =	6.02 5.28 5.87 5.72	 4.99	 4.58	 4.84	 4.94	 4.84
Organic Sulfur (dry basis), % (measured)	2.20	1.72	1.68	1.72	1.86	1.75
Inorganic Sulfur (dry basis), % (measured)	3.52	3.27	2.90	3.12	3.08	3.09

**Table 7.1.1-3 Material Balance for Wet Ground, Split and
Filtered Illinois #6 Coal (First Drum)**

	Pulverized Coal	Split 1	Split 2	Split 3	Split 4	Feed Coal (After Filtration)
Coal (dry), g	227.9	57.8	44.8	51.8	54.0	208.4
Ash Content (dry basis), % (measured)	15.47 17.00 16.26 15.16 16.28 AVERAGE = 16.04	15.25 15.31 14.69 15.08	14.44 14.81 14.71 14.65	15.14 14.92 15.21 15.09	14.81 14.95 15.04 14.94	14.95
Total Sulfur Content (dry basis), % (measured) AVERAGE =	6.35 5.49 5.13 5.66	 4.75	 4.41	 4.98	 4.57	4.69
Organic Sulfur (dry basis), % (measured)	2.09	1.66	1.79	1.71	1.68	1.71
Inorganic Sulfur (dry basis), % (calculated)	3.57	3.09	2.62	3.27	2.89	2.98
Filtrate Weight, g		1191	1025	1130	1154	4500
ICP Sulfur, ppm		280	260	270	270	270
ICP Iron, ppm		69	59	62	62	63

Table 7.1.1-4 Material Balance for Wet Ground, Split and Subjected to Agglomeration Test Illinois #6 Coal (First Drum)

Sample	Sample Weight (dry basis), g	Ash Content, %	Total Sulfur Content, %	Organic Sulfur Content, %	Inorganic Sulfur Content, %
Pulverized Coal	28.47	16.15	4.93	1.52	3.41
Product 1	11.40	9.23	3.69	1.60	2.09
Refuse 1	12.24	18.68	4.26	1.27	2.99
Product 2	12.82	9.24	3.66	1.62	2.04
Refuse 2	14.89	18.37	4.12	1.47	2.65
Product 3	13.45	10.48	3.84	1.71	2.13
Refuse 3	14.11	18.38	4.15	1.51	2.64
Product 4	16.09	10.35	3.88	1.62	2.26
Refuse 4	12.40	19.91	4.21	1.24	2.97
Product 5	13.67	10.08	3.76	1.70	2.06
Refuse 5	13.49	19.17	4.14	1.53	2.61
Product 6	15.66	9.12	3.70	1.64	2.06
Refuse 6	8.49	20.93	4.28	1.37	2.91
Product Average	13.85	9.77	3.76	1.65	2.11
Refuse Average	12.60	19.10	4.18	1.41	2.78
Product+Refuse	26.45	14.22	3.96	1.53	2.43
Product+Refuse (250 g basis)	211.6				

Table 7.1.2-1 Sulfur Forms Analysis for Illinois #6 Coal (First Drum)

	Pulverized Sample 14 mesh x 0			Wet Ground Sample 200 mesh x 0		
	Solid Samples			Solid Samples		
	Without Treatment (S0)	HCL Treatment (S1)	HNO₃ Treatment (S2)	Without Treatment (S0)	HCL Treatment (S1)	HNO₃ Treatment (S2)
Weight, g (before leaching)	10.16	10.16	5.04	10.55	10.55	5.02
Weight, g (after leaching)		9.42	5.07		9.84	5.04
Sulfur Content, % (measured)	4.74 4.63 4.93 4.65 4.61 4.95 4.87 4.80 4.45 4.79	4.01 4.50 4.35 4.04 4.22 4.40	2.01 1.98 1.97 1.78 1.80	4.67 4.53 4.76 4.68 4.69 4.52 4.62 4.72 4.49 4.72	3.73 3.86 3.66 3.82 4.03 3.88 3.97	1.75 1.75 1.64 1.68
AVERAGE =	4.74	4.25	1.91	4.64	3.85	1.71
Ash Content, % (measured)	15.85 15.63 13.49 13.57 14.66	12.09 11.96	7.08 7.35	16.46 16.34 16.91 16.45 16.48	11.92 11.72	8.19 8.24
AVERAGE =	14.64	12.02	7.22	16.53	11.82	8.21
Sulfur, g	0.482	0.401	0.097	0.490	0.379	0.086
Ash, g	1.487	1.132	0.366	1.744	1.163	0.414

Table 7.1.2-1 Sulfur Forms Analysis for Illinois #6 Coal (First Drum)

Continuation

	Pulverized Sample 14 mesh x 0		Wet Ground Sample 200 mesh x 0	
	Filtrates		Filtrates	
	HCL Treatment (F1)	HNO₃ Treatment (F2)	HCL Treatment (F1)	HNO₃ Treatment (F2)
Filtrate Weight, g	906	741	699	681
ICP Fe, ppm	93	143	300	116
ICP S, ppm	100	174	120	161
Iron, g	0.084	0.106	0.210	0.079
Sulfur, g	0.091	0.129	0.084	0.110
	BaSO₄ Precipitation		BaSO₄ Precipitation	
Sample Weight, g	3.15		3.05	
BaSO ₄ weight, g	0.1464		0.1939	
	0.1442		0.1919	
AVERAGE =	0.1453		0.1929	
Sulfate Sulfur, %	0.63		0.87	

Table 7.1.2-2 Sulfur Forms Analysis for Pittsburgh #8 Coal (First Drum)

	Pulverized Sample 14 mesh x 0			-Wet Ground Sample 200 mesh x 0		
	Solid Samples			Solid Samples		
	Without Treatment (S0)	HCL Treatment (S1)	HNO3 Treatment (S2)	Without Treatment (S0)	HCL Treatment (S1)	HNO3 Treatment (S2)
Weight, g (before leaching)	10.00	10.00	5.00	10.00	10.00	5.00
Weight, g (after leaching)		9.65	4.89		9.57	4.90
Sulfur Content, % (measured)	4.27	3.63	1.15	4.20	3.45	1.10
	4.31	3.63	1.15	4.32	3.52	1.09
	4.18	3.63	1.16	4.25	3.69	1.10
	4.37			4.27		
	4.26			4.17		
	4.23			4.90		
	4.26			4.33		
	4.29			4.24		
AVERAGE =	4.27	3.63	1.15	4.34	3.55	1.10
Ash Content, % (measured)	12.41	10.58	6.92	14.60	10.92	7.25
	12.67			14.61		
	12.75			14.40		
	AVERAGE = 12.61	10.58	6.92	14.54	10.92	7.25
Sulfur, g	0.427	0.350	0.056	0.434	0.340	0.054
Ash, g	1.261	1.021	0.338	1.454	1.045	0.355

Table 7.1.2-2 Sulfur Forms Analysis for Pittsburgh #8 Coal (First Drum)

Continuation

	Pulverized Sample 14 mesh x 0		Wet Ground Sample 200 mesh x 0	
	Filtrates		Filtrates	
	HCL Treatment (F1)	HNO3 Treatment (F2)	HCL Treatment (F1)	HNO3 Treatment (F2)
Filtrate Weight, g	1719	1400	1639	1347
ICP Fe, ppm	40	63	122	60
ICP S, ppm	37	73	54	
Iron, g	0.069	0.088	0.200	0.081
Sulfur, g	0.064	0.102	0.089	

Table 7.1.2-3 Average Results of Sulfur Forms Analysis (First Drum)

Sulfur Content, %					
		Pittsburgh #8 Coal		Illinois #6 Coal	
Sulfur Form	Analytical Method	Pulverized Sample	Wet Ground Sample	Pulverized Sample	Wet Ground Sample
TOTAL	LECO S	4.27	4.34	4.74	4.64
Pyritic	LECO S	2.38	2.32	2.03	1.88
	ICP S (from Fe)	1.95	1.78	2.24	1.69
	ICP S	1.97	-	2.37	2.04
Sulfate	LECO S	0.77	0.94	0.79	1.05
	ICP S	0.64	0.89	0.90	0.80
	BaSO ₄ Prec. (ASTM D2492)	-	-	0.63	0.87
Organic	LECO S	1.12	1.08	1.92	1.71

**Table 7.1.2-4 LECO Sulfur Analyses for Upper
Freeport Coal (Second Drum)**

	Total Sulfur, %	Organic + Pyritic Sulfur, %	Organic Sulfur, %
	2.31	1.93	0.63
	2.24	1.75	0.64
	2.39	1.80	0.67
	2.36	1.62	
AVERAGE	2.33	1.78	0.65
STD. DEV.	0.07	0.13	0.02
95% CONFIDENCE ± INTERVAL	0.10	0.20	0.05

	Calculated Value	95% Confidence ± Interval
Sulfate Sulfur, %	0.55	0.20
Pyritic Sulfur, %	1.13	0.21

**Table 7.1.2-5 LECO Sulfur Analyses for Pittsburgh
#8 Coal (Second Drum)**

	Total Sulfur, %	Organic + Pyritic Sulfur, %	Organic Sulfur, %
	4.01	3.60	1.49
	4.53	3.99	1.32
	4.30	3.65	1.43
	4.22	3.78	1.46
	4.46		
	4.24		
	4.17		
AVERAGE	4.28	3.76	1.43
STD. DEV.	0.18	0.17	0.07
95% CONFIDENCE ± INTERVAL	0.16	0.28	0.12

	Calculated Value	95% Confidence ± Interval
Sulfate Sulfur, %	0.52	0.27
Pyritic Sulfur, %	2.33	0.26

Table 7.1.2-6 LECO Sulfur Analyses for Illinois #6 Coal (Second Drum)

	Total Sulfur, %	Organic + Pyritic Sulfur, %	Organic Sulfur, %
	5.11	4.85	1.80
	5.77	5.14	1.79
	5.56	4.48	1.75
	5.40	4.38	1.78
	5.76	4.21	
	5.17	4.37	
AVERAGE	5.46	4.57	1.78
STD. DEV.	0.29	0.35	0.02
95% CONFIDENCE ± INTERVAL	0.30	0.37	0.03

	Calculated Value	95% Confidence ± Interval
Sulfate Sulfur, %	0.89	0.41
Pyritic Sulfur, %	2.79	0.37

Table 7.1.2-7 ICP Analysis Results (Second Drums)

	Coal		
	Upper Freeport	Pittsburgh #8	Illinois #6
Sulfate Sulfur Content, %	0.53	0.52	0.80
Pyritic Sulfur Content, %			
From Fe	1.24	2.09	2.08
From S	1.33	2.12	2.31

Table 7.1.2-8 Comparison Between the Total and Sulfate Sulfur Analyses for the First and Second Drums of the Three Base Coals

	%	COAL		
Sulfur Form	DATE	Upper Freeport	Pittsburgh #8	Illinois #6
TOTAL	1988	2.36	4.27	4.77
	1991	2.33	4.28	5.46
SULFATE	1988	0.02	0.12	0.11
	1991	0.53	0.52	0.80

Table 7.1.2-9 Ash Analysis Results (Second Drums)

	Coal		
	Upper Freeport	Pittsburgh #8	Illinois #6
	12.71	10.92	17.02
	11.79	12.18	15.75
	11.18	10.55	16.88
	12.91	11.36	17.51
	12.16	11.28	16.27
	12.52	11.14	18.23
	12.05	10.82	17.21
	12.01	10.49	15.59
	12.17	11.71	17.27
	11.77	12.02	15.97
AVERAGE	12.13	11.25	16.77
STD. DEV.	0.50	0.58	0.85
95% CONFIDENCE ± INTERVAL	0.36	0.42	0.61

**Table 7.1.3-1 Peak Positions (ESCA Analysis) for Pulverized
(60 mesh x 0) Pittsburgh #8 Coal**

SAMPLE	Peak Position, eV					
	C 1s*	O 1s	Fe 2p	S ⁻²	SO ₄ ²⁻	Si 2s
Base	285.0	533.6	713.0	164.4	169.6	155.2
HCl Leached	285.0	533.8	-	164.3	-	155.4
HNO ₃ Leached	285.0	533.5	-	164.1	-	155.2

* All positions are corrected for charging with the standard C 1s = 285.0 eV

**Table 7.1.3-2 Peak Positions (ESCA Analysis) for Wet
Ground (200 mesh x 0) Pittsburgh #8 Coal**

SAMPLE	Peak Position, eV					
	C 1s*	O 1s	Fe 2p	S ⁻²	SO ₄ ²⁻	Si 2s
Base	285.0	533.2	713.0	164.1	169.5	155.7
HCl Leached	285.0	533.9	-	164.2	-	156.0
HNO ₃ Leached	285.0	533.2	-	164.2	-	155.6

* All positions are corrected for charging with the standard C 1s = 285.0 eV

**Table 7.1.3-3 Percent Atomic Abundances (ESCA Analysis) for
Pulverized (60 mesh x 0) Pittsburgh #8 Coal**

	Percent Atomic Abundance				
SAMPLE	Carbon	Oxygen	Silicon	Sulfur	Iron
Base	75.6	20.9	1.8	1.30	0.31
HCl Leached	75.8	20.7	2.8	0.54	0.18
HNO₃ Leached	69.6	27.7	2.5	0.36	0.03

**Table 7.1.3-4 Percent Atomic Abundances (ESCA Analysis) for
Wet Ground (200 mesh x 0) Pittsburgh #8 Coal**

	Percent Atomic Abundance				
SAMPLE	Carbon	Oxygen	Silicon	Sulfur	Iron
Base	68.7	26.5	3.2	1.00	0.54
HCl Leached	71.0	24.6	3.7	0.48	0.17
HNO₃ Leached	64.7	31.9	3.2	0.16	0.03

**Table 7.1.3-5 Peak Positions (ESCA Analysis) for Pulverized
(14 mesh x 0) Illinois #6 Coal**

SAMPLE	Peak Position, eV					
	C 1s*	O 1s	Fe 2p	S ⁻²	SO ₄ ⁻	Si 2s
Base	285.0	533.9	713.8	164.3	170.8	155.5
HCl Leached	285.0	533.6	-	164.2	-	155.3
HNO ₃ Leached	285.0	533.3	-	164.2	-	155.2

* All positions are corrected for charging with the standard C 1s = 285. 0 eV

**Table 7.1.3-6 Peak Positions (ESCA Analysis) for Wet
Ground (200 mesh x 0) Illinois #6 Coal**

SAMPLE	Peak Position, eV					
	C 1s*	O 1s	Fe 2p	S ⁻²	SO ₄ ⁻	Si 2s
Base	285.0	533.3	713.4	164.2	169.2	155.2
HCl Leached	285.0	533.5	-	164.1	-	155.5
HNO ₃ Leached	285.0	533.7	-	164.3	-	155.9

* All positions are corrected for charging with the standard C 1s = 285. 0 eV

**Table 7.1.3-7 Percent Atomic Abundances (ESCA Analysis)
for Pulverized (14 mesh x 0) Illinois #6 Coal**

	Percent Atomic Abundance				
SAMPLE	Carbon	Oxygen	Silicon	Sulfur	Iron
Base	68.2	27.0	3.4	1.00	0.42
HCl Leached	60.8	32.8	4.8	0.62	0.10
HNO₃ Leached	64.9	30.8	3.8	0.36	0.11

**Table 7.1.3-8 Percent Atomic Abundances (ESCA Analysis) for
Wet Ground (200 mesh x 0) Illinois #6 Coal**

	Percent Atomic Abundance				
SAMPLE	Carbon	Oxygen	Silicon	Sulfur	Iron
Base	59.7	34.2	4.8	0.80	0.56
HCl Leached	61.8	32.2	5.2	0.54	0.15
HNO₃ Leached	61.1	34.6	3.8	0.47	0.05

Table 7.2.1-1 Analysis of Variance for the Effect of Agglomeration Time on the Agglomeration Performance for Upper Freeport Coal

Response Variable	Probability that the Agglomeration Time has NO Effect on the Response Variable
Energy Recovery	0.00
Ash Rejection	0.00
Pyritic Sulfur Rejection	0.50

Table 7.2.1-2 Duncan's Range Test for the Effect of Agglomeration Time on the Agglomeration Performance for Upper Freeport Coal

$\alpha = 0.05$

Response Variable: Ash Rejection, %	
58 C.....B.....A C = 60 B = 30 A = 15	69 A
Response Variable: Energy Recovery, %	
95 A.....B.....C A = 15 B = 30 C = 60	100 C

Table 7.2.1-7 Analysis of Variance for the Effect of Agglomeration Time on the Agglomeration Performance for Illinois #6 Coal

Response Variable	Probability that the Agglomeration Time has NO Effect on the Response Variable
Energy Recovery	0.89
Ash Rejection	0.00
Pyritic Sulfur Rejection	0.00

Table 7.2.1-8 Duncan's Range Test for the Effect of Agglomeration Time on the Agglomeration Performance for Illinois #6 Coal

 $\alpha = 0.05$

**Table 7.2.1-9 Effect of Agglomeration Time on
Oxidation Index for Illinois #6 Coal**

SAMPLE	AGGLOMERATION TIME, s	OXIDATION INDEX	No. of Runs
Feed	-	2.17 ± 0.22	8
Product	30	2.11 ± 0.10	4
	360	2.33 ± 0.48	4
Refuse	30	2.91 ± 0.38	4
	360	2.66 ± 0.65	4

**Table 7.2.1-10 ESCA Results for Illinois #6 Coal
(Agglomeration Tests Samples)**

		Percent Atomic Abundance				
Agglomeration Time, s	Sample	C	O	Si	Fe	S
60	Feed	62.6	30.8	5.7	0.38	0.51
	Product	59.0	27.6	3.7	0.47	0.74
	Refuse	67.5	34.4	5.2	0.51	0.82
360	Feed	60.4	33.5	4.8	0.55	0.74
	Product	66.1	29.1	3.6	0.49	0.76
	Refuse	60.0	33.8	5.0	0.55	0.65

Table 7.2.1-3 Analysis of Variance for the Effect of Agglomeration Time and N-Pentane to Coal Ratio (PCR) on the Agglomeration Performance for Pittsburgh #8 Coal

Source	Probability that the Source has NO Effect on the Response Variable		
	Energy Recovery	Ash Rejection	Pyritic Sulfur Rejection
Agglomeration Time	0.00	0.29	0.88
PCR	0.01	0.08	0.27
Agg. Time, PCR	0.01	0.26	0.26

Table 7.2.1-4 Duncan's Range Test for the Effect of Agglomeration Time and N-Pentane to Coal Ratio (PCR) on the Energy Recovery for Pittsburgh #8 Coal

$$\alpha = 0.05$$

Factor: Agglomeration Time, s		
87 A..... A = 15	B..... B = 30	99C C = 60
Factor: PCR		
92 A..... A = 0.5	94B B = 1.5	

**Table 7.2.1-5 Analysis of Variance for the Effect of Agglomeration Time
on the Agglomeration Performance for Illinois #6 Coal**

Response Variable	Probability that the Agglomeration Time has NO Effect on the Response Variable
Energy Recovery	0.05
Ash Rejection	0.44
Pyritic Sulfur Rejection	0.12

Table 7.2.1-6 Duncan's Range Test for the Effect of Agglomeration Time on the Energy Recovery for Illinois #6 Coal

 $\alpha = 0.05$

Table 7.2.2-1 Analysis of Variance for the Effect of Grinding Method and Agglomeration Time on the Agglomeration Performance for Pittsburgh #8 Coal

Source	Probability that the Source has NO Effect on the Response Variable		
	Energy Recovery	Ash Rejection	Pyritic Sulfur Rejection
Agglomeration Time	0.00	0.10	0.22
Grinding Method	0.00	0.21	0.27
Agg. Time, Grd. Method	0.12	0.96	0.99

Table 7.2.3-1 Effect of pH on the Agglomeration Performance for Illinois #6 Coal

N-Pentane to Coal Ratio	Grinding pH	Ash Rejection, %	Pyritic Sulfur Rejection, %	Energy Recovery, %
0.5	4.5	74	71	72
	10.3	67	79	76
1.0	4.5	72	59	76
	10.1	68	58	78

Table 7.2.3-2 Analysis of Variance for the Effect of N-Pentane to Coal Ratio (PCR) and pH on the Agglomeration Performance for Illinois #6 Coal

Source	Probability that the Source has NO Effect on the Response Variable		
	Energy Recovery	Ash Rejection	Pyritic Sulfur Rejection
PCR	0.14	0.82	0.00
pH	0.20	0.00	0.39
PCR, pH	0.65	0.23	0.28

Table 7.2.4.2-1 ESCA Results for Agglomeration Tests Samples

Coal	Sample	Percent Atomic Abundance				
		C	O	Si	Fe	S
Upper Freeport	Feed	56.8	36.5	5.2	0.68	0.82
	Product	84.9	13.8	0.9	0.06	0.40
	Refuse	27.5	58.8	11.7	1.13	0.88
Pittsburgh #8	Feed	71.0	25.3	2.6	0.35	0.75
	Product	76.4	20.8	1.8	0.29	0.63
	Refuse	69.1	26.8	3.0	0.39	0.79
Illinois #6	Feed	77.2	19.4	2.8	0.29	0.44
	Product	66.3	29.1	3.6	0.47	0.58
	Refuse	52.8	39.4	6.6	0.56	0.57

**Table 7.2.4.3-1 Oxidation Indices and 95% Confidence Intervals for
the Three Base Coals Wet Ground to 200 mesh x 0**

COAL	SAMPLE	OXIDATION INDEX	No. of Runs
Upper Freeport	Feed	1.05 ± 0.22	5
	Product	1.26 ± 0.11	6
	Refuse	4.68 ± 1.60	2
Pittsburgh #8	Feed	1.91 ± 0.21	7
	Product	1.93 ± 0.28	7
	Refuse	1.79 ± 0.30	8
Illinois #6	Feed	2.17 ± 0.22	8
	Product	2.17 ± 0.12	7
	Refuse	2.38 ± 0.49	8

Table 7.3.1-1 Analysis of Variance and Duncan's Range Test for the Effect of N-Heptane to Coal Ratio (HCR) on the Agglomeration Performance for Upper Freeport Coal

Response Variable	Probability that the HCR has NO Effect on the Response Variable
Energy Recovery	0.01
Ash Rejection	0.15
Pyritic Sulfur Rejection	0.00

$$\alpha = 0.05$$

Table 7.3.1-2 Analysis of Variance and Duncan's Range Test for the Effect of N-Heptane to Coal Ratio (HCR) on the Agglomeration Performance for Illinois #6 Coal

Response Variable	Probability that the HCR has NO Effect on the Response Variable
Energy Recovery	0.00
Ash Rejection	0.07
Pyritic Sulfur Rejection	0.04

 $\alpha = 0.05$

Table 7.3.1-3 Oxidation Indices for Illinois #6 Coal Feed, Product, and Refuse Samples from Agglomeration Tests Conducted Using N-Heptane as Agglomerant

Sample	Oxidation Index	No. of Runs
Feed	2.61 ± 0.41	4
Product	2.62 ± 0.26	4
Refuse	2.54 ± 0.41	4

Table 7.3.3.2-1 Use of FeCl₃ as Pyrite Depressant

Pittsburgh #8 Coal

Feed Ash Content: 12.55%

Feed Sulfur Content: 4.20%

	FeCl ₃ Dosage, lb/ton		
	0	3	5
Product Ash Content, %	4.4	4.8	5.0
Product Sulfur Content, %	2.38	2.39	2.43
Yield, %	89	88	87
Ash Rejection, %	69	66	66
Sulfur Rejection, %	50	50	50
Energy Recovery, %	98	97	95

**Table 7.4.2-1 Central Composite Design Average
Results for Upper Freeport Coal**

HCR	0.10	0.23		0.40			0.57		0.70
Grnd. Time, min	55	30	80	12	55	98	30	80	55
pH									
3.0					64 66 99				
4.7		60 74 99	62 71 94				61 73 99	66 70 99	
7.0	53 64 87			49 72 99	63 69 99	66 78 99			65 70 99
9.3		61 74 99	65 74 98				64 72 99	70 73 99	
11.0					66 70 99				

Cell Data: **Ash Rejection**
 Inorganic Sulfur Rejection
 Energy Recovery

Table 7.4.3-1 Effect of Grinding Time on the Agglomeration Performance for Pittsburgh #8 Coal

Grinding Time, min	Particle Size (d₅₀), μm	Agg. Time, s	Ash Rejection, %	Inorganic Sulfur Rejection, %	Energy Recovery, %
60	5.0	120	64	54	96
		150	68	49	99
		180	65	37	99
80	4.5	120	47	52	85
		150	62	56	94
		180	67	47	99
120	3.5	120	45	53	85
		150	69	58	97
		180	70	52	99

Table 7.4.3-2 Effect of Grinding at High pH on the Agglomeration Performance for Pittsburgh #8 Coal

HCR*	Agglom. Time, s	Ash Rejection, %	Inorganic Sulfur Rejection, %	Energy Recovery, %
0.50	90	79	64	99
	120	77	64	99
	150	80	60	99
	120**	82	67	99
0.75	90	78	65	99
	120	78	63	99
	150	77	59	99
	120**	81	65	99

*** N-Heptane to Coal Ratio**

**** Product Subjected to High-Shear Washing Step**

Table 7.4.3-3 Central Composite Design Average Results for Pittsburgh #8 Coal

Agg. Time, s	HCR		0.1		0.3		0.5		0.7		0.9	
	Grnd. Time, min		60		40		20		40		60	
	pH											
30	7											
90	7											
	5											
	9											
150	3											
	7											
	11											
210	5											
	9											
	7											

Cell Data: Ash Rejection
Inorganic Sulfur Rejection
Energy Recovery

Table 7.4.4-1 Average Particle Size for Illinois #6 Coal

d_{50} , μm	Grinding Time, min		
Sample	5	20	60
Feed	29.3	12.4	5.7
Product	29.9	12.4	6.7
Refuse	22.6	12.9	6.3

Table 7.4.4-2 Agglomeration Results as a Function of Grinding Time for Illinois #6 Coal

Feed Ash Content: 17.4%

Feed Total Sulfur Content: 5.02%

Feed Inorganic Sulfur Content: 3.23%

	Grinding Time, min		
	5	20	60
Product Ash Content, %	9.2	10.5	13.5
Product Total Sulfur Content, %	4.26	4.79	5.11
Product Inorganic Sulfur Content, %	2.55	3.09	3.44
Refuse Ash Content, %	29.6	18.8	17.3
Yield, %	70	49	26
Ash Rejection, %	63	70	80
Total Sulfur Rejection, %	41	53	73
Inorganic Sulfur Rejection, %	45	53	72
Energy Recovery, %	78	54	28

**Table 7.4.4-3 Agglomeration Results for Finely Ground
($d_{50} = 6.9 \mu\text{m}$) Illinois #6 Coal**

N-Heptane to Coal Ratio	Agglom. Time, s	Ash Rejection, %	Inorganic Sulfur Rejection, %	Energy Recovery, %
0.50	180	90	89	18
0.75	180	80	82	33
1.00	90	82	80	31
	120	77	80	37
	180	76	78	41
1.50	180	66	72	52
2.00	180	63	67	66
	360	59	61	65
3.00	180	52	61	73
	360	58	63	71
4.00	180	50	61	76
	360	52	58	76
5.00	180	48	60	77

Table 7.4.4-4 Effect of Sieve Size and pH on the Agglomeration Performance for Illinois #6 Coal ($d_{50} = 3.7 \mu\text{m}$)

Sieve Size, mesh	pH	Ash Rejection, %	Inorganic Sulfur Rejection, %	Energy Recovery, %
120	3.8	41	56	76
	11.8	53	76	78
230	3.8	28	45	93
	11.8	38	72	97

Table 7.4.4-5 Statistical Analysis of the Agglomeration Results for Finely Ground Illinois #6 Coal ($d_{50} = 3.7 \mu\text{m}$)

Variable	Probability that the Variable Is Not Significant		
	Energy Recovery	Ash Rejection	Inorganic Sulfur Rejection
Sieve Size	0.00	0.00	0.61
pH	0.29	0.00	0.01
Sieve Size, pH	0.24	0.58	0.28

Table 7.4.4-6 Effect of pH and Particle Size on the Product Ash Content for Illinois #6 Coal

Particle Size	Product Ash Content, %	
	pH = 3.8	pH = 12
$d_{50} = 12.4 \mu\text{m}$ (200 mesh x 0)	9 ± 1	14.6
$d_{50} = 6.9 \mu\text{m}$	10.4	13.0
$d_{50} = 3.7 \mu\text{m}$	12.4	10.3

Table 7.5-1 Selective Grinding Results

COAL	COAL		
	Upper Freeport	Pittsburgh #8	Illinois #6
PT Weight, g	238.0	221.0	151.0
RO Weight, g	4.0	11.0	8.9
Yield, %	98	95	94
Feed Ash, %	12.7	11.5	16.5
PT Ash, %	12.5	11.2	14.5
RO Ash, %	23.4	16.9	51.5
Ash Rejection, %	3	7	17
Feed Total Sulfur, %	1.94	3.40	4.83
PT Total Sulfur, %	1.81	3.40	4.22
RO Total Sulfur, %	9.66	3.46	16.24
Total Sulfur Rejection, %	8	5	18
Feed Inorganic Sulfur, %	1.26	2.04	3.14
PT Inorganic Sulfur, %	1.13	2.03	2.47
RO Inorganic Sulfur, %	9.16	2.18	14.49
Inorganic Sulfur Rejection, %	12	5	26
Energy Recovery, %	99	96	97

PT: Passing through screen fraction

RO: Retained on screen fraction

Table 7.5-2 Selective Grinding Agglomeration Results for Illinois #6 Coal

Grinding Steps	pH	Ash Rejection, %	Inorganic Sulfur Rejection, %	Energy Recovery, %
1	12.5	32	71	95
2	11.4	66	73	95
	12.0	60	73	94
	12.5	55	80	88

Table 7.6-1 Ultimate Analyses of the Additional Coals

Weight % (dry)	COAL		
	Upper Freeport	Wyodak	Kentucky #9
Carbon	74.81	65.23	68.11
Hydrogen	3.68	5.21	5.11
Nitrogen	1.40	1.65	1.64
Oxygen	2.66	19.33	6.73
Sulfur	2.97	0.55	3.84
Ash	14.48	8.03	14.57
Gross Calorific Value, Btu/lb	13079	11239	12711

Table 7.6-2 Proximate Analyses of the Additional Coals

Weight % (dry)	COAL		
	Upper Freeport	Wyodak	Kentucky #9
Volatile Matter	18.82	49.97	37.53
Fixed Carbon	66.70	42.00	47.90
Ash	14.48	8.03	14.57
Volatile Matter, % (Dry, Mineral-Matter-free)	22.01	54.33	43.93
Moist., Mineral-Matter-Free Calorific Value, Btu/lb	15613	12336	15207

Table 7.6-3 Classification of Additional Coals by Rank

COAL	Group
Upper Freeport (Grant County, WV)	Medium Volatile Bituminous
Wyodak (Campbell County, WY)	High Volatile C Bituminous
Kentucky #9 (Hopkins County, KY)	High Volatile A Bituminous

Table 7.6-4 Trace Elements Analyses of the Additional Coals

Trace Element, ppm	COAL		
	Upper Freeport	Wyodak	Kentucky #9
Antimony, Sb	< 8	4	< 6
Arsenic, As	23	3	4
Beryllium, Be	1.4	0.3	1.3
Cadmium, Cd	1.0	0.2	< 0.4
Chromium, Cr	25	4	16
Cobalt, Co	9	< 1	3
Lead, Pb	32	7	27
Manganese, Mn	14	7	57
Mercury, Hg	0.26	0.13	0.16
Nickel, Ni	18	6	10
Selenium, Se	2	< 1	3

**Table 7.6.1-2 Average Agglomeration Results for Upper
Freeport Coal, Grant County, WV**

	Agglomerant	N-Pentane		N-Heptane	
	Sieve Size, mesh	60	120	60	120
pH	4.0	59	60	57	60
		63	61	60	58
		99	99	99	99
	11.8	65	67	68	69
		78	79	80	77
		97	97	97	99

Cell Data: Ash Rejection
 Inorganic Sulfur Rejection
 Clean Coal Yield

**Table 7.6.1-2 Statistical Analysis Results for Upper
Freeport Coal, Grant County, WV**

Source	Probability that the Source is Not Significant		
	Ash Rejection	Inorganic Sulfur Rejection	Clean Coal Yield
Agglomerant	0.33	0.12	0.93
Sieve Size	0.11	0.24	0.07
Agglomerant, Sieve Size	0.94	0.30	0.99
pH	0.00	0.00	0.00
Agglomerant, pH	0.13	0.14	0.14
Sieve Size, pH	0.60	0.55	0.61

Table 7.6.2-1 ANOVA Results for the Effect of Sieve Size and Agglomeration Time on the Process Performance for Wyodak Coal

N-Heptane to Coal Ratio = 1.0

Source	Probability that the Source is Not Significant		
	Ash Rejection	Inorganic Sulfur Rejection	Clean Coal Yield
Sieve Size	0.00	0.00	0.00
Agglomeration Time	0.00	0.00	0.00
Sieve Size, Agg. Time	0.10	0.10	0.12

Table 7.6.2-2 ANOVA Results for the Effect of Sieve Size and N-Heptane to Coal Ratio on the Process Performance for Wyodak Coal

Agglomeration Time = 360 s

Source	Probability that the Source is Not Significant		
	Ash Rejection	Inorganic Sulfur Rejection	Clean Coal Yield
Sieve Size	0.00	0.00	0.00
HCR	0.00	0.00	0.00
Sieve Size, HCR	0.03	0.01	0.02

HCR: N-Heptane to Coal Ratio

**Table 7.7-1 Trace Elements Analyses and Agglomeration
Test Results for Pittsburgh #8 Coal**

Ash Rejection = 70%
Total Sulfur Rejection = 50%
Pyritic Sulfur Rejection = 58%
Energy Recovery = 98%

Element	Concentration, $\mu\text{g/g}$ (dry basis)	
	Feed	Product
Antimony (Sb)	< 6	2
Arsenic (As)	20 ± 7	10
Beryllium (Be)	0.8 ± 0.4	0.9
Cadmium (Cd)	< 0.4	< 0.4
Chromium (Cr)	14 ± 1	-
Cobalt (Co)	3 ± 1	< 2
Lead (Pb)	10 ± 7	< 2
Manganese (Mn)	25 ± 11	16
Mercury (Hg)	0.28 ± 0.06	0.18
Nickel (Ni)	10 ± 3	10
Selenium (Se)	< 2	< 2
Agglomeration Results		
Ash, wt. %	13.5	4.6
Total Sulfur, wt. %	3.54	2.01
Pyritic Sulfur, wt. %	2.57	1.22

**Table 7.7-2 Trace Elements Analyses and Agglomeration
Test Results for Upper Freeport Coal**

Element	Concentration, $\mu\text{g/g}$ (dry basis)		
	Feed	Product (pH = 4.0)	Product (pH = 12.3)
Antimony (Sb)	< 6	< 4	< 4
Arsenic (As)	14	8	8
Beryllium (Be)	1.0	0.9	1.0
Cadmium (Cd)	0.7	0.3	0.2
Chromium (Cr)	75	38	33
Cobalt (Co)	3	2	2
Lead (Pb)	24	10	8
Manganese (Mn)	10	5	5
Mercury (Hg)	0.32	0.38	0.34
Nickel (Ni)	13	7	8
Selenium (Se)	2	3	2
Agglomeration Results			
Ash, wt. %	13.2	5.4	4.5
Total Sulfur, wt. %	2.46	1.28	1.07
Pyritic Sulfur, wt. %	1.81	0.56	0.34
Ash Rejection, %	63		70
Total Sulfur Rejection, %	53		61
Pyritic Sulfur Rejection, %	72		83
Energy Recovery, %	99		99

**Table 7.7-3 Calculated Trace Elements Distribution for
Upper Freeport and Pittsburgh #8 Coals**

Element	Element Percentage in the Mineral Matter Fraction	
	Upper Freeport Coal	Pittsburgh #8 Coal
Antimony (Sb)	*	*
Arsenic (As)	73	79
Beryllium (Be)	21	~0
Cadmium (Cd)	~100	*
Chromium (Cr)	86	*
Cobalt (Co)	60	*
Lead (Pb)	~100	*
Manganese (Mn)	83	59
Mercury (Hg)	~0	60
Nickel (Ni)	73	*
Selenium (Se)	~0	*

* Not available because of the lack of precision of the analysis.

Table 7.9-1 Contact Angle Measurements Using Different Media

Medium	Contact Angle, degrees		
	(Water Phase)		
	Upper Freeport	Pittsburgh #8	Illinois #6
Air	31	45	46
N-pentane	54	48	39
N-heptane			
Non-treated pellet	53	30	43
Treated pellet	128	96	99

Table 7.9-2 Contact Angle Measurements on Agglomeration Test Samples

COAL	Sample	Contact Angle, degrees	
		(Water Phase)	
		Untreated Pellet	Treated Pellet
Upper Freeport	Feed	55	95
	Product	100	110
	Refuse	85	95
Illinois #6	Feed	50	80
	Product	85	100
	Refuse	70	80

Table 7.11-1 Alberta Research Coal (ARC) Agglomeration Results

Feed Ash Content: 10.1%

Feed Total Sulfur Content: 4.54%

Feed Inorganic Sulfur Content: 2.71%

	N-Heptane to Coal Ratio	
	0.3	0.5
Product Ash Content, %	4.4	4.7
Product Total Sulfur Content, %	3.33	3.47
Product Inorganic Sulfur Content, %	1.49	1.62
Yield, %	91	93
Ash Rejection, %	61	57
Total Sulfur Rejection, %	33	29
Inorganic Sulfur Rejection, %	50	44
Clean Coal Yield, %	97	99

APPENDIX B: FIGURES

Figure 2.0-1 Work Breakdown Structure

Figure 3.2.1.1-1 Photographs of Pulverized (14 mesh x 0) Upper Freeport Coal Showing: Vitrinite = V, Dense Pyrite = P, Fusinite = F and Mounting Media = N. Reflected Light in Oil, x443.

Figure 3.2.1.1-2 Photographs of Pulverized (14 mesh x 0) Upper Freeport Coal Showing: Pyrite = P, Exinite = E, Semifusinite = SF, Vitrinite = V, Micrinite = M, Fusinite = F, and Mounting Media = N. Reflected Light in Oil, x443.

Figure 3.2.1.1-3 Photographs of Pulverized (14 mesh x 0) Upper Freeport Coal Showing: Vitrinite = V, Framboidal Pyrite = FP, Highly Irregular Snowflake-Like Pyrite = IP and Clay = C. Reflected Light In Oil, x443.

Figure 3.2.1.1-4 Photographs of Pulverized (14 mesh x 0) Upper Freeport Coal Showing: Quartz = Q, Exinite = E, Vitrinite = V, Micrinite = M, Fusinite = F, and Very Irregular Particle Surfaces = B. Reflected Light in Oil, x443.

Figure 3.2.1.2-1 Photographs of Pulverized (14 mesh x 0) Pittsburgh #8 Coal Showing: Semifusinite = SF, Fine Coal = FC, Vitrinite = V, Exinite = E, Micrinite = M, Resinite? = R, Fusinite = F, and Mounting Media = N. Reflected Light in Oil, x443.

Figure 3.2.1.2-2 Photographs of Pulverized (14 mesh x 0) Pittsburgh #8 Coal Showing: Semifusinite = SF, Vitrinite = V, Exinite = E, Quartz = Q, Pyrite = P, Fusinite = F, Micrinite = M, and Mounting Media = N. Reflected Light in Oil, x443.

Figure 3.2.1.2-3 Photographs of Pulverized (14 mesh x 0) Pittsburgh # 8 Coal Showing: A Bone Coal Particle (Interlayered Coal and Mineral) in Top Photo and Vitrinite = V, Grading to Clay = C. Reflected Light in Oil, x443.

Figure 3.2.1.2-4 Photographs of Pulverized (14 mesh x 0) Pittsburgh # 8 Coal Showing: Pyrite = P in Top Photo and Shale = SH in Bottom Photo. Reflected Light in Oil, x443.

Figure 3.2.1.3-1 Photographs of Pulverized (14 mesh x 0) Illinois # 6 Coal Showing: Vitrinite = V, Resinite = R, Exinite (Leaf Culticle) = EC, Semifusinite = SF, Fusinite = F, Pyrite = P and Mounting Media = N. Reflected Light in Oil, x443.

Figure 3.2.1.3-2 Photographs of Pulverized (14 mesh x 0) Illinois # 6 Coal Showing: Vitrinite = V, Exinite = E, Micrinite = M, Semifusinite = SF, Fusinite = F, and Pyrite = P. Reflected Light in Oil, x443.

Figure 3.2.1.3-3 Photographs of Pulverized (14 mesh x 0) Illinois # 6 Coal Showing: Quartz = Q, Clay = C, Micrinite = M, Exinite = E, Fusinite = F, and Vitrinite = V. Reflected Light in Oil, x443.

Figure 3.2.1.3-4 Photographs of Pulverized (14 mesh x 0) Illinois # 6 Coal Showing: Vitrinite = V, Pyrite = P, Calcite = CA, and Mounting Media = N. Reflected Light in Oil, x443.

Figure 3.3.1-1 Particle Size Distributions of 200 mesh x 0 Three Base Coal Samples Measured by Optical Microscopy

Figure 3.3.1-2 Fine Particle Size Distributions of Three Base Coals by SEM

Figure 3.3.1-3 Compound Particle Size Distributions of Three Base Coals

Figure 3.3.1-4 Particle Size Distributions of the Three Base Coals Ground to 200 mesh x 0 Measured by Optical Image Analyzer

Figure 3.3.1-5 Particle Size Distribution of Glass Beads Measured with Optical Image Analyzer and Microtrac

Figure 3.3.1-6 Particle Size Distribution of Illinois # 6 Coal
200 mesh x 0 Sample Measured with Optical
Image Analyzer and Microtrac

Figure 3.3.2-1 Particle Size Distribution of 28 mesh x 0
Pittsburgh # 8 Coal

Figure 3.5-1 Photomicrographs of 200 mesh x 0 Upper Freeport Coal Showing Microscopic Appearance of the Coal and Associated Minerals. Reflected Light in Air, x215

Figure 3.5-2 Photomicrographs of 200 mesh x 0 Pittsburgh # 8 Coal Showing Microscopic Appearance of the Coal and Associated Minerals. Reflected Light in Air, x215.

Figure 3.5-3 Photomicrographs of 200 mesh x 0 Illinois # 6 Coal Showing Microscopic Appearance of the Coal and Associated Minerals. Reflected Light in Air, x215.

Figure 3.5-4 Pyrite Association for 28 mesh x 0 Samples

Figure 3.5-5 Pyrite Association for 200 mesh x 0 Samples

Figure 3.6.1-1 Chord Ratio (Length of Horizontal Chords to Vertical Chords)
Distributions of Coal Particles for the Three Base Coals

$n = 2$

$n = 3$

$n = 11$

Figure 3.6.2-1 Fourier Harmonics for $n = 2, 3$, and 11 . The arrows indicate the corresponding amplitudes.

Figure 3.6.3-1 SEM Image of Polished Refuse Cake at High Magnification (2400). Top: Secondary Electron Image Showing Pyrite (White) and Silicates (Grey); Bottom: Back Scattered Electron Image. The white spots are pyrite down to Specks.

Figure 3.6.3-2 Pyrite Size Distributions for Three Base Coals by SEM

**Figure 3.6.3-3 Chord Ratio (Length of Horizontal Chords to Vertical Chords)
Distributions of Pyrite Particles for Three Base Coals**

Figure 3.7-1 Typical DRIFT Spectrum. The shaded areas are the ones ratioed for the calculation of the oxidation index.

Figure 3.8.1-1 LAMMA Spectra (an average of 50 spectra) of Upper Freeport Coal

Figure 3.8.2-1 Survey ESCA Spectra for the Three Base Coals

Figure 3.8.2-2 Sulfur 2p and Silicon 2p Spectra
for the Three Base Coals

Figure 3.8.2-3 Iron 2p Spectra for the Three Base Coals

Figure 3.0.2-4 Carbon 1s Spectra for the Three Base Coals

Figure 3.8.2-5 Oxygen 1s Spectra for the Three Base Coals

Figure 3.9-1 Representative Curve Fit Spectra for 28 mesh x 0
Argon Preserved Samples (Upper Freeport Coal)

**Figure 3.9-2 Representative Curve Fit Spectra for 28 mesh x 0
Argon Preserved Samples (Pittsburgh # 8 Coal)**

Figure 3.9-3 Representative Curve Fit Spectra for 28 mesh x 0
Argon Preserved Samples (Illinois # 6 Coal)

Figure 3.11-1 Zeta Potentials of the Three Base Coals at Different pH

Figure 3.13-1 Dubinin-Polanyi Plots of Adsorption of CO_2 on Upper Freeport Coal.
 (W = Volume adsorbed STP/g of coal, P/P_s = Relative CO_2 pressure)

Figure 4.1-1 Schematic Diagram of Agglomeration Unit (Waring Blender)

SLURRY	
●	WATER
▽	Upper Freeport, 28 mesh x 0, 5 wt.%
△	Upper Freeport, 28 mesh x 0, 15 wt.%
◇	Upper Freeport, 200 mesh x 0, 15 wt.%
□	Pittsburgh # 8, 200 mesh x 0, 15 wt.%

Figure 4.1-2 Blender Speeds Measured at Various Conditions

Figure 4.1-3 Calibration Curves Obtained from Four Different Coal Slurries

Figure 4.2.2-1 Schematic Diagram of the Experimental Procedure for the Agglomeration Test

Figure 4.3-1 Calorific Value versus Ash Content for the Three Base Coals

Figure 5.1.1-1 Schematic Diagram of the Environmental Chamber

Figure 5.1.1-2 Top and Bottom View of the Stirred-Ball Mill Lid

Figure 5.1.1-3 Side View of the Stirred-Ball Mill Lid

Figure 5.1.1-4 O-Ring Section of the Shaft

Figure 5.1.2.1-1 Calibration Curve for Dry Grinding to 200 mesh x 0

Figure 5.1.2.2-1 Calibration Curve for Wet Grinding to 200 mesh x 0

Figure 5.1.2.3-1 Calibration Curves for Dry Grinding to 28 mesh x 0

Figure 5.1.2.4-1 Calibration Curves for Wet Grinding to 28 mesh x 0

Figure 5.2.1-1 Comparison of Oxidation Indices for the Three Base Coals Ground under Argon and in Air

Figure 5.2.2-1 Comparison of LAMMA Results for Upper Freeport Coal Samples Prepared under Argon and in Air

Figure 5.2.2-2 Comparison of LAMMA Results for Pittsburgh # 8 Coal Samples Prepared under Argon and in Air

Figure 5.2.2-3 Comparison of LAMMA Results for Illinois #6 Coal Samples Prepared under Argon and in Air

Figure 5.3-1 Washability Analysis Data of Energy Recovery
versus Ash Rejection for Upper Freeport Coal

Figure 5.3-2 Washability Analysis Data of Energy Recovery versus
Pyritic Sulfur Rejection for Upper Freeport Coal

Figure 5.3-3 Washability Analysis Data of Energy Recovery
versus Ash Rejection for Pittsburgh # 8 Coal

Figure 5.3-4 Washability Analysis Data of Energy Recovery versus
Pyritic Sulfur Rejection for Pittsburgh # 8 Coal

Figure 5.3-5 Washability Analysis Data of Energy Recovery
versus Ash Rejection for Illinois # 6 Coal

Figure 5.3-6 Washability Analysis Data of Energy Recovery versus
Pyritic Sulfur Rejection for Illinois # 6 Coal

**Figure 5.3-7 Two-Level Factorial Design Agglomeration
Results for Upper Freeport Coal**

Figure 5.3-8 Two-Level Factorial Design Agglomeration Results for Pittsburgh # 8 Coal

Figure 5.3-9 Two-Level Factorial Design Agglomeration Results for Illinois # 6 Coal

Figure 5.3-10 Effect of Particle Size on Energy Recovery

Figure 5.3-11 Effect of Particle Size and Grinding Method on Energy Recovery

Figure 5.3-12 Effect of Grinding Method on Ash Rejection

Figure 5.3-13 Effect of Particle Size and Grinding Method on Ash Rejection

**Figure 5.4.1-1 SEM Micrographs of Dry Ground (200 mesh x 0)
Illinois # 6 (Top) and Pittsburgh # 8 (Bottom)
Coals**

**Figure 5.4.1-2 SEM Micrograph of Wet Ground
(200 mesh x 0) Pittsburgh # 8 Coal**

**Figure 5.4.1-3 SEM Micrograph of Wet Ground
(200 mesh x 0) Illinois # 6 Coal**

**Figure 5.4.1-4 SEM Micrograph of Dry Ground
(200 mesh x 0) Upper Freeport Coal**

**Figure 5.4.1-5 SEM Micrograph of Wet Ground
(200 mesh x 0) Upper Freeport Coal**

Figure 5.4.3-1 Comparison of LAMMA Results for 200 mesh x 0 Dry and Wet Ground Upper Freeport Coal Samples

Figure 5.4.3-2 Comparison of LAMMA Results for 200 mesh x 0 Dry and Wet Ground Pittsburgh #8 Coal Samples

Figure 5.4.3-3 Comparison of LAMMA Results for 200 mesh x 0
Dry and Wet Ground Illinois # 6 Coal Samples

Figure 5.4.3-4 Effect of Grinding Method on Surface Composition (LAMMA) for Upper Freeport Coal

Figure 5.4.6-1 pH Values of Dry and Wet Ground Upper Freeport Coal Slurries

Figure 5.4.6-2 pH Values of Dry and Wet Ground Pittsburgh # 8 Coal Slurries

Figure 5.4.6-3 pH Values of Dry and Wet Ground Illinois # 6 Coal Slurries

Figure 5.4.8-1 Comparisons of ICP Analysis Results on Filtrate Samples Obtained from Dry and Wet Ground 200 mesh x 0 Upper Freeport Coal

Figure 5.4.8-2 Comparisons of ICP Analysis Results on Filtrate Samples Obtained from Dry and Wet Ground 200 mesh x 0 Pittsburgh # 8 Coal

Figure 5.4.8-3 Comparisons of ICP Analysis Results on Filtrate Samples Obtained from Dry and Wet Ground 200 mesh x 0 Illinois # 6 Coal

Figure 5.5.1-1 Effect of Grinding in the Presence of Light Hydrocarbons on the Agglomeration Performance for Upper Freeport Coal

Figure 5.5.1-2 Effect of Grinding in the Presence of Light Hydrocarbons on the Agglomeration Performance for Pittsburgh #8 Coal

Figure 5.5.1-3 Effect of Grinding in the Presence of Light Hydrocarbons on the Agglomeration Performance for Illinois # 6 Coal

Figure 5.5.2.1-1 Effect of Grinding in the Presence of Light Hydrocarbons on the Oxidation Index for Illinois # 6 Coal

Figure 5.5.2.2-1 Effect of Grinding in the Presence of Light Hydrocarbons on the Surface Composition (LA-MA) for Illinois #6 Coal

Figure 5.5.2.2-2 Effect of Grinding in the Presence of Light Hydrocarbons on the Surface Composition (LAMMA) for Pittsburgh # 8 Coal

Figure 5.5.2.4-1 Effect of Grinding in the Presence of Hydrocarbons on Contact Angle for Upper Freeport Coal

Figure 6.1-1 Agglomeration Results for Upper Freeport Coal Wet Ground to 200 mesh x 0 in the Presence of Surfactants

Figure 6.1-2 Agglomeration Results for Pittsburgh # 8 Coal Wet Ground to 200 mesh x 0 in the Presence of Surfactants

Figure 6.1-3 Agglomeration Results for Illinois #6 Coal Wet Ground to 200 mesh x 0 in the Presence of Surfactants

Figure 6.1-4 LAMMA Results for Upper Freeport Coal Wet Ground to 200 mesh x 0 in the Presence of Aerosol-OT

Figure 6.1-5 Effect of Grinding in the Presence of Surfactants on Contact Angle for Upper Freeport Coal

Figure 6.2-1 Agglomeration Results for Upper Freeport Coal
with Alcohols Added Prior to Agglomeration

**Figure 6.2-2 Agglomeration Results for Pittsburgh # 8 Coal
with Alcohols Added Prior to Agglomeration**

**Figure 6.2-3 Agglomeration Results for Illinois # 6 Coal
with Alcohols Added Prior to Agglomeration**

Figure 6.2-4 LAMMA Results for Illinois #6 Coal with Methanol Added Prior to Agglomeration

Figure 6.2-5 Effect of Adding Alcohols on the Oxidation Index for Illinois # 6 Coal

Figure 6.2-6 Effect of Methanol on Advancing Contact Angle for the Three Base Coals

Figure 6.2-7 Effect of Ethanol on Advancing Contact Angle for the Three Base Coals

Figure 6.3-1 Agglomeration Results for Upper Freeport Coal Wet Ground to 200 mesh x 0 in the Presence of Monomers

Figure 6.3-2 Agglomeration Results for Pittsburgh #8 Coal Wet Ground to 200 mesh x 0 in the Presence of Monomers

Figure 6.3-3 Agglomeration Results for Illinois #6 Coal Wet Ground to 200 mesh x 0 in the Presence of Monomers

Figure 6.3-4 LAMMA Results for Illinois #6 Coal Wet Ground to 200 mesh x 0 in the Presence of Monomers

Figure 6.3-5 LAMMA Results for Pittsburgh # 8 Coal Wet Ground to 200 mesh x 0 with 200 ppm of Tall Oil

Figure 6.3-6 LAMMA Results for Illinois # 6 Coal Wet Ground to 200 mesh x 0 With 200 ppm of Tall Oil

Figure 6.3-7 Comparison Between Agglomeration Results and LAMMA Data for Pittsburgh # 8 Coal

Figure 6.3-8 Comparison of Oxidation Indices for Feed and Product Samples of 200 mesh x 0 Illinois #6 Coal Wet Ground With and Without Tail Oil

Figure 6.3-9 Comparison of Oxidation Indices for Samples of 200 mesh x 0 Pittsburgh # 8 Coal Wet Ground With and Without Tall Oil

Figure 6.3-10 Effect of Tall Oil on Zeta Potentials of the Three Base Coals at Various pH Values

Figure 6.3-11 Effect of Grinding in the Presence of Monomers on Contact Angle for Upper Freeport Coal

Figure 7.1.1-1 Overall Material Balance for Agglomeration Process

Figure 7.1.1-2 Ash Balance for Agglomeration Process

Figure 7.1.1-3 Total Sulfur Balance for Agglomeration Process

Figure 7.1.1-4 Inorganic Sulfur Balance for Agglomeration Process

Figure 7.1.2-1 Comparison Between LECO and ICP Sulfate Sulfur Analyses

Figure 7.1.2-2 Comparison Between LECO and ICP Pyritic Sulfur Analyses

Figure 7.1.3-1 ESCA SO_4^{2-} , S^{2-} , and Si Peaks for Pulverized (14 mesh x 0) Pittsburgh # 8 Coal

Figure 7.1.3-2 ESCA SO₄²⁻, S²⁻, and Si Peaks for Wet Ground (200 mesh x 0) Pittsburgh # 8 Coal.

Figure 7.1.3-3 ESCA Fe Peaks for Pittsburgh # 8 Coal

Figure 7.1.3-4 ESCA SO₄²⁻ and S²⁻ Peaks for Pulverized (60 mesh x 0) Illinois # 6 Coal

Figure 7.1.3-5 ESCA SO_4^{2-} , S^{2-} , and Si Peaks for Wet Ground (200 mesh x 0) Illinois # 6 Coal

Figure 7.1.3-6 ESCA Fe Peaks for Illinois #6 Coal

Figure 7.2.1-1 Effect of Agglomeration Time on the Agglomeration Performance for Upper Freeport Coal

Figure 7.2.1-2 Effect of Agglomeration Time on the Energy Recovery for Pittsburgh # 8 Coal

Figure 7.2.1-3 Effect of Agglomeration Time on the Agglomeration Performance for Illinois # 6 Coal (Slurry Concentration = 2 % by weight)

Figure 7.2.1-4 Effect of Agglomeration Time on the Agglomeration Performance for Illinois # 6 Coal (Slurry Concentration = 4 % by weight)

Figure 7.2.1-5 Effect of Agglomeration Time on Carbon, Oxygen, and Silicon Surface Concentrations for Illinois # 6 Coal (ESCA)

Figure 7.2.1-6 Effect of Agglomeration Time on Iron and Sulfur Surface Concentrations for Illinois # 6 Coal (ESCA)

Figure 7.2.1-7 Effect of Agglomeration Time on the Surface Composition (LAMMA) for Illinois #6 Coal

Figure 7.2.2-1 Effect of Grinding Method on the Energy Recovery for Pittsburgh #8 Coal

Figure 7.2.3-1 Effect of pH on the Ash Rejection for Illinois #6 Coal

Figure 7.2.4.1-1 LAMMA Results for Pittsburgh # 8 Coal Wet Ground to 200 mesh x 0

Figure 7.2.4.1-2 LAMMA Results for Illinois #6 Coal Wet Ground to 200 mesh x 0

Figure 7.2.4.2-1 Carbon, Oxygen, and Silicon Surface Concentrations for Agglomeration Tests Samples (ESCA)

Figure 7.2.4.2-2 Iron and Sulfur Surface Concentrations for Agglomeration Tests Samples (ESCA)

Figure 7.2.4.3-1 Oxidation Indices for the Three Base Coals

Figure 7.3.1-1 Comparison of Energy Recoveries and Pyritic Sulfur Rejections
Between Agglomerants for Upper Freeport Coal

Figure 7.3.1-2 Comparison Between Agglomerants for Pittsburgh #8 Coal

Figure 7.3.1-3 Effect of n-Heptane to Coal Ratio on the Agglomeration Performance for Illinois #6 Coal

Figure 7.3.2-1 Agglomeration Plus High-Shear Washing
Tests Results for Upper Freeport Coal

Figure 7.3.2-2 Agglomeration Plus High-Shear Washing Tests Results for Pittsburgh # 8 Coal

Figure 7.3.3.1-1 Effect of Lime Addition on the Agglomeration Performance for Pittsburgh #8 Coal

Figure 7.3.3.1-2 Effect of Lime on Surface Composition
(LAMMA) for Pittsburgh #8 Coal

Figure 7.3.4-1 Use of Tall Oil as Binder for Illinois #6 Coal

Figure 7.3.5-1 Effect of Sieve Size on the Agglomeration Process Performance for Illinois # 6 Coal

Figure 7.4-1 Particle Size Distribution for Upper Freeport Coal Wet Ground Using 7/32" Ceramic Balls

Figure 7.4-2 Particle Size Distribution for Pittsburgh # 8 Coal Wet Ground Using 7/32" Ceramic Balls

**Figure 7.4-3 Particle Size Distribution for Illinois # 6 Coal
Wet Ground Using 7/32" Ceramic Balls**

Figure 7.4-4 Average Particle Size (d_{50}) for the Three Base Coals Wet Ground Using 7/32" Ceramic Balls

Figure 7.4.1-1 Pyrite Association for Upper Freeport Coal
Wet Ground Using 7/32" Ceramic Balls

Figure 7.4.1-2 Pyrite Association for Pittsburgh # 8 Coal
Wet Ground Using 7/32" Ceramic Balls

Figure 7.4.1-3 Pyrite Association for Illinois # 6 Coal
Wet Ground Using 7/32" Ceramic Balls

Figure 7.4.2-1 Central Composite Design for $k = 3$

Figure 7.4.2-2 Effect of Grinding Time and pH on the Ash Rejection for Upper Freeport Coal

Figure 7.4.3-1 Effect of Agglomeration Time and Grinding Time on the Agglomeration Process Performance for Fine Ground Pittsburgh #8 Coal

Figure 7.4.3-2 Effect of pH and High-Shear Washing on the Agglomeration Process Performance for Fine Ground Pittsburgh #8 Coal

Figure 7.4.3-3 Effect of Grinding Time and pH on the Inorganic Sulfur Rejection for Pittsburgh # 8 Coal (Second Order Response Model)

Figure 7.4.3-4 Effect of Agglomeration Time and pH on the Inorganic Sulfur Rejection for Pittsburgh # 8 Coal (Second Order Response Model)

Figure 7.4.4-1 Particle Size Distribution of Illinois # 6 Coal Samples

Figure 7.4.4-2 Effect of Grinding Time on the Agglomeration Performance for Illinois # 6 Coal

Figure 7.4.4-3 Effect of the n-Heptane to Coal Ratio on the Agglomeration Process Performance for Fine Ground Illinois #6 Coal

**Figure 7.4.4-4 Effect of the pH on the Agglomeration Process
Performance for Fine Ground Illinois # 6 Coal**

Figure 7.6.2-1 Clean Coal Yield for Wyodak Coal

Figure 7.6.2-2 Ash Rejection for Wyodak Coal

Figure 7.6.2-3 Inorganic Sulfur Rejection for Wyodak Coal

— 100 microns

— 10 microns

Figure 7.8-1 Microagglomerates of Upper Freeport Coal (Dispersion Method). SEI Micrograph showing well defined, tight, round agglomerates, sometimes clustered (Bottom).

— 10 microns

— 10 microns

Figure 7.8-2 Microagglomerates of Upper Freeport Coal (Dispersion Method, SEI).

— 100 microns

— 100 microns

Figure 7.8-3 Freeze-dried Agglomerates of Upper Freeport Coal, BSE Imaging. The very white spots are pyrite particles.

100 microns

Figure 7.8-4 Microagglomerates of Illinois #6 Coal (Dispersion Method, Top: SEI, Bottom: BSE Imaging). Note the lack of cohesion of these agglomerates.

— 100 microns

**Figure 7.8-5 Microagglomerate of Illinois #6 Coal
(Dispersion Method, BSE Imaging).**

100 microns

Figure 7.8-6 Freeze-dried Agglomerates of Illinois #6 Coal
 (Top: SEI, Bottom: BSE Imaging of Same Area).
 Note the very open rough texture. Pyrite is
 white in lower micrograph.

— 100 microns

— 100 microns

Figure 7.8-7 Freeze-dried Agglomerate of Illinois # 6 Coal, BSE Imaging.

Figure 7.8-8 Microagglomerates of Pittsburgh # 8 Coal (Dispersion Method, SEI Mode). The microagglomerates are irregular and tend to aggregate together.

B-181

— 100 microns

Figure 7.8-10 Freeze-dried Agglomerates of Pittsburgh # 8 Coal. The Matrix is Tight in Texture and Fairly Continuous with Large Voids. Same Area in SEI (Top) and BSE Imaging (Bottom).

B-183

100 microns

Figure 7.8-12 Microagglomerates of Pittsburgh #8 Coal (Dispersion Method, SEI Mode) Prepared Using a n-Heptane to Coal Ratio of 0.05 and an Agglomeration Time of 60 s.

100 microns

Figure 7.8-13 Microagglomerates of Pittsburgh #8 Coal (Dispersion Method, SEI Mode) Prepared Using a n-Heptane to Coal Ratio of 0.10 and an Agglomeration Time of 60 s.

100 microns

Figure 7.8-14 Microagglomerates of Pittsburgh #8 Coal (Dispersion Method, SEI Mode) Prepared Using a n-Heptane to Coal Ratio of 0.20 and an Agglomeration Time of 60 s.

100 microns

Figure 7.8-15 Microagglomerates of Pittsburgh #8 Coal (Dispersion Method, SEI Mode) Prepared Using a n-Heptane to Coal Ratio of 0.50 and an Agglomeration Time of 60 s.

100 microns

Figure 7.8-16 Microagglomerates of Pittsburgh #8 Coal (Dispersion Method, SEI Mode) Prepared Using a n-Heptane to Coal Ratio of 0.50 and an Agglomeration Time of 15 s.

100 microns

Figure 7.8-17 Microagglomerates of Pittsburgh #8 Coal (Dispersion Method, SEI Mode) Prepared Using a n-Heptane to Coal Ratio of 0.50 and an Agglomeration Time of 120 s.

Figure 7.9-1 Contact Angle Measurement

Figure 7.10-1 XRD Determination of Pyrite

APPENDIX C: PYRITE SIZE DISTRIBUTION CALCULATION

APPENDIX C: PYRITE SIZE DISTRIBUTION CALCULATION

The following discussion is a summary from Chapter 5 of "Quantitative Stereology" by E. E. Underwood⁽⁶⁾.

The plane intersection of a polydispersed system of spheres results in circular sections with a distribution of sizes, even in the case of spheres of uniform diameter. In the case of spheres with different diameters, d_j , d_{j+1} , d_{j+2} , etc., each size contributes circular sections of size d_i ($d_i \leq d_j$). If the polydispersed system of spheres is divided into size intervals, the observed number of sections of diameter d_i , $(N_A)_i$, is the sum of the contributions from intervals containing spheres with diameter equal or larger than d_i . This statement can be expressed as

$$(N_A)_i = \sum_{j=i}^N (N_A)_{ij} \quad (1)$$

where $(N_A)_{ij}$ is the number per unit area of circles of size d_i obtained from spheres of size d_j and N is the number of intervals. For each interval, the number of spheres of diameter d_j per unit volume, $(N_V)_j$, can be written as

$$(N_V)_j = \sum_i (N_A)_{ij} / d_j \quad (2)$$

In order to determine how many circular sections of each size come from spheres in each size interval, the probability of random planes intersecting a sphere must be obtained. If P_{ij} is the probability of a test plane intersecting a sphere of diameter d_j to yield sections of diameter d_i , then

$$P_{ij} = (N_A)_{ij} / \sum_i (N_A)_{ij} \quad (3)$$

Substituting equation 3 into 2 gives the general expression

$$(N_V)_j = \frac{(N_A)_{ij}}{P_{ij} d_j} \quad (4)$$

from which $(N_V)_j$ may be determined. The calculation of P_{ij} is based on simple geometrical considerations. The probability of a plane randomly cutting a sphere within a slice of height h , as shown in Figure C-1, is equal to

$$P_{ij} = \frac{h}{d_j/2} = \frac{h_{i-1} - h_i}{d_j/2} \quad (5)$$

The probability may be expressed in terms of the diameters, as

$$P_{ij} = [\sqrt{(d_j)^2 - (d_{i-1})^2} - \sqrt{(d_j)^2 - (d_i)^2}] / d_j \quad (6)$$

It is immaterial whether a random plane intersects one sphere many times or if many identical spheres are intersected by one plane.

The values of $(N_V)_j$ can be obtained by first calculating $(N_V)_N$ from the above equations for $i = j = N$, as

$$(N_V)_N = \frac{(N_A)_{N,N}}{P_{N,N} d_N} = \frac{(N_A)_N}{P_{N,N} d_N} = \frac{(N_A)_N}{\sqrt{(d_N)^2 - (d_{N-1})^2}} \quad (7)$$

The value of $(N_V)_N$ is then used to determine $(N_A)_{N-1,N-1}$ using equation 1 for $i = N-1$, as

$$(N_A)_{ii} = (N_A)_i - \sum_{j=i+1}^N (N_V)_j P_{ij} d_j \quad (8)$$

$(N_V)_{N-1}$ is then determined using equation 4 for $i = j = N-1$, as

$$(N_V)_i = \frac{(N_A)_{ii}}{P_{ii} d_i} \quad (9)$$

The same procedure is continued down to the smallest particle size. It can be seen that each subtracted term depends on previously calculated values and that the number of smaller particles may be inaccurate because of accumulated errors.

The frequency distribution can then be converted into volume distribution using

$$V_i = \frac{(N_V)_i (d_i)^3}{\sum (N_V)_i (d_i)^3} \quad (10)$$

where V_i is the volume fraction of particles in the diameter interval i .

Figure C-1 Geometry Involved in the Intersection of a Sphere by a Plane Within the Slice h

A computer program based on the above equations was written in BASIC to determine the three-dimensional frequency distribution of sizes for pyrite. The program calculates the volume distributions for locked, semi-locked, and free pyrite particles. A listing of the program is presented next.

Pyrite Size Distribution Program

```
' Transformation from Area Number Distribution to Volume Distribution
'
' Nomenclature
'
' d    diameter
' n    number of diameters
' na   2-D number distribution
' nv   3-D number distribution
' pyrtype$ pyrite type
' v    volume distribution
'
DIM d(50, 3), na(50, 3), nv(50, 3), n(3)
DIM v(50, 3), pyrtype$(3)
'
pyrtype$(1) = "Locked"
pyrtype$(2) = "Semi-Locked"
pyrtype$(3) = "Free"
'
FOR k = 1 TO 3
  d(0, k) = 0
NEXT
'
CLS : LOCATE 3, 10
INPUT "Enter data file name > ", ifn$
OPEN ifn$ FOR INPUT AS #1
'
FOR k = 1 TO 3
  INPUT #1, n(k)
  n = n(k)
  FOR i = 1 TO n
    INPUT #1, d(i, k), na(i, k)
  NEXT
'
nv(n, k) = na(n, k) / SQR(d(n, k) * d(n, k) - d(n - 1, k) * d(n - 1, k))
FOR i = n - 1 TO 1 STEP -1
  nv(i, k) = na(i, k)
  FOR j = n TO i + 1 STEP -1
    nterm = nv(j, k) * (SQR(d(j, k) * d(j, k) - d(i - 1, k) * d(i - 1, k)) - SQR(d(j, k) * d(j, k) - d(i, k) * d(i, k)))
    nv(i, k) = nv(i, k) - nterm
  NEXT
  nv(i, k) = nv(i, k) / SQR(d(i, k) * d(i, k) - d(i - 1, k) * d(i - 1, k))
NEXT
NEXT
```



```

'
sumnv = 0
FOR k = 1 TO 3
  FOR i = 1 TO n(k)
    sumnv = sumnv + nv(i, k)
  NEXT
NEXT
'
sumv = 0
FOR k = 1 TO 3
  FOR i = 1 TO n(k)
    nv(i, k) = 100 * nv(i, k) / sumnv
    v(i, k) = nv(i, k) * d(i, k) * d(i, k) * d(i, k)
    sumv = sumv + v(i, k)
  NEXT
NEXT
'
FOR k = 1 TO 3
  FOR i = 1 TO n(k)
    v(i, k) = 100 * v(i, k) / sumv
  NEXT
NEXT
'
LOCATE 5, 10: INPUT "Enter results file name > ", rfn$
OPEN rfn$ FOR OUTPUT AS #2
PRINT #2, "Data file name: "; ifn$: PRINT #2,
PRINT #2, " Size, 2-D Frequency 3-D Frequency Volume"
PRINT #2, " micron Distribution, % Distribution, % Distribution, %"

FOR k = 1 TO 3
  PRINT #2, : PRINT #2, pyrtype$(k): PRINT #2,
  FOR i = 1 TO n(k)
    PRINT #2, USING " ###.# ###.## ###.## ###.##"; d(i, k); na(i, k); nv(i, k); v(i, k)
  NEXT
NEXT
'
END

```

**APPENDIX D: TWO-LEVEL FACTORIAL DESIGN
AGGLOMERATION TEST RESULTS**

NOMENCLATURE

1. Af: Ash Content of Feed Coal (%)
2. Ap: Ash Content of Product Coal (%)
3. Ar: Ash Content of Refuse (%)
4. ARD: Ash Reduction (%)
$$ARD = (1 - Ap/Af) \times 100$$
5. ARJ: Ash Rejection (%)
$$ARJ = 100 - Y \times Ap / Af$$
6. (Btu)f: Calorific Value of Feed (Btu/lb)
7. (Btu)p: Calorific Value of Product (Btu/lb)
8. BTU: Btu Recovery (%)
$$BTU = (Btu)p / (Btu)f \times Y$$
9. C: Coal Slurry Concentration (Wt.%)
10. N: Mixing Speed (rpm)
11. P: Product Coal Weight (g)
12. PCR: Pentane/Coal Ratio (Weight Basis)
13. PSf: Pyritic Sulfur Content of Feed (%)
14. PSp: Pyritic Sulfur Content of Product (%)
15. PSRJ: Pyritic Sulfur Rejection (%)
$$PSRJ = 100 - Y \times PSp / PSf$$
16. R: Refuse Weight (g)
17. Sf: Total Sulfur Content in the Feed (%)
18. Sp: Total Sulfur Content in the Product (%)
19. SRJ: Total Sulfur Rejection (%)
$$SRJ = 100 - Y \times Sp / Sf$$
20. T: Agglomeration Time (s)
21. Y: Overall Yield (%)
$$Y = P / (P + R) \times 100$$
22. Yc: Clean Coal Yield (%)
$$Yc = Y \times (100 - Ap) / (100 - Af)$$

RUN # DESIGNATION

Coal	Dry Ground		Wet Ground	
	With Splitter		Without Splitter	
Illinois #6 Randolph, IL	W ^a -#-16	WWS ^a -#-16	WWS ^a -#-16	
Pittsburgh #8 Belmont, OH	W ^a -#-P8	WWS ^a -#-P8	WWS ^a -#-P8	
Upper Freeport Indiana, PA	W ^a -#-UI	WWS ^a -#-UI	WWS ^a -#-UI	

*: Work Number given in the original work plan

#: Number for repeat run

Illinois # 6 Coal, 28 mesh x 0

Run #	C (%)	PCR (-)	T (s)	N (rpm)	P (g)	R (g)	Af 15.65		Sf 4.51 3.12		Y (%)	ARJ (%)	ARD (%)	SRJ (%)	PSRJ (%)	Yc (%)	BTU (%)
							Ap (%)	Ar (%)	Sp (%)	PSP (%)							
W1-1-16	2	0.50	15	9238	2.9153	5.7466	8.13	15.80			33.7	82.5	48.1			36.7	37.1
W1-2-16	2	0.50	15	9114	3.3550	5.4113	8.45	16.58	3.24		38.3	79.3	46.0	72.5		41.5	42.1
WWS1-1-16	2	0.50	15	9393	2.4485	7.8025	9.32	16.38			23.9	85.8	40.4			25.7	26.0
WWS1-2-16	2	0.50	15	9331	3.0482	4.8160	8.04	17.04			38.8	80.1	48.6			42.3	42.8
WWS1-3-16	2	0.50	15	8959	2.2711	5.7802	7.98	15.04	3.09		28.2	85.6	49.0	80.7		30.8	31.2
W2-1-16	2	0.50	30	13702	2.9700	5.3796	6.89	16.49			35.6	84.3	56.0			39.3	39.8
W2-2-16	2	0.50	30	13671	3.4245	4.9870	7.72	16.17	3.34		40.7	79.9	50.7	69.8		44.5	45.1
WWS2-1-16	2	0.50	30	14229	1.7310	5.2860	7.57	15.03			24.7	88.1	51.6			27.0	27.4
WWS2-2-16	2	0.50	30	13826	2.9107	5.7100	8.02	15.31	3.43		33.8	82.7	48.8	74.3		36.8	37.3
W3-1-16	2	1.00	30	9269	3.4693	5.6845	7.54	17.67			37.9	81.7	51.8			41.5	42.1
W3-2-16	2	1.00	30	9176	3.7643	4.9600	8.15	17.29	3.15		43.1	77.5	47.9	69.9		47.0	47.6
WWS3-1-16	2	1.00	30	9238	2.4585	5.3990	7.95	13.80			31.3	84.1	49.2			34.1	34.6
WWS3-2-16	2	1.00	30	9362	4.6904	4.6904	8.64	18.04	3.59		50.0	72.4	44.8	60.2		54.2	54.8
WWS3-3-16	2	1.00	30	8959	2.2290	4.9605	8.55	16.16			31.0	83.1	45.4			33.6	34.0
W4-1-16	2	1.00	15	13454	2.8755	5.4482	7.75	16.78	3.14		34.5	82.9	50.5	75.9		37.8	38.3
W4-2-16	2	1.00	15	13720	2.9744	5.3375	8.16	16.56			35.8	81.3	47.9			39.0	39.5
WWS4-1-16	2	1.00	15	13857	2.7340	6.5475	8.88	17.18	3.48		29.5	83.3	43.3	77.3		31.8	32.2

Illinois # 6 Coal, 28 mesh x 0

Run #	C (%)	PCR (-)	T (s)	M (rpm)	P (g)	R (g)	Ap (%)	Ar (%)	Sp (%)	PSP (%)	Y (%)	ARJ (%)	ARD (%)	SRJ (%)	PSRJ (%)	Yc (%)	BTU (%)
W5-1-16	4	0.50	30	9207	6.6015	11.3064	8.53	18.39			36.9	79.9	45.5			40.0	40.5
W5-2-16	4	0.50	30	9362	7.3157	10.3724	9.58	18.08	3.25		41.4	74.7	38.8	70.2		44.3	44.8
WWS5-1-16	4	0.50	30	9207	7.7710	10.1330	8.50	19.04	3.45	2.29	43.4	76.4	45.7	66.8	68.9	47.1	47.7
WWS5-2-16	4	0.50	30	9269	5.0380	12.8870	7.85	17.83			28.1	85.9	49.8			30.7	31.1
WWS5-3-16	4	0.50	30	9362	6.0100	11.0200	8.52	17.23			35.3	80.8	45.6			38.3	38.7
W6-1-16	4	0.50	15	14384	7.3082	10.2595	8.55	19.40	3.34		41.6	77.3	45.4	69.2		45.1	45.7
W6-2-16	4	0.50	15	14640	6.5450	11.0997	7.87	17.29	3.25		37.1	81.3	49.7	73.3		40.5	41.1
WWS6-1-16	4	0.50	15	13919	4.1970	14.1080	8.29	17.20			22.9	87.9	47.0			24.9	25.2
WWS6-2-16	4	0.50	15	13826	5.8940	13.9760	9.45	18.10			29.7	82.1	39.6			31.8	32.2
WWS6-3-16	4	0.50	15	14012	5.8100	12.9200	9.20	16.21	3.44	2.15	31.0	81.8	41.2	76.3	79.1	33.4	33.8
W7-1-16	4	1.00	15	9207	7.2285	11.1715	8.43	17.63	3.26		39.3	78.8	46.1	71.6		42.6	43.2
WWS7-1-16	4	1.00	15	8959	5.6560	12.3200	8.09	16.48			31.5	83.7	48.3			34.3	34.7
WWS7-2-16	4	1.00	15	9021	7.2400	9.8100	7.99	17.52	3.22	1.98	42.5	78.3	48.9	69.7	73.8	46.3	46.9
W8-1-16	4	1.00	30	13733	8.0120	10.4888	8.06	19.09	3.31		43.3	77.7	48.5	68.2		47.2	47.8
WWS8-1-16	4	1.00	30	13981	6.5052	11.1780	8.57	17.21			36.8	79.9	45.2			39.9	40.4
WWS8-2-16	4	1.00	30	13950	5.9100	12.6100	8.23	15.81	3.33	2.18	31.9	83.2	47.4	76.4	78.3	34.7	35.2

Illinois # 6 Coal, 200 mesh x 0

Run #	C (%)	PCR (-)	T (s)	N (rpm)	P (g)	R (g)	Af		Sf		PSf		SRJ (%)	PSRJ (%)	Yc (%)	BTU (%)
							Ap (%)	Ar (%)	Sp (%)	Psp (%)	Y (%)	ARJ (%)				
							16.31		4.59	3.49						(Btu)f 11132
W9-1-16	2	0.50	30	8959	5.8400	3.0464	12.17	21.08			65.7	51.0	25.4		69.0	69.5
W9-2-16	2	0.50	30	8556	5.9735	3.0125	12.25	21.08	4.19		66.5	50.1	24.9	39.3	69.7	70.2
W9-1-16	2	0.50	30	9393	6.0907	2.5322	5.60	31.85	2.71		70.6	75.7	65.7	58.3	79.7	81.1
W9-1-16	2	0.50	30	9393	6.1085	4.1785	5.23	25.11	2.84	1.62	59.4	81.0	67.9	63.3	72.4	68.5
W10-1-16	2	0.50	15	13423	5.8051	2.8738	12.17	21.01			66.9	50.1	25.4		70.2	70.7
W10-2-16	2	0.50	15	13826	6.0611	2.8590	12.20	21.04	4.22		67.9	49.2	25.2	37.5	71.3	71.8
W10-1-16	2	0.50	15	13981	5.9980	2.5810	5.49	31.64	2.78		69.9	76.5	66.3	57.7	79.0	80.4
W10-1-16	2	0.50	15	13919	6.9785	3.7365	6.30	29.05	3.23	1.90	65.1	74.8	61.4	54.2	72.9	74.2
W11-1-16	2	1.00	15	9025	5.9839	2.6692	12.26	20.71			69.2	48.0	24.8		72.5	73.0
W11-2-16	2	1.00	15	9025	6.5880	2.9996	12.38	21.00	4.22		68.7	47.8	24.1	36.8	71.9	72.5
W11-1-16	2	1.00	15	8990	6.0905	2.4313	5.32	34.52	2.51		71.5	76.7	67.4	60.9	80.9	82.3
W11-1-16	2	1.00	15	9300	9.0320	3.4375	5.75	32.94	3.04	1.66	72.4	74.5	64.7	52.0	81.6	83.0
W12-1-16	2	1.00	30	13578	6.0990	2.5774	11.80	20.27	4.22		70.3	49.1	27.7	35.4	74.1	74.7
W12-1-16	2	1.00	30	13423	6.0935	2.7493	11.98	20.71			68.9	49.4	26.5		72.5	73.0
W12-1-16	2	1.00	30	14260	6.3900	1.9235	5.77	37.20	2.83		76.9	72.8	64.6	52.6	86.5	88.1
W12-1-16	2	1.00	30	14105	7.5935	3.0080	5.93	36.77	3.22		71.6	74.0	63.6	49.8	80.5	81.9

Illinois # 6 Coal, 200 mesh x 0

Run #	C (%)	PCR (-)	T (s)	N (rpm)	P (g)	R (g)	Ap (%)	Ar (%)	Sp (%)	Psp (%)	V (%)	ARJ (%)	ARO (%)	SRJ (%)	PSRJ (%)	Yc (%)	BTU (%)
W13-1-16	4	0.50	15	9083	13.6600	4.8584	13.09	20.82	4.31		73.8	40.8	19.7	30.7		76.6	77.1
W13-2-16	4	0.50	15	9238	14.4845	5.2766	12.91	20.90			73.3	42.0	20.8			76.3	76.7
W13-1-16	4	0.50	15	9300	12.8588	4.5305	8.07	30.37	2.87		73.9	63.4	50.5	53.8		81.2	82.4
W13-1-16	4	0.50	15	9269	12.2500	6.9800	7.98	24.62	3.10	1.94	63.7	68.8	51.1	57.0	64.5	70.0	71.0
W14-1-16	4	0.50	30	13609	13.3069	3.9568	12.88	22.68	4.32		77.1	39.1	21.0	27.5		80.2	80.7
W14-2-16	4	0.50	30	13857	14.4308	5.2284	12.64	21.19			73.4	43.1	22.5			76.6	77.1
W14-1-16	4	0.50	30	14477	12.7345	4.3718	8.24	29.74	2.91		74.4	62.4	49.5	52.8		81.6	82.8
W15-1-16	4	1.00	30	9021	14.1348	3.9978	12.85	21.94	4.30		78.0	38.6	21.2	27.0		81.2	81.7
W15-1-16	4	1.00	30	8959	13.1675	3.9460	7.90	32.17	2.77		76.9	62.7	51.6	53.6		84.7	85.9
W15-1-16	4	1.00	30	9145	14.6100	4.7500	8.74	20.67	3.52		75.5	59.6	46.4	42.1		82.3	83.4
W16-1-16	4	1.00	15	13485	13.8700	4.5178	12.94	21.19	4.32		75.4	40.2	20.7	29.0		78.5	79.0
W16-1-16	4	1.00	15	14446	12.8799	4.4500	8.56	29.26	2.97		74.3	61.0	47.5	51.9		81.2	82.3

per Freeport Coal, 28 mesh x 0

Run #	C (%)	PCR (-)	T (s)	M (rpm)	P (g)	R (g)	Af		Sf		Psf		Y (%)	ARJ (%)	ARD (%)	SRJ (%)	PSRJ (%)	Yc (%)	(Btu)f 13380
							Ap (%)	Ar (%)	Sp (%)	Psp (%)	Y (%)	ARJ (%)							
11.78							11.78		2.19	1.66									
W1-1-UI	2	0.50	15	930	7.2563	1.3524	8.71	22.57	1.68		84.3	37.7	26.1	35.3				87.2	87.7
WMS1-1-UI	2	0.50	15	9517	8.6855	0.7130	8.75	35.32	1.25		92.4	31.4	25.7	47.3				95.6	96.1
W2-1-UI	2	0.50	30	14102	8.1607	0.6412	9.00	27.60	1.86		92.7	29.2	23.6	21.3				95.6	96.1
WMS2-1-UI	2	0.50	30	13950	8.0200	0.5290	8.70	41.50	1.24	0.72	93.8	30.7	26.1	46.9	59.4			97.1	97.6
WMS2-2-UI	2	0.50	30	14322	6.3500	0.4355	7.79	32.40			93.6	38.1	33.9					97.8	98.5
WMS2-2-UI	2	0.50	30	13888	7.4800	0.5230	7.46	37.71			93.5	40.8	36.7					98.0	98.8
WMS2-4-UI	2	0.50	30	13950	7.7516	0.7910	8.92	35.20			90.7	31.3	24.3					93.7	94.2
W3-1-UI	2	0.25	30	9362	7.6100	1.9380	8.47	21.85	1.70		79.7	42.7	28.1	38.1				82.7	83.2
WMS3-1-UI	2	0.25	30	9300	5.6950	1.6120	8.42	23.41	1.47	0.75	77.9	44.3	28.5	47.7	64.7			80.9	81.4
WMS3-2-UI	2	0.25	30	930	7.0125	1.3020	9.94	25.11			84.3	28.8	15.6					86.1	86.4
W4-1-UI	2	0.25	15	13826	7.7434	1.7130	9.15	22.43	1.79		81.9	36.4	22.3	33.1				84.3	84.7
WMS4-1-UI	2	0.25	15	13886	7.3680	1.2160	7.64	23.11	1.22	0.61	85.8	44.2	35.1	52.2	68.6			89.9	90.5
W5-1-UI	4	0.50	30	9238	17.0200	1.9800	9.41	28.49	1.90		89.6	28.4	20.1	22.3				92.0	92.4
WMS5-1-UI	4	0.50	30	9300	16.7680	1.0105	8.63	39.64	1.40	0.85	94.3	30.9	26.7	39.7	51.7			97.7	98.3
W6-1-UI	4	0.50	15	14167	16.5200	2.2500	8.93	26.31	1.78		88.0	33.3	24.2	28.5				90.9	91.3
WMS6-1-UI	4	0.50	15	14074	17.2840	1.5260	9.59	35.88	1.32	0.73	91.9	25.2	18.6	44.6	59.6			94.2	94.6
W7-1-UI	4	0.25	15	9207	16.0506	2.9980	8.80	26.96	1.52		84.3	37.0	25.3	41.5				87.1	87.6
WMS7-1-UI	4	0.25	15	9269	16.0230	1.5295	8.86	32.59	1.26	0.67	91.3	31.3	24.8	47.5	63.2			94.3	94.8
W8-1-UI	4	0.25	30	13764	17.4260	1.5560	9.52	31.60	1.74		91.8	25.8	19.2	27.1				94.2	94.6
WMS8-1-UI	4	0.25	30	13919	16.8920	1.3450	8.95	34.16	1.47		92.6	29.6	24.0	37.8				95.6	96.1

Upper Freeport Coal, 200 mesh x 0

Run #	C (%)	PCR (-)	T (s)	N (rpm)	P (g)	R (g)	Ap (%)	Ar (%)	Sp (%)	Psp (%)	Y (%)	ARJ (%)	ARD (%)	SRJ (%)	PSRJ (%)	Yc (%)	BTU (%)	(Btu)f 13330
							12.06		Sf 2.20	PSf 1.70								
W9-1-UI	2	0.50	30	9672	9.5400	0.1200	11.20		2.12		98.8	8.3		6.1		99.7	99.9	
W9-1-UI	2	0.50	30	9331	9.0419	0.9080	5.65	73.28	1.02	0.53	90.9	57.4	53.2	58.4	71.4	97.5	98.6	
W10-1-UI	2	0.50	15	14074	9.2400	0.0300	11.19		2.14		99.7	7.5	7.2	4.3		>99.9	>99.9	
W10-1-UI	2	0.50	15	13764	8.3420	0.7607	5.46	71.35	1.08	0.73	91.6	58.5	54.7	55.6	60.3	98.5	99.7	
W11-1-UI	2	0.25	15	9331	9.0760	0.4765	11.05	23.10	2.06		95.0	12.9	8.4	12.2		96.1	96.3	
W11-1-UI	2	0.25	15	9269	7.8887	1.0220	4.98	60.17	1.07	0.56	88.5	63.4	58.7	57.5	71.0	95.7	96.9	
W12-1-UI	2	0.25	30	14105	8.8337	0.6429	10.89	21.50	2.04		93.2	15.8	9.7	14.7		94.5	94.7	
W12-1-UI	2	0.25	30	13919	7.2880	1.6027	5.51	39.24	1.16	0.70	82.0	62.5	54.3	57.4	66.4	88.1	89.1	
W13-1-UI	4	0.50	15	8990	19.3600	0.0800	11.34		2.13		99.6	6.4	6.0	4.9		>99.9	>99.9	
W13-1-UI	4	0.50	15	9300	18.1057	1.6553	5.67	72.60	1.09		91.6	56.9	53.0	55.2		98.3	99.4	
W14-1-UI	4	0.50	30	13640	19.5100	0.0700	11.38		2.12		99.6	6.0	5.6	5.3		>99.9	>99.9	
W14-1-UI	4	0.50	30	14074	18.4395	1.8982	5.62	69.88	1.07		90.7	57.7	53.4	56.5		97.3	98.4	
W15-1-UI	4	0.25	30	9362	19.2919	0.2835	11.34		2.14		98.6	7.3	6.0	5.4		99.4	99.5	
W15-1-UI	4	0.25	30	9021	18.1620	1.7125	6.54	63.95	1.21	0.77	91.4	50.4	45.8	50.4	58.7	97.1	98.1	
W16-1-UI	4	0.25	15	14198	19.1831	0.0793	11.18		2.08		99.6	7.7	7.3	7.1		>99.9	>99.9	
W16-1-UI	4	0.25	15	14260	15.0352	1.5542	6.13	65.27	1.01	0.59	90.6	53.9	49.2	59.0	68.2	96.7	97.8	

Pittsburgh # 8 Coal, 28 mesh x 0

Run #	C (%)	PCR (-)	T (s)	N (rpm)	P (g)	R (g)	Af			Sf			PSf			SRJ (%)	PSRJ (%)	Yc (%)	BTU (%)
							12.33	3.74	2.92	12.33	3.74	2.92	12.33	3.74	2.92				
U1-1-P8	2	0.50	15	9238	5.4638	3.3866	5.97	18.02					61.7	70.1	51.6			66.2	66.9
U1-2-P8	2	0.50	15	9114	5.5348	3.6374	6.47	17.48	2.54				60.3	68.3	47.5	59.0		64.4	65.0
WMS1-1-P8	2	0.50	15	9393	4.0970	4.4115	7.07	13.19	2.69	1.96			48.2	72.4	42.7	65.4	67.7	51.0	51.5
U2-1-P8	2	0.50	30	13702	5.6422	3.5309	6.58	18.71					61.5	67.2	46.6			65.5	66.2
U2-2-P8	2	0.50	30	13671	5.9110	3.4630	6.55	17.33	2.77				63.1	66.5	46.9	53.3		67.2	67.9
WMS2-1-P8	2	0.50	30	13702	5.0265	4.1213	5.92	14.85	2.88	2.15			54.9	73.6	52.0	57.7	59.5	59.0	59.6
U3-1-P8	2	1.00	30	9269	6.1792	3.0625	7.06	18.12					66.9	61.7	42.7			70.9	71.5
U3-2-P8	2	1.00	30	9176	6.0815	2.9810	6.92	17.39	2.70				67.1	62.3	43.9	51.6		71.2	71.9
WMS3-1-P8	2	1.00	30	9331	4.7760	5.1145	6.38	13.82	2.39	1.83			48.3	75.0	48.3	69.1	69.7	51.6	52.1
U4-1-P8	2	1.00	15	13454	5.8628	3.3322	6.47	19.08					63.8	66.5	47.5			68.0	68.7
U4-2-P8	2	1.00	15	13720	5.6257	3.6162	6.26	18.55	2.68				60.9	69.1	49.2	56.4		65.1	65.7
WMS4-1-P8	2	1.00	15	13671	4.0855	3.8303	6.49	13.33	2.86	2.09			51.6	72.8	47.4	60.5	63.0	55.1	55.6
U5-1-P8	4	0.50	30	9207	10.9200	7.3970	6.86	17.59					59.6	66.8	44.4			63.3	63.9
U5-2-P8	4	0.50	30	9362	10.7009	8.0622	6.56	17.21	2.74				57.0	69.7	46.8	58.2		60.8	61.4
WMS5-1-P8	4	0.50	30	9269	8.4515	11.0999	6.49	13.22	2.27	1.55			43.2	77.2	47.4	73.8	77.0	46.1	46.6
U6-1-P8	4	0.50	15	14384	10.5023	8.1562	6.77	16.78	2.86				56.3	69.1	45.1	57.0		59.9	60.4
U6-2-P8	4	0.50	15	14640	11.8042	8.3161	6.86	17.63					58.7	67.4	44.4			62.3	62.9
WMS6-1-P8	4	0.50	15	13671	8.8959	10.8045	6.74	13.71	2.62	1.78			45.2	75.3	45.3	68.4	72.5	48.0	48.5
U7-1-P8	4	1.00	15	9207	11.5280	6.6606	6.77	18.57	2.81				63.4	65.2	45.1	52.4		67.4	68.0
WMS7-1-P8	4	1.00	15	9362	9.3134	7.1590	6.41	15.26	2.39	1.71			56.5	70.6	48.0	63.9	66.8	60.4	60.9
U8-1-P8	4	1.00	30	13733	12.5628	5.9581	6.80	18.89	2.80				67.8	62.6	44.8	49.2		72.1	72.8
WMS8-1-P8	4	1.00	30	13702	9.5644	7.8575	6.87	14.68	2.92	2.14			54.9	69.4	44.3	57.1	59.7	58.3	58.8

Pittsburgh # 8 Coal, 200 mesh x 0

Run #	C (%)	PCR (-)	T (s)	N (rpm)	P (g)	R (g)	Af		Sf		Psf		Y (%)	ARJ (%)	ARD (%)	SRJ (%)	PSRJ (%)	Yc (%)	BTU (%)
							Ap (%)	Ar (%)	Sp (%)	Psp (%)									
							12.72		3.76	2.99									12307
W9-1-P8	2	0.50	30	9827	7.3225	1.6026	11.30	14.36	3.48		82.0	27.1	11.2	24.1		83.4	83.6		
W9-2-P8	2	0.50	30	9548	7.3339	1.6455	11.49	13.75			81.7	26.2	9.7			82.8	83.0		
W10-1-P8	2	0.50	15	14012	7.1027	1.9542	11.49	14.55			78.4	29.2	9.7			79.5	79.7		
W10-2-P8	2	0.50	15	13826	6.9366	2.1190	11.54	13.77	3.46		76.6	30.5	9.3	29.5		77.6	77.8		
W10-1-P8	2	0.50	15	13981	7.7750	1.2767	3.74	40.74	1.95		85.9	74.7	70.6	55.5		94.7	96.1		
W10-1-P8	2	0.50	15	14229	4.5042	0.8615	3.59	46.60	1.86		83.9	76.3	71.8	58.5		92.7	94.1		
W11-1-P8	2	1.00	15	9455	7.3880	1.4343	11.69	14.41	3.42		83.7	23.0	8.1	23.8		84.7	84.9		
W11-2-P8	2	1.00	15	9424	7.3726	1.4594	11.51	14.51			83.5	24.5	9.5			84.6	84.8		
W12-1-P8	2	1.00	30	13981	7.7311	1.2766	11.48	15.91	3.50		85.8	22.5	9.7	20.1		87.0	87.2		
W13-1-P8	4	0.50	15	9424	13.7423	4.7908	11.54	13.88	3.49		74.2	32.7	9.3	31.2		75.2	75.3		
W13-2-P8	4	0.50	15	9331	13.5295	5.1010	11.60	13.98			72.6	33.8	8.8			73.6	73.7		
W13-1-P8	4	0.50	15	9300	14.1700	4.6010	4.96	23.20	2.31		75.5	70.6	61.0	53.6		82.2	83.2		
W13-1-P8	4	0.50	15	9486	14.2320	4.7100	5.99	23.11	2.27	1.49	75.1	64.6	52.9	54.6	62.4	80.9	81.8		
W14-1-P8	4	0.50	30	13888	15.1007	3.0243	11.50	14.09	3.47		83.3	24.7	9.6	23.1		84.5	84.7		
W14-2-P8	4	0.50	30	14043	15.3300	3.0000	11.37	14.68			83.6	25.2	10.6			84.9	85.1		
W15-1-P8	4	1.00	30	9331	15.1200	3.0300	11.42	14.57	3.48		83.3	25.2	10.2	22.9		84.5	84.7		
W16-1-P8	4	1.00	15	13950	15.5700	2.6400	11.65	14.68	3.46		85.5	21.7	8.4	21.3		86.6	86.7		

**APPENDIX E: AGGLOMERATION TEST RESULTS USING
LIGHT HYDROCARBONS DURING GRINDING**

NOMENCLATURE

1. Af: Ash Content of Feed Coal (%)
2. Ap: Ash Content of Product Coal (%)
3. Ar: Ash Content of Refuse (%)
4. ARD: Ash Reduction (%)
$$ARD = (1 - Ap / Af) \times 100$$
5. ARJ: Ash Rejection (%)
$$ARJ = 100 - Y \times Ap / Af$$
6. (Btu)f: Calorific Value of Feed (Btu/lb)
7. (Btu)p: Calorific Value of Product (Btu/lb)
$$BTU = (Btu)p / (Btu)f \times Y$$
8. BTU: Btu Recovery (%)
$$BTU = (Btu)p / (Btu)f \times Y$$
9. C: Coal Slurry Concentration (Wt.%)
10. N: Mixing Speed (rpm)
11. P: Product Coal Weight (g)
12. PCR: Pentane/Coal Ratio (Weight Basis)
$$Yc = Y \times (100 - Ap) / (100 - Af)$$
13. PSf: Pyritic Sulfur Content of Feed (%)
14. PSp: Pyritic Sulfur Content of Product (%)
15. PSRJ: Pyritic Sulfur Rejection (%)
$$PSRJ = (100 - Y \times PSp / PSf)$$
16. R: Refuse Weight (g)
17. RCR: Reagent to Coal Ratio
18. Sf: Total Sulfur Content in the Feed (%)
19. Sp: Total Sulfur Content in the Product (%)
20. SRJ: Total Sulfur Rejection (%)
$$SRJ = (100 - Y \times Sp / Sf)$$
21. T: Agglomeration Time (s)
22. Y: Overall Yield (%)
$$Y = P / (P + R) \times 100$$
23. Yc: Clean Coal Yield (%)

Agglomeration Tests Without any Additives

Illinois # 6 Coal, Wet Ground to 200 mesh x 0

Run #	C (%)	RCR	PCR (-)	T (s)	N (rpm)	P (g)	R (g)	Af		Sf		PSf		Yc (%)	PSRJ (%)	SRJ (%)	ARD (%)	ARJ (%)	Y (%)	PSP (%)	Sp (%)	AΓ (%)	Ap (%)	R (g)	P (g)	N (rpm)	T (s)	PCR (-)	RCR	C (%)	Run #	
								15.45	4.31	2.92	11265																					
1152.1*0m	4	0.00	0.5	30	14224	13.3884	4.9340	7.64	30.09	3.15	1.70	73.1	63.9	50.6	46.6	57.4	79.8	80.9														
1152.2*0m	4	0.00	0.5	30	14224	16.1703	4.8164	8.58	31.00	3.01	1.75	77.1	57.2	44.5	46.2	53.8	83.3	84.3														
1152.3*0m	4	0.00	0.5	30	14478	14.4016	4.4298	8.57	30.87	2.95	1.43	76.5	57.6	44.5	47.7	62.5	82.7	83.7														
1160.1*0m	4	0.00	0.5	30	13970	15.4265	5.3848	9.41	31.56	3.04	2.16	74.1	58.5	44.1	44.5	48.4	80.7	81.8														
1160.2*0m	4	0.00	0.5	30	14224	14.2698	5.5881	8.78	30.82	2.88	1.90	71.9	62.5	47.8	49.0	56.0	78.8	79.9														
1160.3*0m	4	0.00	0.5	30	14224	15.2588	5.6648	9.61	29.90	2.99	1.98	72.9	58.3	42.9	46.3	53.4	79.2	80.3														
1173.1m	4	0.00	0.5	30	14097	11.3900	6.4200	8.29	24.73	2.59	1.72	64.0	68.3	50.4	62.0	68.3	70.4	71.5														
1173.2m	4	0.00	0.5	30	14224	12.8100	7.1100	9.04	23.56	2.74	1.87	64.3	65.2	45.9	59.6	65.3	70.2	71.2														
1173.3m	4	0.00	0.5	30	14097	11.0700	7.5800	8.50	23.04	2.53	1.46	59.4	69.8	49.2	65.6	75.0	65.2	66.2														
Ave	4	0.00	0.5	30	14196	13.7984	5.7698	8.71	28.40	2.88	1.78	70.3	62.4	46.6	51.9	60.0	76.7	77.7														

Agglomeration Tests Without any Additives

Pittsburgh # 8 Coal, Wet Ground to 200 mesh x 0

Run #	C (%)	RCR	PCR	T (-)	N (rpm)	P (g)	R (g)	Af		Sf		Psf		Yc (%)	PSRJ (%)	SRJ (%)	ARD (%)	ARJ (%)	Y (%)	Psp (%)	Sp (%)	Ar (%)	Ap (%)	Rf (%)	BTU (BTU/f)
								11.27	3.84	3.06	12543														
P147.1*0m	4	0.00	0.5	15	9779	14.3144	4.5188	5.89	22.41	2.24	1.42	76.0	60.3	47.7	55.7	64.7	80.6	81.3							
P147.2*0m	4	0.00	0.5	15	9525	13.8924	3.8596	5.69	24.57	2.25	1.43	78.3	60.5	49.5	54.1	63.4	83.2	83.9							
P147.3*0m	4	0.00	0.5	15	9779	14.4231	4.6448	5.03	20.03	2.32	1.50	75.6	66.2	55.4	54.3	62.9	81.0	81.8							
P60.1S0	4	0.00	0.5	15	9398	14.8755	5.3475	7.25	25.52	2.52	1.64	73.6	55.9	40.0	50.7	59.6	77.6	78.2							
P60.1S0	4	0.00	0.5	15	9271	13.3570	5.6895	6.14	22.67	2.22	1.27	70.1	64.4	49.2	58.6	70.1	74.9	75.6							
P141.1m	4	0.00	0.5	15	9100	13.5649	4.1765	8.45	24.08	2.36	1.45	76.5	49.8	34.3	45.2	56.1	80.3	80.9							
P141.2m	4	0.00	0.5	15	9100	8.5649	2.9344	4.61	28.17	2.03	1.13	74.5	73.3	64.2	54.0	66.7	81.5	82.6							
P141.3m	4	0.00	0.5	15	9100	11.8013	4.1792	6.52	25.43	2.29	1.42	73.8	62.6	49.3	48.6	58.5	79.2	80.1							
P141.4m	4	0.00	0.5	15	9100	10.9539	3.8755	5.95	24.81	2.17	1.23	73.9	65.8	53.7	51.3	64.0	79.7	80.6							
P141.5m	4	0.00	0.5	15	9100	12.6331	4.9879	6.10	23.18	2.23	1.31	71.7	66.0	52.6	51.4	62.8	77.3	78.1							
P141.6m	4	0.00	0.5	15	9100	12.9523	6.0705	6.66	20.76	2.25	1.27	68.1	64.7	48.2	53.4	65.8	72.9	73.7							
P141.7m	4	0.00	0.5	15	9100	12.1000	4.5001	5.90	21.90	2.20	1.36	72.9	66.6	54.1	51.3	60.8	78.7	79.6							
P141.8m	4	0.00	0.5	15	9100	14.0596	5.5483	5.78	21.92	2.29	1.40	71.7	67.8	55.1	50.1	60.3	77.5	78.4							
Ave	4	0.00	0.5	15	9273	12.8840	4.6410	6.15	23.50	2.26	1.37	73.6	63.4	50.2	52.2	62.8	78.8	79.6							

Upper Freeport Coal, Wet Ground to 200 mesh x 0

E-5

Effect of the Addition of N-Pentane During Grinding

Illinois # 6 Coal, Wet Ground to 200 mesh x 0

Run #	C (%)	RCR	PCR (-)	T (s)	N (rpm)	P (g)	R (g)	Af			Sf			PSf			Yc (%)	BTU (%)
								Ap (%)	Ar (%)	Sp (%)	Sp (%)	PSP (%)	Y (%)	ARJ (%)	SRJ (%)	PSRJ (%)		
								16.10		3.94	2.54							11165
1103.1P05m	4	0.05	0.5	30	13716	14.9607	4.4684	11.11	29.22	3.85	1.99	77.0	46.9	31.0	24.8	39.6	81.6	82.3
1103.2P05m	4	0.05	0.5	30	13970	14.7173	5.0616	9.24	29.82	3.34	1.76	74.4	57.3	42.6	36.9	48.6	80.5	81.5
1103.3P05m	4	0.05	0.5	30	13843	15.6110	4.2445	10.22	30.94	3.71	1.89	78.6	50.1	36.5	26.0	41.5	84.1	85.0
1103.4P05m	4	0.05	0.5	30	13843	16.7380	4.9388	10.71	29.78	3.31	1.73	77.2	48.6	33.5	35.1	47.3	82.2	83.0
1161.1P20m	4	0.05	0.5	30	14224	17.7766	4.8105	9.77	33.24	3.54	2.65	78.7	54.3	41.9	31.4	32.6	85.4	86.4
1161.2P20m	4	0.05	0.5	30	14224	14.7345	5.2876	11.04	32.67	3.63	3.01	73.6	51.7	34.4	34.2	28.6	78.7	79.5
1161.3P20m	4	0.05	0.5	30	13970	12.0431	4.9333	9.51	32.70	3.32	2.45	70.9	59.9	43.5	42.0	43.9	77.2	78.2
Ave	4	0.05	0.5	30	13970	15.2259	4.8207	10.23	31.20	3.53	2.21	75.8	52.7	37.6	32.9	40.3	81.4	82.3
1102.1P10m	4	0.10	0.5	30	13843	14.2320	4.1579	9.61	33.83	3.22	1.62	77.4	53.7	40.2	30.8	42.8	83.3	84.3
1102.2P10m	4	0.10	0.5	30	13970	15.1376	4.5526	9.38	33.72	3.34	1.64	76.9	55.1	41.6	28.7	42.8	83.0	84.0
1102.3P10m	4	0.10	0.5	30	13335	13.3897	4.8127	10.19	30.25	3.24	1.69	73.6	53.4	36.6	33.8	43.3	78.7	79.5
1102.4P10m	4	0.10	0.5	30	13843	15.1059	4.9364	10.66	30.60	3.22	1.57	75.4	50.0	33.7	32.6	46.0	80.2	81.0
1162.1P10m	4	0.10	0.5	30	15240	12.3226	4.2133	8.35	32.94	3.07	1.89	74.5	63.0	50.4	43.7	54.5	82.1	83.3
1162.2P10m	4	0.10	0.5	30	14224	12.1951	4.9134	7.80	29.92	2.99	2.11	71.3	66.9	53.6	47.5	51.5	79.0	80.2
1162.3P10m	4	0.10	0.5	30	14224	11.9519	4.8320	8.00	30.50	2.95	1.92	71.2	66.1	52.4	48.3	55.9	78.8	80.0
Ave	4	0.10	0.5	30	14097	13.4764	4.6312	9.14	31.68	3.15	1.78	74.3	58.3	44.1	37.9	48.1	80.7	81.8

Effect of the Addition of N-Pentane During Grinding

Illinois # 6 Coal, Wet Ground to 200 mesh x 0

Run #	C (%)	RCR	PCR (-)	T (s)	M (rpm)	P (g)	R (g)	Af		Sf		Psf		SRJ		PSRJ		Yc		(Btu) f 11129
								Ap (%)	Ar (%)	Sp (%)	Psp (%)	Y (%)	ARJ (%)	ARD (%)	SRJ (%)	PSRJ (%)	Yc (%)			
								16.33		3.79	2.39									
1101.2p20m	4	0.20	0.5	30	13843	12.4877	4.8313	9.31	31.58	3.48	1.53	72.1	58.9	43.0	33.8	53.9	78.2	79.1		
1101.3p20m	4	0.20	0.5	30	13970	13.6985	4.4121	9.71	32.02	3.13	1.60	75.6	55.0	40.5	37.5	49.3	81.6	82.6		
1101.4p20m	4	0.20	0.5	30	13843	14.7711	4.4229	10.37	33.65	3.29	1.43	77.0	51.1	36.5	33.2	53.8	82.4	83.3		
1163.1p5m	4	0.20	0.5	30	14097	13.7077	5.1390	10.29	31.99	3.46	2.26	72.7	55.5	38.8	38.0	46.8	78.4	79.4		
1163.2p5m	4	0.20	0.5	30	13970	13.7826	5.3569	9.10	31.96	3.03	2.37	72.0	61.0	45.9	46.3	44.8	78.7	79.8		
1163.3p5m	4	0.20	0.5	30	14224	12.0375	5.4642	8.72	31.34	3.17	2.45	68.8	64.3	48.2	46.3	45.7	75.5	76.5		
Ave	4	0.20	0.5	30	13991	13.4142	4.9377	9.58	32.09	3.26	1.94	73.0	57.7	42.2	39.2	49.1	79.1	80.1		
1154.1p2m	4	0.50	0.5	30	14351	14.2850	5.1787	8.81	31.41	3.37		73.4	58.1	43.0	42.6		79.2	80.1		
1154.2p2m	4	0.50	0.5	30	14478	13.8169	5.0378	8.45	31.76	3.30	2.06	73.3	59.9	45.3	43.9	51.1	79.3	80.3		
1154.3p2m	4	0.50	0.5	30	14351	13.2150	5.8026	7.95	20.52	3.31	1.82	69.5	64.2	48.5	46.6	59.0	75.7	76.6		
Ave	4	0.50	0.5	30	14393	13.7723	5.3397	8.40	27.90	3.33	1.94	72.1	60.8	45.6	44.4	55.1	78.1	79.0		

Effect of the Addition of N-Pentane During Grinding

Pittsburgh # 8 Coal, Wet Ground to 200 mesh x 0

Run #	C (%)	RCR	PCR (-)	T (s)	M (rpm)	P (g)	R (g)	Af		Sf		PSf		(Btu)f					
								Ap (%)	Ar (%)	Sp (%)	Psp (%)	Y (%)	ARJ (%)	ARD (%)	SRJ (%)	PSRJ (%)	Yc (%)	BTU (%)	
								16.04		3.65	2.56							11766	
P107.1P10m	4	0.10	0.5	15	9525	13.0428	4.4158	8.76	28.71	2.45	1.36	74.7	59.2	45.4	49.9	60.1	81.2	82.2	
P107.2P10m	4	0.10	0.5	15	9652	12.0909	4.1434	8.09	30.06	2.18	1.28	74.5	62.4	49.6	55.5	62.7	81.5	82.7	
P107.3P10m	4	0.10	0.5	15	9525	12.5175	4.0141	8.94	30.62	2.23	1.31	75.7	57.8	44.3	53.7	61.2	82.1	83.2	
Ave	4	0.10	0.5	15	9567	12.5504	4.1911	8.60	29.80	2.29	1.32	75.0	59.8	46.4	53.0	61.3	81.6	82.7	
P108.1P20m	4	0.20	0.5	15	9525	15.0328	5.0283	8.03	25.52	2.14	1.58	74.9	62.5	49.9	56.1	53.7	82.1	83.2	
P108.2P20m	4	0.20	0.5	15	9779	13.8876	4.2638	8.07	32.14	2.20	1.21	76.5	61.5	49.7	53.9	63.8	83.8	85.0	
P108.3P20m	4	0.20	0.5	15	9652	14.4432	4.9172	8.31	30.11	2.18	1.36	74.6	61.4	48.2	55.4	60.3	81.5	82.6	
Ave	4	0.20	0.5	15	9652	14.4545	4.7364	8.14	29.26	2.17	1.38	75.3	61.8	49.3	55.1	59.3	82.4	83.6	

Effect of the Addition of N-Pentane During Grinding

Upper Freeport Coal, Wet Ground to 200 mesh x 0

Run #	C	RCR	PCR	T	N	P	R	Ap	Ar	Sp	Psp	Y	ARJ	ARD	SRJ	PSRJ	Yc	BTU
(%)	(-)	(s)	(rpm)	(g)	(g)	(g)	(g)	(%)	(%)	(%)	(%)	(%)	(%)	(%)	(%)	(%)	(%)	(%)
U142.1P100m	4	0.01	0.5	30	14478	20.7860	1.6017	7.23	80.56	1.19	0.67	92.8	49.9	46.0	42.2	55.9	99.5	>99.9
U142.2P100m	4	0.01	0.5	30	14351	20.9868	1.6412	7.14	79.01	1.31	0.74	92.7	50.6	46.7	36.4	51.3	99.5	>99.9
U142.3P100m	4	0.01	0.5	30	14351	20.5995	1.6256	7.70	80.84	1.16	0.58	92.7	46.7	42.5	43.7	61.8	98.8	99.8
Ave	4	0.01	0.5	30	14393	20.7908	1.6228	7.36	80.14	1.22	0.67	92.8	49.1	45.1	40.8	56.3	99.2	>99.9
U110.1P10m	4	0.10	0.5	30	14224	17.2184	0.7705	9.03	76.82	1.40	0.75	95.7	26.8	23.5	33.3	45.6	98.7	99.2
U110.2P10m	4	0.10	0.5	30	14351	19.3857	0.7924	8.79	76.20	1.35	0.72	96.1	28.4	25.5	35.5	47.6	99.4	99.9
U110.3P10m	4	0.10	0.5	30	14478	18.9133	0.8230	9.02	77.94	1.27	0.59	95.8	26.7	23.6	39.5	57.2	98.9	99.4
Ave	4	0.10	0.5	30	14351	18.5058	0.7953	8.95	76.99	1.34	0.69	95.9	27.3	24.2	36.1	50.1	99.0	99.5

Af 13.40 Sf 1.91 PSf 1.42 (Btu)f 13093

Effect of the Addition of Cyclohexane During Grinding

Illinois # 6 Coal, Wet Ground to 200 mesh x 0

Run #	C (%)	RCR (-)	T (s)	N (rpm)	P (g)	R (g)	Af		Sf		PSf		(Btu)f					
							Ap (%)	Ar (%)	Sp (%)	Psp (%)	Y (%)	ARJ (%)	ARD (%)	SRJ (%)	PSRJ (%)	Yc (%)	BTU (%)	
							15.45		4.31	3.10							11265	
1153.1C20m	4	0.05	0.5	30	14478	12.4966	7.81	31.64	3.10	1.79	73.1	63.0	49.4	47.4	57.7	79.8	80.8	
1153.2C20m	4	0.05	0.5	30	14478	14.2559	7.99	33.95	3.13	1.80	76.8	60.3	48.3	44.2	55.3	83.6	84.6	
1153.3C20m	4	0.05	0.5	30	14478	14.1180	8.04	32.13	3.01	1.59	75.4	60.8	48.0	47.3	61.2	82.0	83.1	
Ave	4	0.05	0.5	30	14478	13.6235	7.95	32.57	3.08	1.73	75.1	61.4	48.6	46.3	58.1	81.8	82.8	
1116.1C10m	4	0.10	0.5	30	14097	14.2214	9.18	25.97	3.10	1.46	73.7	58.8	44.2	56.3	71.3	80.2	81.2	
1116.2C10m	4	0.10	0.5	30	14351	14.7802	9.39	26.01	2.96	1.44	75.0	57.2	42.9	57.5	71.2	81.4	82.4	
1116.3C10m	4	0.10	0.5	30	14351	14.2667	9.27	25.47	3.10	1.39	73.2	58.7	43.6	56.6	72.8	79.5	80.5	
Ave	4	0.10	0.5	30	14266	14.4228	9.28	25.82	3.05	1.43	74.0	58.3	43.6	56.8	71.8	80.3	81.4	
1117.2C20m	4	0.20	0.5	30	14351	13.6405	10.07	26.70	3.72	1.94	72.4	55.7	38.8	48.5	62.5	77.9	78.8	
1117.3C20m	4	0.20	0.5	30	14097	12.1960	9.69	26.98	3.54	1.95	71.5	57.9	41.1	51.6	62.9	77.3	78.2	
Ave	4	0.20	0.5	30	14224	12.9183	9.88	26.84	3.63	1.95	71.9	56.8	39.9	50.1	62.7	77.6	78.5	

Effect of the Addition of Cyclohexane During Grinding

Pittsburgh # 8 Coal, Wet Ground to 200 mesh x 0

Run #	C (%)	RCR	PCR (-)	T (s)	N (rpm)	P (g)	R (g)	Af		Sf		Psf		(Btu)f					
								Ap (%)	Ar (%)	Sp (%)	Psp (%)	Y (%)	ArJ (%)	ARD (%)	SRJ (%)	PSRJ (%)	Yc (%)	STU (%)	
								11.27		3.84		3.06						12543	
P150.1C50m	4	0.02	0.5	15	9652	15.4649	4.8483	6.19	20.69	2.34	1.74	76.1	58.2	45.1	53.6	56.8	80.5	81.2	
P150.2C50m	4	0.02	0.5	15	9652	14.8814	4.5300	6.12	21.29	2.23	1.72	76.7	58.4	45.7	55.5	57.0	81.1	81.8	
P150.3C50m	4	0.02	0.5	15	9652	13.4406	4.1057	5.35	23.90	2.38	1.69	76.6	63.6	52.5	52.5	57.7	81.7	82.5	
Ave	4	0.02	0.5	15	9652	14.5956	4.4947	5.89	21.96	2.32	1.72	76.5	60.1	47.8	53.9	57.2	81.1	81.8	
P120.1C05m	4	0.05	0.5	15	9398	15.4977	4.1850	8.70	24.96	2.84	1.93	78.7	50.9	37.6	54.5	59.5	83.5	84.3	
P120.2C05m	4	0.05	0.5	15	9525	15.4319	4.5492	8.57	24.32	2.75	1.73	77.2	52.6	38.6	56.7	64.4	82.1	82.8	
P120.3C05m	4	0.05	0.5	15	9398	16.0628	4.7983	8.76	23.62	2.81	1.78	77.0	51.6	37.2	55.9	63.4	81.6	82.4	
Ave	4	0.05	0.5	15	9440	15.6641	4.5108	8.68	24.30	2.80	1.81	77.7	51.7	37.8	55.7	62.4	82.4	83.2	
P119.1C10m	4	0.10	0.5	15	8763	16.5217	4.6111	10.54	26.77	3.30	2.35	78.2	40.9	24.4	47.5	50.9	81.7	81.8	
P119.2C10m	4	0.10	0.5	15	9144	16.8627	4.8740	9.45	24.08	3.28	2.19	77.6	47.4	32.3	48.2	54.6	81.6	82.3	
P119.3C10m	4	0.10	0.5	15	9271	16.3227	4.6069	9.51	25.66	2.99	1.92	78.0	46.8	31.8	52.5	60.0	82.0	82.7	
Ave	4	0.10	0.5	15	9059	16.5690	4.6973	9.83	25.50	3.19	2.15	77.9	45.1	29.5	49.4	55.1	81.6	82.2	

Effect of the Addition of Cyclohexane During Grinding

Upper Freeport Coal, Wet Ground to 200 mesh x 0

Run #	C (%)	RCR	PCR (-)	T (s)	N (rpm)	P (g)	R (g)	Af		Sf		PSf		Yc (%)	BTU (%)		
								Ap (%)	Ar (%)	Sp (%)	Psp (%)	Y (%)	ARJ (%)			ARD (%)	SRJ (%)
								13.40	1.91	1.42					13093		
U144.1C100m	4	0.01	0.5	30	14224	17.6897	1.5578	7.10	79.90	1.02		91.9	51.3	47.0	50.8	98.6	99.7
U144.2C100m	4	0.01	0.5	30	14224	19.9831	1.5957	6.94	78.53	1.09	0.56	92.6	52.0	48.2	47.2	63.2	>99.9
U144.3C100m	4	0.01	0.5	30	14224	18.6920	1.6147	7.69	79.08	1.12	0.56	92.0	47.2	42.6	46.0	63.4	99.2
Ave	4	0.01	0.5	30	14224	18.7883	1.5894	7.24	79.17	1.08	0.56	92.2	50.2	45.9	48.0	63.3	99.9

Effect of the Addition of N-Heptane During Grinding

Illinois # 6 Coal, Wet Ground to 200 mesh x 0

Run #	C (%)	RCR	PCR	T (s)	N (rpm)	P (g)	R (g)	Ap (%)	Ar (%)	Sp (%)	Psp (%)	Y (%)	ARJ (%)	ARD (%)	SRJ (%)	PSRJ (%)	Yc (%)	BTUf (Btu/lb)
								16.45		5.24	3.75							11111
1113.1H10m	4	0.10	0.5	30	14224	13.7282	4.5698	8.44	24.54	3.12	1.47	74.9	61.5	48.7	55.4	70.6	82.1	83.3
1113.2H10m	4	0.10	0.5	30	14224	14.8404	6.1602	9.46	22.46	3.67	1.88	70.7	59.4	42.5	50.5	64.6	76.6	77.5
1113.3H10m	4	0.10	0.5	30	14224	13.2181	4.9354	10.04	26.94	4.10	2.65	72.8	55.6	39.0	43.0	48.7	78.4	79.3
1174.1Hm	4	0.10	0.5	30	14224	11.6700	5.9700	9.11	24.83	2.89	2.09	66.2	64.0	45.5	56.1	60.3	72.2	73.2
1174.2Hm	4	0.10	0.5	30	13843	9.9300	6.0200	8.79	23.48	2.84	2.06	62.3	67.3	47.4	59.4	63.1	68.2	69.1
1174.3Hm	4	0.10	0.5	30	14097	13.5000	7.4300	8.69	23.68	2.66	1.77	64.5	66.5	48.0	60.6	67.1	70.7	71.7
Ave	4	0.10	0.5	30	14139	12.8145	5.8509	9.09	24.32	3.21	1.99	68.6	62.4	45.2	54.2	62.4	74.7	75.7
1112.1H20m	4	0.20	0.5	30	14351	13.8688	3.9967	9.59	28.75	3.37	1.76	77.6	54.7	41.7	50.1	61.6	84.0	85.0
1112.2H20m	4	0.20	0.5	30	14097	12.2730	3.9317	9.07	29.17	3.17	1.50	75.7	58.2	44.9	54.2	67.9	82.4	83.5
1112.3H20m	4	0.20	0.5	30	14224	12.4633	4.1534	8.81	28.00	3.06	1.11	75.0	59.8	46.4	56.2	76.5	81.9	83.0
1175.1Hm	4	0.20	0.5	30	14224	13.3500	5.7500	9.92	26.56	2.96	2.12	69.9	58.5	40.7	52.5	57.5	75.6	76.5
1175.2Hm	4	0.20	0.5	30	14351	11.6600	6.3400	9.29	25.41	2.88	2.11	64.8	64.0	44.4	57.2	60.6	70.6	71.5
1175.3Hm	4	0.20	0.5	30	14351	12.4600	6.5100	9.19	24.66	2.82	1.89	65.7	63.9	45.0	57.5	64.4	71.6	72.6
Ave	4	0.20	0.5	30	14266	12.6792	5.1136	9.31	27.09	3.04	1.75	71.5	59.9	43.9	54.6	64.8	77.7	78.7
1155.1H2m	4	0.50	0.5	30	14224	13.9097	6.0200	8.80	23.21	3.10	1.66	69.8	60.2	43.0	49.6	62.5	75.3	76.1
1155.2H2m	4	0.50	0.5	30	14605	13.9103	6.3199	9.95	22.61	3.38	2.02	68.8	55.7	35.6	46.1	55.2	73.2	73.9
1155.3H2m	4	0.50	0.5	30	14224	12.1996	5.5191	9.07	24.19	3.46	2.10	68.9	59.6	41.3	44.7	53.4	74.0	74.9
1176.1Hm	4	0.50	0.5	30	14224	8.4600	8.0400	9.68	20.87	3.19	2.24	51.3	70.3	42.1	62.5	67.0	55.6	56.3
1176.2Hm	4	0.50	0.5	30	14224	7.9400	9.4000	8.73	16.48	3.08	2.22	45.8	76.1	47.8	67.7	70.8	50.2	50.9
1176.3Hm	4	0.50	0.5	30	14224	7.4700	7.9300	8.71	20.27	3.09	2.30	48.5	74.7	47.9	65.6	68.0	53.2	53.9
Ave	4	0.50	0.5	30	14288	10.6483	7.2048	9.16	21.27	3.22	2.09	58.8	66.1	43.0	56.1	62.8	63.6	64.3

Effect of the Addition of N-Heptane During Grinding

Pittsburgh # 8 Coal, Wet Ground to 200 mesh x 0

Run #	C (%)	RCR	PCR (-)	T (s)	N (rpm)	P (g)	R (g)	Af		Sf		PSf		Yc (%)	BTU (%)
								Ap (%)	Ar (%)	Sp (%)	Psp (%)	Y (%)	ArJ (%)		
								11.27		3.84	3.06				12543
P148.1H50m	4	0.02	0.5	15	9652	15.8139	3.3105	6.84	21.60	2.33	1.51	82.7	49.8	39.3	86.8
P148.2H50m	4	0.02	0.5	15	9525	15.9962	3.3694	7.10	21.98	2.34	1.53	82.6	48.0	37.0	86.5
P148.3H50m	4	0.02	0.5	15	9779	14.5446	3.3187	5.98	23.86	2.31	1.58	81.4	56.8	46.9	86.3
Ave	4	0.02	0.5	15	9652	15.4516	3.3329	6.64	22.48	2.33	1.54	82.2	51.5	41.1	86.5
P149.1H20m	4	0.05	0.5	15	9398	16.6598	2.3509	7.31	26.86	2.57	1.92	87.6	43.2	35.1	91.5
P149.2H20m	4	0.05	0.5	15	8636	15.1327	2.9060	7.49	23.22	2.75	1.88	83.9	44.2	33.5	88.0
P149.3H20m	4	0.05	0.5	15	9525	18.7978	3.3045	7.15	20.20	2.63	1.99	85.0	46.0	36.6	89.0
Ave	4	0.05	0.5	15	9186	16.8634	2.8538	7.32	23.43	2.65	1.93	85.5	44.5	35.1	89.9
P118.1H10m	4	0.10	0.5	15	8763	13.1060	2.4379	9.62	35.63	3.34	2.40	84.3	41.9	31.0	88.6
P118.2H10m	4	0.10	0.5	15	9017	14.8094	3.0318	9.98	35.22	3.41	2.23	83.0	40.6	28.5	87.4
P118.3H10m	4	0.10	0.5	15	9398	12.3377	2.1995	9.41	36.41	3.16	2.10	84.9	42.8	32.5	90.1
Ave	4	0.10	0.5	15	9059	13.4177	2.5564	9.67	35.75	3.30	2.25	84.1	41.7	30.7	88.9

Effect of the Addition of N-Heptane During Grinding

Upper Freeport Coal, Wet Ground to 200 mesh x 0

Run #	C (%)	RCR	PCR	T (s)	M (rpm)	P (g)	R (g)	Af		Sf		Psf		(Btu)f				
								Ap (%)	Ar (%)	Sp (%)	Y (%)	ARJ (%)	SRJ (%)	PSRJ (%)	Yc (%)	BTU		
									13.40		1.91	1.42					13093	
U143.1H100m	4	0.01	0.5	30	14097	16.3071	1.3115	7.15	80.42	1.07	0.54	92.6	50.6	46.6	48.1	64.5	99.2	>99.9
U143.2H100m	4	0.01	0.5	30	14351	16.4054	1.4655	7.48	79.52	1.20	0.63	91.8	48.8	44.2	42.3	59.0	98.1	99.2
U143.3H100m	4	0.01	0.5	30	14732	17.6739	1.5415	7.10	80.33	1.26	0.72	92.0	51.3	47.0	39.3	53.0	98.7	99.8
Ave	4	0.01	0.5	30	14393	16.7955	1.4395	7.24	80.09	1.18	0.63	92.1	50.2	45.9	43.3	58.8	98.7	99.7

**APPENDIX F: AGGLOMERATION TEST RESULTS USING
SURFACTANTS DURING GRINDING**

NOMENCLATURE

1. Af: Ash Content of Feed Coal (%)
2. Ap: Ash Content of Product Coal (%)
3. Ar: Ash Content of Refuse (%)
4. ARD: Ash Reduction (%)
$$ARD = (1 - Ap/Af) \times 100$$
5. ARJ: Ash Rejection (%)
$$ARJ = 100 - Y \times Ap / Af$$
6. (Btu)f: Calorific Value of Feed (Btu/lb)
7. (Btu)p: Calorific Value of Product (Btu/lb)
8. BTU: Btu Recovery (%),
$$BTU = (Btu)p / (Btu)f \times Y$$
9. C: Coal Slurry Concentration (wt.%)
10. N: Mixing Speed (rpm)
11. P: Product Coal Weight (g)
12. PCR: Pentane/Coal Ratio (Weight Basis)
13. PSf: Pyritic Sulfur Content of Feed (%)
14. PSp: Pyritic Sulfur Content of Product (%)
15. PSRJ: Pyritic Sulfur Rejection (%)
$$PSRJ = (100 - Y \times PSp / PSf)$$
16. R: Refuse Weight (g)
17. RCR: Reagent to Coal Ratio
18. Sf: Total Sulfur Content in the Feed (%)
19. Sp: Total Sulfur Content in the Product (%)
20. SRJ: Total Sulfur Rejection (%)
$$SRJ = (100 - Y \times Sp / Sf)$$
21. T: Agglomeration Time (s)
22. Y: Overall Yield (%)
$$Y = P / (P + R) \times 100$$
23. Yc: Clean Coal Yield (%)
$$Yc = Y \times (100 - Ap) / (100 - Af)$$

Agglomeration Tests Without any Additives

Illinois # 6 Coal, Wet Ground to 200 mesh x 0

Run #	C (%)	RCR	PCR	T (s)	N (rpm)	P (g)	R (g)	Af		Sf		PSf		Y (%)	ARJ (%)	ARD (%)	SRJ (%)	PSRJ (%)	Yc (%)	BTU (%)
								Ap (%)	Ar (%)	Sp (%)	Psp (%)	Y (%)								
								15.45		4.31	2.92									11265
1152.1*0m	4	0.00	0.5	30	14224	13.3884	4.9340	7.64	30.09	3.15	1.70	73.1	63.9	50.6	46.6	57.4	79.8	80.9		
1152.2*0m	4	0.00	0.5	30	14224	16.1703	4.8164	8.58	31.00	3.01	1.75	77.1	57.2	44.5	46.2	53.8	83.3	84.3		
1152.3*0m	4	0.00	0.5	30	14478	14.4016	4.4298	8.57	30.87	2.95	1.43	76.5	57.6	44.5	47.7	62.5	82.7	83.7		
1160.1*0m	4	0.00	0.5	30	13970	15.4265	5.3848	9.41	31.56	3.04	2.16	74.1	58.5	44.1	44.5	48.4	80.7	81.8		
1160.2*0m	4	0.00	0.5	30	14224	14.2698	5.5881	8.78	30.82	2.88	1.90	71.9	62.5	47.8	49.0	56.0	78.8	79.9		
1160.3*0m	4	0.00	0.5	30	14224	15.2588	5.6648	9.61	29.90	2.99	1.98	72.9	58.3	42.9	46.3	53.4	79.2	80.3		
1173.1m	4	0.00	0.5	30	14097	11.3900	6.4200	8.29	24.73	2.59	1.72	64.0	68.3	50.4	62.0	68.3	70.4	71.5		
1173.2m	4	0.00	0.5	30	14224	12.8100	7.1100	9.04	23.56	2.74	1.87	64.3	65.2	45.9	59.6	65.3	70.2	71.2		
1173.3m	4	0.00	0.5	30	14097	11.0700	7.5800	8.50	23.04	2.53	1.46	59.4	69.8	49.2	65.6	75.0	65.2	66.2		
Ave	4	0.00	0.5	30	14196	13.7984	5.7698	8.71	28.40	2.88	1.78	70.3	62.4	46.6	51.9	60.0	76.7	77.7		

Agglomeration Tests Without any Additives

Pittsburgh # 8 Coal, Wet Ground to 200 mesh x 0

Run #	C (%)	RCR	PCR (-)	T (s)	N (rpm)	P (g)	R (g)	Af		Sf		PSP (%)	Y (%)	ARJ (%)	ARD (%)	SRJ (%)	PSRJ (%)	Yc (%)	(Btu)f 12364
								12.37	3.84	3.06									
P147.1*0m	4	0.00	0.5	15	9779	14.3144	4.5188	5.89	22.41	2.24	1.42	76.0	60.3	47.7	55.7	64.7	80.6	81.3	
P147.2*0m	4	0.00	0.5	15	9525	13.8924	3.8596	5.69	24.57	2.25	1.43	78.3	60.5	49.5	54.1	63.4	83.2	83.9	
P147.3*0m	4	0.00	0.5	15	9779	14.4231	4.6448	5.03	20.03	2.32	1.50	75.6	66.2	55.4	54.3	62.9	81.0	81.8	
P60.1S0	4	0.00	0.5	15	9398	14.8755	5.3475	7.25	25.52	2.52	1.64	73.6	55.9	40.0	50.7	59.6	77.6	78.2	
P60.1S0	4	0.00	0.5	15	9271	13.3570	5.6895	6.14	22.67	2.22	1.27	70.1	64.4	49.2	58.6	70.1	74.9	75.6	
P141.1m	4	0.00	0.5	15	9100	13.5649	4.1765	8.45	24.08	2.36	1.45	76.5	49.8	34.3	45.2	56.1	80.3	80.9	
P141.2m	4	0.00	0.5	15	9100	8.5649	2.9344	4.61	28.17	2.03	1.13	74.5	73.3	64.2	54.0	66.7	81.5	82.6	
P141.3m	4	0.00	0.5	15	9100	11.8013	4.1792	6.52	25.43	2.29	1.42	73.8	62.6	49.3	48.6	58.5	79.2	80.1	
P141.4m	4	0.00	0.5	15	9100	10.9539	3.8755	5.95	24.81	2.17	1.23	73.9	65.8	53.7	51.3	64.0	79.7	80.6	
P141.5m	4	0.00	0.5	15	9100	12.6331	4.9879	6.10	23.18	2.23	1.31	71.7	66.0	52.6	51.4	62.8	77.3	78.1	
P141.6m	4	0.00	0.5	15	9100	12.9523	6.0705	6.66	20.76	2.25	1.27	68.1	64.7	48.2	53.4	65.8	72.9	73.7	
P141.7m	4	0.00	0.5	15	9100	12.1000	4.5001	5.90	21.90	2.20	1.36	72.9	66.6	54.1	51.3	60.8	78.7	79.6	
P141.8m	4	0.00	0.5	15	9100	14.0596	5.5483	5.78	21.92	2.29	1.40	71.7	67.8	55.1	50.1	60.3	77.5	78.4	
Ave	4	0.00	0.5	15	9273	12.8840	4.6410	6.15	23.50	2.26	1.37	73.6	63.4	50.2	52.2	62.8	78.8	79.6	

Agglomeration Tests Without any Additives

Upper Freeport Coal, Wet Ground to 200 mesh x 0

Run #	C (%)	RCR	PCR	T (s)	H (rpm)	P (g)	R (g)	Ap (%)	Ar (%)	Sp (%)	Psp (%)	Y (%)	ARJ (%)	ARD (%)	SRJ (%)	PSRJ (%)	Yc (%)	BTU
								Af		Sf	PSf							(BTU) f
								13.40		1.91	1.42							13093
U145.1*0m	4	0.00	0.5	30	14224	17.4726	1.2857	6.62	77.85	1.25	0.69	93.1	54.0	50.6	39.0	54.4	>99.9	>99.9
U145.2*0m	4	0.00	0.5	30	14859	18.9935	1.5365	6.75	79.97	1.17	0.57	92.5	53.4	49.6	43.3	62.6	99.6	>99.9
U145.3*0m	4	0.00	0.5	30	14351	16.8754	1.4022	6.67	78.65*	1.23	0.60	92.3	54.0	50.2	40.5	60.7	99.5	>99.9
Ave	4	0.00	0.5	30	14478	17.7805	1.4081	6.68	78.82	1.22	0.62	92.7	53.8	50.1	41.0	59.2	99.9	>99.9

Aerosol-OT

Illinois # 6 Coal, 200 mesh x 0, wet ground

Run #	C (%)	RCR	PCR	T (s)	N (rpm)	P (g)	R (g)	Af		Sf		Y (%)	ARJ (%)	ARD (%)	SRJ (%)	PSRJ (%)	Yc (%)	BTU (%)
								14.83	4.59	3.45	(BTU)f 11360							
153.1S10m	4	0.53	0.5	30	13500	14.0089	5.9858	10.54	22.62	3.63	2.21	70.1	50.2	28.9	44.6	55.1	73.6	74.1
153.2S10m	4	0.53	0.5	30	13652	16.0574	4.8899	11.87	26.56	3.81	2.22	76.7	38.6	20.0	36.4	50.6	79.3	79.7
164.1S10m	4	0.53	0.5	30	13843	13.8917	4.2188	9.92	28.42	3.84	2.14	76.7	48.7	33.1	35.8	52.3	81.1	81.8
164.2S10m	4	0.53	0.5	30	13970	13.3317	4.2072	10.29	27.71	3.79	2.17	76.0	47.3	30.6	37.2	52.1	80.1	80.7
164.3S10m	4	0.53	0.5	30	13907	14.1444	4.5012	10.11	28.54	3.03	1.38	75.9	48.3	31.8	49.9	69.6	80.1	80.7
164.4S10m	4	0.53	0.5	30	13716	14.3538	5.0115	10.00	27.97	3.87	2.26	74.1	50.0	32.6	37.5	51.3	78.3	79.0
Ave	4	0.53	0.5	30	13765	14.2980	4.8024	10.46	26.97	3.66	2.07	74.9	47.2	29.5	40.2	55.2	78.7	79.3
154.1S80m	4	4.22	0.5	30	13843	14.8874	5.0499	10.76	26.29	3.82	2.21	74.7	45.8	27.4	37.9	52.1	78.2	78.8
154.2S80m	4	4.22	0.5	30	13843	17.1181	4.9645	11.12	27.78	3.66	2.04	77.5	41.9	25.0	38.2	54.1	80.9	81.4
163.1S80m	4	4.22	0.5	30	13462	13.4288	5.0842	9.26	24.86	3.65	2.04	72.5	54.7	37.6	42.3	57.1	77.3	78.0
163.2S80m	4	4.22	0.5	30	13843	16.0801	5.1327	10.44	23.74	3.66	1.98	75.8	46.6	29.6	39.6	56.4	79.7	80.3
163.3S80m	4	4.22	0.5	30	14034	16.1807	4.8587	9.33	26.40	3.45	1.67	76.9	51.6	37.1	42.2	62.8	81.9	82.6
163.4S80m	4	4.22	0.5	30	13970	14.7637	4.0895	8.56	28.43	3.51	1.84	78.3	54.8	42.3	40.1	58.2	84.1	85.0
Ave	4	4.22	0.5	30	13832	15.4098	4.8633	9.91	26.25	3.63	1.96	76.0	49.2	33.2	40.0	56.8	80.3	81.0

Aerosol-01

Pittsburgh # 8, 200 mesh x 0, wet ground

Run #	C	RCR	PCR	T	N	P	R	Af		Sf		(Btu)f	
								Ap	Ar	Sp	Psp	Yc	BTU
	(%)	-	(-)	(s)	(rpm)	(g)	(g)	(%)	(%)	(%)	(%)	(%)	(%)
P58.1S10	4	0.53	0.5	15	9525	14.9000	5.4444	7.33	24.02	2.33	1.29	73.2	77.6
P58.1S10	4	0.53	0.5	15	9271	14.4445	4.5095	7.25	25.48	2.27	1.37	76.2	80.8
Ave	4	0.53	0.5	15	9398	14.6723	4.9770	7.29	24.75	2.30	1.33	74.7	79.2
P59.1S80	4	4.22	0.5	15	9462	14.9930	6.0170	6.08	24.73	2.21	1.40	71.4	76.8
P59.1S80	4	4.22	0.5	15	9525	13.7918	7.3540	5.67	22.82	2.11	1.16	65.2	70.5
Ave	4	4.22	0.5	15	9494	14.3926	6.6855	5.88	23.78	2.16	1.28	68.3	73.6

Aerosol-OT

Upper Freeport Coal, 200 mesh x 0, wet ground

Run #	C (%)	RCR	PCR	T (s)	N (rpm)	P (g)	R (g)	Af		Sf		PSf		Yc (%)	PSRJ (%)	SRJ (%)	ARD (%)	ARJ (%)	Sp (%)	Psp (%)	Y (%)	BTU (%)
								Ap (%)	Ar (%)	Sp (%)	Psp (%)	Y (%)	ARJ (%)									
								13.28		2.23	1.70											13114
U57.1S10	4	0.53	0.5	30	14034	20.5755	1.5175	7.67	78.23	1.20	0.64	93.1	46.1	42.1	49.9	65.1	99.1	>99.9				
U57.1S10	4	0.53	0.5	30	14477	21.4350	1.5855	7.60	77.71	1.26	0.66	93.1	46.6	42.6	47.4	63.9	99.2	>99.9				
Ave	4	0.53	0.5	30	14256	21.0053	1.5515	7.64	77.97	1.23	0.65	93.1	46.3	42.3	48.6	64.5	99.1	>99.9				
U55.1S80m	4	4.22	0.5	30	13970	20.5183	1.7135	8.64	74.06	1.48	0.78	92.3	40.1	35.1	38.7	57.1	97.3	98.1				
U55.2S80m	4	4.22	0.5	30	14097	21.1650	1.6891	8.21	75.11	1.41	0.71	92.6	42.9	38.4	41.4	60.8	98.1	99.0				
Ave	4	4.22	0.5	30	14034	20.8417	1.7013	8.43	74.59	1.45	0.75	92.5	41.5	36.7	40.1	59.0	97.7	98.6				

Arosurf-HG

Illinois # 6 Coal, 200 mesh x 0, wet ground

Run #	C (%)	RCR	PCR	T (s)	N (rpm)	P (g)	R (g)	Ap (%)	Ar (%)	Sp (%)	Sf		Y (%)	ARJ (%)	ARD (%)	SRJ (%)	PSRJ (%)	Yc (%)	BTU (%)
											Af	PSf							
											14.51	4.59 3.45							(Btu)f 11410
173.1S10m	4	0.53	0.5	30	13018	11.7189	4.9455	10.27	24.27	3.59			70.3	51.3	30.7	45.0	48.9	74.1	74.7
173.2S10m	4	0.53	0.5	30	13970	13.5231	5.2492	9.94	24.65	3.41			72.0	51.7	33.0	46.5	62.2	76.2	76.8
165.2S10	4	0.53	0.5	30	13589	13.0965	4.9350	9.22	24.75	3.32			72.6	52.8	35.0	47.5	68.3	76.8	77.5
165.2S10	4	0.53	0.5	30	14034	12.3955	5.1895	8.85	25.09	3.39			70.5	56.0	37.6	47.9	63.3	74.9	75.6
Ave	4	0.53	0.5	30	13653	12.6835	5.0798	9.57	24.69	3.43			71.4	53.0	34.1	46.7	60.7	75.5	76.1
174.1S80m	4	4.22	0.5	30	13780	13.2261	5.3674	11.67	21.92	3.82		2.16	71.1	44.0	21.3	40.8	55.4	73.8	74.2
174.1S80m	4	4.22	0.5	30	13970	12.9270	4.6915	11.62	23.26	3.69		2.03	73.4	42.5	21.6	41.0	56.8	76.1	76.6
166.2S80	4	4.22	0.5	30	14034	12.0600	5.9805	10.97	21.47	3.55		1.94	66.8	48.3	22.7	48.3	62.8	69.4	69.7
166.2S80	4	4.22	0.5	30	13907	13.5755	5.1895	11.26	21.07	3.32		1.89	72.3	42.6	20.6	47.7	60.7	74.8	75.2
Ave	4	4.22	0.5	30	13923	12.9472	5.3072	11.36	21.93	3.60		2.01	70.9	44.4	21.6	44.4	58.9	73.5	73.9

Arosurf-MG

Pittsburgh # 8 Coal, 200 mesh x 0, wet ground

Run #	C (%)	RCR (-)	PCR (s)	T (rpm)	N (g)	P (g)	R (g)	Af		Sf		PSf		SRJ (%)	PSRJ (%)	Yc (%)	BTU (%)	
								Ap (%)	Ar (%)	Sp (%)	PSp (%)	Y (%)	ARJ (%)					ARD (%)
P75.1S10m	4	0.53	0.5	15	9271	13.6254	6.6160	9.47	22.12	3.06	2.05	67.3	55.5	33.9	45.2	53.4	71.1	71.7
P75.2S10m	4	0.53	0.5	15	9208	15.5241	7.5639	10.97	21.94	3.60	2.59	67.2	48.5	23.4	35.6	41.1	69.9	70.3
P67.2S10	4	0.53	0.5	15	9779	11.1665	5.1305	7.40	23.59	2.55	1.68	68.5	59.3	40.7	53.5	61.5	72.5	73.1
P67.2S10	4	0.53	0.5	15	9398	13.4395	6.4705	7.92	21.86	2.56	1.57	67.5	57.1	36.5	54.0	64.5	71.0	71.6
Ave	4	0.53	0.5	15	9414	13.4389	6.4452	8.94	22.38	2.94	1.97	67.6	55.1	33.6	47.1	55.1	71.1	71.7
P76.1S80m	4	4.22	0.5	15	9398	14.6209	5.5683	12.14	18.32	3.51	2.72	72.4	38.6	15.2	32.4	33.5	74.3	74.6
P76.2S80m	4	4.22	0.5	15	9271	14.6540	6.4685	11.69	17.33	3.46	2.47	69.4	43.4	18.4	36.2	41.7	71.5	71.8
P68.2S80	4	4.22	0.5	15	9271	14.4685	5.7385	9.69	19.08	2.79	1.82	71.6	44.4	22.3	46.9	55.6	73.9	74.2
P68.2S80	4	4.22	0.5	15	9525	14.9015	5.7955	9.49	18.31	2.83	2.02	72.0	45.2	23.9	45.8	51.2	74.4	74.8
Ave	4	4.22	0.5	15	9366	14.6612	5.8927	10.75	18.26	3.15	2.26	71.3	42.9	19.9	40.3	45.5	73.5	73.9

Upper Freeport Coal, 200 mesh x 0, wet ground

Run #	C (%)	RCR	PCR	T (-)	N (rpm)	P (g)	R (g)	Ap (%)	Ar (%)	Sp (%)	PSP (%)	Y (%)	ARJ (%)	ARD (%)	SRJ (%)	PSRJ (%)	Yc (%)	BTU
								Af		Sf	PSf							(BTU)
								13.27		2.23	1.69							13116
U71.1S10m	4	0.53	0.5	30	13970	19.5025	1.7073	7.32	73.54	1.34	0.63	92.0	49.5	45.0	44.7	65.5	98.3	99.4
U71.2S10m	4	0.53	0.5	30	14097	19.9268	1.6610	7.27	74.93	1.29	0.64	92.3	49.6	45.4	46.6	64.8	98.7	99.9
U69.2S10	4	0.53	0.5	30	14160	18.0285	1.6435	6.36	73.91	1.14	0.52	91.6	55.9	51.9	53.1	72.1	98.9	>99.9
U69.2S10	4	0.53	0.5	30	13970	18.9200	1.6335	6.39	73.50	1.15	0.56	92.1	55.5	51.7	52.5	69.8	99.3	>99.9
Ave	4	0.53	0.5	30	14049	19.0945	1.6613	6.84	73.97	1.23	0.59	92.0	52.6	48.5	49.3	68.1	98.8	>99.9
U72.1S80m	4	4.22	0.5	30	14224	19.4800	1.4712	8.52	64.44	1.23	0.57	93.0	40.5	36.0	48.7	68.4	98.1	99.0
U72.2S80m	4	4.22	0.5	30	13970	19.7982	1.5758	8.54	64.22	1.39	0.77	92.6	40.6	35.9	42.3	57.5	97.7	98.6
U70.2S80	4	4.22	0.5	30	14097	17.2815	1.6670	7.29	64.40	1.32	0.58	91.2	49.7	44.9	46.0	68.9	97.4	98.5
U70.2S80	4	4.22	0.5	30	13970	18.9200	1.6825	8.39	63.73	1.19	0.58	91.8	41.7	36.5	51.0	68.8	96.9	97.8
Ave	4	4.22	0.5	30	14065	18.8699	1.5991	8.19	64.20	1.28	0.63	92.2	43.1	38.3	47.0	65.9	97.6	98.5

**APPENDIX G: AGGLOMERATION TEST RESULTS USING
ALCOHOLS BEFORE AGGLOMERATION**

NOMENCLATURE

1. Af: Ash Content of Feed Coal (%)
2. Ap: Ash Content of Product Coal (%)
3. Ar: Ash Content of Refuse (%)
4. ARD: Ash Reduction (%)
$$ARD = (1 - Ap/Af) \times 100$$
5. ARJ: Ash Rejection (%)
$$ARJ = 100 - Y \times Ap / Af$$
6. (Stu)f: Calorific Value of Feed (Stu/lb)
7. (Stu)p: Calorific Value of Product (Stu/lb)
8. BTU: Btu Recovery (%),
$$BTU = (Stu)p / (Stu)f \times Y$$
9. C: Coal Slurry Concentration (Wt.%)
10. N: Mixing Speed (rpm)
11. P: Product Coal Weight (g)
12. PCR: Pentane/Coal Ratio (Weight Basis)
13. PSf: Pyritic Sulfur Content of Feed (%)
14. PSp: Pyritic Sulfur Content of Product (%)
15. PSRJ: Pyritic Sulfur Rejection (%)
$$PSRJ = (100 - Y \times PSp / PSf)$$
16. R: Refuse Weight (g)
17. RCR: Reagent to Coal Ratio
18. Sf: Total Sulfur Content in the Feed (%)
19. Sp: Total Sulfur Content in the Product (%)
20. SRJ: Total Sulfur Rejection (%)
$$SRJ = (100 - Y \times Sp / Sf)$$
21. T: Agglomeration Time (s)
22. Y: Overall Yield (%)
$$Y = P / (P + R) \times 100$$
23. Yc: Clean Coal Yield (%)
$$Yc = Y \times (100 - Ap) / (100 - Af)$$

Agglomeration Tests Without any Additives

Illinois # 6 Coal, Wet Ground to 200 mesh x 0

Run #	C (%)	RCR	PCR	T (s)	N (rpm)	P (g)	R (g)	Af		Sf		Psf		ARD	SRJ	PSRJ	Yc (%)	(Btu)f 11265
								Ap (%)	Ar (%)	Sp (%)	Psp (%)	Y (%)	ARJ (%)					
1152.1*0m	4	0.00	0.5	30	14224	13.3884	4.9340	7.64	30.09	3.15	1.70	73.1	63.9	50.6	46.6	57.4	79.8	80.9
1152.2*0m	4	0.00	0.5	30	14224	16.1703	4.8164	8.58	31.00	3.01	1.75	77.1	57.2	44.5	46.2	53.8	83.3	84.3
1152.3*0m	4	0.00	0.5	30	14478	14.4016	4.4298	8.57	30.87	2.95	1.43	76.5	57.6	44.5	47.7	62.5	82.7	83.7
1160.1*0m	4	0.00	0.5	30	13970	15.4265	5.3848	9.41	31.56	3.04	2.16	74.1	58.5	44.1	44.5	48.4	80.7	81.8
1160.2*0m	4	0.00	0.5	30	14224	14.2698	5.5881	8.78	30.82	2.88	1.90	71.9	62.5	47.8	49.0	56.0	78.8	79.9
1160.3*0m	4	0.00	0.5	30	14224	15.2588	5.6648	9.61	29.90	2.99	1.98	72.9	58.3	42.9	46.3	53.4	79.2	80.3
1173.1m	4	0.00	0.5	30	14097	11.3900	6.4200	8.29	24.73	2.59	1.72	64.0	68.3	50.4	62.0	68.3	70.4	71.5
1173.2m	4	0.00	0.5	30	14224	12.8100	7.1100	9.04	23.56	2.74	1.87	64.3	65.2	45.9	59.6	65.3	70.2	71.2
1173.3m	4	0.00	0.5	30	14097	11.0700	7.5800	8.50	23.04	2.53	1.46	59.4	69.8	49.2	65.6	75.0	65.2	66.2
Ave	4	0.00	0.5	30	14196	13.7984	5.7698	8.71	28.40	2.88	1.78	70.3	62.4	46.6	51.9	60.0	76.7	77.7

Agglomeration Tests Without any Additives

Pittsburgh # 8 Coal, Wet Ground to 200 mesh x 0

Run #	C (%)	RCR	PCR (-)	T (s)	N (rpm)	P (g)	R (g)	Af		Sf		Psf		Y (%)	ARJ (%)	ARD (%)	SRJ (%)	PSRJ (%)	Yc (%)	BTU (%)
								11.27	3.84	3.06	12543									
P147.1*0m	4	0.00	0.5	15	9779	14.3144	4.5188	5.89	22.41	2.24	1.42	76.0	60.3	47.7	55.7	64.7	80.6	81.3		
P147.2*0m	4	0.00	0.5	15	9525	13.8924	3.8596	5.69	24.57	2.25	1.43	78.3	60.5	49.5	54.1	63.4	83.2	83.9		
P147.3*0m	4	0.00	0.5	15	9779	14.4231	4.6448	5.03	20.03	2.32	1.50	75.6	66.2	55.4	54.3	62.9	81.0	81.8		
P60.150	4	0.00	0.5	15	9398	14.8755	5.3475	7.25	25.52	2.52	1.64	73.6	55.9	40.0	50.7	59.6	77.6	78.2		
P60.150	4	0.00	0.5	15	9271	13.3570	5.6895	6.14	22.67	2.22	1.27	70.1	64.4	49.2	58.6	70.1	74.9	75.6		
P141.1m	4	0.00	0.5	15	9100	13.5649	4.1765	8.45	24.08	2.36	1.45	76.5	49.8	34.3	45.2	56.1	80.3	80.9		
P141.2m	4	0.00	0.5	15	9100	8.5649	2.9344	4.61	28.17	2.03	1.13	74.5	73.3	64.2	54.0	66.7	81.5	82.6		
P141.3m	4	0.00	0.5	15	9100	11.8013	4.1792	6.52	25.43	2.29	1.42	73.8	62.6	49.3	48.6	58.5	79.2	80.1		
P141.4m	4	0.00	0.5	15	9100	10.9539	3.8755	5.95	24.81	2.17	1.23	73.9	65.8	53.7	51.3	64.0	79.7	80.6		
P141.5m	4	0.00	0.5	15	9100	12.6331	4.9879	6.10	23.18	2.23	1.31	71.7	66.0	52.6	51.4	62.8	77.3	78.1		
P141.6m	4	0.00	0.5	15	9100	12.9523	6.0705	6.66	20.76	2.25	1.27	68.1	64.7	48.2	53.4	65.8	72.9	73.7		
P141.7m	4	0.00	0.5	15	9100	12.1000	4.5001	5.90	21.90	2.20	1.36	72.9	66.6	54.1	51.3	60.8	78.7	79.6		
P141.8m	4	0.00	0.5	15	9100	14.0596	5.5483	5.78	21.92	2.29	1.40	71.7	67.8	55.1	50.1	60.3	77.5	78.4		
Ave	4	0.00	0.5	15	9273	12.8840	4.6410	6.15	23.50	2.26	1.37	73.6	63.4	50.2	52.2	62.8	78.8	79.6		

Agglomeration Tests Without any Additives

Upper Freeport Coal, Wet Ground to 200 mesh x 0

Run #	C (%)	RCR -	PCR (-)	T (s)	N (rpm)	P (g)	R (g)	Af		Sf		Psf		SRJ (%)	PSRJ (%)	Yc (%)	BTU (%)
								(%)	(%)	(%)	(%)	(%)	(%)				
								13.40		1.91	1.42						13093
U145.1*0m	4	0.00	0.5	30	14224	17.4726	1.2857	6.62	77.85	1.25	0.69	93.1	54.0	50.6	39.0	54.4	>99.9
U145.2*0m	4	0.00	0.5	30	14859	18.9935	1.5365	6.75	79.97	1.17	0.57	92.5	53.4	49.6	43.3	62.6	>99.9
U145.3*0m	4	0.00	0.5	30	14351	16.8754	1.4022	6.67	78.65	1.23	0.60	92.3	54.0	50.2	40.5	60.7	>99.9
Ave	4	0.00	0.5	30	14478	17.7805	1.4081	6.68	78.82	1.22	0.62	92.7	53.8	50.1	41.0	59.2	>99.9

Methanol

Illinois # 6 Coal, 200 mesh x 0, Vet Ground

Run #	C (%)	RCR lb/T (-)	T (s)	N (rpm)	P (g)	R (g)	Af		Sf		PSf		(Btu)f					
							Ap (%)	Ar (%)	Sp (%)	Psp (%)	Y (%)	ARJ (%)	ARD (%)	SRJ (%)	PSRJ (%)	Yc (%)	BTU (%)	
								16.31		4.59	3.49							11132
178.1AC20.1	4	1.06	0.5	30	14097	13.4150	4.9275	9.42	25.74	3.39	2.02	73.1	57.8	42.2	46.0	57.6	79.2	80.1
178.1AC20.2	4	1.06	0.5	30	14224	11.9735	4.4620	9.24	25.57	3.42	1.83	72.9	58.7	43.3	45.7	61.8	79.0	80.0
Ave	4	1.06	0.5	30	14161	12.6943	4.6948	9.33	25.66	3.41	1.93	73.0	58.2	42.8	45.9	59.7	79.1	80.0
178.1AC200.1	4	10.56	0.5	30	14478	10.8795	4.3885	8.88	26.66	3.38	1.80	71.3	61.2	45.6	47.5	63.3	77.6	78.6
178.1AC200.2	4	10.56	0.5	30	14415	12.0635	4.8275	8.81	26.97	3.34	1.74	71.4	61.4	46.0	48.0	64.3	77.8	78.8
Ave	4	10.56	0.5	30	14447	11.4715	4.6080	8.85	26.82	3.36	1.77	71.3	61.3	45.8	47.8	63.8	77.7	78.7

Methanol

Pittsburgh # 8 Coal, 200 mesh x 0, Wet Ground

Run #	C (%)	RCR lb/T (-)	PCR (-)	T (s)	N (rpm)	P (g)	R (g)	Af		Sf		Y	ARJ	ARD	SRJ	PSRJ	Yc	BTU
								(%)	(%)	(%)	(%)	(%)	(%)	(%)	(%)	(%)	(%)	(%)
								13.93		3.76	2.99							(Btu)f 12110
P79.1AC20.2	4	1.06	0.5	15	9589	13.0206	6.5155	7.94	25.22	2.71	1.76	66.6	62.0	43.0	52.0	60.7	71.3	72.0
P79.1AC200.1	4	10.56	0.5	15	9716	14.3460	9.1320	7.40	23.59	2.73	1.83	61.1	67.5	46.9	55.6	62.5	65.7	66.5
P79.1AC200.2	4	10.56	0.5	15	9589	14.5516	8.3340	7.92	21.86	2.81	1.90	63.6	63.8	43.1	52.5	59.5	68.0	68.7
Ave	4	10.56	0.5	15	9652	14.4488	8.7330	7.66	22.73	2.77	1.87	62.3	65.7	45.0	54.1	61.0	66.9	67.6

Methanol

Upper Freeport Coal, 200 mesh x 0, Wet Ground

Run #	C (%)	RCR	PCR (-)	T (s)	N (rpm)	P (g)	R (g)	AP (%)	AF (%)	Sp (%)	PSP (%)	Y (%)	ARJ (%)	ARD (%)	SRJ (%)	PSRJ (%)	YC (%)	BTU (%)	(Btu) f
									13.08	2.23	1.70								13149
U77.1AC20.1	4	1.06	0.5	30	14097	18.6255	1.1785	7.11	78.36	1.26	0.68	94.0	48.9	45.6	46.9	62.5	>99.9	>99.9	
U77.1AC20.2	4	1.06	0.5	30	14351	17.5840	1.2570	6.93	79.90	1.18	0.52	93.3	50.6	47.0	50.6	71.6	99.9	>99.9	
Ave	4	1.06	0.5	30	14224	18.1048	1.2178	7.02	79.13	1.22	0.60	93.7	49.7	46.3	48.7	67.0	>99.9	>99.9	
U77.1AC200.1	4	10.56	0.5	30	14351	18.9860	1.2940	7.04	79.78	1.24	0.68	93.6	49.6	46.2	47.9	62.6	>99.9	>99.9	
U77.1AC200.2	4	10.56	0.5	30	14351	16.4045	1.5554	6.93	79.90	1.23	0.60	91.3	51.6	47.0	49.6	67.9	97.8	98.9	
Ave	4	10.56	0.5	30	14351	17.6953	1.4247	6.99	79.84	1.24	0.64	92.5	50.6	46.6	48.8	65.3	99.0	>99.9	

Ethanol

Illinois # 6 Coal, 200 mesh x 0, Wet Ground

Run #	C (%)	RCR	PCR (-)	T (s)	N (rpm)	P (g)	R (g)	Af		Sf		PSf		ARD	SRJ	PSRJ	Yc (%)	BTU (%)
								Ap (%)	Ar (%)	Sp (%)	PSp (%)	Y (%)	ARJ (%)					
								16.31		4.59	3.49							(BTU)f 11132
185.2AC20.1	4	1.06	0.5	30	14034	14.4720	5.0315	9.34	27.83	3.59	2.11	74.2	57.1	42.2	42.0	55.1	80.2	81.2
185.2AC20.2	4	1.06	0.5	30	13970	13.9915	4.4830	9.76	29.00	3.67	2.20	75.7	54.3	39.6	39.4	52.2	81.5	82.4
Ave	4	1.06	0.5	30	14002	14.2318	4.7573	9.55	28.42	3.63	2.16	75.0	55.7	40.9	40.7	53.6	80.9	81.8
185.2AC200.1	4	10.56	0.5	30	13907	15.1275	4.0530	9.80	32.09	3.66	2.15	78.9	52.2	39.4	37.1	51.3	84.9	85.8
185.2AC200.2	4	10.56	0.5	30	13970	15.4720	4.4305	8.81	26.97	3.81	2.41	77.7	57.6	45.5	35.5	46.4	84.6	85.6
Ave	4	10.56	0.5	30	13939	15.2998	4.2418	9.31	29.53	3.74	2.28	78.3	54.9	42.4	36.3	48.8	84.7	85.7

Ethanol

Pittsburgh # 8 Coal, 200 mesh x 0, Wet Ground

Run #	C (%)	RCR	PCR	T (s)	N (rpm)	P (g)	R (g)	Af		Sf		PSP	Y	ARJ	ARD	SRJ	PSRJ	Yc	(Btu)f 12307
								Ap	Ar	Sp	PSf								
								(%)	(%)	(%)	(%)	(%)	(%)	(%)	(%)	(%)	(%)	(%)	
P90.5E20m	4	1.06	0.5	15	9271	15.3768	5.4318	8.66	25.42	2.39	1.88	73.9	49.7	31.9	53.0	53.1	53.1	77.3	77.9
P90.6E20m	4	1.06	0.5	15	9398	14.7964	5.2625	8.59	27.34	2.36	1.86	73.8	50.2	32.5	53.7	53.7	53.7	77.3	77.8
P80.1E20m	4	1.06	0.5	15	9398	14.7066	5.7840	10.65	28.01	2.93	1.95	73.0	46.6	25.6	44.1	52.8	52.8	74.8	75.3
P86.2AC20.1	4	1.06	0.5	15	9271	15.8695	6.4385	8.23		2.56	1.71	73.1	58.1	41.1	51.6	59.3	59.3	75.9	76.6
Ave	4	1.06	0.5	15	9335	15.1873	5.7292	9.03	26.92	2.56	1.85	72.6	51.1	32.8	50.6	54.7	54.7	76.3	76.9
P90.8E200m	4	10.56	0.5	15	9271	13.2714	6.1736	7.56	25.00	2.30	1.90	68.3	59.4	40.6	58.3	56.3	56.3	72.3	72.9
P79.1AC200.1	4	10.56	0.5	15	9589	15.6900	5.7585	8.08	28.18	2.48		73.2	57.7	42.2	51.8			78.2	79.0
P79.1AC200.2	4	10.56	0.5	15	9398	15.8285	6.0985	7.82	28.73	2.38	1.61	72.2	59.6	44.0	54.3	61.0	61.0	77.3	78.2
Ave	4	10.56	0.5	15	9419	14.9300	6.0102	7.82	27.30	2.39	1.76	71.2	58.9	42.3	54.8	58.6	58.6	75.9	76.7

Ethanol

Upper Freeport Coal, 200 mesh x 0, Wet Ground

Run #	C (%)	RCR	PCR (-)	T (s)	N (rpm)	P (g)	R (g)	Af		Sf		PSf		ARD	SRJ	PSRJ	Yc (%)	(Btu)f 13118
								Ap (%)	Ar (%)	Sp (%)	Psp (%)	Y (%)	ARJ (%)					
U81.1E20m	4	1.06	0.5	30	14097	20.2272	1.4636	7.42	77.14	1.67	0.82	93.3	48.1	44.3	30.2	54.9	99.6	>99.9
U81.2E20m	4	1.06	0.5	30	14224	20.0368	1.4199	6.84	77.62	1.58	0.79	93.4	52.0	48.6	33.8	56.5	>99.9	>99.9
U84.2AC20.1	4	1.06	0.5	30	13843	19.4615	1.3520	7.36	78.72	1.50	0.87	93.5	47.9	44.3	37.1	52.1	99.8	>99.9
U84.2AC20.2	4	1.06	0.5	30	13970	20.6485	1.4490	7.41	79.10	1.52	0.91	93.4	47.6	43.9	36.3	49.9	99.7	>99.9
Ave	4	1.06	0.5	30	14034	20.0935	1.4211	7.26	78.15	1.57	0.85	93.4	48.9	45.3	34.4	53.3	99.9	>99.9
U81.3E200m	4	10.56	0.5	30	13970	20.4095	1.4666	7.39	77.58	1.65	0.91	93.3	48.2	44.5	31.0	49.9	99.7	>99.9
U84.2AC200.1	4	10.56	0.5	30	14097	21.4810	1.5800	7.22	79.40	1.45	0.80	93.1	49.1	45.4	39.4	56.1	99.6	>99.9
U84.2AC200.2	4	10.56	0.5	30	14034	19.8725	1.5310	7.28	79.68	1.50	0.92	92.8	48.9	44.9	37.5	49.7	99.2	>99.9
Ave	4	10.56	0.5	30	14034	20.5877	1.5259	7.30	78.89	1.53	0.88	93.1	48.7	44.9	36.0	51.9	99.5	>99.9

**APPENDIX H: AGGLOMERATION TEST RESULTS USING
MONOMERS DURING GRINDING**

NOMENCLATURE

1. Af: Ash Content of Feed Coal (%)	13. Psf: Pyritic Sulfur Content of Feed (%)
2. Ap: Ash Content of Product Coal (%)	14. Psp: Pyritic Sulfur Content of Product (%)
3. Ar: Ash Content of Refuse (%)	15. PSRJ: Pyritic Sulfur Rejection (%)
4. ARD: Ash Reduction (%)	$PSRJ = (100 - Y \times Psp / Psf)$
$ARD = (1 - Ap / Af) \times 100$	16. R: Refuse Weight (g)
5. ARJ: Ash Rejection (%)	17. RCR: Resagent to Coal Ratio
$ARJ = 100 - Y \times Ap / Af$	18. Sf: Total Sulfur Content in the Feed (%)
6. (Btu)f: Calorific Value of Feed (Btu/lb)	19. Sp: Total Sulfur Content in the Product (%)
7. (Btu)p: Calorific Value of Product (Btu/lb)	20. SRJ: Total Sulfur Rejection (%)
8. BTU: Btu Recovery (%)	$SRJ = (100 - Y \times Sp / Sf)$
$BTU = (Btu)p / (Btu)f \times Y$	21. T: Agglomeration Time (s)
9. C: Coal Slurry Concentration (wt.%)	22. Y: Overall Yield (%)
10. N: Mixing Speed (rpm)	$Y = P / (P + R) \times 100$
11. P: Product Coal Weight (g)	23. Yc: Clean Coal Yield (%)
12. PCR: Pentane/Coal Ratio (Weight Basis)	$Yc = Y \times (100 - Ap) / (100 - Af)$

Tall Oil

Illinois # 6 Coal, 200 mesh x 0, wet ground

Run #	C (%)	RCR	PCR (-)	T (s)	M (rpm)	P (g)	R (g)	Af		Sf		PSf		A1J (%)	ARD (%)	SRJ (%)	PSRJ (%)	Yc (%)	BTU (%)
								15.86	4.31	3.12	(btu)f		11202						
194.1PL0.1	4	0.00	0.5	30	13970	14.0218	4.2660	9.49	31.31	3.86	2.39	76.7	54.1	40.2	31.3	41.4	82.5	83.4	
194.1PL0.2	4	0.00	0.5	30	14097	14.1220	5.4735	10.94	26.05	3.82	2.42	72.1	50.3	31.0	36.1	44.2	76.3	76.9	
1104.1PL0.1	4	0.00	0.5	30	14224	14.4145	5.5444	9.43	29.19	3.38	1.91	72.2	57.6	41.3	43.4	55.7	77.9	78.8	
1104.1PL0.2	4	0.00	0.5	30	14097	15.5970	4.5505	10.33	28.67	3.36	2.18	77.4	50.2	35.7	39.6	46.0	82.7	83.5	
1104.1PL0.3	4	0.00	0.5	30	14224	15.3770	5.6110	10.34		3.62	1.69	73.3	52.9	35.7	38.5	60.3	78.3	79.1	
Ave	4	0.00	0.5	30	14122	14.7065	5.0891	10.11	28.81	3.61	2.12	74.3	53.0	36.8	37.8	49.5	79.5	80.4	
195.1PL20.1	4	1.06	0.5	30	14034	11.8705	6.6443	8.99	25.04	3.64	2.29	64.1	63.7	43.3	45.9	53.0	69.3	70.2	
195.1PL20.2	4	1.06	0.5	30	14224	14.7675	8.1490	10.23	23.12	3.45	2.07	64.4	58.4	35.5	48.4	57.4	68.8	69.4	
Ave	4	1.06	0.5	30	14129	13.3190	7.3967	9.61	24.08	3.55	2.18	64.3	61.0	39.4	47.1	55.2	69.1	69.8	
1105.1PL40.1	4	2.12	0.5	30	13970	12.8290	3.7110	9.75	31.44	3.64	2.43	77.6	52.9	39.3	33.3	38.1	83.4	84.3	
1105.1PL40.2	4	2.12	0.5	30	13970	12.2225	3.4935	8.89	32.22	3.60	2.02	77.8	57.0	44.7	33.8	48.3	84.4	85.5	
1105.1PL40.3	4	2.12	0.5	30	14160	12.3115	3.8875	9.34	31.63	3.44	1.82	76.0	55.8	41.9	38.2	54.6	82.1	83.1	
Ave	4	2.12	0.5	30	14033	12.4543	3.6973	9.33	31.76	3.56	2.09	77.1	55.2	42.0	35.1	47.0	83.3	84.3	
196.1PL200.1	4	10.56	0.5	30	13907	15.1455	5.5525	11.19	26.48	3.81	2.37	73.2	48.4	29.4	42.6	49.6	77.2	77.9	
196.1PL200.2	4	10.56	0.5	30	14351	15.0255	4.0940	11.08	30.54	3.74	2.23	78.6	45.1	30.1	39.5	49.1	83.1	83.8	
Ave	4	10.56	0.5	30	14129	15.0855	4.8233	11.14	28.51	3.78	2.30	75.9	46.7	29.8	41.1	49.4	80.1	80.8	
1106.1PL400.1	4	21.12	0.5	30	14224	11.9695	4.4290	10.65	27.41	3.73	2.38	73.0	51.6	33.7	35.6	42.8	77.7	78.5	
1106.1PL400.2	4	21.12	0.5	30	13970	13.1350	3.9330	11.72	26.66	4.16	2.79	77.0	43.9	27.1	24.3	29.5	80.9	81.6	
1106.1PL400.3	4	21.12	0.5	30	13970	14.9605	3.8090	10.89		3.92	2.40	79.7	46.0	32.2	26.1	37.1	84.6	85.4	
Ave	4	21.12	0.5	30	14055	13.3550	4.0570	11.09	27.04	3.94	2.52	76.6	47.2	31.0	28.7	36.5	81.1	81.8	

Tall Oil

Pittsburgh # 8 Coal, 200x0 mesh, wet ground

Run #	C (%)	RCR (lb/T)	PCR (-)	T (s)	N (rpm)	P (g)	R (g)	Af		Sf		PSf		ARJ (%)	ARD (%)	SRJ (%)	PSRJ (%)	Yc (%)	(Btu)f 12281
								Ap (%)	Ar (%)	Sp (%)	Psp (%)	Y (%)	ARJ (%)						
								12.88		3.19	2.47								
P121.1PL0.1	4	0.00	0.5	15	9779	13.1550	4.7820	6.56	22.68	2.30	1.64	73.3	62.6	49.1	47.1	51.4	78.7	79.5	
P121.1PL0.2	4	0.00	0.5	15	10351	13.8380	4.6670	6.84	23.55	2.70	1.66	74.8	60.3	46.9	36.7	49.7	80.0	80.8	
P121.1PL0.3	4	0.00	0.5	15	10668	14.1120	4.6257	7.28	23.72	2.63	1.64	75.3	57.4	43.5	37.9	50.0	80.2	80.9	
Ave	4	0.00	0.5	15	10266	13.7017	4.6916	6.89	23.32	2.54	1.65	74.5	60.1	46.5	40.6	50.4	79.6	80.4	
P122.1PL20.1	4	1.06	0.5	15	10668	17.9825	6.3422	8.10	21.56	2.90	2.20	73.9	53.5	37.1	32.8	34.3	78.0	78.6	
P122.1PL20.2	4	1.06	0.5	15	10414	15.6455	5.8060	7.31	21.63	2.80	1.54	72.9	58.6	43.2	40.6	54.6	77.6	78.3	
P122.1PL20.3	4	1.06	0.5	15	10350	15.7930	5.7040	7.89	21.90	2.86	1.98	73.5	55.0	38.7	34.1	41.1	77.7	78.3	
Ave	4	1.06	0.5	15	10477	16.4737	5.9507	7.77	21.70	2.79	1.91	73.4	55.7	39.7	35.8	43.3	77.8	78.4	
P123.1PL200.1	4	10.56	0.5	15	10033	17.2310	3.1735	6.05	36.88	2.65	1.67	84.4	60.3	53.0	29.8	43.0	91.1	92.1	
P123.1PL200.2	4	10.56	0.5	15	10160	14.9665	2.0175	6.20	47.14	2.33	1.72	88.1	57.6	51.9	35.6	38.7	94.9	95.9	
P123.1PL200.3	4	10.56	0.5	15	10287	15.6267	3.2090	6.23	35.32	2.77	1.77	83.0	59.9	51.6	28.0	40.5	89.3	90.3	
Ave	4	10.56	0.5	15	10160	15.9414	2.8000	6.16	39.78	2.58	1.72	85.2	59.3	52.2	31.1	40.7	91.7	92.8	

Tall Oil

Upper Freeport Coal, 200 mesh x 0, wet ground

Run #	C (%)	RCR	PCR (-)	T (s)	M (rpm)	P (g)	R (g)	Af		Sf		PSf		ARD	SRJ	PSRJ	Yc (%)	BTU (%)
								Ap (%)	Ar (%)	Sp (%)	PSP (%)	Y (%)	ARJ (%)					
								14.59		2.27	1.52							(Btu)f 12882
U134.110m	4	0.00	0.5	30	14605	16.9889	1.5051	7.42	79.83	1.25	0.62	91.9	53.3	49.1	49.4	62.3	99.6	>99.9
U134.210m	4	0.00	0.5	30	14478	17.1083	1.5308	7.18	80.93	1.26	0.66	91.8	54.8	50.8	49.1	59.9	99.8	>99.9
U134.310m	4	0.00	0.5	30	14605	17.0263	1.4170	7.39	80.86	1.24	0.61	92.3	53.2	49.3	49.6	62.8	>99.9	>99.9
Ave	4	0.00	0.5	30	14563	17.0412	1.4843	7.33	80.54	1.25	0.63	92.0	53.8	49.8	49.3	61.7	99.8	>99.9
U135.1120m	4	1.06	0.5	30	14732	16.1516	1.4705	7.41	79.94	1.32	0.71	91.7	53.4	49.2	46.7	57.0	99.4	>99.9
U135.2120m	4	1.06	0.5	30	14478	14.8792	1.3744	6.54	78.67	1.31	0.64	91.5	59.0	55.2	47.2	61.2	>99.9	>99.9
U135.3120m	4	1.06	0.5	30	14605	16.5992	1.5317	7.24	80.16	1.31	0.71	91.6	54.6	50.4	47.2	57.0	99.4	>99.9
Ave	4	1.06	0.5	30	14605	15.8767	1.4589	7.06	79.59	1.31	0.69	91.6	55.7	51.6	47.0	58.4	99.7	>99.9
U13611200m	4	10.56	0.5	30	14605	15.5586	1.5610	7.49	79.51	1.30	0.62	90.9	53.3	48.7	48.0	62.7	98.4	99.8
U13621200m	4	10.56	0.5	30	14605	15.9345	1.4822	7.53	80.11	1.44	0.83	91.6	52.7	48.4	41.9	49.7	99.2	>99.9
U13631200m	4	10.56	0.5	30	14478	16.9563	1.5322	7.45	80.06	1.27	0.61	91.7	53.2	48.9	48.7	63.0	99.4	>99.9
Ave	4	10.56	0.5	30	14563	16.1498	1.5185	7.49	79.89	1.34	0.69	91.4	53.1	48.7	46.2	58.5	99.0	>99.9

Styrene

Illinois # 6 Coal, 200 mesh x 0, wet ground

Run #	C (%)	RCR	PCR (-)	T (s)	M (rpm)	P (g)	R (g)	Af		Sf		PSf		ARJ (%)	ARD (%)	SRJ (%)	PSRJ (%)	Yc (%)	BTU (%)	(Btu)f 11072
								Ap (%)	Ar (%)	Sp (%)	PSp (%)	Y (%)								
								16.70		4.31	3.11									
1112.2PL0.1	4	0.00	0.5	30	14288	14.4695	4.3315	9.84	28.15	3.40	1.88	76.9	54.7	41.1	39.3	53.7	83.3	84.3		
1112.2PL0.2	4	0.00	0.5	30	14351	18.4535	4.6355	9.68	28.95	3.53	2.14	79.9	53.7	42.0	34.5	45.1	86.7	87.7		
1112.2PL0.3	4	0.00	0.5	30	14288	13.8180	5.5140	10.09	29.46	3.81	2.01	71.5	56.8	39.6	36.8	53.9	77.1	78.1		
Ave	4	0.00	0.5	30	14309	15.5737	4.8270	9.87	28.85	3.58	2.01	76.1	55.1	40.9	36.9	50.9	82.4	83.4		
1113.2PL20.1	4	1.06	0.5	30	14351	14.3945	4.7860	10.09	29.46	3.73	2.40	75.0	54.7	39.6	35.1	42.1	81.0	82.0		
1113.2PL20.2	4	1.06	0.5	30	14351	14.8700	4.8635	10.55	28.73	3.51	2.19	75.4	52.4	36.8	38.6	47.1	80.9	81.8		
1113.2PL20.3	4	1.06	0.5	30	14478	13.4235	4.5010	9.93	29.22	3.84	2.19	74.9	55.5	40.5	33.3	47.3	81.0	81.9		
Ave	4	1.06	0.5	30	14393	14.2293	4.7168	10.19	29.14	3.69	2.26	75.1	54.2	39.0	35.7	45.5	81.0	81.9		
1114.2PL200.1	4	10.56	0.5	30	14097	12.8695	4.1300	9.84	31.44	3.52	2.10	75.7	55.4	41.1	38.2	49.0	81.9	82.9		
1114.2PL200.2	4	10.56	0.5	30	13970	11.0165	4.0530	9.19	30.07	3.59	2.12	73.1	59.8	45.0	39.1	50.2	79.7	80.7		
1114.2PL200.3	4	10.56	0.5	30	14160	10.7330	3.5370	9.13	32.82	3.66	2.18	75.2	58.9	45.3	36.1	47.3	82.0	83.1		
Ave	4	10.56	0.5	30	14076	11.5397	3.9067	9.39	31.44	3.59	2.13	74.7	58.0	43.8	37.8	48.8	81.2	82.3		

Styrene

Pittsburgh # 8 Coal, 200 mesh x 0, wet ground

Run #	C (%)	RCR	PCR (-)	T (s)	M (rpm)	P (g)	R (g)	Af		Sf		PSf		SRJ (%)	PSRJ (%)	Yc (%)	BTU (%)
								Ap (%)	Ar (%)	Sp (%)	Psp (%)	Y (%)	ArJ (%)				
								12.85		3.39	2.62						(Btu)f 12286
P125.2PL0.1	4	0.00	0.5	30	9462	13.6620	4.1285	6.50	25.08	2.19	1.52	76.8	61.2	49.4	50.4	55.5	82.4
P125.2PL0.2	4	0.00	0.5	30	9525	15.6640	4.7100	7.04	23.79	2.23	1.30	76.9	57.9	45.2	49.4	61.8	82.8
P125.2PL0.3	4	0.00	0.5	30	9652	13.6811	4.3710	6.73	23.74	2.58	1.68	75.8	60.3	47.6	42.3	51.4	81.9
Ave	4	0.00	0.5	30	9546	14.3357	4.4032	6.76	24.20	2.33	1.50	76.5	59.8	47.4	47.4	56.2	82.7
P126.2PL20.1	4	1.06	0.5	30	9589	15.2605	4.4045	7.42	23.93	2.25	1.51	77.6	55.2	42.3	48.5	55.2	83.2
P126.2PL20.2	4	1.06	0.5	30	9716	15.1259	4.6000	7.30	23.91	2.80	1.75	76.7	56.4	43.2	36.7	48.9	82.3
P126.2PL20.3	4	1.06	0.5	30	9589	13.6811	4.3710	6.73	23.97	2.63	1.57	75.8	60.3	47.6	41.2	54.5	81.9
Ave	4	1.06	0.5	30	9631	14.6892	4.4585	7.15	23.94	2.56	1.61	76.7	57.3	44.4	42.1	52.9	82.5
P127.2PL200.1	4	10.56	0.5	30	9716	16.1865	6.8490	7.72	21.00	2.50	1.81	70.3	57.8	39.9	48.2	51.3	74.4
P127.2PL200.2	4	10.56	0.5	30	9716	19.3900	9.0267	7.97	18.16	2.47	1.51	68.2	57.7	38.0	50.3	60.7	72.7
P127.2PL200.3	4	10.56	0.5	30	9652	17.0705	5.6665	7.48	21.51	2.69	1.74	75.1	56.3	41.8	40.4	50.1	80.4
Ave	4	10.56	0.5	30	9694	17.5490	7.1807	7.72	20.22	2.55	1.69	71.2	57.3	39.9	46.3	54.0	76.0

Styrene

Upper Freeport Coal, 200 mesh x 0, wet ground

Run #	C (%)	RCR	PCR (-)	T (s)	N (rpm)	P (g)	R (g)	Af		Sf		PSf		ARD (%)	SRJ (%)	PSRJ (%)	Yc (%)	BTU (%)
								13.00	2.01	1.40	13164							
U128.2PL0.1	4	0.00	0.5	30	14224	18.0244	1.5328	7.36	81.38	1.24	0.61	92.2	47.8	43.4	43.1	59.9	98.1	99.2
U128.2PL0.2	4	0.00	0.5	30	14238	19.3652	1.5412	7.28	81.68	1.54	0.94	92.6	48.1	44.0	29.0	37.6	98.7	99.8
U128.2PL0.3	4	0.00	0.5	30	14238	17.1412	1.2224	7.21	81.21	1.42	0.79	93.3	48.2	44.5	34.1	47.2	99.6	>99.9
U128.2PL0.4	4	0.00	0.5	30	14224	13.1675	1.3490	7.11	81.92	1.04	0.53	90.7	50.4	45.3	53.1	65.9	96.8	97.9
U128.2PL0.5	4	0.00	0.5	30	14478	13.9920	1.0565	7.05	80.85	1.38	0.77	93.0	49.6	45.8	36.2	48.8	99.3	>99.9
Ave	4	0.00	0.5	30	14280	16.3381	1.3404	7.20	81.41	1.32	0.73	92.4	48.8	44.6	39.2	52.0	98.5	99.6
U129.2PL20.1	4	1.06	0.5	30	14351	18.5072	1.4727	7.55	81.48	1.42	0.81	92.6	46.2	41.9	34.6	46.3	98.4	99.4
U129.2PL20.2	4	1.06	0.5	30	14351	17.9185	1.4610	7.55	81.65	1.40	0.92	92.5	46.3	41.9	35.6	39.2	98.3	99.2
U129.2PL20.3	4	1.06	0.5	30	14478	18.1049	1.4840	7.67	81.75	1.45	0.86	92.4	45.5	41.0	33.3	43.1	98.1	99.1
Ave	4	1.06	0.5	30	14393	18.1769	1.4726	7.59	81.63	1.42	0.86	92.5	46.0	41.6	34.5	42.9	98.3	99.2
U130.2PL200.1	4	10.56	0.5	30	14351	17.0590	1.4105	7.30	82.13	1.19	0.58	92.4	48.1	43.8	45.3	61.9	98.4	99.5
U130.2PL200.2	4	10.56	0.5	30	14224	16.8045	1.2240	7.23	81.82	1.14	0.54	93.2	48.2	44.4	47.1	64.2	99.4	>99.9
U130.2PL200.3	4	10.56	0.5	30	14351	17.0365	1.3970	7.16	81.86	1.42	0.82	92.4	49.1	44.9	34.7	45.8	98.6	99.7
U130.2PL200.4	4	10.56	0.5	30	14097	13.8280	1.1125	6.99	79.38	1.38	0.71	92.6	50.2	46.2	36.5	53.0	98.9	>99.9
Ave	4	10.56	0.5	30	14256	16.1820	1.2860	7.17	81.30	1.28	0.66	92.6	48.9	44.8	40.9	55.7	98.8	99.9

**APPENDIX I: AGGLOMERATION TEST RESULTS USING
N-PENTANE AS AGGLOMERANT**

NOMENCLATURE

Af: Feed Ash Content (%)

Ap: Product Ash Content (%)

Ar: Refuse Ash Content (%)

ARD: Ash Reduction (%)

$$ARD = (1 - Ap/Af) \times 100$$

ARJ: Ash Rejection (%)

$$ARJ = 100 - Y \times Ap / Af$$

(Btu)f: Feed Calorific Value (Btu/lb)

(Btu)p: Product Calorific Value (Btu/lb)

BTU: Energy Recovery (%),

$$BTU = (Btu)p / (Btu)f \times Y$$

C: Coal-Water Slurry Concentration (wt.%)

GT: Grinding Time (min)

M: Mixing Speed (rpm)

P: Product Weight (g)

PCR: Pentane to Coal Ratio (Weight Basis)

pH AGGL: Agglomeration Test pH

pH GRIND: Grinding pH

PSf: Feed Pyritic Sulfur Content (%)

PSP: Product Pyritic Sulfur Content (%)

PSRJ: Pyritic Sulfur Rejection (%)

$$PSRJ = (100 - Y \times PSP / PSf)$$

R: Refuse Weight (g)

Sf: Feed Total Sulfur Content (%)

Sp: Feed Total Sulfur Content (%)

SRJ: Total Sulfur Rejection (%)

$$SRJ = (100 - Y \times Sp / Sf)$$

T: Agglomeration Time (s)

TEMP: Agglomeration Test Final Temperature (F)

Y: Overall Yield (%)

$$Y = P / (P + R) \times 100$$

Yc: Clean Coal Yield (%)

$$Yc = Y \times (100 - Ap) / (100 - Af)$$

Effect of Agglomeration Time on Performance for Upper Freeport Coal Wet Ground to 200 mesh x 0

Run #	C (%)	GT (min)	PCR (-)	T (s)	N (rpm)	P (g)	R (g)	Af		Sp (%)	Psp (%)	Y (%)	ARJ (%)	ARD (%)	SRJ (%)	PSRJ (%)	Yc (%)	BTU
								13.33	2.08		1.50							(Btu)/f
U1.BV169.1	2	15	0.5	15	9525	8.1867	1.2775	5.38	61.82	0.97	0.49	86.5	65.1	59.6	59.7	71.4	94.4	95.8
U1.BV169.2	2	15	0.5	15	9398	6.4279	1.1919	5.06	57.18	1.01	0.51	84.4	68.0	62.0	59.2	71.0	92.4	93.8
U1.BV169.3	2	15	0.5	15	9398	7.4905	1.2795	5.07	57.19	1.00	0.47	85.4	67.5	62.0	58.9	72.9	93.6	95.0
Ave	2	15	0.5	15	9440	7.3684	1.2496	5.17	58.73	0.99	0.49	85.4	66.9	61.2	59.2	71.8	93.5	94.8
U1.BV169.4	2	15	0.5	30	9462	6.3255	0.8600	5.63	62.74	0.94	0.44	88.0	62.8	57.8	60.2	73.9	95.9	97.2
U1.BV169.5	2	15	0.5	30	9525	6.5775	1.0835	5.64	62.46	0.96	0.59	85.9	63.7	57.7	60.4	65.9	93.5	94.8
U1.BV169.6	2	15	0.5	30	9716	7.3705	0.9195	5.55	64.88	0.95	0.46	88.9	63.0	58.4	59.4	72.4	96.9	98.3
Ave	2	15	0.5	30	9567	6.7578	0.9543	5.61	63.36	0.95	0.50	87.6	63.2	57.9	60.0	70.7	95.4	96.7
U1.BV169.7	2	15	0.5	60	9462	7.9645	0.7115	6.07	73.42	1.06	0.57	91.8	58.2	54.5	53.2	65.3	99.5	>99.9
U1.BV169.8	2	15	0.5	60	9398	6.8058	0.5880	6.07	71.08	1.03	0.53	92.0	58.1	54.5	54.4	67.7	99.8	>99.9
U1.BV169.9	2	15	0.5	60	9589	6.8801	0.5675	6.29	72.54	1.03	0.46	92.4	56.4	52.8	54.3	72.5	99.9	>99.9
Ave	2	15	0.5	60	9483	7.2168	0.6223	6.14	72.35	1.04	0.51	92.1	57.6	53.9	54.0	68.5	99.7	>99.9

Effect of Agglomeration Time on Performance for Pittsburgh # 8 Coal Wet Ground to 200 mesh x 0

Run #	C (%)	GT (min)	PCR (-)	T (s)	N (rpm)	P (g)	R (g)	Af		Sf		PSf		Y (%)	ARJ (%)	ARD (%)	SRJ (%)	PSRJ (%)	Yc (%)	BTU (%)
								12.06		3.50	2.63									12415
P8.BW151.1GT1	2	15	0.5	15	9589	6.3289	1.9668	4.70	32.92	1.72	0.89	76.3	70.3	61.0	62.5	74.1	82.7	83.7		
P8.BW151.1GT1	2	15	0.5	15	9589	6.7980	2.1131	4.77	32.49	1.51	0.71	76.3	69.8	60.4	67.1	79.4	82.6	83.6		
Ave	2	15	0.5	15	9589	6.5635	2.0400	4.74	32.71	1.62	0.80	76.3	70.0	60.7	64.8	76.8	82.6	83.6		
P8.BW151.1GT2	2	15	0.5	30	9652	6.5460	1.3188	3.53	48.72	1.71	0.96	83.2	75.6	70.7	59.3	69.6	91.3	92.6		
P8.BW151.1GT2	2	15	0.5	30	9525	7.3734	1.5060	4.01	44.74	1.65	0.82	83.0	72.4	66.7	60.9	74.1	90.6	91.8		
Ave	2	15	0.5	30	9589	6.9597	1.4124	3.77	46.73	1.68	0.89	83.1	74.0	68.7	60.1	71.8	91.0	92.2		
P8.BW151.1GT3	2	15	0.5	60	9779	7.5812	0.9972	3.35	62.69	1.60	0.78	88.4	75.5	72.2	59.6	73.8	97.1	98.5		
WWS9-1-P8	2	15	0.5	60	9517	8.4315	1.0105	3.45	64.34	2.02		89.3	75.8	72.9	52.0		98.8	>99.9		
Ave	2	15	0.5	60	9648	8.0064	1.0039	3.40	63.52	1.81	0.78	88.8	75.6	72.5	55.8	73.8	98.0	99.4		

Effect of Agglomeration Time on Performance for Pittsburgh # 8 Coal Wet Ground to 200 mesh x 0

Run #	C (%)	GT (min)	PCR (-)	T (s)	N (rpm)	P (g)	R (g)	Af		Sf		Psf		SRJ (%)	PSRJ (%)	Yc (%)	BTU (%)
								Ap (%)	Ar (%)	Sp (%)	PSp (%)	Y (%)	ARD (%)				
P8.151.1GT4	2	15	1.5	15	9652	7.5108	1.4674	4.52	44.59	1.79	1.00	83.7	68.6	57.2	68.4	90.8	91.9
WMS11-1-P8	2	15	1.5	15	9525	7.9205	1.9660	4.31	34.33	2.06		80.1	72.9	56.1		87.8	89.0
Ave	2	15	1.5	15	9589	7.7157	1.7167	4.42	39.46	1.93	1.00	81.9	70.8	56.7	68.4	89.3	90.5
P8.8W151.1GT5	2	15	1.5	30	9525	8.1850	1.3220	4.74	50.22	1.63	0.85	86.1	66.2	59.9	72.1	93.3	94.4
P8.8W151.1GT5	2	15	1.5	30	9525	7.2518	1.2777	3.92	49.84	1.64	0.82	85.0	72.4	60.2	73.5	92.9	94.1
Ave	2	15	1.5	30	9525	7.7184	1.2999	4.33	50.03	1.64	0.84	85.6	69.3	60.0	72.8	93.1	94.2
P8.8W151.1GT6	2	15	1.5	60	9525	7.7950	0.9150	3.84	60.88	1.58	0.71	89.5	71.5	59.6	75.8	97.9	99.2
P8.8W151.1GT6	2	15	1.5	60	9716	7.2875	0.9449	4.01	63.30	1.69	0.87	88.5	70.6	57.3	70.7	96.6	97.9
Ave	2	15	1.5	60	9620	7.5413	0.9300	3.93	62.09	1.64	0.79	89.0	71.0	58.4	73.2	97.2	98.5

Effect of Agglomeration Time on Performance for Illinois # 6 Coal Wet Ground to 200 mesh x 0

Run #	C (%)	GT (min)	PCR (-)	T (s)	N (rpm)	P (g)	R (g)	Af		Sf		PSf		ARD (%)	SRJ (%)	PSRJ (%)	Yc (%)	BTU (%)
								Ap (%)	Ar (%)	Sp (%)	PSp (%)	Y (%)	ARJ (%)					
								16.80		4.42	3.11							(Btu)/f 11057
16.BU168.1	2	15	0.5	15	9398	5.0095	4.3455	6.47	26.63	2.70	1.34	53.5	79.4	61.5	67.3	76.8	60.2	61.3
16.BU168.2	2	15	0.5	15	9398	5.2485	3.7705	6.91	28.14	2.79	1.55	58.2	76.1	58.9	63.3	71.1	65.1	66.2
16.BU168.3	2	15	0.5	15	9271	4.4085	3.9243	6.12	25.98	2.67	1.67	52.9	80.7	63.6	68.0	71.6	59.7	60.8
Ave	2	15	0.5	15	9356	4.8808	4.0134	6.50	26.92	2.72	1.52	54.9	78.7	61.3	66.2	73.2	61.7	62.8
16.BU168.4	2	15	0.5	30	9398	7.3865	4.6776	7.32	29.32	2.65	1.42	61.2	73.3	56.4	63.3	72.0	68.2	69.3
16.BU168.5	2	15	0.5	30	9271	6.2440	3.7685	7.34	29.77	2.74	1.28	62.4	72.8	56.3	61.3	74.4	69.5	70.6
16.BU168.6	2	15	0.5	30	9525	4.1239	3.3023	6.06	27.57	2.77	1.40	55.5	60.0	63.9	65.2	75.1	62.7	63.8
Ave	2	15	0.5	30	9398	5.9181	3.9161	6.91	28.89	2.72	1.37	59.7	75.3	58.9	63.3	73.8	66.8	67.9
16.BU168.7	2	15	0.5	60	9315	5.0447	2.8933	6.70	31.45	2.95	1.57	63.6	74.7	60.1	57.6	67.9	71.3	72.5
16.BU168.8	2	15	0.5	60	9462	4.3278	2.9256	5.84	29.60	2.78	1.61	59.7	79.3	65.2	62.5	69.2	67.5	68.8
16.BU168.9	2	15	0.5	60	9398	5.1605	3.3065	6.19	29.47	2.83	1.46	60.9	77.5	63.2	61.0	71.4	68.7	70.0
Ave	2	15	0.5	60	9391	4.8443	3.0418	6.24	30.17	2.85	1.55	61.4	77.2	62.8	60.3	69.5	69.2	70.4

Effect of Agglomeration Time on Performance for Illinois # 6 Coal Wet Ground to 200 mesh x 0

Run #	C (%)	TEMP (F)	PCR (-)	T (s)	N (rpm)	P (s)	R (s)	Af		Sf		Psf		(Btu)f 1094a							
								Ap (%)	Ar (%)	Sp (%)	Psp (%)	Y (%)	ARJ (%)	ARD (%)	SRJ (%)	PSRJ (%)	Yc (%)	BTU (%)			
								17.50		5.14	3.51										
I180/1.1	4	74	0.5	30	14097	12.4800	6.7900	9.02	23.59	3.28	1.31	64.8	66.6	48.5	58.7	75.8	71.4	72.5			
I180/1.2	4	74	0.5	30	14224	11.1600	7.9000	8.63	22.26	3.60	1.94	58.6	71.1	50.7	59.0	67.7	64.8	65.9			
AVE	4	74	0.5	30	14161	11.8200	7.3450	8.83	22.93	3.44	1.63	61.7	68.9	49.6	58.8	71.7	68.1	69.2			
I180/2.1	4	75	0.5	60	14478	10.9300	6.9800	8.82	21.75	3.10	1.51	61.0	69.2	49.6	63.2	73.7	67.4	68.5			
I180/2.2	4	76	0.5	60	14097	10.0100	5.8300	8.09	23.52	3.04	1.80	63.2	70.8	53.8	62.6	67.6	70.4	71.6			
I180/2.3	4	76	0.5	60	14097	10.5000	8.9300	9.89	19.76	3.09	1.46	54.0	69.5	43.5	67.5	77.5	59.0	59.8			
AVE	4	76	0.5	60	14224	10.4800	7.2467	8.93	21.68	3.08	1.59	59.4	69.8	49.0	64.4	73.0	65.6	66.6			
I180/3.1	4	78	0.5	120	14351	10.0500	8.1300	9.49	19.57	3.14	1.47	55.3	70.0	45.8	66.2	76.8	60.6	61.5			
I180/3.2	4	78	0.5	120	14224	11.4300	7.0700	9.12	20.56	2.95	1.03	61.8	67.8	47.9	64.5	81.9	68.1	69.1			
I180/3.3	4	79	0.5	120	14224	12.5500	6.4400	9.52	21.47	3.22	1.36	65.4	64.4	45.6	59.0	74.6	71.7	72.7			
AVE	4	78	0.5	120	14266	11.3433	7.2800	9.38	20.53	3.10	1.29	60.8	67.4	46.4	63.3	77.8	66.8	67.8			
I180/4.1	4	81	0.5	180	14097	11.6600	6.3000	9.58	23.49	3.33	1.48	64.9	64.5	45.3	57.9	72.6	71.2	72.2			
I180/4.2	4	82	0.5	180	14478	10.8500	6.1300	8.65	23.13	3.29	1.63	63.9	68.4	50.6	59.1	70.3	70.8	71.9			
I180/4.3	4	82	0.5	180	14224	11.7800	5.6700	9.38	23.03	3.17	1.34	67.5	63.8	46.4	58.4	74.2	74.2	75.2			
AVE	4	82	0.5	180	14266	11.4300	6.0333	9.20	23.22	3.26	1.49	65.4	65.6	47.4	58.5	72.4	72.0	73.1			

Effect of Agglomeration Time on Performance for Illinois # 6 Coal Wet Ground to 200 mesh x 0

Run #	C (%)	TEMP (F)	PCR (-)	T (s)	N (rpm)	P (g)	R (g)	Af		Sf		Psf		ARD	SRJ	PSRJ	Yc	BTU
								Ap	Ar	Sp	Err	Psp	Y					
								(%)	(%)	(%)		(%)	(%)	(%)	(%)	(%)	(%)	(Btu) f 11522
								13.78		3.94								
1181/1.2	4	83	0.5	180	14605	11.6200	7.6500	8.35	21.13	2.68		0.68	60.3	39.4	59.0	78.7	64.1	64.7
1181/1.3	4	84	0.5	180	14351	12.7000	7.1100	8.56	21.45	2.95		1.04	64.1	37.9	52.0	65.6	68.0	68.6
AVE	4	84	0.5	180	14478	12.1600	7.3800	8.46	21.29	2.82		0.86	62.2	38.6	55.5	72.2	66.0	66.6
1181/2.1	4	86	0.5	240	14224	11.2800	5.6100	8.30	23.42	3.10		1.21	66.8	39.8	47.5	58.2	71.0	71.7
1181/2.3	4	86	0.5	240	14224	12.1700	7.5800	9.16	21.26	3.14		1.11	61.6	33.5	50.9	64.7	64.9	65.4
AVE	4	86	0.5	240	14224	11.7250	6.5950	8.73	22.34	3.12		1.16	64.2	36.6	49.2	61.4	68.0	68.6
1181/3.1	4	91	0.5	300	14224	11.7300	6.0100	8.40	23.27	3.22		1.44	66.1	39.0	46.0	50.7	70.2	70.9
1181/3.2	4	88	0.5	300	14605	11.4000	6.8000	8.49	21.75	3.01		1.14	62.6	38.4	52.1	63.1	66.5	67.1
1181/3.3	4	89	0.5	300	14605	11.6900	6.7600	8.14	22.87	3.01		0.97	63.4	40.9	51.6	68.3	67.5	68.1
AVE	4	89	0.5	300	14478	11.6067	6.5233	8.34	22.63	3.08		1.18	64.0	39.5	49.9	60.7	68.1	68.7
1181/4.1	4	92	0.5	360	14478	14.4000	7.3700	9.31	20.80	3.25		1.54	66.1	32.4	45.4	47.2	69.6	70.1
1181/4.2	4	93	0.5	360	14478	12.3000	6.2800	7.90	23.14	3.11		1.16	66.2	42.7	47.7	60.3	70.7	71.4
1181/4.3	4	90	0.5	360	14224	12.4700	6.3800	9.51	22.10	3.27		1.46	66.2	31.0	45.1	50.0	69.4	69.9
AVE	4	92	0.5	360	14393	13.0567	6.6767	8.91	22.01	3.21		1.39	66.2	35.4	46.1	52.5	69.9	70.5

Pittsburgh # 8 Coal, 20 hr Jar Mill Grinding

Run #	C (%)	GT (min)	PCR (-)	T (s)	N (rpm)	P (g)	R (g)	Ap (%)	Ar (%)	Sp (%)	Psp (%)	Y (%)	ARJ (%)	ARD (%)	SRJ (%)	PSRJ (%)	Yc (%)	BTU
								12.00		3.69	2.94							(Btu)f 12424
P8-JV147.2GT1	2	1200	0.5	15	9398	5.2085	2.8765	5.86	19.42	1.87	1.03	64.4	68.5	51.2	67.4	77.5	68.9	69.6
P8-JV147.2GT1	2	1200	0.5	15	9462	5.5330	3.3099	6.18	18.33	2.44	1.37	62.6	67.8	48.5	58.6	70.9	66.7	67.3
Ave	2	1200	0.5	15	9430	5.3708	3.0932	6.02	18.88	2.16	1.20	63.5	68.2	49.8	63.0	74.2	67.8	68.5
P8-JV147.2GT2	2	1200	0.5	30	9525	5.8768	2.3312	3.97	27.28	2.01	1.34	71.6	76.3	66.9	61.0	67.5	78.1	79.1
P8-JV147.2GT2	2	1200	0.5	30	9779	6.9082	2.4661	5.26	25.15	2.07	1.20	73.7	67.7	56.2	58.7	70.0	79.3	80.2
Ave	2	1200	0.5	30	9652	6.3925	2.3987	4.62	26.22	2.04	1.27	72.6	72.0	61.5	59.8	68.7	78.7	79.7
P8-JV147.2GT3	2	1200	0.5	60	9652	6.3173	1.9706	4.60	28.98	1.94	1.14	76.2	70.8	61.7	59.9	70.5	82.6	83.6
P8-JV147.2GT3	2	1200	0.5	60	9779	6.9306	2.6477	4.23	25.64	2.17	1.35	72.4	74.5	64.8	57.4	66.8	78.7	79.7
Ave	2	1200	0.5	60	9716	6.6240	2.3092	4.42	27.31	2.06	1.24	74.3	72.6	63.2	58.7	68.7	80.7	81.7

Effect of pH on Agglomeration Performance for Illinois # 6 Coal Wet Ground to 200 mesh x 0

Run #	C (%)	pH AGGL (-)	PCR (-)	T (s)	M (rpm)	P (g)	R (g)	Af		Sf		Psf		Y (%)	ARJ (%)	ARD (%)	SRJ (%)	PSRJ (%)	Yc (%)	BTU (%)
								Ap (%)	Af (%)	Sp (%)		Psp (%)								
								6.72	29.26	2.62	3.49	2.60		61.4	72.6	55.4	53.9	68.0	67.5	68.4
16.BU171.1	2	4.6	0.5	60	9398	4.7485	2.9845	5.77	29.20	2.51		1.35		65.5	74.9	61.7	52.9	63.9	72.7	73.8
16.BU171.2	2	4.4	0.5	60	10287	3.8145	2.0105	6.04	29.05	2.13		0.77		65.9	73.6	59.9	59.8	80.4	72.9	74.0
16.BU171.3	2	4.6	0.5	60	9271	4.9045	2.5355	6.18	29.17	2.42		1.18		64.3	73.7	59.0	55.5	70.8	71.0	72.1
Ave	2	4.5	0.5	60	9652	4.4892	2.5102	7.50	38.31	1.90		0.77		68.9	65.7	50.3	62.5	79.6	75.1	76.0
16.BUPH172.4	2	10.1	0.5	60	9271	5.2655	2.3740	7.54	36.98	2.49		1.11		66.5	66.7	50.0	52.5	71.6	72.5	73.4
16.BUPH172.5	2	10.4	0.5	60	9271	5.7825	2.9065	6.99	37.79	1.99		0.53		69.9	67.6	53.6	60.2	85.6	76.5	77.5
16.BUPH172.6	2	10.3	0.5	60	9525	5.4025	2.3315	7.34	37.69	2.13		0.80		68.4	66.7	51.3	58.4	78.9	74.7	75.7
Ave	2	10.3	0.5	60	9356	5.4835	2.5373	6.59	29.70	2.59		1.48		67.4	70.6	56.3	50.0	61.5	74.1	75.2
16.BU171.7	2	4.3	1.0	60	9271	6.1695	2.9875	5.75	29.76	2.58		1.54		63.5	75.8	61.9	53.1	62.3	70.5	71.6
16.BU171.8	2	4.6	1.0	60	9462	4.4840	2.5765	6.37	39.45	2.72		1.66		72.7	69.3	57.8	43.3	53.4	80.2	81.4
16.BU171.9	2	4.6	1.0	60	9335	5.7825	2.1665	6.24	32.97	2.63		1.56		67.9	71.9	58.6	48.8	59.1	74.9	76.0
Ave	2	4.5	1.0	60	9356	5.4787	2.5768	6.99	39.32	2.45		1.35		72.8	66.2	53.6	48.9	62.2	79.8	80.9
16.BUPH172.10	2	9.9	1.0	60	9271	5.5115	2.0550	6.71	37.69	2.53		1.44		69.8	68.9	55.5	49.4	61.3	76.7	77.7
16.BUPH172.11	2	10.2	1.0	60	9271	5.0315	2.1775	6.97	31.76	2.79		1.88		67.7	68.7	53.8	45.9	50.9	74.2	75.2
16.BUPH172.12	2	10.3	1.0	60	9208	5.5865	2.6635	6.89	36.26	2.59		1.56		70.1	68.0	54.3	48.0	58.1	76.9	77.9
Ave	2	10.1	1.0	60	9250	5.3765	2.2987													

**APPENDIX J: AGGLOMERATION TEST RESULTS USING
N-HEPTANE AS AGGLOMERANT**

NOMENCLATURE

Af: Feed Ash Content (%)	P: Product Weight (g)
Ap: Product Ash Content (%)	PCR: Pentane to Coal Ratio (Weight Basis)
Ar: Refuse Ash Content (%)	PSf: Feed Pyritic Sulfur Content (%)
ARD: Ash Reduction (%)	PSP: Product Pyritic Sulfur Content (%)
$ARD = (1 - Ap/Af) \times 100$	PSRJ: Pyritic Sulfur Rejection (%)
ARJ: Ash Rejection (%)	$PSRJ = (100 - Y \times PSP / PSf)$
$ARJ = 100 - Y \times Ap / Af$	R: Refuse Weight (g)
(Btu)f: Feed Calorific Value (Btu/lb)	Sf: Feed Total Sulfur Content (%)
(Btu)p: Product Calorific Value (Btu/lb)	Sp: Feed Total Sulfur Content (%)
BTU: Energy Recovery (%)	SRJ: Total Sulfur Rejection (%)
$BTU = (Btu)p / (Btu)f \times Y$	$SRJ = (100 - Y \times Sp / Sf)$
C: Coal-Water Slurry Concentration (wt.%)	T: Agglomeration Time (s)
HCR: N-heptane to Coal Ratio (Weight Basis)	Y: Overall Yield (%)
N: Mixing Speed (rpm)	$Y = P / (P + R) \times 100$
	Yc: Clean Coal Yield (%)
	$Yc = Y \times (100 - Ap) / (100 - Af)$

Upper Freeport Coal Effect of N-heptane to Coal Ratio (NCR) on the Agglomeration Performance

Run #	C (%)	NCR (-)	PCR (-)	T (s)	N (rpm)	P (g)	R (g)	Ap (%)	Ar (%)	Sp (%)	Psp (%)	Y (%)	ARJ (%)	ARD (%)	SRJ (%)	PSRJ (%)	Yc (%)	BTU (Btu) f 13093 (%)
								13.40		1.54	0.73							
U182/1.3	4	0.5	0.5	30	14034	16.6000	1.7300	7.43	81.44	1.02	0.21	90.6	49.8	44.6	40.0	73.6	96.8	97.9
U182/1.2	4	0.5	0.5	30	14288	20.8300	1.9700	7.77	81.62	1.01	0.22	91.4	47.0	42.0	40.1	72.1	97.3	98.3
U182/1.1	4	0.5	0.5	30	14034	18.3000	1.6500	7.14	81.07	1.01	0.23	91.7	51.1	46.7	39.8	70.7	98.4	99.5
AVE	4	0.5	0.5	30	14118	18.5767	1.7833	7.45	81.38	1.01	0.22	91.2	49.3	44.4	40.0	72.1	97.5	98.6
U182/2.3	4	0.25	0.25	30	14034	19.1700	2.0100	7.61	72.61	1.03	0.26	90.5	48.6	43.2	39.5	67.3	96.6	97.6
U182/2.2	4	0.25	0.25	30	14034	19.2900	2.2200	8.47	69.84	1.03	0.26	89.7	43.3	36.8	40.0	67.6	94.8	95.7
U182/2.1	4	0.25	0.25	30	14288	18.4400	2.0400	8.03	69.15	1.14		90.0	46.0	40.1	33.3		95.6	96.6
AVE	4	0.25	0.25	30	14118	18.9667	2.0900	8.04	70.53	1.07	0.26	90.1	46.0	40.0	37.6	67.5	95.7	96.6
U182/3.3	4	0.50	0.50	30	14034	19.7800	1.8000	7.95	82.18	1.10	0.34	91.7	45.6	40.7	34.5	56.7	97.4	98.4
U182/3.2	4	0.50	0.50	30	14034	20.4800	1.8800	7.84	81.39	1.07	0.30	91.6	46.4	41.5	36.4	61.9	97.5	98.5
U182/3.1	4	0.50	0.50	30	14034	19.1100	1.7900	7.79	81.78	1.15	0.36	91.4	46.8	41.9	31.7	54.3	97.4	98.4
AVE	4	0.50	0.50	30	14034	19.7900	1.8233	7.86	81.78	1.11	0.34	91.6	46.3	41.3	34.2	57.6	97.4	98.4
U182/4.3	4	0.75	0.75	30	14288	19.8200	2.1000	7.89	80.95	1.18	0.41	90.4	46.8	41.1	30.7	48.5	96.2	97.2
U182/4.2	4	0.75	0.75	30	14034	19.3000	2.1900	7.45	80.16	1.18	0.43	89.8	50.1	44.4	31.2	46.4	96.0	97.0
U182/4.1	4	0.75	0.75	30	14034	18.5200	2.0300	7.53	79.88	1.18	0.39	90.1	49.4	43.8	30.9	51.2	96.2	97.3
AVE	4	0.75	0.75	30	14118	19.2133	2.1067	7.62	80.33	1.18	0.41	90.1	48.7	43.1	30.9	48.7	96.1	97.2

Pittsburgh # 8 Coal Effect of Agglomerant on the Agglomeration Performance

Run #	C (%)	HCR (-)	PCR (-)	T (s)	N (rpm)	P (g)	R (g)	Ap (%)	Ar (%)	Sp (%)	PSP (%)	Y (%)	ARJ (%)	ARD (%)	SRJ (%)	PSRJ (%)	Yc (%)	BTU (%)
											Sf	PSf						(Btu) f
											12.50	3.76	2.85					12343
BU202.PEN.4	4		0.5	60	9589	9.2944	2.3350	4.20		2.09	1.11	79.9	72.6	65.8	55.6	67.5	87.3	88.4
BU202.PEN.5	4		0.5	60	9462	13.4155	2.9207	5.56		2.34	1.40	82.1	62.8	54.7	48.9	58.1	88.4	89.4
AVE	4		0.5	60	9525	11.3550	2.6279	4.88		2.22	1.25	81.0	67.7	60.2	52.2	62.8	87.8	88.9
BU202.HAP.4	4	0.5		60	9716	11.5990	1.5365	3.63		1.99	1.02	88.3	73.9	70.4	53.3	67.1	97.0	98.3
BU202.HAP.5	4	0.5		60	9716	11.5015	1.5450	3.76		2.09	1.10	88.2	73.0	69.4	51.0	64.5	96.7	98.0
BU202.HAP.6	4	0.5		60	9652	14.9510	2.4316	4.28		2.15	1.16	86.0	70.0	65.1	50.8	63.5	93.8	95.1
AVE	4	0.5		60	9694	12.6838	1.8377	3.89		2.08	1.09	87.5	72.3	68.3	51.7	65.0	95.9	97.1

Illinois # 6 Coal

Effect of N-heptane to Coal Ratio (HCR) on the Agglomeration Performance

Run #	C (%)	HCR (-)	T (°)	N (rpm)	P (g)	R (g)	Ap (%)	Ar (%)	Sp (%)	Sf	PSf	Y (%)	ARJ (%)	SRJ (%)	PSRJ (%)	Yc (%)	BTU (Btu)f 11157
							9.95	22.57	3.51	1.78	66.0	59.3	38.4	53.0	65.6	70.9	71.6
BU211.1	4	1.00	180	8827	13.3500	6.8800	9.95	22.57	3.51	1.78	66.0	59.3	38.4	53.0	65.6	70.9	71.6
BU211.6	4	1.00	180	8890	13.6300	7.8900	8.61	22.01	3.56	1.86	63.3	66.2	46.7	54.3	65.5	69.0	69.9
Ave	4	1.00	180	8858	13.4900	7.3850	9.28	22.29	3.54	1.82	64.7	62.8	42.5	53.6	65.5	70.0	70.8
BU211.2	4	1.25	180	8890	15.3600	6.0600	9.76		3.59	1.98	71.7	56.7	39.6	47.8	58.4	77.2	78.0
BU211.7	4	1.25	180	8954	14.6000	5.5100	9.24	24.24	3.65	1.97	72.6	58.5	42.8	46.2	58.0	78.6	79.5
Ave	4	1.25	180	8922	14.9800	5.7850	9.50	24.24	3.62	1.98	72.2	57.6	41.2	47.0	58.2	77.9	78.8
BU211.3	4	1.50	180	8827	14.2300	4.7200	9.77	26.93	3.54	1.90	75.1	54.6	39.5	46.1	58.2	80.8	81.7
BU211.8	4	1.50	180	8954	14.8000	4.7100	9.56	27.94	3.59	1.96	75.9	55.1	40.8	44.8	56.4	81.8	82.8
Ave	4	1.50	180	8890	14.5150	4.7150	9.67	27.44	3.57	1.93	75.5	54.8	40.2	45.4	57.3	81.3	82.2
BU211.4	4	1.75	180	9144	13.3200	4.2600	8.79	30.29	3.53	1.83	75.8	58.8	45.6	45.7	59.4	82.4	83.5
BU211.9	4	1.75	180	8827	13.9900	4.5800	9.58	28.83	3.73	2.08	75.3	55.3	40.7	43.0	54.2	81.2	82.2
Ave	4	1.75	180	8985	13.6550	4.4200	9.19	29.56	3.63	1.95	75.6	57.0	43.1	44.4	56.8	81.8	82.8
BU211.5	4	2.00	180	9017	17.7000	4.9900	10.75	29.76	3.83		78.0	48.1	33.4	39.4		83.0	83.8
BU211.10	4	2.00	180	8954	15.7506	4.6206	9.74	29.97	3.63	1.89	77.3	53.4	39.7	43.1	57.1	83.2	84.2
Ave	4	2.00	180	8985	16.7250	4.8050	10.25	29.87	3.73	1.89	77.7	50.7	36.6	41.2	57.1	83.1	84.0

Upper Freeport Coal		Agglomeration Plus High-Shear Washing Step Tests														(Btu) f	
		Af		Sf												13302	
		12.22		2.58													
Run #	No. of Washing Steps	P (g)	R (g)	R1 (g)	R2 (g)	Ap	Sp	Ar	Ar1	Ar2	Y	ARD	ARJ	SRJ	Yc	BTU	%
	1	0	16.64	1.46		4.98	1.18	75.73			91.9	59.2	62.5	58.0	99.5	100.8	
	2	0	15.33	1.57		6.06	1.28	76.24			90.7	50.4	55.0	55.0	97.1	98.2	
AVE	0	15.99	1.52			5.52	1.23	75.99			91.3	54.8	58.8	56.5	98.3	99.5	
	3	1	15.48	1.59	0.14	5.19	1.32	75.83			89.9	57.5	61.8	54.0	97.2	98.4	
	4	1	17.36	1.56	0.12	5.61	1.30	76.53			91.2	54.1	58.1	54.1	98.0	99.2	
AVE	1	16.42	1.58	0.13		5.40	1.31	76.18			90.6	55.8	60.0	54.0	97.6	98.8	
	5	2	16.23	1.71	0.22	0.93	5.26	1.21	74.42	9.97	85.0	57.0	63.4	60.1	91.8	92.9	
	6	2	18.27	1.47	0.15	0.60	6.24	1.27	75.97	9.93	89.2	48.9	54.5	56.1	95.2	96.3	
AVE	2	17.25	1.59	0.19	0.77	5.75	1.24	75.20		9.95	87.1	52.9	58.9	58.1	93.5	94.6	

Ar: Agglomeration Step Refuse Ash Content, %
 Ar1: First Washing Step Refuse Ash Content, %
 Ar2: Second Washing Step Refuse Ash Content, %
 R: Agglomeration Step Refuse Weight, g
 R1: First Washing Step Refuse Weight, g
 R2: Second Washing Step Refuse Weight, g

Pittsburgh # 8 Coal

Agglomeration Plus High-Shear Washing Step Tests

(Btu) f
(Btu/lb)
12294

Af
X
12.80
Sf
X
3.97

Run #	No. of Washing Steps	P	R	R1	Ap	Sp	Ar	Ar1	Y	ARD	ARJ	SRJ	Yc	BTU
		(g)	(g)	(g)	X	X	X	X	X	X	X	X	X	X
1	0	18.43	2.26		4.14	2.24	72.45		89.1	67.7	71.2	49.7	97.9	99.3
2	0	17.56	2.17		4.27	2.26	75.05		89.0	66.6	70.3	49.3	97.7	99.1
AVE	0	18.00	2.22		4.21	2.25	73.75		89.0	67.1	70.7	49.5	97.8	99.2
3	1	17.00	2.47	0.52	3.01	2.02	70.07	60.67	85.0	76.5	80.0	56.7	94.6	96.1
4	1	16.74	1.96	0.35	3.18	2.01	75.11	62.61	87.9	75.2	78.2	55.5	97.6	99.1
AVE	1	16.87	2.22	0.44	3.10	2.02	72.59	61.64	86.5	75.8	79.1	56.1	96.1	97.6

Ar: Agglomeration Step Refuse Ash Content, %
Ar1: First Washing Step Refuse Ash Content, %

R: Agglomeration Step Refuse Weight, g
R1: First Washing Step Refuse Weight, g

Pittsburgh # 8 Coal

Agglomeration Tests Using Lime as Pyrite Depressant

N-Heptane/Coal Ratio: 0.5 (10 g Heptane / 20 g Coal)

Agglomeration Time: 60 s

Run #	C (%)	RCR (lb/T)	pH	N (rpm)	P (g)	R (g)	Ap (%)	Ar (%)	Sp (%)	Sf	PSf	Y (%)	ARJ (%)	ARD (%)	SRJ (%)	PSRJ (%)	Yc (%)	BTU (Btu)f
							11.85		3.89	2.87								12449
P307.1	4	0.00	3.7	9398	17.69	2.04	4.14	68.06	2.29		1.35	89.7	69.5	66.0	49.1	60.6	97.9	99.1
P307.5	4	0.00	3.8	9525	18.46	2.14	4.22	68.97	2.29		1.23	89.6	69.0	65.4	49.1	64.1	97.7	99.0
AVG	4	0.00	3.8	9462	18.08	2.09	4.18	68.52	2.29		1.29	89.6	69.2	65.7	49.1	62.3	97.8	99.1
P307.2	4	1.55	4.3	9271	20.87	2.74	4.64	64.00	2.30		1.35	88.4	66.3	61.9	49.6	61.1	96.0	97.2
P307.6	4	1.55	4.2	9271	19.73	2.41	4.52	66.45	2.31		1.34	89.1	66.9	62.9	48.9	61.1	96.9	98.1
AVG	4	1.55	4.3	9271	20.30	2.58	4.58	65.23	2.31		1.35	88.8	66.6	62.4	49.2	61.1	96.4	97.6
P307.3	4	1.86	4.3	9208	18.11	2.14	4.39	70.35	2.25		1.24	89.4	67.8	64.0	50.1	63.9	97.4	98.6
P307.7	4	1.86	4.2	9525	17.87	2.10	4.18	71.28	2.27		1.22	89.5	69.3	65.7	49.6	64.4	97.6	98.9
AVG	4	1.86	4.3	9366	17.99	2.12	4.29	70.82	2.26		1.23	89.5	68.5	64.8	49.8	64.2	97.5	98.7
P307.4	4	2.48	4.2	9398	17.59	2.00	3.96	73.10	2.20		1.21	89.8	70.8	67.5	51.0	64.6	98.2	99.5
P307.8	4	2.48	4.4	9271	18.27	2.24	4.12	68.79	2.23		1.22	89.1	69.9	66.2	50.7	64.6	97.3	98.5
AVG	4	2.48	4.3	9335	17.93	2.12	4.04	70.95	2.22		1.22	89.4	70.3	66.8	50.8	64.6	97.7	99.0

Pittsburgh # 8 Coal

Agglomeration Tests Using Lime as Pyrite Depressant

N-Heptane/Coal Ratio: 0.5 (10 g Heptane / 20 g Coal)

Agglomeration Time: 60 s

Run #	C (%)	RCR (lb/T)	pH	N (rpm)	P (g)	R (g)	Af		Sp	Psf		Y (%)	ARJ (%)	ARD (%)	SRJ (%)	PSRJ (%)	Yc (%)	BTU (%)
							11.85	3.29	2.87									(Btu)f 12449
P310.1	4	0.00	3.5	9398	18.40	1.96	4.33	2.31	1.37	1.37	90.4	67.6	64.1	47.9	60.3	98.3	99.5	
P310.3	4	0.00	3.8	9525	16.49	2.00	4.02	2.30	1.27	1.27	89.2	70.3	66.7	48.8	63.7	97.3	98.6	
AVG	4	0.00	3.7	9462	17.45	1.98	4.18	2.31	1.32	1.32	89.8	68.9	65.4	48.4	62.0	97.8	99.1	
P310.4	4	3.32	4.7	9271	17.26	2.05	3.90	2.17	1.14	1.14	89.4	71.1	67.7	51.6	67.3	97.7	99.0	
P310.6	4	3.32	4.7	9398	16.79	1.90	3.89	2.19	1.22	1.22	89.8	71.0	67.7	50.9	64.9	98.2	99.5	
AVG	4	3.32	4.7	9335	17.03	1.98	3.90	2.18	1.18	1.18	89.6	71.1	67.7	51.3	66.1	97.9	99.2	
P310.7	4	6.64	5.0	9271	17.77	2.48	4.16	2.15	1.10	1.10	87.8	69.7	65.5	53.0	69.1	95.6	96.9	
P310.8	4	6.64	4.8	9525	16.07	2.20	3.77	2.06	1.05	1.05	88.0	72.5	68.7	54.8	70.4	96.3	97.5	
AVG	4	6.64	4.9	9398	16.92	2.34	3.97	2.11	1.08	1.08	87.9	71.1	67.1	53.9	69.7	95.9	97.2	

Pittsburgh # 8 Coal

Agglomeration Tests Using Lime as Pyrite Depressant

N-Heptane/Coal Ratio: 0.5 (10 g Heptane / 20 g Coal)

Agglomeration Time: 60 s

Run #	C (%)	RCR (lb/T)	pH	N (rpm)	P (g)	R (g)	Ap (%)	Ar (%)	Sp (%)	Psp (%)	Sf	PSf	ARD (%)	SRJ (%)	PSRJ (%)	Yc (%)	BTU (%)
											11.85	3.89	2.87				12449
P311.1	4	0.00	3.7	9525	17.79	2.11	4.31		2.25	1.23			68.2	48.8	62.7	97.3	98.5
P311.2	4	0.00	3.7	9398	17.85	1.95	4.17		2.24	1.25			68.9	48.6	61.8	98.3	99.5
P311.7	4	0.00	3.7	9462	17.36	1.94	4.08		2.26	1.23			69.7	48.3	62.5	98.2	99.4
AVG	4	0.00	3.7	9462	17.67	2.00	4.19		2.25	1.24			68.9	48.6	62.3	97.9	99.2
P311.3	4	8.19	5.2	9271	15.58	2.67	4.58		2.16	1.16			67.7	53.1	66.4	92.7	93.8
P311.4	4	8.19	5.3	9525	15.37	2.91	4.61		2.13	1.16			68.0	54.4	66.9	91.2	92.4
P311.9	4	8.19	5.3	9398	17.90	2.68	4.45		2.21	1.21			68.0	51.1	64.3	94.5	95.7
AVG	4	8.19	5.3	9398	16.28	2.75	4.55		2.17	1.18			67.9	52.9	65.9	92.8	94.0
P311.5	4	10.62	5.3	9525	16.26	3.94	5.51		2.30	1.29			63.3	52.9	64.8	86.6	87.5
P311.6	4	10.62	5.3	9271	14.81	3.24	5.01		2.20	1.21			66.0	54.1	66.3	88.7	89.7
P311.11	4	10.62	5.3	9398	15.11	3.58	5.49		2.35	1.37			63.0	51.3	62.2	87.6	88.6
AVG	4	10.62	5.3	9398	15.62	3.59	5.34		2.28	1.29			64.1	52.7	64.4	87.6	88.6

Pittsburgh # 8 Coal

Agglomeration Tests Using FeCl₃ as Pyrite Depressant

N-Heptane/Cc. 1 Ratio: 0.5 (10 g Heptane / 20 g Coal)
Agglomeration Time: 60 s

Run #	C (%)	RGR (lb/T)	PM	N (rpm)	P (g)	R (g)	Ap (%)	Ar (%)	Sp (%)	Psp (%)	Y (%)	ARJ (%)	ARD (%)	SRJ (%)	PSRJ (%)	Yc (%)	BTU (%)
							11.85		3.89	2.87							12449
P315.1	4	0.0	3.7	9271	17.40	2.26	4.40		2.38	1.39	88.5	69.0	64.9	49.8	60.9	96.8	98.0
P315.5	4	3.0	3.2	9271	17.27	2.48	4.86		2.39	1.37	87.4	66.1	61.3	50.2	62.0	95.1	96.3
P315.6	4	3.0	3.7	9271	16.68	2.20	4.77		2.39	1.41	88.3	66.4	62.0	49.7	60.5	96.2	97.4
AVG	4	3.0	3.5	9271	16.98	2.34	4.82	0.00	2.39	1.39	87.9	66.3	61.6	50.0	61.2	95.7	96.9
P315.7	4	5.0	3.2	9398	16.76	2.56	4.88		2.47	1.49	86.7	66.3	61.1	49.0	59.0	94.4	95.5
P315.9	4	5.0	3.4	9398	17.56	2.73	5.05		2.39	1.40	86.5	65.2	59.8	50.8	61.5	94.0	95.1
AVG	4	5.0	3.3	9398	17.16	2.65	4.97	0.00	2.43	1.45	86.6	65.7	60.4	49.9	60.3	94.2	95.3

Illinois # 6 Coal

Use of Tall Oil as a Binder

Tall Oil to Coal Ratio = 1/10

Run #	C (%)	HCR (-)	T (s)	N (rpm)	P (g)	R (g)	Ap (%)	Ar (%)	Sp (%)	Psp (%)	Y (%)	ARJ (%)	ARD (%)	SRJ (%)	PSRJ (%)	Yc (%)	BTU (%)	(Btu)f 11157
							16.15		4.93	3.31								
BU207.12	4	1.0	180	9462	20.3200	3.3100	5.90	71.67	3.50	1.82	86.0	68.6	63.5	39.0	54.1	96.5	98.2	

Illinois # 6 Coal

Agglomeration Tests Using a 230-mesh Sieve

Run #	Sieve (mesh)	pH	HCR (-)	T (s)	N (rpm)	P (g)	R (g)	Ap (%)	Ar (%)	Sp (%)	Isp (%)	Y (%)	ARJ (%)	ARD (%)	SRJ (%)	ISRJ (%)	Yc (%)	BTU (%)	(Btu)/f 11247
								15.57		4.20	2.42								
1260/1.1	230	3.8	4	360	9000	10.29	2.00	6.69		3.26	1.26	83.7	64.0	57.1	34.9	56.6	92.6	93.9	
1260/1.2	230	3.8	4	360	9000	11.67	2.40	8.22		3.31	1.34	82.9	56.2	47.2	34.6	54.1	90.2	91.3	
1260/1.3	230	3.8	4	360	9000	11.18	1.91	8.42		3.24	1.27	85.4	53.8	45.9	34.0	55.1	92.7	93.8	
Ave	230	3.8	4	360	9000	11.04	2.10	7.78		3.27	1.29	84.0	58.0	50.1	34.5	55.2	91.8	93.0	
1260/2.1	230	12.0	4	360	9000	9.70	1.93	14.42		2.97	1.13	83.4	22.8	7.4	41.0	61.2	84.5	84.7	
1260/2.2	230	12.0	4	360	9000	10.76	2.36	14.85		2.88	1.04	82.0	21.8	4.6	43.7	64.7	82.7	82.8	
1260/2.3	230	12.0	4	360	9000	10.32	2.13	14.64		2.94	1.13	82.9	22.0	6.0	41.9	61.3	83.8	84.0	
Ave	230	12.0	4	360	9000	10.26	2.14	14.63		2.93	1.10	82.8	22.2	6.0	42.2	62.4	83.7	83.8	

**APPENDIX K: EXPERIMENTAL DATA FOR FINE
WET GROUND COAL SAMPLES**

**Particle Size Distribution for Upper Freeport
Coal Wet Ground Using 7/32" Ceramic Balls**

Particle Diameter, μm	Volume Percent Passing					
	Grinding Time, min					
	5	10	20	30	40	60
125	100.0					
88	98.7					
62	97.8	100.0				
44	91.4	98.2				
31	77.6	90.8				
22	68.0	87.0	100.0	100.0	100.0	100.0
16	52.9	74.6	93.2	95.0	95.9	99.4
11	37.6	58.6	79.2	84.0	86.8	94.8
7.8	27.4	46.1	66.6	72.2	76.3	89.7
5.5	17.2	30.8	48.2	52.4	57.5	74.6
3.9	10.0	19.0	31.0	33.5	38.0	55.8
2.8	7.0	14.0	22.0	24.0	26.8	44.0
1.9	3.4	7.4	11.6	12.8	14.2	25.8
1.4	1.0	2.8	4.4	4.8	5.4	11.2

**Particle Size Distribution for Pittsburgh # 8
Coal Wet Ground Using 7/32" Ceramic Balls**

Particle Diameter, μm	Volume Percent Passing				
	Grinding Time, min				
	5	10	20	40	60
88	100.0				
62	88.9	100.0			
44	78.9	94.8	100.0		
31	61.6	82.5	92.5		
22	51.0	72.6	87.6	100.0	100.0
16	38.8	58.0	75.0	94.2	96.0
11	26.2	41.9	56.5	81.6	90.1
7.8	18.3	29.2	42.2	65.8	79.2
5.5	10.9	17.7	26.0	45.1	57.8
3.9	5.6	10.6	13.6	28.0	36.5
2.8	4.2	6.5	8.8	17.8	24.8
1.9	1.9	2.9	4.0	8.6	12.7
1.4	0.6	0.8	1.1	2.8	4.6

**Particle Size Distribution for Illinois # 6 Coal
Wet Ground Using 7/32" Ceramic Balls**

Particle Diameter, μm	Volume Percent Passing				
	Grinding Time, min				
	5	10	20	40	60
125	100.0				
88	93.4		100.0		
62	85.3	100.0	98.6	100.0	
44	70.3	93.4	95.7	99.0	
31	52.0	77.1	87.5	94.9	
22	41.0	64.2	81.7	93.1	100.0
16	28.4	47.3	64.9	83.7	91.5
11	16.6	30.6	44.4	71.6	78.0
7.8	10.5	19.9	32.1	53.0	66.5
5.5	5.8	13.5	17.9	34.2	48.9
3.9	1.7	6.8	8.6	22.1	30.7
2.8	1.1	1.6	7.5	13.5	22.0
1.9	0.2	0.2	4.0	6.3	11.6
1.4	0.0	0.0	1.5	2.0	4.4

Pyrite Size and Association for Pulverized Upper Freeport Coal

Pyrite Size, micron	Accumulated Volume Percent			Total Accumulated Volume Percent
	Locked	Semi- Locked	Free	
1	0.18	0.03	0.04	0.25
2	0.34	0.18	0.13	0.65
3	0.52	0.38	0.26	1.16
4	0.83	0.67	0.30	1.80
5	1.00	0.88	0.42	2.30
6	1.21	1.01	0.48	2.70
7	1.52	1.14	0.66	3.32
8	1.70	1.48	0.75	3.93
9	2.16	1.57	0.89	4.62
10	2.57	1.87	1.11	5.55
11	2.69	1.98	1.18	5.85
12	3.15	2.74	1.61	7.50
13	3.47	3.18		8.26
14	3.94	3.88	2.04	9.86
15	4.79	4.49	2.50	11.78
16		4.84		12.13
17			3.21	12.84
18	5.55	5.33	3.53	14.41
19	5.82	5.84		15.19
20			4.51	16.17
21		6.34		16.67
22		6.46		16.79
23		7.97		18.30
24		10.53		20.86
25	8.96		4.70	24.19
26		11.71		25.37
27	10.50	14.35		29.55
29	10.97			30.02
30			6.69	32.01
33	11.65			32.69
35		19.71		38.05
36	16.79			43.19
40	18.78	29.65		55.12
65	25.23			61.57
125		39.73		71.65
210	53.58			100.00

**Pyrite Size and Association for Upper Freeport Coal
Wet Ground for 5 min Using 7/32" Ceramic Balls**

Pyrite Size, micron	Accumulated Volume Percent			Total Accumulated Volume Percent
	Locked	Semi- Locked	Free	
1	0.80	2.78	1.61	5.19
2	1.63	6.29	3.88	11.80
3	1.92	9.35	5.98	17.25
4	2.31	12.61	8.70	23.62
5	3.22	13.82	11.83	28.87
6		15.81	14.21	33.24
7	5.06	19.30	17.64	42.00
8		24.39	21.00	50.45
9		27.16	22.61	54.83
10		28.83	25.65	59.54
11		31.18		61.89
12		34.77	29.17	69.00
13		41.71		75.94
16			33.69	80.46
17		49.57		88.32
20			45.38	100.00

**Pyrite Size and Association for Upper Freeport Coal
Wet Ground for 10 min Using 7/32" Ceramic Balls**

Pyrite Size, micron	Accumulated Volume Percent			Total Accumulated Volume Percent
	Locked	Semi- Locked	Free	
1	0.79	2.73	1.81	5.33
2	1.41	6.18	4.22	11.81
3	1.90	11.96	6.99	20.85
4	2.35	15.58	8.68	26.61
5		18.69	11.22	32.26
6		19.87	15.04	37.26
7		21.23	16.35	39.93
8		26.80	18.70	47.85
9		32.55	20.51	53.06
10		37.31	24.12	63.78
13		39.76		66.23
14		53.02		79.49
15			35.26	90.63
17		62.40		100.00

**Pyrite Size and Association for Upper Freeport Coal
Wet Ground for 30 min Using 7/32" Ceramic Balls**

Pyrite Size, micron	Accumulated Volume Percent			Total Accumulated Volume Percent
	Locked	Semi- Locked	Free	
1	1.59	4.28	0.92	6.79
2	3.95	12.46	3.69	20.10
3	5.66	24.36	6.30	36.32
4	6.75	33.01	7.32	47.08
5		36.81	8.24	51.80
6		38.64		53.63
7		42.24		57.23
8		43.91	9.24	59.90
9		46.60		62.59
10		52.04	12.87	71.66
14		59.38		79.00
15			18.33	84.46
20			34.18	100.00

**Pyrite Size and Association for Upper Freeport Coal
Wet Ground for 60 min Using 7/32" Ceramic Balls**

Pyrite Size, micron	Accumulated Volume Percent			Total Accumulated Volume Percent
	Locked	Semi- Locked	Free	
1	3.50	4.43	0.79	8.72
2	6.55	15.08	2.73	24.36
3	8.73	24.96	4.77	38.46
4	9.50	38.25	6.20	53.95
5		42.87		58.57
6		46.25		61.95
7		52.71	7.29	69.50
8		59.48		76.27
9			16.82	85.80
20		73.68		100.00

Pyrite Size and Association for Pulverized Pittsburgh # 8 Coal

Pyrite Size, micron	Accumulated Volume Percent			Total Accumulated Volume Percent
	Locked	Semi-Locked	Free	
1	0.14	0.04	0.01	0.19
2	0.29	0.14	0.06	0.49
3	0.51	0.27	0.09	0.87
4	0.73	0.35	0.13	1.21
5	1.20	0.51	0.16	1.87
6	1.51	0.71	0.21	2.43
7	2.05	0.85	0.30	3.20
8	2.90	0.93	0.49	4.32
9	3.40	1.07		4.96
10	3.80	1.14		5.43
11	4.04	1.22		5.75
12	4.26	1.32		6.07
13	4.80	1.39		6.68
14	5.53	1.84		7.86
15	5.81	2.13		8.43
16	6.16	2.66		9.31
17	6.63			9.78
18	7.37			10.52
19	7.74			10.89
20	8.35	3.64		12.48
23	8.49			12.62
24	9.39			13.52
25		4.13		14.01
28	9.71			14.33
29	10.31			14.93
30	10.86			15.48
31	10.99			15.61
32	13.86			18.48
33	14.73			19.35
34	14.84			19.46
35	22.96			27.58
37	24.90	5.23		30.62
38		11.11		36.50
40	25.52			37.12
45	34.46		2.44	48.01
50	44.63			58.18
60		15.24		62.31
70	48.43			66.11
85	60.47			78.15
145		37.08		100.00

**Pyrite Size and Association for Pittsburgh # 8 Coal
Wet Ground for 5 min Using 7/32" Ceramic Balls**

Pyrite Size, micron	Accumulated Volume Percent			Total Accumulated Volume Percent
	Locked	Semi- Locked	Free	
1	0.43	1.14	0.51	2.08
2	1.11	3.17	1.41	5.69
3	2.09	5.39	2.08	9.56
4	2.53	7.64	2.44	12.61
5	3.06	9.32	3.26	15.64
6	3.45	10.96	3.34	17.75
7		13.86	4.60	21.91
8	3.70	17.84	5.60	27.14
9	5.06	21.34		32.00
10		22.14		32.80
11		23.35		34.01
12		25.64	7.20	37.90
15		26.21		38.47
16	5.34			38.75
17		28.83		41.37
18	11.20			47.23
20		29.03		47.43
23		40.40		58.80
25		49.93		68.33
28		63.02		81.42
40		81.59		100.00

**Pyrite Size and Association for Pittsburgh # 8 Coal
Wet Ground for 20 min Using 7/32" Ceramic Balls**

Pyrite Size, micron	Accumulated Volume Percent			Total Accumulated Volume Percent
	Locked	Semi- Locked	Free	
1	1.41	2.86	0.86	5.13
2	3.34	7.42	2.38	13.14
3	5.46	13.81	3.38	22.65
4	5.89	19.11	4.13	29.13
5	8.15	22.72	4.81	35.68
6		29.52		42.48
7	9.35	39.48		53.64
8		43.93	5.10	58.38
9		45.85	8.52	63.72
10		55.23		73.10
11		64.32		82.19
12		71.29		89.16
14	9.97			89.78
16	20.20			100.00

**Pyrite Size and Association for Pittsburgh # 8 Coal
Wet Ground for 60 min Using 7/32" Ceramic Balls**

Pyrite Size, micron	Accumulated Volume Percent			Total Accumulated Volume Percent
	Locked	Semi- Locked	Free	
1	5.62	6.27	1.18	13.07
2	11.74	15.17	2.86	29.77
3	19.32	30.49	4.61	54.42
4	24.19	40.29	6.39	70.87
5	30.90	49.39	8.23	88.52
6	33.77	58.00		100.00

Pyrite Size and Association for Pulverized Illinois # 6 Coal

Pyrite Size, micron	Accumulated Volume Percent			Total Accumulated Volume Percent
	Locked	Semi- Locked	Free	
1	0.04	0.02	0.02	0.08
2	0.13	0.12	0.12	0.37
3	0.28	0.26	0.36	0.90
4	0.54	0.50	0.93	1.97
5	0.79	0.84	1.50	3.13
6	1.04	1.13	2.00	4.17
7	1.48	1.40	2.30	5.18
8	1.89	1.79	2.72	6.40
9	2.32	2.11	3.24	7.67
10	3.09	2.50	3.70	9.29
11	3.62	2.72	4.16	10.50
12	3.99	3.00	4.18	11.17
13	4.68	3.84		12.70
14	4.71	4.17	4.39	13.27
15		4.26	4.82	13.79
16	5.09	4.38	4.99	14.46
17			5.29	14.76
18	5.76	4.65		15.70
19			5.56	15.97
20	6.25	4.98		16.79
21	6.81	5.22		17.59
22		5.54	5.90	18.25
23		6.05		18.76
24	7.13			19.08
26		7.94	6.52	21.59
30		8.81		22.46
33	8.29			23.62
37	11.00			26.33
44	12.66			27.99
100	14.96			30.29
130	25.28			40.61
140		18.99		50.79
158		45.33		77.13
180	48.15			100.00

**Pyrite Size and Association for Illinois # 6 Coal
Wet Ground for 5 min Using 7/32" Ceramic Balls**

Pyrite Size, micron	Accumulated Volume Percent			Total Accumulated Volume Percent
	Locked	Semi- Locked	Free	
1	0.11	0.22	0.15	0.48
2	0.41	0.86	1.12	2.39
3	0.66	1.66	2.39	4.71
4	1.09	2.59	4.49	8.17
5	1.49	3.85	7.12	12.46
6	1.77	5.42	9.55	16.74
7	2.01	7.03	10.70	19.74
8	2.53	8.92	11.99	23.44
9		10.37	13.18	26.08
10		10.83	14.58	27.94
11			15.08	28.44
12		11.80	15.38	29.71
13		14.49	18.57	35.59
14		15.50	18.76	37.79
15		16.63	20.53	40.69
16		17.41	23.34	44.28
17		24.11	25.12	52.76
18		25.84	28.23	57.60
19		28.32		60.08
20		32.83	31.32	67.68
24		33.96	35.69	73.18
26		40.75		79.97
40		41.31		80.53
44		60.78		100.00

**Pyrite Size and Association for Illinois # 6 Coal
Wet Ground for 20 min Using 7/32" Ceramic Balls**

Pyrite Size, micron	Accumulated Volume Percent			Total Accumulated Volume Percent
	Locked	Semi- Locked	Free	
1	0.45	0.50	0.40	1.35
2	1.41	2.59	2.14	6.14
3	2.54	5.18	4.82	12.54
4	3.90	10.10	7.65	21.65
5	5.02	13.88	9.66	28.56
6	6.58	16.79	14.05	37.42
7	7.03	19.59	15.53	42.15
8	7.77	22.50	18.44	48.71
9	9.27	27.69	18.46	55.42
10		32.56	21.60	63.43
11			22.86	64.69
12	11.39	35.82	24.73	71.94
13		42.22	28.14	81.75
14		45.99		85.52
15			32.53	89.91
16		49.22		93.14
18		56.08		100.00

**Pyrite Size and Association for Illinois # 6 Coal
Wet Ground for 60 min Using 7/32" Ceramic Balls**

Pyrite Size, micron	Accumulated Volume Percent			Total Accumulated Volume Percent
	Locked	Semi- Locked	Free	
1	1.42	1.82	1.28	4.52
2	4.30	6.74	5.12	16.16
3	6.18	13.92	12.59	32.69
4	8.45	24.25	21.05	53.75
5	10.43	27.56	26.79	64.78
6	11.40	31.17	32.04	74.61
7	13.62	35.23	33.12	81.97
8		38.71	34.89	87.22
9		42.83	38.49	94.94
12			43.55	100.00

Upper Freeport Coal Central Composite Design Results

Run #	GT (min)	HCR (-)	pH (-)	T (s)	pH AFTER Grinding	P (g)	R (g)	Af Sf PSf			Y (%)	ARJ (%)	SRJ (%)	PSRJ (%)	Yc (%)	BTU (%)
								Ap (%)	Sp (%)	PSP (%)						
								12.28	2.36	1.72						
UI366.1-1	30	0.23	4.7	15	7.8	17.71	2.05	5.62	1.03	0.41	89.6	59.0	60.9	78.6	96.4	97.5
UI366.1-2	30	0.23	4.7	15	7.8	20.18	2.54	5.95	1.03	0.40	88.8	57.0	61.2	79.3	95.2	96.2
UI375.1-1	30	0.23	4.7	15	7.8	15.58	1.32	4.95	1.14	0.51	92.2	62.8	59.7	72.7	99.9	>99.9
UI375.1-2	30	0.23	4.7	15	7.8	19.32	1.85	5.35	1.24	0.62	91.3	60.2	56.4	67.1	98.5	99.6
AVG	30	0.23	4.7	15	7.8	18.20	1.94	5.47	1.11	0.49	90.5	59.8	57.4	74.4	97.5	98.6
UI374.2-1	80	0.23	4.7	15	7.8	15.27	2.68	5.46	1.22	0.58	85.1	62.2	55.5	71.3	91.7	92.7
UI374.2-2	80	0.23	4.7	15	7.8	15.51	2.28	5.53	1.22	0.62	87.2	60.7	55.0	68.6	93.9	94.9
UI374.2-0	80	0.23	4.7	15	7.8	14.95	2.16	5.14	1.17	0.55	87.4	63.4	58.1	72.1	94.5	95.6
AVG	80	0.23	4.7	15	7.8	15.24	2.37	5.38	1.20	0.58	86.5	62.1	56.2	70.6	93.4	94.4
UI366.3-1	30	0.57	4.7	15	7.8	17.84	1.97	5.57	1.11	0.48	90.1	59.2	54.6	74.9	96.9	98.0
UI366.3-2	30	0.57	4.7	15	7.8	19.98	2.11	5.20	1.05	0.43	90.4	61.7	57.7	77.4	97.7	98.9
UI375.3-1	30	0.57	4.7	15	7.8	17.77	1.46	5.01	1.21	0.56	92.4	62.3	59.2	69.9	>99.9	>99.9
UI375.3-2	30	0.57	4.7	15	7.8	16.67	1.40	5.11	1.22	0.58	92.3	61.6	58.4	68.9	99.8	>99.9
AVG	30	0.57	4.7	15	7.8	18.07	1.74	5.22	1.15	0.51	91.3	61.2	57.5	72.8	98.6	99.8
UI366.4-1	80	0.57	4.7	15	7.8	15.78	1.88	5.03	1.11	0.47	89.4	63.4	59.0	75.6	96.7	97.9
UI372.4-1	80	0.57	4.7	15	7.8	18.41	2.06	4.56	1.18	0.57	89.9	66.6	62.9	70.2	97.9	99.1
UI372.4-2	80	0.57	4.7	15	7.8	17.11	2.10	4.47	1.24	0.59	89.1	67.6	63.6	69.4	97.0	98.2
UI374.4-1	80	0.57	4.7	15	7.8	17.45	1.71	4.36	1.22	0.62	91.1	67.7	64.5	67.2	99.3	>99.9
UI374.4-2	80	0.57	4.7	15	7.8	19.23	1.98	4.43	1.20	0.57	90.7	67.3	63.9	70.0	98.8	>99.9
AVG	80	0.57	4.7	15	7.8	17.60	1.95	4.57	1.19	0.56	90.0	66.5	62.8	70.5	97.9	99.2

Upper Freeport Coal Central Composite Design Results

Run #	GT (min)	HCR (-)	pH (-)	T (s)	pH AFTER Grinding	P (g)	R (g)	Ap (%)	Sp (%)	Psf (%)	Af Sf PSf									
											12.28	2.36	1.72							
UI366.5-1	30	0.23	9.3	15	7.8	16.05	1.43	5.41	1.03	0.42	91.8	59.5	55.9	59.9	77.6	99.0	>99.9			
UI366.5-2	30	0.23	9.3	15	7.8	17.16	1.61	5.45	1.05	0.43	91.4	59.4	55.6	59.3	77.1	98.5	99.6			
UI375.5-1	30	0.23	9.3	15	7.8	18.75	1.43	4.96	1.13	0.50	92.9	62.5	59.6	55.5	73.0	>99.9	>99.9			
UI375.5-2	30	0.23	9.3	15	7.8	18.68	1.49	4.88	1.17	0.55	92.6	63.2	60.3	54.1	70.4	>99.9	>99.9			
AVG	30	0.23	9.3	15	7.8	17.66	1.49	5.18	1.10	0.48	92.2	61.2	57.9	57.2	74.5	99.7	>99.9			
UI364.6-1	80	0.23	9.3	15	7.8	16.14	1.99	5.15	1.07	0.43	89.0	62.7	58.1	59.6	77.7	96.3	97.4			
UI372.6-1	80	0.23	9.3	15	7.8	15.85	1.79	4.89	1.19	0.56	89.9	64.2	60.2	54.7	70.7	97.4	98.6			
UI372.6-2	80	0.23	9.3	15	7.8	16.32	2.16	4.95	1.17	0.56	88.3	64.4	59.7	56.2	71.2	95.7	96.8			
UI374.6-1	80	0.23	9.3	15	7.8	16.92	2.11	4.58	1.10	0.48	88.9	66.8	62.7	58.6	75.2	96.7	97.9			
UI374.6-2	80	0.23	9.3	15	7.8	16.44	1.67	4.40	1.12	0.49	90.8	67.5	64.2	56.9	74.1	98.9	>99.9			
AVG	80	0.23	9.3	15	7.8	16.33	1.94	4.79	1.13	0.50	89.4	65.1	61.0	57.2	73.8	97.0	98.2			
UI366.7-1	30	0.57	9.3	15	7.8	14.06	1.63	5.05	0.99	0.38	89.6	63.1	58.9	62.4	80.2	97.0	98.1			
UI373.7-1	30	0.57	9.3	15	7.8	17.27	1.79	4.75	1.17	0.53	90.6	65.0	61.3	55.1	72.1	98.4	99.6			
UI373.7-2	30	0.57	9.3	15	7.8	18.39	1.86	4.65	1.15	0.53	90.8	65.6	62.1	55.7	72.0	98.7	99.9			
UI375.7-1	30	0.57	9.3	15	7.8	18.47	1.66	4.98	1.26	0.61	91.8	62.8	59.4	51.0	67.5	99.4	>99.9			
UI375.7-2	30	0.57	9.3	15	7.8	19.16	1.79	4.69	1.17	0.55	91.5	65.1	61.8	54.7	70.8	99.4	>99.9			
AVG	30	0.57	9.3	15	7.8	17.47	1.75	4.82	1.15	0.52	90.8	64.3	60.7	55.8	72.5	98.6	99.8			
UI364.8-1	80	0.57	9.3	15	7.8	19.37	2.32	4.36	1.05	0.41	89.3	68.3	64.5	60.3	78.7	97.4	98.6			
UI372.8-1	80	0.57	9.3	15	7.8	16.24	1.98	4.09	1.16	0.55	89.1	70.3	66.7	56.2	71.5	97.5	98.7			
UI372.8-2	80	0.57	9.3	15	7.8	19.38	2.22	4.32	1.19	0.55	89.7	68.4	64.8	54.8	71.3	97.9	99.1			
UI374.8-1	80	0.57	9.3	15	7.8	15.36	1.67	3.75	1.14	0.52	90.2	72.5	69.5	56.4	72.7	99.0	>99.9			
UI374.8-2	80	0.57	9.3	15	7.8	15.59	1.73	3.73	1.14	0.52	90.0	72.7	69.6	56.5	72.8	98.8	>99.9			
AVG	80	0.57	9.3	15	7.8	17.19	1.98	4.05	1.14	0.51	89.7	70.4	67.0	56.8	73.4	98.1	99.4			

Upper Freeport Coal Central Composite Design Results

Run #	GT (min)	HCR (-)	pH (-)	T (s)	pH AFTER Grinding	P (g)	R (g)	Ap (%)	Sp (%)	PSP (%)	Y (%)	ARJ (%)	ARD (%)	SRJ (%)	PSRJ (%)	Yc (%)	BTU (%)
								Af	Sf	PSf							
								12.28	2.36	1.72							
UI367.12-1	12	0.40	7.0	15	7.0	19.24	1.51	6.85	1.17	0.52	92.7	48.3	44.2	54.0	72.0	98.5	99.4
UI367.12-2	12	0.40	7.0	15	7.5	22.09	1.64	6.63	1.14	0.50	93.1	49.7	46.0	55.0	72.9	99.1	>99.9
AVG	12	0.40	7.0	15	7.3	20.67	1.58	6.74	1.16	0.51	92.9	49.0	45.1	54.5	72.5	98.8	99.7
UI368.13-1	98	0.40	7.0	15	7.2	17.66	1.99	4.51	1.03	0.42	89.9	67.0	63.3	60.8	78.1	97.8	99.1
UI368.13-2	98	0.40	7.0	15	7.1	16.28	1.83	4.64	1.07	0.44	89.9	66.0	62.2	59.2	77.0	97.7	98.9
AVG	98	0.40	7.0	15	7.2	16.97	1.91	4.58	1.05	0.43	89.9	66.5	62.7	60.0	77.5	97.8	99.0
UI369.14-1	55	0.10	7.0	15	7.5	16.68	3.81	7.52	1.48	0.83	81.4	50.1	38.8	48.9	60.7	85.8	86.5
UI370.14-1	55	0.10	7.0	15	7.5	14.36	3.21	6.69	1.29	0.68	81.7	55.5	45.5	55.3	67.7	86.9	87.7
AVG	55	0.10	7.0	15	7.5	15.52	3.51	7.11	1.39	0.76	81.6	52.8	42.1	52.1	64.2	86.4	87.1
UI369.15-1	55	0.70	7.0	15	7.5	20.19	2.04	4.66	1.14	0.53	90.8	65.5	62.1	56.1	72.0	98.7	99.9
UI370.15-1	55	0.70	7.0	15	7.5	16.27	1.51	4.76	1.24	0.61	91.5	64.5	61.2	51.9	67.5	99.4	>99.9
AVG	55	0.70	7.0	15	7.5	18.23	1.78	4.71	1.19	0.57	91.1	65.0	61.6	54.1	69.8	99.0	>99.9
UI369.16-1	55	0.40	3.0	15	7.5	19.09	1.62	4.74	1.23	0.61	92.2	64.4	61.4	52.0	67.3	>99.9	>99.9
UI370.16-1	55	0.40	3.0	15	7.5	17.31	1.55	4.81	1.30	0.66	91.8	64.0	60.8	49.4	64.8	99.6	>99.9
AVG	55	0.40	3.0	15	7.5	18.20	1.59	4.78	1.27	0.64	92.0	64.2	61.1	50.7	66.0	99.8	>99.9
UI369.17-1	55	0.40	11.0	15	7.5	17.37	1.64	4.44	1.19	0.57	91.4	67.0	63.8	53.9	69.7	99.5	>99.9
UI370.17-1	55	0.40	11.0	15	7.5	20.06	1.77	4.62	1.19	0.54	91.9	65.4	62.4	53.7	71.2	99.9	>99.9
AVG	55	0.40	11.0	15	7.5	18.72	1.71	4.53	1.19	0.56	91.7	66.2	63.1	53.8	70.4	99.7	>99.9

Upper Freeport Coal Central Composite Design Results

Run #	GT (min)	HCR (-)	pH (-)	T (s)	pH AFTER Grinding	P (g)	R (g)	Ap (%)	Sp (%)	Psp (%)	Af		Y	ARJ (%)	ARD (%)	SRJ (%)	PSRJ (%)	Yc (%)	BTU (%)
											12.28	2.36							
UI370.9	55	0.40	7.0	15	7.4	18.70	1.55	4.88	1.22	0.59	92.3	63.3	92.3	63.3	60.3	52.3	68.3	>99.9	>99.9
UI370.10	55	0.40	7.0	15	7.4	17.54	1.47	5.35	1.18	0.56	92.3	59.8	92.3	59.8	56.4	53.9	70.0	99.6	>99.9
UI370.11	55	0.40	7.0	15	7.4	17.28	1.46	4.86	1.20	0.55	92.2	63.5	92.2	63.5	60.4	53.1	70.5	>99.9	>99.9
UI368.18	55	0.40	7.0	15	7.4	18.01	1.48	4.71	1.24	0.61	92.4	64.6	92.4	64.6	61.6	51.4	67.2	>99.9	>99.9
UI369.19	55	0.40	7.0	15	7.4	15.92	1.20	4.92	1.15	0.52	93.0	62.7	93.0	62.7	59.9	54.7	71.9	>99.9	>99.9
UI369.20	55	0.40	7.0	15	7.4	16.22	1.19	4.72	1.19	0.58	93.2	64.2	93.2	64.2	61.6	53.0	68.6	>99.9	>99.9
AVG	55	0.40	7.0	15	7.4	17.28	1.39	4.91	1.20	0.57	92.5	63.0	92.5	63.0	60.0	53.1	69.4	>99.9	>99.9

Pittsburgh # 8 Coal 60 min grinding, d50 = 5.0 microns

Run #	C (%)	HCR (-)	T (s)	N (rpm)	P (g)	R (g)	Ap (%)	Ar (%)	Sp (%)	Psp (%)	Y (%)	ARJ (%)	ARD (%)	SRJ (%)	PSRJ (%)	Yc (%)	BTU (%)
							Af 10.80		Sf 4.12	PSf							
P326.1	4	0.50	120	9271	18.34	2.41	4.45		2.62		88.4	63.6	58.8	43.8		94.7	95.6
P326.3	4	0.50	150	9398	16.95	1.51	3.73		2.74		91.8	68.3	65.5	38.9		99.1	>99.9
P326.2	4	0.50	180	9525	18.35	1.47	4.12		3.12		92.6	64.7	61.9	29.9		99.5	>99.9

Pittsburgh # 8 Coal 80 min grinding, d50 = 4.5 microns

Run #	C (%)	HCR (-)	T (s)	N (rpm)	P (g)	R (g)	Ap (%)	Ar (%)	Sp (%)	Psp (%)	Y (%)	ARJ (%)	ARD (%)	SRJ (%)	PSRJ (%)	Yc (%)	BTU (%)
							Af 10.92		Sf 4.30	PSf							
P331.1	4	0.50	120	9398	19.58	4.48	7.10		2.84		81.4	47.1	35.0			84.9	85.4
P331.2	4	0.50	150	9398	18.00	2.62	4.74		2.58		87.3	62.1	56.6			93.3	94.3
P331.5	4	0.50	180	9398	19.55	1.84	3.93		2.81		91.4	67.1	64.0			98.6	99.7

Pittsburgh # 8 Coal 120 min grinding, d50 = 3.5 microns

Run #	C (%)	pH (-)	T (s)	N (rpm)	P (g)	R (g)	Ap (%)	Ar (%)	Sp (%)	Psp (%)	Y (%)	ARJ (%)	ARD (%)	SRJ (%)	PSRJ (%)	Yc (%)	BTU (%)
							Af 11.10		Sf 3.87	PSf 2.86							
P335.3	4	4.20	120	9398	16.45	3.93	7.52		2.68	1.66	80.7	45.3	32.3	44.1	53.2	84.0	84.5
P335.2	4	4.20	150	9398	16.75	2.13	3.91		2.35	1.35	88.7	68.7	64.8	46.1	58.1	95.9	97.0
P335.6	4	4.20	180	9398	17.67	1.96	3.74		2.53	1.54	90.0	69.7	66.3	41.2	51.5	97.5	98.6

Pittsburgh # 8 Coal Grinding for 80 min with pH adjustment (Starting pH = 11)

Run #	C (%)	pH (-)	HCR (-)	T (s)	P (g)	R (g)	Af		Sf		Psp (%)	Y (%)	ARJ (%)	ARD (%)	SRJ (%)	PSRJ (%)	Yc (%)	BTU (%)
							Ap (%)	Ar (%)	Sp (%)	Psp (%)								
							11.10		3.94	2.90								
P338.2	4	6.1	0.75	90	18.09	1.95	2.75		2.13	1.12	90.3	77.6	75.2	51.2	65.1	98.7	>99.9	
P338.1	4	6.1	0.75	120	17.75	2.09	2.68		2.22	1.20	89.5	78.4	75.9	49.6	63.0	97.9	99.2	
P338.3	4	6.1	0.75	150	16.37	1.96	2.90		2.33	1.32	89.3	76.7	73.9	47.2	59.3	97.5	98.8	
P338.4	4	6.1	0.75	120 + washing	16.99	2.22	2.34		2.14	1.15	88.4	81.4	78.9	52.0	64.9	97.2	98.5	
P338.6	4	6.1	0.50	90	15.61	1.75	2.63		2.16	1.17	89.9	78.7	76.3	50.7	63.7	98.5	99.8	
P338.5	4	6.1	0.50	120	17.07	1.78	2.77		2.17	1.14	90.6	77.4	75.0	50.1	64.4	99.0	>99.9	
P338.7	4	6.1	0.50	150	18.84	2.00	2.43		2.30	1.28	90.4	80.2	78.1	47.2	60.1	99.2	>99.9	
P338.8	4	6.1	0.50	120 + washing	16.53	2.05	2.19		2.09	1.07	89.0	82.4	80.3	52.8	67.2	97.9	99.2	

Pittsburgh # 8 Coal Central Composite Design Results

Run #	GT (min)	MCR (-)	pH (-)	T (s)	pH AFTER Grinding	P (g)	R (g)	Ap (%)	Sp (%)	Psp (%)	Y (%)	ARJ (%)	ARD (%)	SRJ (%)	PSRJ (%)	Yc (%)	BTU (%)
								Af	Sf	PSf							
								11.40	4.10	3.08							
P341.1	40	0.3	5.0	90	6.0	16.07	1.84	2.63	1.96	0.88	89.7	79.3	76.9	57.1	74.4	98.6	>99.9
P348.1	40	0.3	5.0	90	6.2	16.44	2.13	2.30	1.91	0.85	88.5	82.1	79.8	58.8	75.6	97.6	99.0
AVG	40	0.3	5.0	90	6.1	16.26	1.99	2.47	1.94	0.87	89.1	80.7	78.4	57.9	75.0	98.1	99.5
P347.2	80	0.3	5.0	90	6.1	16.04	2.96	3.10	2.07	0.99	84.4	77.0	72.8	57.4	72.9	92.3	93.5
P353.2-1	80	0.3	5.0	90	6.4	17.64	3.02	2.84	2.26	1.18	85.4	78.7	75.1	52.9	67.3	93.6	94.9
P353.2-2	80	0.3	5.0	90	6.4	15.47	2.13	2.81	2.06	1.02	87.9	78.3	75.4	55.8	70.9	96.4	97.7
P353.2-3	80	0.3	5.0	90	6.4	16.32	2.73	3.22	2.12	1.05	85.7	75.8	71.8	55.7	70.8	93.6	94.8
AVG	80	0.3	5.0	90	6.3	16.37	2.71	2.99	2.13	1.06	85.8	77.5	73.8	55.5	70.5	94.0	95.2
P341.3	40	0.3	9.0	90	6.1	18.33	2.99	3.02	1.93	0.88	86.0	77.2	73.5	59.5	75.4	94.1	95.4
P348.3	40	0.3	9.0	90	6.4	18.60	2.81	3.07	1.94	0.87	86.9	76.6	73.1	58.9	75.5	95.0	96.3
AVG	40	0.3	9.0	90	6.3	18.47	2.90	3.05	1.94	0.88	86.4	76.9	73.3	59.2	75.4	94.6	95.8
P353.4-1	80	0.3	9.0	90	6.4	18.29	3.57	3.53	2.06	1.00	83.7	74.1	69.0	58.0	72.8	91.1	92.2
P353.4-2	80	0.3	9.0	90	6.4	16.66	3.14	2.93	1.97	0.92	84.1	78.4	74.3	59.6	74.9	92.2	93.4
AVG	80	0.3	9.0	90	6.4	17.48	3.36	3.23	2.02	0.96	83.9	76.2	71.7	58.8	73.9	91.6	92.8
P341.5	40	0.3	5.0	210	6.1	16.38	1.68	2.80	2.08	1.03	90.7	77.7	75.4	54.0	69.7	99.5	>99.9
P348.5	40	0.3	5.0	210	6.4	17.02	1.99	3.03	2.03	0.99	89.5	76.2	73.4	55.7	71.2	98.0	99.3
AVG	40	0.3	5.0	210	6.3	16.70	1.84	2.92	2.06	1.01	90.1	77.0	74.4	54.8	70.4	98.7	>99.9
P342.6	80	0.3	5.0	210	6.0	17.14	2.89	3.05	2.03	0.95	85.6	77.1	73.2	57.6	73.6	93.6	94.9
P347.6	80	0.3	5.0	210	6.2	16.98	2.82	2.82	2.13	1.11	85.8	78.8	75.3	55.4	69.1	94.1	95.3
AVG	80	0.3	5.0	210	6.1	17.06	2.86	2.94	2.08	1.03	85.7	77.9	74.3	56.5	71.4	93.8	95.1

Pittsburgh # 8 Coal Central Composite Design Results

Run #	GT (min)	HCR (-)	pH (-)	T (s)	pH AFTER Grinding	P (g)	R (g)	Ap (%)	Sp (%)	Psp (%)	Y (%)	ARJ (%)	ARD (%)	SRJ (%)	PSRJ (%)	Yc (%)	BTU (%)
									Af	Sf	PSf						
									11.40	4.10	3.08						
P341.7	40	0.3	9.0	210	6.2	18.90	2.57	2.30	1.86	0.79	88.0	82.2	79.8	60.1	77.4	97.1	98.5
P348.7	40	0.3	9.0	210	6.2	16.35	2.07	2.40	1.85	0.79	88.8	81.3	78.9	59.9	77.2	97.8	99.2
AVG	40	0.3	9.0	210	6.2	17.63	2.32	2.35	1.86	0.79	88.4	81.8	79.4	60.0	77.3	97.4	98.8
P342.8	80	0.3	9.0	210	6.0	15.98	3.00	2.47	1.75	0.67	84.2	81.8	78.3	64.1	81.7	92.7	94.0
P347.8	80	0.3	9.0	210	6.4	16.61	2.41	2.12	1.85	0.78	87.3	83.8	81.4	60.6	77.9	96.5	97.9
AVG	80	0.3	9.0	210	6.2	16.30	2.71	2.30	1.80	0.73	85.8	82.8	79.9	62.3	79.8	94.6	95.9
P341.9	40	0.7	5.0	90	6.2	15.34	1.75	2.91	2.07	1.01	89.8	77.1	74.5	54.7	70.6	98.4	99.7
P348.9	40	0.7	5.0	90	6.2	19.00	2.27	2.77	1.98	0.89	89.3	78.3	75.7	56.9	74.2	98.0	99.4
AVG	40	0.7	5.0	90	6.2	17.17	2.01	2.84	2.03	0.95	89.5	77.7	75.1	55.8	72.4	98.2	99.5
P342.10	80	0.7	5.0	90	6.1	17.45	2.48	2.96	2.06	0.96	87.6	77.3	74.0	56.0	72.7	95.9	97.2
P347.10	80	0.7	5.0	90	6.4	14.44	1.81	2.73	2.14	1.07	88.9	78.7	76.1	53.6	69.1	97.6	98.9
AVG	80	0.7	5.0	90	6.3	15.95	2.15	2.85	2.10	1.02	88.2	78.0	75.0	54.8	70.9	96.7	98.0
P341.11	40	0.7	9.0	90	6.2	17.28	2.05	2.46	1.91	0.88	89.4	80.7	78.4	58.4	74.5	98.4	99.8
P348.11	40	0.7	9.0	90	6.2	21.88	2.78	2.65	1.95	0.89	88.7	79.4	76.8	57.8	74.4	97.5	98.8
AVG	40	0.7	9.0	90	6.2	19.58	2.42	2.56	1.93	0.89	89.1	80.0	77.6	58.1	74.4	98.0	99.3
P341.12	80	0.7	9.0	90	6.0	17.88	2.68	2.58	1.86	0.81	87.0	80.3	77.4	60.5	77.1	95.6	96.9
P347.12	80	0.7	9.0	90	6.4	18.78	2.58	2.52	1.92	0.88	87.9	80.6	77.9	58.8	74.9	96.7	98.1
AVG	80	0.7	9.0	90	6.2	18.33	2.63	2.55	1.89	0.85	87.4	80.4	77.6	59.7	76.0	96.2	97.5
P341.13	40	0.7	5.0	210	6.2	20.19	2.04	3.12	2.20	1.12	90.8	75.1	72.6	51.3	67.0	99.3	>99.9
P348.13	40	0.7	5.0	210	6.2	17.62	2.22	3.05	2.03	0.94	88.8	76.2	73.2	56.0	72.9	97.2	98.5
AVG	40	0.7	5.0	210	6.2	18.91	2.13	3.09	2.12	1.03	89.8	75.7	72.9	53.6	69.9	98.2	99.5

Pittsburgh # 8 Coal Central Composite Design Results

Run #	GT (min)	HCR (-)	pH (-)	T (s)	pH AFTER Grinding	P (g)	R (g)	Ap (%)	Sp (%)	PSP (%)	Y (%)	ARJ (%)	ARD (%)	SRJ (%)	PSRJ (%)	Yc (%)	BTU (%)
								11.40	4.10	3.08							
P342.14	80	0.7	5.0	210	6.0	18.22	2.39	3.09	2.11	4.01	88.4	76.0	72.9	54.5	71.0	96.7	98.0
P347.14	80	0.7	5.0	210	6.0	14.82	1.82	3.19	2.33	1.24	89.1	75.1	72.0	49.4	64.1	97.3	98.6
AVG	80	0.7	5.0	210	6.0	16.52	2.11	3.14	2.22	1.13	88.7	75.6	72.5	51.9	67.6	97.0	98.3
P341.15	40	0.7	9.0	210	6.2	17.68	1.92	2.70	1.94	0.86	90.2	78.6	76.3	57.3	74.8	99.1	>99.9
P348.15	40	0.7	9.0	210	6.2	16.91	2.09	2.73	1.94	0.87	89.0	78.7	76.1	57.9	74.9	97.7	99.0
AVG	40	0.7	9.0	210	6.2	17.30	2.01	2.72	1.94	0.87	89.6	78.7	76.2	57.6	74.8	98.4	99.7
P342.16	80	0.7	9.0	210	6.0	19.75	2.80	2.66	1.85	0.79	87.6	79.6	76.7	60.5	77.5	96.2	97.5
P347.16	80	0.7	9.0	210	6.0	19.17	2.60	2.35	1.88	0.79	88.1	81.8	79.4	59.6	77.4	97.1	98.4
AVG	80	0.7	9.0	210	6.0	19.46	2.70	2.51	1.87	0.79	87.8	80.7	78.0	60.1	77.5	96.6	98.0
P344.17	60	0.1	7.0	150	5.3	11.44	7.76	6.65	2.49	1.43	59.6	65.2	41.7	63.8	72.3	62.8	63.3
P354.17-1	60	0.1	7.0	150	6.5	13.18	8.15	6.42	2.46	1.39	61.8	65.2	43.7	62.9	72.1	65.3	65.8
AVG	60	0.1	7.0	150	5.9	12.31	7.96	6.54	2.48	1.41	60.7	65.2	42.7	63.4	72.2	64.0	64.5
P344.18	60	0.9	7.0	150	5.2	19.59	2.62	2.99	2.07	0.99	88.2	76.9	73.8	55.5	71.6	96.6	97.9
P354.18-1	60	0.9	7.0	150	6.5	17.71	2.33	2.95	2.04	1.00	88.4	77.1	74.1	56.0	71.3	96.8	98.1
P355.18-2	60	0.9	7.0	150	6.5	20.32	2.62	3.14	2.16	1.10	88.6	75.6	72.5	53.3	68.4	96.8	98.1
AVG	60	0.9	7.0	150	6.1	19.21	2.52	3.03	2.09	1.03	88.4	76.5	73.5	54.9	70.4	96.7	98.0

Pittsburgh # 8 Coal Central Composite Design Results

Run #	GT (min)	HCR (-)	pH (-)	T (s)	pH AFTER Grinding	P (g)	R (g)	Af			Sf			PSf			Yc (%)	BTU (%)
								Ap (%)	Sp (%)	Psp (%)	Y (%)	ARJ (%)	ARD (%)	SRJ (%)	PSRJ (%)			
								11.40	4.10	3.08								
P344.19-1	60	0.5	7.0	150	5.4	19.95	2.28	3.02	2.00	0.98	89.7	76.2	73.5	56.2	71.4	98.2	99.5	
P344.19-3	60	0.5	7.0	150	5.4	16.25	1.91	2.95	2.01	0.93	89.5	76.8	74.1	56.1	73.0	98.0	99.3	
P345.19-1	60	0.5	7.0	150	5.4	17.70	2.00	3.08	2.09	1.05	89.8	75.7	73.0	54.2	69.4	98.3	99.6	
P345.19-2	60	0.5	7.0	150	5.3	17.57	2.09	2.91	2.08	1.02	89.4	77.2	74.5	54.7	70.4	97.9	99.2	
P345.19-3	60	0.5	7.0	150	5.4	17.16	2.08	3.06	2.10	1.02	89.2	76.1	73.2	54.3	70.5	97.6	98.9	
P354.19-1	60	0.5	7.0	150	6.5	19.06	2.22	2.93	2.02	0.97	89.6	77.0	74.3	55.9	71.8	98.1	99.4	
P354.19-2	60	0.5	7.0	150	6.5	19.32	2.21	3.07	2.04	0.96	89.7	75.8	73.1	55.4	72.0	98.2	99.5	
P355.19-1	60	0.5	7.0	150	6.5	18.11	2.08	3.13	2.13	1.05	89.7	75.4	72.5	53.4	69.4	98.1	99.4	
P355.19-2	60	0.5	7.0	150	6.5	16.87	1.91	3.05	2.02	0.98	89.8	76.0	73.2	55.7	71.4	98.3	99.6	
AVG	60	0.5	7.0	150	5.9	18.00	2.09	3.02	2.05	1.00	89.6	76.2	73.5	55.1	71.0	98.1	99.4	
P346.20	20	0.5	7.0	150	6.4	17.13	2.11	3.27	1.90	0.83	89.0	74.5	71.3	58.7	76.0	97.2	98.5	
P356.20-1	20	0.5	7.0	150	6.9	16.25	1.80	3.00	1.94	0.89	90.0	76.3	73.7	57.4	74.0	98.6	99.9	
P356.20-2	20	0.5	7.0	150	6.8	15.82	1.88	3.06	1.91	0.88	89.4	76.0	73.2	58.4	74.5	97.8	99.1	
AVG	20	0.5	7.0	150	6.7	16.40	1.93	3.11	1.92	0.87	89.5	75.6	72.7	58.2	74.8	97.9	99.1	
P343.21-1	100	0.5	7.0	150	5.1	19.82	2.46	3.01	2.16	1.10	89.0	76.5	73.6	53.1	68.2	97.4	98.7	
P343.21-2	100	0.5	7.0	150	5.3	18.99	2.35	3.00	2.16	1.08	89.0	76.6	73.7	53.1	68.8	97.4	98.7	
AVG	100	0.5	7.0	150	5.2	19.41	2.41	3.01	2.16	1.09	89.0	76.5	73.6	53.1	68.5	97.4	98.7	
P344.22	60	0.5	3.0	150	5.3	18.82	2.09	3.19	2.37	1.32	90.0	74.8	72.0	48.0	61.4	98.3	99.6	
P355.22-1	60	0.5	3.0	150	6.5	18.98	2.23	3.11	2.05	1.00	89.5	75.6	72.7	55.3	70.9	97.9	99.1	
P355.22-2	60	0.5	3.0	150	6.5	16.82	1.84	3.20	2.12	1.05	90.1	74.7	71.9	53.4	69.3	98.5	99.8	
AVG	60	0.5	3.0	150	6.1	18.21	2.05	3.17	2.18	1.12	89.9	75.0	72.2	52.2	67.2	98.2	99.5	

1803 8 8 Coal

K-25

Particle Size Distribution for Illinois # 6 Coal Agglomeration Test Samples

Volume Percent Passing	Particle Diameter, μm	Grinding Time, min								
		5			20			60		
		Feed	Product	Refuse	Feed	Product	Refuse	Feed	Product	Refuse
125		100.0	100.0	100.0		100.0				
88		93.4	92.4	94.5	100.0	99.4				
62		85.3	83.3	88.7	98.6	99.0	100.0		100.0	100.0
44		70.3	69.8	76.9	95.7	96.8	98.1		97.1	98.3
31		52.0	51.6	59.2	87.5	86.3	87.8		96.4	97.1
22		41.0	38.8	49.4	81.7	79.9	81.8	100.0	88.1	89.5
16		28.4	27.0	34.4	64.9	63.8	63.4	91.5	74.1	75.7
11		16.6	16.9	21.1	44.4	44.6	41.6	78.0	58.6	61.2
7.8		10.5	9.9	16.6	32.1	27.6	29.1	66.5	40.0	44.6
5.5		5.8	6.4	9.3	17.9	16.0	17.7	48.9	25.2	27.2
3.9		1.7	3.1	3.4	8.6	9.9	8.8	30.7	17.2	15.8
2.8		1.1	0.0	3.4	7.5	3.7	4.9	22.0	8.7	7.2
1.9		0.2		1.8	4.0	1.0	1.8	11.6	3.1	2.2
1.4		0.0		0.6	1.5	0.0	0.3	4.4		

Illinois # 6 Coal Effect of Grinding Time on the Agglomeration Performance

Run #	C (%)	GT (min)	HCR (-)	T (s)	P (g)	R (g)	Ap (%)	Ar (%)	Sp (%)	ISP (%)	Y (%)	ARJ (%)	ARD (%)	SRJ (%)	ISRJ (%)	Yc (%)	BTU (%)	(Btu) f 10963
							Af		Sf	ISf								
							17.41		5.02	3.23								
1242\1	4	5	1.0	60	14.00	5.93	9.24	29.39	4.34	2.63	70.2	62.7	46.9	39.3	42.8	77.2	78.3	
1242\2	4	5	1.0	60	11.85	5.00	8.94	30.47	4.21	2.49	70.3	63.9	48.7	41.0	45.7	77.6	78.7	
1242\3	4	5	1.0	60	12.11	5.23	9.24	30.08	4.03	2.31	69.9	62.9	46.9	43.9	50.1	76.8	77.9	
1242\4	4	5	1.0	60	12.93	5.77	9.46	28.34	4.47	2.76	69.1	62.4	45.7	38.4	40.8	75.8	76.9	
Ave	4	5	1.0	60	12.72	5.48	9.22	29.57	4.26	2.55	69.9	63.0	47.0	40.7	44.9	76.8	77.9	
1244\1	4	20	1.0	60	9.94	9.05	10.75	19.30	4.62	2.92	52.3	67.7	38.2	51.8	52.7	56.5	57.2	
1244\2	4	20	1.0	60	8.50	9.27	10.60	19.01	4.87	3.18	47.8	70.9	39.1	53.6	53.0	51.8	52.4	
1244\3	4	20	1.0	60	9.95	10.07	10.48	18.63	4.82	3.13	49.7	70.1	39.8	52.3	51.9	53.9	54.5	
1244\4	4	20	1.0	60	8.66	9.45	9.97	18.43	4.84	3.15	47.8	72.6	42.8	53.9	53.4	52.1	52.8	
Ave	4	20	1.0	60	9.26	9.46	10.45	18.84	4.79	3.09	49.4	70.3	40.0	52.9	52.8	53.6	54.3	
1246\1	4	60	1.0	60	5.48	16.05	13.58	17.33	5.40	3.74	25.5	80.1	22.0	72.6	70.5	26.6	26.8	
1246\2	4	60	1.0	60	5.62	15.56	13.58	17.29	5.00	3.33	26.5	79.3	22.0	73.6	72.6	27.8	28.0	
1246\3	4	60	1.0	60	5.91	15.79	13.46	17.19	5.18	3.52	27.2	78.9	22.7	71.9	70.3	28.5	28.8	
1246\4	4	60	1.0	60	5.61	16.14	13.23	17.18	4.85	3.18	25.8	80.4	24.0	75.1	74.7	27.1	27.3	
Ave	4	60	1.0	60	5.66	15.89	13.47	17.25	5.11	3.44	26.3	79.7	22.7	73.3	72.0	27.5	27.7	

Illinois # 6 Coal

Grinding Time = 60 min, Grinding Load = 640 g, d_{50} = 6.9 microns

(Btu)f
11350

Illinois # 6 Coal Effect of pH on the Agglomeration Performance for Finely Ground Coal

Run #	d50 micron	HCR (-)	T (s)	P (g)	R (g)	Af		Sp (%)	Psp (%)	Y (%)	ARJ (%)	ARD (%)	SRJ (%)	PSRJ (%)	Yc (%)	BTU (%)
						Ar (%)	Psf (%)									
							14.90		5.29	3.54						(Btu)f 11350
1254/3.4	6.9	3.50	4.00	180	9.55	4.29	9.81	3.78	1.86	69.0	54.6	34.2	50.7	63.7	73.1	73.8
1254/4.3	6.9	3.50	4.00	180	10.81	4.15	10.19	3.83	1.92	72.3	50.6	31.6	47.7	60.8	76.3	76.9
1254/4.4	6.9	3.50	4.00	180	12.47	4.69	10.92	3.90	2.01	72.7	46.7	26.7	46.4	58.7	76.1	76.6
1254/4.5	6.9	3.50	4.00	180	10.11	3.74	10.88	3.83	1.94	73.0	46.7	27.0	47.1	60.0	76.5	77.0
Ave	6.9	3.50	4.00	180	10.73	4.21	10.45	3.84	1.93	71.7	49.6	29.9	48.0	60.8	75.5	76.1
1254/6.1	6.9	8.00	4.00	360	8.92	3.60	9.52	3.25	1.31	71.3	54.5	36.1	56.2	73.6	75.8	76.5
1254/6.2	6.9	8.00	4.00	360	10.48	3.19	10.66	3.43	1.52	76.7	45.1	28.5	50.3	67.1	80.5	81.1
1254/6.3	6.9	8.00	4.00	360	9.35	3.93	10.37	3.40	1.48	70.4	51.0	30.4	54.7	70.6	74.2	74.8
Ave	6.9	8.00	4.00	360	9.58	3.57	10.18	3.36	1.44	72.8	50.2	31.7	53.7	70.4	76.8	77.5
1254/5.2	6.9	11.50	4.00	360	10.03	5.20	12.98	3.16	1.29	65.8	42.6	12.9	60.7	76.0	67.3	67.6
1254/5.3	6.9	11.50	4.00	360	10.60	5.73	13.09	3.17	1.30	64.9	43.0	12.1	61.1	76.2	66.3	66.5
Ave	6.9	11.50	4.00	360	10.32	5.47	13.04	3.17	1.30	65.4	42.8	12.5	60.9	76.1	66.8	67.0

Illinois # 6 Coal Grinding Time = 4 hr, Grinding Load = 640 g, d50 = 3.7 microns

Run #	Ss mesh	pH	HCR (-)	T (s)	P (g)	R (g)	Af		Sf		Y	ARJ (%)	ARD (%)	SRJ (%)	PSRJ (%)	Yc (%)	BTU (%)
							Ap (%)	Ar (%)	Sp (%)	Psp (%)							
							15.51		5.29	3.55							
1255/1.1	120	3.80	4.00	180	9.72	2.74	12.38		3.92	2.06	78.0	37.7	20.2	42.2	54.7	80.9	81.3
1255/2.1	120	3.80	4.00	180	11.39	3.42	13.00		4.01	2.16	76.9	35.5	16.2	41.7	53.2	79.2	79.5
1255/2.2	120	3.80	4.00	180	10.76	3.68	12.57		3.95	2.09	74.5	39.6	19.0	44.3	56.1	77.1	77.5
1255/2.3	120	3.80	4.00	180	9.27	3.73	11.72		4.00	2.13	71.3	46.1	24.4	46.1	57.2	74.5	75.0
Ave	120	3.80	4.00	180	10.29	3.39	12.42		3.97	2.11	75.2	39.8	19.9	43.6	55.3	77.9	78.4
1255/6.1	230	3.80	4.00	180	12.23	1.29	12.81		4.03	2.18	90.5	25.3	17.4	31.1	44.5	93.3	93.8
1255/6.2	230	3.80	4.00	180	11.00	1.43	12.04		4.02	2.15	88.5	31.3	22.4	32.7	46.4	92.1	92.7
Ave	230	3.80	4.00	180	11.62	1.36	12.43		4.03	2.17	89.5	28.3	19.9	31.9	45.4	92.7	93.2
1255/4.1	120	11.80	4.00	360	10.22	3.79	9.18		3.06	1.09	73.0	56.8	40.8	57.8	77.6	78.4	79.3
1255/4.2	120	11.80	4.00	360	9.90	3.92	10.44		3.06	1.12	71.6	51.8	32.7	58.6	77.4	75.9	76.6
1255/4.3	120	11.80	4.00	360	10.33	3.24	10.98		3.16	1.24	76.1	46.1	29.2	54.5	73.4	80.2	80.8
1255/4.4	120	11.80	4.00	360	8.94	3.78	9.72		3.09	1.14	70.3	56.0	37.3	59.0	77.4	75.1	75.8
Ave	120	11.80	4.00	360	9.85	3.68	10.08		3.09	1.15	72.7	52.7	35.0	57.5	76.5	77.4	78.1
1255/5.1	230	11.80	4.00	360	13.86	1.38	10.78		3.03	1.10	90.9	36.8	30.5	47.9	71.8	96.0	96.8
1255/5.2	230	11.80	4.00	360	12.21	1.37	10.44		3.03	1.09	89.9	39.5	32.7	48.5	72.4	95.3	96.2
Ave	230	11.80	4.00	360	13.03	1.37	10.61		3.03	1.10	90.4	38.1	31.6	48.2	72.1	95.7	96.5

**APPENDIX L: AGGLOMERATION TEST RESULTS
FOR THE ADDITIONAL COALS**

NOMENCLATURE

1. Af: Ash Content of Feed Coal (%)
2. Ap: Ash Content of Product Coal (%)
3. Ar: Ash Content of Refuse (%)
4. ARD: Ash Reduction (%)
$$ARD = (1 - Ap/Af) \times 100$$
5. ARJ: Ash Rejection (%)
$$ARJ = 100 - Y \times Ap / Af$$
6. (Btu)f: Calorific Value of Feed (Btu/lb)
7. (Btu)p: Calorific Value of Product (Btu/lb)
8. BTU: Btu Recovery (%),
$$BTU = (Btu)p / (Btu)f \times Y$$
9. C: Coal Slurry Concentration (Wt.%)
10. N: Mixing Speed (rpm)
11. P: Product Coal Weight (g)
12. PCR: Pentane/Coal Ratio (Weight Basis)
13. PSf: Pyritic Sulfur Content of Feed (%)
14. PSp: Pyritic Sulfur Content of Product (%)
15. PSRJ: Pyritic Sulfur Rejection (%)
$$PSRJ = (100 - Y \times PSp / PSf)$$
16. R: Refuse Weight (g)
17. RCR: Reagent to Coal Ratio
18. Sf: Total Sulfur Content in the Feed (%)
19. Sp: Total Sulfur Content in the Product (%)
20. SRJ: Total Sulfur Rejection (%)
$$SRJ = (100 - Y \times Sp / Sf)$$
21. T: Agglomeration Time (s)
22. Y: Overall Yield (%)
$$Y = P / (P + R) \times 100$$
23. Yc: Clean Coal Yield (%)
$$Yc = Y \times (100 - Ap) / (100 - Af)$$

Upper Freeport Coal, Grant County, WV

Run #	AGGL	Ss	pH	T (s)	N (rpm)	P (g)	R (g)	Af		Sf		PSf		SRJ (%)	PSRJ (%)	Yc (%)
								Ap (%)	Sp (%)	PSP (%)	Y (%)	ARJ (%)	ARD (%)			
								14.88	3.18	2.57						
UG258\1.1	Hept	120	4	30	9000	14.39	1.56	6.61	1.78	1.09	90.2	59.9	55.5	49.5	61.6	99.0
UG258\1.2	Hept	120	4	30	9000	19.06	1.95	6.63	1.88	1.20	90.7	59.6	55.4	46.4	57.8	99.5
UG258\1.3	Hept	120	4	30	9000	16.39	1.71	6.41	1.98	1.30	90.5	61.0	56.9	43.6	54.4	99.6
Ave	Hept	120	4	30	9000	16.61	1.74	6.55	1.88	1.20	90.5	60.1	56.0	46.5	57.9	99.4
UG258\2.1	Hept	60	4	30	9000	14.58	1.59	6.41	1.84	1.15	90.2	61.1	56.9	47.8	59.6	99.1
UG258\2.2	Hept	60	4	30	9000	16.97	1.76	7.62	1.81	1.13	90.6	53.6	48.8	48.4	60.1	98.3
Ave	Hept	60	4	30	9000	15.77	1.68	7.02	1.83	1.14	90.4	57.4	52.8	48.1	59.9	98.7
UG258\3.1	Pent	120	4	30	9000	16.75	1.70	6.27	1.79	1.10	90.8	61.7	57.8	48.9	61.1	>99.9
UG258\3.2	Pent	120	4	30	9000	16.92	1.76	6.73	1.78	1.10	90.6	59.0	54.8	49.3	61.4	99.3
Ave	Pent	120	4	30	9000	16.83	1.73	6.50	1.79	1.10	90.7	60.4	56.3	49.1	61.3	99.6
UG258\4.1	Pent	60	4	30	9000	18.45	1.99	7.25	1.76	1.08	90.2	56.0	51.2	50.1	62.2	98.3
UG258\4.2	Pent	60	4	30	9000	19.32	1.90	6.38	1.70	1.01	91.1	61.0	57.1	51.3	64.2	>99.9
Ave	Pent	60	4	30	9000	18.88	1.95	6.82	1.73	1.05	90.7	58.5	54.2	50.7	63.2	99.2

Upper Freeport Coal, Grant County, WV

		Af		Sf		PSf										
		14.88		3.18		2.57										
Run #	AGGL Ss	pH	T (s)	N (rpm)	P (g)	R (g)	Ap (%)	Sp (%)	PSP (%)	Y (%)	ARJ (%)	ARD (%)	SRJ (%)	PSRJ (%)	Yc (%)	
UG258\5.1	Hept	120	11.8	30	9000	14.25	2.05	5.44	1.31	0.61	87.4	68.0	63.5	64.0	79.3	97.1
UG258\5.2	Hept	120	11.8	30	9000	15.61	2.18	5.46	1.30	0.60	87.8	67.8	63.3	64.1	79.6	97.5
UG258\5.3	Hept	120	11.8	30	9000	17.73	2.43	4.86	1.48	0.78	87.9	71.3	67.3	59.1	73.4	98.3
Ave	Hept	120	11.8	30	9000	15.86	2.22	5.25	1.36	0.66	87.7	69.0	64.7	62.4	77.4	97.6
UG258\6.1	Hept	60	11.8	30	9000	15.77	2.22	5.37	1.25	0.55	87.7	68.4	63.9	65.5	81.3	97.4
UG258\6.2	Hept	60	11.8	30	9000	16.16	2.28	5.36	1.32	0.62	87.6	68.4	63.9	63.6	78.9	97.4
Ave	Hept	60	11.8	30	9000	15.96	2.25	5.37	1.29	0.58	87.6	68.4	63.9	64.6	80.1	97.4
UG258\7.1	Pent	120	11.8	30	9000	17.28	2.38	5.69	1.32	0.62	87.9	66.4	61.8	63.5	78.8	97.4
UG258\7.2	Pent	120	11.8	30	9000	14.54	2.03	5.59	1.28	0.58	87.8	67.0	62.4	64.7	80.2	97.3
UG258\7.3	Pent	120	11.8	30	9000	15.84	2.20	5.61	1.31	0.61	87.8	66.9	62.3	63.8	79.2	97.4
Ave	Pent	120	11.8	30	9000	15.89	2.20	5.63	1.30	0.60	87.8	66.8	62.2	64.0	79.4	97.4
UG258\8.1	Pent	60	11.8	30	9000	15.62	2.17	5.97	1.36	0.66	87.8	64.7	59.8	62.5	77.3	97.0
UG258\8.2	Pent	60	11.8	30	9000	16.51	2.36	5.44	1.33	0.63	87.5	68.0	63.4	63.4	78.6	97.2
UG258\8.3	Pent	60	11.8	30	9000	14.97	2.07	6.37	1.32	0.63	87.9	62.4	57.2	63.5	78.6	96.7
Ave	Pent	60	11.8	30	9000	15.70	2.20	5.93	1.34	0.64	87.7	65.0	60.1	63.1	78.2	96.9

Wyodak Coal, Campbell County, WY Grinding Time = 4 hr

Run #	C	Ss	MCR	T	N	P	R	Ap	Sp	PSP	Y	ARJ	ARD	SRJ	PSRJ	YC
	(%)	-	(-)	(s)	(rpm)	(g)	(g)	(%)	(%)	(%)	(%)	(%)	(%)	(%)	(%)	(%)
								8.20	0.59	0.29						
WC259/1.1	4	230	1	180	9000	10.00	5.69	6.36	0.56	0.24	63.7	50.5	22.4	39.4	46.4	65.0
WC259/1.2	4	230	1	180	9000	7.99	5.47	6.81	0.56	0.24	59.4	50.7	16.9	43.7	50.0	60.3
Ave	4	230	1	180	9000	9.00	5.58	6.59	0.56	0.24	61.7	50.4	19.7	41.4	48.1	62.8
WC259/2.1	4	120	1	180	9000	2.45	10.44	6.06	0.59	0.24	19.0	86.0	26.1	80.8	84.0	19.4
WC259/2.2	4	120	1	180	9000	2.60	13.98	5.98	0.57	0.24	15.7	88.6	27.0	84.8	86.8	16.0
Ave	4	120	1	180	9000	2.52	12.21	6.02	0.58	0.24	17.1	87.4	26.6	83.0	85.6	17.5

Wyodak Coal, Campbell County, WY Grinding Time = 4 hr

Run #	C (%)	Ss	HCR (-)	T (s)	N (rpm)	P (g)	R (g)	Ap (%)	Sp (%)	Psp (%)	Y (%)	ARJ (%)	ARD (%)	SRJ (%)	PSRJ (%)	Yc (%)	Af Sf Psf		
																	8.20	0.59	0.29
WC259/3.1	4	120	1	360	9000	3.33	9.98	6.19	0.55	0.23	25.0	81.1	24.5	76.5	80.1	25.6			
WC259/3.2	4	120	1	360	9000	3.36	9.90	6.23	0.55	0.23	25.3	80.7	24.0	76.2	79.8	25.9			
Ave	4	120	1	360	9000	3.35	9.94	6.21	0.55	0.23	25.2	80.9	24.3	76.4	80.0	25.7			
WC259/4.1	4	230	1	360	9000	10.35	3.43	6.45	0.55	0.24	75.1	40.9	21.3	29.6	37.6	76.6			
WC259/4.2	4	230	1	360	9000	10.04	3.40	6.39	0.55	0.24	74.7	41.8	22.1	30.0	38.0	76.2			
Ave	4	230	1	360	9000	10.20	3.41	6.42	0.55	0.24	74.9	41.3	21.7	29.8	37.8	76.4			
WC259/5.1	4	120	2	360	9000	6.62	8.53	6.25	0.55	0.23	43.7	66.7	23.8	59.1	65.2	44.6			
WC259/5.2	4	120	2	360	9000	4.61	10.55	6.41	0.55	0.23	30.4	76.2	21.8	71.5	75.8	31.0			
Ave	4	120	2	360	9000	5.61	9.54	6.33	0.55	0.23	37.0	71.4	22.8	65.3	70.5	37.8			
WC259/6.1	4	230	2	360	9000	9.42	2.50	6.37	0.54	0.22	79.0	38.6	22.3	27.3	39.8	80.6			
WC259/6.2	4	230	2	360	9000	10.47	2.29	6.41	0.54	0.22	82.1	35.8	21.8	24.5	37.5	83.7			
Ave	4	230	2	360	9000	9.94	2.39	6.39	0.54	0.22	80.6	37.2	22.1	25.8	38.6	82.2			
WC259/7.1	4	120	4	360	9000	5.25	6.33	6.49	0.55	0.23	45.3	64.1	20.9	57.5	63.9	46.2			
WC259/7.2	4	120	4	360	9000	7.47	4.22	6.61	0.55	0.23	63.9	48.5	19.4	40.1	49.1	65.0			
Ave	4	120	4	360	9000	6.36	5.27	6.55	0.55	0.23	54.7	56.3	20.1	48.8	56.5	55.7			
WC259/8.1	4	230	4	360	9000	13.29	2.30	6.79	0.54	0.23	85.2	29.4	17.2	21.6	32.2	86.5			
WC259/8.2	4	230	4	360	9000	12.08	2.73	6.91	0.54	0.23	81.6	31.3	15.7	25.0	35.1	82.7			
Ave	4	230	4	360	9000	12.69	2.52	6.85	0.54	0.23	83.5	30.3	16.5	23.2	33.6	84.7			

Kentucky # 9 Coal

Run #	GT (min)	HCR (-)	pH (-)	T (s)	P (g)	R (g)	Ap (%)	Sp (%)	PSP (%)	Y (%)	ARJ (%)	ARD (%)	SRJ (%)	PSRJ (%)	Yc (%)
							Af	Sf	PSf						
							15.1	3.98	2.52						
K406.1	40	0.30	5.0	120	18.20	2.50	3.65	2.49	1.06	87.9	78.7	75.8	45.3	63.0	99.8
K407.1	40	0.30	5.0	120	18.84	2.54	3.70	2.52	1.02	88.1	78.4	75.5	44.5	64.3	100.0
AVG	40	0.30	5.0	120	18.52	2.52	3.68	2.51	1.04	88.0	78.6	75.7	44.9	63.7	99.9
K408.2	80	0.30	5.0	120	18.04	2.75	3.98	2.49	1.06	86.8	77.1	73.6	46.0	63.5	98.1
K409.2	80	0.30	5.0	120	16.85	2.55	3.63	2.42	1.02	86.9	79.1	76.0	47.5	64.8	98.6
AVG	80	0.30	5.0	120	17.45	2.65	3.81	2.46	1.04	86.8	78.1	74.8	46.7	64.2	98.4
K406.3	40	0.30	9.0	120	19.00	2.72	3.86	2.52	1.08	87.5	77.6	74.4	44.9	62.5	99.1
K407.3	40	0.30	9.0	120	15.28	2.27	3.44	2.50	1.07	87.1	80.2	77.2	45.6	63.0	99.0
AVG	40	0.30	9.0	120	17.14	2.50	3.65	2.51	1.08	87.3	78.9	75.8	45.2	62.8	99.0
K408.4	80	0.30	9.0	120	17.61	3.07	4.02	2.42	1.03	85.2	77.3	73.4	48.5	65.2	96.3
K409.4	80	0.30	9.0	120	18.62	3.26	4.29	2.42	1.07	85.1	75.8	71.6	48.5	63.9	95.9
AVG	80	0.30	9.0	120	18.11	3.17	4.16	2.42	1.05	85.1	76.6	72.5	48.5	64.5	96.1
K406.5	40	0.30	5.0	240	19.27	2.59	3.70	2.52	1.13	88.2	78.4	75.5	44.5	60.5	100.0
K407.5	40	0.30	5.0	240	18.42	2.29	3.99	2.61	1.20	88.9	76.5	73.6	42.0	57.6	100.6
AVG	40	0.30	5.0	240	18.85	2.44	3.85	2.57	1.17	88.5	77.4	74.5	43.2	59.1	100.3
K408.6	80	0.30	5.0	240	17.12	2.59	3.64	2.47	1.04	86.9	79.1	75.9	46.4	64.2	98.6
K409.6	80	0.30	5.0	240	18.57	2.89	4.02	2.45	0.99	86.5	77.0	73.4	47.0	66.0	97.8
AVG	80	0.30	5.0	240	17.85	2.74	3.83	2.46	1.02	86.7	78.0	74.6	46.7	65.1	98.2
K406.7	40	0.30	9.0	240	18.63	2.61	3.50	2.48	1.06	87.7	79.7	76.8	45.6	63.1	99.7
K407.7	40	0.30	9.0	240	16.15	2.30	3.42	2.61	1.12	87.5	80.2	77.4	42.9	61.1	99.6
AVG	40	0.30	9.0	240	17.39	2.45	3.46	2.55	1.09	87.6	79.9	77.1	44.3	62.1	99.6

Kentucky # 9 Coal

Run #	GT (min)	HCR (-)	pH (-)	T (s)	P (g)	R (g)	Af Sf PSf				Yc (%)				
							Ap (%)	Sp (%)	PSp (%)	Y (%)		ARJ (%)	ARD (%)	SRJ (%)	PSRJ (%)
							15.1	3.98	2.52						
K408.8	80	0.30	9.0	240	18.02	3.29	3.61	2.40	0.98	84.6	79.8	76.1	49.3	67.1	96.0
K409.8	80	0.30	9.0	240	18.13	3.12	3.58	2.33	0.88	85.3	79.8	76.3	50.3	70.2	96.9
AVG	80	0.30	9.0	240	18.08	3.21	3.60	2.37	0.93	84.9	79.8	76.2	49.8	68.7	96.4
K406.9	40	0.70	5.0	120	14.91	2.37	3.59	2.41	0.91	86.3	79.5	76.2	48.0	68.8	98.0
K407.9	40	0.70	5.0	120	18.46	3.06	3.43	2.49	1.04	85.8	80.5	77.3	46.6	64.6	97.6
AVG	40	0.70	5.0	120	16.69	2.72	3.51	2.45	0.98	86.0	80.0	76.8	47.3	66.7	97.8
K408.10	80	0.70	5.0	120	17.20	2.79	3.44	2.36	0.91	86.0	80.4	77.2	49.2	68.9	97.9
K409.10	80	0.70	5.0	120	18.06	2.95	3.40	2.45	1.02	86.0	80.6	77.5	47.4	65.2	97.8
AVG	80	0.70	5.0	120	17.63	2.87	3.42	2.41	0.97	86.0	80.5	77.4	48.3	67.1	97.8
K406.11	40	0.70	9.0	120	15.94	2.49	3.41	2.49	1.00	86.5	80.5	77.4	46.2	65.7	98.4
K407.11	40	0.70	9.0	120	19.14	3.04	3.25	2.49	1.03	86.3	81.4	78.5	46.3	64.7	98.3
AVG	40	0.70	9.0	120	17.54	2.77	3.33	2.49	1.02	86.4	80.9	77.9	46.2	65.2	98.4
K408.12	80	0.70	9.0	120	17.33	3.02	3.32	2.54	1.04	85.2	81.3	78.0	45.9	64.9	97.0
K409.12	80	0.70	9.0	120	18.02	2.93	3.20	2.41	0.94	86.0	81.8	78.8	48.2	67.9	98.1
AVG	80	0.70	9.0	120	17.68	2.98	3.26	2.48	0.99	85.6	81.5	78.4	47.0	66.4	97.5
K406.13	40	0.70	5.0	240	17.15	3.03	3.17	2.41	0.92	85.0	82.2	79.0	48.8	69.0	96.9
K407.13	40	0.70	5.0	240	16.62	2.92	3.18	2.42	0.93	85.1	82.1	78.9	48.5	68.6	97.0
AVG	40	0.70	5.0	240	16.89	2.98	3.18	2.42	0.93	85.0	82.1	79.0	48.7	68.8	97.0
K408.14	80	0.70	5.0	240	17.11	2.99	3.25	2.36	0.89	85.1	81.7	78.5	49.8	69.9	97.0
K409.14	80	0.70	5.0	240	18.06	3.04	3.19	2.37	0.87	85.6	81.9	78.9	49.3	70.5	97.6
AVG	80	0.70	5.0	240	17.59	3.02	3.22	2.36	0.88	85.4	81.8	78.7	49.5	70.2	97.3

Kentucky # 9 Coal

Run #	GT (min)	HCR (-)	pH (-)	T (s)	P (g)	R (g)	Af Sf PSf					Yc (%)			
							AP (%)	Sp (%)	PSP (%)	Y (%)	ARJ (%)		ARD (%)	SRJ (%)	PSRJ (%)
							15.1	3.98	2.52						
K406.15	40	0.70	9.0	240	18.00	2.70	3.27	2.46	1.00	87.0	81.2	78.3	46.5	65.5	99.1
K407.15	40	0.70	9.0	240	16.93	2.67	3.20	2.44	0.99	86.4	81.7	78.8	47.3	66.1	98.5
AVG	40	0.70	9.0	240	17.47	2.69	3.24	2.45	1.00	86.7	81.4	78.6	46.9	65.8	98.8
K408.16	80	0.70	9.0	240	18.74	3.12	3.19	2.41	0.95	85.7	81.9	78.9	48.3	67.7	97.8
K409.16	80	0.70	9.0	240	17.06	2.80	3.27	2.41	0.94	85.9	81.4	78.3	48.2	68.0	97.9
AVG	80	0.70	9.0	240	17.90	2.96	3.23	2.41	0.95	85.8	81.6	78.6	48.3	67.8	97.8
K411-17	60	0.10	7.0	180	11.99	12.97	9.87	2.55	1.22	48.0	68.6	34.6	69.4	76.7	51.0
K412-17	60	0.10	7.0	180	10.21	7.04	7.08	2.62	1.27	59.2	72.2	53.1	61.2	70.2	64.8
K413-17.3	60	0.10	7.0	180	9.89	9.77	7.64	2.59	1.23	50.3	74.5	49.4	67.4	75.4	54.7
AVG	60	0.10	7.0	180	10.70	9.93	8.20	2.59	1.24	52.5	71.8	45.7	66.0	74.1	56.8
K411-18	60	0.90	7.0	180	20.16	3.22	3.55	2.50	1.00	86.2	79.7	76.5	46.1	65.8	98.0
K412-18	60	0.90	7.0	180	20.24	3.30	3.45	2.64	1.17	86.0	80.4	77.2	43.3	60.1	97.8
AVG	60	0.90	7.0	180	20.20	3.26	3.50	2.57	1.09	86.1	80.0	76.8	44.7	62.9	97.9

Kentucky # 9 Coal

Run #	GT (min)	HCR (-)	pH (-)	T (s)	P (g)	R (g)	Af Sf PSf				Yc (%)								
							AP (%)	Sp (%)	PSP (%)	Y (%)		ARJ (%)	ARD (%)	SRJ (%)	PSRJ (%)				
							15.1	3.98	2.52										
K411-19-1	60	0.50	7.0	180	14.47	2.36	3.09	2.49	1.02	86.0	82.4	79.5	46.5	65.2	98.1				
K411-19-2	60	0.50	7.0	180	19.27	2.91	3.29	2.48	0.99	86.9	81.1	78.2	46.1	65.9	99.0				
K411-19-3	60	0.50	7.0	180	17.53	2.73	3.17	2.50	0.99	86.5	81.8	79.0	45.9	66.0	98.7				
K412-19-4	60	0.50	7.0	180	13.48	2.14	3.10	2.50	1.02	86.3	82.3	79.5	46.1	65.1	98.5				
K412-19-5	60	0.50	7.0	180	21.38	3.08	3.26	2.52	1.04	87.4	81.1	78.4	44.9	63.9	99.6				
K412-19-6	60	0.50	7.0	180	16.54	2.49	3.08	2.49	1.02	86.9	82.3	79.6	45.9	64.8	99.2				
K413-19-7	60	0.50	7.0	180	22.40	3.30	3.21	2.53	1.04	87.2	81.5	78.7	44.9	64.0	99.4				
K413-19-8	60	0.50	7.0	180	17.09	2.56	3.11	2.48	0.99	87.0	82.1	79.4	46.1	65.8	99.3				
K413-19-9	60	0.50	7.0	180	16.50	2.62	3.16	2.55	1.03	86.3	81.9	79.1	45.0	64.7	98.4				
AVG	60	0.50	7.0	180	17.63	2.69	3.16	2.50	1.02	86.7	81.8	79.1	45.7	65.1	98.9				
K414-20-1	20	0.50	7.0	180	18.63	3.12	3.37	2.38	0.91	85.7	80.9	77.7	49.0	69.1	97.5				
K414-20-2	20	0.50	7.0	180	15.88	2.63	3.53	2.42	0.93	85.8	79.9	76.6	48.1	68.3	97.5				
AVG	20	0.50	7.0	180	17.26	2.88	3.45	2.40	0.92	85.7	80.4	77.2	48.6	68.7	97.5				
K410-21-1	100	0.50	7.0	180	18.97	2.95	3.03	2.30	0.83	86.5	82.6	79.9	50.2	71.5	98.8				
K410-21-2	100	0.50	7.0	180	15.96	2.57	3.02	2.40	0.91	86.1	82.8	80.0	48.3	68.9	98.4				
K410-21-3	100	0.50	7.0	180	18.31	3.03	3.07	2.44	1.00	85.8	82.6	79.7	47.7	66.0	98.0				
AVG	100	0.50	7.0	180	17.75	2.85	3.04	2.38	0.91	86.2	82.7	79.9	48.7	68.8	98.4				
K411-22	60	0.50	3.0	180	12.60	2.28	3.33	2.37	0.91	84.7	81.3	77.9	49.8	69.4	96.4				
K412-22	60	0.50	3.0	180	18.76	2.71	3.61	2.61	1.16	87.4	79.1	76.1	43.0	59.8	99.2				
K413-22-3	60	0.50	3.0	180	11.37	2.23	3.58	2.39	0.95	83.6	80.2	76.3	50.0	68.5	94.9				
K412-22-4	60	0.50	3.0	180	15.85	2.57	3.41	2.47	0.99	86.0	80.6	77.4	46.9	66.2	97.9				
AVG	60	0.50	3.0	180	14.65	2.45	3.48	2.46	1.00	85.4	80.3	76.9	47.4	66.0	97.1				

Kentucky # 9 Coal

Run #	GT (min)	HCR (-)	pH (-)	T (s)	P (g)	R (g)	AP (%)	Af Sf		PSP (%)	Y (%)	ARJ (%)	ARD (%)	SRJ (%)	PSRJ (%)	Yc (%)
								15.1	3.98							
K411-23	60	0.50	11.0	180	21.20	3.43	3.85	2.43	0.97	86.1	78.1	74.5	47.7	66.9	97.5	
K412-23-2	60	0.50	11.0	180	18.30	2.98	3.53	2.52	1.05	86.0	79.9	76.6	45.8	64.2	97.7	
AVG	60	0.50	11.0	180	19.75	3.21	3.69	2.48	1.01	86.0	79.0	75.6	46.8	65.5	97.6	
K411-24	60	0.50	7.0	60	17.96	2.83	3.35	2.50	1.04	86.4	80.8	77.8	46.0	64.3	98.3	
K413-24	60	0.50	7.0	60	16.92	2.69	3.41	2.48	1.00	86.3	80.5	77.4	46.5	65.8	98.2	
AVG	60	0.50	7.0	60	17.44	2.76	3.38	2.49	1.02	86.3	80.7	77.6	46.3	65.1	98.3	
K411-25	60	0.50	7.0	300	16.25	2.48	3.02	2.51	0.99	86.8	82.6	80.0	45.6	65.9	99.1	
K411-25N	60	0.50	7.0	300	18.48	2.78	3.25	2.46	1.00	86.9	81.3	78.5	46.5	65.5	99.1	
AVG	60	0.50	7.0	300	17.37	2.63	3.14	2.49	1.00	86.8	82.0	79.2	46.1	65.7	99.1	

END

**DATE
FILMED**

3 / 5 / 93