3572 Iron Works Pike
Lexington, KY 40511-8433
FAX 606-257-0220

DOE/PC/91058--T4

DE93 011446

QUARTERLY PROGRESS REPORT FOR JULY THROUGH SEPTEMBER, 1992

RATE ENHANCEMENT FOR CATALYTIC UPGRADING COAL NAPHTHAS

#DE-AC22-91PC91058

P.I.: B. H. Davis

Begin Date: 9/30/91

End Date: 9/29/93

MASTER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

UK

*An Equal Opportunity/
Affirmative Action University*

yes

BP

W. J. Davis

QUARTERLY TECHNICAL PROGRESS REPORT

Rate Enhancement for Catalytic Upgrading Naphthas - Period ending September 30, 1992

Contract No.: DE-AC22-90PC91058

Contractor: University of Kentucky Research Foundation
Kinkead Hall
Lexington, KY 40506-0057

Starting Date: September 30, 1991

Ending Date: September 29, 1993

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

During this quarter, hydrotreatment of the Black Thunder naphtha sample was carried out using two commercial catalysts. Also, the Illinois #6 naphtha were hydrotreated using unsupported transition metal sulfides. Each reaction condition was maintained for 24 hours and three steady state samples were taken in the last 6 hours of the 24 hours period to calculate the removal of the heteroatoms for each condition. Prior to G.C. analysis, the samples were washed three times with distilled water to remove dissolved H_2S and NH_3 .

Two commercial catalysts, a Co-Mo on alumina (American Cyanamid HDS-1442A, 1/16" x 1/4" pellets) and a Ni-W on alumina (Harshaw Catalyst, Ni-4301, E 1/12, Lot 16, Drum 29) were employed in the processing of the Black Thunder naphtha samples. Analytical data for these catalysts are presented in Table 1.

Unsupported transition metal sulfides were prepared following the procedure published by Chianelli et al. Conventionally, the transition metal sulfide have been prepared at high temperature (above 400°C) by vapor-phase reaction of the halides with hydrogen sulfide or by direct contact of the elements in a sealed tube. The product is usually highly crystalline, low surface area and is often nonstoichiometric and multiphased. The technique presented by Chianelli et al involves precipitation of the amorphous transition metal sulfide from a nonaqueous solution. The corresponding transition metal halide and a sulfide source, i.e. the lithium salts (Li_2S or LiHS) and the ammonium compounds, are used. This procedure yields materials of moderate surface area. Hydroxide solvents in general (alcohols and carboxylic acids) are too reactive to serves as solvents. The solvent used in the preparation of a transition metal sulfide is usually either ethyl acetate or tetrahydrofuran.

Prior to activity testing, the catalysts are pretreated in H_2S for about 8 hours at 400°C , then washed with 12 % acetic acid to remove the LiCl produced during the reaction and then treated again at 400°C in 10 % $\text{H}_2\text{S}/\text{H}_2$. This procedure converts the amorphous sulfides to a poorly crystalline sulfide phase.

The transition metal chlorides used in this work were supplied by Aldrich and Alfa and were used without further treatment. Most of the metal chlorides have 99 % purity or better. Since the reactant and product have been found to be very sensitive to oxygen and/or water, all of the experiments were carried out at a dry box, which is filled with nitrogen or helium.

The general procedure for preparation of a transition metal sulfide is as follows: A 400 ml solution of the transition metal chloride in an organic solvent (ethyl acetate or tetrahydrofuran) was prepared in a dry box under nitrogen. This solution was added to 400 ml of a well-stirred solution of lithium sulfide in the same solvent. This mixture was stirred overnight, the dark precipitate that formed was filtered in the dry box, and washed with 100 ml of the solvent and then dried. The sample was removed from the dry box and pretreated in a flow of 10 % $\text{H}_2\text{S}/\text{H}_2$ for 6 hours at 400°C . After this treatment, the catalyst is stable enough to wash with 12 % acetic acid to remove the residual LiCl . The catalyst was then treated again with 10 % $\text{H}_2\text{S}/\text{H}_2$ at 400°C .

The three grams of catalyst were added to the reactor were presulfided at 660 psig using a mixture of 10 % H_2S in hydrogen (35 mL/min) prior to the beginning of hydrotreating operations. The sulfiding temperature was ramped to 375°C at a rate of $1^\circ\text{C}/\text{min}$, and then maintained at 375°C for 4 hours. The gas flow was switched to helium for 1 hour after sulfiding and prior to the start of liquid and H_2 feed.

Naphtha Feedstock

The naphtha derived from the liquefaction of a bituminous Illinois #6 and a subbituminous Black Thunder coal were obtained from the Wilsonville, Alabama Advanced Integrated Two Stage Liquefaction Plant. The Illinois #6 coal-derived naphtha was obtained during Run 261 and the Black Thunder coal-derived naphtha was obtained during Run 260, Oct. 11, 1990.

The elemental analyses of the naphthas are shown in Table 2. Carbon and hydrogen analyses were performed using a Leco CHN analyzer. Oxygen analyses were obtained using the Fast Neutron Activation Analysis (FNAA) method and were performed by the University of Kentucky Radioanalytical Service. Trace levels of nitrogen was obtained using a Xertex DN-10 total nitrogen analyzer equipped with a chemiluminescence detector.

RESULTS

Heteroatom removal was obtained for temperatures from 200 to 400°C. The temperature was varied while holding constant the total pressure (600 psig), weight hourly space velocity (WHSV = 1), and hydrogen to naphtha g-mole ratio (2.6). The catalyst activities for HDN, HDO and HDS reactions was compared and the activation energies of these three reactions were determined for different catalysts.

Hydrotreatment of Black Thunder Naphtha Using Commercial Catalysts

The nitrogen and sulfur content of products and the % HDN, %HDO and % HDS are shown in Table 3.

Significant levels of nitrogen and sulfur can be removed using these three commercial catalysts; however, for the highest reaction temperature (400°C) in this

test, approximately 42 ppm of nitrogen was still present in the Ill. #6 product using Ni-W catalyst.

The sulfur content were reduced to approximately 20 ppm at 300°C and to 2 ppm at 400°C using commercial catalysts.

The maximum removal of oxygen is approximately 90% by using Co-Mo catalyst at 400°C.

In Figures 1-3, the removal of nitrogen, sulfur and oxygen, respectively, is given at different temperatures. For HDN of Black Thunder naphtha, Figure 1 shows that Ni-W-alumina is more active than Co-Mo-alumina. However the data in Figure 2 show that Co-Mo-alumina is the more active catalyst for HDS reaction. For HDO, the order of catalyst activity was similar to that for HDN. The catalyst activity for the HDN, HDO and HDS reactions can be ordered for the Black Thunder naphtha as follows:

HDN, Ni-W/ Al_2O_3 > Co-Mo/ Al_2O_3 ;

HDS, Co-Mo/ Al_2O_3 > Ni-W/ Al_2O_3 ;

HDO, Co-Mo/ Al_2O_3 $\approx$ Ni-W/ Al_2O_3 .

A comparison of the removal of nitrogen, oxygen and sulfur heteroatoms from Black Thunder naphtha is shown in Figures 4. Sulfur clearly is easier to remove than nitrogen and oxygen. Figure 4 also shows that oxygen is somewhat easier to remove than nitrogen for Black Thunder naphtha.

Hydrotreatment of Ill. #6 Naphtha Using 1st Row Unsupported Transition Metal

Sulfides

Table 4 shows the conditions and results for the preparation of the transition metal sulfides. We were able to obtain transition sulfides with intermediate to high surface areas.

Heteroatom removal was obtained for the temperature range of 350 and 400°C. The temperature was varied while holding constant the total pressure (600 psig), weight hourly space velocity (WHSV = 1), and hydrogen/hydrocarbon ratio. The nitrogen and sulfur content of products and the % HDN and % HDS are shown in Table 5. None of the catalysts exhibited big activity for the removal of nitrogen and sulfur.

For the HDN reaction, the removal of nitrogen is approximately at the same level for all of the catalysts, i.e. 40 % (Figure 5). Increasing the temperature from 350°C to 400°C did not change the conversion for HDN significantly. The results showed in Figure 5 are based on the 3 grams of metal sulfide that was loaded into the reactor. Since the wt % of metal in the metal sulfide catalyst varies, a normalized % HDN based on the same amount of metal is shown in Figure 6. In this case, the maxima HDN activity normalized to the same amount of metal is attained by chromium sulfide and the minimum HDN activity is attained by cobalt sulfide. Chianelli et al also reported that for the 1st row transition metal sulfides, chromium sulfide displays the highest activity per gram of HDS of dibenzothiophene. However, the lowest activity they obtained was for manganese sulfide. When the HDS is normalized to surface area (Figure 7), a significant difference is noted in the curves. The maximum HDN

activities are attained by manganese sulfide and nickel sulfide. The manganese sulfide and nickel sulfide have, however the lowest surface areas (Table 4).

Chianelli et al showed that the surface area normalization results in maximum HDS of dibenzothiophene for MnS and Ni₃S₂.

For the HDS reaction, the maximum activity is attained by manganese sulfide (Figure 8). Increasing the temperature from 350°C to 400°C results an increase of approximately 15 % of the sulfur removal. A comparison of % HDN vs % HDS shows that removal varies for a nearly constant nitrogen level of 40% (Figure 9). A normalized % HDS based on the same amount of metal is shown in Figure 10. In this case, there is only a small difference in the HDS. The maxima HDS activity, normalized to the same amount of metal, is still attained by manganese sulfide and a minimum HDS activity is attained by nickel sulfide. When normalized to surface area (Figure 11), a significant changes occur in the curves. Two maximum HDS activity are attained by manganese sulfide and nickel sulfide as was seen for the HDN reaction. Again, this is due to manganese sulfide and nickel sulfide having a relative low surface area compared to the other catalysts (Table 4), and not due to these two having a very high HDS and HDN activity.

REFERENCES

1. T. A. Pecoraro and R. R. Chianelli, *J. Catal.*, **67**, 430 (1981).
2. S. J. Tauster, T. A. Pecoraro, and R. R. Chianelli, *J. Catal.*, **62** (2), 515 (1980).

Table 1					
Analysis of Catalysis					
Co-Mo-Alumina		Ni-Mo-Alumina		Ni-W-Alumina	
Co	2.7%	Ni	3.1%	Ni	4.8%
Mo	11.1%	Mo	13.3%	W	16.0%
Sg = 288 m ² /g		Sg = 138 m ² /g		Sg = 111 m ² /g	
Sg = BET Surface Area					

Table 2		
Elemental Analysis of Naphtha		
	Illinois #6	Black Thunder
C	85.57%	85.23%
H	13.24%	12.23%
N	1662 ppm	1464 ppm
S	1100 ppm	382 ppm
O	1.26%	180%

Table 3

Nitrogen, Sulfur and Oxygen Content of Products from the
Hydrotreatment of Ill. #6 and Black Thunder Naphtha

Test	Temp., C	N Wt. ppm	S Wt. ppm	O Wt. %	N % HDN	S % HDS	O % HDO	Feed	Catalyst
1	220	1101	202	1.1	24.8	47.2	38.3	B.T.	Co-Mo
2	250	918	133	1.0	37.3	65.1	45.6	B.T.	Co-Mo
3	300	704	21	0.7	51.9	94.5	60.0	B.T.	Co-Mo
4	350	384	5	0.2	73.8	98.7	87.8	B.T.	Co-Mo
5	400	94	2	---	93.6	99.5	---	B.T.	Co-Mo
6	220	1135	221	1.2	22.5	42.1	36.1	B.T.	Ni-W
7	250	886	172	1.0	39.5	55.1	46.7	B.T.	Ni-W
8	300	647	42	0.8	55.8	89.1	58.3	B.T.	Ni-W
9	350	184	9	0.3	87.4	97.6	86.1	B.T.	Ni-W
10	400	42	3	---	97.1	99.2	---	B.T.	Ni-W

Table 4

Row 1 Transition Sulfide Preparation Conditions and Results

	Ti	V	Cr	Mn	Fe	Co	Ni
Metal	20g	20g	25g	25g	25g	30g	25g
Chloride	TiCl ₄	VCl ₄	CrCl ₃	MnCl ₃	FeCl ₃	CoCl ₂	NiCl ₂
Li ₂ S	9.70g	9.53g	10.88g	10.68g	10.83g	5.79g	8.86
EA, mL	None	None	None	800	800	800	800
THF, mL	800	800	800	None	None	None	None
S _g , m ² /g	4.4	25.82	13.02	1.7	10.18	9.34	1.99

EA = Ethyl Acetate

THF = Tetrahydrofuran

S_g = Surface Area

Table 5

Nitrogen and Sulfur Content of Products
from the Hydrotreatment of Ill. #6 Naphtha

Temp. C	Pressure PSIG	Catalyst	Nitrogen Wt. ppm	Sulfur Wt. ppm	Nitrogen % HDN	Sulfur % HDS
350	660	VSx	1030	370	36.6	52.8
350	660	CrSx	1058	465	36.4	40.7
350	660	MnSx	1034	105	37.8	86.6
350	660	FeSx	1049	393	36.9	49.9
350	660	CoSx	1113	301	33.1	61.6
350	660	NiSx	977	446	39.8	43.1
400	660	VSx	958	223	41	71.6
400	660	CrSx	995	385	38.7	50.9
400	660	MnSx	998	87	40	88.9
400	660	FeSx	1047	288	37	63.3
400	660	CoSx	1103	220	33.7	71.9
400	660	NiSx	970	376	40.3	52

Figure 1.

Figure 2.

Figure 3.

Figure 4.

HDN of III. #6 Naphtha

Figure 6.

Figure 7.

Figure 8.

Figure 9.

Figure 10.

Figure 11.

END

DATE
FILMED
5/12/93