DOE/ER/45181--T1

DE93 010530

A Final Report
on Grant No. DE-FG05-85ER45181

MICROSTRUCTURAL EFFECTS ON THE FATIGUE BEHAVIOR
OF Fe-C-X ALLOYS

Submitted to:
Susan G. Hiser
Contracting Officer
Environmental Acquisitions Branch
Procurement and Contracts Division
USDOE, P.O. Box 2001
Oak Ridge, TN 37831-8758

Submitted by G.J. Shiflet
Professor

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

April, 1991

MASTER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

js

TABLE OF CONTENTS

I. Statement of the Problem.....	1
II. Summary of the Most Important Results.....	1
A. Reversal of Phase Continuity.....	1
B. Effects of Morphology and Distribution of Mo ₂ C Carbides on Fatigue in Fe-C-Mo Alloys.....	2
C. Finite Element Modeling	2
D. Final Comments.....	3
III. List of Publications and Technical Reports Published.....	3
IV. List of Personnel.....	4
V. Degrees Earned and Theses Titles.....	4
VI. Appendices.....	5

I. STATEMENT OF THE PROBLEM

This research project was to characterize the microstructure and fatigue properties in dual phase steels. Our primary concern was the effect of strong carbide forming elements and the concomitant formation of carbides on these properties. The morphologies of carbides examined included fibers, interphase boundary needles and randomly dispersed matrix carbides. Microstructures were then modeled using a finite element routine to examine whether the experimental results could be further understood.

II. SUMMARY OF THE MOST IMPORTANT RESULTS

Brief descriptions of important findings are given below; for a more thorough discussion, reprints are attached in Appendix A. In 'A' the macroscopic effects of reversing the continuous phase from ferrite to martensite was examined. Section 'B' looks at the role of carbide distribution and morphology precipitated within ferrite during thermal cycling; and finally in section 'C' we employ finite element modeling to assist in understanding our experimental results.

A. Reversal of Phase Continuity

The effect of phase continuity on the low cycle fatigue crack growth behavior of a Fe-C-Mn dual-phase steel, Fe-0.21C-0.96Mn, was investigated by obtaining two microstructures. One consisted of continuous ferrite and the other continuous martensite. Although there was no difference in the low cycle fatigue lives between the two microstructures, the continuous martensite structure exhibited an extremely high fatigue threshold value of 20 MPa m^{1/2}, compared to 16 MPa m^{1/2} for the continuous ferrite microstructure. A major effect of phase continuity has also been found in the crack closure levels during fatigue crack propagation studied over three decades of crack growth rates. The continuous martensite microstructure exhibited much higher closure levels due to the martensite constraining the plastic deformation in the ferrite and bearing a larger portion of the applied cyclic load. The effect is similar to the extrinsic toughening phenomenon cited in the literature. After accounting for the closure levels the intrinsic or effective fatigue crack growth levels are similar from the two microstructures. These intrinsic thresholds are predicted by employing experimentally obtained low cycle fatigue parameters and the ferrite grain size.

B. Effects of Morphology and Distribution of Mo_2C Carbides on Fatigue in Fe-C-Mo Alloys

This work documents the primary results of carbide morphology on fatigue properties in this class of steels. Dual-phase microstructures consisting of ferrite with carbides (Mo_2C) surrounding equiaxed martensite packets were developed in low alloys, Fe-0.2C-4Mo and Fe-0.2C-2Mo. These alloys were chosen because of the presence of two distinct carbide morphologies: (1) a needle shaped interphase carbide structure, and (2) a fibrous carbide structure. Isothermal transformations were used to control the carbide morphology and distribution in the ferritic regions of the dual-phase macrostructures. In the present research the effects of changes in carbide structure on low cycle fatigue and fatigue crack growth behavior were studied. Crack initiation was observed at prior austenite grain boundaries in the fibrous microstructure, and along intrusion/extrusion defects in the interphase needle microstructure for LCF tests. TEM studies revealed a carbide free region at prior austenite grain boundaries where initiation occurs for the fibrous case. The cyclic stress/strain response of the ferrite portions of the microstructure is determined by the ability of the carbides to homogenize the strain found there. This affects the stress/strain distribution in the composite ferrite-martensite microstructures by changing the hardness ratio of the two phases and subsequently alters the fatigue crack growth behavior and the macroscopic cyclic stress/strain response. Strain localization was also found to affect the roughness induced closure found for fatigue crack growth tests for low R tests ($R=0.1$).

C. Finite Element Modeling

The work in part 'C' was followed up by examining the strain distribution obtained from monotonic finite element methods(FEM) calculations to model the low-cycle fatigue behavior of the Fe-C-Mo dual-phase steels. The microstructures considered have a continuous ferrite matrix (with Mo_2C precipitates) surrounding martensite packets. Two microstructural parameters were controlled: (1) the volume fraction of martensite and (2) the strength of the ferrite matrix. The FEM approximations show that highly strained regions dominate LCF lifetimes. The experimentally observed reductions in plastic strain life from increasing martensite volume fractions are described using M_e , the strain magnification factor, which is obtained from the FEM analyses. Strengthening the ferrite matrix or reducing the volume fraction of martensite reduces M_e . The cyclic softening observed is qualitatively correlated with FEM predictions of increasing plastic strain in the martensite as the ferrite strength increases. The overall cyclic hardening-softening behavior results from the combination of ferritic hardening combined with martensite softening.

The FEM approximations for the plastic strain distribution showed that highly strained regions control LCF lifetimes and that increased plastic strains can be described using M_e , the strain magnification factor, for the strain ranges considered. We also found that the hardening-softening behavior is a consequence of ferrite hardening combined with martensite softening. A stronger ferrite matrix imposes more strain on the martensite, and more softening is observed. Predictions of martensite strain by the FEM model agree qualitatively with this observation. Finally the finite element models were extended to consider microstructural influences on LCF. The good agreement and insight the models provided should prove useful in examining many types of two-phase systems.

D. Final Comments

Once again the versatility of steels in manipulation of microstructure and properties is demonstrated. As stated in the original proposal objectives, we were able to show that microstructures can be dramatically controlled in Fe-C-X alloys. At the macrostructure level the continuous ferrite phase which normally occurs in continuously cooled steels, surrounding martensite, can be totally reversed. Structures an order of magnitude finer can also be altered. The carbide:ferrite association can be controlled so that the carbides are fibrous, interphase boundary (rows), or randomly distributed within the matrix. As microstructure plays a dominant role in the fatigue crack propagation of heat treatable alloys, these changes affect the low cycle fatigue and the fatigue crack growth behavior.

Finally this work was the first development of a Finite Element Model approximation for plastic strain distribution for low cycle fatigue. The model (although of limited sophistication, due in part to computer limitations) did provide true insight in examining two-phase systems. The PI feels that the combination of a small group of researches with expertise in ferrous phase transformations, mechanical properties and computer modeling would provide much useful information in ferrous metallurgy. If any system needs to be examined in this fashion it is steels, because of their rich and extensive combination of phases and properties.

III. LIST OF PUBLICATIONS AND TECHNICAL REPORTS PUBLISHED

The Effect of Phase Continuity on the Fatigue and Crack Closure Behavior of a Dual-Phase Steel, *Metallurgical Transactions A*, Vol. 18A, July 1987, pp. 1291-1298, (R.M. Ramage, K.V. Jata, G.J. Shiflet, and E.A. Starke, Jr.).

The Influence of Mo_2C Morphology and Distribution on the Fatigue Crack Initiation and Propagation Behavior of Fe-C-Mo Dual-Phase Steels, *Metallurgical Transactions A*, Vol. 19A, April 1988, pp. 973-986, (J.H. Beatty, G.J. Shiflet and K.V. Jata).

Orowan Strengthening by Mo_2C Fibers and Needle Interphase Precipitates in Fe-C-Mo Dual-Phase Steels, *Metallurgical Transactions A*, Vol. 19A, June 1988, pp. 1617-1620, (J.H. Beatty and G.J. Shiflet).

The Effect of Precipitate Distribution and Morphology on the Uniaxial Deformation and Plastic Behavior in Fe-C-X Alloys, *Proceedings of and International Symposium on the Plasticity and Resistance to Metal Deformation*, Herciq-Novti, 1989, pp. 9-30 (R.M. Ramage and G.J. Shiflet).

Bainite Viewed Three Ways, *Metallurgical Transactions A*, Vol. 21A, 1990, pp. 1343-1380, (H.I. Aaronson, W.T. Reynolds, G.J. Shiflet and G. Spanos).

Strain Distribution Effects on the Low-Cycle Fatigue Behavior of Fe-C-Mo Steels, *Metallurgical Transactions A*, Vol. 22A, 1991, pp. 675-683.

IV. LIST OF PERSONNEL

G.J. Shiflet, Principal Investigator
 E.A. Starke, Principal Investigator, 1983-1985.
 R.M. Ramage, Graduate Student (MS and Ph.D)
 J. H. Beatty, Graduate Student (Ph.D)

V. Degrees Earned and Theses Titles

Master of Science:

R.M. Ramage, "The Effect of Phase Continuity on the Fatigue Behavior of a Dual-Phase Steel" January, 1986, University of Virginia.

Doctor of Philosophy:

J.H. Beatty, "The Effects of Mo_2C Morphology and Strain Distribution on the Fatigue Properties of Fe-C-Mo Dual-Phase Steels, January, 1988, University of Virginia, (currently John is a Captain in the US Army, Watertown, MA).

R.M. Ramage, "The Effect of Carbide Morphology and Distribution on the Uniaxial Deformation of Fe-C-X Alloys, May, 1989, University of Virginia, (currently Robert is a research scientist at General Motors Research Laboratories, Warren, MI).

VI. APPENDICES

The following are reprints of research papers published under the grant.

*Preprints & reprints
removed and cycled
separately.*

END

**DATE
FILMED**

4 / 20 / 93