DOE/ER/1435-1

REPORT

Received OSTI

DEC 11 1992

AN INVESTIGATION OF
THE EFFECTS OF
HISTORY DEPENDENT
DAMAGE IN TIME
DEPENDENT FRACTURE
MECHANICS, VARIABLE
LOAD CONDITIONS

To

U. S. DEPARTMENT OF ENERGY

NOVEMBER 12, 1992

Battelle

Putting Technology To Work

**PROGRESS REPORT
Phase II**

on

**AN INVESTIGATION OF THE EFFECTS OF HISTORY DEPENDENT
DAMAGE IN TIME DEPENDENT FRACTURE MECHANICS,
VARIABLE LOAD CONDITIONS**

to

**Department of Energy
Office of Basic Energy Sciences**

**November 12, 1992
(Continuation of Grant DE-FG02-90ER14135)**

by

F. W. Brust, P. Krishnaswamy, and B. S. Majumdar

**BATTELLE
505 King Avenue
Columbus, Ohio 43201-2693**

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

MASTER

This report is a work prepared for the United States Government by Battelle. In no event shall either the United States Government or Battelle have any responsibility or liability for any consequences of any use, misuse, inability to use, or reliance upon the information contained herein, nor does either warrant or otherwise represent in any way the accuracy, adequacy, efficacy, or applicability of the contents hereof.

TABLE OF CONTENTS

		<u>Page</u>
1.0	OVERVIEW	1
2.0	OBJECTIVES	1
3.0	WORK ACCOMPLISHED - PHASE II	2
	Phase II - Experiments	3
	Phase II - Analysis	4
4.0	ANTICIPATED WORK - PHASE III	12
	Task No. 1 - Variable Load Creep Experiments	12
	Task No. 2 - Analysis	13
5.0	PRESENTATIONS AND PUBLICATIONS	15
	REFERENCES	16
	APPENDICES A, B, C, D, and E <i>reprints + Preprints removed</i>	

List of Tables

Table 1.	Phase II Tests	3
Table 2.	Phase III Test Matrix	12

List of Figures

Figure 1.	Load Time History for a 316SS Test (CT14)	5
Figure 2.	Overall Displacement - Time History for a 316SS Test (CT14)	6
Figure 3.	Blowup of Displacement Time History for One of the 9 Cr-Mo During a Time of 325 to 365 Hours	7
Figure 4.	Illustration Of Behavior Of Cracked Compact Tension Specimen Before and After Loading With Compressive Stress Zones Corresponding To Unload At $t = 73.8$ Hours	8
Figure 5.	Predicted And Experimental Displacements (a) Through 192 Hours, (b) Blowup of the Last Two Load Cycles	10
Figure 6.	Integral Parameters Versus Time (a) All Parameters, (b) T^* -integral	11
Figure 7.	Schematic Of Research Approach	14

PROGRESS REPORT

on

AN INVESTIGATION OF THE EFFECTS OF HISTORY DEPENDENT DAMAGE IN TIME DEPENDENT FRACTURE MECHANICS, PHASE II, VARIABLE LOAD CONDITIONS

by

F. W. Brust, P. Krishnaswamy, and B. S. Majumdar

**BATTELLE
Columbus, Ohio**

Grant No. DE-FG02-90ER14135

1.0 OVERVIEW

The demands for structural systems to perform reliably under severe temperatures and load conditions continue to increase. These demands will continue with the development of advanced power generation methods and for future aerospace applications. An understanding of the high-temperature creep crack growth process, which is a frequent failure mechanism in these structures, is important. Many investigations which have appeared to date are concerned with creep crack growth which occurs under a constant load and temperature. However, most structural components experience complicated load histories. The history of degradation and damage which accumulates at the crack tip is greatly influenced by these transients. This program aims at gaining an understanding of the history dependent high temperature failure process through a combined experimental and analytical effort. The development of a useful predictive methodology for characterizing this process is being undertaken.

2.0 OBJECTIVES

The objective of this research is to characterize the effects of load and temperature history on time dependent crack growth and fracture. In particular, the purpose is to examine and

develop the predictive capability of certain analytic techniques through direct comparison to carefully performed experiments.

This project is broken into three phases, each phase to examine a different aspect of the high-temperature crack growth problem, and each to last one year. Phase I, Sustained Load Creep, examined the predictive ability of the proposed parameters under the more commonly studied constant load situation. Phase II, Variable Load Creep, which is being reported here, will determine which of the many established or proposed approaches most accurately predicts creep crack growth at the next level of history dependence: variable load history. Phase III is to be performed next year. Along with a continued consideration of the load history dependent effects of creep, Phase III will also consider temperature gradient effects on this damage growth process. This is the most general category of history dependence.

3.0 WORK ACCOMPLISHED - PHASE II

During Phase I, Sustained Load Creep, examined the creep behavior of constant load tests. In this phase, the Murakami and Ohno history dependent creep constitutive law [1, 2] history dependent creep was implemented into a finite element code. In addition, a number of fracture features were implemented including crack growth capability and an integral parameter and damage law (Reference [6]) post processor. Creep crack growth analyses were performed which examined the crack growth behavior of constant load tests on a 1 Cr-Mo rotor steel. Both Murakami-Ohno, Norton, and strain hardening creep laws were used in the analyses and conventional creep fracture parameters (e.g. C^* -integral) and the new integral parameters were examined. It was determined that conventional fracture theories (see References [3, 4]) under constant load conditions are acceptable since the zones of stress reversal for a constant load growing crack experiment are small. This same statement cannot be made for history dependent loading, examined during Phase II.

Considerable progress was made during the Phase II effort, variable load creep. In all, a total of nine experiments were performed, all of which are complete to date. Analyses of the experiments have been performed and continue. The completed experimental and analysis work is presented separately in the next two sections.

Phase II - Experiments

We have chosen two materials to examine in this program: 316 Stainless Steel and a 9 Cr-Mo Steel. Both of these materials will continue to be used in present and future high-temperature applications. In addition, these materials have been carefully characterized by Oak Ridge National Laboratory (ORNL) and ORNL has provided us with material. In all, we have tested nine compact tension specimens, each of which is subjected to a carefully chosen different load-time history. To date, all tests are complete.

Table 1 lists the completed Phase II tests. The original plan (see last year's Continuation Proposal) was to perform a total of three tests on one material. However, through cooperation with Dr. R. Swinderman of ORNL, who provided material, it became possible to perform more tests. All specimens were machined and fatigue precracked prior to testing. During the testing phase, one 316SS specimen at constant load at 593 degrees C experienced failure of one of the electric potential leads, which resulted in incomplete crack growth data. From that point on, two leads were used for other tests. In addition, one variable load 9 Cr-Mo test experienced failure in one of the threaded loading fixtures, also requiring a re-test.

The constant load tests of Table 1 were performed in a creep machine. The variable tests were performed as follows. The experimental technique is automated, with the load history programmed in for each test. The load time history was programmed on an Instron Servohydraulic machine, which required development of a novel spring-loaded extensometer system. After the third test, further tests had crack length monitored using two sets of staggered EP leads, so that if a lead failed, the test still resulted in a complete data set. Data acquisition was triggered by the load changes. This resulted in rapid data acquisition just after load changes and slower acquisition rates as the load is held, which is desired.

Table 1. Phase II Tests

MATERIAL	TEMPERATURE	TYPE OF TEST
316SS	650 Degrees C	1 Variable Load, 1 Constant Load
316SS	593 Degrees C	1 Variable Load, 2 Constant Loads
9Cr-Mo	538 Degrees C	3 Variable Loads, 1 Constant Load

An example load spectrum of one of the 316SS tests is shown in Figure 1. An initial hold period of 36 hours was made to develop an initial creep zone in the specimen. The unload hold times and subsequent reload times were continually decreased until about 90 hours, after which four-hour hold periods and one-hour unload periods were maintained. This assured a truly variable load history. A plot of the displacement versus time history is shown in Figure 2.

The load spectrum for one of the 9 Cr-Mo history dependent tests is similar to Figure 1, except the applied load was 7,000 pounds and the test lasted 400 hours. A corresponding plot of the displacement versus time history of the test between the hours of 325 and 365 are shown in Figure 3.

Several conclusions can be drawn from the experiments:

- During the unload-hold period, load point displacement recovery occurs. This is due to the compressive stresses which develop at the crack tip during unload.
- After reload, the displacement rates increase compared to the rates during the previous load period. This is especially true during later times.
- Load history effects significantly decrease life compared to constant load tests. For instance, a constant load test for the 9 Cr-Mo test described above (identical load of 7,000 pounds) lasted about 1.5 times longer.

Further details are presented in the references cited in Section 5 and provided in the Appendices.

Phase II - Analysis

With the experiments for the Phase II effort now complete, analytical modeling of the experiments is being performed. There is a two-fold purpose to the modeling efforts: (i) Phenomena observed during the experiments can be more fully understood with an appropriate model, and (ii) the development and verification of a fracture mechanics theory which attempts to explain and predict the history dependent creep crack growth process is possible. Such a combined analytical/experimental approach is valuable because theories can be directly validated. Several examples illustrating the analysis being performed follow.

Consider the analysis of a 1 Cr-Mo steel loaded to 7.55 Kn for 84 hours. At times of 49, 61.7, and 73.8 hours, the specimen is unloaded for one hour and held, then reloaded. the crack growth behavior is forced to be identical to that for a constant load test. Figure 4 illustrates the

Figure 1. Load Time History for a 316SS Test (CT14)

Figure 2. Overall Displacement - Time History for a 316SS Test (CT14)

Overall Behavior

Figure 3. Blowup of Displacement Time History for One of the 9 Cr-Mo During a Time of 325 to 365 Hours

Figure 4. Illustration Of Behavior Of Cracked Compact Tension Specimen Before and After Loading With Compressive Stress Zones Corresponding To Unload At $t = 73.8$ Hours

behavior immediately after unloading. Note the large zones of compressive stresses in the vicinity of the crack tip. Upon reload, these stresses again reverse sign. This stress reversal is what leads to increased damage at a crack tip during history dependent loading since creep strain rates increase greatly during stress reversals (see References [7] and [8] for further details of this behavior). The displacement recovery response (typified in Figure 3) during reloading and the behavior of the integral parameters during unloads is discussed in detail in References [9] and [10]. After reloading, the values of the T^* -integral and Watanabe integrals are higher than the corresponding value before unloading and also higher than the values if no unloads had occurred. This is expected since the unloads are expected to damage the crack tip region and result in more rapid crack growth as illustrated in Figure 3. A valid crack tip parameter should behave in this way.

Finally, we briefly show analysis results of another one of the 9 Cr-Mo tests (Table 1). This test, which is described in References [9] and [11], consisted of a load spectrum of load to 23.7 Kn for 24 hours and unload for five minutes, and corresponding reload. The test took about 40 days to complete. We show a few results during the first 192 hours of the test, before crack growth ensued. The finite element mesh was focused and extremely fine near the crack tip. The analysis was computationally intensive. More details of this analysis are found in Reference [11], and more details of the complete test including crack growth will appear in Reference [12] to be submitted at the end of Phase II.

The predicted and experimental displacements are shown in Figure 5. Also shown are the constant load results. The first unload in this specimen occurred very early on (.05 hours). It is clearly seen that constant load predictions greatly underpredict the displacements which accumulate with time. The comparison between the predicted and experimental displacements is considered quite good especially since, in the experiment, small amounts of crack growth occur which were not included in this analysis. Figure 5b shows a blowup between the times of 144 to 200 hours. The displacement recovery upon unload, the corresponding reduced displacement (compared to before unload) after reloading, and the increased displacement rates after the cycle are evident, are seen experimentally (Figures 2, 3). History dependent values of five integral parameters are shown in Figure 6. Figure 6a shows that the T^* -integral and Watanabe (J_w) integrals increase markedly after each unload cycle. In fact, comparing the T^* -integral for the load history case and constant load cases (Figure 6b) shows that load history greatly increases crack tip severity. Based on these results, T^* and J_w appear to be the most promising parameters. Further details and discussion are provided in Reference [11]. The results of all other tests in Table 1 will appear in References [12, 13].

(a)

(b)

**Figure 5. Predicted And Experimental Displacements
(a) Through 192 Hours, (b) Blowup of the
Last Two Load Cycles**

Figure 6. Integral Parameters Versus Time
(a) All Parameters, (b) T^* -integral

Further details of all results to date are provided in the appendices. Please see Section 5 and the corresponding appendices.

4.0 ANTICIPATED WORK - PHASE III

Phase II of this project is scheduled for completion by December, 1992. It is anticipated that all computation involving the experiments listed in Table 1 will be completed by then. In addition, two additional papers detailing the combined experiments and analysis will be completed (References [12,13]).

No significant deviation from the originally proposed work is expected for Phase III. Upon completion of Phase II, Phase III will begin and consists of two tasks. Task 1 involves variable load history tests, which include the effects of thermal gradients, while Task 2 involves using the integral parameters to predict crack growth versus time-to-failure response of experiments. We note that, to our knowledge, no one has yet attempted creep crack growth experiments or analyses in the presence of thermal gradients.

Task No. 1 - Variable Load Creep Experiments

Table 1 describes the variable load history tests performed during the Phase II program. Phase III will consider only 9 Cr-Mo steel because temperature-dependent material property is available (Reference [5]) for 9 Cr-Mo steel and material is readily available from ORNL. Three tests will be performed, which are listed in Table 2.

Table 2. Phase III Test Matrix

TEST NUMBER	TEMPERATURES	COMMENTS
1	538 Degrees C	Variable Load, No Thermal Gradients
2*	538 Degrees C	Constant Load**, With Thermal Gradients
3*	538 Degrees C	Variable Load (Same as Test No. 1), With Thermal Gradients

*These are the thermal gradient tests.

**The constant load will be identical to the maximum load of Tests No. 1 and 3.

Test No. 1 will be a variable load history test without thermal gradients. This will serve two purposes: (i) further increase the data base of Table 1 for 9 Cr-Mo steel, (ii) reduce test time, since the variable load-time test will be chosen so as to reduce the test time to about 4 to 6 days. All the tests for the 9 Cr Mo steel in Table 1 required more than two weeks, which is undesirable. This will make Test No. 2 and Test No. 3 more convenient to perform. Test No. 2 is a constant load test, with the maximum load identical to that in Test No. 1, but with thermal gradients. Test No. 3 will have the same load sequence as Test No. 1, but with thermal gradients. The test matrix of Table 2 ensures that the test results can be compared directly, and will augment, the Phase II tests of Table 1.

The thermal gradient will be chosen to simulate gradients actually experienced by power plant components. Thermal gradients will be created from the front-to-back faces of the test specimen by heating the front face and cooling the back face. Heat input will be developed by high-frequency induction using units with enough power to penetrate the specimen thickness through coils wound to achieve this purpose. Heat will be withdrawn by a heat sink along the back face. This heat sink will involve a hollow rectangular tube made of a low stiffness, high conductivity material intimately joined to the back face. Numerical heat transfer calculations will be done to size this tube and determine the flow rate and temperature of the heat transfer media needed to achieve the desired test conditions. "Steady-state" thermal fields will be established before testing begins. Testing will be done in a closed-loop system with provision to protect the load cell and other transducers from adverse heating effects. The temperature field will be maintained/monitored using a series of thermocouples. Optical pyrometry will be used to verify heat input is uniform along the front face. Thermal transients will not be included here as these effects will complicate matters. Thermal transients can be included in efforts beyond Phase III.

Task No. 2 - Analysis

The integral parameters and damage-based techniques, as identified by the results on the Phase II study and improved as necessary, will be used to predict the crack growth versus time-to-failure response of these experiments. The predicted results will be compared to experimental results as shown in Figure 7.

Task 1: Experiment

Note: Fracture analyses performed using material properties from Task 1.

Task 2: Analyses

Task 3: Results

Figure 7. Schematic Of Research Approach

These analyses will be performed using both the Murakami-Ohno constitutive law and the modification of the Krempl law, as detailed in Reference [5]. As mentioned above, temperature-dependent material properties are available for 9 Cr-Mo steel. This effort will require some modifications to the finite element code to be able to model thermal gradients and thermal inelasticity.

Finally, we will also begin to consider constraint effects in creep crack growth by reconsidering the results of Tables 1 and 2. Parks [14] has been examining such effects for elastic-plastic conditions. Similar studies of creep crack growth have not been considered.

5.0 PRESENTATIONS AND PUBLICATIONS

Symposium presentations based on the work performed during the Phase II effort of this program in 1992 were made at the Tenth Symposium on Energy Engineering Sciences in Chicago in May; at the American Society of Mechanical Engineering Pressure Vessels and Piping (ASME-PVP) Conference in New Orleans in June; and at the ASME Winter Annual Meeting in Anaheim in November.

Publications are listed as follows (in chronological order of submission).

1. Krishnaswamy, P., Brust, F. W., and Ghadiali, N. D., "A Finite Element Algorithm To Study Creep Crack Growth Based On The Creep Hardening Surface", to appear in Int. Journal for Num. Meth. in Engineering, 1993. (See Appendix A.)
2. Brust, F. W., Krishnaswamy, P., and Majumdar, B. S., "Consideration of History Dependent Damage in Creep Crack Growth", Proceedings of the Tenth Symposium on Energy Engineering Sciences, Synergism of Analysis, Modeling, and Experiment, May 11-13, 1992, Argonne, Illinois. (See Appendix B.)
3. Krishnaswamy, P., Brust, F. W., and Ghadiali, N. D., "Finite Element Analysis of History Dependent Damage in Time Dependent Fracture Mechanics", in Fatigue, Fracture, and Risk, 1991 edition, by Bamford, W. H., et al., ASME-PVP Volume 241, 1992. Also, this paper was invited to be published in the ASME Journal of Pressure Vessel Technology and is under additional review. (See Appendix C.)
4. Brust, F. W., Krishnaswamy, P., "A Computational Study of the Time Dependent Crack Growth Process", in ASME Applied Mechanics Division Volume (AMD), edited by A. Nagar, et al., 1992. (See Appendix D.)
5. Brust, F. W. and Majumdar, B. S., "Load History Effects on Creep Crack Growth", submitted to Engineering Fracture Mechanics, September, 1992. (See Appendix E.)

6. Brust, F. W. and Majumdar, B. S., "A General Theory of High Temperature Damage and Crack Growth Under Variable Load Histories", under preparation, to be submitted to the International Journal of Solids and Structure, 1992 (at end of Phase II).
7. Brust, F. W., Majumdar, B. S., and Krishnaswamy, P., "Analytical and Experimental Studies of History Dependent Creep Fracture", under preparation, to be submitted to the International Journal of Fracture, 1992 (at the end of Phase II).

Symposia presentations already planned in 1993 are to be made at the International Conference on Fracture (ICF8), Kiev, USSR, June, 1993, and also at the ASME-PVP Conference and ASME Winter Annual Meeting in 1993. Also, I may present results at the ASTM National Fracture Symposium in 1993. Finally, it is anticipated that two journal publications will result from the Phase III work in 1993.

REFERENCES

- [1] Murakami, S. and Ohno, N., "A Constitutive Equation of Creep Based on the Concept of a Creep Hardening Surface", Int. J. of Solids and Structures, Vol. 18, No. 7, pp. 597-609, 1982.
- [2] Ohno, N., Murakami, S., and Ueno, T., "A Constitutive Model of Creep Describing Creep Recovery and Material Softening Caused by Stress Reversals", J. Engineering Materials and Technology, Vol. 107, pp. 1-6, 1985.
- [3] Riedel, H., Fracture at High Temperatures, Springer-Verlag, 1987.
- [4] Saxena, A., "Creep Crack Growth In High Temperature Ductile Materials", Engineering Fracture Mechanics, Vol. 40, No. 415, pp. 721-736, 1991.
- [5] Blass, J. J., et al., Oak Ridge National Laboratory (ORNL) Annual Report for the period April 1, 1990 to March 31, 1991, ORNL/9CR/91-1.
- [6] Lemaitre, J. and Chaboche, J. L., "Mechanics of Solids Materials", Cambridge University Press, 1990.
- [7] Krishnaswamy, P., Brust, F. W., and Ghadiali, N. D., "A Finite Element Algorithm To Study Creep Crack Growth Based On The Creep Hardening Surface", to appear in Int. Journal for Num. Meth. in Engineering, 1993.
- [8] Krishnaswamy, P., Brust, F. W., and Ghadiali, N. D., "Finite Element Analysis of History Dependent Damage in Time Dependent Fracture Mechanics", in Fatigue, Fracture, and Risk, 1991 edition, by Bamford, W. H., et al., ASME-PVP Volume 241, 1992.
- [9] Brust, F. W., Krishnaswamy, P., and Majumdar, B. S., "Consideration of History Dependent Damage in Creep Crack Growth", Proceedings of the Tenth Symposium on Energy Engineering Sciences, Synergism of Analysis, Modeling, and Experiment, May 11-13, 1992, Argonne, Illinois.
- [10] Brust, F. W., Krishnaswamy, P., "A Computational Study of the Time Dependent Crack Growth Process", in ASME Applied Mechanics Division Volume (AMD), edited by A. Nagar, et al., 1992.
- [11] Brust, F. W. and Majumdar, B. S., "Load History Effects on Creep Crack Growth", submitted to Engineering Fracture Mechanics, September, 1992.
- [12] Brust, F. W. and Majumdar, B. S., "A General Theory of High Temperature Damage and Crack Growth Under Variable Load Histories", to be submitted to the International Journal of Solids and Structure, 1992.

- [13] Brust, F. W., Majumdar, B. S., and Krishnaswamy, P., "Analytical and Experimental Studies of History Dependent Creep Fracture", to be submitted to the International Journal of Fracture, 1992.
- [14] Parks, D. M., "Advances in Characterization of Elastic-Plastic Crack-Tip Fields", to appear in Topics in Fracture and Fatigue, (McClintock Festschrift), Springer-Verlag, 1992.

END

**DATE
FILMED**

12 / 30 / 92