DOE/ER/45257--T2

DE93 012228

**Mechanisms of Time-Dependent Crack
Growth at Elevated Temperature**

Final Project Report

**Submitted to
Basic Energy Sciences Division
Department of Energy**

**DOE Grant No: DE-FG05-86ER45257
Period Covered: 7/1/86 to 8/31/89**

Submitted by:

Ashok Saxena

Ashok Saxena, Professor

Stuart R. Stoek
Stuart R. Stoek, Associate Professor

Contributors:

J.T. Staley, R.H. Norris, B. Gieseke, A. Guvenilir

**School of Materials Engineering
Georgia Institute of Technology
Atlanta, Georgia 30332-0245**

April 15, 1990

MASTER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

1. INTRODUCTION AND SUMMARY

The prediction of design life of components subjected to elevated temperatures in energy conversion machinery require accurate methods for predicting crack growth behavior in the presence of time-dependent creep strains. Significant progress has been made in extending the linear-elastic and elastic fracture mechanics concepts into the creep regime. Thus, the use of fracture mechanics for predicting the crack growth life of elevated temperature components is a viable approach [1,2]. However, serious deficiencies exist in the understanding of the damage mechanisms that lead to time-dependent crack growth. Specifically, the interactions between creep and fatigue damage mechanisms for slow frequency cyclic loading are not well understood. Therefore, cumulative damage laws for creep-fatigue loading based on physical damage mechanisms are non-existent.

The objective of this three year study was to conduct creep and creep-fatigue crack growth experiments and to characterize the crack tip damage mechanisms in a model material (1% Sb-Cu) which is known to cavitate at the grain boundaries under creep deformation. These data and observations were to be used to develop mechanistic models for predicting crack tip damage and the resultant crack growth rates under complex loading conditions at elevated temperatures. The results of this program were to be integrated into Electric Power Research Institute (EPRI) sponsored studies at Georgia Tech. for characterizing the creep-fatigue crack growth behavior of Cr-Mo-V steels. Various new and established

techniques for detecting crack tip cavitation damage including electron metallography, synchrotron x-ray tomography, digital microradiography and small angle neutron scattering (SANS) were also evaluated. The study led to the following important conclusions.

- In the presence of large scale cavitation damage and crack branching, time rate of creep crack growth (da/dt) does not correlate with C_t or with C^* . On the other hand, when the cavitation damage is constrained, da/dt is uniquely characterized by C_t .
- Area fraction of grain boundary cavitated, A_c , appears to be the single damage parameter for characterizing the extent of cavitation damage ahead of crack tips. The distribution of A_c ahead of the crack tip is a complex function of loading wave form and cycle time.
- The use of C_t -parameter was extended for characterizing the creep-fatigue crack growth behavior. It was shown that C_t is suitable for characterizing crack growth rate in the presence of different types of deformation transients.
- It was observed that in materials which are prone to rapid cavity nucleation, the creep cracks grow faster initially and then reach a steady-state during which their growth rate is uniquely characterized by C_t .
- The percent creep life exhausted was shown to correlate with the average cavity diameter and also with fraction

of grain boundary area occupied by cavities.

- Synchrotron x-ray tomographic microscopy (XTM) was successfully demonstrated for imaging individual cavities in the 1 percent Sb-Cu material.
- The above concepts have been incorporated in methodologies for remaining life prediction of elevated temperature power-plant components. Specifically, $(C_t)_{avg}$ has been used to correlate creep-fatigue crack growth behavior in Cr-Mo and Cr-Mo-V steel and in weldments.

In Section 2 of this report, the important results from the program are presented. Section 3 of the report contains a list of the publications and presentations from the work performed under the grant and the status of the various students funded under this grant.

2. HIGHLIGHTS OF ACCOMPLISHMENTS

The creep and creep-fatigue crack growth experiments were conducted on a copper alloy containing 1 weight-percent antimony. The segregation of antimony to the grain boundaries embrittles the boundaries. Therefore, the room temperature fracture in this material is one hundred percent intergranular revealing the cavitation damage on the grain boundary facets. Thus, this alloy was ideally suited for studying the time-dependent damage accumulation at crack tips subjected to creep and creep-fatigue loading. The model alloy was specially produced at the Oak Ridge

National Laboratory and was supplied to Georgia Tech in the form of an extruded rectangular bar which was 2-3/4 in x 2 in cross-section. The chemical composition and the tensile and creep behavior of the material is summarized in reference [3] attached in the Appendix. The highlights of the various aspects of the work are summarized in the following sections.

2.1 Mechanisms of Creep Crack Growth

The creep crack growth data developed in air as a part of this study clearly showed that, in the presence of large scale cavitation damage ahead of the crack tip and crack branching, da/dt does not correlate with C_t (Fig.1). On the other hand, when the damage in the crack tip region is not extensive (or constrained), da/dt is uniquely characterized by C_t after steady-state damage conditions are reached (Fig. 2).

The extensive quantitative damage analysis of the specimens revealed that continuous nucleation and growth of cavities occurs near the crack tip. The fraction of grain boundary area cavitated, A_c , was found to best represent the state of damage at a point ahead of the crack tip. A steep gradient in the extent of cavitation damage as a function of distance from the crack tip was obtained in all creep crack growth specimens which showed constrained cavitation, Fig. 3. A governing equation for damage evolution was proposed (See Ref.3).

In order to promote constrained cavitation during subsequent creep crack growth testing, all specimens were sidegrooved. Also,

to protect the fracture surface from oxidizing, the subsequent testing was performed in ultra-high-purity nitrogen. Fig. 4 shows the creep crack growth rate behavior as a function of C_t from these tests. Transient crack growth rates characterized by non-unique da/dt versus C_t relationship were observed for a substantial portion of the tests. The crack growth rates were high initially and they decreased with subsequent crack extension. Similar transient crack growth behavior has been observed previously [4] in ductile steels but the one observed here is peculiar in two ways. First, the crack growth rates in the transient regime are higher than those at equivalent C_t values in the steady-state crack growth regime. Second, the duration of the crack growth transients in terms of the crack extension required to achieve steady-state was significantly higher in antimony-copper than observed in ductile steels. The transient crack growth rate behavior was examined in great depth through further testing. It was concluded that the transient behavior occurs due to (1) damage done during precracking prior to creep crack growth testing and (2) damage done during initial loading when the crack tip stresses are the highest. A very detailed discussion of this phenomena is contained in a forthcoming M.S. thesis of Mr. Richard Norris. The completed thesis will be mailed to DOE when available.

2.2 Damage and Life Fraction Correlations in Creep Rupture Specimens

Although studying the creep rupture behavior of antimony-copper was not the main objectives of this study, some rupture

testing was necessary to develop the creep constants for crack growth data analysis. Also, the tested specimens were needed to evaluate the nondestructive damage characterization techniques used in this project.

Large gradients in the volume fraction of cavities V_v were observed as a function of distance from the rupture surface of crept specimens (Fig. 5). Optical microscopy and synchrotron microradiography both showed that lower stresses lead to considerably higher damage levels and to more extensive zones of enhanced damage (e.g. much higher than the uniform damage levels elsewhere in the specimens). Each of the curves in Fig. 6 approaches the same asymptotic value of V_v at large distances from the rupture surface, which suggest that a critical level of damage in creep of Cu-1% Sb must be attained to initiate necking leading to fracture.

Both A_c and $\bar{D}$, the average cavity diameter, were determined as a function of lifetime expended for two applied loads (Fig. 6).

Both quantities are linear functions of expended life, and there appears to be little dependence on applied stress. Apparently, failure by ductile rupture is imminent when about 0.45 of the grain boundaries are covered by cavities, regardless of the stress level. This conclusion is consistent with the observation of V_v values far from the rupture surface.

2.3 Crack Growth Mechanisms During Creep-Fatigue Loading

The mechanism of crack advance in Cu-1% Sb is a function of the crack-tip stresses. Below a critical stress, crack growth occurs by coalescence of creep cavities with the crack front. Above this same critical stress, crack growth occurs by a combination of cavity coalescence and grain boundary peeling. The dendritic growth of the crack front, or peeling process occurs when the normal stresses on the boundaries exceed a critical value, and is thus sensitive to grain orientation with respect to the remotely applied stress.

The process of crack growth by cavity coalescence is controlled by the smaller crack-tip cavitation. The size and density distribution of these cavities are functions of loading waveform and cycle time. Any grain boundary area not previously failed by the growth of the large, remote cavities fails by the coalescence of the smaller voids. The widespread, larger cavities have only a secondary effect on the growth rates.

The average rate of crack growth during hold times in trapezoidal loading waveforms, $(\dot{a})_{avg}$ can be uniquely correlated with the average, measured value of the C_t parameter, $(C_t)_{avg}$ (Fig. 7). The $(\dot{a})_{avg}$ vs. $(C_t)_{avg}$ relationship for hold times of $\frac{1}{2}$ hour and longer is identical to that obtained for creep crack growth conditions. This implies, that for hold times larger than $\frac{1}{2}$ hour, creep-fatigue crack growth rates are correlated uniquely by $(C_t)_{avg}$. The creep-fatigue interaction during elevated temperature crack growth may be the result of a change in crack growth mechanism

during the hold times. In the initial portion of each hold time, peeling may occur, and as the stresses relax, crack extension may revert back to a process by cavity coalescence. Thus, shorter hold times maintain higher average crack-tip stresses and have a higher probability for the peeling mechanism to operate. Since peeling occurs at higher stress levels, it is expected to result in higher crack growth rates, and shorter hold times would be expected to have unexpectedly higher crack growth rates.

2.4 Development and Assessment of Advanced Damage Characterization Techniques

Electron radiography and small angle scattering were examined during the very early stages of this three-year study as possible alternatives to optical and scanning electron metallography for damage assessment. Neither was found to be suitable for this study as discussed in earlier progress reports [5]. On the other hand, industrial computed tomography (CT) and high-resolution variants termed x-ray tomographic microscopy (XTM) were found to be very useful for damage characterization; digital microradiography and synchrotron microradiography were also applied successfully to damage characterization in Cu-1% Sb . These novel techniques and results obtained with them as described below.

2.4.1 Microradiography

Synchrotron microradiographs were recorded at the Stanford Synchrotron Radiation Laboratory (SSRL) using white radiation. The nearly parallel, high flux beam makes synchrotron radiation an

ideal source for contact radiography. Optical densitometry tracings of the microradiographs were recorded along a direction normal to the rupture surface and yielded curves such as that shown in Figure 10. Standards of the appropriate thickness and containing no cavitation damage were not run, however, and absolute magnitudes of damage cannot be easily calculated.

Comparison of the relative optical densities with the relative cavity volume fractions for both 3.5 and 6.0 ksi samples (tested to failure) should show quantitative agreement; this is not observed. We suspect that local film saturation occurs at positions where distinct cavity images are seen. This is being checked with further densitometry. During the next experimental period we will also repeat the synchrotron microradiography. We will use undamaged and damaged samples of the same thickness.

Digital microradiography eliminates the photographic emulsion and directly measures the transmitted intensity with electronic x-ray detectors. High resolution can be obtained by using a multiple detector array with very small elements or by using a pinhole collimator and scanning the sample across the beam. The variation of x-ray absorption around a creep crack in the Cu-Sb material was quantified using the latter approach, Ag K α radiation and a 15 μ m diameter beam. The sample studied was CT5 which was crept at 400C and 1.5 ksi(in.)^{0.5}. The sample was mechanically polished to about 0.3 mm thickness, and this was adequate to transmit nearly 30% of the incident beam in the vicinity of the crack. A square array of points with spacing of 0.5 mm was used to cover a 3 mm x 5 mm area

around the crack. Counting times were 10 sec per point, and a minimum of 3×10^5 counts were obtained at each point, well under one percent standard error in counting statistics. We note that these measurements were performed at London Hospital Medical College in collaboration with Dr. J.C. Elliott's group in the Dept. of Child Dental Health.

Figure 11 shows the two dimensional distribution of transmitted intensity around the creep crack. Note that absorption is reduced as far as 1 mm from the crack. The decrease in absorption could be due to preferential thinning near the crack, i.e. near the center of the sample, and this unlikely source of increased transmissivity is presently being checked by precision metrology. Conversion of the data into volume fraction of cavities will follow shortly.

2.4.2 Industrial Computed Tomography

Industrial computed tomography offers considerable promise for characterizing damage in samples with macroscopic dimensions-- as long as high spatial resolution (< 60 or $70\mu\text{m}$) is not required. The compact tension samples crept and fatigued as part of this study are a good example of where use of industrial CT would be very advantageous. Large, long-range gradients in cavitation damage have been observed around the crack (see Sections 2.1 and 2.2) in sample CT2 (tested at $1.5 \text{ ksi}(\text{in.})^{0.5}$ for 1250 hrs. and at $1.65 \text{ ksi}(\text{in.})^{0.5}$ for times greater than 1250 hrs.). We have not yet reproduced the slices from our imaging terminal.

The adjacent slices surrounding the nominal crack plane for sample CT2 were obtained in collaboration with Dr. R. Isaacs of General Electric Corporation and had 62.5 μm pixels and 0.25 mm slice thicknesses. In these first experiments, the entire sample cross-sectional area (approximately 0.6 in. x 1.5 in.) was studied. Considerable beam hardening is evident which precludes quantitative analysis of the data until it is corrected. This correction is currently underway using a wedge-shaped reference sample from undamaged Cu-1% Sb.

The series of slices viewed on our terminal shows that the crack wandered from a single plane and that the crack extension was greater in the middle of the sample than at its edges. The crack tip structure is clearly evident even without correcting for beam hardening. Progress thus far indicates that prospects are excellent for quantitative measurements of the density variation ahead of creep cracks.

2.4.3. X-ray Tomographic Microscopy

A preliminary XTM scan was run of a small, rectangular prism of material taken from a sample which failed under creep loading at 400C. The XTM experiments were performed at SSRL in collaboration with Dr. J.H. Kinney's group at Lawrence Livermore National Laboratory. The creep test was run at 8 ksi, and one end of the centimeter-long prism was from the exposed fracture surface. Approximately 90 slices were recorded using 35 keV x-rays, and every ninth slice from the fracture surface is shown in Fig. 12.

The minimum dimension of this sample was 0.4 mm. Figure 13 shows enlargements of two of the slices. A few small cavities are visible in the interior of one of the slices, and their diameters of 10-20 μm are consistent with those measured from other volumes of the same sample by conventional techniques. Unfortunately, there were significant penetration problems at 35 keV, and higher energies could not be available at SSRL. We intend to use the PEP ring at Stanford with higher x-ray energies to continue this investigation; we should be scheduled during the next PEP run. We have also approached CHESS (Cornell synchrotron) about obtaining time for these experiments. While the XTM sample clearly pushed the limits of what was then available, these results are very exciting: enough so that we will continue this aspect of the research even though the project has concluded.

3. LIST OF PAPERS PUBLISHED, CONFERENCE PRESENTATIONS AND STUDENTS SUPPORTED

In this Section, the published papers and the names of students and Research Associates who received support from the grant are listed.

3.1 Papers Published Acknowledging DOE Support

1. A. Saxena, "Creep Crack Growth Under Transient Conditions", Materials Science and Eng., vol. A(103), 1988, pp. 125-129.
2. A. Saxena and B. Gieseke, "Transients in Elevated Temperature Crack Growth", in High Temperature Fracture

Mechanisms and Mechanics, P. Bensussan Editor, Mech. Eng. Publication, 1990.

3. A. Saxena, "Mechanics and Mechanism of Creep Crack Growth", Invited Book Chapter in Fracture Mechanics: Microstructure and Mechanisms, S.V. Nair et. al. editors ASM International, 1989, pp. 283-334.
4. J.T. Staley, Jr. and A. Saxena, "Mechanisms of Creep Crack Growth in 1 wt-percent Antimony-Copper: Implications for Fracture Parameters", Acta Metallurgica, 1990 (in press).
5. B. Gieseke and A. Saxena, "Correlation of Creep-Fatigue Crack Growth Rates Using Crack Tip Parameters", Advances in Fracture Research, Proceedings of the Seventh International Conference on Fracture, Houston, March 1989, pp. 189-196.
6. A. Saxena, "Recent Advances in Elevated Temperature Crack Growth and Models for Life Prediction", (Keynote Paper), Proceedings of the Seventh International Conference on Fracture, Houston, March 1989, pp. 1675-1688.

3.2 Manuscripts in Preparation

1. S.R. Stock, A. Guvenilir, R. Norris, Y.H. Lee, J.T. Staley, Jr., Z.U. Rek and A. Saxena, "Development of Damage During Creep of Cu-1% Sb at 400 C", to be submitted to Acta Metallurgica.

2. B. Gieseke and A. Saxena, "Mechanisms of Crack Growth in Cu-1% Sb During Hold Time Fatigue", to be submitted to Acta Metallurgica.
3. R.H. Norris and A. Saxena, "A Transients and the Resulting Conditions During Elevated Temperature Crack Growth in an Antimony-Copper Alloy," ASTM STP from the ASTM 22nd. National Symposium on Fracture Mechanics.

3.3 Conference Presentations

1. A. Saxena, "Crack Growth at Elevated Temperature". ASME Applied Mechanics Meeting, June 15-16, 1987, Cincinnati, Ohio (invited).
2. A. Saxena, "Creep Crack Growth Under Transient Conditions", in DOE Workshop on Mechanics and Physics of Crack Growth and Application to Life Prediction", August 4-7, 1987, Keystone, Colorado (invited).
3. A. Saxena and S.D. Antolovich, "Mechanics and Mechanisms of Creep Crack Growth", ASM weekend seminar on Fracture Mechanics, Microstructure and Mechanisms, Oct. 9-10, 1987, Cincinnati, Ohio (invited).
4. A. Saxena and B. Gieseke, "Transients in Elevated Temperature Crack Growth", International Seminar on Mechanics and Mechanisms of High Temperature Fracture", Oct. 13-15, Dourdan, France (invited).
5. B. Gieseke and A. Saxena, "Mechanisms of Creep-Fatigue Crack Growth Interactions in 1wt % Sb-copper", TMS-AIME

Meeting, Phoenix Arizona, Jan. 26-28, 1988.

6. A. Saxena, "Crack Tip Parameters for Correlating Creep Crack Growth Data", (invited) VAMAS meeting, June 18-19, 1988, Freiburg, W. Germany.
7. B. Gieseke and A. Saxena, "Correlation of Creep-Fatigue Crack Growth Rates using Crack Tip Parameters", Seventh International Conference on Fracture, Houston, Texas, March 1989.
8. A. Saxena, "Recent Advances in Elevated Temperature Crack Growth and Models for Life Prediction", (Keynote paper), Seventh International Conference on Fracture, March 1989.

3.4 Students and Research Associates Acknowledging DOE Support

Students

1. James T. Staley, Jr. M.S. 1988, Rockedyne Division, Rockwell International, Canoga Park, CA.
2. Brian Gieseke, Ph.D March 1990, Metals and Ceramics Division, Oak Ridge National Laboratory Oak Ridge, TN.
3. Richard H. Norris, M.S. (expected June 1990 and to continue Ph.D. at Georgia Tech).
4. Abbas Guvenilir, Ph.D (expected December 1991)

Research Associates

1. Dr. K. Banerji (Jan 1987-Dec 1988) currently employed with Motorola Co., W. Palm Beach, Fla.

2. Dr. Y.H. Lee, Visiting Scientist from Korea Dec 86- Dec 87.
3. Dr. C.P. Leung (Jan 1989 - June 1989) currently employed at Southwest Research Institute, San Antonio, Texas.

4. REFERENCES

1. H. Riedel, Fracture at High Temperatures, Springer-Verlag, 1987.
2. A. Saxena, "Mechanics and Mechanism of Creep Crack Growth", in Fracture Mechanics: Microstructure and Micromechanisms, S.V. Nair et al. editors, ASM International, 1989, pp. 283-334.
3. J.T. Staley, Jr. and A. Saxena, "Mechanisms of Creep Crack Growth in 1 wt % Antimony-Copper: Implications for Fracture Parameters", Acta Metallurgica, 1990 (in press).
4. A. Saxena and B. Gieseke, "Transients in Elevated Temperature Crack Growth", in High Temperature Fracture Mechanisms and Mechanics, P. Bensussan Editor, Mech. Eng. Publications, 1990 (in press)
5. A. Saxena, S.R. Stock, J.T. Staley and B. Gieseke, "Mechanisms of Time-Dependent Crack Growth at Elevated Temperature," First Annual Project Report, DOE Project DE-FG05-86ER 45257, Feb 1987.

Fig. 1 (Top) Unconstrained cavitation at the tip of growing creep crack leading to extensive crack branching; (Bottom) the lack of correlation between da/dt versus C_1 when data from specimens which exhibited this behavior were included in the correlation (Staley and Saxena, 1989).

Fig. 2 (Top). Constrained cavitation damage at the tip of a growing creep crack in 1 wt percent antimony-copper; (bottom) the creep crack growth rate as a function of C_t in specimens which exhibited constrained cavitation (Staley and Saxena, 1989).

Fig. 3 - Fraction of grain boundary area cavitated as a function of distance from the crack tip for specimens CT-2 and CT-5.

Fig. 4 - Creep crack growth rate of 1 wt percent Sb - Copper in ultra-high purity N₂.

Fig. 5 - Volume fraction V_v of cavities as a function of distance from the rupture surface of samples of Cu - 1 wt. % Sb tested at 400 C. The measurements were made with optical microscopy on a polished section of each sample.

Fig. 6 - a. Fraction of grain boundary area A_c and b. Average cavity diameter D as functions of fraction of elapsed life-time t/t_f . The solid and open circles are for samples tested under 6.0 and 3.5 ksi loads, respectively.

Fig. 7 - The average da/dt during hold time as a function of the $(C_t)_{avg}$ parameter and comparison with creep crack growth rate for a one percent antimony-alloy at 400°C (Gieseke and Saxena, 1989).

Figure 8. Volume fraction of cavities as a function of distance from the fracture surface of specimens deformed in creep.

Figure 9. Area fraction A_c and average cavity diameter D for samples tested at 3.5 ksi (open circles) and 6 ksi (closed circles).

3C-2

LINE SLICE WIDTH = (0.50 MM) PSI = 90.00 DEGREES
I = 45. J = 81.

Figure 10. Densitometry trace showing gradient of damage in synchrotron microradiographs of sample 3C.

Figure 11. Two-dimensional distribution of transmitted intensity around a creep crack. The vertical axis is transmitted intensity.

Figure 13. Slices recorded with synchrotron XTM parallel to the rupture surface of a Cu- 1 wt. % Sb sample. The sample failed under creep, and the irregularities of the slices shown the jagged rupture surface. The small, dark images, indicated by arrows, appear to be grain boundary cavities.

END

DATE
FILMED

5 / 14 / 93