DOE/ER/45307-5

Department of Materials Science and Engineering
Massachusetts Institute of Technology
Cambridge, MA 02139

DOE/ER/45307--5

DE93 013986

May 1993

Technical Progress Report

GRAIN BOUNDARIES IN COMPLEX OXIDES

Grant No. DE-FG02-87ER45307

Submitted To:

Department of Energy
DOE Chicago Field Office
9800 South Cass Avenue
Argonne, Illinois 60439

Submitted By:

Principal Investigator

Name: Yet-Ming Chiang
Signature: *Ym Chiang*
Title: Associate Professor of Ceramics
Telephone: (617) 253-6471

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

MASTER

yes
RECEIVED

JUN 01 1993

OSTI

Abstract

This research program investigates the properties of grain boundaries in complex multicomponent or nonstoichiometric oxides, including those of interest for electroceramics applications. One area of current research is the relationship between complex lattice defect structures and the ionic space charge at grain boundaries. We focus on TiO_2 as a system with lattice defect properties characteristic of many electroceramics, including nonstoichiometry and regimes of high electronic conductivity. Model experiments are performed using a newly developed STEM method to quantify the grain boundary accumulation of trivalent (Al^{3+} , Ga^{3+}) and pentavalent (Nb^{5+}) cation dopants. A space charge model is developed which explicitly includes the lattice defect chemistry of TiO_2 . This work is aimed at making for the first time a detailed, quantitative comparison between space charge theory and grain boundary segregation. The fundamental defect formation energies at grain boundaries and their variation from boundary to boundary are studied. In future work, space charge effects at nanocrystalline grain sizes, and at bimaterial interfaces, emphasizing crystal-glass interfaces germane to the behavior of thin glassy films at grain boundaries, are to be studied.

A second area of research concerns the direct measurement of grain boundary thermodynamic properties and size-dependent segregation and transport phenomena in nanocrystalline oxides. Current efforts are aimed at using high temperature calorimetry to measure the heat of grain coarsening and excess heat capacity of nanocrystalline TiO_2 , in order to obtain the specific grain boundary enthalpy and entropy and their temperature and composition dependences. With appropriate models for the enthalpy release rate during grain coarsening, *in-situ* measurement of grain growth kinetic parameters (time exponent, activation energies) is possible. The effect of solute segregation on grain boundary thermodynamic and kinetic properties, and size-dependent segregation phenomena, including the effects of space charge fields on grain growth and superplastic deformation, are to be studied.

Major Recent Accomplishments

- 1) Achieved for the first time a detailed, quantitative comparison between space charge theory and segregation at grain boundaries, in the model system TiO_2 . Showed that the ionic space-charge in TiO_2 can be "titrated" from negative to positive potential as a function of composition and temperature. Developed a model for the space charge potential that explicitly includes the lattice defect chemistry. Experimentally separated the formation energies of individual defects in the Frenkel pair for TiO_2 . Showed that variations in electrostatic potential corresponding to differences in defect formation energy of as much as 1 eV exist between individual grain boundaries.
- 2) Developed a highly quantitative STEM method of general applicability for measuring interfacial segregation.
- 3) Synthesized by a chemical route nanocrystalline TiO_2 of equivalent or superior quality to the best physical-vapor-deposited materials available.
- 4) Performed the first direct measurement of grain boundary enthalpy in a ceramic material, using high temperature calorimetry during grain coarsening. Measured the excess heat capacity of nanocrystalline TiO_2 . Directly observed grain coarsening kinetics using high temperature calorimetry.
- 5) Showed conclusively that it is the barium vacancy that forms near surfaces in donor-doped BaTiO_3 electroceramics during oxidative-cooling processing cycles. Obtained support for the existence of metastable defect equilibria in multicomponent ceramics.

3.0 List of Publications Under This Grant During 1990-92:

1. J.A.S. Ikeda and Y.-M. Chiang, *Space Charge Segregation at Grain Boundaries in Titanium Dioxide: I., Relationship Between Lattice Defect Chemistry and Space Charge Potential*, submitted to J. Am. Ceram. Soc., November 1992.
2. J.A.S. Ikeda and Y.-M. Chiang, *Space Charge Segregation at Grain Boundaries in Titanium Dioxide: II., Model Experiments*, submitted to J. Am. Ceram. Soc., November 1992.
3. C.D. Terwilliger and Y.-M. Chiang, "Characterization of Chemically- and Physically-Derived Nanophase Titanium Dioxide," submitted to Nanostructured Materials, October 1992.

4. Y.-M. Chiang, I.P. Smyth, C.D. Terwilliger, W.T. Petuskey and J.A. Eastman, *Measurements of Grain Boundary Properties in Nanocrystalline Ceramics, Nanostructured Materials*, 1[3], 235-240 (1992).
5. Y.-M. Chiang and T. Takagi, "Comment on 'Interfacial Segregation in Perovskites: I-IV'," *J. Am. Ceram. Soc.*, 75[7] (1992).
6. J.A.S. Ikeda, Y.-M. Chiang, and A.J. Garratt-Reed, "Quantification of Grain Boundary Segregation in TiO_2 by STEM," Proc. 50th Annual Meeting of the Electron Microscopy Society of America, edited by G.W. Bailey, J. Bentley, and J.A. Small, San Francisco Press, Inc., San Francisco, 1992.
7. J.A.S. Ikeda, Y.-M. Chiang, and A.J. Garratt-Reed, "Quantification of Grain Boundary Segregation in TiO_2 by STEM," Proc. XIII International Congress on X-ray Optics and Microanalysis, Manchester, U.K., August 31-September 4, 1992.
8. J.A.S. Ikeda and Y.-M. Chiang, *Grain Boundary Electrostatic Potential as a Function of Acceptor and Donor Doping in TiO_2* , in Point Defects and Related Properties of Ceramics, *Ceramic Transactions Vol. 24*, edited by T.O. Mason and J.L. Routbort, The American Ceramic Society, Westerville, Ohio, 1991.
9. C.D. Terwilliger, Y.-M. Chiang, J.A. Eastman and Y. Liao, *Determination of Thermodynamic and Kinetic Properties of Grain Boundaries using High Temperature Calorimetry*, in Point Defects and Related Properties of Ceramics, *Ceramic Transactions Vol. 24*, edited by T.O. Mason and J.L. Routbort, The American Ceramic Society, Westerville, Ohio, 1991.
10. J.A.S. Ikeda, Y.-M. Chiang and B.D. Fabes, *Non-Equilibrium Surface Segregation in Al-Doped TiO_2 under an Oxidizing Potential: Effects on Redox Color-Boundary Migration*, *J. Am. Ceram. Soc.*, 73[6], 1633-40 (1990).
11. Y.-M. Chiang and T. Takagi, *Grain Boundary Chemistry of Barium Titanate and Strontium Titanate: I, High Temperature Equilibrium Space Charge*, *J. Am. Ceram. Soc.*, 73[11], 3278-85 (1990).
12. Y.-M. Chiang and T. Takagi, *Grain Boundary Chemistry of Barium Titanate and Strontium Titanate: II, Origin of Electrical Barriers in Positive-Temperature-Coefficient Thermistors*, *J. Am. Ceram. Soc.*, 73[11], 3286-91 (1990).
13. C.J. Peng and Y.-M. Chiang, *Grain Growth in Donor-Doped Strontium Titanate*, *J. Mat. Res.*, 5[6], 1237-45 (1990).
14. G.M. Dynna and Y.-M. Chiang, *Mechanisms of Grain Growth Enhancement and Inhibition in Donor Doped Barium Titanate*, pp. 547-61 in *Sintering of Advanced Ceramics*, Vol. 7, *Ceramic Transactions*, edited by C.A. Handwerker, J. Blendell, W. Kaysser, The American Ceramic Society, Westerville, Ohio, 1990.

Department of Materials Science and Engineering
Massachusetts Institute of Technology
Cambridge, MA 02139

May 1993

Technical Progress Report

GRAIN BOUNDARIES IN COMPLEX OXIDES

Grant No. DE-FG02-87ER45307

Submitted To:

Department of Energy
DOE Chicago Field Office
9800 South Cass Avenue
Argonne, Illinois 60439

Submitted By:

Principal Investigator

Name: Yet-Ming Chiang
Signature:
Title: Associate Professor of Ceramics
Telephone: (617) 253-6471

Major Recent Accomplishments

- 1) Achieved for the first time a detailed, quantitative comparison between space charge theory and segregation at grain boundaries, in the model system TiO_2 . Showed that the ionic space-charge in TiO_2 can be "titrated" from negative to positive potential as a function of composition and temperature. Developed a model for the space charge potential that explicitly includes the lattice defect chemistry. Experimentally separated the formation energies of individual defects in the Frenkel pair for TiO_2 . Showed that variations in electrostatic potential corresponding to differences in defect formation energy of as much as 1 eV exist between individual grain boundaries.
- 2) Developed a highly quantitative STEM method of general applicability for measuring interfacial segregation.
- 3) Synthesized by a chemical route nanocrystalline TiO_2 of equivalent or superior quality to the best physical-vapor-deposited materials available.
- 4) Performed the first direct measurement of grain boundary enthalpy in a ceramic material, using high temperature calorimetry during grain coarsening. Measured the excess heat capacity of nanocrystalline TiO_2 . Directly observed grain coarsening kinetics using high temperature calorimetry.
- 5) Showed conclusively that it is the barium vacancy that forms near surfaces in donor-doped BaTiO_3 electroceramics during oxidative-cooling processing cycles. Obtained support for the existence of metastable defect equilibria in multicomponent ceramics.

3.0 List of Publications Under This Grant During 1990-92:

1. J.A.S. Ikeda and Y.-M. Chiang, *Space Charge Segregation at Grain Boundaries in Titanium Dioxide: I., Relationship Between Lattice Defect Chemistry and Space Charge Potential*, submitted to J. Am. Ceram. Soc., November 1992.
2. J.A.S. Ikeda and Y.-M. Chiang, *Space Charge Segregation at Grain Boundaries in Titanium Dioxide: II., Model Experiments*, submitted to J. Am. Ceram. Soc., November 1992.
3. C.D. Terwilliger and Y.-M. Chiang, "Characterization of Chemically- and Physically-Derived Nanophase Titanium Dioxide," submitted to Nanostructured Materials, October 1992.

4. Y.-M. Chiang, I.P. Smyth, C.D. Terwilliger, W.T. Petuskey and J.A. Eastman, *Measurements of Grain Boundary Properties in Nanocrystalline Ceramics, Nanostructured Materials*, 1[3], 235-240 (1992).
5. Y.-M. Chiang and T. Takagi, "Comment on 'Interfacial Segregation in Perovskites: I-IV'," *J. Am. Ceram. Soc.*, 75[7] (1992).
6. J.A.S. Ikeda, Y.-M. Chiang, and A.J. Garratt-Reed, "Quantification of Grain Boundary Segregation in TiO_2 by STEM," Proc. 50th Annual Meeting of the Electron Microscopy Society of America, edited by G.W. Bailey, J. Bentley, and J.A. Small, San Francisco Press, Inc., San Francisco, 1992.
7. J.A.S. Ikeda, Y.-M. Chiang, and A.J. Garratt-Reed, "Quantification of Grain Boundary Segregation in TiO_2 by STEM," Proc. XIII International Congress on X-ray Optics and Microanalysis, Manchester, U.K., August 31-September 4, 1992.
8. J.A.S. Ikeda and Y.-M. Chiang, *Grain Boundary Electrostatic Potential as a Function of Acceptor and Donor Doping in TiO_2* , in Point Defects and Related Properties of Ceramics, *Ceramic Transactions Vol. 24*, edited by T.O. Mason and J.L. Routbort, The American Ceramic Society, Westerville, Ohio, 1991.
9. C.D. Terwilliger, Y.-M. Chiang, J.A. Eastman and Y. Liao, *Determination of Thermodynamic and Kinetic Properties of Grain Boundaries using High Temperature Calorimetry*, in Point Defects and Related Properties of Ceramics, *Ceramic Transactions Vol. 24*, edited by T.O. Mason and J.L. Routbort, The American Ceramic Society, Westerville, Ohio, 1991.
10. J.A.S. Ikeda, Y.-M. Chiang and B.D. Fabes, *Non-Equilibrium Surface Segregation in Al-Doped TiO_2 under an Oxidizing Potential: Effects on Redox Color-Boundary Migration*, *J. Am. Ceram. Soc.*, 73[6], 1633-40 (1990).
11. Y.-M. Chiang and T. Takagi, *Grain Boundary Chemistry of Barium Titanate and Strontium Titanate: I, High Temperature Equilibrium Space Charge*, *J. Am. Ceram. Soc.*, 73[11], 3278-85 (1990).
12. Y.-M. Chiang and T. Takagi, *Grain Boundary Chemistry of Barium Titanate and Strontium Titanate: II, Origin of Electrical Barriers in Positive-Temperature-Coefficient Thermistors*, *J. Am. Ceram. Soc.*, 73[11], 3286-91 (1990).
13. C.J. Peng and Y.-M. Chiang, *Grain Growth in Donor-Doped Strontium Titanate*, *J. Mat. Res.*, 5[6], 1237-45 (1990).
14. G.M. Dynna and Y.-M. Chiang, *Mechanisms of Grain Growth Enhancement and Inhibition in Donor Doped Barium Titanate*, pp. 547-61 in *Sintering of Advanced Ceramics*, Vol. 7, *Ceramic Transactions*, edited by C.A. Handwerker, J. Blendell, W. Kaysser, The American Ceramic Society, Westerville, Ohio, 1990.

Department of Materials Science and Engineering
Massachusetts Institute of Technology
Cambridge, MA 02139

May 1993

Technical Progress Report

GRAIN BOUNDARIES IN COMPLEX OXIDES

Grant No. DE-FG02-87ER45307

Submitted To:

Department of Energy
DOE Chicago Field Office
9800 South Cass Avenue
Argonne, Illinois 60439

Submitted By:

Principal Investigator

Name: Yet-Ming Chiang

Signature:

Title:

Telephone:

Associate Professor of Ceramics
(617) 253-6471

Abstract

This research program investigates the properties of grain boundaries in complex multicomponent or nonstoichiometric oxides, including those of interest for electroceramics applications. One area of current research is the relationship between complex lattice defect structures and the ionic space charge at grain boundaries. We focus on TiO_2 as a system with lattice defect properties characteristic of many electroceramics, including nonstoichiometry and regimes of high electronic conductivity. Model experiments are performed using a newly developed STEM method to quantify the grain boundary accumulation of trivalent (Al^{3+} , Ga^{3+}) and pentavalent (Nb^{5+}) cation dopants. A space charge model is developed which explicitly includes the lattice defect chemistry of TiO_2 . This work is aimed at making for the first time a detailed, quantitative comparison between space charge theory and grain boundary segregation. The fundamental defect formation energies at grain boundaries and their variation from boundary to boundary are studied. In future work, space charge effects at nanocrystalline grain sizes, and at bimaterial interfaces, emphasizing crystal-glass interfaces germane to the behavior of thin glassy films at grain boundaries, are to be studied.

A second area of research concerns the direct measurement of grain boundary thermodynamic properties and size-dependent segregation and transport phenomena in nanocrystalline oxides. Current efforts are aimed at using high temperature calorimetry to measure the heat of grain coarsening and excess heat capacity of nanocrystalline TiO_2 , in order to obtain the specific grain boundary enthalpy and entropy and their temperature and composition dependences. With appropriate models for the enthalpy release rate during grain coarsening, *in-situ* measurement of grain growth kinetic parameters (time exponent, activation energies) is possible. The effect of solute segregation on grain boundary thermodynamic and kinetic properties, and size-dependent segregation phenomena, including the effects of space charge fields on grain growth and superplastic deformation, are to be studied.

Major Recent Accomplishments

- 1) Achieved for the first time a detailed, quantitative comparison between space charge theory and segregation at grain boundaries, in the model system TiO_2 . Showed that the ionic space-charge in TiO_2 can be "titrated" from negative to positive potential as a function of composition and temperature. Developed a model for the space charge potential that explicitly includes the lattice defect chemistry. Experimentally separated the formation energies of individual defects in the Frenkel pair for TiO_2 . Showed that variations in electrostatic potential corresponding to differences in defect formation energy of as much as 1 eV exist between individual grain boundaries.
- 2) Developed a highly quantitative STEM method of general applicability for measuring interfacial segregation.
- 3) Synthesized by a chemical route nanocrystalline TiO_2 of equivalent or superior quality to the best physical-vapor-deposited materials available.
- 4) Performed the first direct measurement of grain boundary enthalpy in a ceramic material, using high temperature calorimetry during grain coarsening. Measured the excess heat capacity of nanocrystalline TiO_2 . Directly observed grain coarsening kinetics using high temperature calorimetry.
- 5) Showed conclusively that it is the barium vacancy that forms near surfaces in donor-doped BaTiO_3 electroceramics during oxidative-cooling processing cycles. Obtained support for the existence of metastable defect equilibria in multicomponent ceramics.

3.0 List of Publications Under This Grant During 1990-92:

1. J.A.S. Ikeda and Y.-M. Chiang, *Space Charge Segregation at Grain Boundaries in Titanium Dioxide: I., Relationship Between Lattice Defect Chemistry and Space Charge Potential*, submitted to J. Am. Ceram. Soc., November 1992.
2. J.A.S. Ikeda and Y.-M. Chiang, *Space Charge Segregation at Grain Boundaries in Titanium Dioxide: II., Model Experiments*, submitted to J. Am. Ceram. Soc., November 1992.
3. C.D. Terwilliger and Y.-M. Chiang, "Characterization of Chemically- and Physically-Derived Nanophase Titanium Dioxide," submitted to Nanostructured Materials, October 1992.

4. Y.-M. Chiang, I.P. Smyth, C.D. Terwilliger, W.T. Petuskey and J.A. Eastman, *Measurements of Grain Boundary Properties in Nanocrystalline Ceramics, Nanostructured Materials*, 1[3], 235-240 (1992).
5. Y.-M. Chiang and T. Takagi, "Comment on 'Interfacial Segregation in Perovskites: I-IV'," *J. Am. Ceram. Soc.*, 75[7] (1992).
6. J.A.S. Ikeda, Y.-M. Chiang, and A.J. Garratt-Reed, "Quantification of Grain Boundary Segregation in TiO_2 by STEM," Proc. 50th Annual Meeting of the Electron Microscopy Society of America, edited by G.W. Bailey, J. Bentley, and J.A. Small, San Francisco Press, Inc., San Francisco, 1992.
7. J.A.S. Ikeda, Y.-M. Chiang, and A.J. Garratt-Reed, ""Quantification of Grain Boundary Segregation in TiO_2 by STEM," Proc. XIII International Congress on X-ray Optics and Microanalysis, Manchester, U.K., August 31-September 4, 1992.
8. J.A.S. Ikeda and Y.-M. Chiang, *Grain Boundary Electrostatic Potential as a Function of Acceptor and Donor Doping in TiO_2* , in Point Defects and Related Properties of Ceramics, *Ceramic Transactions Vol. 24*, edited by T.O. Mason and J.L. Routbort, The American Ceramic Society, Westerville, Ohio, 1991.
9. C.D. Terwilliger, Y.-M. Chiang, J.A. Eastman and Y. Liao, *Determination of Thermodynamic and Kinetic Properties of Grain Boundaries using High Temperature Calorimetry*, in Point Defects and Related Properties of Ceramics, *Ceramic Transactions Vol. 24*, edited by T.O. Mason and J.L. Routbort, The American Ceramic Society, Westerville, Ohio, 1991.
10. J.A.S. Ikeda, Y.-M. Chiang and B.D. Fabes, *Non-Equilibrium Surface Segregation in Al-Doped TiO_2 under an Oxidizing Potential: Effects on Redox Color-Boundary Migration*, *J. Am. Ceram. Soc.*, 73[6], 1633-40 (1990).
11. Y.-M. Chiang and T. Takagi, *Grain Boundary Chemistry of Barium Titanate and Strontium Titanate: I, High Temperature Equilibrium Space Charge*, *J. Am. Ceram. Soc.*, 73[11], 3278-85 (1990).
12. Y.-M. Chiang and T. Takagi, *Grain Boundary Chemistry of Barium Titanate and Strontium Titanate: II, Origin of Electrical Barriers in Positive-Temperature-Coefficient Thermistors*, *J. Am. Ceram. Soc.*, 73[11], 3286-91 (1990).
13. C.J. Peng and Y.-M. Chiang, *Grain Growth in Donor-Doped Strontium Titanate*, *J. Mat. Res.*, 5[6], 1237-45 (1990).
14. G.M. Dynna and Y.-M. Chiang, *Mechanisms of Grain Growth Enhancement and Inhibition in Donor Doped Barium Titanate*, pp. 547-61 in *Sintering of Advanced Ceramics*, Vol. 7, *Ceramic Transactions*, edited by C.A. Handwerker, J. Blendell, W. Kaysser, The American Ceramic Society, Westerville, Ohio, 1990.

END

**DATE
FILMED**

6 / 11 / 93